Understanding the Unique Structural and Electronic Properties of SrFeO_2

J.M. Pruneda,¹ Jorge $\tilde{\text{Iniguez}}$,¹ Enric Canadell,¹ Hiroshi Kageyama,² and Mikio Takano³

¹Institut de Ciència de Materials de Barcelona (ICMAB-CSIC), Campus UAB, 08193 Bellaterra, Spain

3 Institute for Chemical Research, Kyoto University, Uji, Kyoto 611-0011, Japan

We report a first-principles study of $SrFeO₂$, an infinite-layer oxide with Fe atoms in a perfect square-planar coordination down to essentially 0 K. Our results reveal this striking behavior relies on the double occupation of the $3d_{z2}$ orbitals of high-spin Fe^{2+} . Such an electronic state results from the hybridization of iron's $3d_{z^2}$ and 4s orbitals, which enables a large reduction of the intra-atomic exchange splitting of the z^2 electrons. The generality of the phenomenon is discussed.

Tsujimoto *et al.* [\[1\]](#page-3-0) have recently reported on $SrFeO₂$, a novel material that exhibits a wealth of surprising properties. Most interestingly, $SrFeO₂$ presents $Fe²⁺$ ions in a square-planar coordination, forming unprecedented infinite $FeO₂$ layers that remain undistorted down to at least 4.2 K (see Fig. [1\)](#page-0-0). In addition, it undergoes a transition to an anti-ferromagnetic (AFM) state at $T_N=473$ K, a surprisingly high temperature given the seemingly twodimensional nature of the compound. The physical origin of these features, which also appear in similar compounds studied more recently [\[2](#page-3-1)], remains unknown. Here we report a first-principles study, based on the "LDA+U" approach to Density Functional Theory (DFT), that confirms the peculiar behavior of $SrFeO₂$ and reveals its electronic origin.

Basic properties.– We begin by showing that our DFT methods, described in [\[3](#page-3-2)], reproduce the main results reported in Ref. [1.](#page-3-0) To investigate the stability of the highly-symmetric phase of $SrFeO₂$, we first determined the structural parameters that minimize the energy of the crystal under the constraints that the P4/mmm space group is preserved and the magnetic order is the AFM one found experimentally. Our results, shown in Table [I,](#page-0-1) are in good agreement with the measurements. We then computed the elastic constants and the phonons that are compatible with the cell of Fig. [1.](#page-0-0) The results, summarized in Table [I,](#page-0-1) indicate that the P4/mmm phase of $SrFeO₂$ is stable upon symmetry-lowering structural distortions, thus confirming it as the ground state of the material at 0 K. It is worth noting that, while obviously anisotropic, the computed elastic constants and phonon frequencies present values that are acceptable for a three-dimensional (3D) crystal (for $\rm SrFeO_3$ we obtained $C_{11}=300$ GPa and $C_{12}=140$ GPa), which suggests this novel infinite-layer phase is robustly (meta-)stable.

We then studied the magnetic interactions in $SrFeO₂$. We considered all the spin arrangements compatible with the cell in Fig. [1,](#page-0-0) and confirmed that the experimentally observed AFM pattern (sketched in the figure) is the magnetic ground state. Further, the Fe^{2+} ions are in a high-spin configuration with a magnetic moment of about 3.6 μ _B, in agreement with experiment. We also

FIG. 1: (color online) 16-atom S rFeO₂ cell considered in most of our calculations. The ground-state magnetic structure is sketched; the lattice and exchange constants are defined.

TABLE I: Computed properties of the P4/mmm phase of SrFeO² (measured lattice parameters in parenthesis).

Structure: $a= b=4.01$ Å (3.99 Å); $c=3.42$ Å (3.47 Å) Elastic constants (GPa): $B=125, C_{11}=C_{22}=317, C_{33}=164, C_{12}=78,$ $C_{13}=C_{23}=51, C_{44}=C_{55}=95, C_{66}=125$ Infra-red active modes (cm^{-1}) : 159 and 276 (A_{2u}) ; 183, 301, and 531 (E_u) Magnetic couplings (meV): $J_1=1.75$, $J_2=6.58$, $J_3=-0.26$

computed the exchange parameters of a model Hamiltonian $H = 1/2 \sum_{ij} J_{ij} S_i S_j$, with $|S|=2$; the results are given in Table [I,](#page-0-1) following the notation defined in Fig. [1.](#page-0-0) We found that the in-plane interactions are considerably stronger than those along the c direction; yet, the material is far from being two-dimensional from the magnetic point of view. Indeed, a simple (admittedly rough) mean field estimate based on our computed J 's renders a Néel temperature above 1000 K, and the energy scale for the magnetic couplings between $FeO₂$ planes, which we can estimate as $S^2(2J_1 - 8J_3)$, is found to be around 260 K.

²Department of Chemistry, Graduate School of Science,

Kyoto University, Sakyo, Kyoto 606-8502, Japan and

Thus, our results confirm the three-dimensional character of magnetism in $SrFeO₂$, and are compatible with the relatively high T_N observed. We checked that values of the U parameter within the 3–6 eV range, which is typical for Fe compounds, do not affect this conclusion.

Electronic structure.– Based on their $57Fe$ Mössbauer spectroscopy results showing a temperature-independent quadrupole splitting of about 1 mm/s, and in accordance with the usual picture from crystal-field theory, the au-thors of Ref. [1](#page-3-0) assumed the $(xz,yz)^3(xy)^1(z^2)^1(x^2-y^2)^1$ electronic configuration for the 3d electrons of Fe^{2+} . However, in such conditions a Jahn-Teller distortion is expected to lift the degeneracy associated to the (xz,yz) orbitals, at odds with the experimental results. Our calculations readily clarify this question. As shown in Fig. [2,](#page-1-0) the DFT electronic structure of $SrFeO₂$ does not agree with the one proposed in Ref. [\[1\]](#page-3-0). We found that the sixth 3d electron of high-spin Fe^{2+} goes to the z^2 minority-spin orbital. At variance with the (xz,yz) 3d orbitals of Fe, the $z²$ state is not degenerate with any other and, thus, its occupancy cannot cause any symmetry-lowering distortion that reduces the energy. Hence, this electronic configuration is compatible with the stability of the P4/mmm phase. Further, we also checked the calculation results are compatible with the Mössbauer data. We address this point below, after having discussed the electronic structure of $SrFeO₂$ in more detail.

Discussion.– Our DFT calculations provide us with a coherent picture of $SrFeO₂$, accounting for the structural and magnetic properties of the material. Yet, that picture relies on a result, the double occupation of the z^2 orbitals of Fe^{2+} , which may seem counterintuitive based on the common knowledge in molecular and solid-state chemistry. We will thus focus on this key issue: Why are the z^2 orbitals of Fe²⁺ doubly occupied in SrFeO₂?

Let us start with a word of caution: Many apparently satisfying answers to the above question do not resist a rigorous analysis. For example, it may be tempting to postulate that the double occupation of the z^2 orbitals is determined by the fact that, as compared with the other 3d's, they suffer from negligible Coulomb repulsion because they find no O^{2-} ions along the direction perpendicular to the $FeO₂$ plane. This kind of argument has been invoked in several occasions [\[8,](#page-3-3) [9](#page-3-4)] and is supported by extended Hückel calculations we have performed. However, it is severely flawed: It implies that the $z²$ orbitals should be the lowest-lying ones for both the majority- and minority-spin electrons of high-spin $Fe²⁺$, which is in evident disagreement with the results in Fig. [2.](#page-1-0) Ultimately, the failure of this argument suggests that an independent-electron picture is not adequate to explain the electronic structure of $SrFeO₂$.

To address the above question, we proceeded by eliminating possibilities in a systematic way. Our key observations are the following. As already discussed, our calculations show $SrFeO₂$ should be regarded as a 3D

FIG. 2: (color online) Panel (a): Computed electronic structure of $SrFeO₂$ around the Fermi energy, which is set to 0 eV . The partial Density of States (pDOS) corresponding to the 3d and 4s orbitals of a particular Fe atom is indicated. The dashed line depicts the total DOS divided by a factor of four. Panels (b) and (c): Representative Γ-point eigenstates with dominating z^2 character, indicated with arrows in the band structure of panel (a). The plotted isosurfaces correspond to the indicated values of the squared modulus of the wave function.

crystal, and one can thus conjecture that interactions along the c direction, particularly between neighboring Fe atoms, might play a role in stabilizing the doublyoccupied z^2 orbital. In order to investigate this possibility, we considered the limit case in which such interactions are totally suppressed. More precisely, we studied an idealized system composed of an isolated $FeO₂$ layer, fixing the number of electrons in the calculation so as to keep the Fe and O atoms in the ionization states they have in $SrFeO₂$. We denote this virtual 2D crystal as "Fe²⁺(O^{2−})₂ + bg", where "bg" refers to the homogeneous charge-compensating background introduced to stabilize the material. Interestingly, the partial Density of States (pDOS) obtained for "Fe²⁺(O^{2-})₂ + bg" is essentially identical to the result for $SrFeO₂$ in Fig. [2,](#page-1-0) indicating that out-of-plane interactions play no role in determining the electronic structure of $SrFeO₂$. Recognizing that the significance of the results with a charge background may be questionable, we also run calculations for $SrFeO₂$ with a significantly increased c lattice constant and ratified this conclusion.

Next, we turned our attention to the interactions within the $FeO₂$ planes. We ran calculations for slightly increased and decreased values of the $a=b$ lattice constants, and found that the most significant changes in the electronic structure pertain to the $x^2 - y^2$ electrons of iron. This is not surprising, as these are the electrons forming σ bonds with the oxygen atoms. In what regards the z^2 electrons, we observed no effect worth noting, which clearly indicates that the Fe–O interactions are not the key to understand the double occupation of the z^2 orbitals. In particular, these results rule out the possibility that π -donor interactions with the oxo ligands, which would destabilize the xz and yz orbitals, are at the origin of the double occupation of z^2 . These conclusions are ratified by a standard Fe–O overlap population analysis. We also checked that the electronic structure of $SrFeO₂$ is essentially independent of the spin arrangement, and we can thus neglect inter-atomic exchange effects in this discussion.

We are thus led to conclude the double occupation of the z^2 orbitals must be determined by some sort of intraatomic mechanism associated to the iron atoms. Indeed, this is the correct perspective to understand the electronic structure of $SrFeO₂$. Let us note a well-known effect that appears to be critically important in this compound: As a result of the tetragonal point symmetry at the Fe site, the z^2 orbital is fully symmetric and can hybridize with the formally-empty Fe-4s state. In fact, the pDOS of Fig. [2](#page-1-0) clearly shows such a hybridization occurs, being particularly important for the majority spin. As illustrated in panels (b) and (c) of Fig. [2,](#page-1-0) the majorityspin wave functions with a significant $4s-3d_{z^2}$ mixing are characterized by (i) a shrinking of the z^2 -like central ring, and (ii) a deformation, and greater relative weight, of the lobes extending out-of-plane. In contrast, the minority-spin electrons display a nearly pure z^2 character. Note also that the very different structure of the z ² pDOS for the majority (roughly, triple-peaked) and minority (single-peaked) spins is consistent with this different mixing with the 4s orbitals. Of course, this peculiar behaviour reflects a mechanism by which the crystal minimizes its energy: Having different spin-up and spin-down z^2 -like electrons results in a reduction of their Coulomb repulsion and, accordingly, of the corresponding intra-atomic exchange spliting Δ . Indeed, the relatively small Δ associated to the z^2 electrons is obvious from Fig. [2.](#page-1-0) For a given orbital type, Δ can be estimated as

FIG. 3: (color online) Computed energy of various electronic solutions of the "Fe²⁺(O^{2−})₃ + bg" virtual system (see text) as a function of the distance $d_{\text{FeO'}}$ between the central Fe atom and the apical oxygens O'.

the difference between the centers of mass of the spin-up and spin-down bands; our calculations indicate that Δ is about 2.9 eV for the z^2 orbitals, while the other $3d$'s present Δ 's of more than 6 eV.

We have thus identified the mechanism that allows $SrFeO₂$ to reduce its energy by adopting an electronic configuration with doubly-occupied z^2 orbitals. Interestingly, for this mechanism to be active we only need to have the appropriate local symmetry at the Fe site, which implies that the newly discovered effect might be quite general. To check this, we performed the following computational experiment: We considered the 3D crystal "Fe²⁺(O^{2-})₃ + bg" sketched in Fig. [3,](#page-2-0) fixing the number of electrons in order to retain the Fe- $3d^6$ configuration. For simplicity, we assumed a ferromagnetic order, which we checked has no effect on the electronic configuration of Fe. We fixed the in-plane lattice constant at the SrFeO_2 value, and monitored the evolution of different electronic solutions [\[10\]](#page-3-5) as the cubic crystal $(d_{FeO'}=2 \text{ Å})$ undergoes a tetragonal distortion. As shown in Fig. [3,](#page-2-0) only one electronic solution is found in the cubic case: the minority-spin 3d electron occupies a combination of t_{2g} orbitals (from which the xy orbital is selected as soon as the tetragonal distortion occurs), closing the gap of the crystal. In contrast, for the largest values of $d_{FeO'}$ considered, several solutions occur, the ground state corresponding to doubly-occupied z^2 orbitals. Interestingly, the solution with doubly-occupied z^2 already exists at $d_{\text{FeO}} = 2.14$ Å; yet, the "xy-to- z^{2} " crossover only occurs at $d_{FeO'}=2.50$ Å. These results show a mere symmetry breaking will not cause the double occupation of the z^2 orbitals; rather, a relatively large tetragonal distortion, which results in both a more anisotropic environment for the Fe atom and a reduction of the Coulomb repulsion for the z^2 orbitals, is required. Finally, we also checked

that changes in the in-plane lattice constant have a minor effect in the xy -to- z^2 crossover.

It is not easy to estimate the universality of this mechanism for the double occupation of the z^2 orbitals. It may seem surprising, for example, that such an electronic solution is not found in molecules with Fe^{2+} centers. However, after reviewing the literature for some well-known cases [\[11](#page-3-6)], we have the impression that the electronic structure of iron is often conditioned by the nature of the ligands or by a reduced atomic symmetry that precedes any electronic effect associated to the metal atom itself. This suggests such systems may not be appropriate to look for effects like the one discussed here. As for crystalline materials, we only know of one candidate to present this kind of effect: the mineral gillespite ($BaFeSi₄O₁₀$), which contains $Fe²⁺$ ions in a squareplanar coordination and displaying a high-spin configuration with doubly-occupied z^2 orbitals [\[8\]](#page-3-3). An appealing possibility, though, would be to synthesize other compounds of the $SrFeO₂$ family. Indeed, we found that crystals like $RbCoO₂$ and $YFeO₂$ would present a similar pattern of electronic levels with doubly-occupied z^2 orbitals. More precisely, our calculations predict $RbCoO₂$ displays a $Co-3d^6$ high-spin configuration with a doublyoccupied z^2 ; thus, this material might remain in the high-symmetry P4/mmm phase down to 0 K, exactly as $SrFeO₂$. On the other hand, YFeO₂ exhibits a Fe-3d⁷ high-spin configuration where, in addition to having a doubly-occupied z^2 , the last 3d electron goes to a (xz,yz) state that closes the band gap; hence, this crystal should undergo a Jahn-Teller distortion.

Finally, let us discuss the compatibility between the value of the quadrupole splitting (QS) obtained from ${}^{57}Fe$ Mössbauer spectroscopy, which is about 1 mm/s, and the double-occupation of the z^2 orbitals, which is expected to result in QS values of 2–3 mm/s. We should begin by noting that $SrFeO₂$ is not the only compound exhibiting this seemingly contradictory behaviour. Indeed, the Fe^{2+} atoms in the above mentioned gillespite have been reported to display QS values below 0.6 mm/s in the 80–650 K temperature range [\[12](#page-3-7)]. As for $SrFeO₂$, we computed the electric field gradient at the Fe site and the corresponding QS, obtaining a value of about 0.8 mm/s. We also checked that varying U between 0 and 6 eV renders QS results in the 0.6–0.9 mm/s range, the greater values corresponding to the smaller U 's. This clearly shows that having an electronic structure with doubly occupied z^2 orbitals is not incompatible with the relatively small QS values measured. As to the mechanism that causes such a reduction of the observed QS with respect to its expected value, two possibilities can be mentioned: (i) that the lattice contribution to the QS is comparable to the one coming from the 3d electrons of iron [\[12\]](#page-3-7), which would lead to a cancelation as their signs are known to be opposite, or (ii) that the splittings associated to iron's 3d electrons are unusual in SrFeO2. Interestingly, our results seem to support the latter possibility: The spread in energy of the majorityspin z^2 and $x^2 - y^2$ electrons (see Fig. [2a](#page-1-0)) will imply a relatively large spacial spread of the corresponding Wannier functions [\[13\]](#page-3-8), which might result in unusually small quadrupole splittings. However, a detailed analysis of this issue is not trivial and goes beyond the scope of this paper.

Summary.– We have used first-principles methods to show that $SrFeO₂$, an unusual high-spin $Fe²⁺$ layered phase recently reported, is free from structural instabilities and exhibits strong magnetic interactions. We find that the hybridization of iron's $3d_{z^2}$ and 4s orbitals, which results in a large reduction of the intra-atomic exchange splitting associated to the z^2 electrons, is the key feature to understand the structural stability of the material.

We acknowledge discussions with E. Molins. Work funded by the Catalan (SGR2005-683) and Spanish (FIS2006-12117-C04-01, CSD2007-00041) Governments, CSIC (PIE-200760I015), and the Marie Curie program.

- [1] Y. Tsujimoto et al., Nature 450, 1062 (2007).
- [2] C. Tassel et al., J. Am. Chem. Soc. (in press).
- [3] Methods: Generalized Gradient Approximation to DFT, as implemented in VASP within the PAW scheme [\[4\]](#page-3-9); "LDA+U" correction $[5]$ for Fe-3d electrons, with $U=4$ eV ($U=0$ renders qualitatively similar results); valence and semi-core electrons considered; plane-wave cutoff: 400 eV. Most calculations with 16-atom cell in Fig. [1;](#page-0-0) $4\times4\times4$ k-point grid. We also used PWscf [\[6\]](#page-3-11) (analysis) and ABINIT [\[7](#page-3-12)] (electric field gradient calculations).
- [4] J.P. Perdew, K. Burke, and M. Ernzerhof, Phys. Rev. Lett. 77, 3865 (1996); G. Kresse and J. Furthmuller, Phys. Rev. B 54, 11169 (1996); P. E. Blochl, Phys. Rev. B 50, 17953 (1994); G. Kresse and D. Joubert, Phys. Rev. B 59, 1758 (1999).
- [5] S.L. Dudarev et al., Phys. Rev. B **57**, 1505 (1998).
- [6] S. Baroni, A. Dal Corso, S. de Gironcoli, and P. Giannozzi, [http://www.pwscf.org/.](http://www.pwscf.org/)
- [7] X. Gonze et al., Comp. Mats. Sci. 25, 478 (2002); [http://www.abinit.org/.](http://www.abinit.org/)
- [8] R.G. Burns, M.G. Clark, and A.J. Stone, Inorg. Chem. 5, 1268 (1966).
- [9] H.J. Xiang, S.-H. Wei, and M.-H. Whangbo, [arXiv:0801.1137v](http://arxiv.org/abs/0801.1137)1.
- [10] Particular electronic solutions can be stabilized by considering specially favorable conditions (e.g., a large value of d_{FeO} for the doubly-occupied z^2). The wave functions thus obtained can be used as the starting point of additional calculations, so as to complete curves as in Fig. [3.](#page-2-0)
- [11] O. Kahn, Molecular Magnetism, VCH Publ. (New York, 1993).
- [12] M.G. Clark, G.M. Bancroft, and A.J. Stone, J. Chem. Phys. 47, 4250 (1967).
- [13] I. Souza, N. Marzari, and D. Vanderbilt, Phys. Rev. B 65, 035109 (2001).