### Relationship between the atomic pair distribution function and small angle scattering: implications for modeling of nanoparticles

Christopher L. Farrow

Department of Physics and Astronomy, Michigan State University, East Lansing, MI, 48824, USA

Simon J. L. Billinge

Department of Applied Physics and Applied Mathematics, Columbia University, New York, NY, 10027, USA sb2896@columbia.edu

#### Abstract

Here we show explicitly the relationship between the functions used in the atomic pair distribution function (PDF) method and those commonly used in small angle scattering (SAS) analyses. The origin of the sloping baseline,  $-4\pi r\rho_0$ , in PDFs of bulk materials is identified as originating from the SAS intensity that is neglected in PDF measurements. The non-linear baseline in nanoparticles has the same origin, and contains information about the shape and size of the nanoparticles.

### 1 Introduction

The atomic pair distribution function (PDF) analysis of x-ray and neutron powder diffraction is growing in popularity with the advent of nanoscience and nanotechnology. The technique is more than 70 years old [1, 2, 3] and was originally applied almost exclusively to the study of glass and amorphous structures [4, 5, 6, 7, 8]. However, the approach is proving powerful in solving structure on the nanoscale [9], where traditional crystallographic methods break down [10]. In particular, the study of the structure of discrete nanoparticles using the PDF method has recently become a focus [11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21]. The convergence of this new need with the availability of powerful sources of high energy synchrotron x-rays and spallation neutrons and fast computing is greatly expanding the power and applicability of the method.

The PDF, G(r), is defined both as a function of the real-space pair density,

 $\rho(r)$ , and the reciprocal space scattering, F(Q) = Q[S(Q) - 1], as follows:

$$G(r) = \frac{2}{\pi} \int_0^\infty F(Q) \sin Q r dQ \tag{1}$$

and

$$G(r) = 4\pi r(\rho(r) - \rho_0), \tag{2}$$

where  $\rho_0$  is the number density of the material [22, 23, 24, 25, 26, 27, 28, 29, 2, 30, 31, 32, 33, 34, 35, 3, 36, 37, 38, 39, 40]. Equation 2 in this form works well for bulk materials, but the negatively sloping baseline,  $-4\pi r\rho_0$ , is no longer valid when the PDF is calculated from finite-sized objects such as discrete nanoparticles [16]. Motivated by the need for a rigorous definition of the form of this baseline we rederive these equations here. We show the correct form of Eq. 2 in a number of cases of practical interest such as discrete nanoparticles and nanoparticle PDFs calculated from bulk models. The important distinction is provided by the small angle scattering (SAS) intensity and we explicitly relate the commonly used PDF functions with commonly used results from SAS. We also show that the widely used pair of definitions for the PDF above are actually incompatible with each other and that the definition Eq. 1 does not give rise to Eq. 2 but rather to R(r)/r, where R(r) is the radial distribution function. This work therefore resolves a long-standing ambiguity in the PDF literature.

Compared to the PDF of a bulk sample [41], the PDF of a nanoparticle is attenuated with increasing-r by a function that is related to the form of the nanoparticle [42]. For simple shapes, such as spheroids, spherical shells, rods and discs, this nanoparticle form factor can be computed analytically [43, 44, 45, 40 and integral equations exist for more complex shapes [46]. This lends itself to a simple nanoparticle modeling procedure where the nanoparticle PDF is calculated from the PDF of a bulk phase analogue by multiplying by the assumed nanoparticle form factor [42, 47, 20]. The approach is successful for extracting precise quantitative structural information about the crystalline core of nanoparticles, including defects and size-dependent bond-lengths [20], and this functionality has been incorporated in the latest version of the PDF modeling software PDFgui [48]. However, the method is not applicable when the nanoparticle structure has no bulk phase analogue. This is the case in general, for example in nanoparticles with surface modifications [12] and inhomogeneous compositions such as core-shell nanoparticles [49]. In these cases, models of discrete nanoparticles must be applied. As we discuss below, this results in an ambiguity about the precise form of the measured correlation function, and therefore how to calculate it. Currently, this is dealt with quite successfully in an ad hoc way, as for example in [16, 50, 51, 37]. This paper presents a rigorous definition of the form of the baseline in terms of the nanoparticle form factor.

In Section 2 we rederive the equations giving rise to the PDF to show the precise relationship between the measured correlation function in an x-ray or neutron total scattering experiment and the underlying model. In Section 3 we make explicit the link between the commonly used PDF and small angle scattering equations. This has implications for calculating PDFs from discrete

nanoparticle models for quantitative comparison with data, which are discussed in Section 4. In Section 5 we discuss the conditions under which the PDF can be calculated in real space. Section 6 contains a brief summary.

### 2 Derivation of the PDF equations

To understand the precise relationship between the commonly used PDF equations, nanoparticle structures, and small angle scattering we rederive the PDF equations from the beginning since subtle details of the derivation that are often overlooked have a significant impact on discussion presented here. Furthermore, the full derivation is not reproduced even in many textbooks on the subject [2, 24, 3, 39] and so these subtleties are not widely appreciated in the community. We start from the scattering amplitude from a set of i atoms at points  $\vec{r_i}$  in the kinematical limit:

$$\psi(\vec{Q}) = \sum_{i} f_{i}(Q)e^{i\vec{Q}\cdot\vec{r_{i}}}$$

$$= \sum_{i} \psi_{i}$$
(3)

If the scattering from these atoms were totally incoherent the total intensity would be the sum of the intensities from each atom,

$$I_{inc} = \sum_{i} \psi_{i}^{*} \psi_{i}$$

$$= \sum_{i} f_{i}^{*}(Q) f_{i}(Q)$$

$$= \sum_{\alpha} N_{\alpha} f_{\alpha}^{*}(Q) f_{\alpha}(Q)$$

$$= N \sum_{\alpha} c_{\alpha} f_{\alpha}^{*}(Q) f_{\alpha}(Q)$$

$$= N \langle f^{2} \rangle,$$

$$(4)$$

where the sum over  $\alpha$  is now over the different species of atoms in the sample with N being the total number of atoms,  $N_{\alpha}$  being the number of atoms of type  $\alpha$  and where the concentration of species  $\alpha$  is  $c_{\alpha} = N_{\alpha}/N$ . Similarly, we can define the sample-averaged scattering power,  $\langle f \rangle = \sum_{\alpha} c_{\alpha} f_{\alpha}$  and

$$\langle f \rangle^2 = \frac{1}{N^2} \sum_{ij} f_j^* f_i$$

$$= \sum_{\alpha\beta} c_{\alpha} c_{\beta} f_{\alpha}^* f_{\beta}.$$
(5)

The full coherent scattering intensity is given by  $\psi^*\psi$  which is

$$I_{c} = \sum_{i} \sum_{j} f_{j}^{*} f_{i} e^{i\vec{Q} \cdot (\vec{r_{i}} - \vec{r_{j}})}$$

$$= \sum_{i,j} f_{j}^{*} f_{i} e^{i\vec{Q} \cdot \vec{r_{ij}}}.$$

$$(6)$$

Here we have dropped the Q-dependence of the atomic scattering factors to simplify the notation, but the fs are understood to retain their Q-dependence. We can separate out the self-scattering, i = j, for which  $\vec{r_{ij}} = 0$ :

$$I_{c} = \sum_{i} f_{i}^{*} f_{i} + \sum_{i \neq j} f_{j}^{*} f_{i} e^{i\vec{Q} \cdot r_{ij}^{*}}$$

$$= N \langle f^{2} \rangle + \sum_{i \neq j} f_{j}^{*} f_{i} e^{i\vec{Q} \cdot r_{ij}^{*}},$$

$$(7)$$

where we have used Eq. 4, resulting in an expression for the discrete scattering intensity for  $i \neq j$  as

$$I_d = I_c - N\langle f^2 \rangle$$

$$= \sum_{i \neq j} f_j^* f_i e^{i\vec{Q} \cdot \vec{r_{ij}}}.$$
(8)

We want an expression for the total scattering structure function,  $S(\vec{Q})$ , which is defined as  $\frac{I_c}{N\langle f \rangle^2} - \frac{\langle (f - \langle f \rangle)^2 \rangle}{\langle f \rangle^2}$ . The second term in this definition is the Laue monotonic diffuse scattering that comes about because of the imperfect cancellation of intensity at the destructive interference condition when atomic sites are occupied by atoms of different scattering strength. It results in a monotonic incoherent background even in the case of perfectly coherent scattering.

To get  $S(\vec{Q})$  from Eq. 7 we therefore must normalize by the total number of scatterers, N,

$$\frac{I_c}{N} = \langle f^2 \rangle + \frac{1}{N} \sum_{i \neq j} f_j^* f_i e^{i\vec{Q} \cdot r_{ij}^*}. \tag{9}$$

Subtracting the normalized self scattering term to get

$$\frac{I_c}{N} - \langle f^2 \rangle = \frac{1}{N} \sum_{i \neq j} f_j^* f_i e^{i\vec{Q} \cdot r_{ij}^2}, \tag{10}$$

and then normalizing by  $\langle f \rangle^2$ , we obtain

$$\frac{I_c}{N\langle f \rangle^2} - \frac{\langle f^2 \rangle}{\langle f \rangle^2} = \frac{1}{N\langle f \rangle^2} \sum_{i \neq j} f_j^* f_i e^{i\vec{Q} \cdot r_{ij}^2}.$$
 (11)

Thus,

$$S(\vec{Q}) - 1 = \frac{I_c}{N\langle f \rangle^2} - \frac{\langle f^2 \rangle}{\langle f \rangle^2}$$

$$= \frac{I_d}{N\langle f \rangle^2}$$

$$= \frac{1}{N\langle f \rangle^2} \sum_{i \neq j} f_j^* f_i e^{i\vec{Q} \cdot r_{ij}^2}.$$
(12)

This expression yields precisely  $S(\vec{Q}) - 1$  in terms of scattering from atoms in our sample.

For an isotropic sample, e.g., a powder of crystals or nanoparticles, we assume there to be a crystallite with every orientation with equal probability and we can take an orientational average. Place the  $\vec{Q}$  along z so that we can express  $\vec{Q} \cdot \vec{r_{ij}} = Qr_{ij}\cos\theta$ . Then the orientational averaging means that  $\theta$  takes all values with equal probability. The sample-averaged intensity for a pair of atoms will therefore be

$$\overline{e^{i\vec{Q}\cdot\vec{r_{ij}}}} = \frac{\int_0^{2\pi} d\phi \int_0^{\pi} d\theta e^{iQr_{ij}\cos\theta} r_{ij}^2 \sin\theta}{\int_0^{2\pi} d\phi \int_0^{\pi} d\theta r_{ij}^2 \sin\theta}$$

$$= \frac{-2\pi r_{ij}^2 \left[e^{iQr_{ij}\cos\theta}\right]_0^{\pi}}{4\pi r_{ij}^2 iQr_{ij}}$$

$$= \frac{\left[e^{iQr_{ij}} - e^{-iQr_{ij}}\right]}{2iQr_{ij}}$$

$$= \frac{\sin(Qr_{ij})}{Qr_{ii}}.$$
(13)

Using this in Eq. 6 gives the average coherent scattering intensity, as expressed originally by Debye [52]. From this we get the total scattering structure function for an isotropic sample,

$$S(Q) - 1 = \frac{1}{N\langle f \rangle^2} \sum_{i \neq j} f_j^* f_i \frac{\sin(Qr_{ij})}{Qr_{ij}}.$$
 (14)

Thus, the reduced total scattering structure function, F(Q) = Q[S(Q) - 1], is

$$F(Q) = \frac{1}{N\langle f \rangle^2} \sum_{i \neq j} f_j^* f_i \frac{\sin(Qr_{ij})}{r_{ij}}.$$
 (15)

It is convenient at this point to get rid of the Q-dependence of the x-ray form-factors. They are assumed to be isotropic so depend only on Q and not  $\vec{Q}$ , which is a good approximation for scattering from core electrons especially. Write  $f(Q) = f(0)\tilde{f}(Q)$ , where  $\tilde{f}(Q)$  has value 1 at Q = 0 and contains the Q-dependence of the form-factor and  $f(0) \approx Z$ , where Z is the atomic number that

scales the form factor. The Morningstar-Warren approximation [5] is that the Q-dependent part of the form factors can be well approximated by an average Q-dependence,  $\overline{\tilde{f}(Q)} = \frac{1}{N_{species}} \sum_{\alpha} c_{\alpha} \tilde{f}_{\alpha}(Q)$ . In this case the Q-dependence,  $\overline{\tilde{f}(Q)}^2$ , comes out of the double sums in Eq. 15 on the top and the bottom and cancels out. The fs that remain are Q-independent, and normally replaced by the atomic number (modified by any anomalous scattering factors). The same result holds for neutron scattering where the fs are replaced by coherent neutron scattering lengths, b. These have no Q-dependence and therefore the approximate method for removing the Q-dependence is not needed.

Now we want to consider the inverse Fourier transform of F(Q). Because F(Q) is an even function, we use the sine-Fourier transform,

$$f(r) = \frac{2}{\pi} \int_0^\infty F(Q) \sin(Qr) dQ. \tag{16}$$

We choose the  $\frac{2}{\pi}$  prefactor so that the direct sine transform has a prefactor of 1. This is precisely the definition of the PDF in Eq. 1. From this we get

$$f(r) = \frac{2}{\pi} \int_{0}^{\infty} \frac{1}{N\langle f \rangle^{2}} \sum_{i \neq j} f_{j}^{*} f_{i} \frac{\sin(Qr_{ij})}{r_{ij}} \sin(Qr) dQ$$

$$= \frac{2}{\pi N\langle f \rangle^{2}} \sum_{i \neq j} \frac{f_{j}^{*} f_{i}}{r_{ij}} \int_{0}^{\infty} \sin(Qr_{ij}) \sin(Qr) dQ$$

$$= \frac{1}{N\langle f \rangle^{2}} \sum_{i \neq j} \frac{f_{j}^{*} f_{i}}{r_{ij}} \left[ \delta(r - r_{ij}) - \delta(r + r_{ij}) \right]$$

$$= \frac{1}{r N\langle f \rangle^{2}} \sum_{i \neq j} f_{j}^{*} f_{i} \left[ \delta(r - r_{ij}) - \delta(r + r_{ij}) \right]$$

$$(17)$$

which, if we confine ourselves to the positive axis only, is

$$f(r) = \frac{1}{rN\langle f \rangle^2} \sum_{i \neq j} f_j^* f_i \, \delta(r - r_{ij}). \tag{18}$$

We can interpret f(r) in terms of the radial distribution function (RDF). The RDF, denoted R(r), is defined for an elemental system such that for an arbitrary atom i at the origin,  $R_i(r)dr$  gives the number of atoms in a shell of thickness dr at a distance r from that atom and the total RDF is the average of the partial RDFs over each atom taken at the origin. Thus, the integral of the RDF between two bounds gives the number of atomic pairs per atom with separation within those bounds. Equation 17 yields this behavior if we multiply

by r. For a solid with  $\alpha$  atomic species we get

$$\int_{a}^{b} R(r) dr = \int_{a}^{b} \frac{1}{N\langle f \rangle^{2}} \sum_{i \neq j} f_{j}^{*} f_{i} \, \delta(r - r_{ij}) dr$$

$$= \frac{1}{N\langle f \rangle^{2}} \sum_{i} \sum_{j \in S} f_{j}^{*} f_{i}$$

$$= \frac{1}{\langle f \rangle^{2}} \sum_{\alpha} c_{\alpha} f_{\alpha} \sum_{j \in S} f_{j}^{*},$$
(19)

where S is the set of atoms with distance from atom i greater than a and less than b. In the case of just one atomic species, this reduces to

$$\int_{a}^{b} R(r) dr = \frac{f^{2}}{f^{2}} \sum_{j \in S} 1$$

$$= N_{a},$$
(20)

as required. Thus,

$$f(r) = \frac{R(r)}{r}$$

$$= 4\pi r \rho(r).$$
(21)

The second expression comes from the relationship between the RDF and the pair density. The pair density is defined such that  $\int \mathrm{d}r \mathrm{d}\phi \mathrm{d}\theta r^2 \sin(\theta) \rho(r) = \int R(r) \mathrm{d}r$ , so that  $4\pi r^2 \rho(r) = R(r)$ . Comparing Equations 16 and 21 we see that the definition Eq. 16 does not yield G(r) (Eq. 2) and strictly  $\frac{2}{\pi} \int_0^\infty F(Q) \sin Q r \mathrm{d}Q = R(r)/r \neq G(r)$ . However, we see below that in practice it is G(r) and not R(r) that is obtained experimentally in most cases.

Finally, reordering Eq. 21 we find

$$\rho(r) = \frac{f(r)}{4\pi r}$$

$$= \frac{1}{4\pi r^2 N \langle f \rangle^2} \sum_{i \neq j} f_j^* f_i \, \delta(r - r_{ij}).$$
(22)

In reality,  $I_c(Q)$  is measured down to a minimum Q due to the experimental setup. This means that in general the forward scattering contributions are lost. We will consider the impact of this on the measured real-space function f(r). We rewrite the expression for the experimental f(r) as

$$f(r;Q_{min}) = \frac{2}{\pi} \int_{Q_{min}}^{\infty} F(Q)\sin(Qr)dQ$$

$$= 4\pi r \rho(r) - \frac{2}{\pi} \int_{0}^{Q_{min}} F(Q)\sin(Qr)dQ.$$
(23)

Of course, we have a finite  $Q_{max}$  as well, but this will be disregarded during the following discussion, as the effects are well understood [53].

### 3 Low angle scattering intensity

We will now consider a number of explicit examples to understand how the missing forward scattering affects the measured  $f(r; Q_{min})$ .

Consider a bulk material of uniform density and infinite extent. Since it has no internal structure there is perfect cancellation of all the discrete scattering intensity,  $I_d$ , everywhere except at Q=0 since for all wavelengths it is always possible to find a pair of volume elements where the scattering is exactly out of phase with each other and cancels. The definition of  $I_d$  in terms of a double sum over atoms is not entirely appropriate for this case (since there are no atoms!), but it gives an intuitive feeling about the behavior.

$$I_d(Q) = (N^2 - N)\langle f \rangle^2 \delta(Q), \tag{24}$$

which is a delta-function spike at Q=0 sitting on a zero background. The integrated intensity in the delta-function scales like the volume of the sample squared. Strictly speaking the sample has to be infinite in extent, and therefore  $N=\infty$ , to get a perfect delta-function. From Eqs. 12 and 24 we see that  $S(0)-1=N-1\approx N$  since  $\lim_{Q\to 0}\sin Qr/Qr=1$ .

Now we do this more formally. Assume the sample has a uniform number density,  $\rho_0$ . Since the scattering length is defined per atom, the scattering amplitude of a volume element  $d\vec{r}$  at position  $\vec{r}$  is  $\psi = \rho_0 \langle f \rangle e^{i\vec{Q}\cdot\vec{r}}d\vec{r}$ . For an infinite crystal, the intensity is given by

$$I_c(\vec{Q}) = \rho_0^2 \langle f \rangle^2 \int \int e^{i\vec{Q} \cdot (\vec{r} - \vec{r'})} d\vec{r} d\vec{r'}, \qquad (25)$$

where the integrals are over all space, which gives a delta-function at Q=0.

If the material is finite in extent then the integrals are finite. To evaluate the integrals, we can define a shape function  $s(\vec{r})$  such that inside the shape s=1 and outside the shape, s=0. For such a material,

$$I_c(\vec{Q}) = \rho_0^2 \langle f \rangle^2 \int \int s(\vec{r}) s(\vec{r'}) e^{i\vec{Q} \cdot (\vec{r} - \vec{r'})} d\vec{r} d\vec{r'}.$$
 (26)

Let us do a change of variables so that  $\vec{r''} = \vec{r} - \vec{r'}$ , and  $d\vec{r''} = d\vec{r}$ , in which case we have

$$I_{c}(\vec{Q}) = \rho_{0}^{2} \langle f \rangle^{2} \int \int s(\vec{r'}) s(\vec{r'} + \vec{r''}) e^{i\vec{Q} \cdot \vec{r''}} d\vec{r'} d\vec{r''}$$

$$= \rho_{0}^{2} \langle f \rangle^{2} \int d\vec{r''} e^{i\vec{Q} \cdot \vec{r''}} \int s(\vec{r'}) s(\vec{r'} + \vec{r''}) d\vec{r'}.$$
(27)

The second integral is a self convolution, or autocorrelation function, of the shape function. Let us define

$$\gamma_0(\vec{r}) = \frac{1}{V} \int s(\vec{r'}) s(\vec{r'} + \vec{r}) d\vec{r'}, \qquad (28)$$

where  $V = \int s(\vec{r}) d\vec{r}$  is the volume defined by the shape function. This  $\gamma_0(\vec{r})$  is the characteristic function of the shape [54], and has been called the nanoparticle form factor in the PDF literature [47, 46, 20]. Defined as such,  $\gamma_0(\vec{r})$  has the following properties:

$$\gamma_0(0) = 1$$

$$\int \gamma_0(\vec{r}) d\vec{r} = V$$
(29)

This definition, and a convenient dropping of the double-primes gives

$$I_c(\vec{Q}) = \rho_0^2 \langle f \rangle^2 V \int \gamma_0(\vec{r}) e^{i\vec{Q} \cdot \vec{r}} d\vec{r}.$$
 (30)

In analogy with the discrete case we want to convert this to  $S(\vec{Q}) - 1 = \frac{I_c}{N(f)^2} - \frac{\langle f^2 \rangle}{\langle f \rangle^2}$ , and using the fact that  $N = \rho_0 V$  we get

$$S(\vec{Q}) - 1 = \frac{1}{N\langle f \rangle^2} \rho_0^2 \langle f \rangle^2 V \int \gamma_0(\vec{r}) e^{i\vec{Q}\cdot\vec{r}} d\vec{r} - \frac{\langle f^2 \rangle}{\langle f \rangle^2}$$
$$= \rho_0 \int \gamma_0(\vec{r}) e^{i\vec{Q}\cdot\vec{r}} d\vec{r} - \frac{\langle f^2 \rangle}{\langle f \rangle^2}.$$
 (31)

The second term,  $\frac{\langle f^2 \rangle}{\langle f \rangle^2}$ , is very small compared to the first term. It is order unity, where the first term scales as  $N = \rho_0 V$ , and can safely be ignored in most cases.

Now we want to take the orientational average. This must be done with care as, in general, the orientation of the nanoparticle shape and the underlying structure are correlated. For example, the morphology of the particles (plates or needles) depends on easy growth directions of the underlying structure. As discussed by Gilbert [40], this means that the shape function and the internal structure of the particle are not, in general, separable and it is not correct to get the scattered intensity by convolving the reciprocal-space intensity with the Fourier transform of the characteristic function. Things are greatly simplified in the case where the underlying structure, or the nanoparticle shape, or both, are isotropic, or approximately so. Then we can denote the angle-averaged characteristic function as

$$\overline{\gamma_0(\vec{r})} = \gamma_0(r) = \frac{\int d\phi \int d\theta \sin(\theta) r^2 \gamma_0(\vec{r})}{\int d\phi \int d\theta r^2 \sin(\theta)}.$$
 (32)

Using this and Eq. 13 we get

$$S(Q) - 1 = \rho_0 \int_0^\infty dr \int_0^{2\pi} d\phi \int_0^\pi d\theta \overline{\gamma_0(\vec{r})} e^{i\vec{Q}\cdot\vec{r}} r^2 \sin\theta$$

$$= \rho_0 \int_0^\infty dr \int_0^{2\pi} d\phi \int_0^\pi d\theta \overline{\gamma_0(\vec{r})} e^{i\vec{Q}\cdot\vec{r}} r^2 \sin\theta$$

$$= \rho_0 \int_0^\infty dr \int_0^{2\pi} d\phi \int_0^\pi d\theta \gamma_0(r) \frac{\sin Qr}{Qr} r^2 \sin\theta$$

$$= \rho_0 \int_0^\infty \gamma_0(r) \frac{\sin Qr}{Qr} 4\pi r^2 dr.$$
(33)

Since the particles have no preferred orientation in space, we have broken the average of the product in the first line into the product of the averages. This gives

$$F(Q) = \int_0^\infty 4\pi \rho_0 r \gamma_0(r) \sin(Qr) dr.$$
 (34)

Noting that this is the direct sine-Fourier transform, we take the inverse transform to get

$$f_u(r) = \frac{2}{\pi} \int_0^\infty F(Q) \sin(Qr) dQ$$
  
=  $4\pi \rho_0 r \gamma_0(r)$ , (35)

where the subscript u indicates that this result is for a solid of uniform density distribution,  $\rho_0$ .

Next we consider a macroscopic crystal. The difference in F(Q) is at higher Q where, instead of complete cancellation of all the discrete intensity it appears at distinct reciprocal lattice points as sharp Bragg peaks. Importantly, in the region of Q below the first Bragg peak, the distinct scattering is zero except at very low-Q where small angle scattering region is reached. The *small angle* scattering intensity,  $I_{sas}$  from the crystal is identical to that from the solid with uniform density:  $I_{u}^{sas} = I_{crystal}^{sas}$ . The small and wide angle scattering regions are well separated in Q and  $I_{sas}$  decays to zero before  $Q_{min}$  is reached in the crystal. Thus,

$$f_{sas}(r) = \frac{2}{\pi} \int_0^{Q_{min}} F(Q) \sin(Qr) dQ$$

$$= f_u(r)$$
(36)

and therefore

$$\frac{2}{\pi} \int_0^{Q_{min}} F(Q) \sin(Qr) dQ = 4\pi \rho_0 r \gamma_0(r). \tag{37}$$

We are now in a position to understand in detail the nature of the measured PDF  $f(r; Q_{min})$ . Substituting Eq. 37 into Eq. 23 we get

$$f(r; Q_{min}) = 4\pi r \rho(r) - 4\pi r \rho_0 \gamma_0(r).$$
 (38)

This is similar to the definition of the PDF from Eq. 2, except that  $\gamma_0(r)$  appears in the sloping baseline term.

### 4 Calculating $f(r; Q_{min})$ from models

We can now consider the calculation of measured PDFs using Eq. 38 in a number of interesting limits.

#### 4.1 Calculating in real-space for bulk crystals

In the case of bulk crystals, the region of interest in the PDF is usually  $r \ll D$ , D being the smallest dimension of the crystal. In this region,  $\gamma_0(r) \approx 1$ . Thus,

$$f(r; Q_{min}) = G(r)$$

$$= 4\pi r(\rho_{bulk}(r) - \rho_0),$$
(39)

which is the familiar definition of G(r) in Eq. 2. The pair density function,  $\rho_{bulk}(r)$ , is calculated from a model with periodic boundary conditions [55, 56], or from a box of atoms that is much larger in extent than the range of r of interest [57], using Eq. 22. The average number density  $\rho_0$  is given by the number of atoms per unit volume, which in the case of crystals is the number of atoms in the unit cell divided by the unit cell volume.

Two approaches are typically taken to account for thermal and zero-point motion of atoms. One approach is to assume that these motions are well approximated by a Gaussian probability distribution, in which case the deltafunctions may be convoluted by Gaussians of finite width to represent the motion. If the motion is anisotropic, Gaussian distributions with different widths in different directions may be used. Because the function being convoluted is a delta-function, from a practical perspective Eq. 39 is simply modified so that a Guassian of the appropriate width is added instead of a delta-function [56, 58]. In models with many thousands of atoms, which is sometimes the case for reverse Monte Carlo methods, the probability distributions can be built up from the static ensemble itself and no convolution is carried out. In this case no presumption of Gaussian dynamics is made. In practice the Guassian approximation works very well in most cases, and deviations from Gaussian behavior can be accounted for by introducing disorder in the models, which is a convenient way of separating the harmonic and non-harmonic contributions to the structure. The effects of correlated dynamics are accounted for using an r-dependent Gaussian broadening [59, 58, 60].

A convolution is also often carried out to account for the termination effects of the Fourier transform. For example, if the data are simply terminated at  $Q_{max}$ , as is often the case when data are available to high-Q, the model PDF must be convoluted with a sinc function [3]. From Eqs. 16 and 39, it is clear that the function that must be so convoluted is  $f(r;Q_{min})$ . This may be done with an integral directly in real-space, but it is often quicker to use a fast Fourier transform and do the convolution as a product in reciprocal space taking advantage of the convolution theorem. Note that, because of the sloping baseline in  $f(r;Q_{min})$ , the two convolutions (thermal motion and termination effects) are applied at different times during the PDF calculation. The thermal convolution is applied to  $\rho_{bulk}(r)$  (Eq. 22) and then this is converted to G(r) (Eq. 2), to which is applied the termination convolution. Modeling programs [56, 48] account for this correctly, but when individual peaks are fit in real-space to extract peak positions and intensities, this is often overlooked, though it seems reasonable to ignore the termination effects in most cases.

# 4.2 Calculating in real-space for nanoparticles modeled as attenuated bulk crystals

In this case  $\rho_{bulk}(r)$  is determined using a model of a bulk structure as described in Section 4.1. The pair density,  $\rho(r)$ , in Eq. 38 is the function for the nanoparticle, which is approximated as  $\gamma_0(r)\rho_{bulk}(r)$  [42]. Thus,

$$f(r;Q_{min}) = 4\pi r \gamma_0(r) (\rho_{bulk}(r) - \rho_0). \tag{40}$$

This approach has been implemented in the PDFgui modeling software [48] and used successfully on rather well ordered CdSe nanocrystals [20]. The main shortcoming is that effects that cannot be incorporated in the average structure, such as surface relaxations or core-shell inhomogeneities, cannot be modeled.

If there is a distribution of nanoparticle sizes and shapes, the characteristic function,  $\gamma_0(r)$  can be replaced with an appropriately averaged characteristic function

$$\gamma(r) = \int \gamma_0(r; R_1, R_2, ...) p(R_1, R_2, ...) dR_1 dR_2 ...$$
 (41)

Here,  $p(R_1, R_2, ...)$  is the normalized distribution of nanoparticle shapes parameterized by  $R_1, R_2, ...$  For example, for spherical nanoparticles of radius R,  $p(R_1, R_2, ...) = p(R)$ , the distribution of nanoparticle radii. Finally, we replace Eq. 40 with

$$f(r;Q_{min}) = 4\pi r \gamma(r) (\rho_{bulk}(r) - \rho_0). \tag{42}$$

Great care should be taken to ensure that the result is unique when refining a number of nanoparticle morphology parameters beyond one or two.

## 4.3 Calculating as the Fourier transform of the properly normalized Debye Function

This approach has been successfully used by a number of authors [12, 61]. The F(Q) function is evaluated using Eq. 15 and then Fourier transformed to obtain

the desired real-space function. To account for thermal and zero-point motion in reciprocal-space calculations, Eq. 15 is replaced with a version that includes Debye-Waller effects,

$$F(Q) = \frac{1}{N\langle f \rangle^2} \sum_{i \neq j} f_j^* f_i \left( e^{-\frac{1}{2}\sigma_{ij}^2 Q^2} \right) \frac{\sin(Qr_{ij})}{r_{ij}}.$$
 (43)

Here,  $\sigma_{ij}^2$  is the correlated broadening factor for the atom pair, which is the real-space Gaussian width discussed in the case of bulk crystals.

As we show here, for a quantitative comparison with measured data, care must be taken with the Fourier transform so that it is carried out over the same range of Q as the experiment. The main drawback of the reciprocal-space approach is that it can be very slow compared to direct real-space calculation due to the long-range extent of the signal from each pair. It is generally preferred for smaller systems. However, due to recent algorithmic advances, the calculation of the Debye equation for larger systems can be greatly accelerated under certain circumstances [61].

Using this method, the termination effects coming from the Fourier transform are implicity included provided the Fourier transforms to obtain the model and data PDFs are terminated with the same  $Q_{min}$  and  $Q_{max}$  values.

### 4.4 Calculating in real-space from discrete nanoparticle models

In this case, Eq. 38 is used directly, where  $\rho(r)$  is calculated from a finite model of the discrete nanoparticle using Eq. 22. The difficulty arises in determining a correct form for the baseline  $-4\pi r \rho_0 \gamma_0(r)$ . Up until now, the shape of the baseline has been approximated using expansions of ad hoc mathematical functions [16, 50, 51, 37]. This is successful at approximating the behavior of the baseline. However, in this work we derive the explicit form of the baseline shape in terms of the characteristic function of the nanoparticle, the autocorrelation function of the nanoparticle shape. This suggests a number of approaches to calculate the PDF baseline in a more physical way.

If we have accurate small angle scattering data from the samples, from Eq. 38 we see that we can compute the PDF baseline from the measured SAS via a Fourier transform. However, care must be exercised as the derivation assumes that the sample is made up of discrete nanoparticles. In general, clusters and aggregates of nanoparticles will form and small angle scattering signals from these structures on different length-scales will be present and must be separated. Also, scattering density fluctuations of any sort in the sample will affect the SAS signal, as discussed elsewhere [62]. None of these effects need be explicitly considered if the SAS signal is not used in the PDF definition, as in Eq. 38, though an alternative method is then required to determine the baseline.

The inclusion of SAS data has the potential to add significant value to any refinement of nanoparticle models from the PDF. Both small and large angle scattering contain information about the shape and size of nanoparticles, but

this information is nearly decoupled from the internal nanoparticle structure in the small angle scattering. This same information is in the PDF, but it can be obscured by structure features, such as when the PDF prematurely attenuates due to a complex or amorphous surface structure. In this case the nanoparticle size obtained from SAS will be larger than the apparent NP size obtained from the PDF that reflects the size of the coherent core structure. Even without the inclusion of SAS data into PDF refinements, we can can learn much from SAS analysis techniques. PDF nanoparticle refinements usually start with a simple model that includes atomic positions restricted by a shape. Therefore, PDF analysis can benefit from the various *ab initio* methods [63, 64] for determining the shape of a scatterer from the SAS.

Without the use of the small angle intensity for determining  $\gamma_0(r)$ , we can consider approaches to determine it self-consistently from the model since it is the autocorrelation of the particle shape which is directly available from the model itself by determining a "shrink-wrapping" of the atomistic model. On the contrary, when the internal structure is well known, but the size and shape distribution of nanoparticles is not, then the characteristic function can be parameterized and refined to obtain the approximate nanoparticle dimensions as was done in [20].

### 5 The extent of small angle scattering

We have considered the two asymptotic situations here of including or excluding all the SAS. If the SAS is retained in the intensity that is Fourier transformed, the resulting real-space function obtained is  $4\pi r \rho(r) = R(r)/r$  (Eq. 17). Excluding it all results in G(r) (Eq. 38). We now consider the possibility that some, but not all, of the small angle scattering is included in the Fourier transform. This might occur in the case of very small nanoparticles, for example, when the SAS extends to wider angles. Here we estimate the circumstances under which a significant amount of small angle intensity will appear in a wide angle PDF experiment for the case of a sphere of uniform density. The scattering intensity is given by [43]

$$I(Q) \propto \frac{9}{(QR)^6} \left[ \sin(QR) - QR \cos(QR) \right]^2, \tag{44}$$

where R is the radius of the sphere. By integrating this equation from 0 to  $Q_{min}$ , and dividing by the total integrated intensity, we get an expression for the proportion of small angle intensity above  $Q_{min}$  for a given nanoparticle diameter [43]:

$$i(x) = 1 - \frac{1}{2\pi r^5} \left[ (2x^4 - x^2 + 3)\cos(2x) + x(x^2 + 6)\sin(2x) + 4x^5 \operatorname{Si}(2x) - (5x^2 + 3) \right].$$
(45)

Here,  $x = Q_{min}R$  and Si(x) represents the sine integral, Si(x) =  $\int_0^x \frac{\sin(x')}{x'} dx'$ . For a very small nanoparticle of radius 5Å, we see that i(5) < 0.01, correspond-

ing to  $Q_{min} \approx 1\text{Å}^{-1}$ , which is typical for a RAPDF [65] experiment. Thus, for even quite small nanoparticles, practically all small angle intensity is below  $Q_{min} = 1\text{Å}^{-1}$  and Eq. 38 is appropriate. However, care should be taken not to extend  $Q_{min}$  too low in Q in a measurement of a nanoparticulate system.

In the few-atom limit, such as the case of discrete small molecules, the small and wide angle scattering are not cleanly separated. To produce a complete real-space signal, one can approximate the small angle scattering from a candidate structure model. This approach is commonly used in the study of small molecules in the gas phase [66]. The Fourier transform of the estimated scattering approximates R(r)/r, the nominal "experimental" or "modified" RDF. An equivalent method for obtaining the modified RDF from wide angle scattering alone is to add a baseline estimated from a model structure to  $f(r, Q_{min})$  [67]. This approach has been successful for calculating the R(r)/r for many-atom nanoparticles.

### 6 Summary

The PDF is a valuable tool for identifying the form and the interior composition of nanoscale materials. Whereas the oscillating component of the PDF gives information about the interatomic distances within the material, the PDF baseline is a function of the characteristic function, a measure of nanoparticle shape which has its origin in the SAS that is usually disregarded in a powder diffraction experiment. This characteristic function goes unnoticed in macroscopic particles, where the PDF is observed at distances that are much smaller than the particle diameter. For nanoparticles, the PDF baseline, and therefore the characteristic function, cannot be disregarded. We have presented a full derivation of the PDF equation taking into account the missing SAS and have reviewed different methods for calculating the PDF for nanoparticles. Given the relationship between the PDF and SAS equations, there is potential benefit in incorporating SAS data and analysis methods into PDF studies.

### 7 Acknowledgments

The authors would like to thank Phil Duxbury and Pavol Juhás for careful proofreading and discussion of this manuscript. The authors acknowledge enlightening conversations with Matteo Leoni, Reinhard Neder, Thomas Proffen, Chong-Yu Ruan, Paolo Scardi and Mike Thorpe. This work was supported by the US National Science foundation through Grant DMR-0703940.

#### References

- [1] Debye, P. and Menke, H. (1930) Physik. Z. 31, 797–8.
- [2] Warren, B. E. (1990) X-ray diffraction, Dover, New York.

- [3] Egami, T. and Billinge, S. J. L. (2003) Underneath the Bragg peaks: structural analysis of complex materials, Pergamon Press, Elsevier, Oxford, England.
- [4] Warren, B. E. (1934) J. Phys. Chem. 2, 551.
- [5] Warren, B. E., Krutter, H., and Morningstar, O. (1936) J. Am. Ceram. Soc. 19, 202–6.
- [6] Franklin, R. E. (1950) Acta Crystallogr. 3, 107.
- [7] Franklin, R. E. (1951) Proc. R. Soc. Lond. A 209, 196.
- [8] Wright, A. C. (1998) Glass. Phys. Chem. 24, 148–179.
- [9] Billinge, S. J. L. and Kanatzidis, M. G. (2004) Chem. Commun. 2004, 749–760.
- [10] Billinge, S. J. L. and Levin, I. (2007) Science **316**, 561–565.
- [11] McKenzie, D. R., Davis, C. A., Cockayne, D. J. H., Muller, D. A., and Vassallo, A. M. FEB 13 1992 Nature 355(6361), 622–624.
- [12] Zhang, H. Z., Gilbert, B., Huang, F., and Banfield, J. F. (2003) Nature 424(6952), 1025–1029.
- [13] Gateshki, M., Hwang, S.-J., Park, D., Ren, Y., and Petkov, V. (2004) J. Phys. Chem. B 108, 14956–14963.
- [14] Gilbert, B., Huang, F., Zhang, H., Waychunas, G. A., and Banfield, J. F. (2004) *Science* **305**, 651–654.
- [15] Page, K., Proffen, T., Terrones, H., Terrones, M., Lee, L., Yang, Y., Stemmer, S., Seshadri, R., and Cheetham, A. K. (2004) Chem. Phys. Lett. 393, 385–388.
- [16] Korsunskiy, V. I. and Neder, R. B. Dec 2005 J. Appl. Crystallogr. 38(6), 1020–1027.
- [17] Petkov, V., Gateshki, M., Choi, J., Gillan, E. G., and Ren, Y. (2005) J. Mater. Chem. 15, 4654.
- [18] Bedford, N., Dablemont, C., Viau, G., Chupas, P., and Petkov, V. (2007) J. Phys. Chem. C 111(49), 18214–18219.
- [19] Ehm, L., Antao, S. M., Chen, J., Locke, D. R., Michel, F. M., Martin, C. D., Yu, T., Parise, J. B., Antao, S. M., Lee, P. L., Chupas, P. J., Shastri, S. D., and Guo, Q. (2007) *Powder Diffr.* 22, 108–112.
- [20] Masadeh, A. S., Božin, E. S., Farrow, C. L., Paglia, G., Juhás, P., Karkamkar, A., Kanatzidis, M. G., and Billinge, S. J. L. (2007) Phys. Rev. B 76, 115413.

- [21] Pradhan, S. K., Mao, Y., Wong, S. S., Chupas, P., and Petkov, V. (2007) Chem. Mater. 19, 6180–6186.
- [22] Kaplow, R., Strong, S. L., and Averbach, B. L. (1965) Phys. Rev. 138, 1336.
- [23] Kaplow, R., Rowe, T. A., and Averbach, B. L. (1968) Phys. Rev. 168, 1068.
- [24] Klug, H. P. and Alexander, L. E. (1974) X-ray diffraction procedures for polycrystalline and amorphous materials, Wiley, New York 2nd edition.
- [25] Johnson, P. A. V., Wright, A. C., and Sinclair, R. N. (1982) J. Non-Cryst. Solids 50, 281–311.
- [26] Soper, A. K. and Silver, R. N. (1982) Phys. Rev. Lett. 49(7), 471–474.
- [27] Korsunskii, V. I. (1985) J. Struct. Chem. 26, 208–216.
- [28] Wright, A. C. (1985) J. Non-Cryst. Solids 76, 187.
- [29] Nanao, S., Dmowski, W., Egami, T., Richardson, J. W., and Jorgensen, J. D. (1987) Phys. Rev. B 35(2), 435-440.
- [30] Egami, T., Rosenfeld, H. D., Toby, B. H., and Bhalla, A. (1991) Ferroelectrics 120, 11.
- [31] Billinge, S. J. L., Kwei, G. H., and Takagi, H. (1994) Phys. Rev. Lett. 72, 2282.
- [32] Petkov, V., Gerber, T., and Himmel, B. (1998) *Phys. Rev. B* **58(18)**, 11982–11989.
- [33] Petkov, V. and Danev, R. (1998) J. Appl. Crystallogr. 31, 609.
- [34] Keen, D. A. (2001) J. Appl. Crystallogr. 34, 172–177.
- [35] Tucker, M. G., Dove, M. T., and Keen, D. A. (2001) J. Appl. Crystallogr. 34, 630–638.
- [36] Soper, A. K. (2007) J. Phys.: Condens. Mat. 19, 335206.
- [37] Neder, R. B., Korsunskiy, V. I., Chory, C., Müller, G., Hofmann, A., Dembski, S., Graf, C., and Rühl, E. (2007) *Phys. Status Solidi C* **4(9)**, 1610–1634.
- [38] Billinge, S. J. L. (2008) J. Solid State Chem. 181, 1698–1703.
- [39] Robert E. Dinnebier and Simon J. L. Billinge, (ed.) (2008) Powder diffraction: theory and practice, Royal Society of Chemistry, London, England.
- [40] Gilbert, B. (2008) J. Appl. Crystallogr. 41, 554.
- [41] Levashov, V. A., Billinge, S. J. L., and Thorpe, M. F. (2007) J. Comput. Chem. 28, 1865–1882.

- [42] Guinier, A. (1963) X-ray diffraction in crystals, imperfect crystals, and amorphous bodies., San Francisco, W.H. Freeman, San Francisco.
- [43] Rayleigh, L. (1914) Proc. R. Soc. Lond A90, 219.
- [44] O. Glatter and O. Kratky, (ed.) (1982) Small Angle X-ray Scattering, Academic Press Inc., London 1st edition.
- [45] Thorpe, M. F. and Lei, M. Nanoparticle shape factors for spheroids unpublished (2007).
- [46] Kodama, K., Iikubo, S., Taguchi, T., and Shamoto, S. (2006) Acta Crystallogr. A 62, 444–453.
- [47] Qiu, X., Th. Proffen, Mitchell, J. F., and Billinge, S. J. L. (2005) Phys. Rev. Lett. 94, 177203.
- [48] Farrow, C. L., Juhás, P., Liu, J. W., Bryndin, D., Božin, E. S., Bloch, J., Proffen, T., and Billinge, S. J. L. (2007) J. Phys: Condens. Mat. 19, 335219.
- [49] Liz-Marzán, L. M., Giersig, M., and Mulvaney, P. (1996)  $Langmuir~\mathbf{12},~4329-4335.$
- [50] Neder, R. B. and Korsunskiy, V. I. (2005) J. Phys.: Condens. Mat. 17(5), S125–S134.
- [51] Korsunskiy, V. I., Neder, R. B., Hofmann, A., Dembski, S., Graf, C., and Rühl, E. Dec 2007 *J. Appl. Crystallogr.* **40(6)**, 975–985.
- [52] Debye, P. (1915) Annalen der Physik (Berlin, Germany) 46, 809–823.
- [53] Toby, B. H. and Egami, T. (1992) Acta Crystallogr. A 48(3), 336–46.
- [54] Guinier, A., Fournet, G., Walker, C., and Yudowitch, K. (1955) Small-angle scattering of x-rays, John Wiley & Sons, Inc., New York.
- [55] Billinge, S. J. L. (1998) In S. J. L. Billinge and M. F. Thorpe, (ed.), Local Structure from Diffraction, New York: Plenum. p. 137.
- [56] Proffen, T. and Billinge, S. J. L. (1999) J. Appl. Crystallogr. 32, 572–575.
- [57] McGreevy, R. L. and Pusztai, L. (1988) Mol. Simul. 1, 359–367.
- [58] Thorpe, M. F., Levashov, V. A., Lei, M., and Billinge, S. J. L. (2002) In S. J. L. Billinge and M. F. Thorpe, (ed.), From semiconductors to proteins: beyond the average structure, New York: Kluwer/Plenum. pp. 105–128.
- [59] I.-K. Jeong, Proffen, T., Mohiuddin-Jacobs, F., and Billinge, S. J. L. (1999) J. Phys. Chem. A 103, 921–924.

- [60] Jeong, I. K., Heffner, R. H., Graf, M. J., and Billinge, S. J. L. (2003) Phys. Rev. B 67, 104301.
- [61] Cervellino, A., Giannini, C., and Guagliardi, A. (2006) J. Comput. Chem. 27, 995–1008.
- [62] Cargill, III, G. S. (1971) J. Appl. Crystallogr. 4, 277.
- [63] Svergun, D. I. and Stuhrmann, H. B. (1991) Acta Crystallogr. A 47(6), 736–744.
- [64] Chacón, P., Morán, F., Díaz, J. F., Pantos, E., and Andreu, J. M. (1998) Biophys. J. 74(6), 2760–2775.
- [65] Chupas, P. J., Qiu, X., Hanson, J. C., Lee, P. L., Grey, C. P., and Billinge, S. J. L. (2003) J. Appl. Crystallogr. 36, 1342–1347.
- [66] István Hargittai and Magdolna Hargittai, (ed.) (1988) Stereochemical applications of gas-phase electron diffraction, VHC Publishers, New York 1st edition.
- [67] Ruan, C.-Y., Murooka, Y., Raman, R., and Murdick, R. (2007) Nano Lett. 7(5), 1290–1296.