arXiv:0811.1836v1 [cond-mat.other] 12 Nov 2008 [arXiv:0811.1836v1 \[cond-mat.other\] 12 Nov 2008](http://arxiv.org/abs/0811.1836v1)

Slow Dynami
s in Hard Condensed Matter: A Case Study of the Phase Separating System NdNiO3

Devendra Kumar,¹ K.P. Raieev,^{1,*} J. A. Alonso,² and M. J. Martínez-Lope²

¹ Department of Physi
s, Indian Institute of Te
hnology Kanpur 208016, India

"Instituto de Ciencia de Materiales de Madrid, CSIC, Cantoblanco, E-28049 Madrid, Spain

We report the time dependent response of electrical resistivity in the non-magnetic perovskite oxide NdNiO₃ in its phase separated state and provide a physical explanation of the observations. We also model the system and do an accurate Monte Carlo simulation of the observed behavior. While cooling a phase separation takes place in this system below its metal-insulator transition temperature and in this state the material exhibits various dynami
al phenomena su
h as relaxation of resistivity, dependen
e of resistivity on ooling rate and rejuvenation of the material after ageing. These phenomena signal that the phase separated state of $NdNiO₃$ is not in thermodynamic equilibrium and we conjecture that it consists of supercooled paramagnetic metallic and antiferromagnetic insulating phases. The super
ooled phases are metastable and they swit
h over to the insulating equilibrium state stochastically and this can account for the slow dynamics observed in our system. We also verify the predictive power of our model by simulating the result of a new experiment and confirming it by actual measurements.

PACS numbers: 64.60.My, 64.70.K-, 71.30.+h,

Keywords: Phase Separation, Hysteresis, Super
ooling, Relaxation, Time dependen
e, Metal-Insulator Transition

I. **INTRODUCTION**

Usually hard ondensed matter is asso
iated with fast dynamics, but sometimes we also see slow dynamics, particularly in cases such as glasses, spin glasses, phase separated systems et
. Dynami
s of glasses and spin glasses have been intensively studied from the middle of last century, but su
h studies on phase separated systems started attra
ting a good deal of interest from physi
ists only towards the end of last entury. Phase separation always seems to be associated with a broadened first order phase transition and it has been observed in su
h systems as transition metal oxides, a famous example being the olossal magnetoresistan
e (CMR) manganites, and alloys which show martensitic phase transitions.^{1,2,3,4,5}

There has been a large number of studies on the phase separated states associated with a broad first order metal-insulator (M-I) transition in transition metal oxides such as VO_2 , CMR manganites, the rare earth nickelate $PrNiO₃$, the cobaltite $La_{1-x}Sr_xCoO₃$ etc. They exhibit unusual phenomena su
h as very slow relaxation of resistivity^{6,7,8,9,10,11} and magnetization,^{12,13} rejuvenation of resistivity after ageing and dependen
e of physi
al properties on cooling rate.^{8,14,15,16} A significant amount of work has gone in to study these systems in detail but they are not, as yet, well understood even though there is a recognition that the phenomena described above originate from phase separation. The presen
e of the slow glass-like relaxations in the above systems has led many people to onsider the phase separated systems as spin glasses, luster glasses and it has been argued that the inter
luster magneti intera
tions are responsible for the observed glass-like dynami
s in these systems.4,13 The above picture has been proposed for magnetic systems, but similar phenomena have been seen in non-magneti

systems as well.^{6,9} This raises the possibility that a spin glass like model may not be the most appropriate to des
ribe the dynami
s of phase separation in general. There has been other attempts to des
ribe these phenomena in CMR manganites in terms of a phenomenologi
al model where it has been proposed that the phase boundaries relax through a hierarchy of energy barriers.^{8,12} Though this is a ommendable attempt we feel that this model does not really apture the essen
e of the phenomena be ause it does not onsider what happens to the system while heating. There has been a more recent approach to understand the dynami
s of phase separated systems based on the on
ept of kineti arrest of a super
ooled system into a magnetic glass and its subsequent de-arrest on warming 11,15 But there are systems which are nonmagneti and non-glassy and it would be very interesting to make an attempt to find out the physics behind the slow dynamics in such systems because what it might reveal may turn out to have wider implications. $6,17,18$

The perovskite oxide $NdNiO₃$, which undergoes a temperature driven M-I transition and has an asso
iated phase separated state,¹⁹ we believe, can be taken as a model system to probe the dynami
s of oexisting phases in non-magnetic, non-glassy systems. NdNi O_3 is a clean system whi
h does not require any doping to see the phase separated state and it is essentially unaffected by the application of a magnetic field and it does not show any eviden
e of glass transition.20,21 Moreover the phase separated state exists over a relatively large temperature range whi
h makes it easy to study slow dynami
s and phase separation.

 $NdNiO₃$ is a member of the series of compounds known as rare earth nickelates $(RNiO₃)$, which are one of the few families of perovskite oxides that undergo a first order metal-insulator phase transition.²² These com-

pounds rystallize in an orthorhombi
ally distorted perovskite structure with space group P_{bnm} . The ground state of the nickelates $(R \neq La)$ is insulating,^{22,23} charge ordered^{24,25,26,27,28} and antiferromagnetic.²⁹ On increasing temperature from absolute zero these ompounds undergo a temperature driven antiferromagneti to paramagneti transition, and an insulator to metal transition. Below the M-I transition temperature (T_{MI}) , transport properties of NdNiO3 exhibit ^a large hysteresis and in this region, the physi
al state of the system is phase separated and it has been shown to consist of paramagnetic metallic and antiferromagnetic insulating phases.^{19,22}

In this work we use areful time and temperature dependent resistivity measurements on $NdNiO₃$ to gain an understanding of its phase separated state and its dynami
s. The phase separated state omes into existen
e on ooling the material below its M-I transition temperature and vanishes at sufficiently low temperature and does not form at all during subsequent heating. We have provided a redible physi
al explanation along with a Monte Carlo simulation to des
ribe all the behavior exhibited by our system. The simulation results are found to reprodu
e the experimental results quite well. Our results indi
ate that in the phase separated state of $NdNiO₃$, the metallic phase is present in its super
ooled state. The super
ooled metalli phase is metastable and it relaxes to the insulating equilibrium state giving rise to the various observed phenomena.

II. EXPERIMENTAL DETAILS

Polycrystalline $NdNiO_3$ samples in the form of 6 mm diameter and 1 mm thi
k pellets were prepared and characterized as described elsewhere.³⁰ The preparation method uses a high temperature of 1000◦^C and ^a high oxygen pressure of 200 bar.

All the temperature and time dependent measurements were done in a home made cryostat. To avoid thermal gradients in the sample during measurement it was mounted inside a thi
k-walled opper en
losure so that during the measurement the sample temperature would be uniform. It was found that mounting the sample in this fashion improved the reprodu
ibility of the time dependence measurements significantly. A Lakeshore Cryotroni
s temperature ontroller was used to ontrol the temperature and the temperature stability was found to be better than 3 mK during onstant temperature measurements.

Below T_{MI} ($\approx 200 \text{ K}$) NdNiO₃ is not in thermodynami equilibrium and slowly relaxes be
ause of whi
h the experimental data that we get depend on the procedure used for the measurement. The procedure we used was as follows. While cooling we start from 300 K , and then re
ord the data in steps of 1 K interval after allowing the temperature to stabilize at ea
h point. In between two temperature points the sample was cooled at a fixed cooling rate of $2 K/min$. After the cooling run is over

we wait for one hour at 82 K and then the heating data was olle
ted at every one degree interval. The heating rate between temperature points was the same as the cooling rate used earlier. This cycle of measurements was repeated with a different cooling and heating rate of $0.2 K/min$ also.

It was observed that the resistivity above 200 K and below 115 K does not show any time dependen
e, and it is also independent of measurement history. Thus to avoid the effect of any previous measurements, all time dependent experiments in the ooling run were done as follows: first take the sample to $220 K$ (sufficiently above 200 K , wait for half an hour, then cool at 2.0 K/min to the temperature of interest and on
e the temperature has stabilized re
ord the resistan
e as a fun
tion of time. In the heating run the time dependent resistivity was done in a similar fashion: first take the sample to 220 K , wait for half an hour, then cool at 2.0 K/min to 85 K , wait for one hour, and then heat at $2.0 K/min$ to the temperature of interest and on
e the temperature has stabilized re
ord the resistan
e as a fun
tion of time.

The four probe van der Pauw method was used to measure the resistivity and standard precautions, such as current reversal to take are of stray emfs, were taken during the measurement. We also took are to ensure that the measuring current was not heating up the sample.

III. RESULTS

Figure [1](#page-2-0) shows the electrical resistivity of $NdNiO₃$ as a function of temperature. The resistivity is multiple valued, the cooling and heating data differing significantly from ea
h other and forming a large hysteresis loop. The resistivity plot indicates that $NdNiO₃$ undergoes a relatively sharp M-I transition at about 200 K while heating with a width of about $10K$. In contrast, while cooling, the resistivity shows a rather broad M-I transition entered around 140 K with a spread of about 40 K. Below $115 K$ or so, the heating and cooling data merge and the $\log \rho$ vs $1/T$ plot is linear. This indicates that the sample is insulating at low temperatures and, if the band gap is ∆, the resistivity should follow the relation

$$
\rho(T) = \rho_0 e^{\frac{\Delta}{k_B T}} \tag{1}
$$

Below $115K$ both the heating and the cooling data fit quite well to this model, with a coefficient of determination, $R^2= 0.99955$. ρ_0 and Δ for the insulating region turn out to be $99 \text{ m}\Omega \text{ cm}$ and 42 meV respectively, which are in reasonable agreement with the values previously reported.¹⁹

We collected more hysteresis data with different minimum temperatures su
h as 140 K, 146 K and 160 K. In these measurements we ool the sample from 220 K to one of the minimum temperatures mentioned above and then heat it back to $220 K$, both operations being carried out at a fixed rate of $2 K/min$. Loops formed in this

fashion are called minor loops and these are indicated by the labels a, b and c in Figure [1.](#page-2-0) In the cooling cycle all the three minor loops coincide with the cooling curve of the full hysteresis loop. In the heating cycle, for loops a and b with lower minimum temperatures, the resistivity de
reases with in
reasing temperature and joins the full loop at 200 K . In the case of loop c, as we increase the temperature, the resistivity in
reases somewhat till about 188 K and then it falls and joins the full loop at 200 K.

The resistivity also shows a noti
eable dependen
e on the rate of temperature change in the cooling cycle as shown in the inset of Figure [1.](#page-2-0) The data for the lowest curve was collected at $2 K/min$ and for the middle curve at 0.2 K/min . The uppermost curve is an estimate obtained by extrapolating the time dependen
e data shown in Figure [2](#page-2-1) to infinite time. We did not see any dependen
e on rate of hange of temperature when heating from 80 K to 220 K. This means that while cooling, below the M-I transition temperature (200 K), the system is not in equilibrium and on the other hand while heating, the system is either in, or very close to, equilibrium. These observations are orroborated by the data shown in the next Figure.

A subset of the time dependent resistivity data taken

Figure 1: (Color online) ρ vs. $1/T$ plot for NdNiO₃. The blue circles represent cooling data and the red squares stand for heating data (cooling/heating rate 2.0 K/min). The solid line is a least square fit to the band gap insulator model below 115 K. The curves labeled $a, b \& c$ were taken as described in the text. The accuracy of the data points is better than 1% everywhere. The error does not exceed 0.8 m Ω cm anywhere. The inset shows ρ vs $1/T$ for three different cooling rates: lower curve (blue stars): $2 K/min$, middle curve (red circles): 0.2 K/min , upper curve (black pluses): infinitely slowly (explained in text). The onne
ting lines are to guide the eyes.

Figure 2: (Color online) Time dependen
e of resistivity while cooling, at various temperatures in the range 140 to 155 K, for a period of one hour. The maximum time dependence is seen at 145 K which is about 200 %. The curve at the bottom, which looks like a horizontal straight line, shows the increase in resistivity in a heating run taken at 145 K and the total change for one hour in this case is less than 0.2 %. Not all the data are shown here to avoid lutter.

while cooling is shown in Figure [2.](#page-2-1) The data are presented as $\rho(t)/\rho(t=0)$ so that the values are normalized to unity at $t = 0$ for easy comparison. We found that that below 160 K, the resistivity of the sample in
reases with time considerably. A maximum relative increase in resistivity of about 200 % for a duration of one hour is seen at 145 K, the time dependen
e being lower both above and below this temperature. We fitted the $\rho(T, t)$ curves in figure 2 to the stretched exponential function

$$
\rho(t) = \rho_0 + \rho_1 \left(1 - e^{-\left(\frac{t}{\tau}\right)^{\gamma}} \right) \tag{2}
$$

where ρ_0 , ρ_1 , τ and γ are fit parameters. The fits are quite good with the R^2 value greater than 0.999 in most cases. See Table [I.](#page-3-0) We note that the exponent γ lies in the range $0.5 < \gamma < 0.6$ and τ has a peak around 147.5 K. The variation of resistivity with time shows that the system slowly evolves towards an insulating state at a onstant temperature. We olle
ted data up to 12 hours (not shown here) to he
k whether the system rea
hes an equilibrium state, but found that it was ontinuing to relax even after su
h a long time.

The magnitude of time dependen
e in heating runs (maximum $\approx 0.2\%$) is negligible compared to what one gets in cooling runs (maximum≈ 200%) (figure [2\)](#page-2-1), which suggest that in the heating run, below T_{MI} , the sample is almost fully insulating and stable.

Figure [3](#page-3-1) compares the resistivity in a cooling run with and without intermediate aging. These data were taken as follows: we start from 220 K, ome down to 160 K at

	$\# T(K) $	ρ_1/ρ_0	τ (10 ³ s)	γ	χ^2/DOF	R^2
		1 140.0 0.764(5)		$1.52(1)$ 0.538(3)	9.5	0.99971
	2 142.5	1.89(1)	2.02(2)	0.554(2)	5.9	0.99981
	3 145.0	4.59(3)	5.05(5)	0.567(1)	0.67	0.99993
	4 147.5	3.39(6)	7.9(3)	0.568(3)	0.51	0.99978
5°	150.0	1.22(1)	4.04(6)	0.582(2)	0.0014	0.99988
6		155.0 0.391(5)	2.6(1)	0.557(7)	0.0003	0.99845

Table I: Fit parameters for the time dependen
e data shown in Figure [2.](#page-2-1) The degrees of freedom of the fits $DOF \approx 1000$. The χ^2/DOF for 150 K and 155 K are too small, indicating that we have overestimated the error in resistivity in these cases. Anyway, we note that, the R^2 values are consistently good and indicate reasonably good fits.

Figure 3: (Color online) Temperature dependence of ρ on ooling with ageing by intermediate stops of one hour ea
h (blue open circles) at 155, 150, 145, 140, 135, and 130 K. The bla
k line show the resistivity without ageing. The red line shows the results of the simulation discussed in section [IV D.](#page-6-0)

2K/min, collect time dependence data for one hour and after that resume cooling at $2 K/min$ and go down to 155 K, olle
t resistivity time dependen
e again for one hour and so on down to 110K for every 5K interval. We note that when ooling is resumed after aging for an hour, $\rho(T)$ curve merges smoothly with the curve obtained without aging within a few kelvin. A rather similar observation has been reported in the phase-separated manganite $\rm La_{0.5}Ca_{0.5}Mn_{0.95}Fe_{0.05}O_3$ $^{\circ}$

IV. DISCUSSION

We have seen that, below T_{MI} , while cooling, the system is not in equilibrium and evolves with time whi
h suggests that it is in a metastable state. Or, possibly, it onsists of at least one metastable onstituent. We infer that the resistivity of this metastable onstituent slowly increases with time which probably implies that a slow metal to insulator transition is going on in the system. On the other hand while heating up from low temperature we saw that the system remains insulating all the way up to 188 K and then it transforms to the metalli state by 200 K. The resistivity was found to have negligible time dependen
e during the whole of the heating run. This result suggests that while heating from low temperature the system is in a stable equilibrium state.

It is well known that below a phase transition temperature a high temperature phase an survive as a metastable super
ooled state. Based on this information we propose that below the M-I transition temperature, in the hysteresis region, our system onsists of super
ooled (SC) metalli regions and stable insulating regions. A supercooled metallic region would be separated from its stable insulating state by an energy barrier which can be rossed with the help of perturbations su
h as thermal fluctuations, mechanical disturbances and so on. The rossing of the barrier from the metalli state into a stable insulating state can give rise to time dependence of resistivity in the system. Now, it is known that, on cooling a supercooled system it can either switch to a stable state or get kineti
ally arrested into a glassy state. From the fact that no time dependence is observed while heating from low temperature towards the M-I transition temperature we rule out the possibility of any glassy phases forming in the system. For, if a glassy phase did form, time dependen
e would have been observed while heating from low temperature because of the de-arrest of the same. Consequently we are forced to conclude that the supercooled phases which are present while cooling would switch to the stable insulating state at a sufficiently low temperature. At a low enough temperature all of the material would be in the stable insulating state and hen
e subsequent heating will not show any time dependen
e.

Based on the fact that no time dependence is observed above the M-I transition temperature, while heating, we rule out the possibility of the existen
e of superheated phases in our system.

In the next subse
tions we get down to the nitty-gritty of the model we use to understand the experimental observations.

A. The Model

In a first order transition, a metastable SC phase can survive below the first order transition temperature (T_C) , till a certain temperature called the limit of metastability (T^*) is reached.^{3,31,32} In the temperature range $T^* \stackrel{\textstyle{<}}{<} T < T_C$ there is an energy barrier separating the SC metastable phase from the stable insulating state. The height of the energy barrier, U , can be written as $U \propto f(\overline{T} - T^*)$, where \overline{f} is a continuous and monotonic function of $(T - T^*)$, and vanishes for $T \leq T^*$. As the

temperature is lowered, at $T = T^*$, the SC metastable phase be
omes unstable and swit
hes over to the stable insulating state as the energy barrier be
omes zero in this case. 31 At $T > T^*$ the SC metastable phase can cross over to the stable insulating state with a probability (p) which is governed by the Arrhenius equation

$$
p \propto e^{-\frac{U}{k_B T}} \tag{3}
$$

which tells us that the barrier will be crossed with an ensemble average time constant $\tau \propto 1/p$. If we imagine an ensemble of such SC phases with the same barrier U , then the volume of the metastable phase will exponentially decay with a time constant τ .

A transition from a super
ooled state to a stable state is an avalan
he-like transition whi
h happens abruptly. Thus a single crystal or a crystallite, in the case of a poly
rystalline material, would remain in the SC state above its temperature of metastability, and it will swit
h to the stable state as a whole when it is pushed over the free energy barrier by an energy fluctuation or if in the pro
ess of ooling the temperature of metastability is attained. Examples for this would be the sharp M-I transitions along with hysteresis and time dependen
e observed in VO, V_2O_3 , Li and Na.^{6,17,18} It has been claimed that the presen
e of defe
ts, strains and non-stoi
hiometry an give rise to different T^* 's for different crystallites, or it $\stackrel{\circ}{\rm{max}}$ even produce regions having different $T^{*}{ }$'s inside a hay even produce regions $\frac{1}{3,33,34,35}$ We will call a crystallite or a region within a crystallite that will switch as a singe entity as a switchable region (SR) in our discussion.

Carrying forward the above arguments to our poly rystalline system, whi
h is made up of tiny rystallites, we can say that it will be made up of a large collection of SR's. Ea
h SR will have a unique temperature of metastability, T^* , and a volume, V. The energy barrier U that we discussed earlier, being an extensive quantity, will be proportional to the volume of the SR and we can write

$$
U = Vf(T - T^*)
$$
\n⁽⁴⁾

where f is the continuous and monotonic function which vanishes for non-positive values of its argument. This means that the various SR's with their different T^* and V will have different energy barriers, which implies that the time constant τ will spread out and become a distribution of time onstants depending on the distribution of the size and T^* of the \overrightarrow{SR} 's. This can give rise to the volume of the metallic state decaying in a stretched exponential manner with time.^{36,37} This behavior of the metalli volume with time will lead to the resistivity also evolving with time in a similar fashion. We shall see in the next subsection how the metallic volume and the resistivity are related to each other.

Figure 4: (Color online)Temperature variation of $V = 1-f$, the insulating volume fraction. The blue circles show the cooling cycle $(2 K/min$ cooling rate) and the red squares represent the heating cycle. The green pluses represent the insulating volume fraction for 0.2 K/min cooling rate. The dashed horizontal line with the label $V_{TH}(= 84\%$ insulating volume) represents the per
olation threshold. The inset shows the variation of $\left| dV/dT \right|$ for the cooling cycle (blue circles: cooling rate 2 K/min , and green pluses: cooling rate 0.2 K/min .

B. Volume Fraction Calculation

To check the validity of our model through numerical simulations we need to deal with the volumes of super ooled and stable phases. Our experimental measurements are of resistivity and we need to find a way of estimating the volumes of the different phases from our data. It is well known that the conductivity of a binary mixture onsisting of insulating and metalli phases depends on their respe
tive volume fra
tions, geometries, distribution, and ondu
tivities of the insulating and metalli phases(σ_I and σ_M).

We shall use an easy to use formula given by $McLachlan³⁸$ which is based on a general effective medium (GEM) theory, for doing this onversion. The McLachlan GEM equation has been successfully applied to a wide variety of isotropic, binary, macroscopic mixpercolation threshold.^{38,39,40} If σ_E is the effective electrical conductivity of a binary MI mixture, the GEM equation says

$$
(1-f)\frac{(\sigma_I^{1/t} - \sigma_E^{1/t})}{(\sigma_I^{1/t} + A\sigma_E^{1/t})} + f\frac{(\sigma_M^{1/t} - \sigma_E^{1/t})}{(\sigma_M^{1/t} + A\sigma_E^{1/t})} = 0 \qquad (5)
$$

where f is the volume fraction of the metallic phases and

 $A = (1 - f_c)/f_c$, f_c being the volume fraction of metallic phases at the percolation threshold, and t is a critical exponent which is close to 2 in three dimensions.^{39,41} The constant f_c depends on the lattice dimensionality, and for 3D its value is 0.16.42

In order to calculate the volume fraction of metallic and insulating phases from Equation [\(5\)](#page-4-0), we need their respective resistivities ρ_M and ρ_I as functions of temperature. $\rho_M(T)$ was obtained using $\rho_M = \rho_0 + \beta T$, where β is the temperature coefficient of resistivity estimated from the resistivity data above the M-I transition. $\rho_I(T)$ was calculated using Equation [\(1\)](#page-1-0) with the parameters obtained by fitting the resistivity data below 115 K. Using the above information and the resistivity data of the major loop shown in Figure [1,](#page-2-0) we calculated the volume fraction of metallic and insulating phases and it is shown in Figure [4.](#page-4-1) In the cooling cycle the volume fraction of the insulating phases $(V = 1 - f)$ slowly increases on decreasing the temperature below T_{MI} , while in the heating y
le it remains nearly onstant up to about 185 K, and then drops to zero by 200 K. As an be seen from Figure [4](#page-4-1) the percolation threshold for the cooling runs occurs at around 144 K. Below this temperature there will be no ontinuous metalli paths in the system.

Figure [5](#page-5-0) displays the in
rement of insulating volume fraction, $\Delta V(exp)$, as a function of time that has been extracted from the time dependent resistivity data of Figure [2.](#page-2-1) We see that the maximum time dependen
e in volume fraction is seen at 147.5 K which is not the same temperature at whi
h the maximum time dependen
e in resistivity is seen. It is interesting to note that the rate of change of metallic volume fraction, $\left| dV/dT \right|$, has a maximum around 147.5 K in the ooling runs (inset of Figure [4\)](#page-4-1) and it oin
ides with the temperature of the maximum volume time dependen
e.

During cooling $\left| dV/dT \right|$ of the inset of Figure [4](#page-4-1) represents the amount of volume that will hange from the super
ooled metalli to the insulating state for a unit temperature hange. Now a small hange in temperature from T to $T - \delta T$ will result in all the supercooled SR's with their T^* falling in that temperature range switching to the insulating state from the super
ooled state. This means that $\frac{dV}{dT}$ δT at T is a good measure of the volume fra
tion of super
ooled metastable regions whi
h have their T^* close to T within a temperature range δT . Thus $|dV/dT|$ of the cooling curve represents the volume $\operatorname{distribution}$ of $T^{*\text{'s}}$ in the system. In coming to the above on
lusion we have disregarded the small fra
tion of SR's that would be switching due to the time elapsed in covering the small temperature change. The justification for this is the fact that the $\left| dV/dT \right|$ values calculated from the $2 K/min$ and $0.2 K/min$ cooling curves are practically indistinguishable as an be seen from the inset of Figure $\overline{4}$.

Figure 5: (Color online) ΔV vs time for 140 K to 155 K. The gray symbols show the values derived from experiments and the bla
k lines show the simulated values. The inset shows how the parameter a depends on temperature. The red lines indicate the values we have chosen for the simulation.

C. Details of the Simulation

We arried out Monte Carlo simulations to try to understand the experimental data. We take a distribution of 10^5 SR's which have their volumes (V) uniformly distributed in a certain range (V_0, V_{max}) . These SR's were assigned a T^* in such a way that the volume distribution of the supercooled metallic SR's matches with the $|dV/dT|$ curve shown in the inset of Figure [4.](#page-4-1) These metalli SR's have an energy barrier given by Equation [\(4\)](#page-4-2) that separates them from the insulating equilibrium state. Now we assume that $f(T - T^*)$ has the simple power law form $f = c(T - T^*)^{\alpha}$ for $T > T^*$, where c and α are positive constants, and $f = 0$ for $T \leq T^*$. Using Equation [3,](#page-4-3) at any given temperature, the probability of swit
hing from the metalli to the insulating state in a ertain time interval is taken to be

$$
p = e^{-aV\frac{f(T - T^*)}{T}}
$$
 (6)

with $a = c/k_B$ ⁴³

Now to arry forward the simulation we have to estimate the parameters V_0 , V_{max} , a, and α . We decided to first simulate the time dependence of the insulating volume evolution shown in Figure [5](#page-5-0) for this purpose. The time dependen
e of the insulating volume is generated as follows. To begin with we quen
h the simulated sample from above T_{MI} to the temperature of interest. In this process all the SR's which have their T^* 's above the temperature of interest are swit
hed from the metalli to

the insulating state. Now the swit
hing probability of ea
h of the remaining metalli SR's is ompared with a uniform random number in the interval [0,1) and if the swit
hing probability is greater than the random number, the metallic SR is flipped to the insulating state and the increase in the insulating volume fraction is recorded. This operation is carried out for each one of the metallic SR's. The time required for this process is taken to be the time interval at whi
h the experimental data was recorded, which in our case is 3.6 seconds. We repeat this process one thousand (n) times to generate data for one hour whi
h is the time over whi
h the experimental data was collected. The parameter space of V_0 , V_{max} , a, and α was searched to minimize the error function

$$
Err(V_0, V_{max}, a, \alpha) = \sum_{i=0}^{n} |(\Delta V(exp)_i - \Delta V(cal)_i)|
$$
\n(7)

where $\Delta V(exp)_i$ is the increase in insulating volume fraction obtained from experimental data, $\Delta V (cal)_i$ is the inrease in insulating volume fra
tion al
ulated from the simulation and the subscript i stands for the number of the time step. We found that as far as the volume of the SR's are concerned it is the ratio of V_{max} to V_0 that decides the minimum value of $Err(V_0, V_{max}, a, \alpha)$ and not the individual values. So we fixed V_0 to be equal to unity and found that overall $V_{max} \approx 6$ and $\alpha \approx 0.25$ gave the best values for the error function with parameter a lying in the range 270 to 400 depending on the temperature. We refined the simulation by fixing the values of V_{max} to be 6 and α to be 0.25 and varying only a. We compare in Figure [5](#page-5-0) the experimental data (gray symbols) and the simulation (bla
k lines) and see that the simulation reproduces the experimental data quite closely. In the inset of the figure we show how the parameter a varies with temperature.⁴⁴ For further calculations we fixed the value of a to be 280 up to 146 K and above that temperature a was taken to vary linearly with temperature as $a = 280 + 14(T - 146)$ and this is shown as red lines in the inset of Figure [5.](#page-5-0)

It would have been ideal if all the parameters of the simulation turned out to be constants. But we find that we have to introdu
e some temperature dependen
e in a to simulate the experimental results accurately. The temperature dependence of a could possibly be related to the per
olation threshold whi
h is at 144 K. Below this temperature the ba
kground matrix for most of the SR's would be insulating while above this temperature the ba
kground would gradually hange to a metalli one as one goes away from the per
olation threshold. We also note that an SR in its insulating state would have a slightly more distorted crystal structure along with a somewhat larger volume. Thus we see that the surroundings of an SR would be very different above and below 144 K and this may have a bearing on the energy barrier the SR has to cross and this could result in a temperature dependent a.

In the simulation we quen
h the sample from above T_{MI} to the temperature of interest while in the experiment the sample is cooled at a fixed cooling rate $(2 K/min)$ to the temperature of interest. In the simulation we an ool the sample slowly only if we know the parameters, and sin
e we have no idea of the parameters to begin with, as a way out we de
ided to quen
h the sample. As we shall see soon, the simulation and the experimental data agree quite well for the other experiments and hence it was felt that further refining of the simulation parameters would not improve the simulation very mu
h and hen
e we de
ided to sti
k with the parameters obtained by quen
hing.

D. Simulation Results

We will now describe the simulation results on resistivity hysteresis and minor loops, ooling rate dependen
e and rejuvenation.

1. Hysteresis and Minor Loops in Resistivity

Hysteresis and minor loops in resistivity are calculated by first simulating how the insulating volume evolves as one ools and heats the (simulated) sample. The ooling was done by lowering the temperature by 0.12 K first, during which process all those SR's with their T^* in that 0.12 K range are swit
hed to the insulating state, followed by a time step of 3.6 seconds, during which all the remaining metalli SR's are given a han
e to relax to the insulating state. We consider the above procedure to be a good approximation for cooling at a rate of $2 K/min$. This process is repeated as many times as required to omplete the ooling part of the simulation. In the heating part of the simulation we again take temperature steps and time steps as before. But it may be noted that a temperature step while heating will not swit
h any of the SR's to the insulating state be
ause all those SR's with T^* 's falling inside the temperature step would have already been swit
hed to the insulating state during the pre
eding ooling pro
ess. During a time step all of the metalli SR's do get a han
e to swit
h their states, but we point out that during heating the chance of a metallic SR switching to the insulating state would decrease drastically with increasing temperature because the energy barrier is a monotonically increasing function of $T - \widetilde{T}^*$ and all the remaining metallic SR's would have their T^* below the turning point, *i.e.*, the temperature at which the ooling was stopped and heating started. After the volume simulation is ompleted we translate the results ba
k to resistivity using Equation [\(5\)](#page-4-0).

In Figure [6](#page-7-0) we show the simulated results for hysteresis and minor loops and we note that they are very similar to the experimental results shown in Figure [1](#page-2-0) ex
ept for the sharp transition in the simulation during heating. This can be attributed to the fact that we have not taken into

Figure 6: (Color online) Simulated results for the hysteresis along with minor loops. The labeling and color coding are the same as in Figure [1.](#page-2-0) Cooling rate dependen
e of resistivity is shown in the inset where the symbols represent the experimental data and the lines are from simulation. Blue star and blue line: $2 K/min$, red circles and red line: $0.2 K/min$, black $line: 1 K/hour simulation, black pluses: infinitely slow cooling$ rate, estimated from experiment.

account the broadening of the M-I transition due to disorder and finite size effects in our simulation. It is interesting to note that the simulated minor loops reprodu
e quite losely some of the features of the experimental loops su
h as the positive slope of the heating (top) part of loop a and the negative slope at the beginning of the heating part of loop c . The heating part of curve a has a positive slope be
ause in this ase most of the SR's are in their insulating state and the temperature dependen
e of their resistivity is the dominating factor which determines its behavior. On the other hand the beginning of the heating part of curve c has a negative slope because in this ase most of SR's are in the metastable metalli state and the in
rease of their resistivity with time is the dominating fa
tor here.

2. Cooling Rate Dependen
e

Simulating the ooling rate dependen
e is straightforward. The time steps were fixed at 3.6 seconds and the temperature steps were adjusted in size to simulate faster or slower ooling. The results are shown in the inset of Figure [6.](#page-7-0) It is lear that the experimental data and the simulation agree very well for 0.2 K/min and 2 K/min ooling rates. We have also shown the simulation result for $1K$ /hour cooling rate and it is seen to fall in between

the $2 K/min$ data and the infinitely slow data. It is easy to see that a slower ooling rate will result in a higher resistivity be
ause more of the SR's swit
h to the insulating state during slow ooling thus resulting in a higher resistivity.

3. Intermediate Ageing

Intermediate ageing is also fairly easy to simulate. We cool the simulated sample at $2 K/min$ to the temperature of interest, do one thousand time steps to simulate waiting for one hour, and resume cooling and so on. In the inset of Figure [3](#page-3-1) we have shown the simulation results for intermediate ageing and we see that the agreement between data and simulation is reasonable.

From Figure [3](#page-3-1) it is clear that on resuming cooling after an intermediate stop of one hour the cooling curve merges with the curve obtained without ageing within about $3K$ or less. When we stop the ooling and age the sample at a fixed temperature the supercooled metallic SR's with relatively small U will switch over to the insulating state. As an be inferred from Equation [\(4\)](#page-4-2) those SR's will have a small U which have (i) their metastability temperature (T^*) close to their temperature (T) (ii) a small size. The major contributions to resistivity change will come from the relatively larger SR's making the transition from the metallic state to the insulating state. In the light of this the merger of the cooling curves with and without ageing within a small temperature change of about $3K$ means that most of the larger SR's whi
h undergo the transition from metal to insulator during ageing have their T^* within a few kelvin of the temperature of the sample.

E. Predi
tive Power of the Model

A model is no good if it annot predi
t new results. So to test our model we decided to do a simulation first and then see whether experiment will reprodu
e it. In the simulation we os
illate the temperature of the sample between 145 K and 146 K for one hour immediately after cooling it from $220 K$ to $145 K$. All temperature variations were done at $2 K/min$. Figure [7\(](#page-8-10)a) shows the results of the simulation. We see that the resistivity keeps on in creasing on repeated thermal cycling; the increase per cycle is larger at the beginning and slowly it tapers off. We repeated the simulation on the heating cycle also, cooling the sample first from 220 K down to 85 K and then bringing it ba
k up to 145 K before starting the temperature os
illations. No dete
table hange in resistivity was seen with thermal cycling.

We expected that during the cooling cycle the temperature os
illations would disturb the sample and we would get a larger in
rease in resistivity than if the temperature were kept fixed at 145 K. See Figure [2.](#page-2-1) But instead, we find intriguingly, that the increase in resistivity while osillating the temperature is onsiderably less than what

Figure 7: (a) shows the simulation results of how the resistivity evolves if the temperature of the sample is os
illated between 145 K and 146 K for one hour after cooling from above T_{MI} . ρ_0 is the resistivity of the sample when it reaches 145 K after ooling from 220 K at 2 K/min. The arrows indi
ate that the resistivity keeps on increasing on thermal cycling. (b) shows the experimental results for the same.

one gets at the onstant temperature of 145 K. Even more surprisingly it is less than that observed at 147.5 K. It will be very interesting to see if experiment agrees with this predi
tion.

In Figure [7\(](#page-8-10)b) we show the experimental results obtained during thermal cycling after cooling the sample from 205 K. One can see that the agreement between the simulation and the experiment is very good. We repeated the thermal cycling after cooling the sample down to 85 K and bringing the temperature ba
k up to 145 K, just as in the simulation. Here also the experiment agreed very well with the simulation; no detectable change in resistivity was found.

The unexpectedly lower resistance rise when the temperature is os
illated after ooling an be attributed to (1) the smaller number of SR's available for swit
hing because all those SR's with T^* falling in the range 145 $\breve{\text{K}}$ to 146 K would have already swit
hed to the stable insulating state the first time the temperature was lowered

to 145 K and (2) a higher average barrier height whi
h an SR has to over
ome, be
ause the barrier height goes as $(T - T^*)^{\alpha}$.

CONCLUSION V.

Our experimental results and its ex
ellent agreement with the simulation suggests strongly that while cooling the physical state of $NdNiO₃$ is phase separated below the M-I transition temperature; the phase separated state onsists of SC metalli and insulating regions. A metastable metallic region switches from the metallic to the insulating state sto
hasti
ally depending on the loseness of the temperature of metastability and the size of the region. At low temperature, below 115 K or so, the system is insulating, all the SR's having swit
hed over to the insulating state. While heating the SR's remain in the stable insulating state till the M-I transition temperature is rea
hed and then swit
h over to the metalli state.

In our study we have developed a physi
al explanation of the time dependence effects observed in $NdNiO₃$ based on phase separation and super
ooling. We believe that the physics developed here may have implications for first order solid-solid phase transitions in general. We have shown that our model has predictive power and we feel that it may serve as a useful template for understanding slow dynamics in hard condensed matter in such cases where there is phase separation. The apparently counter intuitive simulation prediction in the temperature oscillation experiment and its experimental confirmation gives us confidence that our model has captured the underlying physi
s of the problem truthfully.

A
knowledgments

DK thanks the University Grants Commission of India for financial support. KPR and DK thank Prof V. Subrahmaniam for useful discussions regarding the simulation. JAA and MJM-L a
knowledge the Spanish Ministry of Education for funding the Project MAT2007-60536

- * Electronic address: kpraj@iitk.ac.in
- ¹ L. Zhang, C. Israel, A. Biswas, R. L. Greene, and A. de Lozanne, Science 298, 805 (2002).
- ² M. M. Qazilbash, M. Brehm, Byung-Gyu Chae, P.-C. Ho, G. O. Andreev, Bong-Jun Kim, Sun Jin Yun, A. V. Balatsky, M. B. Maple, F. Keilmann, Hyun-Tak Kim, and D. N. Basov, Science 318, 1750 (2007).
- ³ P. Chaddah, [ond-mat/0109310v](http://arxiv.org/abs/cond-mat/0109310)1.
- ⁴ E. Dagotto, Nanos
ale phase separation and Colossal Magnetoresistan
e (Springer, Berlin, 2002).
- ⁵ L. M. Stadler, B. Sepiol, J. W. Kantelhardt, I. Zizak, G. Grúbel, and G. Vogl, Phys. Rev. B 69, 224301 (2004).
- ⁶ F. J. Morin, Phys. Rev. Lett. 3, 34 (1959).
- ⁷ X. J. Chen, H.-U. Habermeier, and C. C. Almasan, Phys. Rev. B 68, 132407 (2003).
- ⁸ P. Levy, F. Parisi, L. Granja, E. Indeli
ato, and G. Polla, Phys. Rev. Lett. 89, 137001 (2002).
- \sim X. Granados, J. Fontcuberta, X. Obradors, and J. B. Tor-
- ¹⁰ J. Wu, H. Zheng, J. F. Mitchell, and C. Leighton, Phys. Rev. B 73, 020404(R) (2006).
- ⁻⁻ P. Chaddah, Kranti Kumar, and A. Banerjee, Phys. Rev. B 77, 100402 (2008).
- ¹² L. Ghivelder, and F. Parisi, Phys. Rev. B 71, 184425

(2005).

- ¹³ F. Rivadulla, M. A. López-Quintela, and J. Rivas, Phys. Rev. Lett. 93, 167206 (2004).
- ¹⁴ L. M. Fis
her, A. V. Kalinov, I. F. Voloshin, N. A. Babushkina, D. I. Khomskii, Y. Zhang, and T. T. M. Palstra, Phys. Rev. B 70, 212411 (2004).
- ¹⁵ M. K. Chattopadhyay, S. B. Roy, and P. Chaddah, Phys. Rev. B 72, 180401 (2005).
- ¹⁶ M. Uehara and S.-W. Cheong, Europhys. Lett. 52, 674 (2000) .
- \pm H. G. Smith, Phys. Rev. Lett. 58, 1228 (1987).
- ¹⁸ H. Abe, K. Ohshima, T. Suzuki, S. Hoshino, and K. Kakurai, Phys. Rev. B 49, 3739 (1994).
- ¹⁹ X. Granados, J. Font
uberta, X. Obradors, Ll. Mañosa and J. B. Torran
e, Phys. Rev. B 48, 11 666 (1993).
- ²⁰ R. Mallik, E. V. Sampathkumaran, J. A. Alonso, and M. J. Martínez- Lope, J. Phys.: Condens. Matter 10, 3969
- 21 Devendra Kumar, K.P. Rajeev, J. A. Alonso, M. J. Martínez-Lope, J. Phys.: Conf. Ser. (Accepted). Also [arXiv:0712.3990](http://arxiv.org/abs/0712.3990)
- ²² M. L. Medarde, J. Phys.: Condens. Matter 9, 1679 (1997).
- ²³ P. La
orre, J. B. Torran
e, J. Pannetier, A. I. Nazzal, P. W. Wang, and T. C. Huang, J. Solid State Chem. 91, 225 (1991) .
- ²⁴ J. A. Alonso, J. L. García-Munõz, M. T. Fernández-Díaz, M. A. G. Aranda, M. J. Martínez- Lope, and M. T. Casais, Phys. Rev Lett. 82, 3871 (1999).
- ²⁵ J. A. Alonso, M. J. Martínez- Lope, M. T. Casais, J. L. Gar
ía-Munõz, M. T. Fernández-Díaz, Phys. Rev. B 61, 1756 (2000). 1756 (2000).
- ²⁶ S.-J. Kim, G. Demazeau, I. Presniakov, K. Pokholok, A. Baranov, A. Sobolev, D. Pankratov, and N. Ovanesyan, Phys. Rev. B 66, 014427 (2002).
- ²⁷ T. Mizokawa, D. I. Khomskii, and G. A. Sawatzky, Phys. Rev. B 61, 11263 (2000).
- ²⁸ U. Staub, G. I. Meijer, F. Fauth, R. Allenspa
h, J. G. Bednorz, J. Karpinski, S. M. Kazakov, L. Paolasini, and

F.d' A
apito, Phys. Rev Lett. 88, 126402 (2002).

- - -J. B. Torran
e, P. La
orre, A. I. Nazzal, E. J. Ansaldo, and Ch. Niedermayer, Phys. Rev. B 45, 8209 (1992).
- ³⁰ N. E. Massa, J. A. Alonso, M. J. Martínez-Lope, I. Rasines, Phys. Rev. B 56, 986 (1997).
- ³¹ P. M. Chaikin and T. C. Lubensky, Prin
iples of Condensed Matter Physi
s (Cambridge University Press 1998) hapter 4.
- ³² P. Chaddah, and S. B. Roy, Phys. Rev. B 60, 11926 (1999).
- E. Dagotto, Science 309, 257 (2005).
- \sim Y. Imry, and M. Wortis, Phys. Rev. B 19, 3580 (1979).
- ³⁵ A. Soibel, E. Zeldov, M. Rappaport, Y. Myasoedov, T. Tamegai, S. Ooi, M. Kon
zykowski, V. B. Geshkenbein, Nature 406, 282 (2000).
- R. G. Palmer, D. L. Stein, E. Abrahams and P. W. Anderson, Phys. Rev Lett. 53, 958 (1984).
- ³⁷ M. D. Ediger, C. A. Angell, Sidney R. Nagel, J. Phys. Chem. 100, 13200 (1996).
- ⁻⁻ D. S. McLachian, J. Phys. C 20, 865 (1987).
- G. Hurvits, R. Rosenbaum, and D. S. McLachlan, J. Appl. Phys. 73, 7441 (1993).
- \sim K. H. Kim, M. Uehara, C. Hess, P. A. Sharma, and S-W. Cheong, Phys. Rev Lett. 84, 2961 (2000).
- 41 H. J. Herrmann, B. Derrida, and J. Vannimenus, Phys.
- $R⁴²$ A. L. Efros, Physics and Geometry of Disorder Percolation
- ⁴³ The time interval referred to here is 3.6 seconds which is the time step used in the simulation. Please note that the parameters we would be extracting by minimizing the error fun
tion in Equation [7](#page-6-1) not only depend on the sample
- With $a = 280 \text{ K}^{0.75}/(\mu \text{m})^3$ and taking T − T^* to be 1 K, the height of the energy barrier for a $1 \mu m^3$ sized SR turns out to be 24 meV. At 145 K this SR would ip, on an average, in 7 se
onds and this looks a very reasonable number.