Ferromagnetism in the Extended Periodic Anderson Model Near Selective Mott Localization.

M.S. Laad

Max-Planck-Institut für Physik Komplexer Systeme, 01187 Dresden, Germany

(Dated: November 6, 2018)

Motivated by the experimental finding of Ferromagnetism (FM) near non-FL quantum phase transitions (QPT), I investigate FM in an Extended Periodic Anderson Model (EPAM). Using the Frobenius-Perron theorem, a FM *metallic* phase near the selective Mott localization is rigorously found. Interesting connections with Tasaki's flat-band ferromagnetism, as well as with the well-known double exchange (DE) mechanism are elucidated. This finding is a higher dimensional generalization of numerical work on the D = 1 PAM, and constitutes a robust way to FM metallic behavior in D > 1. Finally, we discuss a concrete manifestation of our results to UGe_2 .

PACS numbers:

Itinerant Ferromagnetism (FM) in solids is a longstanding topic of interest in condensed matter physics. Progress in understanding FM had to await the quantum revolution. FM is a quintessentially quantum phenomenon, and has spurred intense theoretical efforts [1]: the problem is subtle, mandating a careful treatment of the interplay between kinetic energy gain (by delocalization) and potential energy gain (by localization). We recall that precisely the same interplay underpins another core issue of correlation-driven metal-insulator transitions in d-band compounds [2]. The connections between the two phenomena, and the resulting set(s) of conditions under which FM is possible in appropriate model Hamiltonians are of enduring interest. Ingenious schemes have been constructed [3, 4, 5] in this context. Tasaki's review summarizes the extensive study conducted over the years to find FM in *fermionic* models. In *real* materials, orbital degeneracy is considered to be essential for stable FM phases, where the so-called *double exchange* (DE) mechanism operates [6].

In contrast to *d*-band systems, FM in *f*-band materials has been scantily addressed. Most conclusions are obtained from numerical studies [7, 8], apart from Sigrist's FM in the J >> t Kondo lattice in D = 1. In principle, the existence of narrow-band f electrons and wide-band c-electrons hybridized with each other in an interacting model, the Periodic Anderson Model (PAM), should favor FM, given its similarity to multi-orbital models, where one can easily escape Pauli exclusion restrictions, except close to half-filling. Strong correlations in the narrow f-band could Mott-localize the f-electrons, creating local moments, and, with a partially filled c-band electrons interacting with f-moments, a DE-like mechanism could give a FM metallic state. Whether FM can arise without rigorous Mott localization of the f electrons is more subtle. Nor is the issue purely of academic interest [9, 10]. In f-band systems, sizable f - c hybridization is always present, and the f-electrons cannot be viewed as localized in a strict sense.

Here, I address the possibility of unearthing a FM

metallic phase in an extended PAM (christened EPAM) containing a finite f - f hopping, t_f , an extended f - chybridization, V_{fc} , and a direct f - c interaction, U_{fc} , in addition to the usual PAM. Hence, the f-electrons are never rigorously localized. Naively, one might associate this with a renormalized itinerant picture at low energies. However, as shown earlier [11, 12], a peculiar interference arising from interplay between $t_{f,c}$, V_{fc} and U_{fc} can destroy the heavy FL state. Given that this nFL metal is an unstable fixed point, one, or more broken symmetry phases will pre-empt it at lower T. How might this happen? Is it possible to study this issue, as rigorously as possible?

I start with the Hamiltonian, $H = H_0 + H_1$, with

$$H_0 = t_f \sum_{\langle i,j \rangle,\sigma} f^{\dagger}_{i\sigma} f_{j\sigma} + t_c \sum_{\langle i,j \rangle,\sigma} c^{\dagger}_{i\sigma} c_{j\sigma} + V_{fc} \sum_{\langle i,j \rangle,\sigma} f^{\dagger}_{i\sigma} c_{j\sigma}$$
(1)

and

Following earlier work [11, 12], I take:

(i) $V_{fc1} = \sqrt{t_c t_f}$ and $U_{ff} = \infty$.

(ii) I choose ϵ_f to lie close to the bottom of the *c*-band to begin with: this condition will be made more precise below. It could be relaxed later. But the exact argument goes through for this specific case, in what follows.

(iii) the *total* band-filling, $n = n_c + n_f$, is chosen such that $\epsilon_f = E_F$.

Under these conditions, in an earlier work, I have studied the selective Mott QCP in f-band systems, and applied it to attempt an understanding of the singular non-FL metallic behavior in $YbRh_2Si_2$. Remarkably, it will turn out that exactly these same conditions (but now with the additional condition (ii)) will be required for proving that the ferromagnetic metallic state is the rigorous, unique ground state of the EPAM for a critical, finite density. To diagonalize H_0 , but with $U_{ff} = \infty$, I introduce the combinations $a_{i\sigma} = uX_{if\sigma} + vc_{i\sigma}, b_{i\sigma} = vX_{if\sigma} - uc_{i\sigma}$, with $u^2 = t_f/t, v = t_c/t$ and the $X_{if\sigma} = (1 - n_{if,-\sigma})f_{i\sigma}$ are projected fermion operators satisfying $[X_{if\sigma}, X_{jf\sigma'}^{\dagger}]_+ = \delta_{ij}\delta_{\sigma\sigma'}(1 - n_{if,-\sigma})$. Also, $t = (t_c + t_f)$. In terms of these, H becomes the spin S = 1/2 Falicov-Kimball model (FKM) with a *local* a - b hybridization:

$$H_{FKM} = t \sum_{\langle i,j \rangle,\sigma} (a_{i\sigma}^{\dagger} a_{j\sigma} + h.c) + U_{fc} \sum_{i} n_{ia} n_{ib} \quad (3)$$

and

$$H_{hyb} = (\epsilon_f - E_F) \sum_{i,\sigma} (n_{ia} + n_{ib} + a^{\dagger}_{i\sigma} b_{i\sigma} + h.c) \qquad (4)$$

and at $\epsilon_f = E_F$, I recover H_{FKM} with $U_{ff} = \infty$. In general, for arbitrary V_{fc} and ϵ_f , inter- and intra-site a-b hybridization terms supplement H_{FKM} above. Obviously, both H and the effective H_{FKM} commute with $both S_{total}^z$ and S_{total}^2 . However, pseudospin $(\tau^+ = X_{f\sigma}^{\dagger}c_{\sigma}, \tau^- = c_{\sigma}^{\dagger}X_{f\sigma}, \tau^z = (n_{Xf\sigma} - n_{c\sigma})/2)$ SU(2) invariance is explicitly broken, as is manifest in the form of H_{FKM} . We also notice that the term $U_{ff}n_{f\uparrow}n_{f\downarrow}$ transforms to $U_{ff}[u^4n_{a\uparrow}n_{a\downarrow} + v^4n_{b\uparrow}n_{b\downarrow} + u^2v^2\sum_{\sigma}n_{a\sigma}n_{b,-\sigma}]$ in the a-b basis. This implies that both the a- and b-states are singly occupied and the $(a\sigma, b-\sigma)$ local configuration is forbid-den.

At V_{fc1} and $\epsilon_f = E_F$, the rigorous, local U(1) invariance of H_{FKM} implies, by Elitzur's theorem [13], that the "excitonic" average, $\Delta_{ab} = \langle (a_{i\sigma}^{\dagger}b_{i\sigma} + h.c) \rangle = 0.$ This gives $\Delta_{cf} = \langle (X_{if\sigma}^{\dagger} c_{i\sigma} + h.c) \rangle = -(2V_{fc1}/(t_c - t_{cc}))$ (t_f) $\langle (n_{ic\sigma} - n_{if\sigma}) \rangle$. Also, using this relation, $\langle (n_{ia\sigma} - n_{if\sigma}) \rangle$. $(n_{ib\sigma})\rangle = ((t_c + t_f)/2V_{fc1})\langle (X_{if\sigma}^{\dagger}c_{i\sigma} + h.c)\rangle$. Hence, in the original EPAM, the selective Mott localization actually corresponds to a *finite* "excitonic" average, $\Delta_{cf} =$ $\langle (X_{if\sigma}^{\dagger}c_{i\sigma}+h.c)\rangle = (2V_{fc1}/t)\langle (n_{ia\sigma}-n_{ib\sigma})\rangle$, or a finite $\langle \tau_i^x \rangle$. These relations also show that $\Delta_{cf} = 0$ for $V_{fc} = 0$ in the EPAM, in agreement with *exact* arguments ruling out excitonic order in the FKM (spin is irrelevant for Δ_{cf}). This would imply electronic ferroelectricity [14] (EFE). Thus, the selective metal supports ferro-excitonic order, an intriguing result. Physically, the fact that the bfermions rigorously localize aids in formation of local electronic polarization, $\langle \mathbf{P}_i \rangle = -e\mathbf{r}_i \langle (X_{if\sigma}^{\dagger} c_{i\sigma} + h.c) \rangle \propto \langle \tau_i^x \rangle$, co-existing with metallic behavior.

How about FM? First consider the EPAM at a chosen filling, $n = n_c + n_f = n_1 = n_b + 1 \neq 1$ per site: i.e, the *b*-levels are singly occupied (with $U_{ff} = \infty$), and there is a *single* additional electron in the dispersive *a* band. In the original EPAM, one has a *partially* filled case. The itinerant *c*-fermions fill up available Bloch states, and, when $\epsilon_f = E_F$, the much narrower *f*-band states are progressively filled. Since $U_{ff} = \infty$, one has either singlyoccupied or empty *f* states. In the "rotated" FKM, the problem (recollect that, with the f-band at the bottom of the c-band, the effective FKM has the b-band also lying at the bottom of the a band) is now reduced to that of a band of localized b fermions, interacting with the single, itinerant a-fermion via U_{fc} . Moreover, the connectivity condition is always satisfied on most "simple" lattice structures (see Tasaki's review for a precise characterization), and, with nearest neighbor hopping, now solely of the a-fermion, any state can be reached from any other by repeatedly applying H. These are precisely the set of conditions under which the Frobenius Perron theorem [15] can be exploited for showing FM. This is what we now show.

Consider a large but finite-sized system of NIn the a - b basis, for an arbitrary sites. configuration of the *localized* b-fermions, $|\alpha_b\rangle$ = $|\sigma_{b1}, \sigma_{b2}, ..., \sigma_{b,i-1}, h_{i,\sigma}, \sigma_{b,i+1}, ..., \sigma_{bN}\rangle$ with a single *elec*tron, now necessarily in the a-orbital at site i, we have $H_{ij} = \langle i | H_{FKM} | j \rangle = t$ for |i - j| = 1, and zero otherwise. The finite (spin-independent) U_{fc} only adds diagonal entries in H_{ij} in the a - b basis, since, with immobile bfermions, it acts like a one-body scattering potential for the *a*-fermion. Since $|\alpha_b\rangle$ contains eigenstates of S_{total}^z but not S_{total}^2 , the Hilbert space is separable into sectors with fixed S_{total}^z . In each S_{total}^z sector, H_{ij} has z non-zero entries in each row (and column). Clearly, the connectivity condition [15] is satisfied in our case. If t is chosen positive, the Frobenius-Perron (FP) theorem implies that the *nodeless* eigenvector has positive eigenvalue, $E_{max} = zt$, and is non-degenerate, which is the ground state (GS). Since there is no other orthogonal eigenstate having all co-efficients positive, this GS is unique. This state clearly has $S_{total}^{z} = S_{max}$, and, since $[H, S_{total}^{2}] = 0$, the state with $S_{total}^{2} = S_{max}(S_{max} + 1)$ turns out to have the same energy in each S_{total}^{z} -sector. Since the (nodeless) state with $E_{max} = zt$ is the unique GS in each S^z_{total} sector, it must have the same $S_{total}^2 = S_{max}(S_{max} + 1)$. The GS is thus *ferromagnetic*. Moreover, with arbitrary band-filling, $n = n_a + n_b < 1$, it is also metallic. Notice that the proof only implies a FM GS in the sense that its spin is an extensive quantity (scaling with N, the number of sites). It does not describe its structure, since the proof tells us nothing about the spin-spin correlation function, e.g, $\chi_{ij} = \langle S_i^z S_j^z \rangle$.

This FM is a special case of Tasaki's flat-band FM in the EPAM at the selective Mott point. It can also be interpreted in the "double exchange" (DE) sense: since $U_{ff} = \infty$, the *b-spin* configuration is composed of a large number of degenerate, arbitrary spin configurations. Since the hopping (necessarily of the *a*-hole) is independent of spin, maximum kinetic energy gain occurs when the "background", localized *b*-spins are ferromagnetically polarized. Also, with large U_{ff} , it is energetically unfavorable (actually, with $U_b = U_{ff}(t_f/t)^2 = \infty$ in H_{FKM} , this is forbidden) to have the $a \uparrow, b \downarrow$ local configuration, again stabilizing the FMM state. Since *f*-electrons are never strictly localized, (only $b_{\sigma} = (vX_{f\sigma} - uc_{\sigma})$ is "localized" (SMT)), the analogy with DE is only a formal mathematical one. Thus, our proof is a demonstration of *itinerant* FM in the EPAM. Further, $n_1 = n_b + 1 = n_f + n_c$ implies finite itinerant (c) electron density in the original EPAM.

This means that, under the conditions on the parameters as chosen above, a ferromagnetic metallic state is the rigorous ground state of the EPAM at finite electron density.

This is, to my knowledge, the *first* rigorous demonstration of a FMM ground state in the *finite density* EPAM. In previous work [11, 12], I have shown how selective Mott localization drives non-FL behavior in the uniform phase of the EPAM. Since the *b*-fermions are rigorously localized for $V_{fc1}, \epsilon_f = E_F$, a finite U_{fc} produces strong resonant scattering between locally degenerate configurations with $n_b = 0, 1$, i.e., produces singular *b*-fermion "valence" fluctuations. In the DMFT [12], this gives rise to infra-red singularities in the local response functions, as a consequence of the Anderson orthogonality catastrophe (AOC), and the symmetry unbroken metallic state is a non-FL metal. Notice, however, that the AOC will occur in the symmetry-unbroken metallic phase of H in any D at this special point, and so this conclusion should survive beyond DMFT. In this selective-Mott (non-FL) state the local *b*-fermion and "excitonic" (a - b) correlators show *branch cut* structure instead of a renormalized pole structure, characteristic of *local* quantum critical behavior: [11, 12]

 $\rho_{bb}(\omega) \simeq \theta(\omega) |\omega|^{-(1-\eta)}$ (5)

and

$$\chi_{ab}"(\omega) \simeq \theta(\omega) |\omega|^{-(2\eta - \eta^2)} \tag{6}$$

with $\eta = (\delta/\pi)^2$, and $\delta = \tan^{-1}(U_{fc}/W)$ is the unrenormalizable scattering phase shift in the impurity version of H_{FKM} . Thus, the nFL state is characterized by soft, interband excitons, and coupling of fermionic quasiparticles to these soft excitons destroys FL behavior. Interestingly, it turns out that, for $U_{ff} = \infty$, this nFL state is unstable to a FM metal (FMM).

How stable are these states to changes in V_{fc} , ϵ_f ? For $V_{fc} \neq V_{fc1}$ or $\epsilon_f = E_F$, either an inter- or intra-site hybridization term is added to H_{FKM} . Diagonalizing the bilinear part of the resulting H, two bands, one with dominant a(c) character with large width, and the second with dominant b(f) character and narrow width, are obtained. Such models have been solved both within DMFT(QMC) [16] and large lattice-size QMC [7] calculatons. In both, a robust FMM phase is obtained over a range of band-fillings. Also interesting in this context is the work of Biermann *et al.* [17], where a non-FL state

is found to be unstable to a FMM state at lower T. The nFL phase is presumably caused by the AOC in their two-orbital model as well, but, in contrast to the analytic selective-Mott picture [12], it is hard to extract Z = 0 at low T from DMFT(QMC). Thus, the FMM phase found near the selective-Mott point in the EPAM seems to be stable as one moves away from that point. Interestingly, a "DE-like" picture, related to ours, is also proposed by Batista *et al.* [7] in D = 1. In all earlier studies, however, the intimate link between the SMT in the EPAM and the FMM phase has never been addressed. The analysis here bares this connection, we believe, for the first time. Moreover, our findings are independent of dimensionality, and rely only upon the existence of the SMT and $U_{ff} = \infty$. Additionally, *both* the SMT and FMM support excitonic order. The proof goes through for $U_{fc} = 0$, but not for $t_f = 0$. At this point, we have the S = 1/2 FKM in the f-c basis. It is easy, from the above, to infer that simultaneous satisfaction of conditions (i)-(iii) forces only one electron in the c-band for the FP theorem to work (now in the f - c basis) in this case. Neither does the model exhibit excitonic order: the exact local U(1) symmetry of the EPAM at $t_f = 0$ rigorously implies $\Delta_{cf} = 0$, by Elitzur's theorem. An analytic proof of FMM for large, but finite U_{ff} , remains elusive for the full EPAM.

However, with $t_f = 0$, and a *local* hybridization, V, the analysis of Batista [7] (where our t_f is their t_a) can be exploited to show FM. Diagonalizing H_0 in the EPAM gives two hybridized bands, α and β . If $|V| << t_c$, there are two subspaces in *each* band where the states have dominantly $f, (\phi)$ or $c, (\psi)$ character. Batista *et al.* showed that, under these conditions, H can be re-expressed, to a very good approximation, in terms of the ψ, ϕ fermionic combinations of the $\alpha_{k\sigma}, \beta_{k\sigma}$ fermions in *real* space. The term $U_{fc} \sum_{i,\sigma,\sigma'} n_{if\sigma} n_{ic\sigma'}$ transforms to $U_{fc} \sum_{r,\sigma,\sigma'} n_{r\sigma}^{\phi} n_{r'\sigma'}^{\psi}$. It turns out then that $H(\psi, \phi) = H_0(\phi, \psi) + H_1(\phi, \psi)$ with $U = \infty$ and the *narrow-band a*-level energy, ϵ_a at E_F is closely related to our H_{FKM} at $V_{fc} = \sqrt{t_f t_c}, \epsilon_f = E_F$:

$$H_0(\psi,\phi) \simeq t_{\psi} \sum_{r,r',\sigma} \psi_{r\sigma}^{\dagger} \psi_{r'\sigma} + t_{\phi} \sum_{r,r',\sigma} \phi_{r\sigma}^{\dagger} \phi_{r'\sigma} \qquad (7)$$

and

$$H_1 = U \sum_r n^{\phi}_{r,\uparrow} n^{\phi}_{r\downarrow} + U_{fc} \sum_{r,\sigma,\sigma'} n^{\phi}_{r\sigma} n^{\psi}_{r'\sigma'} \tag{8}$$

so that when $t_a(t_f) = 0$, the dispersionless a, (f) level sits at E_F . Once again, partial band occupancy of the a, b orbitals implies partially filled ψ, ϕ bands. When $U = \infty$ and the ϕ level lies at the bottom of the ψ band, the FP theorem should give a FM metallic ground state. More transparently, this is understood as follows. In any dimension, D, the ϕ -fermion band will undergo Mott-Hubbard splitting for large U. The ψ -fermions now hop in the background of *localized* moments associated with the ϕ fermions. Clearly, at $U = \infty$, maximum kinetic energy gain occurs when the ϕ fermion spins are ferromagnetically aligned, *a la* double exchange.

What could be the experimental fingerprints of such a FMM state near the selective-Mott QCP? Since the bfermions are rigorously immobile at the QCP, but acquire a finite, heavy mass away from it, de-Haas van Alphen (dHvA) measurements should show erosion of the heavy (b-fermion) Fermi sheet as the QCP is approached. Since entering the FM ordered phase drastically reduces the carrier scattering rate, as seen for example, in DMFT work [17], the *a*-fermion FS sheet should reflect *coher*ent quasiparticles, manifesting in well-defined quantum oscillations in the dHvA frequencies as function of applied magnetic field. These oscillations should become ill defined in the incoherent nFL regime, since the large damping $(\text{Im}\Sigma_a(\omega))$ within DMFT [12, 17] will overdamp the dHvA frequencies. Away from the SMT-QCP, appearance of the second, heavy b-fermion FS sheet should lead to additional dHvA frequencies. We emphasize that only the b_{σ} combination, rather than the *f*-electrons themselves, are localized in the EPAM. Within the local, DMFT picture of the SMT, anomalous power-law responses should characterize the thermodynamic, transport and magnetic responses in the critical region: these should evolve smoothly into coherent low-energy forms as one moves away from the QCP. Emergence of an FMM state is then tied to having $\epsilon_f \simeq E_F$. We are not able to say whether this is a generic requirement for FMM in the EPAM(PAM), but our result suggests that it might be the case.

Whether the soft *interband* excitonic modes found at the SMT can act as an electronic "glue" for unconventional multi-band SC is an interesting issue. Since the soft triplet excitonic modes are generated by the orthogonality catastrophe, and so are not directly related to FM, they can even arise within the FM phase [9]. In fact, in UGe_2 , an additional line, $T_x(p)$, in the T-p phase diagram is known to exist. Jumps in thermodynamic responses and dHvA frequencies across $T_x(p)$ is suggestive of a kind of selective localization occuring across that curve. Interestingly, spin-triplet SC seems to be centered around the QPT associated with $T_x(p) = 0$, rather than with $T_c^{FM} = 0$ [9]. In light of our analysis, it is tempting to associate the unconventional, multi-band, spin-triplet SC in UGe_2 with emergence of possible soft, spin-triplet excitonic modes around a hypothesized selective localization across $T_x(p)$. An explicit calculation is out of scope of this work, however.

In conclusion, I have studied the interesting issue of

having an itinerant FMM phase near the selective-Mott transition in an extended, periodic Anderson model. Using the FP theorem, I rigorously show, for $U_{ff} = \infty$ and partially filled c, f (or a, b) bands, that the FM state is the unique ground state. Remarkably, the same feature, i.e, dispersionless b-fermion states, which facilitates singular, non-FL dynamics in the uniform metallic phase, also turns out to be crucial to prove FM in the EPAM. Moreover, this partial localization is also characterized by soft, interband excitonic modes in the non-FL phase as a consequence of the Anderson orthogonality catastrophe. In a FM ordered background, such soft interband spin-triplet excitons could induce unconventional, spin-triplet SC.

Acknowledgements I thank Montu Saxena for a discussion on UGe_2 and the MPI-PKS, Dresden for financial support.

- C. Herring, in "Magnetism", Vol IV, eds. G. Rado and H. Suhl (Academic, NY, 1966).
- [2] J. Hubbard, Proc. Roy. Soc. (London) A276, 238 (1963).
- [3] E. H. Lieb, Phys. Rev. Lett. 62, 1927 (1989).
- H. Tasaki, Phys. Rev. Lett. 69, 1608 (1992); ibid J. Stat.
 Phys. 84, 535 (1996); ibid Prog. Theo. Phys. 99, 4, 489 (1998), and references therein.
- [5] E. Müller-Hartmann, J. Low. Temp. Phys. 99, 349 (1995).
- [6] C. Zener, Phys. Rev. 82, 403 (1951).
- [7] C. Batista, J. Bonca, and J. Gubernatis, Phys. Rev. B68, 214430 (2003).
- [8] H. Tsunetsugu, M. Sigrist, and K. Ueda, Rev. Mod. Phys. 69, 809 (1997), and references therein.
- [9] S. S. Saxena, *et al.*, Nature **604**, 587 (2000). K. Sandeman, G.Lonzarich and A. Schofield, Phys. Rev. Lett. **90**, 167005 (2003) and Ref.[11] therein, where dHvA data for UGe_2 show a change in the character of the Fermi surface across $T_x(p)$, indicating selective localization of a subset of carriers.
- [10] P. Gegenwart et al., Phys. Rev. Lett. 94, 076402 (2005).
- [11] M. S. Laad, cond-mat/0805.2115, submitted tp Phys. Rev. Lett.
- [12] M. S. Laad, arXiv:0811.3767, submitted to Phys. Rev. Lett.
- [13] S. Elitzur, Phys. Rev. D 12, 3978 (1975).
- [14] C. Batista, Phys. Rev. Lett. 89, 166403 (2002).
- [15] R.A. Horn and C.R. Johnson, Matrix Analysis, Cambridge University Press, 1990 (chapter 8).
- [16] U. Yu, K. Byczuk, and D. Vollhardt, condmat/0808.0079, and references therein.
- [17] S. Biermann, L. de'Medici and A. Georges, Phys. Rev. Lett. 95, 206401 (2005).