Low Resistance Metal Contacts to MoS₂ Devices with Nickel-Etched-Graphene Electrodes

Wei Sun Leong,[†] Xin Luo,^{‡,[¥]} Yida Li,[†] Khoong Hong Khoo,^{‡,[¥]} Su Ying Quek,^{*,‡} and

John T. L. Thong *, †

[†]Department of Electrical and Computer Engineering, National University of Singapore, Singapore 117583.

[‡]Department of Physics, Centre for Advanced 2D Materials and Graphene Research Centre, National University of Singapore, Singapore 117546.

[¥]Institute of High Performance Computing, 1 Fusionopolis Way, #16-16 Connexis, Singapore 138632.

*Address correspondence to elettl@nus.edu.sg (experiment); phyqsy@nus.edu.sg (theory)

ABSTRACT We report an approach to achieve low-resistance contacts to MoS_2 transistors with the intrinsic performance of the MoS_2 channel preserved. Through a dry transfer technique and a metalcatalyzed graphene treatment process, nickel-etched-graphene electrodes were fabricated on MoS_2 that yield contact resistance as low as 200 Ω .µm. The substantial contact enhancement (~2 orders of magnitude) as compared to pure nickel electrodes, is attributed to the much smaller work function of nickel-graphene electrodes, together with the fact that presence of zigzag edges in the treated graphene surface enhances tunneling between nickel and graphene. To this end, the successful fabrication of a clean graphene-MoS₂ interface and a low resistance nickel-graphene interface is critical for the experimentally measured low contact resistance. The potential of using graphene as an electrode interlayer demonstrated in this work paves the way towards achieving high performance next-generation transistors.

KEYWORDS Transition metal dichalcogenide, molybdenum disulfide, contact resistance, graphene, field-effect transistor, heterostructure

Two-dimensional transition metal dichalcogenides (TMDs) are materials that present unique electronic and optical properties. Among them, molybdenum disulfide (MoS_2) has received the most attention in recent years. Theoretically, MoS₂ field-effect transistors (FETs) have been predicted to possess reasonable electron mobility, large transconductance, and superior on/off ratios (>10¹⁰) due to the large direct bandgap (1.9 eV) for monolayer MoS₂.¹⁻³ More importantly, due to its natural two-dimensional form, MoS₂ is expected to be insusceptible to short channel effects endowing it with great promise as an alternate channel material for post-silicon electronics.^{1, 3} Despite such potential advantages, in reality, MoS₂ devices with such excellent performance have yet to be realized, one of the most serious impediments being the non-trivial contact resistance at the metal-MoS₂ interfaces. The large source/drain contact resistance that has been hampering the realization of ideal MoS₂ FETs can be attributed to Fermi level pinning in MoS₂ close to the conduction band edge as a result of sulfur-vacancy defect level and charge neutral level location.^{3,4} Regardless of this underlying principle, prior attempts to mitigate this by choosing the most appropriate material as contact metallization to MoS₂ have met with limited success -- the lowest contact resistance reported to date using scandium contacts is still far from satisfactory.³ Alternatively, gas⁵ and charge transfer based molecular doping⁶ on MoS₂ flakes have been used to lower the contact resistance of MoS₂ devices but accompanying severe degradation in the on/off performance was observed. Recently, chloride molecular doping technique and formation of contacts to metallic-phase MoS₂ have been demonstrated to lower the contact resistance of MoS₂ transistors to 500 Ω .µm⁷ and 200-300 $\Omega.um$.⁸ respectively. Both techniques involve hours of chemical immersion and how the chemicals affect the MoS₂/dielectric interface requires careful investigation for future technology development.

On the other hand, some research groups have attempted the use of graphene as electrical contacts to MoS₂ devices since it has the ability to enhance electron injection into the conduction band of MoS₂ through lowering of the Schottky barrier height.⁹⁻¹¹ However, graphene by itself as electrode is too thin for electrical characterization (probing) and thus necessitates the use of metal-graphene hybrid as electrical contact for MoS₂ devices.^{9, 12} The situation at the metal-graphene-MoS₂ contact has become more complicated as it combines both metal-graphene and graphene-MoS₂ interfaces. Taken individually,

the former contact resistance is known to be large (up to hundreds of Ω .mm) without any contact treatment, while cleanliness is a key requirement for the latter interface. Failure to optimize either one of these interfaces could compromise the contact enhancement brought about by the graphene interlayer. For example, the contact resistance for Ti-graphene-contacted MoS₂ devices ($3.7 \pm 0.3 \Omega$.mm when back gate bias = 30 V)¹¹ has been reported to be large compared to the lowest contact resistance values reported for MoS₂ devices.⁸

Here, we demonstrate that the resistance of metal contacts to semiconducting-phase MoS₂ can be as low as that of metallic-phase MoS₂ with the use of etched-graphene as buffer layer at the metal-MoS₂ interface. To ensure clean graphene-MoS₂ interfaces, a polymer-assisted dry transfer technique is used to layer the graphene onto the MoS₂. Hence, the bottom side of the exfoliated graphene flake, which has never been exposed to any polymer or solvent, is clean and bonds to the MoS₂ crystal lattice through van der Waals force. This is followed by metallization to the graphene using nickel. In order to optimize the metal-graphene interface, we propose to treat the graphene with a nickel-catalyzed etching process prior to stacking on MoS₂, which creates in the graphene a vast density of nano-sized pits with zigzagterminated edges that covalently bond to the deposited nickel (Ni) metallization, thus minimizing the resistance at metal-graphene interface.¹³ In brief, the MoS₂ devices with Ni-etched-graphene electrodes show not only about 2 orders of magnitude improvement in contact resistance and 3-fold enhancement in effective mobility, but also performance enhancement in terms of on/off current ratio and subthreshold swing.

Results and Discussion

The fabrication process of a back-gated MoS₂ FET with Ni-etched-graphene sandwiched at metal-MoS₂ contacts is illustrated in Figure 1. In order to carry out a fair comparison between MoS₂ FETs with and without treated graphene as an interlayer at the source/drain contacts, we fabricated on the same MoS₂ strip exfoliated from molybdenite crystal (SPI supplies[®]) an array of MoS₂ back-gated field-effect transistors consisting of both Ni-MoS₂ and Ni-treated-graphene-MoS₂ contacts (see Methods for details).

Graphene flakes and MoS₂ flakes were first exfoliated onto separate oxidized degenerately p-doped silicon substrate with 285 nm thick SiO₂ (Figure 1a). Exfoliated bilayer graphene (BLG) was identified and then treated with a Ni-catalyzed etching technique,¹³ which involves nickel deposition, annealing in hydrogen, and removal of nickel particles by acid. From the other substrate, a freshly-exfoliated MoS₂ strip (16 nm thick) with uniform width (~2 μ m) was chosen. Using a polymer-assisted dry transfer technique, the treated graphene was delaminated from its substrate and transferred onto the selected MoS₂ strip (Figure 1b). Thereafter, the source/drain contacts were delineated and metallized with 60 nm of Ni (Figure 1c). Finally, the exposed graphene was completely removed by using the Ni electrodes as a self-aligned hard mask in combination with a benign oxygen plasma process (Figure 1d). As can be seen from Figures 2(a) and (b), the exposed graphene was removed by the oxygen plasma process leaving behind only the MoS₂ as the effective channel for Ni-treated-graphene contacted MoS₂ devices. In addition, the unprotected MoS₂ portion shows no visible damage under an optical microscope. Indeed, the output characteristics of Ni-contacted MoS₂ devices remain unchanged (Figure 3a) prior to and following the benign oxygen plasma process.

For this study, we extracted the contact resistance using transfer length method (TLM). An array of two-terminal devices with Ni-MoS₂ contacts and a corresponding adjacent array of two-terminal devices with Ni-treated-BLG-MoS₂ contacts were fabricated on the same MoS₂ flake of 2 μ m width and channel lengths varying from 0.5 to 3 μ m, in steps of 0.5 μ m (Figure 2b). The two-terminal resistance of each device was measured as a function of back-gate voltage, V_G. Subsequently, the data was fitted using equation (1):

$$R = 2R_C(W) + R_s \frac{L}{W} \tag{1}$$

where R is the two-terminal resistance of each device being measured, R_C is the contact resistance of each contact as a function of width, R_S is the sheet resistance, and L and W represent channel length and width, respectively. Electrical characterizations on all devices were performed in vacuum at room temperature and no annealing was performed prior to measurement.

The extracted R_C as a function of back-gate voltage is plotted in Figure 3b, with error bars that represent uncertainty in the fitting. The R_C of all devices in this study exhibits clear gate-voltage dependence (Figure 3b). This trend corroborates other findings reported in literature,^{6, 14} where the MoS₂ is electrically doped under high gate bias, resulting in smaller effective Schottky barrier height, and hence the R_C reduces with back-gate bias. As can be seen in Figure 3b, the fitted R_C for devices with Ni-treated-BLG-MoS₂ contacts was found to be $0.26 \pm 0.06 \ \Omega$.mm and $0.46 \pm 0.11 \ \Omega$.mm at back-gate biases of 50 V and 0 V, respectively, which is within 15% of the MoS_2 FETs' on-resistance and approaches the R_C required for current state-of-the-art silicon MOSFETs.¹⁵ On the other hand, the fitted R_C for Ni-contacted MoS₂ devices without any contact interlayer is $9.6 \pm 2.1 \Omega$.mm and $36.6 \pm 7.8 \Omega$.mm at back-gate biases of 50 V and 0 V, respectively, which is about 37 and 80 times higher than the fitted R_C of devices with Nitreated-BLG-MoS₂ contacts, respectively. It should be noted that these 2 sets of devices were fabricated on the same MoS₂ strip. For comparison purposes, devices with Ni-single-layer-graphene(SLG)-MoS₂ contacts were fabricated on another MoS_2 strip of a similar thickness and the fitted R_C is also plotted in Figure 3b. The R_C of devices with Ni-SLG-MoS₂ contacts is $0.83 \pm 0.18 \Omega$.mm and $1.80 \pm 0.44 \Omega$.mm at back-gate biases of 50 V and 0 V, respectively, which represents 12 and 20 times improvement, respectively, compared to that of pure Ni contacts to MoS₂. On the other hand, with untreated BLG as the contact interlayer, the extracted R_C of $0.81 \pm 0.16 \Omega$ mm and $1.31 \pm 0.41 \Omega$ mm at back-gate biases of 50 V and 0 V, respectively, is comparable to that of Ni-SLG-MoS₂ contacts (Figure 3b). Nonetheless, these values are at least 3 times larger than those of Ni-treated-BLG-MoS₂ contacts regardless of back-gate biases. This additional contact enhancement with the use of treated BLG as the contact interlayer, compared to both untreated SLG and BLG, can be attributed to the much smaller resistance at the Nigraphene interface as illustrated by Figure S1. In spite of that, the use of treated SLG as the contact interlayer showed inferior contact performance compared to that of untreated SLG (Table S1). This can be attributed to the perforated treated-SLG contact interlayer that no longer prevents direct interaction between Ni and MoS₂ atoms.

It should be noted that the Ni-catalyzed etching treatment performed on graphene (either SLG or BLG) is capable of creating a significant amount of zigzag graphene edges (either triangular or hexagonal nanosized pits)¹³ in the graphene surface (see Supporting Information S3 for details). More importantly, these zigzag graphene edges are expected to directly bond to the subsequent nickel metallization in endcontacted geometry,¹³ rather than the surface-contacted geometry, and thus results in metal-graphene interfaces with smaller contact resistance ($R_{edge} \ll R_{surface}$) as has been predicted theoretically¹⁶ and proven experimentally.^{17, 18} In addition, due to weak van der Waals bonds, the tunneling resistance between graphene layers in BLG is found to be larger compared to that of end-contacted metal-graphene contacts ($R_{edge} \ll R_{interlayer}$)¹⁹ and hence graphite (>2 layers of graphene) should be avoided to minimize the contribution of tunneling resistance between graphene layers. In brief, the results show that insertion of graphene as an interlayer by itself already enhances the carrier injection at the metal-MoS₂ contacts, and the use of the Ni-catalyzed etching technique further boosts the carrier injection at the metal-MoS₂ contacts.

In Figure 4, we compare the output and transfer characteristics of two MoS₂ FETs with different types of contacts: Ni-MoS₂ and Ni-treated-BLG-MoS₂ contacts. Both FETs were fabricated with the same device dimensions and on the same MoS₂ flake. Electrical characterization were performed in vacuum at room temperature. As can be seen from Figure 4(a), the MoS₂ devices show ~10 times improvement in terms of on-current at $V_{DS} = 2$ V and $V_G = 50$ V with the insertion of treated-graphene as a sandwich layer at metal-MoS₂ contacts. This observation is consistent across all the fabricated FETs regardless of the channel length. In addition, back-gate measurements were also performed on these pairs of MoS₂ FETs and both FETs exhibit n-type behaviour with similar threshold voltage. This implies that the treated-graphene sandwich layer at metal-MoS₂ contacts exhibit larger on/off current ratio (10⁵) and better subthreshold-swing (3.7 V/decade at V_{DS} = 0.2 V) compared to those of Ni-MoS₂ contacts (10⁴ and 6.7 V/decade at V_{DS} = 0.2 V) as can be seen from the inset of Figure 4(b). We then extract the extrinsic mobility of these pairs of MoS₂ FETs using equation (2):

$$\mu = \frac{1}{C_{ox} \bullet V_{DS}} \bullet \frac{L_{ch}}{W_{ch}} \bullet \frac{\Delta I_{DS}}{\Delta V_G}$$
(2)

where C_{ox} is the gate capacitance $(1.21 \times 10^{-8} \text{ F/cm}^2 \text{ for } 285 \text{ nm thick SiO}_2)$, L_{ch} and W_{ch} are channel length and width, respectively, I_{DS} is the drain current, V_{DS} is the drain voltage and V_G is the gate voltage. The electron mobility for the typical device with Ni-treated-BLG-MoS₂ contacts is 80 cm²/V-s, while for the device with Ni-MoS₂ contacts is 27 cm²/V-s. This 3-fold improvement in extrinsic mobility can be attributed to the reduced contact resistance. It is worth noting that both the contact resistance and mobility values reported here can be better by elimination of residual PMMA left over by the lithography and polymer-assisted dry transfer processes.

We now elucidate, using first principles calculations, the essential physics behind the observed smaller contact resistance in Ni-treated-BLG-MoS₂ compared to Ni-MoS₂ contacts. Since the largest reduction in contact resistance occurs when Ni-MoS₂ contacts are replaced by Ni-SLG-MoS₂ and Ni-BLG-MoS₂ contacts (Figure 3b), we first focus on the effect of inserting SLG and BLG at the Ni-MoS₂ contacts. The Schottky Barrier Height (SBH) is a key factor that determines contact resistances in semiconductor MOSFETs, and in particular in the MoS₂ transistors considered here.²⁰ We therefore perform a comparative SBH analysis on Ni-MoS₂, Ni-SLG-MoS₂, and Ni-BLG-MoS₂ interfaces. Figure 5 shows the calculated minority-spin bands and side views of the corresponding optimized atomic structures, while the majority spin bands and top view of the atomic structures are presented in Figure S4. When MoS_2 is in direct contact with Ni, the binding energy between them is large and the equilibrium interface distance is only 1.92 Å, smaller than the value of 2.08 Å for graphene chemisorbed on Ni. The strong binding influences the electronic structure, as can be seen in Figure 5a, where the projected band structure on MoS₂ (represented by blue dots with the projection weight represented by dot size) is strongly perturbed and bears little resemblance to that of pristine MoS₂ (Figure S4). For the Ni-SLG-MoS₂ contact, graphene p_z -states (represented by magenta dots in Figure 5b) hybridize strongly with the Ni *d*-states, and serve as a buffer layer separating the MoS_2 from Ni. Therefore, the projected band structure of MoS_2 is similar to that of an isolated MoS₂ layer (Figures 5b and S4). In both cases, the Fermi level is closer to the MoS₂ conduction band minimum (CBM) than to the valence band maximum (VBM), so that the SBH is extracted by taking the energy difference between the Fermi level of the electrode and the CBM of MoS₂ (Figure 6). Remarkably, the extracted SBH is reduced from 0.8 eV to 0.3 eV with the insertion of a graphene layer at the Ni-MoS₂ contacts (Figure 6a). The accuracy of our calculated SBH is verified using higher convergence criteria (Table S2). With the insertion of BLG as a contact interlayer at the Ni-MoS₂ contacts, Ni states are sufficiently isolated from MoS₂ and its adjoining graphene layer (Figure 5). Thus, we can see an intact MoS₂ projected band structure and a graphene projected band structure that exhibits clear graphene characteristics (represented by orange dots in Figure 5c), such as the Dirac conical points which are shifted from the K-point to the Γ -point due to Brillouin zone folding. The extracted SBH for Ni-BLG-MoS₂ contacts is very similar to that for Ni-SLG-MoS₂ contacts (Figure 6a).

Generally, it has been found that the SBH at metal-MoS₂ contacts increases as the work function of the contacting metal electrode increases.²⁰⁻²² This trend makes sense considering the fact that the SBH at metal-MoS₂ contacts is computed as the difference between the Fermi level of the electrode and the CBM of MoS₂; in experiments, the SBH is more accurately given by the difference between the Fermi level of the electrode and the defect levels in MoS₂ (which are also close to the CBM).^{2, 23} In the simplest consideration, in order for the Fermi level not to fall too far into the band gap of MoS₂, the ideal electrode would be one whose work function is as close as possible to (or if not, smaller than) the electron affinity of MoS₂. In Figure 6a, the SBH from our calculations are plotted against the work functions of different electrodes (*i.e.* Ni, Ni-SLG and Ni-BLG). These plots strongly suggest that the significant reduction of the SBH is closely related to the reduction of the work function of the Ni-graphene electrodes (both Ni-SLG and Ni-BLG electrodes) compared to that of Ni electrodes. The calculated work functions, $q\phi_M$ of the Ni-graphene electrodes (3.64 eV for Ni-SLG and 4.08 eV for Ni-BLG) are smaller than the calculated electron affinity, $q\chi$ of isolated MoS₂ (4.33 eV); in contrast, the work function of Ni is significantly higher (5.52 eV). As the work function of Ni is substantially larger than the electron affinity of MoS₂, even with partial Fermi level pinning from metal-induced gap states at the strongly hybridized Ni-MoS₂ interface,²¹ the resulting SBH is still quite large. On the other hand, due to the weak van der Waals interactions

between graphene and MoS₂, Ni-graphene electrodes interact with MoS₂ mainly by charge transfer, which determines the resulting SBH. Specifically, one expects electrons to be transferred from the electrodes to MoS₂, resulting in an interface dipole that raises the relative potential at MoS₂, giving rise to a small SBH (Figure 6b). By comparing the magnitude of the dipole at the electrode-MoS₂ interface, we found that the dipole moment is stronger in the Ni-SLG-MoS₂ interfaces compared to that of Ni-BLG-MoS₂, causing a larger upward shift of the MoS₂ bands. This is why even though the work function of the Ni-SLG electrode is 0.4 eV smaller than that of the Ni-BLG electrode, the SBH is comparable in both Ni-SLG-MoS₂ and Ni-BLG-MoS₂ interfaces. Figures 5d-f plot the plane-averaged charge difference Δn obtained by subtracting the plane-averaged charge density of the composite slab from that of individual components of the slab using the same supercell, *i.e.* $\Delta n = n_{Ni-graphene-MoS_2}(z) - n_{Ni}(z) - n_{graphene}(z) - n_{MoS_2}(z)$. These plots give further evidence that the interaction between MoS₂ and the electrode is larger for the bare Ni electrodes than for the Ni-graphene electrodes. On the other hand, the complicated charge density profile at the Ni-graphene interface shows that there is strong interaction between Ni and graphene, which explains the large reduction in work function of the Ni-graphene electrodes.²⁴

The above discussion indicates that the large reduction in contact resistance going from Ni-MoS₂ interfaces to Ni-SLG-MoS₂ and Ni-BLG-MoS₂ interfaces arises from the reduction in SBH due to the significantly smaller work functions of the Ni-graphene electrodes (both Ni-SLG and Ni-BLG electrodes). As we have seen in the literature,^{20, 21} the computed SBH is expected to be slightly larger than the experimentally extracted SBH, partly due to the neglect of defect levels and to the fact that monolayer MoS₂ is considered in the calculations. However, the trends predicted by theory have been shown to be robust^{20, 21} and we expect that the large change in SBH predicted here also exists in experiment.

Moving on to explain the further reduction in contact resistance going from Ni-BLG-MoS₂ to Nitreated-BLG-MoS₂ interfaces, we consider the effects of zigzag graphene edges at the Ni-graphene interface (Figure S5a-b). It is interesting that our computed SBH for Ni-treated-BLG-MoS₂ interfaces is very similar to that of Ni-BLG-MoS₂ interfaces. Furthermore, by performing nonequilibrium Green's function (NEGF) density functional theory calculations,²⁵ we find that the contact resistance of zigzagedge-contacted Ni-graphene interface (233 Ω .µm) is significantly smaller than that of surface-contacted Ni-graphene interface (340 Ω .µm; see Methods for details and Figure S6 for geometries). Similar calculations comparing surface and edge-contacted graphene by other metals have also found edge-contacted metal-graphene interfaces to yield lower contact resistances, due to the stronger metal-graphene coupling at these interfaces.¹⁶ Therefore, we can infer that the effect of Ni-mediated etching treatment on reducing the contact resistance arises primarily from the stronger coupling between Ni and zigzag graphene edges. It is important to note that although stronger coupling can reduce the contact resistance as shown here, tunnelling probabilities depend exponentially on the SBH; therefore, the reduction in SBH going from Ni-MoS₂ to Ni-graphene-MoS₂ interfaces has a larger effect on the contact resistance than the extent of coupling between MoS₂ and the electrodes, which we have not considered here. We also find that the SBH of Ni-treated-SLG-MoS₂ interfaces is slightly larger than those of Ni-SLG-MoS₂ and Ni-BLG-MoS₂ interfaces, but smaller than that of Ni-MoS₂ interfaces (Table S2, Figure S5c). These results are consistent with the contact resistances measured in experiment (Table S1).

Conclusions

We have shown that the insertion of graphene as a contact interlayer into Ni-MoS₂ contacts can significantly reduce the contact resistance. A further treatment of the bilayer graphene surface, namely Ni-mediated etching, can further reduce the contact resistance. Sets of TLM structures consisting of multiple FETs each were fabricated with 4 types of contact structures: Ni-MoS₂, Ni-SLG-MoS₂, Ni-BLG-MoS₂, and Ni-treated-BLG-MoS₂ contacts on exfoliated MoS₂ of similar thickness. Electrical measurements made on all sets of FETs indicate that the contact resistance of the Ni-SLG-MoS₂ FETs is significantly reduced by 20-fold as compared to the Ni-MoS₂ FETs, and is further reduced by an additional 3-fold for the FETs with Ni-treated-BLG-MoS₂ contacts. This significant contact enhancement results in improved field-effect mobility in the FETs with treated-BLG as a contact interlayer, compared to the more traditional FETs with pure Ni as the contact electrodes (80 cm²/V-s *versus* 27 cm²/V-s). From our I-V measurements, it is clear that regardless of the insertion of untreated or treated graphene at the contacts,

a much lower effective Schottky barrier height can be observed. First-principles calculations indicate that the large reduction in contact resistance observed experimentally results from the lower work function in the Ni-graphene electrodes, resulting in a smaller SBH in Ni-graphene-MoS₂ contacts. The effect of Nimediated etching treatment of bilayer graphene further reduces the contact resistance due to stronger coupling between Ni and the zigzag graphene edges. The significant contact resistance reduction, and enhancement of the on-off ratio, subthreshold-swing and mobility with the use of graphene as the contact interlayer is remarkable considering the fact that there is no systematic method reported to date to improve the contact and adhesion of metal to MoS₂. Our findings provide an insight into how the contact resistance at metal-MoS₂ contacts can be engineered with the use of graphene as an interlayer. Moreover, the proposed Ni-mediated etching treatment for graphene that further lowers the contact resistance is compatible with semiconductor industry manufacturing technology. Hence, with the approach demonstrated in this work, the use of MoS₂ as a mainstream electronic material is brought one step closer to the forefront.

Methods

Fabrication of MoS₂ field-effect transistor with Ni-etched-graphene sandwiched at metal-MoS₂ contacts. MoS₂ and graphene flakes were first exfoliated on separate oxidized degenerately p-doped silicon substrate with 285 nm thick SiO₂ (Figure 1a). The exfoliated bilayer graphene was then treated with a Ni-catalyzed etching technique.¹³ This started with the deposition of a thin film (2 nm) of Ni on the exfoliated graphene *via* thermal evaporation at a rate of 0.1 nm per second. Subsequently, the graphene sample was annealed at 580 °C for 10 min in a hydrogen ambient and a significant amount of etched pits with well-defined zigzag edges is created on the graphene basal plane based on a Ni-catalyzed gasification process: C (solid) + 2H₂ (gas) -> CH₄ (gas).¹³ Thereafter, all nickel particles were removed using acid. This was followed by spin-coating of a polymethylmethacrylate (PMMA) layer (600 nm thick) and baked at 120°C in an oven for 10 min. The PMMA film with the graphene was then delaminated from the substrate using a Scotch tape and transferred onto the targeted substrate with the freshly-exfoliated MoS₂

strip (16 nm thick) of uniform width (~2 μ m) (Figure 1b). For this dry transfer technique, a micromanipulator was used to align the treated-graphene to the exfoliated MoS₂ (Figure 1c). The sample was then baked at 100 °C to improve adhesion. Subsequently, the source/drain contacts were delineated and metallized with 60 nm of Ni (Figure 1c). Finally, the exposed graphene was completely removed by utilizing the Ni electrodes as a self-aligned hard mask in combination with a benign oxygen plasma process (10 W RF power, 30 V substrate bias, for 30 seconds). Electrical characterization on all devices were performed at room temperature in a high vacuum chamber (10⁻⁶ mbar) to avoid unnecessary interaction with moisture in ambient.²⁶

First principles calculations. The first principles calculations are performed using a plane wave basis set at the level of density functional theory (DFT), as implemented in the VASP code.²⁷ The local spin density approximation (LSDA)²⁸ is employed for the exchange-correlation functional and projectoraugmented wave (PAW)²⁹ potentials are used throughout the calculation. The (111) surface of Ni has similar lattice constants with graphene. To construct a commensurate interface between Ni-graphene/Ni and MoS₂, we use a rotated 30° 6×6 supercell of graphene to accommodate the MoS₂ 4×4 supercell, and the Ni electrode is modeled by a slab consisting of four atomic layers of Ni. The constructed structures have about 1% compressive strain in graphene and such supercells have been observed experimentally.³⁰ A plane wave kinetic energy cut-off of 450 eV is used for the wave function basis set, and a Gamma centered $3 \times 3 \times 1$ k-point grid is sampled in the Brillouin zone (BZ). Increasing the cut-off energy and k-point grid only leads to minor differences with the present results (Table S2). Dipole corrections are applied in the self-consistent calculations to prevent interactions between moments of different supercells. The slabs are separated by a vacuum of at least 12 Å to prevent interactions between periodic image slabs. The interface structures and internal coordinates are fully relaxed with fixed lattice constants such that the maximum component of the Hellmann-Feynman force acting on each ion is less than 0.02 eV/Å. In the work function calculations, the unit cells of Ni, Ni-SLG and Ni-BLG are used together with a much denser BZ k-point sampling of $44 \times 44 \times 1$. The energy convergence threshold is set at 10^{-6} eV.

It is worth noting that the computed work functions in this work are consistent with the values in prior experimental works. The calculated work function of our Ni and Ni-SLG electrodes are respectively 5.52 eV and 3.64 eV, consistent with previous DFT calculations,³¹ and also close to the experimental values (5.35 eV for Ni and 3.9 eV for Ni-SLG).^{32, 33}

NEGF-DFT calculations were performed using the ATOMISTIX TOOLKIT (ATK) package, that employs a numerical localized basis sets and the Nonequilibrium Green's function (NEGF) formalism. Self-consistent calculations were performed using a double- ξ polarized basis set and a density mesh cutoff of 300 Ry. Exchange correlation was treated using the local spin density approximation²⁸ and all atoms were relaxed such that the force per atom was less than 0.05 eV/Å. The k-point samplings of 15 x 1 and 15 x 4 were employed for the surface- and edge-contacted interfaces respectively along the in-plane directions. To obtain the transmission spectrum, a denser k-point grid of 500 x 1 and 500 x 50 was used for the side and edge contact interfaces respectively along the in-plane directions. Figure S6 shows the geometries. The contact resistance was obtained from the calculated transmission spectra *T*(*E*) using the formula

$$Rc = \left(\int T(E) \frac{e^{(E-E_F)/k_B T}}{\left(e^{(E-E_F)/k_B T} + 1\right)^2} \frac{dE}{k_B T}\right)^{-1}$$

with the temperature set to 300K.

Acknowledgements: This project is supported by grant R-263-000-A76-750 from the Faculty of Engineering, NUS and grant NRF-NRFF2013-07 from the National Research Foundation, Singapore.

References

1. Yoon, Y.; Ganapathi, K.; Salahuddin, S. How Good Can Monolayer MoS2 Transistors Be? *Nano Lett.* 2011, 11, 3768-3773.

2. Radisavljevic, B.; Radenovic, A.; Brivio, J.; Giacometti, V.; Kis, A. Single-Layer MoS2 Transistors. *Nat. Nanotechnol.* 2011, 6, 147-150.

3. Das, S.; Chen, H.-Y.; Penumatcha, A. V.; Appenzeller, J. High Performance Multilayer MoS2 Transistors with Scandium Contacts. *Nano Lett.* 2013, 13, 100-105.

4. Liu, D.; Guo, Y.; Fang, L.; Robertson, J. Sulfur Vacancies in Monolayer MoS2 and Its Electrical Contacts. *Appl. Phys. Lett.* 2013, 103, 183113-1-183113-4.

5. Fang, H.; Tosun, M.; Seol, G.; Chang, T. C.; Takei, K.; Guo, J.; Javey, A. Degenerate n-Doping of Few-Layer Transition Metal Dichalcogenides by Potassium. *Nano Lett.* 2013, 13, 1991-1995.

6. Du, Y.; Liu, H.; Neal, A. T.; Mengwei, S.; Ye, P. D. Molecular Doping of Multilayer MoS2 Field-Effect Transistors: Reduction in Sheet and Contact Resistances. *IEEE Electron Device Lett.* 2013, 34, 1328-1330.

7. Yang, L.; Majumdar, K.; Liu, H.; Du, Y.; Wu, H.; Hatzistergos, M.; Hung, P. Y.; Tieckelmann, R.; Tsai, W.; Hobbs, C.; Ye, P. D. Chloride Molecular Doping Technique on 2D Materials: WS2 and MoS2. *Nano Lett.* 2014, 14, 6275–6280.

8. Kappera, R.; Voiry, D.; Yalcin, S. E.; Branch, B.; Gupta, G.; Mohite, A. D.; Chhowalla, M. Phase-Engineered Low-Resistance Contacts for Ultrathin MoS2 Transistors. *Nat. Mater.* 2014, 13, 1128–1134.

Roy, T.; Tosun, M.; Kang, J. S.; Sachid, A. B.; Desai, S.; Hettick, M.; Hu, C. C.; Javey, A. Field-Effect Transistors Built from All Two-Dimensional Material Components. *ACS Nano* 2014, 8, 6259-6264.
Yoon, J.; Park, W.; Bae, G.-Y.; Kim, Y.; Jang, H. S.; Hyun, Y.; Lim, S. K.; Kahng, Y. H.; Hong, W.-K.; Lee, B. H.; *et al.* Highly Flexible and Transparent Multilayer MoS2 Transistors with Graphene Electrodes. *Small* 2013, 9, 3295-3300.

11. Du, Y.; Yang, L.; Zhang, J.; Liu, H.; Majumdar, K.; Kirsch, P. D.; Ye, P. D. MoS2 Field-Effect Transistors With Graphene/Metal Heterocontacts. *IEEE Electron Device Lett.* 2014, 35, 599-601.

12. Yu, L.; Lee, Y.-H.; Ling, X.; Santos, E. J. G.; Shin, Y. C.; Lin, Y.; Dubey, M.; Kaxiras, E.; Kong, J.; Wang, H.; *et al.* Graphene/MoS2 Hybrid Technology for Large-Scale Two-Dimensional Electronics. *Nano Lett.* 2014, 14, 3055-3063.

13. Leong, W. S.; Gong, H.; Thong, J. T. L. Low-Contact-Resistance Graphene Devices with Nickel-Etched-Graphene Contacts. *ACS Nano* 2014, 8, 994-1001.

14. Liu, H.; Neal, A. T.; Ye, P. D. Channel Length Scaling of MoS2 MOSFETs. *ACS Nano* 2012, 6, 8563-8569.

15. International Technology Roadmap for Semiconductors. In *Process Integration, Devices, and Structures* 2012. http://www.itrs.net/Links/2012ITRS/Home2012.htm.

16. Matsuda, Y.; Deng, W.-Q.; Goddard, W. A. Contact Resistance for "End-Contacted" Metal–Graphene and Metal–Nanotube Interfaces from Quantum Mechanics. *J. Phys. Chem. C* 2010, 114, 17845-17850.

17. Wang, L.; Meric, I.; Huang, P. Y.; Gao, Q.; Gao, Y.; Tran, H.; Taniguchi, T.; Watanabe, K.; Campos, L. M.; Muller, D. A.; *et al.* One-Dimensional Electrical Contact to a Two-Dimensional Material. *Science* 2013, 342, 614-617.

18. Leong, W. S.; Nai, C. T.; Thong, J. T. L. What Does Annealing Do to Metal–Graphene Contacts? *Nano Lett.* 2014, 14, 3840-3847.

19. Chu, T.; Chen, Z. Understanding the Electrical Impact of Edge Contacts in Few-Layer Graphene. *ACS Nano* 2014, 8, 3584-3589.

20. Das, S.; Appenzeller, J. Where Does the Current Flow in Two-Dimensional Layered Systems? *Nano Lett.* 2013, 13, 3396-3402.

21. Gong, C.; Colombo, L.; Wallace, R. M.; Cho, K. The Unusual Mechanism of Partial Fermi Level Pinning at Metal–MoS2 Interfaces. *Nano Lett.* 2014, 14, 1714-1720.

22. Chen, W.; Santos, E. J. G.; Zhu, W.; Kaxiras, E.; Zhang, Z. Tuning the Electronic and Chemical Properties of Monolayer MoS2 Adsorbed on Transition Metal Substrates. *Nano Lett.* 2013, 13, 509-514.

23. Yu, W. J.; Li, Z.; Zhou, H.; Chen, Y.; Wang, Y.; Huang, Y.; Duan, X. Vertically Stacked Multi-Heterostructures of Layered Materials for Logic Transistors and Complementary Inverters. *Nat. Mater.* 2013, 12, 246-252.

24. Giovannetti, G.; Khomyakov, P. A.; Brocks, G.; Karpan, V. M.; van den Brink, J.; Kelly, P. J. Doping Graphene with Metal Contacts. *Phys. Rev. Lett.* 2008, 101, 026803.

25. Brandbyge, M.; Mozos, J.-L.; Ordejón, P.; Taylor, J.; Stokbro, K. Density-Functional Method for Nonequilibrium Electron Transport. *Phys. Rev. B* 2002, 65, 165401.

26. Qiu, H.; Pan, L.; Yao, Z.; Li, J.; Shi, Y.; Wang, X. Electrical Characterization of Back-Gated Bilayer MoS2 Field-Effect Transistors and The Effect of Ambient on Their Performances. *Appl. Phys. Lett.* 2012, 100, 123104-1-123104-3.

27. Kresse, G.; Furthmüller, J. Efficient Iterative Schemes for *Ab Initio* Total-Energy Calculations Using a Plane-Wave Basis Set. *Phys. Rev. B* 1996, 54, 11169-11186.

28. Perdew, J. P.; Zunger, A. Self-Interaction Correction to Density-Functional Approximations for Many-Electron Systems. *Phys. Rev. B* 1981, 23, 5048-5079.

29. Blöchl, P. E. Projector Augmented-Wave Method. Phys. Rev. B 1994, 50, 17953-17979.

30. Coy Diaz, H.; Addou, R.; Batzill, M. Interface Properties of CVD Grown Graphene Transferred onto MoS2(0001). *Nanoscale* 2014, 6, 1071-1078.

31. Khomyakov, P. A.; Giovannetti, G.; Rusu, P. C.; Brocks, G.; van den Brink, J.; Kelly, P. J. First-Principles Study of The Interaction and Charge Transfer between Graphene and Metals. *Phys. Rev. B* 2009, 79, 195425.

32. Michaelson, H. B. The Work Function of the Elements and its Periodicity. J. Appl. Phys. 1977, 48, 4729-4733.

33. Oshima, C.; Nagashima, A. Ultra-Thin Epitaxial Films of Graphite and Hexagonal Boron Nitride on Solid Surfaces. *J. Phys.: Condens. Matter* 1997, 9, 1.



Figure 1. Schematics of the process showing the fabrication steps of a back-gated MoS₂ field-effect transistor with Ni-etched-graphene sandwiched at metal-MoS₂ contacts. (a) Exfoliated graphene on a p^+ Si/SiO₂ substrate was first treated with Ni-mediated etching process to create large amount of zigzag edges¹³ on the graphene surface while pristine MoS₂ strip was exfoliated on another p^+ Si/SiO₂ substrate. (b) The treated graphene was peeled-off from the substrate using "Scotch-tape" technique and transferred onto another substrate with freshly-exfoliated MoS₂ strip on it. For comparison purposes, the treated graphene was aligned to cover half of the MoS₂ strip. (c) Ni metallization deposited as electrical contacts to the MoS₂ device forming both Ni-MoS₂ and Ni-treated-graphene-MoS₂ contacts. (d) Exposed graphene was removed completely by utilizing the Ni electrodes as self-aligned hard mask in combination with a benign oxygen plasma process.



Figure 2. Optical images showing a MoS_2 field-effect transistors array consisting of 5 Ni-contacted devices and 6 Ni-treated-graphene-contacted devices with channel lengths varying from 0.5 to 3 μ m, in steps of 0.5 μ m before (a) and after (b) removal of the exposed graphene by benign oxygen plasma.



Figure 3. (a) I_D - V_D characteristics of a typical Ni-contacted MoS₂ device shows negligible changes before and after the benign oxygen plasma process. (b) Contact resistance comparison for MoS₂ devices fabricated with 4 different types of contacts: Ni-MoS₂, Ni-single-layer-graphene-MoS₂, Ni-bilayergraphene-MoS₂ and Ni-treated-bilayer-graphene-MoS₂ contacts. The lowest R_C of our Ni-treated-bilayergraphene-contacted MoS₂ devices is as low as 200 Ω .µm, which shows ~40 times improvement compared to the Ni-contacted MoS₂ devices.



Figure 4. (a) I_D - V_D characteristics of both MoS₂ devices with and without the treated graphene as a sandwich layer. The on-current at $V_{DS} = 2$ V and $V_G = 50$ V shows ~10 times improvement, as a result of reduced contact resistance. (b) I_D - V_G characteristics of both MoS₂ devices with and without the treated graphene as a sandwich layer. Inset: I_D - V_G characteristics of the same MoS₂ devices in logarithmic scale. Extrinsic mobility of the typical Ni-treated-bi-layer-graphene-contacted MoS₂ device is 3 times higher than that of the Ni-contacted MoS₂ device.



Figure 5. Band structures of single layer MoS₂ interfaced with (a) Ni, (b) Ni-SLG, and (c) Ni-BLG, only the minority bands are shown here for magnetic systems. The blue, pink and orange dots represent the projected bands of MoS₂, graphene layer close to Ni, and graphene layer adjacent to MoS₂ respectively, with the projection weight indicated by the dot size. The black solid curves and red dashed curves show the positions of the Fermi level and conduction band minimum of MoS₂ respectively. The side views of the atomic structures and plane averaged charge differences Δn along the z direction are shown below the band structures in panels (d), (e) and (f). The Δn is obtained by subtracting the plane-averaged charge density of the composite slab from that of individual components of the slab using the same supercell, *i.e.* $\Delta n = n_{Ni-graphene-MoS_2}(z) - n_{Ni}(z) - n_{graphene}(z) - n_{MoS_2}(z)$.



Figure 6. (a) Plot of calculated Schottky barrier height as a function of the electrode work function, the electron affinity (EA) of MoS₂ is shown in the red dash line. (b) Schematic illustration of the potential shift at the interface of the Ni-BLG-MoS₂ system.

Low Resistance Metal Contacts to MoS₂ Devices with Nickel-Etched-Graphene Electrodes

Wei Sun Leong,[†] Xin Luo,^{‡,¥} Yida Li,[†] Khoong Hong Khoo,^{‡,¥} Su Ying Quek,^{*,‡} and

John T. L. Thong *, †

[†]Department of Electrical and Computer Engineering, National University of Singapore, Singapore 117583.

[‡]Department of Physics, Centre for Advanced 2D Materials and Graphene Research Centre, National University of Singapore, Singapore 117546.

^{*}Institute of High Performance Computing, 1 Fusionopolis Way, #16-16 Connexis, Singapore 138632.

*Address correspondence to elettl@nus.edu.sg (experiment); phyqsy@nus.edu.sg (theory)

S1. Average contact resistance on MoS2 devices fabricated using different electrodes

Table S1. The average contact resistance of MoS₂ devices fabricated using 5 types of contact structures: Ni-MoS₂, Ni-single-layer-graphene(SLG)-MoS₂, Ni-bi-layer-graphene(BLG)-MoS₂, Ni-treated-SLG-MoS₂, and Ni-treated-BLG-MoS₂ contacts on exfoliated MoS₂ of similar thickness (16 nm).

Types of electrodes	Number of samples	Contact resistance at back-gate bias = 50 V	
Ni-MoS ₂	5	$11 \pm 3 \Omega.mm$	
Ni-SLG-MoS ₂	2	$0.83 \pm 0.18 \ \Omega.mm$	
Ni-BLG-MoS ₂	3	$0.81 \pm 0.16 \ \Omega.mm$	
Ni-treated-SLG-MoS ₂	2	$1.59 \pm 1.08 \ \Omega.mm$	
Ni-treated-BLG-MoS ₂	5	$0.30 \pm 0.10 \ \Omega.mm$	





Figure S1. Cross-section schematic view of back-gated MoS₂ field-effect transistors and resistor network models at the metal-MoS₂ contacts with bilayer graphene (a) and treated bilayer graphene (b) as a sandwich layer, where $R_{surface}$ is resistance across the surface-contacted metal-graphene contacts, $R_{interlayer}$ is the tunneling resistance between graphene layers, $R_{G/MoS2}$ is the resistance between graphene and MoS₂ interface, R_{edge} is the resistance of the edge-contacted metal-graphene contacts, and particularly $R_{edge} \ll$ $R_{surface}$ and $R_{edge} \ll R_{interlayer}$.

<u>S3. Characterization of bilayer graphene after the Ni-catalyzed etching treatment</u>

Here, we characterize a piece of bilayer graphene (BLG) before and after the Ni-catalyzed etching treatment. Using the same recipe as described in main text, we first exfoliate a piece of BLG on a degenerately p-doped silicon substrate with 285 nm thick SiO₂ (Figure S2a). The as-exfoliated BLG was then treated with the Ni-catalyzed etching treatment. It was started with the deposition of a thin Ni film (2 nm) on the exfoliated graphene via thermal evaporation, followed by annealing at 580 °C for 10 min in a hydrogen ambient. After that, acid was used to remove the Ni. Figure S2b shows the optical image of the treated BLG. As can be seen, the treated BLG looked similar to when it was freshly-exfoliated although the Ni-catalyzed etching treatment is expected to create a significant amount of etched pits with well-defined zigzag edges on the graphene basal plane as mentioned in the main text.¹ This is because the size of etched pits formed in the graphene surface is in the range of 7 to 27 nm only (Figure S3), which is far beyond the optical resolution limit. In Figure S2c, we compare the Raman spectrum of the BLG when it was freshly-exfoliated and after it undergone the Ni-catalyzed etching treatment. As can be seen, the BLG remains defect-free after the treatment as there is no D-band signal captured at around 1350 cm⁻¹, which confirms the etched pits formed in the graphene surface are surrounded by zigzag edges. In addition, the full width at half maximum (FWHM) of the 2D-band signal changes significantly from 50.9 cm⁻¹ when it was as-exfoliated to 39.1 cm⁻¹ after the Ni-catalyzed etching treatment. The average FWHM of the 2D-band signal of 1600 spectra of the freshly-exfoliated BLG sample is 51.2 ± 1.2 cm⁻¹ (Figure S2d), which proves that the graphene is of bilayer.² However, the average FWHM of the 2D-band signal of 100 spectra of the treated BLG sample is 37.5 ± 3.4 cm⁻¹ (Figure S2d), which is between the range of single-laver $(27.5 \pm 3.8 \text{ cm}^{-1})$ and bilaver graphene $(51.7 \pm 1.7 \text{ cm}^{-1})$ as presented in an earlier Raman studies.² Apart from that, the average depth of etched pits is measured to be 0.52 ± 0.13 nm (Figure S3b), while the thickness of the BLG film is about 1.2 nm as measured by tapping mode atomic force microscopy. Overall, the results suggests that the etched pits are most likely to be formed in the uppermost graphene layer only while the bottom layer of the BLG remains as a perfect sp²-hybridized carbon layer.



Figure S2. Optical image of a bilayer graphene (a) when it was freshly-exfoliated and (b) after the Nicatalyzed etching treatment. (c) Raman spectrum of the bilayer graphene prior to and following the treatment. (d) The average full width at half maximum (FWHM) of the 2D-band signal of 1600 spectra of the bilayer graphene prior to and following the treatment.



Figure S3. (a) Typical 60° tilted SEM image of an etched bilayer graphene showing Ni particles sitting in the middle of each etched pit, which can be partially seen. (b) Typical AFM image of a bilayer graphene after removal of the Ni particles. Inset: Height profile along the dotted line.

<u>S4. Band structure of MoS2 interfaced with different electrodes</u>



Figure S4. (a) Band structure of isolated single layer MoS₂ in 4×4×1 supercell. Majority spin band structures for single layer MoS₂ interfacing with (b) Ni, (c) Ni-SLG and (d) Ni-BLG, respectively. The top views of their structures are shown at the bottom. The blue, pink and orange dot, respectively, represent the projected band of MoS₂, graphene layer close to Ni and MoS₂ side, and the weight is indicated by the dot size.

Table S2. The calculated Schottky barrier height for different types of interfaces with different k-point sampling of the Brillouin Zone. A smaller supercell is used to obtain the zigzag-edge-contacted Ni-graphene interfaces. Both set of values are very close, indicating the calculation is converged.

Convergence parameters Schottky barrier height	k-point: 3×3×1	k-point: 4×4×1
Ni-MoS ₂	0.804 eV	0.806 eV
Ni-SLG-MoS ₂	0.299 eV	0.290 eV
Ni-BLG-MoS ₂	0.343 eV	0.332 eV
Ni-treated-SLG-MoS ₂	0.375 eV	0.370 eV
Ni-treated-BLG-MoS ₂	0.265 eV	0.265 eV



Figure S5. Relaxed atomic structures and band structure of (a) Ni-BLG-MoS₂ interfaces, (b) Ni-treated-BLG-MoS₂ interfaces and (c) Ni-treated-SLG-MoS₂ interfaces in $3 \times 3 \times 1$ supercell. The blue and pink dots represent the projected band of MoS₂ and graphene layer, respectively, and the weight is indicated by the dot size. Both majority and minority spin band structures show a similar Schottky barrier height in Ni-BLG-MoS₂ and Ni-treated-BLG-MoS₂ interfaces, while the Schottky barrier height of Ni-treated-SLG-MoS₂ is 0.11 eV higher than that in the Ni-treated-BLG-MoS₂ as shown in Table S2.



Figure S6. Geometries used to model the (a) surface- and (b) edge-contacted Ni-graphene interfaces for NEGF-DFT calculations. Green, grey and white atoms represent Ni, C and H respectively.

References and Notes

1. Leong, W. S.; Gong, H.; Thong, J. T. L. Low-Contact-Resistance Graphene Devices with Nickel-Etched-Graphene Contacts. *ACS Nano* 2014, 8, 994-1001.

2. Hao, Y.; Wang, Y.; Wang, L.; Ni, Z.; Wang, Z.; Wang, R.; Koo, C. K.; Shen, Z.; Thong, J. T. L. Probing Layer Number and Stacking Order of Few-Layer Graphene by Raman Spectroscopy. *Small* 2010, 6, 195-200.