Record breaking bursts in a fiber bundle model of creep rupture

Zsuzsa Danku and Ferenc Kun*

Department of Theoretical Physics, University of Debrecen, P.O.Box: 5, Debrecen, H-4010, Hungary

Correspondence*: Ferenc Kun Department of Theoretical Physics, University of Debrecen, P.O.Box: 5, Debrecen, H-4010, Hungary, ferenc.kun@science.unideb.hu

Research Topic

ABSTRACT

We investigate the statistics of record breaking events in the time series of crackling bursts in a fiber bundle model of the creep rupture of heterogeneous materials. In the model fibers break due to two mechanisms: slowly accumulating damage triggers bursts of immediate breakings analogous to acoustic emissions in experiments. The rupture process accelerates such that the size of breaking avalanches increases while the waiting time between consecutive events decreases towards failure. Record events are defined as bursts which have a larger size than all previous events in the time series. We analyze the statistics of records focusing on the limit of equal load sharing (ELS) of the model and compare the results to the record statistics of sequences of independent identically distributed random variables. Computer simulations revealed that the number of records grows with the logarithm of the event number except for the close vicinity of macroscopic failure where an exponential dependence is evidenced. The two regimes can be attributed to the dominance of disorder with small burst sizes and to stress enhancements giving rise efficient triggering of extended bursts, respectively. Both the size of records and the increments between consecutive record events are characterized by power law distributions with a common exponent 1.33 significantly different from the usual ELS burst size exponents of fiber bundles. The distribution of waiting times follows the same behavior, however, with two distinct exponents for low and high loads. Studying the evolution of records we identify a load dependent characteristic scale of the system which separates slow down and acceleration of record breaking as failure is approached.

Keywords: Fracture, crackling noise, fiber bundle model, avalanche, record breaking statistics

1 INTRODUCTION

The fracture of heterogeneous materials proceeds in bursts generated by newly nucleating cracks or by intermittent propagation steps of crack fronts **Alava et al.** (2006). Measuring acoustic emissions of breaking bursts the fracture process can be decomposed into a time series of crackling events, which contains valuable information about the microscopic dynamics of fracture **Deschanel et al.** (2009); **Salminen et al.** (2002); **Rosti et al.** (2010). The analysis of crackling time series has usually been focused on the integrated statistics of events such as the probability distribution of the size (energy) and duration of bursts and of the waiting time between consecutive events. All these distributions are found to have

power law functional form with exponents having a high degree of robustness with respect to materials' details **Deschanel et al.** (2009); **Salminen et al.** (2002); **Rosti et al.** (2010).

In applications materials are often subject to constant sub-critical loads which may lead to failure in a finite time. Such creep rupture processes are typical for components of engineering constructions and they also play a crucial role in the emergence of natural catastrophes such as land slides, stone and snow avalanches, and earthquakes Nechad et al. (2005b,a); Petri et al. (1994); Garcimartin et al. (1997); Main (2000); Santucci et al. (2004); Deschanel et al. (2006); Santucci et al. (2006); Kovács et al. (2008); Ramos et al. (2013). It is of high practical importance to understand how the creeping system approaches macroscopic failure using the data of acoustic monitoring Garcimartin et al. (1997); Nechad et al. (2005b); Kovács et al. (2008); Deschanel et al. (2009). Computer simulations of discrete stochastic models of creep rupture are indispensable to analyze how the time series of crackling events evolves and to identify possible signatures of the imminent catastrophe. A unique feature of this evolution is that the rupture process is highly non-stationary, i.e. approaching failure larger and larger bursts are triggered while the process accelerates indicated by the decreasing waiting time between consecutive events Garcimartin et al. (1997); Nechad et al. (2005b). On the macro-scale, the strain rate has been found to exhibit time-to-failure power law behavior Nechad et al. (2005b,a); Deschanel et al. (2006, 2009) which is accompanied by the emergence of an Omori-type acceleration of the rate bursts on the micro-scale Danku and Kun (2013a).

In the present paper we investigate the evolution of the crackling time series of creep rupture by analyzing the statistics of record breaking (RB) bursts in a fiber bundle model (FBM) of creep failure. Records are bursts which have the largest size since the beginning of the time series, hence, their behavior involves extreme value statistics Galambos (1978); Arnold et al. (2011). Motivated mainly by climate research Redner and Petersen (2006) and by the investigation of earthquake time series Yoder et al. (2010); Davidsen et al. (2008); Shcherbakov et al. (2013) interesting analytical results have recently been obtained for the record breaking statistics of sequences of independent identically distributed (IID) random variables. The statistics of records has proven useful to identify trends in time series of measurements and to infer correlations of events Shcherbakov et al. (2013); Yoder et al. (2010). Focusing on the limit of equal load sharing of our FBM we demonstrate that the record breaking statistics of crackling events provides novel insight into rupture phenomena. Comparing the outcomes of large scale computer simulations to the corresponding IID results on records we can identify regimes of the failure process dominated by the disorder of materials and by the enhanced triggering of breaking avalanches towards failure. The size distribution of records proved to have a power law form with a novel exponent of equal load sharing FBMs. Simulations revealed the emergence of a load dependent characteristic record rank which separates slow down and acceleration of record breaking when approaching failure.

2 MATERIAL & METHODS

To investigate the time series of breaking bursts we use a generic fiber bundle model (FBM) of creep rupture introduced recently **Kun et al.** (2007, 2009, 2008); **Halász et al.** (2012); **Danku and Kun** (2013a,b). We briefly summarize the main ingredients of the model construction emphasizing aspects most relevant for the present study.

2.1 FIBER BUNDLE MODEL WITH TWO BREAKING MECHANISMS

In the framework of the model the sample is discretized in terms of a bundle of parallel fibers which have a brittle response with identical Young modulus E. The bundle is subject to a constant external load σ_0 below the fracture strength σ_c of the system parallel to the fibers' direction. Fibers are assumed to break due to two physical mechanisms: immediate breaking occurs when the local load σ_i on fibers exceeds their fracture strength σ_{th}^i , i = 1, ..., N. Under a sub-critical load $\sigma_0 < \sigma_c$ this breaking mechanism would lead to a partially failed configuration with an infinite lifetime. Time dependence is introduced in such a way that those fibers, which remained intact, undergo an aging process accumulating damage c(t). The damage mechanism represents the environmentally induced slowly developing aging of materials such as corrosion cracking and thermally or chemically activated degradation **Kun et al.** (2007, 2009, 2008); **Halász et al.** (2012); **Danku and Kun** (2013a) similar to damage dynamics based models of rock fracture developed for instance in **Turcotte et al.** (2003). The rate of damage accumulation Δc_i is assumed to have a power law dependence on the local load

$$\Delta c_i = a \sigma_i^{\gamma} \Delta t, \tag{1}$$

where a is a constant and the exponent γ controls the time scale of the aging process with $0 \leq \gamma < +\infty$. The total amount of damage $c_i(t)$ accumulated up to time t is obtained by integrating over the entire loading history of fibers $c_i(t) = a \int_0^t \sigma_i(t')^{\gamma} dt'$. Fibers can tolerate only a finite amount of damage so that when $c_i(t)$ exceeds the local damage threshold c_{th}^i the fiber breaks. Each breaking event is followed by a redistribution of load over the remaining intact fibers. Two limiting cases of load sharing are usually considered in FBMs: under equal load sharing (ELS) conditions all the intact fibers keep the same amount of load so that the load on a single fiber is $\sigma_i = N\sigma_0/(N-i)$ after the breaking of i fibers. ELS realizes the mean field limit of FBMs where no stress heterogeneity can arise. In the opposite limit of localized load sharing (LLS) the load of broken fibers is equally redistributed solely over their intact nearest neighbors in the bundle. LLS leads to a high stress concentration around failed regions and it gives rise to the emergence of spatial correlations between consecutive breaking events. In the present study we consider only the ELS case where the homogeneous stress field hinders spatial correlation. In the model the quenched heterogeneity of materials is represented by the randomness of breaking thresholds $\sigma_i^{th}, c_i^{th}, i = 1, \ldots, N$. For simplicity, for both threshold values we assume uniform distributions between zero and one. Since under ELS the value of the exponent γ only controls the time scale of creep **Danku and Kun** (2013a) the damage parameters were fixed to $\gamma = 1$ and a = 1.

When the load is put on the bundle, first some week fibers break immediately which may generate further breakings until a stable configuration is reached where all remaining intact fibers can sustain the elevated load. The time evolution of the creeping system starts from this partially failed configuration **Kun et al.** (2007, 2009). The present setup of the model implies that the critical stress where immediate catastrophic failure occurs is equal to its static value $\sigma_c = 0.25$ **Kun et al.** (2007, 2009, 2008). In the presentation of the results the constant external load level will be characterized by the ratio $\sigma_s = \sigma_0/\sigma_c$ which can take values in the range $0 < \sigma_s \leq 1$.

2.2 BURSTS DRIVEN BY DAMAGE SEQUENCES

The separation of time scales of the slow damage process and of immediate breaking leads to a highly complex time evolution in agreement with experiments **Kun et al.** (2009, 2008); **Halász et al.** (2012); **Danku and Kun** (2013a,b): starting from the initial configuration damaging fibers break slowly one-by-one gradually increasing the load on the remaining intact fibers. After a certain number Δ_d of damage breakings the load increment becomes sufficient to induce the immediate breaking of a fiber which in turn triggers an entire burst of immediate breakings. As a consequence, the time evolution of creep rupture occurs as a series of bursts corresponding to the nucleation and propagation of cracks, separated by silent periods of slow damaging. The size of bursts Δ is defined as the number of fibers breaking in avalanches. The number of fibers breaking in a damage sequence and its duration determine the length of the damage sequence Δ_d and the physical waiting time T between consecutive events, respectively.

Figure 1 shows a representative example of the time series of bursts as the system evolves towards failure. In order to have a clear view on the details of the sequence of events we intentionally used a relatively small system of $N = 10^5$ fibers subject to the load $\sigma_s = 0.001$ which gave rise to 9793 bursts. The size Δ of bursts is shown in the figure as a function of the discrete time, i.e. order number or natural time $n = 1, 2, \ldots$ so that no information is presented about the physical waiting time T elapsed between the bursts. Strong fluctuations of the burst size Δ can be observed which is caused by the



Figure 1. Time series of bursts in a mean field (ELS) simulation of the FBM of creep. For demonstration purposes a relatively small system $N = 10^5$ is presented at the load $\sigma_s = 0.001$ giving rise to 9793 avalanches. In order to have a clear view on the structure of the time series, sub-sequences starting at record breaking events are highlighted by different colors. The horizontal lines serve to demonstrate the increments between consecutive record bursts.

quenched disorder of fiber strength. The time series has a non-stationary behavior which is indicated by the increasing average size of bursts. Of course, the physical waiting time T decreases between consecutive events, however, this information is not visible in this representation. (The analysis of waiting times of the model can be found in **Kun et al.** (2008, 2009); **Danku and Kun** (2013a).)

A record of the time series is a burst which has a size Δ_r larger than any previous events. Consecutive records are identified by their increasing rank k as $k = 1, 2, 3, \ldots$ which occurred as the n_k th burst of the complete time series. The first burst n = 1 is by definition considered to be a record of rank k = 1 with $n_1 = 1$. In the example of Fig. 1 all together 18 record breaking events are identified Δ_r^k ($k = 1, \ldots, 18$), which are highlighted by using different colors for the consecutive smaller events. It can be observed that RB events form a sub-sequence of bursts with monotonically increasing size, however, both the record size and the number of avalanches between two consecutive records exhibit strong fluctuations. In order to characterize these features we introduce the size increment δ_k and the waiting time m_k between two records with the definitions

$$\delta_k = \Delta_r^{k+1} - \Delta_r^k, \qquad \text{and} \qquad m_k = n_{k+1} - n_k, \tag{2}$$

respectively. Note that the catastrophic burst which breaks all remaining intact fibers and destroys the bundle is not included in the time series so that the last burst in the bundle may not be an RB event.

3 RESULTS

To investigate the occurrence of record breaking events during the rupture process computer simulations were carried out for a system of size $N = 10^7$ fibers averaging over 10^4 realizations of the threshold disorders at each load value σ_s . The external load σ_s was varied over a broad range $0.001 \le \sigma_s \le 0.9$, where the limits were set to have a sufficient number of bursts in the time series. We identify all record breaking avalanches Δ_r^k that occur up to macroscopic failure of the bundle and carry out a detailed analysis of their statistics.



Figure 2. (a) Fraction of fibers breaking in bursts $\langle d_{burst} \rangle$ and due to damage $\langle d_{dam} \rangle$ as function of load σ_s together with the number of bursts $\langle N_\Delta \rangle$. The quantity $\langle d_{burst} \rangle$ was calculated as the sum of the size of all bursts that occurred up to failure. The straight line has slope 0.87, furthermore, the vertical dashed line indicates the position of the characteristic load $\sigma_s^* = 0.48$. (b) Ratio of the average size of bursts $\langle \Delta \rangle$ and of damage sequences $\langle \Delta_d \rangle$ as a function of the order number *n* of bursts for several load values. (c) Average size of the largest record breaking event $\langle \Delta_r^{max} \rangle$ and the average value of the largest waiting time $\langle m^{max} \rangle$ between consecutive records as function of load. All quantities are normalized by the number of fibers N in the bundle. The upper and lower straight lines have slope 0.625 and 0.65, respectively.

3.1 NUMBER OF RECORD BREAKING AVALANCHES

An important feature of our system is that under low load values most of the fibers break due to slow damaging since the resulting load increments are too small to trigger extended bursts of immediate breakings. Figure 2(a) shows that the fraction of fibers breaking in avalanches $\langle d_{burst} \rangle$ and due to damage $\langle d_{dam} \rangle$ are monotonically increasing and decreasing functions of the external load σ_s , respectively. The two curves intersect each other at the characteristic load $\sigma_s^* \approx 0.48$, which coincides with the position of the maximum of the average number of avalanches $\langle N_{\Delta} \rangle$. The result demonstrates that for $\sigma_s < \sigma_s^*$ damage dominates the failure process, while the vicinity of catastrophic failure $\sigma_s > \sigma_s^*$ is controlled by the bursting activity with large burst sizes Δ and a decreasing number N_{Δ} of bursts (see also **Kun et al.** (2008)).

Figure 3(a) presents the average number of records $\langle N_n \rangle$ that occurred until n avalanches have been generated in the time series at several load values. Due to the breaking dynamics described above at low loads avalanches remain small typically comprising a few breaking fibers, and hence, new records mainly occur close to macroscopic failure. For instance, at loads $\sigma_s \leq 0.01$ the number of records has very low values $\langle N_n \rangle < 3$ up to large n followed by a fast increase in the vicinity of the failure point. As σ_s increases the qualitative form of the $\langle N_n \rangle$ curves remains the same, they just shift to higher record numbers due to the more intensive triggering of larger bursts at high loads. The most important feature of the record number $\langle N_n \rangle$ is that it has a logarithmic dependence on n over a broad range, which is in agreement with the analytic prediction of the logarithmic dependence of record numbers of IIDs on the close vicinity of macroscopic failure disorder dominates the process of creep rupture, and the occurrence of breaking avalanches can be well approximated as a stochastic process of IIDs. However, close to failure the increase of the stress on single fibers results in enhanced triggering which in turn gives rise to a sudden increase of records. The complete curves of $\langle N_n \rangle (n)$ can be characterized by the functional form

$$\langle N_n \rangle = A + B \ln n + C \exp\left[(n/D)^{\xi}\right],$$
(3)

where the exponential term describes the rapid generation of high rank records close to catastrophic failure. It can be observed in Fig. 3(a) that Eq. (3) provides an excellent fit of the numerical data over the complete load range considered. The additive parameter A has the same value A = 0.38 for all loads, while the multiplication factor B increases from 0.16 to 0.87 in the load range considered (see Fig. 3(b)). The shape of the $\langle N_n \rangle$ curves in the accelerating regime is controlled by the exponent ξ which is nearly constant $\xi \approx 1.5$ for loads below σ_s^* then it decreases to 0.33 as σ_s increases in Fig. 3(b). The scale parameter D mainly sets the transition point between the two regimes dominated by disorder and by



Figure 3. (a) Average number of records $\langle N_n \rangle$ as a function of the total number of avalanches *n* for several load values. For low record numbers logarithmic dependence is evidenced, which is followed by a faster exponential increase. The continuous black lines represent fits with Eq. (3). (b, c) Fitting parameters *B*, ξ , and *D* of Eq. (3) as function of the external load σ_s . (d) Probability distribution of the total number of records N_n^{tot} occurred up to failure for several load values. The distributions obtained at different loads are rescaled with the corresponding average and standard deviation. The continuous line represents the standard Gaussian Eq. (4).

stress enhancement. It can be seen in Fig. 3(c) that D increases with the external load and has a maximum in the vicinity of σ_s^* , which is consistent with the behaviour of the total number of bursts $\langle N_{\Delta} \rangle$ in Fig. 2(a) reflecting the overall dominance of damage and bursts in the failure process on the two sides of σ_s^* . To support the emergence of a characteristic event number D separating different regimes of bursting activity, Fig. 2(b) presents the ratio of the average size of bursts $\langle \Delta \rangle (n)$ and the average size of the damage sequence $\langle \Delta_d \rangle (n)$ that initiated the *n*th event. At the beginning of the process a large number of fibers must break randomly one-by-one in damage sequences until a small burst of size 1-2 fibers is initiated giving rise to $\langle \Delta \rangle / \langle \Delta_d \rangle < 1$. Comparing to Fig. 3(a) the onset of the rapid exponential increase of record breakings corresponds to the event number from where extended bursts are triggered by shorter damage sequences due to the effect of stress enhancements. As the consequence of the increasing burst size and shortening damage sequences it becomes more and more probable that a record gets broken after a fewer bursts leading to the exponential increase of the record number.

Figure 3(b) shows that the probability distribution $p(N_n^{tot}, \sigma_s)$ of the total number of records accumulated up to failure has a Gaussian form. The distributions $p(N_n^{tot}, \sigma_s)$ obtained at different loads were rescaled by the corresponding average $\langle N_n^{tot} \rangle$ and standard deviation $\sigma_{N_n^{tot}}$ of the total number of records which results in a high quality collapse in the figure. The scaling function has a good agreement with the standard Gaussian

$$p(x) = \frac{1}{\sqrt{2\pi}} \exp\left(-x^2/2\right),$$
 (4)

which has been predicted for RB sequences of IIDs **Arnold et al.** (2011); **Shcherbakov et al.** (2013). The Gaussian functional form prevails in spite of the complex effect of the acceleration of the occurrence of



Figure 4. Size distribution of record breaking bursts (a) and their increments (c) for several load values. (b) and (d) demonstrate that rescaling the distributions with the external load high quality collapse of the curves can be achieved. The continuous lines in (b) and (d) represent fits with Eq. (6).

records towards failure. Deviations can be observed at the tails of the distribution which may indicate a slight right-handed asymmetry.

3.2 STATISTICS OF RECORD SIZES AND WAITING TIMES

Recently, it has been shown that in our model the size distribution of avalanches $p(\Delta)$ accumulating all crackling events up to failure during the creep process follows a power law distribution **Kun et al.** (2008, 2009)

$$p(\Delta) \sim \Delta^{-\tau},$$
 (5)

where the value of the exponent τ coincides with the usual mean field exponent of FBMs $\tau = 5/2$ **Kloster et al.** (1997). As the external load approaches the critical value $\sigma_s \rightarrow 1$ a crossover is obtained to a lower exponent $\tau = 3/2$ **Kun et al.** (2008) in agreement with the mean field prediction of simple FBMs subject to a quasi-statically increasing load **Pradhan et al.** (2010, 2005); **Raischel et al.** (2006).

Figure 4(a) presents the size distribution $p(\Delta_r, \sigma_s)$ of record breaking bursts accumulating all records up to failure at different load values. The distributions can be well described by a power law followed by a finite size cutoff of exponential form. Since at higher loads larger avalanches are triggered the cutoff of the distributions shifts to higher values but the functional form remains the same for all loads. Figure 4(b) illustrates that rescaling the two axis in Fig. 4(a) with appropriate powers of the external load a high quality data collapse can be achieved. The result implies that record size distributions obtained at different loads obey the scaling structure

$$p(\Delta_r, \sigma_s) = \Delta_r^{-\tau_r} \phi(\Delta_r / \sigma_s^{\alpha}), \tag{6}$$

where the exponent α controls the load dependence of the cutoff record

$$\langle \Delta_r^{max} \rangle \sim \sigma_s^{\alpha}. \tag{7}$$

Frontiers in Interdisciplinary Physics



Figure 5. (a) Probability distribution of waiting times $p(m, \sigma_s)$ between consecutive records for several values of the external load σ_s . In (b) and (c) the same distributions are presented after rescaling the two axis with powers of the external load σ_s separately above and below σ_s^* , respectively. The good quality data collapse demonstrates the validity of the scaling structure Eq. (8).

The power law dependence of the cutoff record size $\langle \Delta_r^{max} \rangle$ is also confirmed by Fig. 2(c), where the largest records Δ_r^{max} of single simulations were directly averaged. Best fit is obtained with the exponent $\alpha = 0.65$ which provides also the best collapse in Fig. 4(b). Note that due to the normalization of the distributions the scaling exponent used for the transformation along the vertical axis has to be equal to the product of τ_r and α which is explicitly indicated in Fig. 4(b). The size distribution exponent of record bursts $\tau_r = 1.33 \pm 0.03$ proved to be significantly smaller than the usual mean field burst size exponents of FBMs **Kun et al.** (2008, 2009); **Kloster et al.** (1997); **Pradhan et al.** (2005, 2010), which is the consequence of the relatively high frequency of large burst sizes in the RB sequence with respect to the complete time series. The short flat region for the smallest bursts occurs due to down sampling of small sized events in the RB sequence. To fit the scaling function in Fig. 4(b) the cutoff function $\phi(x)$ was assumed to have a stretched exponential form $\phi(x) \sim \exp(-(x/x_0)^{\beta})$ with $\beta = 0.65$. It is important to emphasize that the distribution $p(\Delta_r, \sigma_s)$ has a homogeneous evolution with increasing external load, i.e. the exponent τ_r remains constant when the critical load is approached $\sigma_s \to 1$.

For the advancement of the RB sequence of bursts during the evolution of the rupture process the size increments $\delta_k = \Delta_r^{k+1} - \Delta_r^k$ between consecutive records carry also interesting information. Figure 4(c) presents that the distribution $p(\delta_r, \sigma_s)$ of increments δ_r has a qualitatively similar behavior to record sizes $p(\Delta_r, \sigma_s)$, i.e. power laws are obtained followed by an exponential cutoff as described by Eq. (6). Careful scaling analysis in Fig. 4(d) shows that both the value of the exponent τ_r of the power law regime and the scaling exponent α of σ_s have the same values for the two distributions, the only difference is that the cutoffs of increments are smaller than the one of record sizes.

After a record occurred as the n_k th avalanche of the time series it gets broken after a certain number of events by the n_{k+1} th avalanche. The waiting time m_k between RB avalanches defined by Eq. (2) is an important characteristic quantity of the RB sequence of bursts. Figure 5(a) presents the accumulated statistics of waiting times m considering all records k in the RB sequence for several load values. Based on the statistics of extremes **Galambos** (1978), for IIDs a power law behavior is expected $p(m) \sim m^{-z}$ with the exponent $z_{IID} = 1$ **Arnold et al.** (2011). It can be observed in the figure that our results are generally consistent with the IID prediction, however, distributions $p(m, \sigma_s)$ obtained below and above σ_s^* form two groups of different power law exponents. Figures 5(b) and (c) demonstrate that rescaling mand the distributions $p(m, \sigma_s)$ with appropriate powers of the external load σ_s , good quality data collapse can be achieved in both load regimes. The scaling structure is similar to Eq. (6)

$$p(m) = m^{-z}\psi(m/\sigma_s^{\alpha}),\tag{8}$$

however, both exponents z and α proved to have different values below and above the characteristic load σ_s^* . In Figures 5(b) and (c) best collapse is obtained with the exponents z = 0.72, $\alpha = -1.45$ ($\sigma_s^* < \sigma_s$)

and z = 1.15, $\alpha = 0.625$ ($\sigma_s^* > \sigma_s$). The value of z reflects an interesting aspect of the dynamics of the creep process: the low value of $z < z_{IID}$ at high loads shows that long waiting times more frequently occur than for IID. The reason is that due to the large bursts triggered under high external loads it takes longer for the system to break a record. At low loads the waiting time exponent z is slightly larger than the IID prediction implying an elevated frequency of short waiting times with respect to IIDs. Note that α has different signs in the two regimes corresponding to the increasing and decreasing behavior of the cutoff of the distribution with increasing load. An independent test of the load dependence of the cutoff waiting time $\langle m^{max} \rangle$ is shown in Fig. 2(c), where m^{max} was directly averaged over the simulations. A maximum is obtained at σ_s^* in agreement with the scaling behavior in Figs. 5(b) and (c). The flattening of the distributions $p(m, \sigma_s)$ for low m values and the small bump close to the cutoff observed for low loads in Fig. 5(c) are caused by the finite system size and by the distribution of the time needed to break the first record, respectively.

3.3 EVOLUTION OF THE SEQUENCE OF RECORDS

The creeping system approaches macroscopic failure through an accelerating sequence of bursts of increasing size. In order to understand how record breaking events occur during this evolution we evaluated average values of the characteristic quantities of single records as a function of their rank k. In Fig. 6(a) the average record size $\langle \Delta_r^k \rangle$ has the same generic form for all loads, i.e. a nearly exponential increase is obtained with a slight minimum of the derivative of the curves for intermediate ranks. Note that for a given value of k a record can have a higher value at low loads than at higher ones, e.g. at k = 15 the corresponding record burst is significantly larger at $\sigma_s = 0.001$ than at $\sigma_s = 0.1$ in spite of the two orders of magnitude higher external load in the second case. The reason is that for avalanche triggering the load on single fibers is the most relevant quantity, hence, at the generation of the kth record the creeping system can be closer to catastrophic failure at lower loads than at higher ones, which implies larger burst sizes. In order to gain information about the rate of increase of records, we determined the relative increments of consecutive RB events defined as the ratio δ_k/Δ_r^k . Figure 6(b) shows that at the beginning of the rupture process the average $\langle \delta_k / \Delta_r^k \rangle$ starts from a high value simply because the first record has size $\Delta_r^1 = 1$ and it gets typically broken by a burst of size $\Delta_r^2 = 2$ or $\Delta_r^2 = 3$. Then the relative increment rapidly decreases to the vicinity of 0.25. The remarkable result is that for records of the highest rank $\langle \delta_k / \Delta_r^k \rangle$ tends to 1, which implies that as the system approaches macroscopic failure record breakings occur by nearly doubling the size of the previous record. Hence, not only the record sizes but also the increments form a monotonically increasing sequence when approaching failure.

As the external load increases larger avalanches are triggered in the system and they occur with an increasing rate **Danku and Kun** (2013a). Based on this general tendency it could be expected that the average time $\langle n_k \rangle$ where the *k*th record appears is a decreasing function of the external load σ_s . Figure 6(c) shows that for low load values just the opposite happens: records of a given rank *k* occur later after a larger number of avalanches. The reason is that as the load increases early records get larger, and hence, they are more difficult to overcome. The situation changes at the characteristic load σ_s^* so that in the range $\sigma > \sigma_s^*$ the average record time $\langle n_k \rangle$ decreases with increasing load.

The time series presented in Fig. 1 does not contain information about the physical time elapsed between events. However, the acceleration of the system can still be inferred from the natural time n, because the number of bursts between RB events decreases when approaching catastrophic failure. Due to this acceleration the average waiting time $\langle m_k \rangle$ is expected to decrease between consecutive records. It is interesting to note that for higher loads the decreasing branch of $\langle m_k \rangle$ is preceded by a rapidly increasing regime indicating the slow down of record breaking before acceleration sets on. The maximum of $\langle m_k \rangle$ already develops for the lowest loads with the position $k^* = 2$ and it gradually shifts to $k^* = 13$ for the highest ones. Comparing Figs. 6(b) and (d) it can be seen that the record rank k^* of the maximum of $\langle m_k \rangle$ falls close to the position of the minimum of the relative increments $\langle \delta_k / \Delta_r^k \rangle$. The result demonstrates the emergence of a characteristic time scale n_{k^*} of the system which separates slow down and acceleration of



Figure 6. Characteristic quantities of single records: the average value of the size $\langle \Delta_r^k \rangle$ (*a*), and relative increments $\langle \delta_k / \Delta_r^k \rangle$ of record breaking events (*b*). In (*b*) the horizontal dashed line highlights the limit value 1. Time of occurrence $\langle n_k \rangle$ (*c*) and waiting time $\langle m_k \rangle$ between consecutive records (*d*).

the dynamics of record breaking. This is also in agreement with the behavior of record numbers in Fig. 3(a) so that n_{k^*} approximately coincides with the onset time of the exponential increase of $\langle N_n \rangle$.

4 DISCUSSION

We investigated the statistics of records in a sequence of crackling avalanches which occur during the creep rupture of heterogeneous materials. Synthetic sequences of bursts were generated by computer simulations of a realistic fiber bundle model where slowly developing damage triggers avalanches of immediate breaking of fibers. The bundle is subject to a constant external load below the fracture strength of the system. We analyzed the mean field limit of the model where all fibers keep the same load so that no spatial correlation develops between local failure events.

Record events are defined solely based on the burst size, i.e. a record is a bursts whose size is larger than that of all previous bursts. This way a monotonically increasing sub-sequence of crackling events is identified. Computer simulations revealed that during the evolution of the rupture process the average number of records increases logarithmically with the number of avalanches except for the close vicinity of macroscopic failure where an exponential form is evidenced. Additionally, the total number of records obtained up to failure at different load values has a Gaussian distribution. These findings are in agreement with the robust analytic predictions on the RB statistics of sequences of independent identically distributed random variables which shows that the beginning of the creep process is mainly controlled by the quenched disorder of the system. The enhanced triggering close to failure due to the rapidly increasing load on single fibers is responsible for the exponential acceleration of record numbers.

The size of records proved to have a power law distribution with an exponent 1.33 significantly lower than the usual mean field exponents 5/2 and 3/2 of the burst sizes of FBMs. The size increments between consecutive records are found to have the same scaling structure and the value of exponents as the record size. To prove the independence of the exponents on the external load a careful data collapse analysis was performed. The probability distribution of waiting times between consecutive events has also a power

law functional form, however, with different exponents below and above the characteristic load σ_s^* . In order to characterize the evolution of the sequence of records we studied the average value of the relative increment and of the waiting time between consecutive events as a function of the record rank. Both quantities show the emergence of a load dependent characteristic scale in the system: at the beginning a slow down of record breaking occurs with an increasing waiting time and decreasing relative increment. Beyond a characteristic record rank k^* the approach to failure results in an acceleration of record breaking with decreasing waiting times and increasing relative increments. In our study the disorder of materials was represented by uniformly distributed failure thresholds. We repeated the complete RB analysis for Weibull distributed disorder varying the Weibull exponent. It has to be emphasized that the qualitative behavior of the results and the value of the exponents of the record size, increment and waiting time distributions all proved to be universal, only the characteristic load σ_s^* , furthermore, the scaling and cutoff exponents α and β depend on the disorder.

Recently, the record breaking statistics of driven threshold models of complex systems has been analyzed in **Shcherbakov et al.** (2013). These are cellular automata models of self organized criticality where the slow external driving leads to the emergence of a steady state characterized by intermittent avalanches of relaxation events. Comparing the statistics of records of the models to the corresponding results of IIDs the authors could point out correlations in the complex spatio-temporal evolution of avalanches. The most prominent deviation from IIDs was found for the Olami-Feder-Christensen model **Olami et al.** (1992) where the number of records proved to increase as a power of the logarithm of the avalanche number. The main difference of the dynamics of our FBM and the above models is that during creep both the size and the rate of avalanches increase so that no steady state arises. Hence, the comparison to IIDs in our case helped to determine regimes controlled either by disorder or by the increasing stress level of intact fibers. Record breaking statistics of inter-event times in aftershock sequences of earthquakes has recently been studied in **Yoder et al.** (2010). Based on the non-homogeneous Poissonian process describing the rate of events, a power law behavior of the record number was obtained following the logarithmic increase. Our study demonstrates that the investigation of the record breaking statistics of the time series of crackling events reveals also interesting novel aspects of rupture phenomena.

ACKNOWLEDGMENT

This research was supported by the European Union and the State of Hungary, co-financed by the European Social Fund in the framework of TÁMOP 4.2.4. A/2-11-1-2012-0001 "National Excellence Program". This work was supported by the European Commissions by the Complexity-NET pilot project LOCAT and by NFÜ under the contract ERANET_HU_09-1-2011-0002. We also acknowledge the projects TAMOP-4.2.2.A-11/1/KONV-2012-0036 and OTKA K84157.

REFERENCES

Alava, M., Nukala, P. K., and Zapperi, S. (2006), Statistical models of fracture, *Adv. in Phys.*, 55, 349476 Arnold, B. C., Balakrishnan, N., and Nagaraja, H. N. (2011), Records (John Wiley & Sons)

- Danku, Z. and Kun, F. (2013a), Creep rupture as a non-homogeneous poissonian process, *Sci. Rep.*, 3, 2688; DOI:10.1038/srep02688
- Danku, Z. and Kun, F. (2013b), Temporal and spacial evolution of bursts in creep rupture, *Phys. Rev. Lett.*, 111, 084302
- Davidsen, J., Grassberger, P., and Paczuski, M. (2008), Networks of recurrent events, a theory of records, and an application to finding causal signatures in seismicity, *Phys. Rev. E*, 77, 066104
- Deschanel, S., Vanel, L., Godin, N., and Ciliberto, S. (2009), Experimental study of crackling noise: conditions on power law scaling correlated with fracture precursors, *J. Stat. Mech.*, P01018

- Deschanel, S., Vanel, L., Vigier, G., Godin, N., and Ciliberto, S. (2006), Statistical properties of microcracking in polyurethane foam under tensile test, influence of temperature and density, *Int. J. Fract.*, 140, 87–98
- Galambos, J. (1978), The Asymptotic Theory of Extreme Order Statistics (Wiley, New York)
- Garcimartin, A., Guarino, A., Bellon, L., and Ciliberto, S. (1997), Statistical properties of fracture precursors, *Phys. Rev. Lett.*, 79, 3202
- Halász, Z., Danku, Z., and Kun, F. (2012), Competition of strength and stress disorder in creep rupture, *Phys. Rev. E*, 85, 016116
- Kloster, M., Hansen, A., and Hemmer, P. C. (1997), Burst avalanches in solvable models of fibrous materials, *Phys. Rev. E*, 56, 26152625
- Kovács, K., Nagy, S., Kun, F., Herrmann, H. J., and Pagonabarraga, I. (2008), Critical ruptures in a bundle of slowly relaxing fibers, *Phys. Rev. E*, 77, 036102
- Kun, F., Carmona, H. A., Jr, J. S. A., and Herrmann, H. J. (2008), Universality behind basquin's law of fatigue, *Phys. Rev. Lett.*, 100, 094301
- Kun, F., Costa, M. H., Filho, R. N. C., Jr, J. S. A., Soares, J. B., and Herrmann, H. J. (2007), Fatigue failure of disordered materials, *J. Stat. Mech.*, 2007, P02003
- Kun, F., Halász, Z., Andrade, J. S., and Herrmann, H. J. (2009), Crackling noise in sub-critical fracture of heterogeneous materials, J. Stat. Mech., 2009, 01, P01021
- Main, I. G. (2000), A damage mechanics model for power-law creep and earthquake aftershock and foreshock sequences, *Geophys. J. Int.*, 142, 151
- Nechad, H., Helmstetter, A., Guerjouma, R. E., and Sornette, D. (2005a), Andrade and critical time to failure laws in fiber-matrix composites: Experiments and model, *J. Mech. Phys. Solids*, 53, 1099
- Nechad, H., Helmstetter, A., Guerjouma, R. E., and Sornette, D. (2005b), Creep ruptures in heterogeneous materials, *Phys. Rev. Lett.*, 94, 045501
- Olami, Z., Feder, H. J. S., and Christensen, K. (1992), Self-organized criticality in a continuous, nonconservative cellular automaton modeling earthquakes, *Phys. Rev. Lett.*, 68, 1244–1247
- Petri, A., Paparo, G., Vespignani, A., Alippi, A., and Costantini, M. (1994), Experimental evidence for critical dynamics in microfracturing processes, *Phys. Rev. Lett.*, 73, 3423
- Pradhan, S., Hansen, A., and Chakrabarti, B. K. (2010), Failure processes in elastic fiber bundles, *Rev. Mod. Phys.*, 82, 499
- Pradhan, S., Hansen, A., and Hemmer, P. C. (2005), Crossover behavior in burst avalanches: Signature of imminent failure, *Phys. Rev. Lett.*, 95, 125501
- Raischel, F., Kun, F., and Herrmann, H. J. (2006), Local load sharing fiber bundles with a lower cutoff of strength disorder, *Phys. Rev. E*, 74, 035104
- Ramos, O., Cortet, P.-P., Ciliberto, S., and Vanel, L. (2013), Experimental study of the effect of disorder on subcritical crack growth dynamics, *Phys. Rev. Lett.*, 110, 165506
- Redner, S. and Petersen, M. R. (2006), Role of global warming on the statistics of record-breaking temperatures, *Phys. Rev. E*, 74, 061114
- Rosti, J., Koivisto, J., and Alava, M. J. (2010), Statistics of acoustic emission in paper fracture: precursors and criticality, *J. Stat. Mech.*, 2010, P02016
- Salminen, L. I., Tolvanen, A. I., and Alava, M. J. (2002), Acoustic emission from paper fracture, *Phys. Rev. Lett.*, 89, 185503
- Santucci, S., Cortet, P., Deschanel, S., Vanel, L., and Ciliberto, S. (2006), Subcritical crack growth in fibrous materials, *Europhys. Lett.*, 74, 595–601
- Santucci, S., Vanel, L., and Ciliberto, S. (2004), Sub-critical statistics in rupture of fibrous materials: experiments and model, *Phys. Rev. Lett.*, 93, 095505
- Shcherbakov, R., Davidsen, J., and Tiampo, K. F. (2013), Record-breaking avalanches in driven threshold systems, *Phys. Rev. E*, 87, 052811
- Turcotte, D. L., Newman, W. I., and Shcherbakov, R. (2003), Micro and macroscopic models of rock fracture, *Geophys. J. Int.*, 152, 3, 718
- Yoder, M. R., Turcotte, D. L., and Rundle, J. B. (2010), Record-breaking earthquake intervals in a global catalogue and an aftershock sequence, *Nonlinear Processes in Geophysics*, 17, 2, 169–176