## Voigt-wave propagation in active materials

Tom G. Mackay\*

School of Mathematics and Maxwell Institute for Mathematical Sciences University of Edinburgh, Edinburgh EH9 3FD, UK

and

NanoMM — Nanoengineered Metamaterials Group
Department of Engineering Science and Mechanics
Pennsylvania State University, University Park, PA 16802–6812, USA

## Akhlesh Lakhtakia<sup>†</sup>

NanoMM — Nanoengineered Metamaterials Group
Department of Engineering Science and Mechanics
Pennsylvania State University, University Park, PA 16802–6812, USA

## Abstract

If a dissipative anisotropic dielectric material, characterized by the permittivity matrix  $\underline{\underline{\varepsilon}}$ , supports Voigtwave propagation, then so too does the analogous active material characterized by the permittivity matrix  $\underline{\underline{\varepsilon}}$ , where  $\underline{\underline{\varepsilon}}$  is the hermitian conjugate of  $\underline{\underline{\varepsilon}}$ . Consequently, a dissipative material that supports Voigt-wave propagation can give rise to a material that supports the propagation of Voigt waves with attendant linear gain in amplitude with propagation distance, by infiltration with an active dye.

Keywords: Voigt-wave propagation, active materials, anisotropic dielectric materials

Plane-wave analysis is a cornerstone in the electromagnetic theory. Although plane waves themselves are idealizations, possessing limitless spatial and temporal extents and limitless energy, they can facilitate deep insights into fields distant from sources and, by means of superpositions of plane waves, realistic signals may be conveniently represented. Therefore, undergraduate textbooks on electromagnetics and optics invariably present plane waves right after introducing the Maxwell equations and the standard boundary conditions [1, 2, 3].

In nondissipative dielectric materials (and vacuum), plane waves are straightforwardly characterized. These waves propagate with only one phase speed, with arbitrary states of polarization, in any direction. Accordingly, such materials are called unirefringent. In nondissipative anisotropic dielectric materials, generally two distinct plane waves can propagate in any direction, with their phase speeds and polarization states being dependent upon the propagation direction [4, 5]. Accordingly, such materials are called birefringent. In any uniaxial dielectric material, ordinary plane waves propagate with a phase speed that is independent of the propagation direction whereas extraordinary plane waves propagate with a phase speed that depends

\*E-mail: T.Mackay@ed.ac.uk. †E-mail: akhlesh@psu.edu upon the propagation direction. Along the two directions aligned with the optic axis of the material, the phase speeds of the ordinary and the extraordinary plane waves are the same. In a biaxial dielectric material, generally two extraordinary plane waves can propagate, at two different phase speeds, depending upon propagation direction. There are two optic axes for these materials, with the phase speeds of both plane waves being the same for propagation along an optic axis.

Matters are further complicated if the materials are dissipative. In certain dissipative anisotropic dielectric materials, there exist propagation directions — distinct from the directions aligned with the optic axes — along which plane waves have only one phase speed. A plane wave that propagates along such a direction is called a Voigt wave [6, 7, 8, 9, 10]. A Voigt wave represents a singular form of plane-wave propagation that can arise inside certain dissipative biaxial dielectric materials of the monoclinic and triclinic types [11], as well as inside certain gyrotropic materials [12, 13], but neither inside nondissipative materials nor inside isotropic or uniaxial dielectric materials. Mathematically, Voigt-wave propagation arises when an eigenvalue of the corresponding plane-wave propagation matrix has an algebraic multiplicity which exceeds its geometric multiplicity [11, 14]. A crucial difference between a Voigt wave and a plane wave propagating along an optic axis is that the amplitude of the Voigt wave varies linearly with propagation distance whereas this is not the case for the plane wave propagating along the optic axis.

While Voigt waves were first investigated experimentally and theoretically for pleochroic minerals [6, 7, 10], greater scope for realizing Voigt-wave propagation is offered by engineered materials [15, 16], especially homogenized composite materials [17, 18]. The directions in which Voigt waves propagate in a homogenized composite material may be controlled through careful design of the microstructure and selection of the constitutive properties of the component materials [19], or by the application of an external field in the case of electro-optic materials [20]. Indeed, the ability to control the directions for Voigt wave propagation is promising for technological applications such as optical sensing [21].

All previous works on Voigt waves have focused on dissipative materials. The issue of Voigt waves in active materials — that is, materials in which plane-wave propagation is accompanied by a net flow of energy from the material to the field — has not been addressed hitherto. Active materials are useful, or indeed essential, for a host of technoscientific applications. Prime examples are provided by lasing materials, scintillators, and luminescent solar concentrators [22, 23, 24, 25]. In this context, let us, for example, single out doped tungstate materials, which can both support Voigt-wave propagation courtesy of their monoclinic crystal symmetry and function as highly efficient lasing materials [26, 27].

Analytical treatment of Voigt waves involves electromagnetic theory, and a commensurate level of mathematics, accessible to senior undergraduate students of the physical sciences and related engineering disciplines. In particular, the following presentation highlights the usefulness of matrix algebra and complex numbers in physics, and introduces the notion of active materials which is largely conspicuous by its absence in undergraduate electromagnetics courses.

Let us consider a general anisotropic dielectric material, characterized by the frequency-domain constitutive relations [11]

$$\frac{\underline{D}(\underline{r}) = \underline{\underline{\varepsilon}} \cdot \underline{E}(\underline{r})}{\underline{B}(\underline{r}) = \mu_0 \underline{H}(\underline{r})} \right\}, \tag{1}$$

where the components  $\varepsilon_{\ell j}$   $(\ell, j \in \{1, 2, 3\})$  of the permittivity matrix

$$\underline{\underline{\varepsilon}} = \begin{pmatrix} \varepsilon_{xx} & \varepsilon_{xy} & \varepsilon_{xz} \\ \varepsilon_{yx} & \varepsilon_{yy} & \varepsilon_{yz} \\ \varepsilon_{zx} & \varepsilon_{zy} & \varepsilon_{zz} \end{pmatrix}$$
 (2)

are complex valued and  $\mu_0 = 4\pi \times 10^{-7} \text{ H m}^{-1}$  is the permeability of free space. Without loss of generality, let a Voigt wave propagate along the z axis. Then, an eigenvalue/eigenvector analysis reveals that the conditions for Voigt-wave propagation are met when the following two conditions are satisfied [28]:

(i) 
$$C_a(\underline{\underline{\varepsilon}}) = (\delta_{11} - \delta_{22})^2 + 4\delta_{12}\delta_{21} = 0$$
, and

(ii) 
$$C_{b1}(\underline{\underline{\varepsilon}}) = \delta_{12} \neq 0$$
 and/or  $C_{b2}(\underline{\underline{\varepsilon}}) = \delta_{21} \neq 0$ ,

where the scalar parameters

$$\delta_{11} = \varepsilon_{xx}\varepsilon_{zz} - \varepsilon_{xz}\varepsilon_{zx} 
\delta_{12} = \varepsilon_{xy}\varepsilon_{zz} - \varepsilon_{xz}\varepsilon_{zy} 
\delta_{21} = \varepsilon_{yx}\varepsilon_{zz} - \varepsilon_{yz}\varepsilon_{zx} 
\delta_{22} = \varepsilon_{yy}\varepsilon_{zz} - \varepsilon_{yz}\varepsilon_{zy}$$
(3)

The flow of energy associated with propagation is represented by the time-averaged Poynting vector  $\langle \underline{P}(\underline{r}) \rangle_t = (1/2) \operatorname{Re} [\underline{E}(\underline{r}) \times \underline{H}^*(\underline{r})]$ , with the superscript \* denoting the complex conjugate and the operator  $\operatorname{Re} [\cdot]$  delivering the real part. In particular, the divergence of the time-averaged Poynting vector is given by [5]

$$\underline{\nabla} \cdot \langle \underline{P}(\underline{r}) \rangle_t = \operatorname{Re} \left\{ \frac{i\omega}{2} \left[ \underline{H}^*(\underline{r}) \cdot \underline{B}(\underline{r}) - \underline{E}(\underline{r}) \cdot \underline{D}^*(\underline{r}) \right] \right\}, \tag{4}$$

where  $\omega > 0$  is the angular frequency. For the anisotropic dielectric material characterized by the constitutive relations (1), the divergence (4) simplifies to [5]

$$\underline{\nabla} \cdot \langle \underline{P}(\underline{r}) \rangle_t = \frac{i\omega}{4} \, \underline{E}^*(\underline{r}) \cdot (\underline{\varepsilon} - \underline{\tilde{\varepsilon}}) \cdot \underline{E}(\underline{r}), \tag{5}$$

where  $\underline{\tilde{\varepsilon}}$  represents the hermitian conjugate of  $\underline{\varepsilon}$ ; i.e., the components of  $\underline{\tilde{\varepsilon}}$  are  $\tilde{\varepsilon}_{\ell j} = \varepsilon_{j\ell}^*$  ( $\ell \in \{x, y, z\}$  and  $j \in \{x, y, z\}$ ).

Now, if the material characterized by the constitutive relations (1) is:

- dissipative then  $\underline{\nabla} \cdot \langle \underline{P(r)} \rangle_t < 0$ , which, according to Eq. (5), implies that the three eigenvalues of the matrix  $i\left(\underline{\varepsilon} \underline{\tilde{\varepsilon}}\right)$  are negative valued (i.e., the matrix  $i\left(\underline{\varepsilon} \underline{\tilde{\varepsilon}}\right)$  is negative definite) [14];
- active then  $\underline{\nabla} \cdot \langle \underline{P}(\underline{r}) \rangle_t > 0$ , which, according to Eq. (5), implies that the three eigenvalues of the matrix  $i\left(\underline{\underline{\varepsilon}} \underline{\underline{\tilde{\varepsilon}}}\right)$  are positive valued (i.e., the matrix  $i\left(\underline{\underline{\varepsilon}} \underline{\tilde{\varepsilon}}\right)$  is positive definite) [14].

Therefore, if the material possessing the permittivity matrix  $\underline{\underline{\varepsilon}}$  is dissipative then the material described by the permittivity matrix  $\underline{\underline{\varepsilon}}$  is active, and vice versa.

Let us turn to the conditions (i) and (ii) that must be satisfied for Voigt-wave propagation. After some algebraic manipulations, one finds

Therefore, if a dissipative (or active) material described by the permittivity matrix  $\underline{\underline{\varepsilon}}$  supports Voigt-wave propagation then so too must the analogous active (or dissipative) material described by the permittivity matrix  $\underline{\underline{\varepsilon}}$ .

An important implication of this finding is as follows. Suppose we consider a certain dissipative material, say a porous homogenized composite material with monoclinic biaxial symmetry. Voigt waves can propagate in this material with attendant linear attenuation as the propagation distance increases [17]. Now if this material were to be infiltrated with a sufficient quantity of an active dye (which is fluorescent [29]), such that the monoclinic symmetry remained unchanged, then Voigt waves could propagate in this material with attendant linear gain as the propagation distance increased. Thus, one could linearly amplify signals propagating along a specific direction in addition to the exponential amplification, while along other directions the signal amplification would be just exponential.

**Acknowledgements.** TGM acknowledges the support of EPSRC grant EP/M018075/1. AL thanks the Charles Godfrey Binder Endowment at Penn State for ongoing support of his research activities.

## References

- [1] Hayt Jr W H and Buck J A 2011 Engineering Electromagnetics, 8th Edition (New York, NY: McGraw-Hill)
- [2] Iskander M F 2012 Electromagnetic Fields and Waves, 2nd Edition (Long Grove, IL: Waveland Press)
- [3] Ida N 2015 Engineering Electromagnetics, 3rd Edition (New York, NY: Springer)
- [4] Born M and Wolf E 1980 Principles of Optics, 6th Edition (Oxford, UK: Pergamon Press)
- [5] Chen H C 1983 Theory of Electromagnetic Waves (New York, NY: McGraw-Hill)
- [6] Voigt W 1902 On the behaviour of pleochroitic crystals along directions in the neighbourhood of an optic axis Phil. Mag. 4 90–97
- [7] Pancharatnam S 1955 The propagation of light in absorbing biaxial crystals I. Theoretical Proc. Ind. Acad. Sci. A 42 86–109
- [8] Khapalyuk A P 1962 On the theory of circular optical axes Opt. Spectrosc. (USSR) 12 52–54
- [9] Fedorov F I and Goncharenko A M 1963 Propagation of light along the circular optical axes of absorbing crystals *Opt. Spectrosc. (USSR)* **14** 51–53
- [10] Ranganath G S 1994 Optics of absorbing anisotropic media Curr. Sci. 67 231–237
- [11] Mackay T G and Lakhtakia A 2008 Electromagnetic fields in linear bianisotropic mediums Prog. Optics 51 121–209
- [12] Agranovich V M and Ginzburg V L 1984 Crystal Optics with Spatial Dispersion, and Excitons (Berlin, Germany: Springer)
- [13] Grechushnikov B N and Konstantinova A F 1988 Crystal optics of absorbing and gyrotropic media Comput. Math. Applic. 16 637–655
- [14] Whitelaw T A 1995 Introduction to Abstract Algebra, 3rd edition (Glasgow, UK: Blackie)
- [15] Lakhtakia A 1998 Anomalous axial propagation in helicoidal bianisotropic media *Opt. Commun.* **157** 193–201
- [16] Berry M V 2005 The optical singularities of bianisotropic crystals Proc. R. Soc. A 461 2071–2098
- [17] Mackay T G and Lakhtakia A 2003 Voigt wave propagation in biaxial composite materials J. Opt. A: Pure Appl. Opt. 5 91–95
- [18] Mackay T G and Lakhtakia A 2004 Correlation length facilitates Voigt wave propagation  $Waves\ Random\ Media\ 14\ L1-L11$
- [19] Mackay T G 2011 Voigt waves in homogenized particulate composites based on isotropic dielectric components J. Opt. 13 105702
- [20] Mackay T G 2015 Controlling Voigt waves by the Pockels effect J. Nanophoton. 9 093599
- [21] Mackay T G 2014 On the sensitivity of directions that support Voigt wave propagation in infiltrated biaxial dielectric materials *J. Nanophoton.* **8** 083993
- [22] Hecht J 2008 Understanding Lasers: An Entry-Level Guide, 3rd Edition (Piscataway, NJ: IEEE Press)
- [23] Vij D K (editor) 1998 Luminescence of Solids (New York, NY: Plenum Press)

- [24] Yukihara E G and McKeever S W S 2011 Optically Stimulated Luminescence: Fundamentals and Applications (Chicester, UK: Wiley)
- [25] Debije M G and Verbunt P P C 2012 Thirty years of luminescent solar concentrator research: Solar energy for the built environment Adv. Energy Mater. 2 12–35
- [26] Kaminskii A A, Ueda K, Eichler H E, Findeisen J, Bagayev S N, Kuznetsov F A, Pavlyuk A A, Boulon G and Bourgeois F 1998 Monoclinic tungstates  $KDy(WO_4)_2$  and  $KLu(WO_4)_2$  New  $\chi^{(3)}$  active crystals for laser Raman shifters Jpn.~J.~Appl.~Phys.~37~L923–L926
- [27] Kareka A, Boudelliouaa A, Lebboub K, Brenierb A and Boulonb G 2009 Structural and spectroscopic characterization of the double tungstate NaBi(WO<sub>4</sub>)<sub>2</sub> crystals doped with Yb<sup>3+</sup> and grown by the micro-pulling down technique *Phys. Procedia* 2 497500
- [28] Gerardin J and Lakhtakia A 2001 Conditions for Voigt wave propagation in linear, homogeneous, dielectric mediums *Optik* **112** 493–495
- [29] Jameson D M 2014 Introduction to Fluorescence (Boca Raton, FL: CRC Press)