Photonic Band Gap in 1D Multilayers Made by Alternating SiO_2 or PMMA with MoS_2 or WS_2 monolayers

Diana Gisell Figueroa del Valle^{1,2}, Eduardo Aluicio-Sarduy^{1,3}, Francesco Scotognella^{1,2,4*}

- ¹ Center for Nano Science and Technology@PoliMi, Istituto Italiano di Tecnologia, Via Giovanni Pascoli, 70/3, 20133, Milan, Italy
- ² Dipartimento di Fisica, Politecnico di Milano, Piazza Leonardo da Vinci 32, 20133 Milano, Italy
- ³ Dipartimento di Chimica, Materiali e Ingegneria Chimica "Giulio Natta", Politecnico di Milano, Piazza Leonardo da Vinci 32, 20133 Milano, Italy
- ⁴ Istituto di Fotonica e Nanotecnologie CNR, Piazza Leonardo da Vinci 32, 20133 Milano
- * Corresponding author at: Dipartimento di Fisica, Politecnico di Milano, Piazza Leonardo da Vinci 32, 20133 Milano, Italy. E-mail address: francesco.scotognella@polimi.it (F. Scotognella).

Abstract

Atomically thin molybdenum disulphide (MoS_2) and tungsten disulphide (WS_2) are very interesting two dimensional materials for optics and electronics. In this work we show the possibility to obtain one-dimensional photonic crystals consisting of low-cost and easy processable materials, as silicon dioxide (SiO_2) or poly methyl methacrylate (PMMA), and of MoS_2 or WS_2 monolayers. We have simulated the transmission spectra of the photonic crystals using the transfer matrix method and employing the wavelength dependent refractive indexes of the materials. This study envisages the experimental fabrication of these new types of photonic crystals for photonic and light emission applications.

Keywords: photonic crystals; transfer matrix method; transition metal dichalcogenides; MoS₂ monolayer; WS₂ monolayer.

Introduction

The research on atomically thin molybdenum disulphide (MoS_2) and tungsten disulphide (WS_2) is gaining considerable attention, since they are promising for several applications in optics and electronics [1–3]. In literature there are several reports on the optical properties, time resolved photogeneration, and luminescence of few-layers of MoS_2 [4], MoS_2 monolayer [5–7], and WS_2 monolayer [8]. Very recently, the development of population inversion, very useful for laser applications, has been observed in WS_2 [9].

Photonic crystals are composite materials in which two compounds, with a different refractive index, are alternated and the arising periodicity is comparable with the wavelength of light. Such periodicity gives rise to energy regions where the photons are not allowed to propagate in the materials, called photonic band gap [10–12]. Multilayered structures are a particular case of one-dimensional photonic crystals, which are easy to fabricate with several methods [13–15], and can be employed for different applications, as sensors [16], electro-optic switches [17], and lasers [18]. In literature there are interesting reports on one-dimensional photonic crystals containing MoS_2 [19] and on microcavities in which a MoS_2 monolayer is embedded [20,21]. However, a study of the transmission properties of one-dimensional multilayer photonic crystals, where atomically thin layers of different semiconducting transition-metal dichalcogenides are employed in the periodic structures, is still missing.

Here we describe the realization of a one-dimensional photonic crystal that is made with materials that are usually employed for these types of crystals, as silicon dioxide (SiO₂) or poly methyl methacrylate (PMMA), and transition metal dichalcogenides as MoS₂ or WS₂. The photonic crystals consist of multilayers and we have simulated the transmission spectra of the photonic crystals using the transfer matrix method and utilizing the wavelength dependent

refractive indexes of the materials. We have found that a photonic band gap arises with atomically thin layers of MoS_2 or WS_2 .

Methods

We have considered an air/multilayer/glass system. The wavelength dependent refractive index of SiO₂ is taken from Ref. [22], and the corresponding Sellmeier equation is:

$$n_{SiO_2}(\lambda) = \left(1 + \frac{0.6962\lambda^2}{\lambda^2 - 0.0684^2} + \frac{0.4080\lambda^2}{\lambda^2 - 0.1162^2} + \frac{0.8975\lambda^2}{\lambda^2 - 9.8962^2}\right)^{1/2} \tag{1}$$

Instead, the refractive index of PMMA is taken from Ref. [23] and the Sellmeier equation is:

$$n_{PMMA}(\lambda) = \left(1 + \frac{0.99654\lambda^2}{\lambda^2 - 0.00787} + \frac{0.18964\lambda^2}{\lambda^2 - 0.02191} + \frac{0.00411\lambda^2}{\lambda^2 - 3.85727}\right)^{1/2} \tag{2}$$

The unit for the wavelength in the two Sellmeier equations is micrometer.

The wavelength dependent dielectric function (real and imaginary parts) of MoS₂ is taken from Ref. [24], while the one of WS₂ from Ref. [25], considering the refractive index of MoS₂/WS₂ $n_{MoS_2/WS_2} = \sqrt{\varepsilon_{MoS_2/WS_2}}$.

The simulation of the transmission spectra of the multilayers have been performed by using the transfer matrix method, exhaustively described in Refs. [26–28].

Results and Discussion

We have simulated the transmission spectra of multilayer photonic crystals in which the layers of SiO₂, or PMMA, are alternated with monolayers of MoS₂, or WS₂. In Figure 1 we have depicted a sketch of the photonic crystal.




Figure 1. Schemes of the photonic crystals made by alternating layers of SiO₂ or PMMA with atomically thin layers of MoS₂ or WS₂.

We have carefully taken into account the wavelength dependent refractive index of all the employed materials, in order to give an accurate prediction of the transmission spectra of the photonic crystals. For the MoS_2/SiO_2 multilayer, we have chosen a thickness of the SiO_2 layers of 250 nm, while the thickness of the monolayer of MoS_2 is 0.65 nm [24]. In Figure 2 we show the transmission spectrum of a MoS_2/SiO_2 photonic crystal made by 15 bilayers.




Figure 2. Transmission spectrum of a one-dimensional photonic crystal made alternating 15 layers of SiO_2 and 15 monolayers of MoS_2 .

In the spectrum the transmission valleys at around 450, 605, and 660 nm are related to the absorption of MoS_2 (due to the excitonic resonances [29–31]). The valley at about 720 nm is related to a photonic band gap arising from the periodicity of the refractive index.

For the WS_2/SiO_2 multilayer the thickness of the SiO_2 layers is again 250 nm, and the thickness of the monolayer of WS_2 is 0.65 nm [25]. In Figure 3 we show the transmission spectrum of a WS_2/SiO_2 photonic crystal made by 15 bilayers. In this multilayer the transmission valleys related to the excitonic resonances of WS_2 [8,29] are at 435 nm, 515 nm, and the very intense one at 618 nm. The photonic band gap is observed at about 720 nm.




Figure 3. Transmission spectrum of a one-dimensional photonic crystal made alternating 15 layers of SiO_2 and 15 monolayers of WS_2 .

We have also simulated the transmission spectra of photonic crystals in which the transition metal dichalcogenide monolayers are alternated with a plastic material as PMMA. For the $MoS_2/PMMA$ multilayer the thickness of the PMMA layers, as for SiO_2 , is 250 nm, and its transmission spectrum is shown in Figure 4.




Figure 4. Transmission spectrum of a one-dimensional photonic crystal made alternating 15 layers of PMMA and 15 monolayers of MoS₂.

Also in the case of the atomically thin $WS_2/PMMA$ multilayer the thickness of the PMMA layers is 250 nm, and its transmission spectrum is shown in Figure 5 (1ML, i.e. a monolayer).




Figure 5. Transmission spectrum of a one-dimensional photonic crystal made alternating 15 layers of PMMA and 15 monolayers of WS_2 (1ML) or 15 tetralayers of WS_2 (4ML).

It is worth noting the photonic band gaps on the multilayers that we have shown are weak in intensity, with a transmission minimum between 70% and 80%. This is due to the fact the thickness of MoS_2 or WS_2 monolayers is inherently very small (i.e. 0.65 nm). To obtain a more intense photonic band gap a higher number of bilayers is needed. Another possible solution is to increase the thickness of MoS_2 or WS_2 in the multilayer, i.e. from a monolayer to a tetralayer. For example, we have also simulated the transmission spectrum of a multilayer photonic crystal where the WS_2 consists of a tetralayer, with a thickness of 2.6 nm. In this case, because of the larger thickness of WS_2 , we have decreased the thickness of PMMA to 245 nm. The transmission spectrum of the photonic crystal is shown in Figure 5 (4ML). We have observed that the photonic band gap is already very strong with 15 bilayers, reaching a transmission, at about 750 nm, of around 0.1.

From an experimental point of view, the photonic crystals can be fabricated by employing different techniques. The deposition of the SiO_2 layers can be done by radiofrequency sputtering [14] or chemical vapor deposition [20], while the deposition of the PMMA layers by spin coating [32]. Transition metal dichalcogenide monolayers can be synthetized by ambient pressure chemical vapour deposition and transfer, on the other layers of the photonic crystal, via an aqueous solution transfer method [20,33].

Conclusion

In summary, we have shown the possibility to realize a one dimensional multilayer photonic crystal consisting of the usual low cost materials for multilayers, as silicon dioxide or PMMA, and atomically thin layers of two different transition metal dichalcogenides, as MoS_2 and WS_2 . We have simulated the transmission spectra of the photonic crystals using the transfer matrix method and taking into account the wavelength dependent refractive indexes of the materials. The study here described envisages the experimental fabrication of these photonic crystals for photonic and light emission applications. For example, the photonic band gap can be tuned in order modulate, and enhance, the luminescence of MoS_2 or WS_2 monolayers [2,6,7].

Acknowledgements

D.G.F.d.V. and F.S. want to acknowledge the ITN project 316633 "POCAONTAS". F. S. also wants to acknowledges financial support from the Italian Ministry of University and Research (project PRIN 2010-2011 "DSSCX" No. 20104XET32).

References

- [1] Q.H. Wang, K. Kalantar-Zadeh, A. Kis, J.N. Coleman, M.S. Strano, Electronics and optoelectronics of two-dimensional transition metal dichalcogenides, Nat. Nanotechnol. 7 (2012) 699–712. doi:10.1038/nnano.2012.193.
- [2] R. Lv, J.A. Robinson, R.E. Schaak, D. Sun, Y. Sun, T.E. Mallouk, et al., Transition Metal Dichalcogenides and Beyond: Synthesis, Properties, and Applications of Single- and Few-Layer Nanosheets, Acc. Chem. Res. 48 (2015) 56–64. doi:10.1021/ar5002846.
- [3] F. Xia, H. Wang, D. Xiao, M. Dubey, A. Ramasubramaniam, Two-dimensional material nanophotonics, Nat. Photonics. 8 (2014) 899–907. doi:10.1038/nphoton.2014.271.
- [4] T. Borzda, C. Gadermaier, N. Vujicic, P. Topolovsek, M. Borovsak, T. Mertelj, et al., Charge Photogeneration in Few-Layer MoS₂, Adv. Funct. Mater. 25 (2015) 3351–3358. doi:10.1002/adfm.201500709.
- [5] A.K.M. Newaz, D. Prasai, J.I. Ziegler, D. Caudel, S. Robinson, R.F. Haglund Jr., et al., Electrical control of optical properties of monolayer MoS_2 , Solid State Commun. 155 (2013) 49–52. doi:10.1016/j.ssc.2012.11.010.
- [6] K.F. Mak, C. Lee, J. Hone, J. Shan, T.F. Heinz, Atomically Thin MoS₂: A New Direct-Gap Semiconductor, Phys. Rev. Lett. 105 (2010). doi:10.1103/PhysRevLett.105.136805.
- [7] A. Splendiani, L. Sun, Y. Zhang, T. Li, J. Kim, C.-Y. Chim, et al., Emerging Photoluminescence in Monolayer MoS_2 , Nano Lett. 10 (2010) 1271–1275. doi:10.1021/nl903868w.
- [8] A. Chernikov, T.C. Berkelbach, H.M. Hill, A. Rigosi, Y. Li, O.B. Aslan, et al., Exciton Binding Energy and Nonhydrogenic Rydberg Series in Monolayer WS₂, Phys. Rev. Lett. 113 (2014). doi:10.1103/PhysRevLett.113.076802.
- [9] A. Chernikov, C. Ruppert, H.M. Hill, A.F. Rigosi, T.F. Heinz, Population inversion and giant bandgap renormalization in atomically thin WS_2 layers, Nat. Photonics. 9 (2015) 466–470. doi:10.1038/nphoton.2015.104.
- [10] E. Yablonovitch, Inhibited Spontaneous Emission in Solid-State Physics and Electronics, Phys. Rev. Lett. 58 (1987) 2059–2062. doi:10.1103/PhysRevLett.58.2059.
- [11] S. John, Strong localization of photons in certain disordered dielectric superlattices, Phys. Rev. Lett. 58 (1987) 2486–2489. doi:10.1103/PhysRevLett.58.2486.
- [12] K. Sakoda, Optical Properties of Photonic Crystals, Springer Science & Business Media, 2004.
- [13] L.D. Bonifacio, B.V. Lotsch, D.P. Puzzo, F. Scotognella, G.A. Ozin, Stacking the Nanochemistry Deck: Structural and Compositional Diversity in One-Dimensional Photonic Crystals, Adv. Mater. 21 (2009) 1641–1646. doi:10.1002/adma.200802348.
- [14] S. Valligatla, A. Chiasera, S. Varas, N. Bazzanella, D.N. Rao, G.C. Righini, et al., High quality factor 1-D Er³+-activated dielectric microcavity fabricated by RF-sputtering, Opt.

- Express. 20 (2012) 21214–21222. doi:10.1364/0E.20.021214.
- [15] K.D. Singer, T. Kazmierczak, J. Lott, H. Song, Y. Wu, J. Andrews, et al., Melt-processed all-polymer distributed Bragg reflector laser, Opt. Express. 16 (2008) 10358. doi:10.1364/0E.16.010358.
- [16] I. Pavlichenko, A.T. Exner, M. Guehl, P. Lugli, G. Scarpa, B.V. Lotsch, Humidity-Enhanced Thermally Tunable TiO_2/SiO_2 Bragg Stacks, J. Phys. Chem. C. 116 (2011) 298–305. doi:10.1021/jp208733t.
- [17] L. Criante, F. Scotognella, Low-Voltage Tuning in a Nanoparticle/Liquid Crystal Photonic Structure, J. Phys. Chem. C. 116 (2012) 21572–21576. doi:10.1021/jp309061r.
- [18] T. Komikado, S. Yoshida, S. Umegaki, Surface-emitting distributed-feedback dye laser of a polymeric multilayer fabricated by spin coating, Appl. Phys. Lett. 89 (2006) 061123. doi:10.1063/1.2336740.
- [19] X. Ma, W. Gu, Optical Transfer Properties of Nanosized MoS₂-Based One-Dimensional Photonic Crystals, J. Nanoelectron. Optoelectron. 9 (2014) 502–506. doi:10.1166/jno.2014.1616.
- [20] X. Liu, T. Galfsky, Z. Sun, F. Xia, E. Lin, Y.-H. Lee, et al., Strong light–matter coupling in two-dimensional atomic crystals, Nat. Photonics. 9 (2014) 30–34. doi:10.1038/nphoton.2014.304.
- [21] J.-T. Liu, T.-B. Wang, X.-J. Li, N.-H. Liu, Enhanced absorption of monolayer MoS₂ with resonant back reflector, J. Appl. Phys. 115 (2014) 193511. doi:10.1063/1.4878700.
- [22] I.H. Malitson, Interspecimen Comparison of the Refractive Index of Fused Silica, J. Opt. Soc. Am. 55 (1965) 1205–1208. doi:10.1364/JOSA.55.001205.
- [23] M. N. Polyanskiy. Refractive index database. Available at http://refractiveindex.info.
- [24] B. Mukherjee, F. Tseng, D. Gunlycke, K.K. Amara, G. Eda, E. Simsek, Complex electrical permittivity of the monolayer molybdenum disulfide (MoS_2) in near UV and visible, Opt. Mater. Express. 5 (2015) 447. doi:10.1364/OME.5.000447.
- [25] Y. Li, A. Chernikov, X. Zhang, A. Rigosi, H.M. Hill, A.M. van der Zande, et al., Measurement of the optical dielectric function of monolayer transition-metal dichalcogenides: MoS₂, MoSe₂, WS₂, and WSe₂, Phys. Rev. B. 90 (2014) 205422. doi:10.1103/PhysRevB.90.205422.
- [26] M. Born, E. Wolf, Principles of Optics: Electromagnetic Theory of Propagation, Interference and Diffraction of Light, CUP Archive, 2000.
- [27] J.M. Bendickson, J.P. Dowling, M. Scalora, Analytic expressions for the electromagnetic mode density in finite, one-dimensional, photonic band-gap structures, Phys. Rev. E. 53 (1996) 4107–4121. doi:10.1103/PhysRevE.53.4107.
- [28] M. Bellingeri, I. Kriegel, F. Scotognella, One dimensional disordered photonic structures

- characterized by uniform distributions of clusters, Opt. Mater. 39 (2015) 235–238. doi:10.1016/j.optmat.2014.11.033.
- [29] A. Ramasubramaniam, Large excitonic effects in monolayers of molybdenum and tungsten dichalcogenides, Phys. Rev. B. 86 (2012). doi:10.1103/PhysRevB.86.115409.
- [30] D.Y. Qiu, F.H. da Jornada, S.G. Louie, Optical Spectrum of MoS_2 : Many-Body Effects and Diversity of Exciton States, Phys. Rev. Lett. 111 (2013). doi:10.1103/PhysRevLett.111.216805.
- [31] M.M. Ugeda, A.J. Bradley, S.-F. Shi, F.H. da Jornada, Y. Zhang, D.Y. Qiu, et al., Giant bandgap renormalization and excitonic effects in a monolayer transition metal dichalcogenide semiconductor, Nat. Mater. 13 (2014) 1091–1095. doi:10.1038/nmat4061.
- [32] J. Yoon, W. Lee, J.-M. Caruge, M. Bawendi, E.L. Thomas, S. Kooi, et al., Defect-mode mirrorless lasing in dye-doped organic/inorganic hybrid one-dimensional photonic crystal, Appl. Phys. Lett. 88 (2006) 091102. doi:10.1063/1.2174090.
- [33] Y.-H. Lee, L. Yu, H. Wang, W. Fang, X. Ling, Y. Shi, et al., Synthesis and Transfer of Single-Layer Transition Metal Disulfides on Diverse Surfaces, Nano Lett. (2013) 130329103804007. doi:10.1021/nl400687n.