Double-negative electromagnetic metamaterials due to chirality

Habib Ammari* Wei Wu[†] Sanghyeon Yu[†]

Abstract

The aim of this paper is to provide a mathematical theory for understanding the mechanism behind the double-negative refractive index phenomenon in chiral materials. The design of double-negative metamaterials generally requires the use of two different kinds of subwavelength resonators, which may limit the applicability of double-negative metamaterials. Herein, we rely on media that consist of only a single type of dielectric resonant element, and show how the chirality of the background medium induces double-negative refractive index metamaterial, which refracts waves negatively, hence acting as a superlens. Using plasmonic dielectric particles, it is proved that both the effective electric permittivity and the magnetic permeability can be negative near some resonant frequencies. A justification of the approximation of a plasmonic particle in a chiral medium by the sum of a resonant electric dipole and a resonant magnetic dipole, is provided. Moreover, the set of resonant frequencies is characterized. For an appropriate volume fraction of plasmonic particles with certain conditions on their configuration, a double-negative effective medium can be obtained when the frequency is near one of the resonant frequencies.

Mathematics Subject Classification (MSC2000). 35R30, 35C20.

Keywords. Plasmonic nanoparticles, sub-wavelength resonance, electric and magnetic resonant dipoles, chiral materials, effective medium theory, double-negative metamaterials.

1 Introduction

The resolving power of conventional imaging systems is generally limited by the operating wavelength, which prevents imaging of subwavelength structures. However, systems having a negative refractive index can produce sharp images, with a potential to resolve subwavelength features [29]. Negative index materials were first considered in [34]. Their recently added potential for subwavelength imaging led to an enormous interest in their properties [32, 31, 33, 35].

^{*}Department of Mathematics, ETH Zürich, Rämistrasse 101, CH-8092 Zürich, Switzerland (habib.ammari@math.ethz.ch, wei.wu@sam.math.ethz.ch, sanghyeon.yu@sam.math.ethz.ch).

The negative sign of the refractive index arises in the description of electromagnetic properties of materials with simultaneously negative values of dielectric permittivity and magnetic permeability. A negative refractive index means that the phase velocity of a propagating wave is opposite to the movement of the energy flux of the wave, represented by the Poynting vector [35].

Negative refractive index materials are often referred to as double-negative metamaterials. The design of double-negative metamaterials generally requires the use of two different kinds of building blocks or specific subwavelength resonators presenting overlapping resonances. The negative index is caused by simultaneous resonant electric and magnetic responses. The resonant electric dipole modes in the background medium contribute to the effective dielectric permittivity while the resonant magnetic dipole modes contribute to the effective magnetic permeability. Such a requirement limits the applicability of double-negative metamaterials.

Recently, it has been predicted and experimentally demonstrated that introducing a single type of sub-wavelength resonant dielectric element into chiral materials leads to double-negative metamaterials [30, 36, 37].

A material is defined to be chiral if it lacks any planes of mirror symmetry. In terms of electromagnetic responses, chiral materials exhibit a different refractive index for each polarization of the electromagnetic wave and are characterized by a cross coupling between the electric and magnetic dipoles along the same direction. The coupling strength is given by the magnitude of a quantity known as the chirality admittance which determines the bulk electromagnetic properties of chiral materials. Wave propagation inside chiral materials is investigated, for instance, in [5, 7, 9, 10, 17, 18, 19, 25].

Plasmonic nanoparticles are sub-wavelength resonant dielectric elements. They exhibit quasi-static resonances, called plasmonic resonances. At or near these resonant frequencies, the plasmonic particles behave as strong electric dipoles. The plasmonic resonances are related to the spectra of the non-self adjoint Neumann-Poincaré type operators associated with the particle shapes. We refer the reader to [1, 8, 11, 12, 15, 16] for recent mathematical analysis of fundamental plasmonic resonance phenomena and their implications in subwavelength imaging.

In this paper, we aim to understand the mechanism behind the double-negative refractive index phenomenon in chiral media. Herein, we rely on media that consists of plasmonic resonant particles, and show how to turn a chiral material into a negative refractive index metamaterial. For this purpose, we first derive the leading-order perturbations in the electromagnetic fields in the far-field, which are caused by the presence of a plasmonic nanoparticle. To our knowledge, these asymptotic expansions, which are uniformly valid with respect to the frequency, have never been established. They generalize those derived in [1, 6, 13] to chiral media. They show that the plasmonic nanoparticle can be approximated by the sum of resonant electric and magnetic dipole sources. Then, we completely characterize the set of resonant frequencies in terms of the plasmonic resonances of the nanoparticle in free space and the chiral admittance of the background medium. Finally, by using the point interaction approximation, we show that double-negative electromagnetic materials can be obtained by embedding in a chiral

medium a large number of regularly spaced, randomly oriented plasmonic particles, each modeled as the sum of resonant electric and magnetic dipole sources. Near or at the resonant frequencies, the effective electric and magnetic properties of the medium can both be negative. We recall that the idea of point interaction approximation goes back to Foldy's paper [23]. It is a natural tool to analyze a variety of interesting problems in the continuum limit. It was first applied to the analysis of boundary value problems in regions with many small holes [26, 27], then in [22] to the heat conduction in material with many small holes, and in [20] on sound propagation in bubbly fluid.

Our methodology in this paper follows the one introduced recently for achieving double-negative acoustic media using bubbles [4]. In acoustics, it is known that the air bubbles are subwavelength resonators [24]. Due to the high contrast between the air density inside and outside an air bubble in a fluid, a quasi-static acoustic resonance known as the Minnaert resonance occurs [2]. At or near this resonant frequency, the size of a bubble can be up to three orders of magnitude smaller than the wavelength of the incident wave, and the bubble behaves as a strong monopole scatterer of sound. The Minnaert resonance phenomenon makes air bubbles good candidates for acoustic subwavelength resonators. In [4], it is proved that, using bubble dimers, the effective mass density and bulk modulus of the bubbly fluid can both be negative over a non empty range of frequencies. A bubble dimer consists of two identical separated bubbles. It features two slightly different subwavelength resonances, called the hybridized Minnaert resonances. The hybridized Minnaert resonances are fundamentally different modes. One mode is a monopole as in the case of a single bubble, while the other one is a dipole. The resonance associated with the dipole mode is usually referred to as the antiresonance. For an appropriate volume fraction, when the excitation frequency is close to the anti-resonance, a double-negative effective mass density and bulk modulus for bubbly media consisting of a large number of bubble dimers with certain conditions on their distribution are obtained. The dipole modes in the background medium contribute to the effective mass density while the monopole modes contribute to the effective bulk

The paper is organized as follows. In Section 2, we introduce some preliminaries on electromagnetic wave propagation in chiral materials. In Section 3, we derive an asymptotic expansion of the scattered electric and magnetic fields by a plasmonic nanoparticles in a chiral material. We prove that the plasmonic nanoparticle can be approximated as a pair of electric and magnetic dipole sources. We also characterize the set of resonant frequencies. In Section 4, we derive a double-negative effective medium theory for plasmonic particles in chiral media near the resonant frequencies. In Appendix A, we provide some explicit calculations for the case of spherical chiral inclusions. In Appendix B, we review layer potential formulations for electromagnetic scattering in a chiral medium.

2 Electromagnetic scattering in a chiral material

In this section, we consider an infinite chiral material in \mathbb{R}^3 with only one plasmonic particle. Let the particle $\Omega \subset \mathbb{R}^3$ be an open bounded set, with smooth boundary $\partial\Omega$.

We assume that the particle Ω is centered at the origin and is of size $O(\delta)$, where $\delta > 0$ is small. Denote $\Omega = \delta B$, |B| = O(1). Obviously, $|\Omega| = \delta^3 |B| = O(\delta^3)$, where $|\cdot|$ denotes the volume. The electric permittivity $\epsilon(x)$, permeability $\mu(x)$, and chiral admittance $\beta(x)$ in \mathbb{R}^3 satisfy

$$\beta = \begin{cases} \beta_m & \text{in } \mathbb{R}^3 \setminus \overline{\Omega} \\ 0 & \text{in } \Omega \end{cases}, \quad \epsilon = \begin{cases} \epsilon_m & \text{in } \mathbb{R}^3 \setminus \overline{\Omega} \\ \epsilon_c & \text{in } \Omega \end{cases}, \quad \text{and } \mu(x) = \mu_m \text{ for all } x \in \mathbb{R}^3.$$
(2.1)

Here, ϵ_m , μ_m , and β_m are positive constants and ϵ_c depends on the operating frequency ω and is assumed to be negative.

2.1 Drude-Born-Fedorov equations

The starting points of this paper are the Maxwell equations and the constitutive relations for the chiral medium. Different expressions exist for the constitutive relations. The Drude-Born-Fedorov constitutive equations are used hereinafter.

Optical activity of the chiral medium can be explained by the direct substitution of the Drude-Born-Dedorov constitutive equations [9, 10]:

$$\begin{cases} D = \epsilon(x)(E + \beta(x)\nabla \times E) & \text{in } \mathbb{R}^3, \\ B = \mu(x)(H + \beta(x)\nabla \times H) & \text{in } \mathbb{R}^3, \end{cases}$$
 (2.2)

into Maxwell's equations

$$\begin{cases} \nabla \times E = i\omega B & \text{in } \mathbb{R}^3, \\ \nabla \times H = -i\omega D & \text{in } \mathbb{R}^3, \end{cases}$$
 (2.3)

which gives the constitutive relations

$$\begin{cases} (1 - (k(x)\beta(x))^{2})D = \epsilon(x)E + i\frac{\beta(x)}{\omega}(k(x))^{2}H, \\ (1 - (k(x)\beta(x))^{2})B = \mu(x)H - i\frac{\beta(x)}{\omega}(k(x))^{2}E, \end{cases}$$
(2.4)

where

$$k(x) = \omega \sqrt{\epsilon(x)\mu(x)}$$

Combining (2.3) and (2.4) leads to

$$\begin{cases}
\nabla \times E = (\gamma(x))^2 \beta(x) E + i\omega \mu_m (\frac{\gamma(x)}{k(x)})^2 H & \text{in } \mathbb{R}^3, \\
\nabla \times H = (\gamma(x))^2 \beta(x) H - i\omega \epsilon(x) (\frac{\gamma(x)}{k(x)})^2 E & \text{in } \mathbb{R}^3,
\end{cases}$$
(2.5)

where

$$\gamma(x)^{2} = \frac{k(x)^{2}}{1 - (k(x)\beta(x))^{2}}.$$

Let us denote

$$k_m = \omega \sqrt{\epsilon_m \mu_m}, \quad \gamma_m = \frac{k_m^2}{1 - k_m^2 \beta_m^2}.$$

Throughout this paper, we assume $k_m \beta_m < 1$. Note that, $k(x) = k_m$ and $\gamma(x) = \gamma_m$ when x is outside Ω .

Let

$$\begin{cases}
\gamma_1 = \frac{\omega\sqrt{\epsilon_m\mu_m}}{1 - \omega\sqrt{\epsilon_m\mu_m}\beta_m}, & \omega_1 = \frac{\omega}{1 - \omega\sqrt{\epsilon_m\mu_m}\beta_m}, \\
\gamma_2 = \frac{\omega\sqrt{\epsilon_m\mu_m}}{1 + \omega\sqrt{\epsilon_m\mu_m}\beta_m}, & \omega_2 = \frac{\omega}{1 + \omega\sqrt{\epsilon_m\mu_m}\beta_m}.
\end{cases} (2.6)$$

Consider an incident plane wave given by

$$\begin{cases}
E^{in}(x) = q_1 e^{i\gamma_1 p_1 \cdot x} + q_2 e^{i\gamma_2 p_2 \cdot x}, \\
H^{in}(x) = -i\sqrt{\frac{\epsilon_m}{\mu_m}} (q_1 e^{i\gamma_1 p_1 \cdot x} + q_2 e^{i\gamma_2 p_2 \cdot x}),
\end{cases} (2.7)$$

where the complex vectors p_1 , p_2 , q_1 , and q_2 satisfy the following relations:

$$p_1 \cdot q_1 = 0, \quad p_1 \times q_1 = -iq_1,$$

 $p_2 \cdot q_2 = 0, \quad p_2 \times q_2 = iq_2.$ (2.8)

Note that, under assumption (2.8), we have

$$\begin{cases}
\nabla \times (q_1 e^{i\gamma_1 p_1 \cdot x}) = \gamma_1 q_1 e^{i\gamma_1 p_1 \cdot x}, \\
\nabla \times (q_2 e^{i\gamma_1 p_2 \cdot x}) = -\gamma_2 q_2 e^{i\gamma_1 p_2 \cdot x}.
\end{cases}$$
(2.9)

The incident field E^{in} is then a combination of a left-circularly polarized plane wave and a right-circularly polarized one, and it satisfies the homogeneous Drude-Born-Fedorov equations in \mathbb{R}^3 .

2.2 Radiation condition and Lippmann-Schwinger representation

Let $E^{sc} := E - E^{in}$ and $H^{sc} := H - H^{in}$ be the scattered electric and magnetic fields, respectively. In [9], it is established that the classical Silver-Müller radiation condition,

$$\left| E^{sc}(x) - \sqrt{\frac{\mu_m}{\epsilon_m}} H^{sc}(x) \times \frac{x}{|x|} \right| \le \frac{C}{|x|^2} \quad \text{for } |x| \to +\infty,$$

uniformly in x/|x|, remains valid in chiral media. Moreover, there exists a unique solution to the scattering problem. The uniqueness follows from the Bohren decomposition of the electric and magnetic fields,

$$\begin{pmatrix} E \\ H \end{pmatrix} = \frac{1}{2} \begin{pmatrix} E^{(1)} \\ H^{(1)} \end{pmatrix} + \frac{1}{2} \begin{pmatrix} E^{(2)} \\ H^{(2)} \end{pmatrix},$$

where

$$\begin{pmatrix} E^{(1)} \\ H^{(1)} \end{pmatrix} = \begin{pmatrix} 1 & i\sqrt{\frac{\mu_m}{\epsilon_m}} \\ -i\sqrt{\frac{\epsilon_m}{\mu_m}} & 1 \end{pmatrix} \begin{pmatrix} E \\ H \end{pmatrix} \quad \text{and} \quad \begin{pmatrix} E^{(2)} \\ H^{(2)} \end{pmatrix} = \begin{pmatrix} 1 & -i\sqrt{\frac{\mu_m}{\epsilon_m}} \\ i\sqrt{\frac{\epsilon_m}{\mu_m}} & 1 \end{pmatrix} \begin{pmatrix} E \\ H \end{pmatrix}.$$

The existence is established by using an integral equation approach; see [9, Theorem 5.6].

Let us introduce the fundamental solution to the isotropic Drude-Born-Fedorov chiral medium. Let g^k be the outgoing fundamental solution of $\Delta + k^2$, i.e.,

$$g^k(x) = \frac{e^{ik|x|}}{4\pi|x|}$$
 for $x \neq 0$.

According to [9], the outgoing fundamental solution G of (2.5) is given by

$$G = \frac{1}{2} \left(\mathcal{G}_1 \begin{pmatrix} 1 & i\sqrt{\frac{\mu_m}{\epsilon_m}} \\ -i\sqrt{\frac{\epsilon_m}{\mu_m}} & 1 \end{pmatrix} + \mathcal{G}_2 \begin{pmatrix} 1 & -i\sqrt{\frac{\mu_m}{\epsilon_m}} \\ i\sqrt{\frac{\epsilon_m}{\mu_m}} & 1 \end{pmatrix} \right),$$

with

$$\mathcal{G}_{j} = \frac{\gamma_{j}^{2}}{\omega_{j}} \begin{pmatrix} 1 + \frac{\nabla \nabla \cdot}{\gamma_{j}^{2}} & i\sqrt{\frac{\mu_{m}}{\epsilon_{m}}} \frac{1}{\gamma_{j}} \nabla \times \\ -i\sqrt{\frac{\epsilon_{m}}{\mu_{m}}} \frac{1}{\gamma_{j}} \nabla \times & 1 + \frac{\nabla \nabla \cdot}{\gamma_{j}^{2}} \end{pmatrix} g^{\gamma_{j}}.$$

In [9], it was proved that the following Lippmann-Schwinger representation formula for Drude-Born-Fedorov equation (2.5) holds:

$$\begin{pmatrix} E(x) - E^{in}(x) \\ H(x) - H^{in}(x) \end{pmatrix} = \omega \int_{\Omega} G(x - y) \begin{pmatrix} \tilde{\epsilon}(y) & i\omega \tilde{\tilde{\mu}}(y) \\ -i\omega \tilde{\tilde{\epsilon}}(y) & \tilde{\mu}(y) \end{pmatrix} \begin{pmatrix} E(y) \\ H(y) \end{pmatrix} dy, \tag{2.10}$$

where

$$\begin{split} \tilde{\epsilon}(y) &= \frac{\epsilon(y)}{\epsilon_m (1 - \omega^2 \epsilon(y) \mu(y) \beta^2(y))} - \frac{1}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2}, \\ \tilde{\mu}(y) &= \frac{\mu(y)}{\mu_m (1 - \omega^2 \epsilon(y) \mu(y) \beta^2(y))} - \frac{1}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2}, \\ \tilde{\tilde{\epsilon}}(y) &= \frac{\epsilon(y) \mu(y) \beta(y)}{\mu_m (1 - \omega^2 \epsilon(y) \mu(y) \beta^2(y))} - \frac{\epsilon_m \beta_m}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2}, \\ \tilde{\tilde{\mu}}(y) &= \frac{\epsilon(y) \mu(y) \beta(y)}{\epsilon_m (1 - \omega^2 \epsilon(y) \mu(y) \beta^2(y))} - \frac{\mu_m \beta_m}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2}. \end{split}$$

3 Derivation of the dipole approximation

In this section, by the method of matched asymptotic expansions, we construct asymptotic expansions of the scattered electromagnetic fields by the particle Ω as its characteristic size $\delta \to 0$. We prove that, as $\delta \to 0$, the particle can be approximated by a pair

of electric and magnetic dipole sources. We then show that the sources can be resonant for some negative permittivity ϵ_c . It is worth emphasizing that, in a non-chiral medium, a dielectric plasmonic particle acts only as an electric dipole source [1, 13].

3.1 Matched asymptotic expansion

As in [6], to reveal the nature of the perturbations in the electric and magnetic fields, we introduce the local variables $\xi = x/\delta$ and set the fields $e_{\delta}(\xi) = E(\delta \xi)$ and $h_{\delta}(\xi) = H(\delta \xi)$. We expect that E(x) and H(x) will differ appreciably from $E^{in}(x)$ and $H^{in}(x)$ for x close to 0, but they will differ little from $E^{in}(x)$ and $H^{in}(x)$ for x far from 0. Therefore, in the spirit of matched asymptotic expansions, we shall represent each of the fields E and E by two different expansions, an inner expansion for E near 0, and an outer expansion for E far from 0. The outer expansions must begin with E^{in} and E for E and E from 0.

$$E(x) = E^{in}(x) + \delta^{\alpha_1} E_1(x) + \delta^{\alpha_2} E_2(x) + \cdots, \quad \text{for } |x| \gg O(\delta),$$

$$H(x) = H^{in}(x) + \delta^{\alpha_1} H_1(x) + \delta^{\alpha_2} H_2(x) + \cdots, \quad \text{for } |x| \gg O(\delta),$$
(3.1)

where $0 < \alpha_1 < \alpha_2 < \cdots$, and (E_1, H_1) , (E_2, H_2) , \cdots are to be found. Inserting this series into equation (2.5) and observing that

$$\epsilon(\frac{x}{\delta}) \equiv \epsilon_m, \quad \mu(\frac{x}{\delta}) \equiv \mu_m$$

for $|x| \gg O(\delta)$, we find that the outer coefficients $(E_j, H_j), j = 1, 2, \cdots$ are solutions to

$$\begin{cases}
\nabla \times E_j = \gamma_m^2 \beta_m E_j + i\omega \mu_m (\frac{\gamma_m}{k_m})^2 H_j, \\
\nabla \times H_j = \gamma_m^2 \beta_m H_j - i\omega \epsilon_m (\frac{\gamma_m}{k_m})^2 E_j
\end{cases}$$

for $|x| \gg O(\delta)$. Moreover, all (E_j, H_j) satisfy the Silver-Müller radiation condition. We write the inner expansion as

$$E(\delta\xi) = e_{\delta}(\xi) = e_{0}(\xi) + \delta e_{1}(\xi) + \cdots \quad \text{for } |\xi| = O(1),$$

$$H(\delta\xi) = h_{\delta}(\xi) = h_{0}(\xi) + \delta h_{1}(\xi) + \cdots \quad \text{for } |\xi| = O(1),$$
(3.2)

where (e_0, h_0) , (e_1, h_1) , (e_2, h_2) , \cdots are to be found. The functions $e_j(\xi)$ and $h_j(\xi)$ are defined everywhere in \mathbb{R}^3 .

In order to determine $E_j(x)$, $H_j(x)$, $e_j(\xi)$, and $h_j(\xi)$, we need to equate the inner and the outer expansions in some overlap domain within which the stretched variable ξ is large and x is small. In this domain the matching conditions are

$$E^{in}(x) + \delta^{\alpha_1} E_1(x) + \dots \sim e_0(\xi) + \delta e_1(\xi) + \dots ,$$

$$H^{in}(x) + \delta^{\alpha_1} H_1(x) + \dots \sim h_0(\xi) + \delta h_1(\xi) + \dots .$$
(3.3)

These matching conditions will be made more precise later on.

Inserting the inner expansions into the Lippmann-Schwinger representation formula (2.10), we arrive at

$$\begin{pmatrix} \delta^{\alpha_1} E_1(x) + \cdots \\ \delta^{\alpha_1} H_1(x) + \cdots \end{pmatrix} = \omega \delta^3 \int_{\Omega} G(x - \delta \xi) \begin{pmatrix} \tilde{\epsilon}(\delta \xi) & i\omega \tilde{\tilde{\mu}}(\delta \xi) \\ -i\omega \tilde{\tilde{\epsilon}}(\delta \xi) & \tilde{\mu}(\delta \xi) \end{pmatrix} \begin{pmatrix} e_0(\xi) + \delta e_1(\xi) + \cdots \\ h_0(\xi) + \delta h_1(\xi) + \cdots \end{pmatrix} d\xi$$
(3.4)

for $|x| \gg O(\delta)$. Therefore, the matching conditions (3.3) imply that

$$\alpha_i = 2 + i, \quad i = 1, 2, \cdots.$$

If we substitute the inner expansion (3.2) into (2.5) and equate coefficients of δ^{-1} , then we get the following equations:

$$\begin{cases}
\nabla \times e_0 = 0 & \text{in } \mathbb{R}^3, \\
\nabla \cdot \left(\epsilon (1 + \gamma^2 \beta^2) e_0 + i \omega \epsilon \mu \beta \left(\frac{\gamma}{k} \right)^2 h_0 \right) = 0 & \text{in } \mathbb{R}^3, \\
\nabla \times h_0 = 0 & \text{in } \mathbb{R}^3, \\
\nabla \cdot \left(\mu (1 + \gamma^2 \beta^2) h_0 - i \omega \epsilon \mu \beta \left(\frac{\gamma}{k} \right)^2 e_0 \right) = 0 & \text{in } \mathbb{R}^3, \\
e_0(\xi) \to E^{in}(0) & \text{as } |\xi| \to +\infty, \\
h_0(\xi) \to H^{in}(0) & \text{as } |\xi| \to +\infty.
\end{cases}$$
(3.5)

Here, the derivatives are taken with respect to ξ .

Since the curl of $e_0(\xi)$ and $h_0(\xi)$ are both zero, there exists scalar functions $V(\xi)$ and $W(\xi)$ satisfying

$$e_0(\xi) = \nabla V(\xi), \qquad h_0(\xi) = \nabla W(\xi), \quad \xi \in \mathbb{R}^3.$$

Then (3.5) becomes

$$\begin{cases} \nabla \cdot \left(\epsilon (1 + \gamma^2 \beta^2) \nabla V + i \omega \epsilon \mu \beta \left(\frac{\gamma}{k} \right)^2 \nabla W \right) = 0 & \text{in } \mathbb{R}^3, \\ \nabla \cdot \left(\mu (1 + \gamma^2 \beta^2) \nabla W - i \omega \epsilon \mu \beta \left(\frac{\gamma}{k} \right)^2 \nabla V \right) = 0 & \text{in } \mathbb{R}^3, \\ V(\xi) - E^{in}(0) \cdot \xi \to 0 & \text{as } |\xi| \to +\infty, \\ W(\xi) - H^{in}(0) \cdot \xi \to 0 & \text{as } |\xi| \to +\infty. \end{cases}$$

$$(3.6)$$

The first two equations in (3.6) imply that the normal components of

$$\epsilon (1 + \gamma^2 \beta^2) \nabla V + i \omega \epsilon \mu \beta \left(\frac{\gamma}{k}\right)^2 \nabla W,$$

and

$$\mu(1+\gamma^2\beta^2)\nabla W - i\omega\epsilon\mu\beta\left(\frac{\gamma}{k}\right)^2\nabla V,$$

are continuous on ∂B . Therefore, (3.6) is equivalent to

$$\begin{cases}
\Delta V = \Delta W = 0 & \text{in } B \cup (\mathbb{R}^3 \backslash \overline{B}), \\
V|^- = V|^+, \quad W|^- = W|^+ & \text{on } \partial B, \\
\epsilon_c \frac{\partial V}{\partial \nu}\Big|^- = \epsilon_m (1 + \gamma_m^2 \beta_m^2) \frac{\partial V}{\partial \nu}\Big|^+ + i\omega \epsilon_m \mu_m \beta_m \left(\frac{\gamma_m}{k_m}\right)^2 \frac{\partial W}{\partial \nu}\Big|^+ & \text{on } \partial B, \\
\mu_c \frac{\partial W}{\partial \nu}\Big|^- = \mu_m (1 + \gamma_m^2 \beta_m^2) \frac{\partial W}{\partial \nu}\Big|^+ - i\omega \epsilon_m \mu_m \beta_m \left(\frac{\gamma_m}{k_m}\right)^2 \frac{\partial V}{\partial \nu}\Big|^+ & \text{on } \partial B, \\
(V - V^{in})(\xi) \to 0 & \text{as } |\xi| \to \infty, \\
(W - W^{in})(\xi) \to 0 & \text{as } |\xi| \to \infty.
\end{cases}$$
(3.7)

Here, $\frac{\partial}{\partial \nu}$ denotes the normal derivative on ∂B , and the subscripts + and – indicate the limits from outside and inside B, respectively.

3.2 Small volume expansion and its resonant behavior

In this subsection, we formally derive a small volume expansion of (E, H) by solving (e_0, h_0) and using the Lippmann-Schwinger equation. We emphasize that the expansion can be rigorously proved. To solve $e_0 = \nabla V$ and $h_0 = \nabla W$, we make use of boundary layer potentials. We also discuss the resonant behavior of the expansion due to the negative permittivity of the plasmonic particle.

We define the single-layer potential S_B as

$$S_B[\psi](x) := -\frac{1}{4\pi} \int_{\partial B} \frac{1}{|x-y|} \psi(y) d\sigma(y), \quad x \in \mathbb{R}^3,$$

for $\psi \in H^{-1/2}(\partial B)$. We also define the Neumann-Poincaré operator \mathcal{K}_B^* by

$$\mathcal{K}_{B}^{*}[\psi](x) = \int_{\partial B} \frac{(x-y) \cdot \nu(x)}{4\pi |x-y|^{3}} \psi(y) d\sigma(y), \quad x \in \partial B$$

with $\nu(x)$ being the outward normal at $x \in \partial B$. It is well-known that the following jump relation holds:

$$\frac{\partial \mathcal{S}_B}{\partial \nu} \Big|_{\partial B}^{\pm} [\psi] = (\pm \frac{1}{2} + \mathcal{K}_B^*)[\psi]. \tag{3.8}$$

The functions V and W can be represented by using the single layer potential as

$$V = V^{in} + \mathcal{S}_B[\psi_E],$$

$$W = W^{in} + \mathcal{S}_B[\psi_H].$$
(3.9)

Using the transmission conditions on ∂B in (3.7) and the jump relation (3.8), it can be shown that the pair (ψ_E, ψ_H) is the solution to the boundary integral equation

$$A(\epsilon_c) \begin{pmatrix} \psi_E \\ \psi_H \end{pmatrix} = \begin{pmatrix} f_E \\ f_H \end{pmatrix}, \tag{3.10}$$

where

$$\mathcal{A} = \begin{pmatrix} \lambda_{\epsilon} I - \mathcal{K}_B^* & i\omega d_{\epsilon}(\frac{1}{2} + \mathcal{K}_B^*) \\ -i\omega d_{\mu}(\frac{1}{2} + \mathcal{K}_B^*) & \lambda_{\mu} I - \mathcal{K}_B^* \end{pmatrix},$$

and

$$\begin{pmatrix} f_E \\ f_H \end{pmatrix} := \begin{pmatrix} 1 & -i\omega d_{\epsilon} \\ i\omega d_{\mu} & 1 \end{pmatrix} \begin{pmatrix} E^{in}(0) \cdot \nu \\ H^{in}(0) \cdot \nu \end{pmatrix} \bigg|_{\partial B}.$$
 (3.11)

Here, the parameters $\lambda_{\epsilon}, \lambda_{\mu}, d_{\epsilon}$ and d_{μ} are given by

$$\lambda_{\epsilon} = \frac{\epsilon_{c} + \epsilon_{m} (1 + \gamma_{m}^{2} \beta_{m}^{2})}{2(\epsilon_{c} - \epsilon_{m} (1 + \gamma_{m}^{2} \beta_{m}^{2}))},$$

$$\lambda_{\mu} = \frac{\mu_{m} + \mu_{m} (1 + \gamma_{m}^{2} \beta_{m}^{2})}{2(\mu_{m} - \mu_{m} (1 + \gamma_{m}^{2} \beta_{m}^{2}))},$$

$$d_{\epsilon} = \frac{\epsilon_{m} \mu_{m} \beta_{m} (\gamma_{m} / k_{m})^{2}}{\epsilon_{c} - \epsilon_{m} (1 + \gamma_{m}^{2} \beta_{m}^{2})},$$

$$d_{\mu} = \frac{\epsilon_{m} \mu_{m} \beta_{m} (\gamma_{m} / k_{m})^{2}}{\mu_{m} - \mu_{m} (1 + \gamma_{m}^{2} \beta_{m}^{2})}.$$

It is known that the operator \mathcal{K}_B^* can be symmetrized using Calderón identity and hence becomes self-adjoint [3, 15]. Let $H_0^{-1/2}(\partial B)$ be the subspace of $H^{-1/2}(\partial B)$ with zero mean value. Let $\mathcal{H}^*(\partial B)$ be the space $H_0^{-1/2}(\partial B)$ equipped with inner product

$$\langle \varphi_1, \varphi_2 \rangle_* = -\langle \mathcal{S}_B[\varphi_2], \varphi_1 \rangle_{\frac{1}{2}, -\frac{1}{2}},$$

and (λ_j, ϕ_j) , $j = 1, 2, \cdots$ be the pair of eigenvalue and normalized eigenfunction of \mathcal{K}_B^* in $\mathcal{H}^*(\partial B)$. For any $\varphi \in H^*(\partial B)$, the following spectral representation formula holds:

$$\mathcal{K}_{B}^{*}[\varphi] = \sum_{j=1}^{\infty} \lambda_{j} \phi_{j} \langle \phi_{j}, \varphi \rangle_{*}.$$

It is then easy to see that the operator A has a block matrix structure. Indeed, we have

$$\mathcal{A} \begin{pmatrix} a\phi_n \\ b\phi_n \end{pmatrix} = \begin{pmatrix} \lambda_{\epsilon}(\epsilon_c) - \lambda_n & i\omega d_{\epsilon}(\epsilon_c)(\frac{1}{2} + \lambda_n) \\ -i\omega d_{\mu}(\frac{1}{2} + \lambda_n) & \lambda_{\mu} - \lambda_n \end{pmatrix} \begin{pmatrix} a\phi_n \\ b\phi_n \end{pmatrix}
:= A_n \begin{pmatrix} a\phi_n \\ b\phi_n \end{pmatrix}.$$
(3.12)

Since $\{\phi_j\}_{j=1}^{\infty}$ forms a complete and orthonormal basis, we can write

$$\psi_E = \sum_{n=1}^{\infty} \psi_E^n \phi_n, \quad \psi_H = \sum_{n=1}^{\infty} \psi_H^n \phi_n,$$

$$f_E = \sum_{n=1}^{\infty} f_E^n \phi_n, \quad f_H = \sum_{n=1}^{\infty} f_H^n \phi_n,$$

with the coefficients

$$\psi_E^n = \langle \psi_E, \phi_n \rangle_*, \quad \psi_H^n = \langle \psi_H, \phi_n \rangle_*,$$

$$f_E^n = \langle f_E, \phi_n \rangle_*, \quad f_H^n = \langle f_H, \phi_n \rangle_*.$$

Then, from (3.12), we have

$$\begin{pmatrix} \psi_E^n \\ \psi_H^n \end{pmatrix} = A_n^{-1} \begin{pmatrix} f_E^n \\ f_H^n \end{pmatrix} = A_n^{-1} \begin{pmatrix} 1 & -i\omega d_\epsilon \\ i\omega d_\mu & 1 \end{pmatrix} \begin{pmatrix} \langle E^{in}(0) \cdot \nu, \phi_n \rangle_* \\ \langle H^{in}(0) \cdot \nu, \phi_n \rangle_* \end{pmatrix} \bigg|_{\partial B}. \tag{3.13}$$

Therefore, we obtain the solution V and W in terms of the eigenvalue λ_n and eigenfunctions ϕ_n of the Neumann-Poincaré operator \mathcal{K}_B^* .

Now, we derive a small volume expansion of (E, H) using the Lippmann-Schwinger equation. Since $\Omega = \delta B$ and $\delta \ll 1$, by Taylor's expansion, (2.10) leads to

$$\begin{pmatrix}
E - E^{in} \\
H - H^{in}
\end{pmatrix} (x) = \omega \int_{\Omega} (G(x) + O(\delta)) \begin{pmatrix}
\tilde{\epsilon}(0) & i\omega\tilde{\tilde{\mu}}(0) \\
-i\omega\tilde{\tilde{\epsilon}}(0) & \tilde{\mu}(0)
\end{pmatrix} \begin{pmatrix}
E(y) \\
H(y)
\end{pmatrix} dy$$

$$\approx \omega G(x) K_0 \int_{\Omega} \begin{pmatrix}
E(y) \\
H(y)
\end{pmatrix} dy$$

$$\approx \omega G(x) K_0 \delta^3 \int_{B} \begin{pmatrix}
e_0 \\
h_0
\end{pmatrix},$$
(3.14)

where K_0 is defined by

$$K_0 = \begin{pmatrix} \frac{\epsilon_c}{\epsilon_m} - \frac{1}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2} & -i\omega \frac{\mu_m \beta_m}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2} \\ i\omega \frac{\epsilon_m \beta_m}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2} & 1 - \frac{1}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2} \end{pmatrix}.$$

Since

$$\begin{pmatrix} e_0 \\ h_0 \end{pmatrix} = \begin{pmatrix} E^{in}(0) \\ H^{in}(0) \end{pmatrix} + \begin{pmatrix} \nabla \mathcal{S}_B[\psi_E] \\ \nabla \mathcal{S}_B[\psi_H] \end{pmatrix}, \tag{3.15}$$

we get

$$\begin{pmatrix} E - E^{in} \\ H - H^{in} \end{pmatrix} (x) \approx \omega G(x) K_0(\epsilon_c) \delta^3 \int_{\mathcal{B}} \begin{pmatrix} E^{in}(0) + \nabla \mathcal{S}_B[\psi_E] \\ H^{in}(0) + \nabla \mathcal{S}_B[\psi_H] \end{pmatrix}. \tag{3.16}$$

Hence, we need to analyze the integral

$$\int_{B} \begin{pmatrix} \nabla \mathcal{S}_{B}[\psi_{E}] \\ \nabla \mathcal{S}_{B}[\psi_{H}] \end{pmatrix}$$

Let us define

$$\begin{pmatrix} M_n^{EE} & M_n^{EH} \\ M_n^{HE} & M_n^{HH} \end{pmatrix} = (-1)A_n^{-1} \begin{pmatrix} 1 & -i\omega d_{\epsilon} \\ i\omega d_{\mu} & 1 \end{pmatrix}. \tag{3.17}$$

Then (3.13) can be written as

$$\psi_E^n = -M_n^{EE} \langle E^{in}(0) \cdot \nu, \phi_n \rangle_* - M_n^{EH} \langle H^{in}(0) \cdot \nu, \phi_n \rangle_*,$$

$$\psi_H^n = -M_n^{HE} \langle E^{in}(0) \cdot \nu, \phi_n \rangle_* - M_n^{HH} \langle H^{in}(0) \cdot \nu, \phi_n \rangle_*.$$

For convenience of notation, here we slightly generalize the definition of the inner product $\langle \varphi_1, \varphi_2 \rangle_*$ to the case when $\varphi_1 \in (\mathcal{H}^*(\partial B))^k, k \in \mathbb{N}$ by

$$\langle \varphi_1, \varphi_2 \rangle_* = \begin{pmatrix} \langle \varphi_1^1, \varphi_2 \rangle_* \\ \langle \varphi_1^2, \varphi_2 \rangle_* \\ \vdots \\ \langle \varphi_1^k, \varphi_2 \rangle_* \end{pmatrix}.$$

With this notation, we get

$$\psi_E^n = -M_n^{EE} \langle \nu, \phi_n \rangle_*^\top E^{in}(0) - M_n^{EH} \langle \nu, \phi_n \rangle_*^\top H^{in}(0),$$

$$\psi_H^n = -M_n^{HE} \langle \nu, \phi_n \rangle_*^\top E^{in}(0) - M_n^{HH} \langle \nu, \phi_n \rangle_*^\top H^{in}(0),$$

where the superscript \top denotes the Hermitian conjugate. By using the integration by parts, it follows that

$$\int_{B} \nabla \mathcal{S}_{B}[\psi_{E}] dx = \sum_{n=1}^{\infty} \psi_{E}^{n} \int_{B} \nabla \mathcal{S}_{B}[\phi_{n}] dx$$

$$= \sum_{n=1}^{\infty} (-1) \psi_{E}^{n} \langle \nu, \phi_{n} \rangle_{*}$$

$$= \sum_{n=1}^{\infty} M_{n}^{EE} \langle \nu, \phi_{n} \rangle_{*} \langle \nu, \phi_{n} \rangle_{*}^{\top} E^{in}(0) + \sum_{n=1}^{\infty} M_{n}^{EH} \langle \nu, \phi_{n} \rangle_{*} \langle \nu, \phi_{n} \rangle_{*}^{\top} H^{in}(0),$$
(3.18)

and similarly for ψ_H ,

$$\int_{B} \nabla \mathcal{S}_{B}[\psi_{H}] dx = \sum_{n=1}^{\infty} M_{n}^{HE} \langle \nu, \phi_{n} \rangle_{*} \langle \nu, \phi_{n} \rangle_{*}^{\top} E^{in}(0) + \sum_{n=1}^{\infty} M_{n}^{HH} \langle \nu, \phi_{n} \rangle_{*} \langle \nu, \phi_{n} \rangle_{*}^{\top} H^{in}(0).$$
(3.19)

Now, if we define the polarization tensor by

$$M = M(\epsilon_c, B) = \begin{pmatrix} M^{EE} & M^{EH} \\ M^{HE} & M^{HH} \end{pmatrix}, \tag{3.20}$$

where

$$M^{EE} = \sum_{n=1}^{\infty} M_n^{EE} \langle \nu, \phi_n \rangle_* \langle \nu, \phi_n \rangle_*^{\top},$$

$$M^{EH} = \sum_{n=1}^{\infty} M_n^{EH} \langle \nu, \phi_n \rangle_* \langle \nu, \phi_n \rangle_*^{\top},$$

$$M^{HE} = \sum_{n=1}^{\infty} M_n^{HE} \langle \nu, \phi_n \rangle_* \langle \nu, \phi_n \rangle_*^{\top},$$

$$M^{HH} = \sum_{n=1}^{\infty} M_n^{HH} \langle \nu, \phi_n \rangle_* \langle \nu, \phi_n \rangle_*^{\top},$$

$$M^{HH} = \sum_{n=1}^{\infty} M_n^{HH} \langle \nu, \phi_n \rangle_* \langle \nu, \phi_n \rangle_*^{\top},$$
(3.21)

then (3.18) and (3.19) can be rewritten as

$$\int_{B} \begin{pmatrix} \nabla \mathcal{S}_{B}[\psi_{E}] \\ \nabla \mathcal{S}_{B}[\psi_{H}] \end{pmatrix} dx = M(\epsilon_{c}, B) \begin{pmatrix} E^{in}(0) \\ H^{in}(0) \end{pmatrix}. \tag{3.22}$$

Finally, from (3.16) and (3.22), we obtain a small volume expansion

$$\begin{pmatrix}
E - E^{in} \\
H - H^{in}
\end{pmatrix} (x) \approx \omega G(x) K_0(\epsilon_c) \delta^3 \widetilde{M}(\epsilon_c, B) \begin{pmatrix}
E^{in}(0) \\
H^{in}(0)
\end{pmatrix}, \quad |x| \gg O(\delta), \tag{3.23}$$

where $\widetilde{M} := |B|I + M$.

Now, let us discuss a resonant behavior of the polarization tensor M. Straightforward computation shows that

$$\det A_n(\epsilon_c) = (-1) \frac{(1/2 - \lambda_n)(1 - k_m^2 \beta_m^2 (1/2 - \lambda_n))(1 - k_m^2 \beta_m^2)}{k_m^2 \beta_m^2} \frac{\epsilon_c - \epsilon_{c,n}^*}{(1 - k_m^2 \beta_m^2)\epsilon_c - \epsilon_m},$$

where

$$\epsilon_{c,n}^* = -\epsilon_m \frac{1/2 + \lambda_n}{1/2 - \lambda_n} (1 - k_m^2 \beta_m^2 (1/2 - \lambda_n))^{-1}.$$

It is clear that $\epsilon_{c,n}^* < 0$. Therefore, when the particle is plasmonic, i.e., $\text{Re}\{\epsilon_c\} < 0$, the polarization tensor can be very large if ϵ_c is close to $\epsilon_{c,n}^* < 0$ for some n.

Regarding the permittivity ϵ_c , We make the following assumptions.

Assumption 3.1. Suppose that

- (i) There exists $n \in \mathbb{N}$ such that $\langle \nu, \phi_n \rangle_* \neq 0$;
- (ii) The permittivity ϵ_c of the plasmonic particle is close to $\epsilon_{c,n}^* < 0$.

It is worth mentioning that, when Ω is a ball, then the above assumption is satisfied with n = 1 (see Appendix A). Under the above assumption, $A_n(\epsilon_c)^{-1}$ is nearly singular. In view of (3.17), it follows that

$$\widetilde{M}(\epsilon_c, B) = M_n(\epsilon_c, B) + O(1) = O\left(\frac{1}{\det A_n(\epsilon_c)}\right).$$

Therefore, from (3.23), we arrive at

$$\begin{pmatrix} E(x) - E^{in}(x) \\ H(x) - H^{in}(x) \end{pmatrix} \approx \delta^3 \omega G(x) K_0 M_n(\epsilon_c, B) \langle \nu, \phi_n \rangle_* \langle \nu, \phi_n \rangle_*^\top \begin{pmatrix} E^{in}(0) \\ H^{in}(0) \end{pmatrix}. \tag{3.24}$$

Theorem 1. For $|x| \gg O(\delta)$, the following asymptotic expansion holds:

$$\begin{pmatrix}
E(x) - E^{in}(x) \\
H(x) - H^{in}(x)
\end{pmatrix} = \delta^3 \omega G(x) K_0 M_n(\epsilon_c, B) \langle \nu, \phi_n \rangle_* \langle \nu, \phi_n \rangle_*^\top \begin{pmatrix}
E^{in}(0) \\
H^{in}(0)
\end{pmatrix} + O(\frac{\delta^4}{|\det A_n|}).$$
(3.25)

Remark 3.1. Using the layer potential formulation (B.6) in Appendix B, Theorem 1 can be proved rigorusly by applying to (B.6) essentially the same method as the one in [1].

Remark 3.2. Note that $K_0 = 0$ if $\epsilon_c = \epsilon_m$. Moreover, from the definitions of M_n^{EE} , M_n^{EH} , M_n^{HE} , M_n^{HH} and K_0 , we can conclude that M_n and K_0 are independent of the position of particles. Formula (3.25) shows that the scattered wave from a single particle behaves similarly to a pair of resonant electric and magnetic dipole sources in the far-field. These dipole sources resonate at the set of permittivities ϵ_c satisfying $\det A_n(\epsilon_c) \approx 0$.

4 Effective medium theory and double-negative materials

We are now ready to study when we could reach double-negative mode with multiple dilute nanoparticles embedded into a chiral medium. We first derive an effective medium theory for a large number nanoparticles embedded in a chiral medium. Some conditions on the volume fraction and distribution of the nanoparticles are required. Then we prove that both the effective electric permittivity and effective magnetic permeability can be negative near the resonant frequencies.

Let Ω be a bounded smooth domain. We consider a collection of small identical plasmonic particles $\{\Omega_j^N\}_{j=1}^{N^3}$ with size of order δ . Each particle can be represented by $\Omega_j^N = \delta B + z_j^N$, where z_j^N is the center location of Ω_j^N . Let

$$\Omega^N = \Omega \setminus \overline{\cup_{j=1}^{N^3} \Omega_j^N}.$$

We assume that the following assumptions on the distribution of the plasmonic particles over the domain Ω hold.

Assumption 4.1. There exists a smooth function \widetilde{V} such that for arbitrary smooth functions f and g,

$$\max_{1 \le j \le N^3} \left| \frac{1}{N^3} \sum_{i \ne j} G(z_i^N - z_j^N) \begin{pmatrix} f(z_i^N) \\ g(z_i^N) \end{pmatrix} - \int_{\Omega} G(z - z_j^N) \widetilde{V}(z) \begin{pmatrix} f(z) \\ g(z) \end{pmatrix} dz \right|$$

$$0 \ asN \to +\infty.$$

$$(4.1)$$

The scattering problem of electromagnetic waves in a chiral media by the system of plasmonic particles can be modeled as

$$\begin{cases} \nabla \times E^{N} = i\omega \mu_{m} H^{N} & \text{in } \bigcup_{j=1}^{N^{3}} \Omega_{j}^{N}, \\ \nabla \times H^{N} = -i\omega \epsilon_{c} E^{N} & \text{in } \bigcup_{j=1}^{N^{3}} \Omega_{j}^{N}, \\ \nabla \times E^{N} = \gamma_{m}^{2} \beta_{m} E^{N} + i\omega \mu_{m} \left(\frac{\gamma_{m}}{k_{m}}\right)^{2} H^{N} & \text{in } \mathbb{R}^{3} \setminus \overline{\bigcup_{j=1}^{N^{3}} \Omega_{j}^{N}}, \\ \nabla \times H^{N} = \gamma_{m}^{2} \beta_{m} H^{N} - i\omega \epsilon_{m} \left(\frac{\gamma_{m}}{k_{m}}\right)^{2} E^{N} & \text{in } \mathbb{R}^{3} \setminus \overline{\bigcup_{j=1}^{N^{3}} \Omega_{j}^{N}}, \\ E^{N} \times \nu|_{-} = E^{N} \times \nu|_{+} & \text{on } \partial \Omega_{j}^{N}, \ j = 1, ..., N^{3}, \\ H^{N} \times \nu|_{-} = H^{N} \times \nu|_{+} & \text{on } \partial \Omega_{j}^{N}, \ j = 1, ..., N^{3}. \end{cases}$$

$$(4.2)$$

Moreover, the pair $(E^N - E^{in}, H^N - H^{in})$ satisfies the Silver-Müller radiation condition. Then, using the layer potential formulation in Appendix B, the solution (E^N, H^N) can be represented as

$$E^N = E^{in} + \mathcal{Q}^E_{\Omega^N} \begin{bmatrix} \varphi^N \\ \psi^N \end{bmatrix}, \quad H^N = H^{in} + \mathcal{Q}^H_{\Omega^N} \begin{bmatrix} \varphi^N \\ \psi^N \end{bmatrix},$$

where (φ^N, ψ^N) is the solution to

$$\left(\mathcal{J}_{\Omega^N} + \mathcal{C}_{\Omega^N}\right) \begin{bmatrix} \varphi^N \\ \psi^N \end{bmatrix} = \begin{bmatrix} \nu \times E^{in}|_{\partial \Omega^N} \\ \nu \times H^{in}|_{\partial \Omega^N} \end{bmatrix}.$$

Here, we have used the notations

$$\varphi^{N} = (\varphi_{1}^{N}, ..., \varphi_{N^{3}}^{N}),$$

$$\psi^{N} = (\psi_{1}^{N}, ..., \psi_{N^{3}}^{N}),$$

and

$$\mathcal{F}_{\Omega^N} \begin{bmatrix} \varphi^N \\ \psi^N \end{bmatrix} = \sum_{j=1}^{N^3} \mathcal{F}_{\Omega^N_j} \begin{bmatrix} \varphi^N_j \\ \psi^N_j \end{bmatrix}$$

for $\mathcal{F} = \mathcal{Q}^E, \mathcal{Q}^H, \mathcal{J}$ and \mathcal{C} .

We further assume that all the particles are aligned in a dilute manner.

Assumption 4.2. There exists $\Lambda > 0$ and a > 0, such that

$$\delta = \Lambda^{1/3} N^{-1-a}.$$

In this case, the total volume of all plasmonic particles is of order $O(\delta^3 N^3) = O(N^{-3a})$, which converges to 0 as $N \to \infty$.

One of the most important reason that we align particles in dilute way is that, we can approximate the scattered field $(E - E^{in}, H - H^{in})$ by the sum of fields generated by individual particles, i.e., the interaction between scattering fields from different particles is negligible.

For simplicity, we also assume that the particle is symmetric so that the tensor $M_n(\epsilon_c, R_{\theta_j}B)\langle \nu, \phi_n \rangle_*^\top$ is proportional to the identity matrix I. More precisely, we assume that

$$\langle \nu, \phi_n \rangle_* \langle \nu, \phi_n \rangle_*^{\top} = c_n I, \tag{4.3}$$

for some $c_n > 0$. A more general case can be considered in the same way by assuming that the particles are randomly oriented and using averaging with respect to the orientation of the particle (see Remark 4.1). When B is a unit ball, one can check that $c_1 = \frac{4\pi}{27}$ (see Appendix A).

For $1 \le j \le N^3$, we define

$$E_j^{in,N} = E^{in} + \sum_{i \neq j} \mathcal{P}_{\Omega_i^N} \begin{bmatrix} \varphi_i^N \\ \psi_i^N \end{bmatrix}, \quad H_j^{in,N} = H^{in} + \sum_{i \neq j} \mathcal{Q}_{\Omega^N} \begin{bmatrix} \varphi_i^N \\ \psi_i^N \end{bmatrix}.$$

For each $1 \le j \le N^3$ and $x \in \Omega^N$,

$$E^{N}(x) = E^{in}(x) + \sum_{i=1}^{N^{3}} E_{i}^{sc,N}(x)$$
$$= E_{j}^{in,N}(x) + E_{j}^{sc,N}(x). \tag{4.4}$$

Proposition 1. For each $1 \le j \le N^3$ and $x \in \Omega^N$,

$$\begin{pmatrix} E_j^{sc,N}(x) \\ H_j^{sc,N}(x) \end{pmatrix} = \delta^3 \omega G(x - z_j^N) K_0 M_n(\epsilon_c, B) c_n \begin{pmatrix} E^{in,N}(z_j^N) \\ H^{in,N}(z_j^N) \end{pmatrix} + (\frac{N^3 \delta^4}{|\det A_n|}).$$

4.1 Derivation of the homogenized equation and analysis of effective parameters

Let us assume that

$$N^{-3a}|\det A_n|^{-1} = O(1), \tag{4.5}$$

and define

$$\begin{pmatrix} \tilde{\epsilon}_{\text{eff}}^N & i\omega\tilde{\tilde{\mu}}_{\text{eff}}^N \\ -i\omega\tilde{\tilde{\epsilon}}_{\text{eff}}^N & \tilde{\mu}_{\text{eff}}^N \end{pmatrix} := \Lambda N^{-3a} c_n K_0 M_n(\epsilon_c, B).$$

Then, from (4.4) and Proposition 1, we can see that

$$\begin{pmatrix}
E^{N}(x) \\
H^{N}(x)
\end{pmatrix} = \begin{pmatrix}
E^{in}(x) \\
H^{in}(x)
\end{pmatrix} + \frac{1}{N^{3}} \sum_{j=1}^{N^{3}} \omega G(x - z_{j}^{N}) \begin{pmatrix}
\tilde{\epsilon}_{\text{eff}}^{N} & i\omega\tilde{\mu}_{\text{eff}}^{N} \\
-i\omega\tilde{\tilde{\epsilon}}_{\text{eff}}^{N} & \tilde{\mu}_{\text{eff}}^{N}
\end{pmatrix} \begin{pmatrix}
E^{N}(z_{j}^{N}) \\
H^{N}(z_{j}^{N})
\end{pmatrix} + O(\frac{N^{3}\delta^{4}}{|\det A_{n}|})$$
(4.6)

for $x \in \Omega \setminus (\bigcup_{j=1}^{N^3} z_j^N)$. Assuming the homogenized limit $(E^h, H^h) := \lim_{N \to \infty} (E^N, H^N)$ exists in some sense, we can easily expect that (E^h, H^h) satisfies

$$\begin{pmatrix} E^{h} \\ H^{h} \end{pmatrix} = \begin{pmatrix} E^{in} \\ H^{in} \end{pmatrix} + \int_{\Omega} \omega G(\cdot - z) \begin{pmatrix} \tilde{\epsilon}_{\text{eff}}(z) & i\omega \tilde{\tilde{\mu}}_{\text{eff}}(z) \\ -i\omega \tilde{\tilde{\epsilon}}_{\text{eff}}(z) & \tilde{\mu}_{\text{eff}}(z) \end{pmatrix} \begin{pmatrix} E^{h}(z) \\ H^{h}(z) \end{pmatrix} dz \quad \text{in } \Omega, \quad (4.7)$$

where

$$\begin{pmatrix} \tilde{\epsilon}_{\mathrm{eff}} & i\omega\tilde{\tilde{\mu}}_{\mathrm{eff}} \\ -i\omega\tilde{\tilde{\epsilon}}_{\mathrm{eff}} & \tilde{\mu}_{\mathrm{eff}} \end{pmatrix} := \tilde{V} \lim_{N \to \infty} \begin{pmatrix} \tilde{\epsilon}_{\mathrm{eff}}^{N} & i\omega\tilde{\tilde{\mu}}_{\mathrm{eff}}^{N} \\ -i\omega\tilde{\tilde{\epsilon}}_{\mathrm{eff}}^{N} & \tilde{\mu}_{\mathrm{eff}}^{N} \end{pmatrix}.$$

Straightforward but tedious computations show that the following compatibility condition holds:

$$\frac{\tilde{\epsilon}_{\text{eff}} + \frac{\epsilon_m \beta_m}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2}}{\tilde{\mu}_{\text{eff}} + \frac{\mu_m \beta_m}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2}} = \frac{\epsilon_m}{\mu_m}.$$
(4.8)

We can conclude by comparing (4.7) with the Lippmann-Schwinger equation (2.10), that the effective electric permittivity ϵ_{eff} and magnetic permeability μ_{eff} are determined by solving the system of three equations

$$\tilde{\epsilon}_{\text{eff}} = \frac{\epsilon_{\text{eff}}}{\epsilon_m (1 - \omega^2 \epsilon_{\text{eff}} \mu_{\text{eff}} \beta_{\text{eff}}^2)} - \frac{1}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2},$$

$$\tilde{\mu}_{\text{eff}} = \frac{\mu_{\text{eff}}}{\mu_m (1 - \omega^2 \epsilon_{\text{eff}} \mu_{\text{eff}} \beta_{\text{eff}}^2)} - \frac{1}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2},$$

$$\tilde{\epsilon}_{\text{eff}} = \frac{\epsilon_{\text{eff}} \mu_{\text{eff}} \beta_{\text{eff}}}{\mu_m (1 - \omega^2 \epsilon_{\text{eff}} \mu_{\text{eff}} \beta_{\text{eff}}^2)} - \frac{\epsilon_m \beta_m}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2}.$$
(4.9)

Here, β_{eff} is the effective chiral admittance. Note that, due to the compatibility condition (4.8), the following relation immediately holds:

$$\tilde{\tilde{\mu}}_{\text{eff}} = \frac{\epsilon_{\text{eff}} \mu_{\text{eff}} \beta_{\text{eff}}}{\epsilon_m (1 - \omega^2 \epsilon_{\text{eff}} \mu_{\text{eff}} \beta_{\text{eff}}^2)} - \frac{\mu_m \beta_m}{1 - \omega^2 \epsilon_m \mu_m \beta_m^2}.$$

In fact, the equation (4.9) is uniquely solvable. One can easily check that

$$\epsilon_{\text{eff}} = \epsilon_m \left((\tilde{\epsilon}_{\text{eff}} + \tilde{\gamma}_m) - \omega^2 (\tilde{\tilde{\epsilon}}_{\text{eff}} + \epsilon_m \beta_m \tilde{\gamma}_m) \frac{\tilde{\tilde{\mu}}_{\text{eff}} + \mu_m \beta_m \tilde{\gamma}_m}{\tilde{\mu}_{\text{eff}} + \tilde{\gamma}_m} \right),$$

$$\mu_{\text{eff}} = \mu_m \left((\tilde{\mu}_{\text{eff}} + \tilde{\gamma}_m) - \omega^2 (\tilde{\tilde{\mu}}_{\text{eff}} + \mu_m \beta_m \tilde{\gamma}_m) \frac{\tilde{\tilde{\epsilon}}_{\text{eff}} + \epsilon_m \beta_m \tilde{\gamma}_m}{\tilde{\epsilon}_{\text{eff}} + \tilde{\gamma}_m} \right), \tag{4.10}$$

where

$$\tilde{\gamma}_m = \frac{1}{1 - k_m^2 \beta_m^2}.$$

Therefore, (E^h, H^h) satisfies

$$\begin{cases}
\nabla \times E^{h} = \gamma_{h}^{2} \beta_{h} E^{h} + i \omega \mu_{h} \left(\frac{\gamma_{h}}{k_{h}}\right)^{2} H^{h} & \text{in } \Omega, \\
\nabla \times H^{h} = \gamma_{h}^{2} \beta_{h} H^{h} - i \omega \epsilon_{h} \left(\frac{\gamma_{h}}{k_{h}}\right)^{2} E^{h} & \text{in } \Omega,
\end{cases}$$
(4.11)

with the homogenized material parameters

$$\epsilon_h = \begin{cases} \epsilon_{\text{eff}}, & \text{in } \Omega \\ \epsilon_m, & \text{in } \mathbb{R}^3 \setminus \Omega \end{cases}, \quad \mu_h = \begin{cases} \mu_{\text{eff}}, & \text{in } \Omega \\ \mu_m, & \text{in } \mathbb{R}^3 \setminus \Omega \end{cases}.$$

The other parameters β_h, γ_h , and k_h are defined similarly.

4.2 Double-negative effective properties

Here, we show that the effective properties ϵ_{eff} and μ_{eff} can be both negative.

Let us first consider the resonant behavior of the matrix

$$\begin{pmatrix} \tilde{\epsilon}_{\text{eff}}^{N} & i\omega\tilde{\tilde{\mu}}_{\text{eff}}^{N} \\ -i\omega\tilde{\tilde{\epsilon}}_{\text{eff}}^{N} & \tilde{\mu}_{\text{eff}}^{N} \end{pmatrix},$$

when ϵ_c is close to $\epsilon_{c,n}^*$. Straightforward but tedious computations show that each of components has the following behavior with respect to ϵ_c :

$$\tilde{\epsilon}_{\text{eff}}^{N} = \frac{\Lambda N^{-3\alpha} c_{n} \epsilon_{m}}{(1/2 - \lambda_{n})^{3} (1 - \beta_{m}^{2} k_{m}^{2} (1/2 - \lambda_{n}))^{2}} \left(\frac{-1}{\epsilon_{c} - \epsilon_{c,n}^{*}} + O(1)\right),$$

$$\tilde{\mu}_{\text{eff}}^{N} = \frac{\Lambda N^{-3\alpha} c_{n} \epsilon_{m} k_{m}^{2} \beta_{m}^{2}}{(1/2 - \lambda_{n}) (1 - \beta_{m}^{2} k_{m}^{2} (1/2 - \lambda_{n}))^{2}} \left(\frac{-1}{\epsilon_{c} - \epsilon_{c,n}^{*}} + O(1)\right),$$

$$\tilde{\epsilon}_{\text{eff}}^{N} = \frac{\Lambda N^{-3\alpha} c_{n} \epsilon_{m}^{2} \beta_{m}}{(1/2 - \lambda_{n})^{2} (1 - \beta_{m}^{2} k_{m}^{2} (1/2 - \lambda_{n}))^{2}} \left(\frac{-1}{\epsilon_{c} - \epsilon_{c,n}^{*}} + O(1)\right),$$

$$\tilde{\mu}_{\text{eff}}^{N} = \frac{\Lambda N^{-3\alpha} c_{n} \epsilon_{m} \mu_{m} \beta_{m}}{(1/2 - \lambda_{n})^{2} (1 - \beta_{m}^{2} k_{m}^{2} (1/2 - \lambda_{n}))^{2}} \left(\frac{-1}{\epsilon_{c} - \epsilon_{c,n}^{*}} + O(1)\right).$$
(4.12)

Here O(1) means that the remainder does not diverge for any ϵ_c .

Now we turn to the effective properties $\epsilon_{\text{eff}}(y)$ and $\mu_{\text{eff}}(y)$ for $y \in \Omega$. For the sake of simplicity of presentation, we assume that at y, $\widetilde{V}(y) = 1$. By applying the asymptotics (4.12) to (4.10), one can check that each of ϵ_{eff} and μ_{eff} has a removable singularity at $\epsilon_c = \epsilon_{c,n}^*$. In fact, ϵ_{eff} (or μ_{eff}) diverges only when ϵ_c satisfies $\widetilde{\mu}_{\text{eff}} + \widetilde{\gamma}_m = 0$ (respectively $\widetilde{\epsilon}_{\text{eff}} + \widetilde{\gamma}_m = 0$). Let $\epsilon_{c,n}^*[\epsilon_{\text{eff}}]$ (and $\epsilon_{c,n}^*[\mu_{\text{eff}}]$) be the value of ϵ_c at which ϵ_{eff} (respectively μ_{eff}) diverges. Then, it can be easily checked that, for large N,

$$\epsilon_{c,n}^* [\epsilon_{\text{eff}}] \approx \epsilon_{c,n}^* + \frac{\epsilon_m k_m^2 \beta_m^2}{(1/2 - \lambda_n)(1 - \beta_m^2 k_m^2 (1/2 - \lambda_n))^2} \tilde{\gamma}_m^{-1} c_n \Lambda N^{-3\alpha}$$
(4.13)

$$\epsilon_{c,n}^*[\mu_{\text{eff}}] \approx \epsilon_{c,n}^* + \frac{\epsilon_m}{(1/2 - \lambda_n)^3 (1 - \beta_{\text{m}}^2 k_{\text{m}}^2 (1/2 - \lambda_n))^2} \tilde{\gamma}_m^{-1} c_n \Lambda N^{-3\alpha}$$
 (4.14)

Note that

$$\epsilon_{c,n}^*[\mu_{\text{eff}}] > \epsilon_{c,n}^*[\epsilon_{\text{eff}}].$$

Now we choose ϵ_c such that ϵ_c is slightly above the two resonant permittivities. More precisely, we assume the following.

Assumption 4.3. Let 0 < s < 1 be given and assume that

$$\epsilon_c = \epsilon_{c,n}^* + s^{-1} \frac{\Lambda N^{-3\alpha} c_n \epsilon_m}{(1/2 - \lambda_n)^3 (1 - \beta_m^2 k_m^2 (1/2 - \lambda_n))^2} \tilde{\gamma}_m^{-1}. \tag{4.15}$$

If s is very close to one, ϵ_c is slightly above the resonant permittivity $\epsilon_{c,n}^*[\mu_{\text{eff}}]$.

By substituting (4.15) into (4.12) and then taking limit $N \to \infty$, we have

$$\begin{split} \tilde{\epsilon}_{\text{eff}} &= -s\tilde{\gamma}_m, \\ \tilde{\mu}_{\text{eff}} &= -s\tilde{\gamma}_m (k_m\beta_m)^2 (1/2 - \lambda_n)^2, \\ \tilde{\tilde{\epsilon}}_{\text{eff}} &= -s\tilde{\gamma}_m\epsilon_m\beta_m (1/2 - \lambda_n), \\ \tilde{\tilde{\mu}}_{\text{eff}} &= -s\tilde{\gamma}_m\mu_m\beta_m (1/2 - \lambda_n). \end{split}$$

So, using (4.10), we finally get the formulas for the effective material parameters as follows:

$$\epsilon_{\text{eff}} = \epsilon_m \tilde{\gamma}_m \Big((1 - s) - \omega^2 \Big(1 - s(1/2 - \lambda_n) \Big) \frac{\mu_m \beta_m (1 - s(1/2 - \lambda_n))}{1 - s(k_m \beta_m)^2 (1/2 - \lambda_n)^2} \Big),$$

$$\mu_{\text{eff}} = \mu_m \tilde{\gamma}_m \Big(1 - s(k_m \beta_m)^2 (1/2 - \lambda_n)^2 - \frac{1}{1 - s} (k_m \beta_m)^2 \Big(1 - s(1/2 - \lambda_n))^2 \Big). \tag{4.16}$$

Now we can prove that the above effective parameters are both negative as shown in the following theorem.

Theorem 2. (Double-negative property) Suppose that the permittivity ϵ_c of the plasmonic particle is given as in Assumption 4.3. Then, the effective parameters ϵ_{eff} and μ_{eff} of the homogenized equation are both negative provided s is sufficiently close to one.

Proof. Since 0 < s < 1, $|\lambda_n| < 1/2$ and $k_m \beta_m < 1$, the conclusion immediately follows from (4.16).

Remark 4.1. Although we assume the shape of the particle is symmetric, our result can be extended to the case of arbitrary shaped particles. Suppose that the particles are randomly oriented. Then the average of $\langle \nu, \phi_n \rangle_* \langle \nu, \phi_n \rangle_*^\top$ over the orientation of the particle becomes a diagonal matrix as in the symmetric case (4.3). Therefore, we obtain in exactly the same manner negative effective permittivity and negative effective permeability for frequencies near the resonant permittivity $\epsilon_{c,n}^*$.

Remark 4.2. We provide a numerical example in Figure 1. We plot the effective parameters ϵ_{eff} and μ_{eff} as functions of ϵ_c . We set $\omega=1, \epsilon_m=1, \mu_m=1$ $\Lambda=3, N=125$ and a=0.965. In the left figure, we use $\beta_m=1.09$. Clearly, both the effective parameters are negative near $\epsilon_c=-2.94455$. In the right figure, we change β_m as $\beta_m=0$, which means that there is no chirality. In this case, only ϵ_{eff} is resonant but μ_{eff} remains as one. This shows the importance of the chirality to achieve the double-negative metamaterial.


Remark 4.3. The resonance frequency can be determined by the Drude model

$$\epsilon_c(\omega) = 1 - \frac{\omega_p^2}{\omega^2 + i\tau\omega},$$

where ω_p and τ are two given positive constants.

Remark 4.4. For simplicity, we assume that ϵ_c is real. The analysis in this section applies to the case where $\operatorname{Im}_{\epsilon_c}$ is sufficiently small.

Remark 4.5. By using the same approach as in [14, 22, 28], we provide under some assumptions on the distribution of the plasmonic particles a justification of the derivation of the effective medium parameters. See Appendix C.






Figure 1: The effective properties of the homogenized media. A chiral media $\beta_m \neq 0$ (left), a non-chiral media $\beta_m = 0$ (right).

5 Concluding remarks

In this paper, we have first derived an asymptotic expansion of the scattered electromagnetic fields by a small plasmonic dielectric nanoparticle in a chiral medium. We have shown that the plasmonic particle can be approximated by the sum of a resonant electric dipole and a resonant magnetic dipole. We have also characterized these resonant frequencies in terms of the chirality admittance of the background medium and the material parameters and the shape of the particle. Then we have obtained an effective medium theory for materials consisting of a large number of plasmonic nanoparticles embedded in a chiral background medium. We have shown that the dielectric plasmonic particles contribute to both the effective electric permittivity and the effective magnetic permeability. Finally, we have proved that both the effective electric permittivity and magnetic permeability can be negative near some resonant frequencies.

A Explicit computation for a ball

Suppose that B is the unit ball. In this case, we are able to write out its polarization tensor $M(\epsilon_c, B)$ defined in (3.20) explicitly. In order to do so, we compute the tensor $\sum_{l=-1}^{1} \langle \nu, Y_1^l \rangle_* \langle \nu, Y_1^l \rangle_*^{\top}$. The following lemma from [3] will be required.

Lemma 1. For $n = 0, 1, \dots$, we have

$$\mathcal{K}_{B}^{*}[Y_{n}^{l}] = \frac{1}{2(2n+1)}Y_{n}^{l}(\hat{x}), \quad |x| = 1, l = -n, \cdots, n,$$

where $\hat{x} = x/|x|$ and $(Y_n^l)_{l=-n,\dots,n}$ are the orthonormal spherical harmonics of degree n

and order l. Moreover,

$$\langle \nu, Y_n^l \rangle_* = -\int_{\partial \Omega} \mathcal{S}_B[Y_n^l] \nu d\sigma(x)$$

$$= -\int_{\partial B} -\frac{1}{2n+1} Y_n^l(\hat{x}) \hat{x} d\sigma(x)$$

$$= \frac{1}{2n+1} \int_{\partial B} Y_n^l(\hat{x}) \hat{x} d\sigma(\hat{x}).$$

Since $\hat{x} = (\sin \theta \cos \varphi, \sin \theta \sin \varphi, \cos \theta)$, and by definition of the spherical harmonic functions,

$$Y_n^l(\theta,\varphi) := \sqrt{\frac{2n+1}{4\pi} \frac{(n-|l|)!}{(n+|l|)!}} P_n^{|l|}(\cos\theta) e^{il\varphi},$$

with $P_n^{|l|}$ being the associated Legendre polynomial of degree n and order |l|, we have

$$\begin{split} Y_{1}^{-1}(\theta,\varphi) &= \frac{1}{2} \sqrt{\frac{3}{2\pi}} P_{1}^{1}(\cos\theta) e^{-i\varphi} = \frac{1}{2} \sqrt{\frac{3}{2\pi}} \sin\theta e^{-i\varphi}, \\ Y_{1}^{1}(\theta,\varphi) &= \frac{1}{2} \sqrt{\frac{3}{2\pi}} P_{1}^{1}(\cos\theta) e^{i\varphi} = \frac{1}{2} \sqrt{\frac{3}{2\pi}} \sin\theta e^{i\varphi}, \\ Y_{1}^{0}(\theta,\varphi) &= \frac{1}{2} \sqrt{\frac{3}{\pi}} P_{1}^{0}(\cos\theta) = \frac{1}{2} \sqrt{\frac{3}{\pi}} \cos\theta. \end{split}$$

Consequently,

$$\sin\theta\cos\varphi = \sqrt{\frac{2\pi}{3}}(\bar{Y}_1^{-1} + \bar{Y}_1^1),$$

$$\sin\theta\sin\varphi = i\sqrt{\frac{2\pi}{3}}(\bar{Y}_1^1 - \bar{Y}_1^{-1}),$$

$$\cos\theta = 2\sqrt{\frac{\pi}{3}}\bar{Y}_1^0,$$

where \bar{Y}_n^l is the complex conjugate of Y_n^l . Since $\{Y_n^l\}$ is an orthogonal basis of $L^2(\partial B)$, the infinite sum in (3.20) is actually finite, and among all the terms only $\langle \nu, Y_1^{-1} \rangle_*$,

 $\langle \nu, Y_1^0 \rangle_*$, and $\langle \nu, Y_1^1 \rangle_*$ are nonzero. We can calculate that

$$\begin{split} \sum_{l,n} \langle \nu, Y_n^l \rangle_* \langle \nu, Y_n^l \rangle_*^\top &= \sum_{l=-1}^1 \langle \nu, Y_1^l \rangle_* \langle \nu, Y_1^l \rangle_*^\top \\ &= \frac{1}{9} \left(\begin{pmatrix} -\sqrt{\frac{2\pi}{3}} \\ i\sqrt{\frac{2\pi}{3}} \\ 0 \end{pmatrix} \left(-\sqrt{\frac{2\pi}{3}} & -i\sqrt{\frac{2\pi}{3}} & 0 \right) + \begin{pmatrix} 0 \\ 0 \\ 2\sqrt{\frac{\pi}{3}} \end{pmatrix} \left(0 & 0 & 2\sqrt{\frac{\pi}{3}} \right) \right) \\ &+ \frac{1}{9} \left(\begin{pmatrix} -\sqrt{\frac{2\pi}{3}} \\ -i\sqrt{\frac{2\pi}{3}} \\ 0 \end{pmatrix} \left(-\sqrt{\frac{2\pi}{3}} & i\sqrt{\frac{2\pi}{3}} & 0 \right) \right) \\ &= \frac{4\pi}{27} I. \end{split}$$

B Layer potentials for electromagnetic waves in a chiral medium

In this appendix, we briefly review the results in [17] concerning the layer potential techniques for electromagnetic scattering by the particle Ω in a chiral medium.

For $s = \pm 1/2$, let $H^s(\partial\Omega)$ denote the usual Sobolev space of order s on $\partial\Omega$ and let

$$H_T^s(\partial\Omega) = \left\{ \varphi \in \left(H^s(\partial\Omega) \right)^3, \nu \cdot \varphi = 0 \right\}.$$

Let $\nabla_{\partial\Omega}$, $\nabla_{\partial\Omega}$ and $\Delta_{\partial\Omega}$ denote the surface gradient, surface divergence and Laplace-Beltrami operator respectively and define the vectorial and scalar surface curl by $\vec{\operatorname{curl}}_{\partial\Omega}\varphi = -\nu \times \nabla_{\partial\Omega}\varphi$ for $\varphi \in H^{\frac{1}{2}}(\partial\Omega)$ and $\vec{\operatorname{curl}}_{\partial\Omega}\varphi = -\nu \cdot (\nabla_{\partial\Omega}\times\varphi)$ for $\varphi \in H^{-\frac{1}{2}}_T(\partial\Omega)$, respectively. We introduce the following functional space:

$$H_T^{-\frac{1}{2}}(\mathrm{div},\partial\Omega) \ = \ \left\{\varphi\in H_T^{-\frac{1}{2}}(\partial\Omega), \nabla_{\partial\Omega}\cdot\varphi\in H^{-\frac{1}{2}}(\partial\Omega)\right\}.$$

We introduce the boundary layer potentials by

$$\begin{split} \vec{\mathcal{S}}_{\Omega}^{k}[\varphi](x) &= \int_{\partial\Omega} g^{k}(x-y)\varphi(y)d\sigma(y), \quad x \in \mathbb{R}^{3}, \\ \mathcal{S}_{\Omega}^{k}[\psi](x) &= \int_{\partial\Omega} g^{k}(x-y)\psi(y)d\sigma(y) \quad \text{for a scalar function } \psi \in H^{-\frac{1}{2}}(\partial\Omega) \text{ and } x \in \mathbb{R}^{3}, \\ \mathcal{M}_{\Omega}^{k}[\varphi](x) &= \int_{\partial\Omega} \nu(x) \times \nabla_{x} \times g^{k}(x-y)\varphi(y)d\sigma(y), \quad x \in \partial\Omega, \\ \mathcal{L}_{\Omega}^{k}[\varphi](x) &= \nu(x) \times \left(k^{2}\vec{\mathcal{S}}_{\Omega}^{k}[\varphi](x) + \nabla\mathcal{S}_{\Omega}^{k}[\nabla_{\partial\Omega} \cdot \varphi](x)\right), \quad x \in \partial\Omega. \end{split}$$

We also introduce the notations

$$\alpha_{1,c} = \frac{1}{i\tau_c}, \quad \alpha_{2,c} = -i\tau_c, \quad \alpha_{1,m} = \frac{1}{i\tau_m}, \quad \alpha_{2,m} = -i\tau_m,$$

where $\tau_c = \sqrt{\mu_m/\epsilon_c}$ and $\tau_m = \sqrt{\mu_m/\epsilon_m}$.

We consider the Bohren decomposition of (E, H) into Beltrami fields, i.e.,

$$E = Q_1 + \alpha_{2,c}Q_2, \quad H = \alpha_{1,c}Q_1 + Q_2 \quad \text{in } \Omega.$$
 (B.1)

Similarly,

$$E^{sc} = Q_1 + \alpha_{2,m}Q_2, \quad H^{sc} = \alpha_{1,m}Q_1 + Q_2 \quad \text{in } \mathbb{R}^3 \setminus \overline{\Omega}.$$
 (B.2)

We can see that they satisfy the vector Helmholtz equations as

$$\begin{cases} (\Delta + \gamma_{j,c}^2)Q_j = 0, & \text{in } \Omega, \\ (\Delta + \gamma_{j,m}^2)Q_j = 0, & \text{in } \mathbb{R}^3 \setminus \overline{\Omega}, \end{cases}$$

where

$$\gamma_{j,m} = \frac{k_m}{1 + (-1)^j k_m \beta_m}, \quad \gamma_{j,c} = \omega \sqrt{\epsilon_c \mu_m}, \quad j = 1, 2.$$

We define the operator Q_j , for $(\varphi_1, \varphi_2) \in H_T^{-\frac{1}{2}}(\text{div}, \partial\Omega)$, by

$$Q_{\Omega,j} \begin{bmatrix} \varphi_1 \\ \varphi_2 \end{bmatrix} = \begin{cases} ((-1)^{j+1} \gamma_{j,c} \nabla \times \vec{\mathcal{S}}_{\Omega}^{\gamma_{j,c}} + \nabla \times \nabla \times \vec{\mathcal{S}}_{\Omega}^{\gamma_{j,c}}) [\varphi_j] & \text{in } \Omega, \\ ((-1)^{j+1} \gamma_{j,c} \nabla \times \vec{\mathcal{S}}_{\Omega}^{\gamma_{j,m}} + \nabla \times \nabla \times \vec{\mathcal{S}}_{\Omega}^{\gamma_{j,m}}) [\zeta_{j1} \varphi_1 + \zeta_{j2} \varphi_2] & \text{in } \mathbb{R}^3 \setminus \overline{\Omega} \end{cases}$$

with ζ_{ij} , i, j = 1, 2, given by

$$\zeta_{11} = \frac{1}{2}(1 + \frac{\tau_m}{\tau_c}), \quad \zeta_{12} = \frac{i}{2}(\tau_c - \tau_m),$$
(B.3)

$$\zeta_{21} = \frac{i}{2} \left(\frac{1}{\tau_m} - \frac{1}{\tau_c} \right), \quad \zeta_{22} = \frac{i}{2} \left(1 + \frac{\tau_c}{\tau_m} \right).$$
(B.4)

Then the solution Q_j , for j = 1, 2, can be represented as

$$Q_j = \mathcal{Q}_{\Omega,j} \begin{bmatrix} \psi_1 \\ \psi_2 \end{bmatrix}, \tag{B.5}$$

where (ψ_1, ψ_2) is the solution of the integral equation

$$(\mathcal{J}_{\Omega} + \mathcal{C}_{\Omega}) \begin{pmatrix} \psi_1 \\ \psi_2 \end{pmatrix} = \begin{pmatrix} \nu \times E^{in} |_{\partial \Omega} \\ \nu \times H^{in} |_{\partial \Omega} \end{pmatrix}.$$
 (B.6)

Here, the operator \mathcal{J}_{Ω} is given by

$$\begin{split} (\mathcal{J}_{\Omega})_{11} &= -\zeta_{11}\mathcal{L}_{\Omega}^{\gamma_{1,m}} + \mathcal{L}_{\Omega}^{\gamma_{1,c}} - \zeta_{21}\alpha_{2,m}\mathcal{L}_{\Omega}^{\gamma_{2,m}} - \frac{1}{2}(\zeta_{11}\gamma_{1,m} + \gamma_{1,c} - \zeta_{21}\alpha_{2,m}\gamma_{2,m})I, \\ (\mathcal{J}_{\Omega})_{12} &= -\zeta_{11}\mathcal{L}_{\Omega}^{\gamma_{1,m}} + \alpha_{2,m}\mathcal{L}_{\Omega}^{\gamma_{2,m}} - \zeta_{22}\alpha_{2,m}\mathcal{L}_{\Omega}^{\gamma_{2,m}} - \frac{1}{2}(\zeta_{12}\gamma_{1,m} - \alpha_{2,c}\gamma_{2,c} - \zeta_{22}\alpha_{2,m}\gamma_{2,m})I, \\ (\mathcal{J}_{\Omega})_{21} &= -\zeta_{21}\mathcal{L}_{\Omega}^{\gamma_{2,m}} + \alpha_{1,m}\mathcal{L}_{\Omega}^{\gamma_{1,m}} - \zeta_{11}\alpha_{1,m}\mathcal{L}_{\Omega}^{\gamma_{1,m}} - \frac{1}{2}(-\zeta_{21}\gamma_{2,m} + \alpha_{1,c}\gamma_{1,c} + \zeta_{11}\alpha_{1,m}\gamma_{1,m})I, \\ (\mathcal{J}_{\Omega})_{22} &= -\zeta_{22}\mathcal{L}_{\Omega}^{\gamma_{2,m}} + \mathcal{L}_{\Omega}^{\gamma_{2,c}} - \zeta_{12}\alpha_{1,m}\mathcal{L}_{\Omega}^{\gamma_{1,m}} - \frac{1}{2}(\zeta_{22}\gamma_{2,m} - \gamma_{2,c} + \zeta_{12}\alpha_{1,m}\gamma_{1,m})I, \end{split}$$

and the operator \mathcal{C}_{Ω} is given by

$$\begin{split} &(\mathcal{C}_{\Omega})_{11} = -\zeta_{11}\gamma_{1,m}\mathcal{M}_{\Omega}^{\gamma_{1,m}} - \gamma_{1,c}\mathcal{M}_{\Omega}^{\gamma_{1,c}} + \zeta_{21}\alpha_{2,m}\gamma_{2,m}\mathcal{M}_{\Omega}^{\gamma_{2,m}}, \\ &(\mathcal{C}_{\Omega})_{12} = -\zeta_{12}\gamma_{1,m}\mathcal{M}_{\Omega}^{\gamma_{1,m}} + \alpha_{2,c}\gamma_{2,c}\mathcal{M}_{\Omega}^{\gamma_{2,c}} + \zeta_{22}\alpha_{2,m}\gamma_{2,m}\mathcal{M}_{\Omega}^{\gamma_{2,m}}, \\ &(\mathcal{C}_{\Omega})_{21} = \zeta_{21}\gamma_{2,m}\mathcal{M}_{\Omega}^{\gamma_{2,m}} - \alpha_{1,c}\gamma_{1,c}\mathcal{M}_{\Omega}^{\gamma_{1,c}} - \zeta_{11}\alpha_{1,m}\gamma_{1,m}\mathcal{M}_{\Omega}^{\gamma_{1,m}}, \\ &(\mathcal{C}_{\Omega})_{22} = -\zeta_{22}\gamma_{2,m}\mathcal{M}_{\Omega}^{\gamma_{2,m}} + \gamma_{2,c}\mathcal{M}_{\Omega}^{\gamma_{2,c}} - \zeta_{12}\alpha_{1,m}\gamma_{1,m}\mathcal{M}_{\Omega}^{\gamma_{1,m}}. \end{split}$$

The operator $\mathcal{C}_{\Omega}: H_T^{-\frac{1}{2}}(\operatorname{div}, \partial \Omega) \to H_T^{-\frac{1}{2}}(\operatorname{div}, \partial \Omega)$ is compact.

$$Q_{\Omega}^{E} = Q_{\Omega,1} + \alpha_{2,c}Q_{\Omega,2}, \quad Q_{\Omega}^{H} = \alpha_{1,c}Q_{\Omega,1} + Q_{\Omega,2}.$$

In view of (B.1), (B.2) and (B.5), the operator \mathcal{Q}_{Ω}^{E} (or \mathcal{Q}_{Ω}^{H}) maps density functions on $\partial\Omega$ to the corresponding electric field (respectively, the magnetic field).

C Justification of the homogenization procedure

In this appendix, we provide a justification of the point interaction approximation for deriving the effective medium parameters. We make the following assumptions.

Assumption C.1. (i) The function \widetilde{V} defined in Assumption 4.1 belongs to $C_0^2(\Omega)$.

(ii) (4.1) holds for functions $(f,g) \in X$, where $X := \mathcal{C}^{0,\alpha}(\Omega)^3 \times \mathcal{C}^{0,\alpha}(\Omega)^3$ with $0 < \alpha \le 1$.

We define the operator $\mathcal{T}: X \to X$ by

$$\mathcal{T}\begin{pmatrix} u \\ v \end{pmatrix} = \omega \int_{\Omega} G(\cdot - z) \begin{pmatrix} \tilde{\epsilon}_{\text{eff}}(z) & i\omega \tilde{\tilde{\mu}}_{\text{eff}}(z) \\ -i\omega \tilde{\tilde{\epsilon}}_{\text{eff}}(z) & \tilde{\mu}_{\text{eff}}(z) \end{pmatrix} \begin{pmatrix} u(z) \\ v(z) \end{pmatrix} dz. \tag{C.1}$$

Then, the Lippmann-Schwinger equation can be written as

$$(I - \mathcal{T}) \begin{pmatrix} E^h \\ H^h \end{pmatrix} = \begin{pmatrix} E^{in} \\ H^{in} \end{pmatrix}.$$

We assume that the homogenized problem (4.11) is well-posed. More precisely, we make the following assumption.

Assumption C.2. For given material parameters ϵ_{eff} and μ_{eff} with negative real parts and an incident field (E^{in}, H^{in}) , there exists a unique solution to (4.11) such that $(E - E^{in}, H - H^{in})$ satisfies the Silver-Müller radiation condition at infinity.

Lemma 2. The following statements are equivalent:

(i) There exists a unique solution to the differential equation (4.11) such that $(E - E^{in}, H - H^{in})$ satisfies the Silver-Müller radiation condition at infinity:

(ii) There exists a unique solution $(E, H) \in X$ to the Lippmann-Schwinger equation

$$(I - \mathcal{T}) \begin{pmatrix} E \\ H \end{pmatrix} = \begin{pmatrix} E^{in} \\ H^{in} \end{pmatrix},$$

where \mathcal{T} is given by (C.1).

Note that, under Assumptions C.1 (i) and C.2, the operator \mathcal{T} is Fredholm of index zero on the set of functions $(u, v) \in X$ such that [21]

$$\nabla \cdot \left(\left[\begin{pmatrix} \tilde{\epsilon}_{\text{eff}}(z) & i\omega \tilde{\tilde{\mu}}_{\text{eff}}(z) \\ -i\omega \tilde{\tilde{\epsilon}}_{\text{eff}}(z) & \tilde{\mu}_{\text{eff}}(z) \end{pmatrix} + \begin{pmatrix} \frac{1}{1-\omega^2\epsilon_m\mu_m\beta_m^2} & i\omega \frac{\mu_m\beta_m}{1-\omega^2\epsilon_m\mu_m\beta_m^2} \\ -i\omega \frac{\epsilon_m\beta_m}{1-\omega^2\epsilon_m\mu_m\beta_m^2} & \frac{1}{1-\omega^2\epsilon_m\mu_m\beta_m^2} \end{pmatrix} \right] \begin{pmatrix} u(z) \\ v(z) \end{pmatrix} \right) = 0 \quad \text{for } z \in \Omega.$$

Let us introduce a regularized operator \mathcal{T}_{η} of \mathcal{T} by replacing g^k with

$$g_{\eta}^{k}(x,y) = \frac{e^{ik|x-y|}}{4\pi|x-y|+\eta}, \qquad \eta > 0.$$

It is clear that the operator \mathcal{T}_{η} is compact in X. Using Fredholm's theory, we have the following lemma.

Lemma 3. The operator $I - \mathcal{T}_{\eta}$ is invertible with a bounded inverse in X.

Let (E_n^h, H_n^h) be the solution to

$$(I - \mathcal{T}_{\eta}) \begin{pmatrix} E_{\eta}^{h} \\ H_{\eta}^{h} \end{pmatrix} = \begin{pmatrix} E^{in} \\ H^{in} \end{pmatrix}.$$

Next, assume for simplicity that $\tilde{\epsilon}_{\text{eff}}^N, \tilde{\mu}_{\text{eff}}^N, \tilde{\tilde{\epsilon}}_{\text{eff}}^N$, and $\tilde{\tilde{\mu}}_{\text{eff}}^N$ are replaced with their limits as $N \to +\infty$ and consider the regularized form of (4.6), that is,

$$\begin{pmatrix}
E_{\eta}^{N}(x) \\
H_{\eta}^{N}(x)
\end{pmatrix} = \begin{pmatrix}
E^{in}(x) \\
H^{in}(x)
\end{pmatrix} + \frac{1}{N^{3}} \sum_{j=1}^{N^{3}} \omega G_{\eta}(x - z_{j}^{N}) \begin{pmatrix}
\tilde{\epsilon}_{\text{eff}} & i\omega\tilde{\tilde{\mu}}_{\text{eff}} \\
-i\omega\tilde{\tilde{\epsilon}}_{\text{eff}} & \tilde{\mu}_{\text{eff}}
\end{pmatrix} \begin{pmatrix}
E_{\eta}^{N}(z_{j}^{N}) \\
H_{\eta}^{N}(z_{j}^{N})
\end{pmatrix} (C.2)$$

for $x \in \widetilde{\Omega}$. Here, G_{η} is obtained from G by replacing g^k with g_{η}^k , and $(E_{\eta}^N(z_j^N), H_{\eta}^N(z_j^N))$ is obtained by solving the linear system

$$\begin{pmatrix} E_{\eta}^{N}(z_{i}^{N}) \\ H_{\eta}^{N}(z_{i}^{N}) \end{pmatrix} = \begin{pmatrix} E^{in}(z_{i}^{N}) \\ H^{in}(z_{i}^{N}) \end{pmatrix} + \frac{1}{N^{3}} \sum_{j=1, j \neq i}^{N^{3}} \omega G_{\eta}(z_{i}^{N} - z_{j}^{N}) \begin{pmatrix} \tilde{\epsilon}_{\text{eff}} & i\omega\tilde{\tilde{\mu}}_{\text{eff}} \\ -i\omega\tilde{\tilde{\epsilon}}_{\text{eff}} & \tilde{\mu}_{\text{eff}} \end{pmatrix} \begin{pmatrix} E_{\eta}^{N}(z_{j}^{N}) \\ H_{\eta}^{N}(z_{j}^{N}) \end{pmatrix},$$
(C.3)

for $i = 1, ..., N^3$.

To insure the uniform invertibility of (C.3) with respect to N and η (at least for ω small enough), we need some more assumptions regarding $\{z_j^N\}$ in addition to Assumption 4.2. We assume that

$$\frac{1}{N^6} \sum_{i,j=1, i \neq j}^{N^3} \|G(z_i^N - z_l^N)\|^2 \le CN^{-6a},$$

for some positive constant C. Define \tilde{e}_{η}^N and \tilde{h}_{η}^N by $\tilde{e}_{\eta}^N:=E_{\eta}^h-E_{\eta}^N$ and $\tilde{h}_{\eta}^N:=H_{\eta}^h-H_{\eta}^N$. Then, we have

$$\begin{pmatrix} \tilde{e}_{\eta}^{N}(x) \\ \tilde{h}_{\eta}^{N}(x) \end{pmatrix} - \frac{1}{N^{3}} \sum_{j=1}^{N^{3}} \omega G_{\eta}(x-z_{j}^{N}) \begin{pmatrix} \tilde{\epsilon}_{\text{eff}} & i\omega\tilde{\tilde{\mu}}_{\text{eff}} \\ -i\omega\tilde{\tilde{\epsilon}}_{\text{eff}} & \tilde{\mu}_{\text{eff}} \end{pmatrix} \begin{pmatrix} \tilde{e}_{\eta}^{N}(z_{j}^{N}) \\ \tilde{h}_{\eta}^{N}(z_{j}^{N}) \end{pmatrix}$$

$$=\omega\int_{\Omega}G_{\eta}(x-y)\begin{pmatrix}\tilde{\epsilon}_{\mathrm{eff}} & i\omega\tilde{\tilde{\mu}}_{\mathrm{eff}}\\ -i\omega\tilde{\tilde{\epsilon}}_{\mathrm{eff}} & \tilde{\mu}_{\mathrm{eff}}\end{pmatrix}\begin{pmatrix}E_{\eta}^{h}(y)\\ H_{\eta}^{h}(y)\end{pmatrix}dy-\frac{1}{N^{3}}\sum_{j=1}^{N^{3}}\omega G_{\eta}(x-z_{j}^{N})\begin{pmatrix}\tilde{\epsilon}_{\mathrm{eff}} & i\omega\tilde{\tilde{\mu}}_{\mathrm{eff}}\\ -i\omega\tilde{\tilde{\epsilon}}_{\mathrm{eff}} & \tilde{\mu}_{\mathrm{eff}}\end{pmatrix}\begin{pmatrix}E_{\eta}^{h}(z_{j}^{N})\\ H_{\eta}^{h}(z_{j}^{N})\end{pmatrix}$$

Therefore, by the same arguments as those in [4, 14], one can prove that

$$||E_{\eta}^{N} - E_{\eta}^{h}||_{\mathcal{C}^{0,\alpha}(\Omega)^{3}} + ||H_{\eta}^{N} - H_{\eta}^{h}||_{\mathcal{C}^{0,\alpha}(\Omega)^{3}} \to 0 \text{ as } N \to +\infty,$$

uniformly in η . Then, since on one hand, $E_{\eta}^{N} \to E^{N}$ and $H_{\eta}^{N} \to H^{N}$ in $\Omega \setminus \cup (z_{j})_{j=1}^{N^{3}}$ as $\eta \to 0$ and on the other hand, $E_{\eta}^{h} \to E^{h}$ and $H_{\eta}^{h} \to H^{h}$ in Ω as $\eta \to 0$, we obtain the desired justification of the homogenization procedure.

References

- [1] H. Ammari, Y. Deng, and P. Millien, Surface plasmon resonance of nanoparticles and applications in imaging, Arch. Ration. Mech. Anal., 220 (2016), 109–153.
- [2] H. Ammari, B. Fitzpatrick, D. Gontier, H. Lee, and H. Zhang, Minnaert resonances for acoustic waves in bubbly media, arXiv:1603.03982, 2016.
- [3] H. Ammari, B. Fitzpatrick, H. Kang, M. Ruiz, S. Yu, and H. Zhang, Mathematical and Computational Methods in Photonics and Phononics, to appear (SAM Research Report No. 2017-05).
- [4] H. Ammari, B. Fitzpatrick, H. Lee, S. Yu, and H. Zhang, Double-negative acoustic metamaterials, arXiv:1709.08177.
- [5] H. Ammari, K. Hamdache, and J.C. Nédélec, Chirality in the Maxwell equations by the dipole approximation, SIAM J. Appl. Math., 59 (1999), 2045–2059.
- [6] H. Ammari and A. Khelifi, Electromagnetic scattering by small dielectric inhomogeneities, J. Math. Pures Appl., 82 (2003), 749–842.
- [7] H. Ammari, M. Laouadi, and J.C. Nédélec, Low frequency behavior of solutions to electromagnetic scattering problems in chiral media, SIAM J. Appl. Math., 58 (1998), 1022 - 1042.
- [8] H. Ammari, P. Millien, M. Ruiz, and H. Zhang, Mathematical analysis of plasmonic nanoparticles: the scalar case, Arch. Ration. Mech. Anal., 224 (2017), 597–658.

- [9] H. Ammari and J.C. Nédélec, Time-Harmonic Electromagnetic Fields in Chiral Media, Modern mathematical methods in diffraction theory and its applications in engineering (Freudenstadt, 1996), 174–202, Methoden Verfahren Math. Phys., 42, Peter Lang, Frankfurt am Main, 1997.
- [10] H. Ammari and J.C. Nédélec, *Time-harmonic electromagnetic fields in thin chiral curved layers*, SIAM J. Math. Anal., 29 (1998), 395–423.
- [11] H. Ammari, M. Ruiz, S. Yu, and H. Zhang, Mathematical analysis of plasmonic resonances for nanoparticles: the full Maxwell equations, J. Differ. Equa., 261 (2016), no. 6, 3615–3669.
- [12] H. Ammari, M. Ruiz, S. Yu, and H. Zhang, Reconstructing fine details of small objects by using plasmonic spectroscopic data, SIAM J. Imaging Sci., to appear.
- [13] H. Ammari, M.S. Vogelius, and D. Volkov, Asymptotic formulas for perturbations in the electromagnetic fields due to the presence of inhomogeneities of small diameter. II. The full Maxwell equations, J. Math. Pures Appl., 80 (2001), 769–814.
- [14] H. Ammari and H. Zhang, Effective medium theory for acoustic waves in bubbly fluids near Minnaert resonant frequency, SIAM J. Math. Anal., 49 (2017), 3252–3276.
- [15] K. Ando and H. Kang, Analysis of plasmon resonance on smooth domains using spectral properties of the Neumann-Poincaré operator, J. Math. Anal. Appl., 435 (2016), 162–178.
- [16] K. Ando, H. Kang, and H. Liu, Plasmon resonance with finite frequencies: a validation of the quasi-static approximation for diametrically small inclusions, SIAM J. Appl. Math., 76 (2016), 731–749.
- [17] C.E. Athanasiadis, C. Costakis, and I.G. Stratis, *Electromagnetic scattering by a homogeneous chiral obstacle in a chiral environment*, IMA J. Appl. Math., 64 (2000), 245–258.
- [18] C.E. Athanasiadis, S. Dimitroula, E. Kikeri, and K.I. Skourogiannis, Aspects of electromagnetic scattering in chiral media, Math. Methods Appl. Sci., 40 (2017), 2071–2077.
- [19] C. Athanasiadis, P.A. Martin, and I.G. Stratis, Electromagnetic scattering by a homogeneous chiral obstacle: boundary integral equations and low-chirality approximations, SIAM J. Appl. Math., 59 (1999), 1745–1762.
- [20] R.E. Caflisch, M.J. Miksis, G.C. Papanicolaou, and L. Ting, *Effective equations for wave propagation in bubbly liquids*, J. Fluid Mech., 153 (1985), 259-273.
- [21] D. Colton and R. Kress, *Inverse acoustic and electromagnetic scattering theory*. Second edition. Applied Mathematical Sciences, 93. Springer-Verlag, Berlin, 1998.

- [22] R. Figari, G. Papanicolaou and J. Rubinstein, *Remarks on the point interaction approximation*, Hydrodynamic Behavior and Interacting Particle Systems, G. Papanicolaou (ed.), Springer-Verlag New York Inc. 1987.
- [23] L.L. Foldy, The multiple scattering of waves. I. General theory of isotropic scattering by randomly distributed scatterers, Physical Review, 67.3-4 (1945), 107.
- [24] M. Minnaert, On musical air-bubbles and the sounds of running water, The London, Edinburgh, Dublin Philos. Mag. and J. of Sci., 16 (1933), 235–248.
- [25] M. Mitrea, The method of layer potentials for electromagnetic waves in chiral media, Forum Math., 13 (2001), 423–446.
- [26] S. Ozawa, Point interaction potential approximation for $(-\triangle+U)^{-1}$ and eigenvalues of the Laplacian on wildly perturbed domain, Osaka J. Math. 20(1983), 923-937.
- [27] S. Ozawa, On an elaboration of M. Kac's theorem concerning eigenvalues of the Laplacian in a region with randomly distributed small obstacles, Comm. Math. Phys., 91 (1983), 473-487.
- [28] G.C. Papanicolaou, Diffusion in random media, Surveys in Applied Mathematics, volume 1, Edited by J.P. Keller, D. W. McLaughlin and G.C. Papanicolaou, Plenum Press, New York, 1995.
- [29] J.B. Pendry, Negative refraction makes a perfect lens, Phys. Rev. Lett., 85 (2000), 3966–3969.
- [30] J.B. Pendry, A Chiral route to negative refraction, Science, 306 (2004), 1353–1355.
- [31] V.M. Shalaev, Optical negative-index metamaterials, Nature Photonics, 1 (2007), 41–48.
- [32] D.R. Smith, J.B. Pendry, and M.C.K. Whiltshire, Metamaterials and negative refractive index, Science, 305 (2004), 788–792.
- [33] C.M. Soukoulis and M. Wegener, Past achievements and future challenges in the development of three-dimensional photonic materials, Nature Photonics, 5 (2011), 523–530.
- [34] V.G. Veselago, The electrodynamics of substances with simultaneously negative values of ϵ and μ . Sov. Phys. Usp., 10 (1968), 509–514.
- [35] V.G. Veselago and E.E. Narimanov, The left hand of brightness: past, present and future of negative index materials, Nature Materials, 5 (2006), 759–762.
- [36] S. Zhang, Y.-S. park, J. Li, X. Lu, W. Zhang, and X. Zhang, Negative refractive index in chiral metamaterials, Phys. Rev. Lett., 102 (2009), 023901.
- [37] J. Zhou, J. Dong, B. Wang, T. Koschny, M. Kafesaki, and C.M. Soukoulis, *Negative refractive index due to chirality*, Phys. Rev. B, 79 (2009), 121104(R).