Light Sources with Bias Tunable Spectrum based on van der Waals Interface Transistors

Hugo Henck,^{1,2} Diego Mauro,^{1,2} Daniil Domaretskiy,^{1,2} Marc Philippi,^{1,2} Shahriar Memaran,^{3,4}

Wenkai Zheng,^{3,4} Zhengguang Lu,^{3,4} Dmitry Shcherbakov,⁵ Chun Ning Lau,⁵

Dmitry Smirnov,^{3,4} Luis Balicas,^{3,4} Kenji Watanabe,⁶ Takashi Taniguchi,⁷ Vladimir I. Fal'ko,^{8,9} Ignacio Gutiérrez-Lezama,^{1,2} Nicolas Ubrig,^{1,2,*} and Alberto F. Morpurgo^{1,2,†}

¹Department of Quantum Matter Physics, University of Geneva, 24 Quai Ernest Ansermet, CH-1211 Geneva, Switzerland

²Department of Applied Physics, University of Geneva, 24 Quai Ernest Ansermet, CH-1211 Geneva, Switzerland

³National High Magnetic Field Laboratory, Tallahassee, FL 32310, USA

⁴Department of Physics, Florida State University, Tallahassee, FL 32306-4350, USA

⁵Department of Physics, The Ohio State University, Columbus, OH 43210

⁶Research Center for Functional Materials, National Institute for Materials Science, 1-1 Namiki, Tsukuba 305-0044, Japan

⁷International Center for Materials Nanoarchitectonics, National

Institute for Materials Science, 1-1 Namiki, Tsukuba 305-0044, Japan

⁸National Graphene Institute, University of Manchester, Booth St E, M13 9PL, Manchester, UK

⁹Henry Royce Institute for Advanced Materials, M13 9PL, Manchester, UK

(Dated: July 11, 2022)

ABSTRACT

Light-emitting electronic devices are ubiquitous in key areas of current technology, such as data communications, solid-state lighting, displays, and optical interconnects. Controlling the spectrum of the emitted light electrically, by simply acting on the device bias conditions, is an important goal with potential technological repercussions. However, identifying a material platform enabling broad electrical tuning of the spectrum of electroluminescent devices remains challenging. Here, we propose light-emitting field-effect transistors based on van der Waals interfaces of atomically thin semiconductors as a promising class of devices to achieve this goal. We demonstrate that large spectral changes in room-temperature electroluminescence can be controlled both at the device assembly stage -by suitably selecting the material forming the interfaces- and on-chip, by changing the bias to modify the device operation point. Even though the precise relation between device bias and kinetics of the radiative transitions remains to be understood, our experiments show that the physical mechanism responsible for light emission is robust, making these devices compatible with simple large areas device production methods.

INTRODUCTION

Since the discovery that monolayer semiconducting transition metal dichalcogenides (TMDs) are direct gap semiconductors exhibiting strong luminescence,^{1,2}

two-dimensional (2D) materials have attracted interest for optoelectronic applications.^{3–6} Their potential stems from the ease with which the electronic properties of 2D semiconductors can be tuned by different means.^{7–11} In phosporene, for instance, mechanical strain can be used to tune the band gap by a very large amount, resulting in a controllable change of the wavelength of emitted light, as observed in recent photoluminescence measurements.¹² In semiconducting TMDs, electrostatic gating gives access to a variety of excitonic states with different energy,^{13,14} an effect that has been used to realize bias tunable electroluminescent devices with emission energy that has been varied by several tens of meV.^{9,11} Realizing electroluminescent devices enabling much broader changes in the spectrum of the emitted light by simply acting on the device operation point (*i.e.*, on the device bias) has however not been possible so far.

Light-emitting field-effect transistors (LEFETs) are three-terminal devices that allow switching of both the electrical conductance and light emission.^{15–19} They rely on semiconductors that support ambipolar transport to inject simultaneously in the transistor channel electrons and holes,²⁰ whose radiative recombination is the origin of the emitted light.^{21,22} Past research on LEFETs has concentrated on organic semiconductors, which have suitable properties for their realization.^{18,19,23–25} Ionic gated LEFETs based on 2D semiconductors are a recently discovered alternative that offer potential advantages, such as higher and well-balanced electron and hole mobilities, as well as low-bias operation.^{26–30} Efficient LEFETs, however, require the use of 2D semiconductors with a direct bandgap, whose paucity limits the possibility to tune the spectrum of the emitted light. Van der Waals (vdW) interfaces formed by atomically thin semiconducting materials provide a strategy to address this issue because the wavelength of

^{*} nicolas.ubrig@unige.ch

[†] alberto.morpurgo@unige.ch



Figure 1. LEFETs based on van der Waals interfaces. a. Schematics of an ionic gated field-effect transistor, with the source-drain (S-D) contacts connected to a semiconducting layer and the gate electrode, all in contact with an ionic liquid. The zoom in on the channel regions shows that upon the application of a gate voltage charge is accumulated on the semiconductor (see Supplementary Section S2 for details). b and c. Electron-hole recombination in the channel of an ionic liquid (IL) based LEFET operated in the ambipolar injection regime (with electrons and holes injected at opposite contacts) for a device based on a individual 2D material (b) and on a vdW interface (c). In the latter case, light is emitted by the recombination of electrons and holes hosted in different layers, which offers new opportunity to control its spectrum (see main text; here we use interfaces of bilayer TMDs, hosting holes, and InSe multilayers, hosting electrons). d. The type-II band alignment between InSe and TMDs around the Γ -point enables k-direct interlayer radiative transitions between the two band edges (as indicated by the orange arrow and labelled IX). Higher energy bands originating from the quantum confinement of charge carriers in the two layers (as indicated by the thin lines) can lead to radiative transitions with different energy. e. Optical micrograph of a device used in this work, based on 2L WS₂ and 4L InSe (the contours of the layers are marked by the blue and white lines; the stacking sequence is indicated on top). The vdW interface is in contact with the liquid through an opening in the PMMA layer covering the entire sample. The scale bar is 2 μ m. f. Peak in the PL spectrum of a 5L InSe crystal encapsulated between two thicker hBN layers: the narrow width indicates the high quality of the material.

light emitted by interlayer transitions (electrons hosted in one layer recombining with holes hosted in the other) can be engineered by selecting constituent materials with an appropriate band alignment.^{31–35}

Here, we demonstrate experimentally LEFETs realized on vdW interfaces, and show that they can be operated as electrically tunable light sources. As compared to LEFETs based on individual monolayers, devices fabricated on vdW interfaces potentially offer more functionality. The electronic structure of the individual layers, for instance, is often only minorly affected by the interface formation, so that a rich set of electronic levels -i.e., the bands of the two materials, including the sub-bands originating from quantum confinement- is present.³⁶⁻⁴⁰ If properly populated by acting on the device operation point (*i.e.*, the applied source-drain and gate voltages, V_{SD} and V_G , respectively), these levels may enable the energy of the emitted light to be tuned. Additionally, the electric field perpendicular to the transistor channel creates a potential difference between the layers forming the interface, which shifts the energy of the recombining electrons and holes.^{41,42} The wavelength of light generated by interlayer transitions is expected to shift accordingly, providing another route to tune the emission spectrum by acting on the device operation point. These ideas disclose possible mechanisms to operate LEFETs based on vdW interfaces as electrically tunable light sources. However, neither their validity nor the potential of LEFETs based on vdW interfaces has been assessed so far.

Here, we show that light-emitting transistors based on a recently discovered type of van der Waals (vdW) heterostructures –which we refer to as Γ - Γ interfaces (see discussion below)- exhibit room-temperature electroluminescence that can be tuned over a much broader spectral range (from below 1.2 to 1.7 eV, in the devices reported here) by acting exclusively on the device operation point. Our work relies on devices made of bilayers (2L) of semiconducting transition metal dichalcogenides (TMDs; we use WS_2 and MoS_2) and InSe multilayers, to form vdW interfaces that belong to a recently identified class exhibiting robust radiative interlayer transitions (e.g., transitions that are radiative irrespective of the lattice structure of the constituent materials or of their relative orientation).^{38,43,44} The robustness originates from having the conduction and valence band extrema in the two layers at k = 0, *i.e.*, at the Γ -point of the Brillouin zone (which is why we refer to these systems as to Γ - Γ interfaces. It is important because it facilitates the device assembly, and makes it compatible with simple large-area production techniques. 9,45 Indeed, we find that all our LEFETs exhibit electroluminescence, with a wavelength that can be engineered by selecting the constituent layers, and with a spectrum that can be tuned by acting on the device operation point. Contrary to earlier studies of Γ - Γ interfaces⁴⁴ –in which photoluminescence (PL) was only observed at cryogenic temperatures- electroluminescence (EL) is already present at room temperature, a key finding when assessing the technological potential of these devices.



Figure 2. Transistor characteristics of a 2L WS₂/4L InSe device. a. Room-temperature transfer curve (I_{SD} -vs- V_G at fixed $V_{SD} = 50$ mV) of a 2L-WS₂/4L-Inse. b. The high device quality is evidenced by the low subthreshold swings for electron and hole transport, whose values (115 mV/decade and 90 mV/decade, respectively, for this specific transistor) are close to the ultimate limit of 60 mV/decade. c and d. Output characteristics (I_{SD} as function of V_{SD}) of the same device for different negative and positive gate biases, respectively. Linear, saturation, and ambipolar injection regimes can be clearly identified upon increasing the magnitude of V_{SD} , as described in the main text (see also Supplementary Section S2).

RESULTS

Device fabrication and characterization

Ionic gated LEFETs (see Figure 1a-c and Supplementary Section 1) based on 2L-TMD/InSe vdW interfaces (see Figure 1d) are realized using techniques commonly employed for the assembly of structures based on 2D materials.⁴⁶ TMD bilayers and InSe multilayers are exfoliated from bulk crystals onto Si/SiO₂ substrates. Heterostructures are formed by picking up layers one after the other, and transferring the resulting interface onto a fresh Si/SiO₂ substrate, with the TMD layer covering the InSe one and effectively encapsulating it (which is important in view of the non-perfect stability of InSe in ambient; the interface assembly process is carried out in the controlled atmosphere of a glove box). Source and drain contacts, as well as a large pad acting as gate electrode, are defined by means of electron beam lithography, electron-beam evaporation of a Pt-Au film (5/30 nm) and lift off (see Figure 1e). Subsequently, a window in PMMA is patterned to define the region

where the ionic liquid ((N,N-diethyl-N-methyl-N-(2-methoxyethyl) ammonium bis(trifluoromethylsulfonyl) imide) commonly referred to as DEME-TFSI) contacts the interface. The liquid is applied as a final step, prior to inserting the devices in a vacuum chamber with optical access (see Methods section for more details).

The WS_2 and MoS_2 crystals used for exfoliation are purchased from HQ Graphene. InSe is a less commonly employed compound and care is needed because the crystal quality varies strongly depending on details of the growth process. Lower quality can result in a large density of defects^{47–49} that create in-gap states acting as hole traps, which is why our earlier attempts to use InSe crystals to realize vdW interface LEFETs failed (in-gap states prevent the electrostatic accumulation of holes in the valence band of the TMD, and impede ambipolar transport). The InSe crystals that we employ here, grown at Florida State University (see Methods Section for details of the growth process), appear to have high quality and a low density of defects, as we directly infer from the transistor electrical characteristics and from the narrow lines observed in PL studies of h-BN-encapsulated multilayers (see Figure 1f).

Figure 2a shows the room-temperature transfer curve (source-drain current I_{SD} versus gate voltage V_G at fixed source-drain voltage $V_{SD} = 50 \text{ mV}$) of a device realized on a 2L-WS₂/4L-InSe interface. The behavior is typical of ambipolar transistors with current mediated by holes and electrons flowing for sufficiently large negative and positive V_G , respectively.^{24,26,50–55} Accumulation of electrons and holes leads to comparable current levels, confirming that transport is well-balanced and that residual defects in InSe do not prevent high-quality device operation. When plotted in logarithmic scale (Figure 2b) the data allow determining the subthreshold swing $S = \ln 10 \frac{dV_G}{d(\ln I_{SD})}$, equal to S = 115 and 90 mV/decade near the threshold for hole and electron conduction, respectively (other devices exhibit values even closer to the ultimate room-temperature limit of 60 mV/decade).⁵⁶ The output curves $(I_{SD}$ -vs- V_{SD} plotted for different, fixed V_G) shown in Figure 2c and 2d also exhibit the expected behavior. Upon increasing V_{SD} , I_{SD} increases linearly at first then saturates, and eventually exhibits a very steep increase, when entering the ambipolar injection regime. This regime -in which electrons and holes are injected at opposite contacts- is the one of interest for LEFET operation (see Supplementary Section 1), and can be reached irrespective of the polarity of the applied gate voltage.

Electroluminescence from vdW interface LEFET

EL is expected to occur concomitantly with ambipolar injection, with light emission starting at one



Figure 3. Electroluminescence from a Γ - Γ interface. a. Images of the channel of a transistor based on a 2L-WS₂/4L-InSe heterostructure taken with an optical microscope (top) and with the camera of our spectrometer (bottom). The bottom image, taken with the device biased at the onset of the ambipolar injection regime, shows a bright spot due to EL. The scale bars are 1 μ m. b. Device output curve measured at, $V_G = +0.5$ V (electron accumulation). c. False-color plot of the EL intensity measured by the spectrometer, as a function of photon energy and applied V_{SD} , showing a peak centered around 1.25 eV that emerges at $V_{SD} = +1.9$ V, corresponding to the onset of ambipolar injection (see b). d. Individual EL spectra at selected V_{SD} values extracted from c: in this bias range the spectrum remains unchanged, and the intensity increases following the increase in source-drain current. e-g. Data analogous to those of panels b-d are shown for $V_G = -2.2$ V (hole accumulation), demonstrating that the presence of EL is robust and that at sufficiently low bias the spectrum is virtually identical for electron and hole accumulation. h. The peak in the EL spectrum (acquired with $V_{SD} = +2.2$ V and $V_G = +0.5$ V) is red-shifted relative to the PL emission energies of the layers forming the interface (purple: 4L Inse; blue: 2L WS₂; for InSe, PL data are taken at 5 K, because no PL is observed at room temperature), as expected from an interlayer Γ - Γ transition (see i). j. Comparison between the normalized EL (thick red line) and PL (thin red line) emission spectra of the interface. The energy difference originates from having to measure PL at cryogenic temperatures (T = 5 K), since no PL is observed at room temperature.

of the contacts and shifting into the channel as V_{SD} is further increased.¹⁸ This is indeed what we observe (see Figure 3a as well as Supplementary Figure 2 and accompanying discussion in Supplementary Section 1). The light emitted by the LEFET is collected by a microscope objective and fed into a spectrometer. The spectral analysis performed on data measured at fixed V_G , by increasing V_{SD} past the onset of the ambipolar injection regime ($V_{SD} > +1.9$ V in Figure 3b for $V_G > 0$ and $V_{SD} < -2.2$ V in Figure 3e for $V_G < 0$ V), is shown in Figures 3c and 3d for $V_G > 0$ V, and in Figures 3f and 3g for $V_G < 0$ V. As the current increases exponentially rapidly, we initially limit the maximum applied V_{SD} to avoid damaging the devices. EL is detected in all cases, with an intensity that increases rapidly with V_{SD} . The light exhibits a dominant spectral line just above 1.2 eV, irrespective of the precise value of V_{SD} and of whether V_G has positive or negative polarity (an additional shoulder at 1.4 eV is visible for $V_G < 0$, see Figure 3g, is also present –albeit less pronounced– for $V_G > 0$).

In Figure 3h, we plot the device EL spectrum (red line; $V_G = +0.5$ V and $V_{SD} = +2.2$ V) together with the PL spectrum of 4L-InSe (purple line; PL is measured at T = 5 K, since no signal is observed at room temperature) and 2L-WS₂ (blue line). The

5



Figure 4. **LEFET based on a MoS**₂/InSe interface. a and b. Transfer and output characteristics of a 2L-MoS₂/5L-InSe transistor. c. EL spectra of the device biased near the onset of ambipolar injection, for electron and hole accumulation (the grey and blue curves are measured respectively at $V_G = -0.7$ V and $V_{SD} = +2.1$ V, and at $V_G = -2.7$ V and $V_{SD} = -2.3$ V), showing a peak around 1.3 eV independently of the applied gate voltage. d. Dependence of EL intensity on photon energy and V_{SD} , measured at $V_G = -0.7$ V, showing that near the onset of ambipolar transport the spectrum is independent of V_{SD} . e. Also in this case, the EL spectrum (thick orange line) is red-shifted as compared to the PL emission energy of the layers forming the interface (purple: 4L InSe; green: 2L MoS₂), as expected for an interlayer transition. f. EL spectrum of LEFETs realized using four different interfaces, based on two different 2L TMDs (blue: MoS₂; red: WS₂) and three different thicknesses of the InSe layer (3L, 4L, and 5L, as indicated in the figure), showing a dense coverage of part of the visible spectrum (a broader range of photon energy can be spanned using other semiconducting TMD compounds).

energy of the EL peak is considerably lower than the recombination energy in either 4L-InSe or 2L-WS₂, as expected for an interlayer transition.⁴⁴ The energy of the room-temperature EL signal (Figure 3j, thick line) matches that of low-temperature interlayer transitions seen in PL (Figure 3j, thin line) due to electrons in InSe recombining with holes in WS₂, if we take into account that the TMD and the InSe gap typically increases by approximatively 50-100 meV upon cooling from 300 to 5 K.^{14,57–59} The measurements, therefore, confirm that our LEFET operates as anticipated, with electrons injected in the InSe layer and holes in the WS₂ one recombining via an interlayer transition. Finding that this transition results in EL even at room temperature is a positive, unexpected surprise.

Devices based on other Γ - Γ vdW interfaces should exhibit all key properties of 2L-WS₂/4L-InSe LEFETs. We verify that this is indeed the case using transistors realized on interfaces of $2L-MoS_2$ (instead of $2L-WS_2$), and 3L-, 4L-, and 5L-InSe. Without going through all details (see Supplementary Section 2), the data show the occurrence of ambipolar transport (Figure 4a) and of the ambipolar injection regime past saturation Upon entering the ambipolar injection (Figure 4b). regime, EL is observed resulting in a line at 1.3 eV (for 2L-MoS₂/5L-InSe) independently of V_{SD} (see Figure 4c and 4d), *i.e.*, an energy lower than that of the transitions in the constituent materials (see Figure 4e). Figure 4f overviews the results obtained, by plotting together the room-temperature EL spectrum of LEFETs fabricated

on all different vdW interfaces, and shows that combining different 2D materials indeed allows a dense coverage of part of the near-infrared and visible spectral range. Selecting multilayers of different thicknesses or having different compositions (*e.g.*, MoSe₂ or MoTe₂) would further broaden the accessible spectrum, both on the higher and lower end.^{38,43,44}

Electrically tunable EL spectrum in vdW interface LEFET

Having established that LEFETs based on Γ - Γ interfaces provide a robust platform to generate roomtemperature EL, we test whether the light spectrum can be controlled by varying the device operation point. Figure 5 illustrates the evolution of the spectrum of the light emitted by a $2L-WS_2/4L-InSe$ (Figure 5a-c) and by a $2L-MoS_2/5L-InSe$ (Figure 5d-f) LEFETs, upon pushing the source-drain bias V_{SD} to reach deeper in the ambipolar transport regime. The green rectangle in Figure 5a delimits the V_{SD} interval discussed earlier, and the corresponding part of the spectrum in Figure 5c (also delimited by a green rectangle) shows emission from the interlayer transition just above 1.2 eV, in agreement with the data shown in Figure 3b and 3c. When larger V_{SD} is applied, corresponding to the interval in the rectangle delimited by the red line in Figure 5a, the spectrum evolves. Additional transitions appear, visible in Figure 5b in the region delimited by the red rectangle,



Figure 5. Bias tunable light emission from vdW interface LEFETs. a. Output characteristics of the $2L-WS_2/4L$ -In Se device, whose data are shown in Figure 3 ($V_G = +0.2$ V). The colored dashed lines delimit the low-bias (green line) and high-bias (red line) regime, which exhibit different EL spectral properties. b. Color plot of the EL spectrum as a function of photon energy and V_{SD} . In the low-bias regime (region inside the green rectangle) EL exhibit a single peak, due to a Γ - Γ interlayer transition from the bottom of the InSe conduction band to the top of the WS_2 valence band (see Figure 3). In this regime the spectrum is independent of bias. In the highbias regime (region inside the red rectangle), the EL spectrum evolves upon increasing V_{SD} , showing that the LEFET acts a light source with bias-tunable spectrum. c. Individual EL emission spectra measured in the high-bias regime, upon varying V_{SD} from 2.3 to 2.5 V. d-f. Same measurements as those shown in panels d-f performed on a LEFET realized on a 2L-MoS₂/5L-InSe device (data taken at $V_G = -0.7$ V). The data illustrate that the evolution of the EL spectrum observed in this $MoS_2/InSe$ LEFET is fully analogous that observed in the $WS_2/InSe$ LEFET, showing the robustness of the device operation.

as well as in Figure 5c, which shows the spectrum of the emitted light at specific values of V_{SD} . A qualitatively identical behavior is observed in LEFETs based on 2L-MoS₂/5L-InSe, with the regime of lower and higher V_{SD} highlighted by red and green rectangles in Figure 5d and the corresponding spectra shown in Figure 5e and 5f.

We have also measured the spectrum of the emitted light at a fixed V_{SD} value, as a function of V_G , and found that in that case as well, the spectrum depends strongly on the device operation point. Figures 6a-d show the spectrum of the light emitted by a device realized on a 2L-WS₂/4L-InSe interface, as a function of gate voltage, for two different values of source-drain bias $(V_{SD} = +2.4 \text{ V} \text{ a-b} \text{ and } V_{SD} = +3.12 \text{ V} \text{ c-d})$. Changing the gate voltage at fixed V_{SD} allows switching the spectrum of the light between two transitions visible in Figures 6b,c. In particular, at large positive gate voltage $(V_G > +0.4 \text{ V in Figure 6a and } V_G > +0.8 \text{ V in Fig-}$ ure 6c), the spectrum of the emitted light is dominated by the interlayer transition at 1.2 eV between the bottom of the InSe conduction band and the top of the TMD valence band. At low gate voltage ($V_G < +0.2$ V in Figure 6a and $V_G < +0.6$ V in Figure 6c), instead, light is emitted by another transition (possibly by multiple transitions, as suggested by the broad linewidth) at higher energy (approximately 1.4 eV), which appears to blue shift upon increasing V_G . Unexpectedly, the two regimes are separated by an interval of gate voltages in which the power of emitted light vanishes (or is below the sensitivity of our detector). Finding that the gate allows switching the spectrum between two different emission lines is interesting, as it may provide new functionality to these LEFETs devices.

As part of our experiments, we have also determined the external quantum efficiency of our devices –i.e., the ratio between the number of emitted photons detected in our set-up and the number of injected electrons- by comparing the measured EL signal to the signal measured (with the same set-up) when using a commercial light-emitting diode as source. We found that, in the experimental configuration employed to detect EL, the external quantum efficiency of our devices is approximately 0.005 %, three orders of magnitude smaller than that of commercial devices. It should be realized, however, that in our set-up the external quantum efficiency is much lower than the actual quantum efficiency, because the optical selection rules for interlayer $transitions^{37,60}$ dictate that light is mostly emitted in the plane of the interface. This implies that the majority of the photons emitted by our light-emitting transistors are not collected by the microscope objective, and that adopting strategies to improve the light outcoupling should lead to a drastic enhancement of the measured external quantum efficiency.

Irrespective of these considerations about the external quantum efficiency, our observation that the EL spectrum does depend on the device operation point proves that LEFETs based on vdW interfaces are indeed electrically tunable light sources. Understanding in detail how the EL spectrum depends on the LEFET operation point is however complex, both because different processes likely play a role, and because screening due to charges accumulated in the transistor channel can strongly (and non-linearly) affect the potential difference between the two layers forming the interface, especially in the region of the transistor channel where



Figure 6. Gate-tuning of the spectrum of the light emitted from a 2L-WS₂/4L-InSe LEFET device. a. Color plot of the intensity of the light emitted by a 2L-WS₂/4L-InSe LEFET device as function of photon energy and gate voltage (V_{SD} is fixed to +2.4 V). The data show that varying V_G allows the frequency of the emitted light to be tuned: for $V_G > 0.4$ V, the spectrum is peaked at 1.25 eV, *i.e.*, the characteristic energy of the interlayer transition between the bottom of the InSe conduction band and the top of the WS₂ valence band; for $V_G < 0.2$ V a broader peak centered around 1.4 eV and shifting with varying V_G is observed. b. Individual horizontal cuts of the color plot shown in a, for V_G varying from -0.1 V to +0.7 V in 0.1 V steps. c and d. Same measurements as in a and b with V_{SD} fixed at +3.12 V. The individual spectral cuts range from $V_G = +0.2$ V to +1.1 V in 0.1 V steps.

electron-hole recombination occurs. At sufficiently large V_{SD} , we expect that electrons are injected not only in the conduction band of InSe but also in that of the TMD, so that light can be emitted also from intralaver transitions within the TMD. This may account for the peak centered around 1.6 eV in $2L-WS_2/4L-InSe$, which corresponds well to one of the 2L-WS₂ PL peaks. An intralayer transition in the semiconducting TMD is likely also responsible for part of the broad peak around 1.5 eV in the MoS_2 -based interfaces (the energy matches one of the peaks observed in PL of $2L-MoS_2$). The less pronounced peaks near 1.4 eV (at comparable but different energies in the 2L-WS₂ and the 2L-MoS₂ devices; see Figure 5b and 5e) occur at an energy that changes slightly upon changing V_{SD} . As the energy of these peaks is lower than all known intralaver transitions in the respective systems, we attribute their origin to an interlayer transition between an electron in a higher energy InSe sub-band recombining with a hole in the TMD (whose precise energy is affected by the electrostatic potential difference between the layers). This attribution is also consistent with data taken at fixed V_{SD} upon varying V_G (see Figure 6), in which the transition energy is seen to blue shift upon changing the gate voltage.

More work is clearly needed to understand in detail the electroluminescence spectrum of Γ - Γ interfaces at large biases, as well as its evolution with both source-drain and gate biases (as mentioned earlier, screening plays a major and complex role in the way spectral features shift as function of biases, and a quantitative description will require a separate, dedicated modeling effort). We note, however, that the spectrum of light emitted by LEFETs based on monolayer TMDs remains unchanged even under driving the device with very large source-drain

biases, as discussed in Supplementary Section 3 and shown in Figure S4 in there. The data, therefore, appear to substantiate our initial idea –namely that LEFETs based on vdW interfaces offer more functionalities than similar devices realized from individual monolayers– irrespective of the precise microscopic origin of the emitted light (i.e., of the specific transitions involved in the light emission process).

DISCUSSION

The results presented above demonstrate the operation of vdW interface LEFETs and show that these transistors do allow the realization of light sources with a bias tunable spectrum. Finding that devices realized with multiple semiconducting TMDs and with InSe layers of different thickness lead to a qualitatively similar evolution of the spectrum of the emitted light with bias indicates that the operation mechanism is robust and of general validity. This robustness is important because –whereas only a few examples of electroluminescent devices with an electrically controllable spectrum have been reported in the past^{61–64}– a large variety of 2D semiconductors exists that can be employed to realize light-emitting Γ - Γ interfaces.

It is clear that at this stage light-emitting transistors based on Γ - Γ vdW interfaces remain proof-of-principle devices and that considerable research is needed to characterize them and optimize their operation. We anticipate, for instance, that ionic liquid gating can be replaced by conventional solid-state gates using nm-thick h-BN dielectrics to separate the gate electrode from the vdW heterostructure. Indeed, h-BN layers that are a few nanometers thick exhibit breakdown field values approaching 1 V/nm,⁶⁵ which are likely sufficient to achieve ambipolar transport and to operate the devices with V_{SD} larger than V_G . Similarly –as already mentioned- the external quantum efficiency of our devices will need to be improved by adopting suitable strategies to optimize light outcoupling. While it is clear that at this stage different aspects of the device require improvements, it is worth re-iterating that Γ - Γ interfaces used within a light-emitting transistor configuration represent a platform that offers a very high potential for the realization of electroluminescent devices with bias tunable spectrum, and that satisfies many key requirements essential to the development of a successful technology. These include room-temperature operation and insensitivity of the devices to details of their assembly process, which ensures their robust operation. It is for these reasons that exploring the development of light-emitting transistors based on Γ - Γ interfaces appears to be promising for future device applications.

METHODS

Crystal growth

InSe single crystals were grown through the Bridgman method: 6N-pure indium and 5N-pure selenium pellets in an atomic ratio of 52:48 were sealed in an evacuated quartz ampule and subsequently placed into a radio frequency (RF) furnace where the RF power was gradually increased to raise the temperature up to 800° C. The ampule was then pulled through the hottest zone at a rate of 2 mm/hour. Single crystals were characterized via electron dispersive spectroscopy and aberration-corrected transmission electron microscopy. X-ray diffraction measurements confirmed that γ -InSe adopts the R3m space group (160) with unit cell dimensions a = 4.08(2) Å and c = 24.938(24) Å. The quality of the crystals grown in this way is illustrated by the different measurements presented in the main text, including the narrow photoluminescence spectrum measured on exfoliated multilayers encapsulated in between hBN crystals, and the ambipolar transport properties of InSe/TMD heterostructures.

Sample fabrication

The fabrication of the heterostructures used to perform the measurements discussed in the main text relies on conventional techniques that are commonly employed to manipulate atomically thin crystals⁴⁶ and is briefly outlined here for completeness. Atomically thin layers of TMDs and InSe are obtained by mechanical exfoliation of bulk crystals in a nitrogen gas-filled glove box with a < 0.5 ppm concentration of oxygen and water. The exfoliated crystals are transferred onto Si/SiO₂ substrates and suitable layers are identified by looking at their optical contrast under an optical microscope. The heterostructures are then assembled in the same glove box with by-now conventional pick-up and release techniques based on either PPC/PDMS (Poly(propylene carbonate) /polydimethylsiloxane) or PC/PDMS (polycarbonate) polymer stacks placed on glass slides.⁴⁶ To avoid degradation of air-sensitive InSe crystals, the structures are assembled so that the InSe layer lays on a thick hBN layer (≈ 20 nm) and is covered by the TMD layer (thereby ensuring that the InSe layer is properly encapsulated in between air-stable materials). Metallic electrodes (Pt/Au) are attached to the TMD layer by conventional nanofabrication techniques using electronbeam lithography, electron-beam evaporation, and liftoff. The sample is wire-bonded with indium or gold wires to a chip carrier and a small amount of ionic liquid ((N,N-diethyl-N-methyl-N-(2-methoxyethyl) ammonium bis(trifluoromethylsulfonyl) imide) commonly referred to as DEME-TFSI) is dropcasted onto the surface of the substrate to cover the metallic gate electrode and the transistor channel. The device is then rapidly transferred into the vacuum chamber with optical access and pumped overnight to remove moisture from the ionic liquid prior to the optical and electrical investigations.

Optical measurements

The sample is mounted in a vacuum chamber positioned under an optical microscope, providing optical and electrical access to the sample. The photoluminescence and electroluminescence of our light-emitting field-effect transistors are collected with help of a microscope objective and sent to a Czerny-Turner monochromator with a grating of 150 grooves/mm (Andor Shamrock 500i). The signal is detected with a Silicon Charge Coupled Device (CCD) array (Andor Newton 970 EMCCD). For photoluminescence measurements, the sample is illuminated with a laser beam generated by a supercontinuum white light laser source combined with a contrast filter, allowing to set the illumination wavelength to 610 nm. The laser power is kept at 50 μ W, to avoid damaging the structures.

Transport measurements

The electrical characterization of our FET is performed in the same chamber used for optical measurements. The gate bias voltage is applied using either a Keithley 2400 source unit or a homemade low-noise voltage source. The current and voltage signals are amplified with homemade low-noise amplifiers, and the amplified signals are recorded with an Agilent 34410A digital multimeter unit.

The data supporting the findings of this study are available free of charges from the Yareta repository of the University of Geneva. https://doi.org/10.26037/yareta:mze42hgmc5cqtdsqmeszkprfxm

- Splendiani, A. et al. Emerging Photoluminescence in Monolayer MoS2. Nano Letters 10, 1271-1275 (2010). URL http://dx.doi.org/10.1021/n1903868w.
- [2] Mak, K. F., Lee, C., Hone, J., Shan, J. & Heinz, T. F. Atomically Thin MoS_{2}: A New Direct-Gap Semiconductor. *Physical Review Letters* 105, 136805 (2010). URL http://link.aps.org/doi/10. 1103/PhysRevLett.105.136805.
- Mak, K. F. & Shan, J. Photonics and optoelectronics of 2D semiconductor transition metal dichalcogenides. *Nature Photonics* 10, 216-226 (2016). URL https: //www.nature.com/articles/nphoton.2015.282. Number: 4 Publisher: Nature Publishing Group.
- [4] Avouris, P., Heinz, T. F. & Low, T. (eds.) 2D Materials: Properties and Devices (Cambridge University Press, Cambridge, 2017). URL https: //www.cambridge.org/core/books/2d-materials/ A87B3521C3A8A5885319F58E6F387830.
- [5] Mueller, T. & Malic, E. Exciton physics and device application of two-dimensional transition metal dichalcogenide semiconductors. *npj 2D Materials and Applications* 2, 1-12 (2018). URL https://www.nature.com/ articles/s41699-018-0074-2.
- [6] Shree, S., Paradisanos, I., Marie, X., Robert, C. & Urbaszek, B. Guide to optical spectroscopy of layered semiconductors. *Nature Reviews Physics* 3, 39– 54 (2021). URL https://www.nature.com/articles/ s42254-020-00259-1.
- [7] He, K., Poole, C., Mak, K. F. & Shan, J. Experimental Demonstration of Continuous Electronic Structure Tuning via Strain in Atomically Thin MoS2. *Nano Letters* 13, 2931–2936 (2013). URL https://doi.org/10.1021/ nl4013166. Publisher: American Chemical Society.
- [8] Island, J. O. et al. Precise and reversible band gap tuning in single-layer MoSe2 by uniaxial strain. Nanoscale
 8, 2589-2593 (2016). URL https://pubs.rsc.org/en/ content/articlelanding/2016/nr/c5nr08219f. Publisher: The Royal Society of Chemistry.
- [9] Withers, F. et al. Heterostructures Produced from Nanosheet-Based Inks. Nano Letters 14, 3987–3992 (2014). URL https://doi.org/10.1021/nl501355j.
- [10] Withers, F. et al. Light-emitting diodes by bandstructure engineering in van der Waals heterostructures. Nature Materials 14, 301-306 (2015). URL http://www. nature.com/articles/nmat4205.
- [11] Paur, M. et al. Electroluminescence from multiparticle exciton complexes in transition metal dichalcogenide semiconductors. Nature Communications 10, 1709 (2019). URL https://www.nature.com/articles/ s41467-019-09781-y/. Number: 1 Publisher: Nature Publishing Group.

- [12] Kim, H. et al. Actively variable-spectrum optoelectronics with black phosphorus. Nature 596, 232– 237 (2021). URL https://www.nature.com/articles/ s41586-021-03701-1.
- [13] Mak, K. F. et al. Tightly bound trions in monolayer MoS2. Nature Materials 12, 207-211 (2013). URL http://www.nature.com/nmat/journal/ v12/n3/abs/nmat3505.html.
- [14] Ross, J. S. et al. Electrical control of neutral and charged excitons in a monolayer semiconductor. Nature Communications 4, 1474 (2013). URL https://www.nature. com/articles/ncomms2498.
- [15] Feng, M., Holonyak, N. & Hafez, W. Light-emitting transistor: Light emission from InGaP/GaAs heterojunction bipolar transistors. *Applied Physics Letters* 84, 151– 153 (2004). URL https://aip.scitation.org/doi/10. 1063/1.1637950.
- [16] Hepp, A. et al. Light-Emitting Field-Effect Transistor Based on a Tetracene Thin Film. *Physical Review Letters* 91, 157406 (2003). URL https://link.aps.org/doi/ 10.1103/PhysRevLett.91.157406.
- [17] Rost, C. et al. Ambipolar light-emitting organic fieldeffect transistor. Applied Physics Letters 85, 1613– 1615 (2004). URL https://aip.scitation.org/doi/ 10.1063/1.1785290.
- [18] Zaumseil, J., Friend, R. H. & Sirringhaus, H. Spatial control of the recombination zone in an ambipolar lightemitting organic transistor. *Nature Materials* 5, 69-74 (2006). URL https://www.nature.com/articles/ nmat1537.
- [19] Takenobu, T. et al. High Current Density in Light-Emitting Transistors of Organic Single Crystals. *Physical Review Letters* 100, 066601 (2008). URL https://link. aps.org/doi/10.1103/PhysRevLett.100.066601.
- [20] Kang, M. S. & Frisbie, C. D. A Pedagogical Perspective on Ambipolar FETs. *ChemPhysChem* 14, 1547-1552 (2013). URL https://onlinelibrary.wiley.com/doi/ abs/10.1002/cphc.201300014.
- [21] Meijer, E. J. et al. Solution-processed ambipolar organic field-effect transistors and inverters. Nature Materials 2, 678-682 (2003). URL https://www.nature. com/articles/nmat978.
- [22] Muccini, M. A bright future for organic field-effect transistors. *Nature Materials* 5, 605-613 (2006). URL https://www.nature.com/articles/nmat1699.
- [23] Capelli, R. et al. Organic light-emitting transistors with an efficiency that outperforms the equivalent lightemitting diodes. Nature Materials 9, 496-503 (2010). URL https://www.nature.com/articles/nmat2751.
- [24] Bisri, S. Z., Shimizu, S., Nakano, M. & Iwasa, Y. Endeavor of Iontronics: From Fundamentals to Applications of Ion-Controlled Electronics. Advanced Materials

29, 1607054 (2017). URL https://www.onlinelibrary. wiley.com/doi/abs/10.1002/adma.201607054.

- [25] Qin, Z., Gao, H., Dong, H. & Hu, W. Organic Light-Emitting Transistors Entering a New Development Stage. Advanced Materials 33, 2007149 (2021). URL https://onlinelibrary.wiley.com/doi/abs/10. 1002/adma.202007149.
- [26] Jo, S., Ubrig, N., Berger, H., Kuzmenko, A. B. & Morpurgo, A. F. Mono- and Bilayer WS2 Light-Emitting Transistors. *Nano Letters* 14, 2019–2025 (2014).
- [27] Zhang, Y. J., Oka, T., Suzuki, R., Ye, J. T. & Iwasa, Y. Electrically Switchable Chiral Light-Emitting Transistor. Science 344, 725–728 (2014). URL https: //www.science.org/doi/10.1126/science.1251329.
- [28] Lezama, I. G. et al. Surface transport and band gap structure of exfoliated 2H-MoTe 2 crystals. 2D Materials 1, 021002 (2014). URL https://doi.org/10.1088% 2F2053-1583%2F1%2F2%2F021002.
- [29] Gutierrez-Lezama, I., Reddy, B. A., Ubrig, N. & Morpurgo, A. F. Electroluminescence from indirect band gap semiconductor ReS2. 2D Materials 3, 045016 (2016). URL http://stacks.iop.org/2053-1583/3/i= 4/a=045016.
- [30] Ponomarev, E., Gutierrez-Lezama, I., Ubrig, N. & Morpurgo, A. F. Ambipolar Light-Emitting Transistors on Chemical Vapor Deposited Monolayer MoS2. Nano Letters 15, 8289-8294 (2015). URL http://dx.doi.org/ 10.1021/acs.nanolett.5b03885.
- [31] Ceballos, F., Bellus, M. Z., Chiu, H.-Y. & Zhao, H. Ultrafast Charge Separation and Indirect Exciton Formation in a MoS2-MoSe2 van der Waals Heterostructure. ACS Nano 8, 12717–12724 (2014). URL https: //doi.org/10.1021/nn505736z.
- [32] Rivera, P. et al. Observation of long-lived interlayer excitons in monolayer MoSe2-WSe2 heterostructures. Nat. Commun. 6, 6242 (2015). URL http://www.nature. com/doifinder/10.1038/ncomms7242.
- [33] Lien, D.-H. et al. Large-area and bright pulsed electroluminescence in monolayer semiconductors. Nature Communications 9, 1229 (2018). URL https://www.nature. com/articles/s41467-018-03218-8/.
- [34] Wang, J., Verzhbitskiy, I. & Eda, G. Electroluminescent Devices Based on 2D Semiconducting Transition Metal Dichalcogenides. Advanced Materials 30, 1802687 (2018). URL https://onlinelibrary.wiley.com/doi/ abs/10.1002/adma.201802687.
- [35] Ponomarev, E., Ubrig, N., Gutierrez-Lezama, I., Berger, H. & Morpurgo, A. F. Semiconducting van der Waals Interfaces as Artificial Semiconductors. *Nano Letters* 18, 5146–5152 (2018).
- [36] Amin, B., Singh, N. & Schwingenschlogl, U. Heterostructures of transition metal dichalcogenides. *Physical Review B* 92, 075439 (2015). URL http://link.aps.org/ doi/10.1103/PhysRevB.92.075439.
- [37] Magorrian, S. J., Zolyomi, V. & Fal'ko, V. I. Electronic and optical properties of two-dimensional InSe from a DFT-parametrized tight-binding model. *Physical Review* B 94, 245431 (2016). URL https://link.aps.org/doi/ 10.1103/PhysRevB.94.245431.
- [38] Ozcelik, V. O., Azadani, J. G., Yang, C., Koester, S. J. & Low, T. Band alignment of two-dimensional semiconductors for designing heterostructures with momentum space matching. *Physical Review B* 94, 035125 (2016). URL https://link.aps.org/doi/10.

1103/PhysRevB.94.035125.

- [39] Wilson, N. R. et al. Determination of band offsets, hybridization, and exciton binding in 2D semiconductor heterostructures. Science Advances 3, e1601832 (2017). URL https://www.science.org/doi/10.1126/sciadv. 1601832.
- [40] Hamer, M. J. et al. Indirect to Direct Gap Crossover in Two-Dimensional InSe Revealed by Angle-Resolved Photoemission Spectroscopy. ACS Nano 13, 2136– 2142 (2019). URL https://doi.org/10.1021/acsnano. 8b08726.
- [41] Ciarrocchi, A. et al. Polarization switching and electrical control of interlayer excitons in two-dimensional van der Waals heterostructures. Nature Photonics 13, 131– 136 (2019). URL https://www.nature.com/articles/ s41566-018-0325-y.
- [42] Jauregui, L. A. et al. Electrical control of interlayer exciton dynamics in atomically thin heterostructures. Science 366, 870-875 (2019). URL https://www.science. org/doi/10.1126/science.aaw4194.
- [43] Terry, D. J. et al. Infrared-to-violet tunable optical activity in atomic films of GaSe, InSe, and their heterostructures. 2D Materials 5, 041009 (2018). URL http://stacks.iop.org/2053-1583/5/i=4/a=041009.
- [44] Ubrig, N. et al. Design of van der Waals interfaces for broad-spectrum optoelectronics. Nature Materials 19, 299–304 (2020).
- [45] Hu, G. et al. Functional inks and printing of twodimensional materials. Chemical Society Reviews 47, 3265-3300 (2018). URL https://pubs.rsc.org/en/ content/articlelanding/2018/cs/c8cs00084k.
- [46] Zomer, P. J., Dash, S. P., Tombros, N. & van Wees, B. J. A transfer technique for high mobility graphene devices on commercially available hexagonal boron nitride. *Appl. Phys. Lett.* **99**, 232104 (2011). URL https: //aip.scitation.org/doi/abs/10.1063/1.3665405.
- [47] Chevy, A. Improvement of growth parameters for Bridgman-grown InSe crystals. Journal of Crystal Growth 67, 119-124 (1984). URL https://linkinghub. elsevier.com/retrieve/pii/0022024884901404.
- [48] Kudrynskyi, Z. et al. Giant Quantum Hall Plateau in Graphene Coupled to an InSe van der Waals Crystal. Physical Review Letters 119, 157701 (2017). URL https://link.aps.org/doi/10.1103/ PhysRevLett.119.157701.
- [49] Arora, H. et al. Effective Hexagonal Boron Nitride Passivation of Few-Layered InSe and GaSe to Enhance Their Electronic and Optical Properties. ACS Applied Materials & Interfaces 11, 43480–43487 (2019). URL https://doi.org/10.1021/acsami.9b13442.
- [50] Podzorov, V., Gershenson, M. E., Kloc, C., Zeis, R. & Bucher, E. High-mobility field-effect transistors based on transition metal dichalcogenides. *Applied Physics Letters* 84, 3301 (2004). URL http://apl.aip.org/resource/ 1/applab/v84/i17/p3301_s1.
- [51] Zhang, Y., Ye, J., Matsuhashi, Y. & Iwasa, Y. Ambipolar MoS2 Thin Flake Transistors. *Nano Letters* 12, 1136–1140 (2012). URL http://dx.doi.org/10.1021/ nl2021575.
- [52] Braga, D., Gutierrez Lezama, I., Berger, H. & Morpurgo, A. F. Quantitative Determination of the Band Gap of WS2 with Ambipolar Ionic Liquid-Gated Transistors. *Nano Letters* **12**, 5218–5223 (2012). URL http: //dx.doi.org/10.1021/nl302389d.

- [53] Seo, S. G., Hong, J. H., Ryu, J. H. & Jin, S. H. Low-Frequency Noise Characteristics in Multilayer MoTe2 FETs With Hydrophobic Amorphous Fluoropolymers. *IEEE Electron Device Letters* 40, 251–254 (2019).
- [54] Gutierrez-Lezama, I., Ubrig, N., Ponomarev, E. & Morpurgo, A. F. Ionic gate spectroscopy of 2D semiconductors. *Nature Reviews Physics* 3, 508-519 (2021). URL https://www.nature.com/articles/ s42254-021-00317-2.
- [55] Mootheri, V. et al. Understanding ambipolar transport in MoS2 field effect transistors: the substrate is the key. Nanotechnology 32, 135202 (2021). URL https://doi. org/10.1088/1361-6528/abd27a.
- [56] Sze, S. M. & Ng, K. K. Physics of Semiconductor Devices (John Wiley & Sons, 2006). URL file: ///austausch/buecher/Simon_M._Sze,_Kwok_K._Ng_ Physics_of_Semiconductor_Devices____2006.pdf.
- [57] O'Donnell, K. P. & Chen, X. Temperature dependence of semiconductor band gaps. *Applied Physics Letters* 58, 2924-2926 (1991). URL https://aip.scitation.org/ doi/10.1063/1.104723.
- [58] Shubina, T. V. et al. InSe as a case between 3D and 2D layered crystals for excitons. Nature Communications 10, 3479 (2019). URL https://www.nature.com/ articles/s41467-019-11487-0. Number: 1 Publisher: Nature Publishing Group.
- [59] Patil, P. D., Wasala, M., Ghosh, S., Lei, S. & Talapatra, S. Broadband photocurrent spectroscopy and temperature dependence of band gap of few-layer indium selenide (InSe). *Emergent Materials* 4, 1029–1036 (2021). URL https://doi.org/10.1007/s42247-021-00248-9.
- [60] Brotons-Gisbert, M. et al. Out-of-plane orientation of luminescent excitons in two-dimensional indium selenide. Nature Communications 10, 3913 (2019). URL https: //www.nature.com/articles/s41467-019-11920-4.
- [61] Baumgartner, A., Chaggar, A., Patane, A., Eaves, L. & Henini, M. Upconversion electroluminescence in InAs quantum dot light-emitting diodes. *Applied Physics Let*ters 92, 091121 (2008). URL https://aip.scitation. org/doi/10.1063/1.2885074.
- [62] Liu, S., Wu, R., Huang, J. & Yu, J. Color-tunable and high-efficiency organic light-emitting diode by adjusting exciton bilateral migration zone. *Applied Physics Letters* 103, 133307 (2013). URL https://aip.scitation.org/ doi/10.1063/1.4823476.
- [63] Binder, J. et al. Upconverted electroluminescence via Auger scattering of interlayer excitons in van der Waals heterostructures. Nature Communications 10, 2335 (2019). URL https://www.nature.com/articles/ s41467-019-10323-9.
- [64] Di Paola, D. M. et al. Room temperature upconversion electroluminescence from a mid-infrared In(AsN) tunneling diode. Applied Physics Letters 116, 142108 (2020). URL https://aip.scitation.org/doi/abs/10. 1063/5.0002407.
- [65] Hattori, Y., Taniguchi, T., Watanabe, K. & Nagashio, K. Layer-by-Layer Dielectric Breakdown of Hexagonal Boron Nitride. ACS Nano 9, 916–921 (2015). URL

https://doi.org/10.1021/nn506645q.

Acknowledgements

We gratefully acknowledge Alexandre Ferreira for continuous and precious technical support. AFM gratefully acknowledges financial support from the Swiss National Science Foundation (Division II) and from the EU Graphene Flagship project. VF acknowledges support from EC-FET Quantum Flagship Project 2D-SIPC and EPSRC grant EP/S030719/1. L.B. acknowledges support from US NSF-DMR 1807969 (synthesis, physical characterization, and heterostructure fabrication) and the Office Naval Research DURIP Grant 11997003 (stacking under inert conditions). L.B. acknowledges the use of of the facilities at the Platform for the Accelerated Realization, Analysis, and Discovery of Interface Materials (PARADIM) which is supported by the US-NSF under the Cooperative Agreement No. DMR-2039380. DS acknowledges support from the U.S. Department of Energy (DE-FG02-07ER46451) for photoluminescence measurements of InSe. DS and CNL acknowledge the support by NSF/ECCS award 2128945. The National High Magnetic Field Laboratory acknowledges support from the US-NSF Cooperative agreement Grant number DMR-1644779 and the state of Florida. K.W. and T.T. acknowledge support from the Elemental Strategy Initiative conducted by the MEXT, Japan (Grant Number JP-MXP0112101001) and JSPS KAKENHI (Grant Numbers 19H05790, 20H00354 and 21H05233).

Author contributions

H.H., D.M., D.D., and M.P. fabricated the devices with the help of I.G.L.; H.H., and N.U. measured the devices and analyzed the data. S.M, W.Z. and L.B. grew the InSe crystals. Z.L., D.S., C.N.L., and D.S. performed photoluminescence measurements on hBN encapsulated InSe multilayer, to characterize their quality. V. F. identified the high quality of the InSe crystals and suggested their use the realization of different devices. K.W. and T.T. provided the hBN crystals. H.H., I.G.L., N.U., and A.F.M discussed the data. A.F.M. wrote the manuscript with input from N.U., H.H., and I.G.L. All the authors read and commented on the manuscript. N.U. and A.F.M. supervised the research.

Competing interests

The Authors declare no competing interests.