Attraction Between Electron Pairs in High Temperature Superconductors

Phil Attard

phil.attard1@gmail.com

4 Mar., 2022

It is proposed that in high temperature superconductors Cooper pairs form and condense due to the monotonic-oscillatory transition in the pair potential of mean force, which occurs quite generally at high coupling in charge systems. It is shown that the predicted transition temperatures are broadly in line with measured superconducting transition temperatures for reasonable values of the total electron density and the residual dielectric permittivity arising from the immobile electrons. The predicted transition is independent of the isotopic masses of the solid. Consequent design principles for high temperature superconductors are discussed.

I. INTRODUCTION

The Bardeen-Cooper-Schrieffer $(BCS)^1$ theory of superconductivity is based on electron pairs forming zeromomentum, zero-spin bosons bound together by an attractive interaction. For normal low temperature superconductors the accepted mechanism for the attraction is the dynamic interaction of the electron pair with phonons, which are the quantized vibrations of the solid lattice. The dependence of the transition temperature on the isotopic masses of the solid^{2,3} confirms BCS theory.

In the late 1980's high temperature superconductors with transition temperatures above 30 K were discovered.^{4,5} These are independent of the isotopic masses, which rules out the phonon exchange mechanism. New materials with ever higher superconducting transition temperatures have been discovered in the ensuing years, but despite many proposals,⁶⁻¹² no consensus has emerged for the nature of the attractive potential that forms Cooper pairs in these materials.

In this paper I propose that the electron attraction responsible for Cooper pairs in high temperature superconductors is due to the oscillatory pair static correlation function that occurs at high coupling. This has long been established for like-charged particles in the one component plasma and in primitive model electrolytes.^{13–20} Here the high-temperature superconductor is modeled as a one-component plasma in media, with the relatively few electrons in the Fermi foam comprising the fluid charges, and the fixed nuclei and majority immobile electrons in the Fermi sea forming the neutralizing background and static relative permittivity (dielectric constant). The predicted temperatures for the monotonic-oscillatory transition in this model encompass the measured transition temperatures for high temperature superconductors for physically reasonable values of the total electron density and static relative permittivity.

II. MODEL AND ANALYSIS

The solid conductor is modeled as a one component plasma (mobile electrons in a uniform counter-charge background), together with a finite relative permittivity, $\epsilon_{\rm r} = \mathcal{O}(10^2)$, that results from the remaining immobile but polarizable electrons (i.e. those deep in the Fermi sea). The mobile electrons at the Fermi foam have number density $\rho_{\rm F}(T)$ derived below. Arguments concerning this model are canvassed in the conclusion.

I begin with the restricted primitive model electrolyte for three reasons: First, there are a wealth of analytic, numeric, and experimental results known for electrolytes. Second, it shows the generality of the monotonic-oscillatory transition in charge systems. And third, it gives a specific value for the width of the accessible energy states, which is required to determine the electron density of the Fermi foam.

In the restricted primitive model electrolyte (ions of equal hard sphere diameter), the pair distribution function undergoes an oscillatory transition when¹⁹

$$\kappa_{\rm D} d \ge \sqrt{2},$$
 (2.1)

where d is the hard core diameter of the ions. The inverse Debye screening length for the binary symmetric electrolyte is $\kappa_{\rm D} = \sqrt{(4\pi\beta/\epsilon)2\rho_{\rm F}q^2}$, where q is the ionic charge (in this case the electron charge), and $\rho_{\rm F}$ is the number density of each type of ion. Here $\beta = 1/k_{\rm B}T$ is the inverse temperature, and $\epsilon = 4\pi\epsilon_0\epsilon_{\rm r}$ is the total permittivity of the medium, ϵ_0 being the permittivity of free space (SI units). This result is based on the Debye-Hückel form for the pair distribution function combined with the exact Stillinger-Lovett second moment condition. More accurate analytic and numeric approximations exist,¹⁹ but this is sufficient for the present purposes.

To make the connection with the one component plasma, which does not impose a hard core diameter, the distance of closest approach of the electrons can be set as the point at which the Coulomb potential *in media* reaches several times the thermal energy, $u(d) = \alpha k_{\rm B}T$, or $d = \beta e^2/\epsilon \alpha$. With these the oscillatory transition in the symmetric electrolyte occurs when

$$2 \le \frac{4\pi\beta 2\rho_{\rm F} e^2}{\epsilon} \frac{\beta^2 e^4}{\epsilon^2 \alpha^2} = \frac{6}{\alpha^2} \Gamma^3.$$
 (2.2)

Here the plasma coupling parameter with finite relative permittivity is $\Gamma \equiv \beta e^2 / [\epsilon (3/4\pi\rho_{\rm F})^{1/3}]$.

As mentioned, the parameter α is the multiple of the thermal energy which bounds the accessible states.

Choosing $\alpha = \sqrt{24} \approx 4.9$, the transition criterion becomes

$$\Gamma \ge 2. \tag{2.3}$$

With this value of α , the value of the coupling constant at the transition given for the restricted primitive model electrolyte agrees with that found by Monte Carlo simulations of the one component plasma.¹³

I now estimate the density of the electrons in the Fermi foam modeling them as a non-interacting ideal gas, also known as the free electron model. The Fermi momentum and the Fermi energy for ideal fermions are²¹

$$p_{\rm F} = 2\pi\hbar \left(\frac{3\rho}{8\pi}\right)^{1/3}$$
, and $\epsilon_{\rm F} = \frac{(2\pi\hbar)^2}{2m} \left(\frac{3\rho}{8\pi}\right)^{2/3}$, (2.4)

where $\rho = N/V$ is the total electron number density. The thermal wavelength is $\Lambda = \sqrt{2\pi\beta\hbar^2/m}$, and $\beta\epsilon_{\rm F} = 2\pi(3\rho\Lambda^3/8\pi)^{2/3}/2$, which is much larger than unity.

With momentum state spacing being $\Delta_p = 2\pi\hbar/L$,^{22,23} where the volume is $V = L^3$, the number in the Fermi foam is

$$N_{\rm F} = 2\Delta_p^{-3} \int_{\epsilon_{\rm F}-\alpha/\beta}^{\epsilon_{\rm F}+\alpha/\beta} \mathrm{d}\epsilon \, 4\pi m \sqrt{2m\epsilon} \frac{e^{-\beta(\epsilon-\epsilon_{\rm F})}}{1+e^{-\beta(\epsilon-\epsilon_{\rm F})}} \\ \approx 4\alpha V \Lambda^{-3} (3\rho \Lambda^3/8\pi)^{1/3}.$$
(2.5)

An expansion to leading order for large $\beta \epsilon_{\rm F}$ has been made to obtain the final equality. That is

$$\rho_{\rm F}\Lambda^3 = 4\alpha \left(\frac{3\rho\Lambda^3}{8\pi}\right)^{1/3}.$$
 (2.6)

The total excitable electron density, $\rho_{\rm F}$, is significantly less than the total electron density, ρ . It is proportional to the number of accessible energy states at the Fermi energy, which is fixed by equating the results of the restricted primitive model to those of the one component plasma, $\alpha = \sqrt{24}$

The idea that only the electrons at the Fermi surface contribute to screening also underlies the Thomas-Fermi model of the electron gas.²⁴ This idea is taken a little further here by modeling the remaining immobile electrons as being polarisable and contributing to the residual dielectric constant.

III. NUMERICAL RESULTS

The predicted oscillatory-monotonic transition temperature is now explored for a range of the two free parameters: the total electron density ρ and the residual static relative permittivity $\epsilon_{\rm r}$. For these a guide is provided by values for ceramic materials. The total electron density of zirconia ZrO₂ is $\rho = 1.65 \times 10^{30} \, {\rm m}^{-3}$. The relative permittivity of typical ceramic insulators is on the order of $\epsilon_{\rm r} = 10^1 \text{--} 10^2.^{25}$



FIG. 1: Coion pair potential of mean force as a function of separation in the symmetric binary monovalent electrolyte $(d = 3.41 \text{ Å}, \epsilon_r = 100, T = 100 \text{ K}, \text{ hypernetted chain approximation})$. The solid curve is 0.5 M, $(\kappa_D^2 d^2 = 1.5, \Gamma = 1.8)$, the short-dash curve is 1.0 M, $(\kappa_D^2 d^2 = 2.9, \Gamma = 2.3)$, the long-dash curve is for 2.0 M $(\kappa_D^2 d^2 = 5.9, \Gamma = 2.9)$. The solid line is an eye guide.

Figure 1 shows the coion pair potential of mean force above and below the oscillatory transition close to contact. The results were obtained with the hypernetted chain approximation for the restricted primitive model binary electrolyte.¹⁹ The qualitative difference that the transition makes is apparent. Increasing coupling corresponds to decreasing temperature at constant concentration, or increasing concentration at constant temperature, which is the case shown in the figure.

At the lowest concentration shown 0.5 M, the potential of mean force is monotonic repulsive and exponentially decaying. In this case the coupling is below the transition value predicted for the restricted primitive model and also below that predicted for the one component plasma. At the intermediate concentration in the figure, 1.0 M, a shallow primary minimum appears with width on the order of 10^3 Å. At the highest concentration shown, 2.0 M, the primary minimum has become relatively deep and narrow, and the potential of mean force is clearly oscillatory with a noticeable barrier to the primary minimum. For the present parameters, the location of the transition predicted by the Debye-Hückel-Stillinger-Lovett approximation for the primitive model electrolyte, Eq. (2.1), is more or less equal to that observed in the one component plasma, Eq. (2.3).

The molecular interpretation of the attraction is that it arises at high coupling from over-charging by counterions (or the background charge) combined with packing constraints.¹⁹ As mentioned, it also occurs in the one component plasma.¹³

Figure 2 shows the value of the plasma coupling parameter as a function of the relative permittivity for fixed total electron density. Values $\Gamma > 2$ mark oscillatory pair correlation functions. One sees that this occurs for low temperatures. For the lowest relative permittivities shown, $\epsilon_{\rm r} = 100$ and 75, the transition temperatures



FIG. 2: Plasma coupling parameter *in media* using electron density $\rho_{\rm F}(T)$, Eq. (2.6), and, from bottom to top, relative permittivity $\epsilon_{\rm r} = 200, 150, 100, \text{ and } 75$. The dotted line marks the transition to oscillatory behavior. In all cases $\alpha = \sqrt{24}$ and $\rho = 10^{30} \,\mathrm{m}^{-3}$.



FIG. 3: Transition temperature as a function of the relative permittivity. From left to right the curves are for a total electron density of $\rho = 0.1$, 1, and $10 \times 10^{30} \,\mathrm{m}^{-3}$.

are greater than those measured for high temperature superconductors. 4,5

Figure 3 shows the transition temperature as a function of relative permittivity for several values of the electron density. The transition temperature increases with decreasing relative permittivity and with increasing electron density. It is more sensitive to changes in the permittivity than the electron density. The range of calculated transition temperatures encompasses those measured for high temperature superconductors. From the figure one can conclude that a high superconducting transition temperature requires both a high electron density and a low static relative permittivity. Since the latter can be expected to increase with increasing electron density, there is an obvious competition between these two requirements. This undoubtedly restricts the structure and composition of suitable candidate materials for high temperature superconductivity.

IV. CONCLUSION

Perhaps the most controversial aspect of the proposed model is the invocation of a finite relative permittivity for the solid. The perceived wisdom is that a conductor has infinite permittivity. Also, the one component plasma is usually modeled in vacuo, $\epsilon_{\rm r} = 1$. In response to these anticipated objections I make the following points. First, one has to distinguish between an experimental challenge and a fundamental limitation of nature. There is no doubt that a macroscopic measurement of the dielectric constant of a conductor yields an infinite dielectric constant in the zero frequency limit. In my opinion, all this says is that the conductivity dominates the measurement; it does not say that the residual relative permittivity is either unity or infinity. Second, fixed atoms surrounded by the electrons deep in the Fermi sea, which include the immobile inner shell electrons, remain polarizable, and therefore they must contribute to a finite relative permittivity. Third, if the relative permittivity were truly infinite at the molecular level, then the immobile electrons could not interact via the Coulomb repulsion, and they would be utterly transparent to each other, which is obvious nonsense. Fourth, and finally, insulators that are close in chemical composition and physical structure to specific high temperature superconductors, have a measured finite relative permittivity greater than unity. For example, cuprate superconductors are insulators if the doping fraction is less than 0.1 holes per CuO_2 .²⁶ It seems plausible that the small changes in composition that turn these into conductors do not much change the residual static relative permittivity. Instead the simpler interpretation is that the infinite conduction permittivity swamps any attempt to measure macroscopically the finite residual static relative permittivity.

The most reliable way to measure the residual static dielectric permittivity of a high temperature superconductor may turn out to be by extrapolation from an insulator of similar chemical and structural composition.

As mentioned in connection with Fig. 3, a high monotonic-oscillatory transition temperature relies upon the competing requirements of high electron density and low relative permittivity. One might speculate that the reason for the prevalence of layered structures amongst high temperature superconductors is that they combine a high electron density within the conducting planes together with a low electron density and hence low polarisability in the interlayer space. At the level of dielectric continuua, the consequent image charges increase the coupling between the electrons in the dense layer²⁷ and increase the temperature of the oscillatory transition compared to a uniform dielectric medium.

Of course one has to be a little skeptical about the quantitative accuracy of modeling a crystalline layered conductor as a homogeneous charge fluid. On the one hand the universality of the monotonic-oscillatory transition for the like-charge pair potential of mean force at high coupling is robust and undeniable. On the other hand, the quantitative prediction of the transition temperature and the depth of the primary minimum cannot be taken too literally for electrons in the layered crystalline solids that are of interest in high temperature superconductivity.

This paper proposes that the oscillatory potential of mean force that occurs at high coupling is responsible for Cooper pair formation and superconductivity. The BCS theory is predicated upon an attractive potential, not an attractive potential of mean force. The difference between the pair potential and the pair potential of

- ¹ J. Bardeen, L. N. Cooper, and J. R. Schrieffer, "Theory of Superconductivity", *Phys. Rev.* 108, 1175 (1957).
- ² E. Maxwell, "Isotope Effect in the Superconductivity of Mercury", *Phys. Rev.* **78**, 477 (1950).
- ³ C. A. Reynolds, B. Serin, W. H. Wright, and L. B. Nesbitt, "Superconductivity of Isotopes of Mercury", *Phys. Rev.* **78**, 487 (1950).
- ⁴ J. G. Bednorz and K. A. Möller, "Possible high T_c superconductivity in the Ba-La-Cu-O system", Z. Phys. B 64, 189 (1986).
- ⁵ M. K. Wu, J. R. Ashburn, C. J. Torng, P. H. Hor, R. L. Meng, L. Gao, Z. J. Huang, Y. Q. Wang, and C. W. Chu, "Superconductivity at 93 K in a New Mixed-Phase Y-Ba-Cu-O Compound System at Ambient Pressure", *Phys. Rev. Lett.* 58, 908 (1987).
- ⁶ P. Anderson, "The resonating valence bond state in La_2CuO_4 and superconductivity", *Science* **235**, 1196 (1987).
- ⁷ N. E. Bickers, D. J. Scalapino, and R. T. Scalettar, "CDW and SDW mediated pairing interactions", *Int. J. Mod. Phys. B* **1**, 687 (1987).
- ⁸ M. Inui, S. Doniach, P. J. Hirschfeld, A. E. Ruckenstein, Z. Zhao, Q. Yang, Y. Ni, and G. Liu, "Coexistence of antiferromagnetism and superconductivity in a mean-field theory of high-Tc superconductors", *Phys. Rev. B* **37**, 5182 (1988).
- ⁹ C. Gros, D. Poilblanc, T. M. Rice, and F. C. Zhang, "Superconductivity in correlated wavefunctions", *Physica C*, 153–155, 543 (1988).
- ¹⁰ G. Kotliar, and J. Liu, "Superexchange mechanism and d-wave superconductivity", *Phys. Rev. B* 38, 5142 (1988).
- ¹¹ A. Mann, "High-temperature superconductivity at 25: Still in suspense", *Nature* **475** 280 (2011).
- ¹² P. Monthoux, A. V. Balatsky, and D. Pines, "Toward a theory of high-temperature superconductivity in the antiferromagnetically correlated cuprate oxides", *Phys. Rev. Lett.* 67, 3448 (1991).
- ¹³ S. G. Brush, H. L. Sahlin and E. Teller, "Monte Carlo Study of a One-Component Plasma. I. J. Chem. Phys. 45, 2102 (1966).
- ¹⁴ F. H. Stillinger and R. Lovett, "Ion-Pair Theory of Concentrated Electrolytes. I. Basic Concepts", J. Chem. Phys. 48, 3858 (1968).
- ¹⁵ M. Parrinello and M. P. Tosi, "Structure and dynamics of

mean force is fundamentally the difference between quantum mechanics and quantum statistical mechanics. It is the latter, not the former, that is the appropriate theory for condensed matter. In an accompanying paper I give a new quantum statistical mechanical theory for superconductivity that shows explicitly how Cooper pairs form and condense depending upon the potential of mean force.²⁸ The theory uses the classical phase space formulation of quantum statistical mechanics,^{29,30} together with techniques recently developed for superfluidity.^{30,31}

simple ionic liquids", Rev. Nuovo Cimento 2 1 (1979).

- ¹⁶ C. W. Outhwaite, "Modified Poisson-Boltzmann equation in electric double layer theory based on the Bogoliubov-Born-Green-Yvon integral equations", J. Chem. Soc. Faraday Trans. 2 74, 1214 (1978).
- ¹⁷ M. E. Fisher and B. Widom, "Decay of Correlations in Linear Systems", J. Chem. Phys. 50, 3756 (1969).
- ¹⁸ G. Stell, K. C. Wu, and B. Larsen, "Critical Point in a Fluid of Charged Hard Spheres", *Phys. Rev. Lett.* **37**, 1369 (1976).
- ¹⁹ P. Attard, "Asymptotic Analysis of Primitive Model Electrolytes and the Electrical Double Layer", *Phys. Rev. E* 48, 3604 (1993).
- ²⁰ J. Ennis, R. Kjellander, and D. J. Mitchell, "Dressed Ion Theory for Bulk Symmetric Electrolytes in the Restricted Primitive Model", J. Chem. Phys. **102**, 975 (1995).
- ²¹ R. K. Pathria, *Statistical Mechanics* (Pergamon Press, Oxford, 1972).
- ²² A. Messiah Quantum Mechanics (Vol 1 and 2) (North-Holland, Amsterdam, 1961).
- ²³ E. Merzbacher, *Quantum Mechanics* 2nd edn (Wiley, New York, 1970).
- ²⁴ C. Kittel, *Introduction to Solid State Physics* 5th edn (Wiley, New York, 1976).
- ²⁵ /www.ceramtec.com/ceramic-materials/dielectric/ (Accessed 1 Feb., 2022).
- ²⁶ http://hyperphysics.phy-astr.gsu.edu/hbase/Solids /hitc.html (Accessed 1 Feb., 2022).
- ²⁷ P. Attard, D. J. Mitchell, and B. W. Ninham, "Beyond Poisson-Boltzmann: Images and Correlations in the Electric Double Layer. II. Symmetric Electrolyte." J. Chem. Phys. 89, 4358 (1988).
- ²⁸ P. Attard, "New Theory for Cooper Pair Formation and Superconductivity", arXiv:2203.12103v2 (2022).
- ²⁹ P. Attard, "Quantum Statistical Mechanics in Classical Phase Space. Expressions for the Multi-Particle Density, the Average Energy, and the Virial Pressure", arXiv:1811.00730 (2018).
- ³⁰ P. Attard, Quantum Statistical Mechanics in Classical Phase Space, (IOP Publishing, Bristol, 2021).
- ³¹ P. Attard, "Bose-Einstein Condensation, the Lambda Transition, and Superfluidity for Interacting Bosons", arXiv:2201.07382 (2022).