

A machine learning approach to predict the structural and magnetic properties of Heusler alloy families

Srimanta Mitra*^{a,b}, Aquil Ahmad^c, Sajib Biswas^a and Amal Kumar Das*^a

^a Indian Institute of Technology Kharagpur, Khargapur-721302, India

^b Sensor Development Area, Space Applications Centre, ISRO, Ahmedabad-380015, India

^c National Changhua University of Education, Changhua city, Taiwan-500

***email:** ^{a,b} srimanta_44@sac.isro.gov.in; ^a amal@phy.iitkgp.ac.in;

Abstract

Random forest (RF) regression model is used to predict the lattice constant, magnetic moment and formation energies of full Heusler alloys, half Heusler alloys, inverse Heusler alloys and quaternary Heusler alloys based on existing as well as indigenously prepared databases. Prior analysis was carried out to check the distribution of the data points of the response variables and found that in most of the cases, the data is not normally distributed. The outcome of the RF model performance is sufficiently accurate to predict the response variables on the test data and also shows its robustness against overfitting, outliers, multicollinearity and distribution of data points. The parity plots between the machine learning predicted values against the computed values using density functional theory (DFT) shows linear behavior with adjusted R^2 values lying in the range of 0.80 to 0.94 for all the predicted properties for different types of Heusler alloys. Feature importance analysis shows that the valence electron numbers plays an important feature role in the prediction for most of the predicted outcomes. Case studies with one full Heusler alloy and one quaternary Heusler alloy were also mentioned comparing the machine learning predicted results with our earlier theoretical calculated values and experimentally measured results, suggesting high accuracy of the model predicted results.

1. Introduction

In recent years, there is a constant increasing interest in the field of machine learning (ML) methods in multiple areas of research, e.g. image recognition [1-3], speech recognition [4-5], event forecasting [6-8], pattern recognition [9], self-driving cars [10-11], medical diagnosis [12-13], automatic language translation [14-15] etc. Materials informatics (MI) is one of the emerging areas of study where informatics is used to understand and predict materials' properties [16-18]. Applications of ML in material science domain is much attractive and is of keen interest in current

time [19-25]. In MI, ML models are used to develop and predict new materials' properties using different databases [26-30, 31]. There are many studies that have been carried out to predict the electronic band gap [32-33], magnetism [34-36], magnetic entropy change [37-38], superconducting critical temperature [39-43], melting temperatures [44-45], dielectric properties [46-47], molecular atomization energies [25] and different properties of polymers [48-49] and molecules [50-52] using the essence of ML models. Applying ML methods in materials science accelerates the prediction of new novel materials [31, 53-54] which not only can bypass the criticality of the first principle calculations [55] having limitation to the requirement of advanced technical infrastructures but also the involved experimental synthesis and characterization of new materials.

Heusler alloys (HAs) are one of the most important classes of materials due to their versatile properties, which have major technical importance in spintronics research. They show half-metallic ferromagnetism [56], antiferromagnetism and compensated ferrimagnetism [57-58], superconductivity [59], shape memory effect [60], giant magnetoresistance [61], tunneling magnetoresistance [62], anomalous that helps to automate analytical model building and thus can take decision by finding the pattern in the data, without the intervention of human brains [73, 74], i.e. self-learning from data and experience. It is having the intersection of mathematics, statistics and computer science. ML methods are broadly classified into three types: a) supervised learning, having the labelled training data, b) unsupervised learning, with the unlabelled training data and c) reinforcement learning, with the intermix of training and testing phases [75]. In MI, majorly supervised learning methods are used. Previously, few studies [76-80] report about the use of ML algorithms to predict few HA properties. In this work, we have used supervised learning algorithm to predict structural and magnetic properties of all the classes of HAs, such that it is more detailed

and general as compared to the previous reports. In section 2, methodology of general ML technique is described in step-by-by process; section 3 covers the results and discussion and section 4 ends with the conclusion. Hall effect [63], magneto-optic phenomena [64], thermoelectric effect and topological insulating behavior [65], magnetic semiconductivity [66], spin-gapless semiconductivity [67] etc. From application perspectives, they are suitable for spin-injection devices [68], magnetic tunnel junctions [62], spin-voltage generators [69], spin-valves [70], magnetic refrigerators [71], thermoelectric generators [65, 72] and many more. With their profound scientific and technological importance, search for new HAs is still going on. Thus accelerating the discovery of new HAs may help the materials research community to overcome several technological challenges. This is where ML can be a tool to predict new HAs based on the databases of existing current research on its domain. ML is a mathematical data analysis technique

2. Methodology

Prediction of the dependent or response variables with ML techniques generally follow the steps, shown in Fig. 1.




Fig. 1. Schematic diagram of general machine learning method.

2.1. Collection of data

The first step in any ML based approach is gathering data either from proprietary sources or from existing databases. The role of volume and quality of data is very crucial in any ML model. In materials sciences, popular sources of data can be found at refs. [26-30, 31], where information about materials' crystal structure and other properties is available. Specific to HAs, the database can be found at ref [30]. In this work, this database [30] is mainly used to predict the lattice constant, saturation magnetic moment and formation energy of full HAs, half HAs and inverse HAs. For quaternary HAs, a modular database has been prepared by using existing literatures [81-135].

2.2. Data cleaning and preprocessing

Data cleaning and preprocessing is the most crucial and time-consuming step in ML models. It is required to make the collected raw data into understandable format by removing incorrect, irrelevant and duplicate data and thus improving the productivity and efficiency of the model. This step also handles missing and noisy data. Outliers in a dataset degrades a model's performance metrics and requires special attention for its removal. There are few graphical (e.g. box plots) and numerical (e.g. Z-score) techniques which can give information about the outliers. Fig. 2 shows the box plots of the datasets for different types of HAs. Data which are beyond the minimum values of the boxes, are the potential outliers, which are removed here in prior before applying the ML model to the final dataset.




Fig. 2. Box plots for different types of HAs dataset (a) full HA, (b) half HA, (c) quaternary HA, (d) inverse HA.

2.3. Data visualization and feature engineering

Data visualization makes the data more understandable and interpretable by showing the trends and patterns, thus making the decision faster. There are different types of graphical data visualization tool e.g. histogram plots, scatter plots, bar charts, heat maps etc. Fig. 3 to Fig. 6 shows the scatter plots of the response variables: lattice constants, magnetic moment and formation energies for full HAs, half HAs, inverse HAs and quaternary HAs respectively. In ML, generally data is assumed to be distributed normally, to ease the model building, though it is not mandatory. Thus it is useful to check whether the data is normally distributed or not. Here, in this work,

Shapiro-Wilk (S-W) test [136] is used to confirm a normally distributed data. In S-W test, if the p-value is greater than a significance level ($\alpha = 0.05$), then it is considered to be normally distributed, otherwise not.




Fig. 3. Scatter plots of (a) lattice constant, (b) magnetic moment and (c) formation energy for full Heusler alloys. Inset shows the histogram plots of the same.

Inset curves in Figs. 3 (a) to 3(c) shows the histogram plots of each of the response variables in case of full HAs. From the curves it is evident that except formation energy ($p = 0.834$), lattice constant ($p = 2.92 \times 10^{-5}$) and magnetic moment ($p = 1.36 \times 10^{-9}$) values are not normally distributed.




Fig. 4. Scatter plots of (a) lattice constant, (b) magnetic moment and (c) formation energy for half Heusler alloys. Inset shows the histogram plots of the same.

Figs. 4 (a) to (c) shows the scatter plots of the response variables for half HAs, along with their histograms. Lattice constant and magnetic moment with their p-values of 0.003 and 1.79×10^{-15} respectively shows that they are not normally distributed; however the formation energy values are normally distributed ($p = 0.112$).

Figs. 5 (a) to (c) shows that only formation energy values of inverse HAs are normally distributed with $p = 0.27$. Similarly, fig. 6 (a) and (b) shows that none of the lattice constant ($p = 3.67 \times 10^{-5}$) and the magnetic moment ($p = 9.32 \times 10^{-7}$) values of quaternary HAs are normally distributed.




Fig.5. Scatter plots of (a) lattice constant, (b) magnetic moment and (c) formation energy for inverse Heusler alloys. Inset shows the histogram plots of the same.

Thus, from the scatter plots and the histogram plot it is evident that the data points of the response variables, except formation energy, are not normally distributed, and care is taken to counteract this observations while selecting the ML model to achieve best prediction results.

To predict the response variables selecting the best feature variables is crucial and this is done by proper feature engineering techniques. In this work, feature variables are selected as: total number of valence electrons, ionic radii and electronegativities of the atomic elements of the HAs. The integrity of the features are filtered by prior variance thresholding techniques. Correlations among

the input features can be found from correlation matrices shown in Figs. 8(d), 9 (d), 10 (d) and 11(d).




Fig.6. Scatter plots of (a) lattice constant, (b) magnetic moment for quaternary Heusler alloys. Inset shows the histogram plots of the same.

2.4. Machine learning model: Random forest

Selecting the best model is one of the most vital step in ML applications. Though it is not possible to select a single model for all types of uses, it saves both time and cost by choosing the right model for specific applications. The selection criteria may be depending upon the size of the training data and training time, inference time, dimensionality of the data and interpretability of the model. Also, it becomes more helpful when the model is sufficiently robust against multicollinearity, overfitting and outliers.

Random forest (RF) regression algorithm [137-139] with Python scikit-learn package [140] is used in this work to predict the structural and magnetic properties of the HA families. RF is one of the decision tree based ensemble approach which is famous for its robustness to overfitting and outliers [141]. It works well for high dimensional, imbalanced data and moderately robust

against the multicollinearity [142] between the predictor variables in the dataset, as it uses bootstrap sampling and feature sampling by randomly picking up different groups of features for different decision models, where each model selects a different sub-set of data points. RF can be considered as a variance reduction method, which can provide substantial improved results over a single decision tree based approach and may be used where the dataset has error rate considerably depending upon the variance [138]. Relative feature importance can also be predicted while using RF [141, 143-144] algorithms. RF does not require the data points to be normally distributed, which is generally assumed in linear regression based models.

2.5. Performance metrics

The ML model is trained with 70% of the dataset and the performance of the model is evaluated on rest of the 30% of the data, using cross-validation technique. Measuring the performance of the RF regression model is usually achieved using the coefficient of determination (R^2) (equation 1).

$$R^2 = 1 - \frac{RSS}{TSS} = 1 - \frac{\sum(x_i - \hat{x})^2}{\sum(x_i - \bar{x})^2} \quad (1)$$

where, RSS = sum of square of residuals and TSS = total sum of squares, x_i = ith observation for the feature x, and \bar{x} is the mean value of x in the dataset.

R^2 can be taken as a statistical measure of the goodness of fit between the ML-predicted and DFT-computed results and gives information about the extent of correlation between them. However, adjusted R^2 (equation 2) gives more accurate measure of the correlation by considering all other independent variables, thus making the model more robust against adding new feature variables.

$$\text{Adj. } R^2 = 1 - \frac{(1-R^2)(N-1)}{N-p-1} \quad (2)$$

where, N = total # of observations and p = # of independent variables.

We have used Adj. R^2 as the performance metric in this work.

3. Results and discussion

The crystal structure of different types of HAs is shown in Fig. 7, in which full HAs (FHA), half HAs (HHA), inverse HAs (IHA) and quaternary HAs (QHA) are symbolized as in Table 1, where X, X', Y atoms are transition metal atoms and Z is the main group element. Table .1 shows the crystal structure details of different types of HAs with their symbols, space groups, Wyckoff positions and site occupancies with reference to Fig. 7.

Table 1 Crystal structure details of different types of HAs

Type	Symbol	Space group	Wyckoff positions	Sites			
				A	B	C	D
FHA	X_2YZ	Fm-3m (225)	X: 8c (1/4,1/4,1/4) and (3/4,3/4,3/4)	X	Y	X	Z
			Y: 4b (1/2,1/2,1/2)				
			Z: 4a (0,0,0)				
HHA	XYZ	F-43m (216)	X: 4a (0,0,0)	X	Y	Void	Z
			Y: 4b (1/2,1/2,1/2)				
			Z: 4c (1/4,1/4,1/4)				
QHA	$XX'YZ$	F-43m (216)	X: (3/4,3/4,3/4)	X	Y	X'	Z
			X': (1/4,1/4,1/4)				
			Y: (1/2,1/2,1/2)				
			Z: (0,0,0)				
IHA	X_2YZ	F-43m (216)	X: 4a (0,0,0) and 4d (3/4,3/4,3/4)	X	X	Y	Z
			Y: 4b (1/2,1/2,1/2)				
			Z: 4c (1/4,1/4,1/4)				

In this work, prediction of the structural and magnetic properties of all types of HAs is carried out by taking the seven input features as: N_v = Total # of valence electrons; $r(i)$ = Ionic radius and $E(i)$ = Electronegativity of i atom, where $i = X, X', Y$ and Z ;




Fig.7. Schematic diagram of crystal structure with different sites of occupancy for different types of Heusler alloys [145].

Fig. 8 (a) to (c) show the parity plots of the lattice constant, magnetic moment and formation energies of full HAs indicating the variation of the machine learning predicted properties with the DFT- computed values. The inset shows the importance of each input feature variable in predicting the results. Close agreement of the model prediction performance can be concluded from the adjusted R^2 values, which is greater than 0.8 in each case. Fig. 8 (d) shows the correlation matrix explaining the mutual correlations among the feature variables for FHAs. It can be seen that even though there is moderate correlations between the input feature variables, RF model can predict the response variables with sufficient accuracy.

Similar parity plots of the lattice constant, magnetic moment, formation energies of half HAs, and inverse HAs are shown in Fig. 9 and Fig. 10 respectively, where the prediction is reasonably well. Fig. 11 shows the parity plots of (a) lattice constant and (b) magnetic moment for

quaternary Heusler alloys. In each plots, the inset shows the importances of the input features and it is observed that for almost every cases, the role of the valence electrons number is important. It




Fig.8. Parity plots of the response variables (a) lattice constant, (b) magnetic moment, (c) formation energy for full Heusler alloys showing the variation of machine learning predicted values against the values computed from density functional theory. (d) Correlation matrix showing the correlation between the predictor feature variables used to predict the above response variables.

can also be noticed that the performance of the RF regression model is not hampered by the moderate correlations present between some of the prediction variables, as observed from the correlation matrices Figs.8 (d), 9 (d), 10 (d) and 11 (d).




Fig. 9. Parity plots of the response variables (a) lattice constant, (b) magnetic moment, (c) formation energy for half Heusler alloys showing the variation of machine learning predicted values against the values computed from density functional theory. (d) Correlation matrix showing the correlation between the predictor feature variables used to predict the above response variables.





Fig. 10. Parity plots of the response variables (a) lattice constant, (b) magnetic moment, (c) formation energy for inverse Heusler alloys showing the variation of machine learning predicted values against the values computed from density functional theory. (d) Correlation matrix showing the correlation between the predictor feature variables used to predict the above response variables.



(c)

QHA Features	N_v	r_X	$r_{X'}$	r_Y	r_Z	E_X	$E_{X'}$	E_Y	E_Z
N_v	1	-0.37	-0.08	0.51	-0.04	0.66	0.30	-0.13	0.38
r_X	-0.37	1	-0.03	-0.32	-0.18	-0.67	0.04	0.03	-0.04
$r_{X'}$	-0.08	-0.03	1	0.13	0.20	0.12	-0.47	0.07	-0.10
r_Y	0.51	-0.32	0.13	1	0.25	0.40	-0.12	0.09	
r_Z	-0.04	-0.18	0.20	0.25	1	0.07	-0.16	0.18	-0.07
E_X	0.66	-0.67	0.12	0.40	0.07	1	-0.10	-0.05	0.21
$E_{X'}$	0.30	0.04	-0.47	0.10	-0.16	-0.10	1	-0.18	0.03
E_Y	-0.13	0.03	0.07	-0.12	0.18	-0.05	-0.18	1	-0.20
E_Z	0.38	-0.04	-0.10	0.09	-0.07	0.21	0.03	-0.20	1

Fig. 11. Parity plots of the response variables (a) lattice constant, (b) magnetic moment, for quaternary Heusler alloys showing the variation of machine learning predicted values against the values computed from density functional theory. (c) Correlation matrix showing the correlation between the predictor feature variables used to predict the above response variables.

Case study:

Based on the model analysis and prediction results above, a case study is performed by selecting two samples: Co_2FeGe full HA and CoFeTiSi quaternary HA. Both these alloys were studied using density functional theory (DFT) based first principle calculations and were also

synthesized experimentally in our previous works [146-147]. The comparison table of the ML predicted results and the results obtained from theoretical calculations and experimental characterizations of the prepared samples is described in Table 2.

Table 2 Comparison table showing the values of lattice constant and saturation magnetic moment of Co₂FeGe full HA and CoFeTiSi quaternary HA, obtained from theory, experiments and machine learning based predictions.

Heusler Alloys	Theory (DFT calculations)		Experiments		Machine learning predictions (This work)	
	Lattice constant (Å)	Magnetic Moment (μ_B /f.u.)	Lattice constant (Å)	Magnetic Moment (μ_B /f.u.)	Lattice constant (Å)	Magnetic Moment (μ_B /f.u.)
Co ₂ FeGe (FHA) [146]	5.74	5.69 (GGA) 5.99 (GGA+U)	5.74	6.1	5.78	5.64
CoFeTiSi (QHA) [147]	5.74	1	5.74	1.24	5.78	1.03

Table 2 shows that the performance of Random Forest model used in this work in predicting the values of lattice constant and saturation magnetic moment is at par with the results obtained from both theory and experiments and thus can be treated as an reliable alternative way to find the HA properties.

4. Conclusion

Systematic process is followed to predict structural and magnetic properties of different types of HAs, using machine learning technique. Existing databases are used to predict the properties of full HAs, half HAs and inverse HAs; however, an indigenous database is created with the lattice constant, magnetic moment of quaternary HAs from the existing literatures. Decision tree based random forest regression algorithm is used to predict the response variables: lattice constant,

magnetic moment and formation energies, after closely visualizing the input datasets, which is majorly not normally distributed as per Shapiro-Wilk test. This non-parametric approach is robust against overfitting and outliers and performs well in predicting the response variables even though some of the input features have moderate correlations between them. The outcome of the Random Forest model is reasonably accurate as observed from the adjusted R^2 values, which remains in the range of 0.8-0.94 for most of the predictions. Feature importance computations show that number of valence electrons remains one of the most important input features for the predictions. Use of Random Forest model in predicting the mentioned response variables for all types of HAs is carried out for the first time to the best of our knowledge. Case studies were mentioned comparing the machine learning predicted results with the earlier theoretical calculations and experimental observations, suggesting the high accuracy of the Random Forest model. This work will be very helpful to the materials researchers such that a preliminary knowledge of the most important structural and magnetic properties of any types of unknown HAs can also be accurately predicted even before any first principle based calculations and experimental synthesis of the alloys.

Acknowledgements

Mr. Srimanta Mitra wish to thank Dr. B. Narasiha Sharma (Head, SSD/EOSDIG/SEDA), Mrs. Arti Sarkar (Group Director, EOSDIG/SEDA), Mr. Soumya S. Sarkar (Deputy Director, SEDA), Mr. N. M. Desai (Director), Space Applications Centre, ISRO, Ahmedabad for providing their support and motivations to complete this work.

References

- [1] J. Matuszewski, A. Rajkowski, The use of machine learning algorithms for image recognition, Proc. of SPIE. 1144218 (2019) 1-11.
- [2] S. Chen, H. Wang, F. Xu, Y.Q. Jin, Target Classification Using the Deep Convolutional Networks for SAR Images, IEEE Trans Geosci Remote Sens. 54 (2016) 4806-4817.
- [3] M. Pak, S. Kim, A Review of Deep Learning in Image Recognition, 4th International Conference on Computer Applications and Information Processing Technology (CAIPT), (2017) 1-3.
- [4] J. Li, L. Deng, R. H. Umbach, Y. Gong, Robust Automatic Speech Recognition A Bridge to Practical Applications, Elsevier. (2016).
- [5] S. Alharbi, M. Alrazgan, A. Alrashed, T. Alnomasi, R. Almojel, R. Alharbi, S. Alharbi, S. Alturki, F. Alshehri, M. Almojil, Automatic Speech Recognition: Systematic Literature Review, IEEE Access. 9 (2021) 131858-131876.
- [6] D. A. Neu, J. Lahann, P. Fettke, A systematic literature review on state-of-the-art deep learning methods for process prediction, Artif. Intell. Rev. 55 (2022) 801-827.
- [7] J. Evermann, J. R. Rehse, P. Fettke, Predicting process behaviour using deep learning, Decis. Support Syst. 100 (2017) 129-140.
- [8] J. F. Torres, D. Hadjout, A. Sebaa, F. M. Alvarez, A. Troncoso, Deep Learning for Time Series Forecasting: A Survey, Big Data. 9 (2021) 3-21.
- [9] C. M. Bishop, Pattern Recognition and Machine Learning, Springer, UK, (2006).
- [10] A. Gupta, A. Anpalagan, L. Guan, A. S. Khwaja, Deep learning for object detection and scene perception in self-driving cars: Survey, challenges, and open issues, Array. 10 (2021) 100057.

- [21] O. A. V. Lilienfeld, K. Burke, Retrospective on a decade of machine learning for chemical discovery, *Nat Commun.* 11 (2020) 4895.
- [22] D. Dragoni, T. D. Daff, G. Csanyi, N. Marzari, Achieving DFT accuracy with a machine-learning interatomic potential: Thermomechanics and defects in bcc ferromagnetic iron, *Phys. Rev. Mater.* 2 (2018) 013808.
- [23] M. Rupp, R. Ramakrishnan, O. A. V. Lilienfeld, Machine Learning for Quantum Mechanical Properties of Atoms in Molecules, *J. Phys. Chem. Lett.* 6 (2015) 3309-3313.
- [24] G. Montavon, M. Rupp, V. Gobre, A. V. Mayagoitia, K. Hansen, A. Tkatchenko, K. R. Muller, O. A. V. Lilienfeld, Machine learning of molecular electronic properties in chemical compound space, *New J. Phys.* 15 (2013) 095003.
- [25] M. Rupp, A. Tkatchenko, K. R. Muller, O. A. V. Lilienfeld, Fast and Accurate Modeling of Molecular Atomization Energies with Machine Learning, *Phys. Rev. Lett.* 108 (2012) 058301.
- [26] <http://nomad-coe.eu>.
- [27] <http://materialsproject.org>
- [28] <http://www.aflowlib.org>
- [29] <http://oqmd.org>
- [30] <http://heusleralloys.mint.ua.edu>
- [31] J. Chai, X. Chu, K. Xu, H. Li, J. Wei, Machine learning-driven new material discovery, *Nanoscale Adv.* 2 (2020) 3115.
- [32] Y. Huang, C. Yu, W. Chen, Y. Liu, C. Li, C. Niu, F. Wang, Y. Jia, Band gap and band alignment prediction of nitride based semiconductors using machine learning, *J. Mater. Chem. C*, 7 (2019) 3238-3245.

- [33] Y. Dong, C. Wu, C. Zhang, Y. Liu, J. Cheng, J. Lin, Bandgap prediction by deep learning in configurationally hybridized graphene and boron nitride, *Npj Comput. Mater.* 5 (2019) 26.
- [34] H. Hosokawa, E. L. Calvert, K. Shimojima, Machine learning prediction for magnetic properties of Sm-Fe-N based alloys produced by melt spinning, *J. Magn. Mater.* 526 (2021) 167651.
- [35] G. Katsikas, C. Sarafidis, J. Kioseoglou, Machine Learning in Magnetic Materials, *Phys. Status Solidi (B): Basic Res.* 258 (2021) 2000600.
- [36] Y. Iwasaki, R. Sawada, E. Saitoh, M. Ishida, Machine learning autonomous identification of magnetic alloys beyond the Slater-Pauling limit, *Commun. Mater.* 2 (2021) 31.
- [37] P. B. de Castro, K. Terashima, T. D. Yamamoto, Z. Hou, S. Iwasaki, R. Matsumoto, S. Adachi, Y. Saito, P. Song, H. Takeya, Y. Takano, Machine-learning-guided discovery of the gigantic magnetocaloric effect in HoB₂ near the hydrogen liquefaction temperature, *NPG Asia Mater.* 12 (2020) 35.
- [38] Y. Zhang, X. Xu, Machine learning the magnetocaloric effect in manganites from compositions and structural parameters, *AIP Adv.* 10 (2020) 035220.
- [39] P. J. Garcia-Nieto, E. Garcia-Gonzalo, J. P. Paredes-Sanchez, Prediction of the critical temperature of a superconductor by using the WOA/MARS, Ridge, Lasso and Elastic-net machine learning techniques, *Neural. Comput. Appl.* 33 (2021) 17131–17145.
- [40] D. Lee, D. You, D. Lee, X. Li, S. Kim, Machine-Learning-Guided Prediction Models of Critical Temperature of Cuprates, *J. Phys. Chem. Lett.* 12 (2021) 6211-6217.
- [41] V. Stanev, C. Oses, A. G. Kusne, E. Rodriguez, J. Paglione, S. Curtarolo, I. Takeuchi, Machine learning modeling of superconducting critical temperature, *Npj Comput. Mater.* 4 (2018) 29.

- [42] S. Li, Y. Dan, X. Li, T. Hu, R. Don, Z. Cao, J. Hu, Critical Temperature Prediction of Superconductors Based on Atomic Vectors and Deep Learning, *Symmetry*. 12 (2019) 262.
- [43] B. Roter, S. V. Dordevic, Predicting new superconductors and their critical temperatures using machine learning, *Phys. C: Supercond. Appl.* 575 (2020) 1353689.
- [44] V. Venkatraman, S. Evjen, H. K. Knuutila, A. Fiksdahl, B. K. Alsberg, Predicting Ionic Liquid Melting Points using Machine Learning, *J. Mol. Liq.* 264, (2018) 318-326.
- [45]] G. Pilania, J. E. Gubernatis, T. Lookman, Structure classification and melting temperature prediction in octet AB solids via machine learning, *Phys. Rev. B.* 91 (2015) 214302.
- [46] L. Chen, C. Kim, R. Batra, J. P. Lightstone, C. Wu, Z. Li, A. A. Deshmukh, Y. Wang, H. D. Tran, P. Vashishta, G. A. Sotzing, Y. Cao, R. Ramprasad. Frequency-dependent dielectric constant prediction of polymers using machine learning, *Npj Comput. Mater.* 6 (2020) 61.
- [47] A. Takahashi, Y. Kumagai, J. Miyamoto, Y. Mochizuki, F. Oba, Machine learning models for predicting the dielectric constants of oxides based on high-throughput first-principles calculations, *Phys. Rev. Mater.* 4 (2020) 103801.
- [48] H. D. Tran, C. Kim, L. Chen, A. Chandrasekaran, R. Batra, S. Venkatram, D. Kamal, J. P. Lightstone, R. Gurnani, P. Shetty, M. Ramprasad, J. Laws, M. Shelton, R. Ramprasad, Machine-learning predictions of polymer properties with Polymer Genome, *J. Appl. Phys.* 128 (2020) 171104.
- [49] S. Wu, Y. Kondo, M. Kakimoto, B. Yang, H. Yamada, I. Kuwajima, G. Lambard, K. Hongo, Y. Xu, J. Shiomi, C. Schick, J. Morikawa, R. Yoshida, Machine-learning-assisted discovery of polymers with high thermal conductivity using a molecular design algorithm, *Npj Comput. Mater.* 5 (2019) 66.

- [50] D. Lemm, G. F.V. Rudroff, O. A. V. Lilienfeld, Machine learning based energy-free structure predictions of molecules, transition states, and solids, *Nat. Commun.* 12 (2021) 4468.
- [51] K. Hansen, F. Biegler, R. Ramakrishnan, W. Pronobis, O. A. V. Lilienfeld, K. R. Muller, A. Tkatchenko, Machine Learning Predictions of Molecular Properties: Accurate Many-Body Potentials and Nonlocality in Chemical Space, *J. Phys. Chem. Lett.* 6 (2015) 2326-2331.
- [52] G. A. Pinheiro, J. Mucelini, M. D. Soares, R. C. Prati, J. L. F. D. Silva, and M. G. Quiles,, Machine Learning Prediction of Nine Molecular Properties Based on the SMILES Representation of the QM9 Quantum-Chemistry Dataset, *J. Phys. Chem. A.* 124 (2020) 9854–9866.
- [53] Y. Liu, T. Zhao, W. Ju, S. Shi, Materials Discovery and Design using Machine Learning, *J. Materiomics*, 3 (2017) 159-177.
- [54] T. Mueller, A. Kusne, R. Ramprasad, Machine learning in materials science: recent progress and emerging applications, *Rev. Comput. Chem.* 29 (2016) 186.
- [55] F. Brockherde, L. Vogt, L. Li, M. E. Tuckerman, K. Burke, K. R. Muller, Bypassing the Kohn-Sham equations with machine learning, *Nat. Commun.* 8 (2017) 872.
- [56] A. Kundu, A. Ghosh, R. Banerjee, S. Ghosh, B. Sanyal, New quaternary half-metallic ferromagnets with large Curie temperatures, *Sci. Rep.* 7 (2017) 1803.
- [57] R. Stinshoff, G. H. Fecher, S. Chadov, A. K. Nayak, B. Balke, S. Ouardi, T. Nakamura, and C. Felser, Half-metallic compensated ferrimagnetism with a tunable compensation point over a wide temperature range in the Mn-Fe-V-Al Heusler system, *AIP Adv.* 7 (2017) 105009.
- [58] T. Graf, C. Felser, S. S. P. Parkin, Simple rules for the understanding of Heusler compounds, *Prog. Solid. State Ch.* 39 (2011) 1-50.

- [59] T. Klimczuk, C. H. Wan, K. Gofryk, F. Ronning, J. Winterlik, G. H. Fecher, J. C. Griveau, E. Colineau, C. Felser, J. D. Thompson, D. J. Safarik, R. J. Cava, Superconductivity in the Heusler family of intermetallics, *Phys. Rev. B.* 85, (2012) 174505.
- [60] T. Bachaga, J. Zhang, M. Khitouni, J. J. Sunol, NiMn-based Heusler magnetic shape memory alloys: a review, *J. Adv. Manuf. Technol.* 103 (2019) 2761–2772.
- [61] M. J. Carey, S. Maat, S. Chandrashekariaih, J. A. Katine, W. Chen, B. York, J. R. Childress, Co₂MnGe-based current-perpendicular-to-the-plane giant-magnetoresistance spinvalve sensors for recording head applications, *J. Appl. Phys.* 109 (2011) 093912.
- [62] T. Marukame, T. Ishikawa, K. Matsuda, T. Uemura, M. Yamamoto, High tunnel magnetoresistance in fully epitaxial magnetic tunnel junctions with a full Heusler alloy Co₂Cr_{0.6}Fe_{0.4}Al thin film, *Appl. Phys. Lett.* 88 (2006) 262503.
- [63] H. L. Huang, J. C. Tung, G. Y. Guo, Anomalous Hall effect and current spin polarization in Co₂FeX Heusler compounds (X = Al, Ga, In, Si, Ge, and Sn): A systematic ab initio study, *Phys. Rev. B.* 91 (2015) 134409.
- [64] F. Ricci, S. Picozzi, A. Continenza, F. D’Orazio, F. Lucari, K. Westerholt, M. Kim, A. J. Freeman, Optical and magneto-optical properties of ferromagnetic full-Heusler films: Experiments and first-principles calculations, *Phys. Rev. B.* 76 (2007) 014425.
- [65] F. Casper, T. Graf, S. Chadov, B. Balke, C. Felser, Half-Heusler compounds: novel materials for energy and spintronic applications, *Semicond. Sci. Technol.* 27 (2012) 063001.
- [66] Y. Wang, X. Zhang, B. Ding, Z. Hou, E. Liu, Z. Liu, X. Xi, H. Zhang, G. Wu, W. Wang, Magnetic semiconductors based on quaternary Heusler compounds, *Comput. Mater. Sci.* 150 (2018) 321-324.

- [67] G. Xu, Y. You, Y. Gong, E. Liu, F. Xu, W. Wan, Highly dispersive spin gapless semiconductors in rare-earth-element contained quaternary Heusler compounds, *J. Phys. D: Appl. Phys.* 50 (2017) 105003.
- [68] S. N. Holmes, M. Pepper, Cobalt-Based Heusler Alloys for Spin-Injection Devices, *J. Supercond.* 16 (2003) 191-194.
- [69] B. Balke, S. Ouardi, T. Graf, J. Barth, C. G. F. Blum, G. H. Fecher, A. Shkabko, A. Weidenkaff, C. Felser, Seebeck coefficients of half-metallic ferromagnets, *Solid State Commun.* 150 (2010) 529-532.
- [70] T. M. Nakatani, N. Hase, H. S. Goripati, Y. K. Takahashi, T. Furubayashi, K. Hono, Co-Based Heusler Alloys for CPP-GMR Spin-Valves With Large Magnetoresistive Outputs, *IEEE Trans. Magn.* 48 (2012) 1751-1757.
- [71] C. S. Mejia, A. M. Gomes, L. A. S. Oliveira, A less expensive NiMnGa based Heusler alloy for magnetic refrigeration, *J. Appl. Phys.* 111 (2012) 07A923.
- [72] R. J. Quinn, J. W. G. Bos, Advances in half-Heusler alloys for thermoelectric power generation, *Mater. Adv.* 2 (2021) 6246.
- [73] A. L. Samuel, Some Studies in Machine Learning Using the Game of Checkers, *IBM J. Res. Dev.* 3 (1959) 210-229.
- [74] R. C. Fong, W. J. Scheirer, D. D. Cox, Using human brain activity to guide machine learning, *Sci. Rep.* 8 (2018) 5397.
- [75] M. Mohri, A. Rostamizadeh, A. Talwalkar, *Foundation of Machine Learning*, second edition, MIT press, Cambridge, (2018).

- [76] J. Carrete, W. Li, N. Mingo, Finding Unprecedentedly Low-Thermal-Conductivity Half-Heusler Semiconductors via High-Throughput Materials Modeling, *Phys. Rev. X.* 4 (2014) 011019.
- [77] S. Sanvito, C. Oses, J. Xue, A. Tiwari, M. Zic, T. Archer, P. Tozman, M. Venkatesan, M. Coey, S. Curtarolo, Accelerated discovery of new magnets in the Heusler alloy family, *Sci. Adv.* 3 (2017) e1602241.
- [78] K. Kim, L. Ward, J. He, A. Krishna, A. Agrawal, C. Wolverton, Machine-learning-accelerated high-throughput materials screening: Discovery of novel quaternary Heusler compounds, *Phys. Rev. Mater.* 2 (2018) 123801.
- [79] A. O. Oliynyk, E. Antono, T. D. Sparks, L. Ghadbeigi, M. W. Gaultois, B. Meredig, A. Mar, High-Throughput Machine-Learning Driven Synthesis of Full-Heusler Compounds, *Chem. Mater.* 28 (2016) 7324–7331.
- [80] Y. Zhang, X. Xu, Machine learning modeling of lattice constants for half-Heusler alloys, *AIP Advances.* 10 (2020) 045121.
- [81] N. A. Koshi, R. John, Half-Metallic Ferrimagnetism in CoFeNbZ ($Z = \text{Al, Si, Ge, Sn}$) Quaternary Heusler Alloys: a DFT Study, *J. Supercond. Nov. Magn.* 32 (2019) 977-986.
- [82] L. Bainsla, K. G. Suresh, Equiatomic quaternary Heusler alloys: a material perspective for spintronic applications, *Appl. Phys. Rev.* 3 (2016) 031101.
- [83] L. Xion, L. Yi, G. Y. Gao, Search for half-metallic magnets with large half-metallic gaps in the quaternary Heusler alloys CoFeTiZ and CoFeVZ ($Z = \text{Al, Ga, Si, Ge, As, Sb}$), *J. Magn. Mater.* 360 (2014) 98–103.

- [84] Q. Gao, L. Li, G. Lei, J. B. Deng, X. R. Hu, A first-principle study on the properties of a new series of quaternary Heusler alloys CoFeScZ ($Z = \text{P, As, Sb}$), *J. Magn. Magn. Mater.* 379 (2015) 288–293.
- [85] A. Q. Seh, D. C. Gupta, Quaternary Heusler alloys a future perspective for revolutionizing conventional semiconductor technology, *J. Alloys Compd.* 871 (2021) 159560.
- [86] S. Idrissi, H. Labrim, S. Ziti, L. Bahmad, Investigation of the physical properties of the equiatomic quaternary Heusler alloy CoYCrZ ($Z = \text{Si and Ge}$): a DFT study, *Appl. Phys. A.* 126 (2020) 190.
- [87] M. N. Rasool, S. Mehmood, M.A. Sattar, M. A. Khan, A. Hussain, Investigation of structural, electronic and magnetic properties of 1:1:1:1 stoichiometric quaternary Heusler alloys YCoCrZ ($Z = \text{Si, Ge, Ga, Al}$): An ab-initio study, *J. Magn. Magn. Mater.* 395 (2015) 97-108.
- [88] F. N. Gharbi, I. E. Rabah, M. Rabah, H. Rached, D. Rached, N. Benkhattou, F. Boukabrine, Theoretical Studies of the Structural, Electronic and Magnetic Properties of the CoFeCeZ ($Z = \text{P, As and Sb}$) Quaternary Heusler Alloys, *Spin*, 10, (2020) 2050002.
- [89] M. Shakil, H. Arshad, S. Aziz, S. S. A. Gillani, M. Rizwan, M. Zafar, Determination of phase stability, half metallicity, mechanical and thermal behavior of Fe based quaternary Heusler alloys, *J. Alloys Compd.* 856 (2021)157370.
- [90] M. I. Khan, H. Arshad, M. Rizwan, S. S. A. Gillani, M. Zafar, S. Ahmed, and M. Shakil, Investigation of structural, electronic, magnetic and mechanical properties of a new series of equiatomic quaternary Heusler alloys CoYCrZ ($Z = \text{Si, Ge, Ga, Al}$): A DFT study, *J. Alloys Compd.* 819 (2020) 152964.

- [91] M. A. Hossain, M. T. Rahman, M. Khatun, E. Haque, Structural, elastic, electronic, magnetic and thermoelectric properties of new quaternary Heusler compounds CoZrMnX ($X=\text{Al, Ga, Ge, In}$), *Comput. Condens. Matter.* 15 (2018) 31-41.
- [92] A. R. Chandra, V. Jain, N. Lakshmi, V. K. Jain, K. Soni, R. Jain, Electronic structure properties of new equiatomic CoCuMnZ ($Z=\text{In, Sn, Sb}$) quaternary Heusler alloys: an ab-initio study, *J. Alloys Compd.* 748 (2018) 298-304.
- [93] R. Paudel, J. Zhu, J. Structural, Electronic, Magnetic, Elastic, and Thermal properties of Co-based Equiatomic Quaternary Heusler alloys, *J. Magn. Magn. Mater.* 453 (2018) 10-16.
- [94] K. Benkaddour, A. Chahed, A. Amar, H. Rozale, A. Lakdja, O. Benhelal, A. Sayede, First-principles study of structural, elastic, thermodynamic, electronic and magnetic properties for the quaternary Heusler alloys CoRuFeZ ($Z = \text{Si, Ge, Sn}$), *J. Alloys Compd.* 687 (2016) 211-220.
- [95] M. W. Mohamedi, A. Chahed, A. Amar, H. Rozale, A. Lakdja, O. Benhelal, A. Sayede, Ab-initio study of structural, elastic, thermal, electronic and magnetic properties of quaternary Heusler alloys CoMnCrZ ($Z = \text{Al, As, Si, Ge}$), *Eur. Phys. J. B*, 89 (2016) 267.
- [96] S. Bahramian, and Ahmadian, Half-metallicity and magnetism of quaternary Heusler compounds CoRuTiZ ($Z=\text{Si, Ge, and Sn}$), *J. Magn. Magn. Mater.* 424 (2017) 122-129.
- [97] M. Shakil, H. Arshad, M. Zafar, M. Rizwan, S. S. A. Gillani, S. Ahmed, First-principles computation of new series of quaternary Heusler alloys CoScCrZ ($Z = \text{Al, Ga, Ge, In}$): a study of structural, magnetic, elastic and thermal response for spintronic devices, *Mol. Phys.* (2020) e1789770.
- [98] K. Jafari, F. Ahmadian, F. First-Principles Study of Magnetism and Half-Metallic Properties for the Quaternary Heusler Alloys CoRhYZ ($Y = \text{Sc, Ti, Cr, and Mn}$; $Z = \text{Al, Si, and P}$), *J Supercond Nov Magn.* (2017) 14.

- [99] R. Haleoot, B. Hamad, Ab Initio Investigations of the Structural, Electronic, Magnetic, and Thermoelectric Properties of CoFeCuZ ($Z = \text{Al, As, Ga, In, Pb, Sb, Si, Sn}$) Quaternary Heusler Alloys, *J. Electron. Mater.* 48 (2019) 1164-1173.
- [100] G. Forozani, A. A. M. Abadi, S. M. Baizae, A. Gharaati, Structural, electronic and magnetic properties of CoZrIrSi quaternary Heusler alloy: First-principles study, *J. Alloys Compd.* 815 (2020) 152449.
- [101] S. A. Khandy, First Principles understanding of Structural Electronic and Magnetic properties of new Quaternary Heusler alloy: FeVRuSi, *Mater. Res. Express.* 5 (2018) 056516.
- [102] Y. C. Gao, X. Gao, The half-metallicity of LiMgPdSn-type quaternary Heusler alloys FeMnScZ ($Z = \text{Al, Ga, In}$): A first-principle study, *AIP Adv.* 5 (2015) 057157.
- [103] L. Feng, J. Ma, Y. Yang, T. Lin, L. Wang, The Electronic, Magnetic, Half-Metallic and Mechanical Properties of the Equiatomic Quaternary Heusler Compounds FeRhCrSi and FePdCrSi: A First-Principles Study, *Appl. Sci.* 8 (2018) 2370.
- [104] P. L. Yan, J. M. Zhang, B. Zhou, K.W. Xu, The structural, electronic, magnetic and mechanical properties of quaternary Heusler alloys ZrTiCrZ ($Z = \text{Al, Ga, In, Si, Ge, Sn}$): a first-principles study, *J. Phys. D: Appl. Phys.* 49 (2016) 255002.
- [105] D. Rani, L. Bainsla, K. G. Suresh, A. Alam, Experimental and theoretical investigation on the possible half-metallic behaviour of equiatomic quaternary Heusler alloys: CoRuMnGe and CoRuVZ ($Z = \text{Al, Ga}$), *J. Magn. Magn. Mater.* 492 (2019) 165662.
- [106] A. Erkisi, An ab initio study on the structural, electronic and mechanical properties of quaternary full-Heusler alloys FeMnCrSn and FeMnCrSb, *Philos. Mag.* 98 (2018) 1656-1673.

- [107] Y. Han, M. Wu, M. Kuang, T. Tang, X. Chen, X. Wang, All-*d*-metal equiatomic quaternary Heusler hypothetical alloys ZnCdTMn (T = Fe, Ru, Os, Rh, Ir, Ni, Pd, Pt): A first-principle investigation of electronic structures, magnetism, and possible martensitic transformations, *Results Phys.* 11 (2018) 1134-1141.
- [108] M. N. Rasul, A. Javed, M. A. Khan, M. A. Hussain, Study of the structural, mechanical, electronic and magnetic properties of quaternary YFeCrX (X = Al, Ga, In, Si, Ge, Sn, P, As, Sb) Heusler alloys, *J. Magn. Magn. Mater.* 476 (2019) 398-411.
- [109] S. Singh, D. C. Gupta, Magneto-electronic, thermoelectric, thermodynamic and optical properties of rare earth YCoTiX (X = Al, Ga, Si, Ge) alloys, *J. Alloys Compd.* 806 (2019) 1292-1308.
- [110] X. Wang, Z. Cheng, R. Guo, J. Wang, H. Rozale, L. Wang, Z. Yu, G. Liu, First-principles study of new quaternary Heusler compounds without 3d transition metal elements: ZrRhHfZ (Z = Al, Ga, In), *Mater. Chem. Phys.* 193 (2017) 99-108.
- [111] R. Guo, G. Liu, X. Wang, H. Rozale, L. Wang, R. Khenata, Z. Wu, X. Dai, First-principles study on quaternary Heusler compounds ZrFeVZ (Z = Al, Ga, In) with large spin-flip gap, *RSC Adv.* 6 (2016) 109394-109400.
- [112] X. Wang, Z. Cheng, G. Liu, X. Dai, R. Khenata, L. Wang, A. Bouhemadou, Rare earth based quaternary Heusler compounds MCoVZ (M = Lu, Y; Z = Si, Ge) with tunable band characteristics for potential spintronic applications, *IUCrJ*, 4 (2017) 758-768.
- [113] K. Ozdogan, E. Sasioglu, I. Galanakis, Slater-Pauling behavior in LiMgPdSn-type multifunctional quaternary Heusler materials: Half-metallicity, spin-gapless and magnetic semiconductors, *J. Appl. Phys.* 113 (2013) 193903.

- [114] Q. Gao, H. H. Xie, G. Lei, J. B. Deng, X. R. Hu, First-principle study on some new spin-gapless semiconductors: The Zr-based quaternary Heusler alloys, *Superlattices Microstruct.* 85 (2015) 536–542.
- [115] S. Berri, M. Ibrir, D. Maouche, M Attallah, First principles study of structural, electronic and magnetic properties of ZrFeTiAl, ZrFeTiSi, ZrFeTiGe and ZrNiTiAl, *J. Magn. Magn. Mater.* 371 (2014) 106-111.
- [116] T. Samanta, S. Chaudhuri, S. Singh, V. Srihari, A. K. Nigam, P. A. Bhobe, Structural, electronic, magnetic, and transport properties of the equiatomic Ni-based quaternary Heusler alloys, *J. Alloys Compd.* 819 (2020) 153029.
- [117] N. Karimian, F. Ahmadian, Electronic structure and half-metallicity of new quaternary Heusler alloys NiFeTiZ (Z= Si, P, Ge, and As), *Solid State Commun.* 223 (2015) 60-66.
- [118] M. Halder, M. D. Mukadam, K. G. Suresh, S. M. Yusuf, Electronic, structural, and magnetic properties of the quaternary Heusler alloy NiCoMnZ (Z= Al, Ge, and Sn), *J. Magn. Magn. Mater.* 377 (2015) 220-225.
- [119] V. Alijani, J. Winterlik, G. H. Fecher, S. S. Naghavi, C. Felser, Quaternary half-metallic Heusler ferromagnets for spintronics applications, *Phys. Rev. B.* 83 (2011) 184428.
- [120] S. Singh, D. C. Gupta, Lanthanum based quaternary Heusler alloys LaCoCrX (X= Al, Ga): Hunt for half-metallicity and high thermoelectric efficiency, *Results Phys.* 13 (2019) 102300.
- [121] A. Q. She, D. C. Gupta, Comprehensive DFT investigation of transitionmetal-based new quaternary Heusler alloys CoNbMnZ (Z = Ge, Sn): compatible for spindependent and thermoelectric applications, *RSC Adv.* 10 (2020) 43870.

- [122] N. A. Koshi, R. John, First principles study on the structural, electronic, magnetic and thermoelectric properties of $\text{CoX}^{\prime}\text{NbGa}$ ($X^{\prime} = \text{Cr, Mn, Fe}$) quaternary Heusler alloys, *Eur. Phys. J. B.* 92 (2019) 86.
- [123] H. L. Huang, J. C. Tung, H. T. Jeng, A first-principles study of rare earth quaternary Heusler compounds: RXVZ ($R = \text{Yb, Lu}$; $X = \text{Fe, Co, Ni}$; $Z = \text{Al, Si}$), *Phys. Chem. Chem. Phys.* 23, (2021) 2264.
- [124] Z. Haque, G. S. Thakur, S. Ghara, L. C. Gupta, A. Sundaresan, A. K. Ganguli, Structural and magnetic properties of a new and ordered quaternary alloy MnNiCuSb (SG: $\overline{\text{F43m}}$), *J. Magn. Magn. Mater.* 397 (2016) 315-318.
- [125] R. B. Ray, G. C. Kaphle, R. K. Rai, D. K. Yadav, R. Paudel, D. Paudyal, Strain induced electronic structure, and magnetic and structural properties in quaternary Heusler alloys ZrRhTiZ ($Z = \text{Al, In}$), *J. Alloys Compd.* 867 (2021) 158906.
- [126] W. Liu, X. Zhang, H. Jia, R. Khenata, X. Dai, G. Liu, Theoretical Investigations on the Mechanical, Magneto-Electronic Properties and Half-Metallic Characteristics of ZrRhTiZ ($Z = \text{Al, Ga}$) Quaternary Heusler Compounds, *Appl. Sci.* 9 (2019) 883.
- [127] Y. Ma, H. Hao, Y. Xin, H. Luo, H. Liu, F. Meng, E. Liu, Atomic ordering and magnetic properties of quaternary Heusler alloys NiCuMnZ ($Z = \text{In, Sn, Sb}$), *Intermetallics*. 86 (2017) 121-125.
- [128] A. Afaq, Shanian, A. Bakar, First-Principles Study for Structural, Elastic and Mechanical Properties of CuCoMnZ ($Z = \text{Si, Sn, Sb}$) Heusler Alloys, *Mater. Res. Express*. 6 (2019) 026522.
- [129] S. Idrissi, H. Labrim, S. Ziti, L Bahmad, A DFT study of the equiatomic quaternary Heusler alloys ZnCdXMn ($X = \text{Pd, Ni or Pt}$), *Solid State Commun.* 331 (2021) 114292.

- [130] M. Mushtaq, M. A. Sattar, S. A. Dar, I. Qasim, I. Muhammad, Search for half-metallicity in new ferrimagnetic quaternary $MnXMoAl$ ($X = Co$ and Ti) Heusler alloys: A DFT based investigation, *Mater. Chem. Phys.* 245 (2020) 122779.
- [131] M. N. Rasul, A. Javed, M. A. Khan, A. Hussain, Structural stability, mechanical, electronic and magnetic behaviour of quaternary $ScNiCrX$ ($X = Al, Ga$) Heusler alloys under pressure, *Mater. Chem. Phys.* 222 (2019) 321-332.
- [132] X. Wang, H. Khachai, R. Khenata, H. Yuan, L. Wang, W. Wang, A. Bouhemadou, L. Hao, X. Dai, R. Guo, G. Liu, Z. Cheng, Structural, electronic, magnetic, half-metallic, mechanical, and thermodynamic properties of the quaternary Heusler compound $FeCrRuSi$: A first-principles study, *Sci. Rep.* 7 (2017) 16183.
- [133] S. A. Dine, G. S. Pomrehn, A. P. Jones, K. J. Laws, L. Bassman, First-principles investigation of structural and magnetic disorder in $CuNiMnAl$ and $CuNiMnSn$ Heusler alloys, *Phys. Rev. B.* 95 (2017) 024108.
- [134] P. L. Yan, J. M. Zhang, K. W. Xu, The structural, electronic and magnetic properties of quaternary Heusler alloy $TiZrCoIn$, *Solid State Commun.* 231-232 (2016) 64-67.
- [135] M. H. Elahmar, H. Rached, D. Rached, R. Khenata, G. Murtaza, S. B. Omran, W. K. Ahmed, Structural, mechanical, electronic and magnetic properties of a new series of quaternary Heusler alloys $CoFeMnZ$ ($Z = Si, As, Sb$): A first principle study, *J. Magn. Mater.* 393, (2015) 165-174.
- [136] S. S. Shapiro, M. B. Wilk, An analysis of variance test for normality (complete samples), *Biometrika*, 52 (1965) 591.
- [137] L. Breiman, Random Forests, *Mach. Learn.* 45 (2001) 5-32.

- [138] V. Svetnik, A. Liaw, C. Tong, J. C. Culberson, R. P. Sheridan, B. P. Feuston, Random Forest: A Classification and Regression Tool for Compound Classification and QSAR Modeling, *J. Chem. Inf. Comput. Sci.* 43 (2003) 1947-1958.
- [139] R. Genuer, J. M. Poggi, Random Forest with R, Springer, (2020).
- [140] F. Pedregosa, G. Varoquaux, A. Gramfort, V. Michel, B. Thirion, O. Grisel, M. Blondel, P. Prettenhofer, R. Weiss, V. Dubourg, J. Vanderplas, A. Passos, D. Cournapeau, M. Brucher, M. Perrot, E. Duchesnay, Scikit-learn: Machine Learning in Python, *J. Machine Learn. Res.* 12 (2011) 2825–2830.
- [141] T. Hastie, R. Tibshirani, J. Friedman, The Elements of Statistical Learning: Data Mining, Inference, and Prediction, Second edition, Springer, (2009) 587-604.
- [142] B. Gregorutti, B. Michel, P. S. Pierre, Correlation and variable importance in random forests, *Stat. Comput.* 27 (2017) 659-678.
- [143] U. Gromping, Variable Importance Assessment in Regression: Linear Regression versus Random Forest, *Am. Stat.* 63 (2009) 308-319.
- [144] R. Genuer, J. M. Poggi, C. T. Malot, Variable selection using random forests, *Pattern Recognit. Lett.* 31, (2010) 2225-2236.
- [145] I. Galanakis, Heusler Alloys: Properties, Growth, Applications, Springer Series in Material Science. 222 (2016) p-4.
- [146] S. Mitra, A. Ahmad, S. Chakrabarti, S. Biswas, A. Das, Investigation on structural, electronic and magnetic properties of Co_2FeGe Heusler alloy: Experiment and theory, *J. Magn. Magn. Mater.* 2022, 552, 169148.

[147] S. Mitra, A. Ahmad, S. Chakrabarti, S. Biswas, A. Das, Study of structural, electronic, magnetic and vibrational properties of CoFeTiSi quaternary Heusler alloy, Phys. B: Condens. Matter. 640 (2022) 413878.