

Charge-density wave fluctuation driven composite order in the layered Kagome Metals

Alexei M. Tsvelik¹ and Saheli Sarkar¹

¹*Division of Condensed Matter Physics and Materials Science,
Brookhaven National Laboratory, Upton, NY 11973-5000, USA*

The newly discovered kagome metals AV_3Sb_5 ($A = K, Rb, Cs$) offer an exciting route to study exotic phases arising due to interplay between electronic correlations and topology. Besides superconductivity, these materials exhibit a charge-density wave (CDW) phase occurring at around 100 K, whose origin still remains elusive. The robust multi-component 2×2 CDW phase in these systems is of great interest due to the presence of an unusually large anomalous Hall effect. In quasi-2D systems with weak inter-layer coupling fluctuation driven exotic phases may appear. In particular in systems with multi-component order parameters fluctuations may lead to establishment of composite order when only products of individual order parameters condense while the individual ones themselves remain disordered. We argue that such fluctuation-driven regime of composite CDW order may exist in thin films of kagome metals above the CDW transition temperature. We also find that the transition from the composite to individual CDW order is in the \mathbb{Z}_3 Potts universality class. Our findings suggest possible presence of exotic phases in the weakly coupled layered kagome metals, more so in the newly synthesized thin films of kagome metals.

I. INTRODUCTION

The interplay between electronic correlations and topology is a major field of study in the condensed matter systems.^{1,2} The recently discovered kagome metals AV_3Sb_5 with ($A = K, Rb, Cs$) are quasi-two dimensional (2D) system with hexagonal lattice symmetry.³ The band structure of the kagome metals exhibit a flat band, saddle-point van Hove singularities (vHSs) and a pair of Dirac points. Owing to such an electronic structure, these systems have created a new platform to study exotic phases which can occur due to presence of both correlations and topology.^{4,5}

All of the AV_3Sb_5 undergo a charge-density-wave (CDW) transition⁶⁻¹⁰ at around temperature $T_{CDW} \sim 100$ K. Along with the emergence of the CDW order, experiments and theoretical studies have found different unusual properties, such as bond density modulations,¹¹ a chiral flux phase,^{12,13} a giant anomalous Hall effect¹⁴⁻¹⁶ with time-reversal symmetry breaking,¹⁷⁻²⁰ which can be associated with loop currents.²¹⁻²³

At much lower temperatures these materials may exhibit superconductivity^{4,24-26} with $T_c \sim 1$ K. The nature of the superconducting phase is still under debate. Some experiments found the gap to be nodeless,²⁷ some to contain nodes.²⁸ Theoretical studies suggest unconventional nature of the superconductivity.²⁹⁻³³ There have been also proposals of more exotic superconductivity like pair-density wave,^{34,35} charge 4e and charge 6e superconducting states³⁵ and nematicity.³⁶⁻³⁸

There have been a great amount of works³⁹⁻⁴⁴ to gain insight into the nature of the CDW phase. So far it is well established that the CDW order of the kagome metals is a multicomponent (3Q) one. Moreover, the CDW order doubles the unit cell in the (a,b) plane and hence has a robust 2×2 feature as found in scanning tunneling-microscopy (STM),⁶ angle-resolved photoemission spectroscopy (ARPES)⁴⁵ and X-ray⁴⁶ experiments. However, some X-ray and STM experiments found a modulation in the crystallographic c- direction for the kagome metals with alkali atoms Rb and Cs. The simultaneous ordering of CDW phase with commensu-

rate momenta $3Q$ are believed to be driven by nested Fermi surface instabilities,^{29,47-49} enhanced through the presence of vHS due to logarithmically diverging density of states at the vHS points⁵⁰ in two dimensions. In this paper we explore the situation²⁹ of $5/12$ filled band when the chemical potential lies at the van Hove singularity.

According to the Mermin -Wagner theorem⁵¹ fluctuations are enhanced in low dimensions. The presence of strong fluctuations is well established in such quasi-2D systems as cuprates, iron based superconductors⁵² where they are responsible for pseudogap phase,⁵³⁻⁵⁵ anomalous phonon softening⁵⁶ and also different emergent orders.⁵⁷⁻⁵⁹ These prototype examples indicate that fluctuations may also play an important role in the layered quasi-2D kagome metal materials. However, as of now, although several theoretical works have considered a mean-field scenario of the CDW order parameters, the effect of fluctuations in kagome CDW metals has not been discussed. Their effect will become even more important in the kagome metal mono-layers⁶⁰ and thin films.⁶¹⁻⁶³

In this paper, we go beyond the mean-field theory of the multi-component CDW order and consider the fluctuations in these orders within a Ginzburg-Landau (GL) free energy model. As its microscopic justification we consider an effective low energy theory⁴⁷ described by the patch model considering only the V atoms of AV_3Sb_5 , giving rise to vHS at the three M points in the Brillouin zone. We find that there an interval of temperatures above the CDW phase transition where only a composite order of the three CDWs can exist while the individual CDW order parameters remain fluctuating. The latter ones condense at low temperatures through a transition of the 3 -state Potts model universality class.⁶⁴

We organize the rest of the paper as follows. In Section II, we present our working microscopic model which includes the interactions in the system, giving rise to the electronic CDW instability. Then, in Section III, we perform the mean field analysis of the CDW orders. In Section IV, we consider fluctuations of the CDW order parameters and present a GL free energy by incorporating the vortex configurations by means of dual fields. In Section V, we consider a simplified case, where only two CDW orders develop. We discuss




FIG. 1: The hexagonal Brillouin zone, showing the high symmetry points. AV_3Sb_5 exhibit saddle points at the $\mathbf{M}_{1,2,3}$, shown by green and blue circles. The \mathbf{M}_a points are connected by the three nesting vectors $\mathbf{Q}_{1,2,3}$, which are also the ordering wave-vectors of the CDW.

appearance of the composite order in this model. At last we give a conclusion of our work in Section VI.

II. MODEL

The goal of our work is to describe fluctuations in the CDW regime of Kagome metals described by the patch model adopted by T. Park *et.al.*⁴⁷ A similar model leading to the same Ginzburg-Landau energy was used in.¹¹ Both models consider just one vanadium orbital per site of the kagome lattice. The CDW order is believed to be electronically driven. However, there are some experiments which point to the role of phonons.⁶⁵

First principle calculations^{4,66,67} for the kagome metals AV_3Sb_5 show saddle points at the \mathbf{M}_a points of the hexagonal Brillouin zone, giving rise to the logarithmically divergent density of states. Hence we consider an effective low-energy model which takes into account only patches of the Fermi surface around the \mathbf{M}_a points in the Brillouin zone [Fig. 1] of kagome metals AV_3Sb_5 and interactions among the fermionic states between these saddle points as was done by T. Park paper.⁴⁷

The non-interacting Hamiltonian is given by

$$H_0 = \sum_{a=1}^3 \sum_{|k| < \Lambda} c_{a\sigma}^\dagger(k) [\epsilon_a(k) - \mu] c_{a\sigma}(k), \quad (1)$$

where the single electron dispersion close to the saddle points \mathbf{M}_a are given by,

$$\begin{aligned} \epsilon_1 &= k_1(k_1 + k_2), \\ \epsilon_2 &= -k_1 k_2, \\ \epsilon_3 &= k_2(k_1 + k_2), \\ k_{1,2} &= k_x \pm \sqrt{3}k_y, \end{aligned} \quad (2)$$

and μ is the chemical potential. Now, we consider electron-electron interactions among the fermions in the three patches close to the \mathbf{M}_a saddle points.

$$\begin{aligned} H_{int} = & \sum_{a \neq b} \sum_{k_1, k_2, k_3, k_4} \left[g_1 (c_{a, k_1, \sigma}^\dagger c_{b, k_4, \sigma}) (c_{b, k_2, \sigma'}^\dagger c_{a, k_3, \sigma'}) + \right. \\ & g_2 (c_{a, k_1, \sigma}^\dagger c_{a, k_4, \sigma}) (c_{b, k_2, \sigma'}^\dagger c_{b, k_3, \sigma'}) + \\ & \left. g_3 (c_{a, k_1, \sigma}^\dagger c_{a, k_2, -\sigma}) (c_{b, k_3, -\sigma}^\dagger c_{b, k_4, \sigma}) \right] \\ & + \sum_a \sum_{k_1, k_2, k_3, k_4} g_4 (c_{a, k_1, \sigma}^\dagger c_{a, k_4, \sigma}) (c_{a, k_2, -\sigma}^\dagger c_{a, k_3, -\sigma}). \end{aligned} \quad (3)$$

The total effective Hamiltonian is given by

$$H = H_0 + H_{int} \quad (4)$$

In the Hamiltonian, $a = 1, 2, 3$ are the patch indices and \mathbf{k} is momentum measured from the \mathbf{M}_a . In the Eqn.(3), we have the constraint $\mathbf{k}_1 + \mathbf{k}_2 + \mathbf{k}_3 + \mathbf{k}_4 = 0$. The coupling constants g_1, g_2, g_3 and g_4 represent interpatch exchange, interpatch density-density, Umklapp and intra-patch scattering terms respectively.

The parquet renormalization group (pRG) analysis⁴⁷ suggests that an instability in the system occurs if the corresponding interaction strength becomes positive. For our work, we are interested only in various charge-density wave (CDW) instabilities. We do not consider⁴⁷ interplay between the superconductivity and the CDW, as the superconductivity appears only at very low temperature. Now one can construct the following CDW type order parameters in the patch model.

For the real CDW (rCDW), and imaginary CDW (iCDW), the order parameters are respectively,

$$\Omega_a \sim G_1 \sum_{k, \sigma} \langle c_{a2k}^\dagger c_{a3k'} \rangle, \quad (5)$$

$$\Psi_a \sim \frac{G_2}{i} \sum_{k, \sigma} \langle c_{a2k}^\dagger c_{a3k'} \rangle. \quad (6)$$

The effective interaction strengths for the rCDW and iCDW are $G_1 = -2g_1 + g_2 - g_3$ and $G_2 = -2g_1 + g_2 + g_3$ respectively. Moreover, $\mathbf{k}' = \mathbf{k} + \mathbf{Q}_a$. \mathbf{Q}_a are the three nesting vectors connecting the \mathbf{M}_a and the ordering wave-vectors for the CDW order parameters as shown in the Fig. 1.

The interactions are assumed to be quasi-local with Λ being the UV cut-off. The Hamiltonian is $SU(2) \times Z_3 \times U(1)$ invariant.

III. MEAN FIELD THEORY

In this section we perform a mean-field decoupling of the Eqn.(4) in the CDW channels. This already suggests that we have $g_4 = 0$, as the effective interactions for rCDW and iCDW do not depend on g_4 . We keep both the rCDW and iCDW and

derive a mean-field Hamiltonian and a GL free energy in terms of a complex CDW order parameters.

If the leading interaction term is g_1 , one can perform the Hubbard-Stratonovich transformation,

$$H_{mf} = |V_{ab}|^2/2g_1 + \sum_{a>b} [V_{ab}c_{a\sigma}^+c_{b\sigma} + V_{ab}^*c_{b\sigma}^+c_{a\sigma}] + \sum_{a=1}^3 \sum_{|k|<\Lambda} \epsilon_a(k)c_{a\sigma}^+(k)c_{a\sigma}(k). \quad (7)$$

We introduce notations $V_{12} = \Delta_3$, $V_{13} = \Delta_2$, $V_{23} = \Delta_1^*$. Now, by integrating out the fermion field, we obtain the action in terms of the CDW order parameter fields $\Delta_a = \Omega_a + i\Psi_a = |\Delta_a|e^{i\phi_a}$:

$$F = \frac{1}{2g_1} \int d^2x d\tau |\Delta_a|^2 - \text{Tr} \ln \mathcal{G}^{-1}, \quad (8)$$

where \mathcal{G}^{-1} is the inverse Green's function matrix. The electronic spectrum at the saddle point is determined by the equation:

$$\begin{vmatrix} -E + \epsilon_1 & \Delta_3 & \Delta_2 \\ \Delta_3^* & -E + \epsilon_2 & \Delta_1^* \\ \Delta_2^* & \Delta_1 & -E + \epsilon_3 \end{vmatrix} = 0, \quad (9)$$

The result is

$$(\epsilon_1 - E)(\epsilon_2 - E)(\epsilon_3 - E) + E(|\Delta_1|^2 + |\Delta_2|^2 + |\Delta_3|^2) - \epsilon_1|\Delta_1|^2 - \epsilon_2|\Delta_2|^2 - \epsilon_3|\Delta_3|^2 + \Delta_1\Delta_3\Delta_2 + \Delta_1^*\Delta_2^*\Delta_3^* = 0. \quad (10)$$

We assume that the fluctuations of moduli are gapped and consider the saddle point where all $|\Delta_a|$ are equal. It follows from Eqn.(2) that

$$\epsilon_1\epsilon_2 + \epsilon_1\epsilon_3 + \epsilon_2\epsilon_3 = 0, \quad (11)$$

which leads to simplification of Eqn.(10) resulting in

$$(E \pm 1)^2(E \mp 2) - 3(k_x^2 + k_y^2)(E^2 - 1) + 4k_x^2(k_x^2 - 3k_y^2)^2 = 0. \quad (12)$$

where we set $|\Delta_a| = 1$. According to,⁶⁸ plus sign in the first bracket corresponds to the $-3Q$ phase. In this phase there is a Fermi surface [see Fig. 2]. The minus sign corresponds to the $+3Q$ phase where the quasiparticle spectrum is fully gapped. At $g_3 \neq 0$, the mean-field spectrum should be corrected :

$$\Delta_a \rightarrow \Delta_a + (g_3/g_1)\Delta_a^*, \quad (13)$$

This change does not modify the spectrum qualitatively though it modifies the Green's function.




FIG. 2: Contour plots of the gapless quasiparticle branch in the $-3Q$ phase. The Fermi surface is the boundary between the grey and the brown areas.

IV. GINZBURG-LANDAU FREE ENERGY

We will follow the conclusions of the previous papers and, as we have mentioned above, consider the saddle point solution with all $|\Delta_a|$ being equal and treat fluctuations of the moduli of Δ 's as gapped. Hence the subsequent analysis of the GL free energy will include only phase fluctuations. In the absence of the Umklapp $g_3 = 0$ the only phase dependent term in the free energy density corresponds to the product of all three Δ 's:

$$\delta F = -G \cos(\phi_1 + \phi_2 + \phi_3). \quad (14)$$

Hence in the absence of the Umklapp two phase fields remain critical in the low - temperature phase. However, if $g_3 \neq 0$ there is a contribution to the free energy density:

$$g_3 [\Delta_a^2 + (\Delta_a^*)^2] \sim g_3 [\cos(2\phi_1) + \cos(2\phi_2) + \cos(2\phi_3)] \quad (15)$$

A. Fluctuations in the CDW order parameters

Now we will consider phase fluctuations of the CDW order parameters which requires inclusion of the gradient terms. To properly account for topologically nontrivial configurations of the phase fields (vortices) we regularize the model by putting it on a suitable lattice with lattice constant b and then taking a continuum limit.

The form of the free energy functional Eqn.(16) reflects the fact that the order parameters are periodic functions of ϕ_a . This feature allows for topologically nontrivial configurations of the fields in the form of vortices - configurations where ϕ_a fields change by 2π along closed spacial loops. In the continuum limit such configurations are singular which explains the necessity for lattice regularization. It is well known that in 2D vortices can change a character of phase transitions. One way

to take them into account in the continuous limit is to introduce dual phase fields $\bar{\phi}_a$.⁶⁹ In the present case is slightly unusual because in the region of interest the GL action contains the terms which depend on both ϕ and $\bar{\phi}$. The corresponding formalism was introduced in⁷⁰ (see also⁵⁸). The regularized GL free energy density is

$$\mathcal{F}/T = -\frac{J}{T} \sum_a \sum_{\langle b \rangle} \frac{1}{b^2} \cos [\phi_a(\mathbf{x}) - \phi_a(\mathbf{x} + \mathbf{b})] - G \cos(\phi_1 + \phi_2 + \phi_3) + Ag_3 \sum_a \cos(2\phi_a), \quad (16)$$

where coefficient $A \sim \Delta^2/T > 0$.

Now we can follow the standard procedure and write down the the continuum limit of Eqn.(16) as (in what follows we will set the stiffness $J = 1$):

$$\mathcal{F}/T = \sum_a \left[\frac{1}{2T} (\partial_x \phi_a)^2 + \frac{T}{2} (\partial_x \bar{\phi}_a)^2 + i \partial_x \phi_a \partial_y \bar{\phi}_a + Ag_3 \cos(2\phi_a) + \eta \cos(2\pi \bar{\phi}_a) \right] - G \cos(\phi_1 + \phi_2 + \phi_3). \quad (17)$$

The coupling η is proportional to the vortex fugacity. The model Eqn.(17) contains both original fields ϕ_a and their dual fields $\bar{\phi}_a$ which take care of the vortex configurations. The corresponding path integral for the partition function includes integration over both fields:

$$Z = \int D\phi_a(x) D\bar{\phi}_a(x) \exp \left(- \int d^2x \mathcal{F}/T \right). \quad (18)$$

To determine whether the cosine terms are relevant or irrelevant, one has to calculate their scaling dimensions. To compute the scaling dimensions of various perturbations, we start with the Gaussian model. The results are

$$d_{g_3} = T/\pi, \quad d_\eta = \pi/T, \quad d_G = 3T/4\pi, \quad (19)$$

The direct and dual operators cannot order simultaneously which creates an interesting situation at the transition where both of them are relevant. It is a nontrivial situation, see, for example.⁵⁸

In what follows we consider a limit of large G when the sum of all phases is fixed.³¹ Now, we can make a transformation as follows:

$$\phi_a = \Phi/\sqrt{3} + (\sqrt{2/3})\mathbf{e}_a \chi, \quad \mathbf{e}_a = (1, 0), (-1/2, \sqrt{3}/2), (-1/2, -\sqrt{3}/2). \quad (20)$$

with $\chi = (\chi_1, \chi_2)$ and treat Φ as gapped.

In this case we get following the calculation shown in Ap-




FIG. 3: The appearance of the composite order: The figure shows the phase transition in the layered kagome metals due to the phase fluctuations in the CDW orders. For $J=1$, the composite order develops at $\frac{T}{\pi} = \frac{8}{3}$, where the sum of the phases are frozen. This order breaks the lattice-translational symmetry. Then, there is a second phase transition around $\frac{T}{\pi} = \sqrt{3}$, below which individual CDW's order. For $g_3 > 0$ the low temperature phase breaks time-reversal symmetry.

pendix A, an effective free energy:

$$\mathcal{F}_{eff}/T = \sum_{a=1}^3 \left[\bar{A}g_3 \cos(\sqrt{8/3}\mathbf{e}_a \chi) - B \cos(2\pi\sqrt{2}\omega_a \bar{\chi}) \right] + \sum_{i=1,2} \left[\frac{1}{2T} (\partial_x \chi_i)^2 + \frac{T}{2} (\partial_x \bar{\chi}_i)^2 + i \partial_x \chi_i \partial_y \bar{\chi}_i \right], \quad (21)$$

where $\omega_a = (0, 1), (\sqrt{3}/2, 1/2), (\sqrt{3}/2, -1/2)$, $B \sim \eta^2$ and $\bar{A} = \langle \cos(\Phi/\sqrt{3}) \rangle > A$.

The scaling dimensions of the cosines are

$$d_{g_3} = 2T/3\pi, \quad d_B = 2\pi/T \quad (22)$$

The perturbations are relevant or irrelevant when the scaling dimension of the operators $d_{op} < D$ and $d_{op} > D$ respectively, D being the spatial dimension of the system. We observe that below $T/\pi = 3$ both direct and dual cosine terms are relevant provided the G -term is relevant which is true for $T/\pi < 8/3$.

Below $T_{c1}/\pi = 8/3$, the G -term is relevant and the sum of all phases is frozen. However, the vortices destroy the order of individual CDWs. Only the product of their order parameters acquires a finite average, which we refer as a composite order $(\Delta_1 \Delta_2 \Delta_3)$ [see Fig. 3]. It does break translational symmetry, but no other.

There is a second phase transition in a phase where individual phases are frozen [see Fig. 3]. The character of the low temperature phase is determined by the sign of g_3 . If $g_3 < 0$ the vacuum corresponds to $\chi_1 = \chi_2 = 0$. This is $rCDW$ - real CDWs. If $g_3 > 0$ there are degenerate vacua situated on a hexagonal lattice of $\chi_{1,2}$. There are two inequivalent points $\sqrt{8/3}(\chi_1, \chi_2) = (4\pi/3, 0)$ and $(2\pi/3, 2\pi/\sqrt{3})$. At each of these vacua all Δ_a 's are the same and are equal either to $\exp(4\pi i/3)$ or its complex conjugate. In the broken sym-

metry state one of this vacua is chosen which corresponds to complex $rCDW + iCDW$ with a broken time-reversal.

The second transition temperature is determined by the competition between normal and dual cosine perturbations. It can be estimated by comparing the mass scales generated by the competing operators. A relevant perturbation can drive a phase transition and the transition point can be determined by estimating the scale of mass gaps in the corresponding phases and comparing them with each other. The scale of the mass gap can be estimated by the fact that the contribution to the action of the relevant operator inducing a finite correlation length, becomes of the order of unity. Therefore, we notice that the phase transition from the composite order state to the state with individual CDWs occurs when

$$B^{1/(2-d_B)} \sim (\bar{A}g_3)^{1/(2-d_{g_3})}. \quad (23)$$

Solving this equation with logarithmic accuracy we get the estimate for the transition temperature:

$$T_{c2}/\pi = \frac{3}{2} \left(1 - \alpha + \sqrt{1 - 2\alpha/3 + \alpha^2} \right), \quad \alpha = \frac{\ln(\bar{A}g_3)}{\ln B}. \quad (24)$$

For comparable coupling constants it yields $T_{c2}/\pi = \sqrt{3}$ and $d^* = 2/\sqrt{3}$.

As we have said, below T_{c2} , the individual Δ 's order. Following the results of a very similar model,⁷¹ we argue that the transition in our theory where individual Δ 's order belongs to the \mathbb{Z}_3 Potts universality class. The critical exponents at the critical point of the phase transition are $\nu = \frac{5}{6}$, $\eta = \frac{4}{15}$.⁷²

V. SIMPLIFIED CASE

The purpose of this section is to study an example of a treatable model describing a phase transition driven by mutually dual cosines. This model describes the case when only two CDWs develop: $\Delta_3 = 0$, $|\Delta_1| = |\Delta_2|$, describing a nematicity³⁸ in the system. Then there are two phases ϕ_1 and ϕ_2 , whose fluctuations are described by action Eqn.(16). Once there sum is frozen we arrive at model (Eqn.(A7)) with a single pair of fields $\chi, \bar{\chi}$. This situation was studied in⁵⁸ repeat the calculations here for illustrative purposes.

In this case at $T/\pi = 1$ the scaling dimensions of the cosines are equal to 1, giving rise to comparable values of $\bar{A}g_3$ and B . At this point, the bosonic action (Eqn.(A7)) can be reformionized and recast as a model of relativistic fermions with two kinds of mass terms:⁷³

$$\mathcal{F}_{eff}/T = R^+(\partial_y - i\partial_x)R + L^+(\partial_y + i\partial_x)L + \bar{A}g_3(R^+L + L^+R) + B(RL + L^+R^+). \quad (25)$$

The next step is to express the Dirac fermions in terms of Majoranas:

$$R, L = \frac{1}{\sqrt{2}}[\rho_{R,L}^{(+)} + i\rho_{R,L}^{(-)}]. \quad (26)$$

As a result we get two separate models for Majorana fermions with masses $m_{\pm} = \bar{A}g_3 \pm B$. Each Majorana species corresponds to 2D Ising model where the mass is proportional to $(T - T_c)$. For any sign of g_3 the transition occurs only for one Majorana species. As was shown in⁵⁸ the CDW order parameter (for instance, Δ_1 , since in the given case $\Delta_2 = \Delta_1^*$) can be written as

$$\Delta = i\sigma_+\sigma_- + \mu_+\mu_-, \quad (27)$$

where σ_{\pm} are the order and μ_{\pm} are the disorder parameters of the Ising models with masses m_{\pm} . One of these models is always in the ordered $\langle \sigma \rangle \neq 0$ or disordered ($\langle \mu \rangle \neq 0$) phase, the other one undergoes a phase transition. It can be shown that in the part of the phase diagram where $m_{\pm} > 0$, the expectation value of $\sigma_{1/2}$ is non vanishing, whereas average of $\mu_{1/2}$ vanishes. Also, for $m_{\pm} < 0$, the average of σ_{\pm} vanishes, while average of μ_{\pm} becomes finite.

The \mathbb{Z}_3 symmetric case is more complicated. As was demonstrated in,⁷¹ at the transition point theory (A7) can be represented as a sum of the critical \mathbb{Z}_3 Potts model and a W_3 Conformal Field Theory perturbed by a relevant operator:

$$H = H_{\mathbb{Z}_3}^0 + H_{W_3}^0 - \gamma\Phi_{\lambda_1+\lambda_2,0}, \quad (28)$$

where λ 's are fundamental weights of the SU(3) group. The latter theory is massive.

VI. CONCLUSIONS

In this work we have studied a fluctuation regime in the CDW order, within an effective low energy interacting patch model.⁴⁷ We study the fluctuation by considering a field theoretic technique where both the discrete symmetry breaking order and the vortex physics interact with each other in two dimensions. We observe that the interplay of fluctuations and topology (vortices) makes it possible a formation of a special regime where a composite order of three CDW orders condense while the individual remains fluctuating. Apart from the thermodynamic signatures this phase differs from the high temperature disordered one by the presence of quasiparticle spectral gap.

At further lowering of the temperature the system undergoes a second phase transition in the phase with individual CDW order. This transition belongs to the \mathbb{Z}_3 Potts universality class.

VII. ACKNOWLEDGEMENTS

This work was supported by Office of Basic Energy Sciences, Material Sciences and Engineering Division, U.S. Department of Energy (DOE) under Contracts No. DE-SC0012704. We are grateful to Philippe Lecheminant for attracting our attention to a beautiful paper.

Appendix A: Free energy for a large value of G :

The free energy considered in the section IV A is given by:

$$\mathcal{F}/T = \sum_a \left[\frac{1}{2T} (\partial_x \phi_a)^2 + \frac{T}{2} (\partial_x \bar{\phi}_a)^2 + i \partial_x \phi_a \partial_y \bar{\phi}_a + A g_3 \cos(2\phi_a) + \eta \cos(2\pi \bar{\phi}_a) \right] - G \cos(\phi_1 + \phi_2 + \phi_3). \quad (\text{A1})$$

At $\eta = 0$ one can integrate over $\partial_x \bar{\phi}_a$:

$$\begin{aligned} & \int D\bar{\phi}_a \exp\left\{-\int d^2x \left[\frac{T}{2} (\partial_x \bar{\phi}_a)^2 + i \partial_x \phi_a \partial_y \bar{\phi}_a\right]\right\} \\ &= \text{const.} \int D\bar{\phi}_a \exp\left\{-\int d^2x \left[\frac{T}{2} (\partial_x \bar{\phi}_a)^2 - i \partial_y \phi_a \partial_x \bar{\phi}_a\right]\right\} \\ &\sim \exp\left[-\frac{1}{2T} \int d^2x (\partial_y \phi)^2\right] \end{aligned} \quad (\text{A2})$$

The result is the partition function for ϕ fields:

$$Z[\phi] = \int D\phi_a \exp\left\{-\int d^2x \left[\frac{1}{2T} [(\partial_x \phi_a)^2 + (\partial_y \phi_a)^2] + A g_3 \cos(2\phi_a) - G \cos(\phi_1 + \phi_2 + \phi_3)\right]\right\}. \quad (\text{A3})$$

In a similar way at $g_3 = 0$ we can integrate out the ϕ -fields.

In the limit of large G , we can consider the sum of all phases to be fixed. Hence the GL free energy can be transformed with

$$\begin{aligned} \phi_1 &= \Phi/\sqrt{3} + (\sqrt{2/3})\chi_1, \\ \phi_2 &= \Phi/\sqrt{3} + (\sqrt{2/3})(-\chi_1/2 + \sqrt{3}/2\chi_2), \\ \phi_3 &= \Phi/\sqrt{3} - (\sqrt{2/3})(\chi_1/2 + \sqrt{3}/2\chi_2). \end{aligned} \quad (\text{A4})$$

In this case, $\cos(\phi_1 + \phi_2 + \phi_3) = \cos(\sqrt{3}\Phi)$. When Φ is frozen, the dual field $\bar{\Phi} = \sum_a \bar{\phi}_a$ fluctuates strongly so that correlators of the dual exponents decay exponentially. Then the dual perturbation is generated in the second order in η :

$$\eta^2 \int d^2x \exp\{i\bar{\Phi}/\sqrt{3} + \sqrt{8/3\pi} e_a \bar{\chi}\}_{\mathbf{r}} \times \exp\{-i\bar{\Phi}/\sqrt{3} - \sqrt{8/3\pi} e_b \bar{\chi}\}_{\mathbf{r}+\mathbf{x}}, \quad (\text{A5})$$

giving rise to the operators

$$\cos[\sqrt{8/3\pi}(e_a - e_b)\bar{\chi}], \quad (\text{A6})$$

with scaling dimension $2\pi/T$. In that case we get

$$\begin{aligned} \mathcal{F}_{eff}/T &= \sum_{a=1}^3 \left[\bar{A} g_3 \cos(\sqrt{8/3} e_a \bar{\chi}) - B \cos(2\pi\sqrt{2}\omega_a \bar{\chi}) \right] + \\ &\sum_{i=1,2} \left[\frac{1}{2T} (\partial_x \chi_i)^2 + \frac{T}{2} (\partial_x \bar{\chi}_i)^2 + i \partial_x \chi_i \partial_y \bar{\chi}_i \right]. \end{aligned} \quad (\text{A7})$$

with $\omega_a = (0, 1), (\sqrt{3}, 1)/2, (\sqrt{3}, -1)/2$. More explicitly:

$$\begin{aligned} \sum_a \cos(\sqrt{8/3} e_a \bar{\chi}) &= \cos[\sqrt{8/3}\chi_1] + \cos[\sqrt{2/3}(\chi_1 - \sqrt{3}\chi_2)] + \\ &\cos[\sqrt{2/3}(\chi_1 + \sqrt{3}\chi_2)], \end{aligned} \quad (\text{A8})$$

and,

$$\begin{aligned} \sum_a \cos(2\pi\sqrt{2}\omega_a \bar{\chi}) &= \cos[2\pi\sqrt{2}\bar{\chi}_2] + \cos[\pi\sqrt{2}(\bar{\chi}_2 + \sqrt{3}\bar{\chi}_1)] \\ &+ \cos[\pi\sqrt{2}(\bar{\chi}_2 - \sqrt{3}\bar{\chi}_1)]. \end{aligned} \quad (\text{A9})$$

- ¹ D. M. Kennes, M. Claassen, L. Xian, A. Georges, A. J. Millis, J. Hone, C. R. Dean, D. Basov, A. N. Pasupathy, and A. Rubio, *Nature Physics* **17**, 155 (2021).
- ² M. Dzero, J. Xia, V. Galitski, and P. Coleman, *Annual Review of Condensed Matter Physics* **7**, 249 (2016).
- ³ B. R. Ortiz, L. C. Gomes, J. R. Morey, M. Winiarski, M. Bordelon, J. S. Mangum, I. W. H. Oswald, J. A. Rodriguez-Rivera, J. R. Neilson, S. D. Wilson, E. Ertekin, T. M. McQueen, and E. S. Toberer, *Phys. Rev. Mater.* **3**, 094407 (2019).
- ⁴ B. R. Ortiz, S. M. L. Teicher, Y. Hu, J. L. Zuo, P. M. Sarte, E. C. Schueller, A. M. M. Abeykoon, M. J. Krogstad, S. Rosenkranz, R. Osborn, R. Seshadri, L. Balents, J. He, and S. D. Wilson, *Phys. Rev. Lett.* **125**, 247002 (2020).
- ⁵ B. R. Ortiz, P. M. Sarte, E. M. Kenney, M. J. Graf, S. M. L. Teicher, R. Seshadri, and S. D. Wilson, *Phys. Rev. Mater.* **5**, 034801 (2021).
- ⁶ Y.-X. Jiang, J.-X. Yin, M. M. Denner, N. Shumiya, B. R. Ortiz, G. Xu, Z. Guguchia, J. He, M. S. Hossain, X. Liu, *et al.*, *Nature materials* **20**, 1353 (2021).
- ⁷ H. Li, T. T. Zhang, T. Yilmaz, Y. Y. Pai, C. E. Marvinney, A. Said, Q. W. Yin, C. S. Gong, Z. J. Tu, E. Vescovo, C. S. Nelson, R. G.

Moore, S. Murakami, H. C. Lei, H. N. Lee, B. J. Lawrie, and H. Miao, *Phys. Rev. X* **11**, 031050 (2021).

- ⁸ E. Uykur, B. R. Ortiz, S. D. Wilson, M. Dressel, and A. A. Tsirlin, *npj Quantum Materials* **7**, 16 (2022).
- ⁹ B. R. Ortiz, S. M. L. Teicher, L. Kautzsch, P. M. Sarte, N. Ratcliff, J. Harter, J. P. C. Ruff, R. Seshadri, and S. D. Wilson, *Phys. Rev. X* **11**, 041030 (2021).
- ¹⁰ H. Tan, Y. Liu, Z. Wang, and B. Yan, *Phys. Rev. Lett.* **127**, 046401 (2021).
- ¹¹ M. M. Denner, R. Thomale, and T. Neupert, *Phys. Rev. Lett.* **127**, 217601 (2021).
- ¹² X. Feng, K. Jiang, Z. Wang, and J. Hu, *Science bulletin* **66**, 1384 (2021).
- ¹³ L. Yu, C. Wang, Y. Zhang, M. Sander, S. Ni, Z. Lu, S. Ma, Z. Wang, Z. Zhao, H. Chen, *et al.*, arXiv preprint arXiv:2107.10714 (2021).
- ¹⁴ S.-Y. Yang, Y. Wang, B. R. Ortiz, D. Liu, J. Gayles, E. Derunova, R. Gonzalez-Hernandez, L. Šmejkal, Y. Chen, S. S. Parkin, *et al.*, *Science advances* **6**, eabb6003 (2020).
- ¹⁵ F. H. Yu, T. Wu, Z. Y. Wang, B. Lei, W. Z. Zhuo, J. J. Ying, and X. H. Chen, *Phys. Rev. B* **104**, L041103 (2021).

- ¹⁶ E. M. Kenney, B. R. Ortiz, C. Wang, S. D. Wilson, and M. J. Graf, *Journal of Physics: Condensed Matter* **33**, 235801 (2021).
- ¹⁷ C. Mielke III, D. Das, J.-X. Yin, H. Liu, R. Gupta, Y.-X. Jiang, M. Medarde, X. Wu, H. Lei, J. Chang, *et al.*, *Nature* **602**, 245 (2022).
- ¹⁸ R. Khasanov, D. Das, R. Gupta, C. Mielke, M. Elender, Q. Yin, Z. Tu, C. Gong, H. Lei, E. T. Ritz, R. M. Fernandes, T. Birol, Z. Guguchia, and H. Luetkens, *Phys. Rev. Res.* **4**, 023244 (2022).
- ¹⁹ R. Gupta, D. Das, C. Mielke III, E. Ritz, F. Hotz, Q. Yin, Z. Tu, C. Gong, H. Lei, T. Birol, *et al.*, arXiv preprint arXiv:2203.05055 (2022).
- ²⁰ Y. Xu, Z. Ni, Y. Liu, B. R. Ortiz, S. D. Wilson, B. Yan, L. Balents, and L. Wu, arXiv preprint arXiv:2204.10116 (2022).
- ²¹ Y.-P. Lin and R. M. Nandkishore, *Phys. Rev. B* **104**, 045122 (2021).
- ²² M. H. Christensen, T. Birol, B. M. Andersen, and R. M. Fernandes, *Phys. Rev. B* **106**, 144504 (2022).
- ²³ Y. Wang, S. Yang, P. K. Sivakumar, B. R. Ortiz, S. M. Teicher, H. Wu, A. K. Srivastava, C. Garg, D. Liu, S. S. Parkin, *et al.*, arXiv preprint arXiv:2012.05898 (2020).
- ²⁴ K. Y. Chen, N. N. Wang, Q. W. Yin, Y. H. Gu, K. Jiang, Z. J. Tu, C. S. Gong, Y. Uwatoko, J. P. Sun, H. C. Lei, J. P. Hu, and J.-G. Cheng, *Phys. Rev. Lett.* **126**, 247001 (2021).
- ²⁵ S. Ni, S. Ma, Y. Zhang, J. Yuan, H. Yang, Z. Lu, N. Wang, J. Sun, Z. Zhao, D. Li, *et al.*, *Chinese Physics Letters* **38**, 057403 (2021).
- ²⁶ C. Mu, Q. Yin, Z. Tu, C. Gong, H. Lei, Z. Li, and J. Luo, *Chinese Physics Letters* **38**, 077402 (2021).
- ²⁷ W. Duan, Z. Nie, S. Luo, F. Yu, B. R. Ortiz, L. Yin, H. Su, F. Du, A. Wang, Y. Chen, *et al.*, *Science China Physics, Mechanics & Astronomy* **64**, 107462 (2021).
- ²⁸ C. Zhao, L. Wang, W. Xia, Q. Yin, J. Ni, Y. Huang, C. Tu, Z. Tao, Z. Tu, C. Gong, *et al.*, arXiv preprint arXiv:2102.08356 (2021).
- ²⁹ M. L. Kiesel, C. Platt, and R. Thomale, *Phys. Rev. Lett.* **110**, 126405 (2013).
- ³⁰ W.-S. Wang, Z.-Z. Li, Y.-Y. Xiang, and Q.-H. Wang, *Phys. Rev. B* **87**, 115135 (2013).
- ³¹ X. Wu, T. Schwemmer, T. Müller, A. Consiglio, G. Sangiovanni, D. Di Sante, Y. Iqbal, W. Hanke, A. P. Schnyder, M. M. Denner, M. H. Fischer, T. Neupert, and R. Thomale, *Phys. Rev. Lett.* **127**, 177001 (2021).
- ³² C. Wen, X. Zhu, Z. Xiao, N. Hao, R. Mondaini, H. Guo, and S. Feng, *Phys. Rev. B* **105**, 075118 (2022).
- ³³ Y.-P. Lin and R. M. Nandkishore, *Physical Review B* **106**, L060507 (2022).
- ³⁴ H. Chen, H. Yang, B. Hu, Z. Zhao, J. Yuan, Y. Xing, G. Qian, Z. Huang, G. Li, Y. Ye, *et al.*, *Nature* **599**, 222 (2021).
- ³⁵ S. Zhou and Z. Wang, *Nature Communications* **13**, 7288 (2022).
- ³⁶ Y. Xiang, Q. Li, Y. Li, W. Xie, H. Yang, Z. Wang, Y. Yao, and H.-H. Wen, *Nature communications* **12**, 6727 (2021).
- ³⁷ L. Nie, K. Sun, W. Ma, D. Song, L. Zheng, Z. Liang, P. Wu, F. Yu, J. Li, M. Shan, *et al.*, *Nature* **604**, 59 (2022).
- ³⁸ F. Grandi, A. Consiglio, M. A. Sentef, R. Thomale, and D. M. Kennes, arXiv preprint arXiv:2302.01615 (2023).
- ³⁹ M. Kang, S. Fang, J.-K. Kim, B. R. Ortiz, S. H. Ryu, J. Kim, J. Yoo, G. Sangiovanni, D. Di Sante, B.-G. Park, *et al.*, *Nature Physics* **18**, 301 (2022).
- ⁴⁰ R. Lou, A. Fedorov, Q. Yin, A. Kuibarov, Z. Tu, C. Gong, E. F. Schwier, B. Büchner, H. Lei, and S. Borisenko, *Phys. Rev. Lett.* **128**, 036402 (2022).
- ⁴¹ H. Luo, Q. Gao, H. Liu, Y. Gu, D. Wu, C. Yi, J. Jia, S. Wu, X. Luo, Y. Xu, *et al.*, *Nature communications* **13**, 273 (2022).
- ⁴² S. Wu, B. R. Ortiz, H. Tan, S. D. Wilson, B. Yan, T. Birol, and G. Blumberg, *Phys. Rev. B* **105**, 155106 (2022).
- ⁴³ R. Tazai, Y. Yamakawa, S. Onari, and H. Kontani, *Science Advances* **8**, eabl4108 (2022).
- ⁴⁴ X. Feng, Z. Zhao, J. Luo, J. Yang, A. Fang, H. Yang, H. Gao, R. Zhou, and G.-q. Zheng, arXiv preprint arXiv:2303.01225 (2023).
- ⁴⁵ S. Cho, H. Ma, W. Xia, Y. Yang, Z. Liu, Z. Huang, Z. Jiang, X. Lu, J. Liu, Z. Liu, J. Li, J. Wang, Y. Liu, J. Jia, Y. Guo, J. Liu, and D. Shen, *Phys. Rev. Lett.* **127**, 236401 (2021).
- ⁴⁶ H. Li, G. Fabbri, A. Said, Y. Pai, Q. Yin, C. Gong, Z. Tu, H. Lei, J. Sun, J.-G. Cheng, *et al.*, arXiv preprint arXiv:2202.13530 (2022).
- ⁴⁷ T. Park, M. Ye, and L. Balents, *Phys. Rev. B* **104**, 035142 (2021).
- ⁴⁸ R. Nandkishore, L. S. Levitov, and A. V. Chubukov, *Nature Physics* **8**, 158 (2012).
- ⁴⁹ W.-S. Wang, Z.-Z. Li, Y.-Y. Xiang, and Q.-H. Wang, *Phys. Rev. B* **87**, 115135 (2013).
- ⁵⁰ L. Van Hove, *Phys. Rev.* **89**, 1189 (1953).
- ⁵¹ N. D. Mermin and H. Wagner, *Phys. Rev. Lett.* **17**, 1133 (1966).
- ⁵² R. M. Fernandes, A. V. Chubukov, J. Knolle, I. Eremin, and J. Schmalian, *Phys. Rev. B* **85**, 024534 (2012).
- ⁵³ C. M. Varma, *Phys. Rev. B* **73**, 155113 (2006).
- ⁵⁴ P. A. Lee, *Phys. Rev. X* **4**, 031017 (2014).
- ⁵⁵ C. Pépin, D. Chakraborty, M. Grandadam, and S. Sarkar, *Annual Review of Condensed Matter Physics* **11**, 301 (2020).
- ⁵⁶ S. Sarkar, M. Grandadam, and C. Pépin, *Phys. Rev. Res.* **3**, 013162 (2021).
- ⁵⁷ Y. Wang and A. Chubukov, *Phys. Rev. B* **90**, 035149 (2014).
- ⁵⁸ A. Tsvelik and A. Chubukov, *Physical Review B* **89**, 184515 (2014).
- ⁵⁹ S. Sarkar, D. Chakraborty, and C. Pépin, *Phys. Rev. B* **100**, 214519 (2019).
- ⁶⁰ S.-W. Kim, H. Oh, E.-G. Moon, and Y. Kim, *Nature Communications* **14**, 591 (2023).
- ⁶¹ Y. Song, T. Ying, X. Chen, X. Han, X. Wu, A. P. Schnyder, Y. Huang, J.-g. Guo, and X. Chen, *Phys. Rev. Lett.* **127**, 237001 (2021).
- ⁶² B. Song, X. Kong, W. Xia, Q. Yin, C. Tu, C. Zhao, D. Dai, K. Meng, Z. Tao, Z. Tu, *et al.*, arXiv preprint arXiv:2105.09248 (2021).
- ⁶³ T. Wang, A. Yu, H. Zhang, Y. Liu, W. Li, W. Peng, Z. Di, D. Jiang, and G. Mu, arXiv preprint arXiv:2105.07732 (2021).
- ⁶⁴ F.-Y. Wu, *Reviews of modern physics* **54**, 235 (1982).
- ⁶⁵ N. Ratcliff, L. Hallett, B. R. Ortiz, S. D. Wilson, and J. W. Harter, *Phys. Rev. Mater.* **5**, L111801 (2021).
- ⁶⁶ J. Zhao, W. Wu, Y. Wang, and S. A. Yang, *Phys. Rev. B* **103**, L241117 (2021).
- ⁶⁷ Y. Hu, X. Wu, B. R. Ortiz, S. Ju, X. Han, J. Ma, N. C. Plumb, M. Radovic, R. Thomale, S. D. Wilson, *et al.*, *Nature Communications* **13**, 2220 (2022).
- ⁶⁸ Y.-P. Lin and R. M. Nandkishore, *Phys. Rev. B* **106**, L060507 (2022).
- ⁶⁹ J. V. José, L. P. Kadanoff, S. Kirkpatrick, and D. R. Nelson, *Phys. Rev. B* **16**, 1217 (1977).
- ⁷⁰ I. L. Aleiner, D. E. Kharzeev, and A. M. Tsvelik, *Phys. Rev. B* **76**, 195415 (2007).
- ⁷¹ P. Lecheminant, *Physics Letters B* **648**.
- ⁷² P. Francesco, P. Mathieu, and D. Sénéchal, *Conformal field theory* (Springer Science & Business Media, 2012).
- ⁷³ A. Tsvelik and A. Kuklov, *New Journal of Physics* **14**, 115033 (2012).