Auth:

*Corey E. Frank,^{1,2} Sylvia K, Lewin,^{1,2} Gicela Saucedo Salas,^{2,1} Peter Czajka,^{1,2} Ian Hayes,² Hyeok Yoon,² Tristin Metz,² Johnpierre Paglione,² John Singleton,³ *Nicholas P. Butch^{1,2}

- 1. NIST Center for Neutron Research, National Institute of Standards and Technology, Gaithersburg, MD, USA
- 2. Maryland Quantum Materials Center, Department of Physics, University of Maryland, College Park, MD, USA
- National High Magnetic Field Laboratory, Los Alamos National Laboratory, Los Alamos, NM, USA

*To whom correspondence should be addressed

Abstract

Reentrant superconductivity is a phenomenon in which the destructive effects of magnetic field on superconductivity are mitigated, allowing a zero-resistance state to survive under conditions that would otherwise destroy it. Typically, the reentrant superconducting region derives from a zero-field parent superconductor. Here, we show that in specifically-prepared UTe₂ crystals, extremely large magnetic field gives rise to an unprecedented high field superconductor that lacks a zero-field parent phase. This orphan superconductivity exists at fields between 37 T and 52 T, over a smaller angular range than observed in superconducting UTe₂. The stability of field-induced orphan superconductivity is a challenge to existing theoretical explanations, and underscores the likelihood of a field-induced modification of the electronic structure of UTe₂.

Introduction

Although uranium ditelluride (UTe₂) has been known since the mid-1900's to be a paramagnet,^{1,2} its unconventional superconductivity was not reported until 2019.^{3,4} In most superconductors, applied magnetic fields destroy superconductivity at and above the Pauli limit, the field at which Zeeman splitting destabilizes spin anti-aligned Cooper pairs.⁵ In UTe₂, however, superconductivity survives to fields at least double the Pauli limit when the field is aligned in any crystallographic direction, indicating the presence of unconventional superconductivity.^{3,4} When the applied field is aligned along the crystallographic *b* axis, superconductivity persists to a striking value of 35 T, above which it is sharply truncated by a metamagnetic transition into a field polarized state.⁴ Moreover, superconductivity returns and persists up to an estimated 70 T at off-axis angles of 20°-40° from the crystallographic *b*- to *c*-axes.^{6,7} This anisotropic and highly robust superconductivity strongly implies that UTe₂ is an

intrinsic spin-triplet superconductor.^{4,7} Owing to the potential for spin-triplet superconductors to host non-Abelian Majorana fermions,⁸ such materials would be very attractive as building blocks for emergent technologies such as fault tolerant quantum computers.⁹

Despite intense research, the pairing state of the superconducting order parameter at low fields is yet to be unambiguously determined.¹⁰⁻¹² Determining the nature of the highest field superconductivity is even more of a challenge,¹³⁻¹⁵ and the relationship between the low- and high-field superconducting phases is also uncertain. Although this question has been primarily addressed theoretically, there has been some experimental input. For example, NMR Knight-shift measurements suggest that there is a field-induced d-vector rotation involving a switch between B_{3u} and B_{2u} components.^{11,16} Nonetheless, the most important effect underlying the intense field enhancement of superconductivity remains unclear. Leading explanations include lower dimensionality,^{14,15} which can suppress the orbital limiting effects of magnetic fields, or internal exchange fields that counteract the applied external field,^{4,7} leading the superconducting phase to experience smaller total magnetic fields.

To explore the relationship between the superconducting phases in UTe₂, we prepared samples of nominally non-superconducting UTe₂ via chemical vapor transport. The stability of superconductivity was mapped via magnetoresistance measurements that were performed in applied magnetic fields of up to 60 T with the field-angle rotated between the *b* and *c* axes. Our results show that these UTe₂ samples host an "orphaned" high field stabilized superconductivity without an accompanying low-field superconducting phase. In addition to being the field-stabilized superconductor, these findings dramatically limit possible explanations for the stability of high-field superconductivity in UTe₂, demanding a new theoretical framework.

Results and Discussion

UTe₂ crystalizes in a centrosymmetric orthorhombic structure (*Immm*, No. 71) with D_{2h} point group symmetry. The anisotropy of this structure, coupled with the strong spin orbit coupling of 5*f* uranium, leads to strongly anisotropic response to applied magnetic field. Low-field superconductivity in UTe₂ persists to at least 8 T in all directions; superconductivity survives to the highest fields (~35 T) when $H \parallel b$, the low-field magnetic hard axis. Whether the superconductivity along the b-axis consists of more than one phase is an open question.^{12,17,18}

In the UTe₂ samples studied here, there is no evidence of superconductivity in any orientation for magnetic field smaller than 35 T. Instead, the samples are paramagnetic metals. Zero-field resistance measurements demonstrate Fermi-liquid T² dependence below 10 K (See Supplementary Information, Fig S.2) without evidence of a superconducting transition down to 110 mK, or 1/19 of the expected critical temperature, ^{3,4,7,19-23} reflecting the absence of zero-field superconductivity. One measure of the disorder in this sample is given by the residual resistivity ratio (RRR) of 7.5, which compares to a typical RRR of 18 – 30, as first discussed by Ran *et al*,³ and recent high RRR (RRR \approx 1000) grown via salt flux.¹⁹

Absent superconductivity, the dominant feature in the data (**Fig. 1**) is the metamagnetic transition at applied field, H_m . At H_m , the magnetization along the *b*-axis jumps discontinuously, and the system enters a field-polarized state. As shown in **Fig. 1**, the metamagnetic transition occurs just below 35 T along the *b* axis. This value is slightly lower than previous observations of H_m reported from typically superconducting samples of UTe₂.^{4,7,18,24-26}

The onset field of the metamagnetic transition in UTe₂ is of similar energy scale to the temperature at which there is a maximum in the magnetic susceptibility with field along *b*, $T_{\chi}^{max} \approx 35$ K, previously reported for both nonsuperconducting²⁷ and superconducting⁶ UTe₂. This feature is typical of heavy fermion paramagnets with metamagnetic transitions, implying in those cases that Hm and T_{χ}^{max} are related by a single energy scale.²⁸ The agreement between the energy scales associated with T_{χ}^{max} and Hm is also important in UTe₂^{24,25,29} and reflects the Kondo hybridization energy scale, as further observed in scanning tunneling microscopy²⁹ and magnetic excitations in inelastic neutron scattering experiments.³⁰ These results show that the heavy fermion state in UTe₂ is a robust characteristic.

We now consider the orphaned field-induced orphan superconducting phase (SC_{FP}) that occurs at fields greater than H_m in the field polarized state. This SC_{FP} phase, with boundaries defined as 50% of the observed transition, emerges close to a 29° offset from *b* to *c* and extends to 42° (**Fig. 1a**). The narrower angular range of the orphan SC_{FP} is striking when compared to previously published data from typically superconducting UTe₂, which extends from 25° to $42^{o4,24,25,31}$ (**Fig. S.6** in Supplementary Information). The orphan SC_{FP} phase only survives to 52 T, compared to extrapolated values above 65 T in other reports.^{4,7,32} Nevertheless, magnetoresistance (**Fig. 1b**) shows that the transition into the SC_{FP} state is qualitatively similar to that in other samples. Note two important features: wider transitions as a function of field and a limited range of zero resistance, both as measured at 0.5 K. The zero-resistance state is centered at 36°, suggesting that there is no direct relationship between the stability of SC_{FP} and the crystallographic (0 1 1) direction, situated at 23.7°.

The temperature dependence of orphan SC_{FP} gives further information about the robustness of the superconductivity. The zero resistance state, measured at a 38.7° offset from *b* to *c*, persists to 0.5 K (**Fig. 2**), and a superconducting envelope persists to almost 0.9 K. All resistive signatures of superconductivity are suppressed by 1 K. This temperature differs dramatically from the value of 1.5 K reported before in samples exhibiting low field superconductivity.⁴ Previously, the similar T_c 's of low-field and SC_{FP} states lead to the inference that the two phases must involve similar pairing energies.⁴ The presence of orphan SC_{FP} suggests that this interpretation is incorrect, or that additional mechanisms must be considered, such as substantial differences in the effects of the same disorder on the smearing of the superconducting energy gaps, perhaps due to differences in gap structure.

The challenge of identifying any theoretical mechanism for field stabilization of SC_{FP} is made more difficult by the absence of low-field superconductivity. Existing relevant theoretical attempts to describe high field superconductivity generally require the presence of zero-field superconductivity,^{3,4,7,13-15,33}. It is instructive to review these mechanisms in light of the

recontextualization demanded by the orphan SC_{FP} phase. The magnetic field dependence of the superconductivity due to these mechanisms is illustrated in **Fig. 3**.

Reentrant superconductivity in organic superconductors and several chevrel phases is reportedly stabilized by the Jaccarino-Peter mechanism.³⁴⁻³⁶ This mechanism involves an internal exchange field generated by the short-range magnetic fluctuations of localized moments which opposes the applied magnetic field, stabilizing reentrant superconductivity (**Fig. 3**).³⁷ For example, in the chevrel phase $Eu_{0.75}Sn_{0.25}Mo_6S_{7.2}Se_{0.8}$, zero-field superconductivity appears below 3.9 K and is suppressed by 1 T.³⁴ Above 4 T, the external field begins to adequately compensate for the internal exchange field, and superconductivity returns, persisting to approximately 22 T.³⁴ A similar mechanism is believed relevant to field-stabilized superconductivity in the antiferromagnetic insulator λ -(BETS)₂FeCl₄. Chemical substitution experiments show that the high field range of the superconductivity is decreased when antiferromagnetism is destabilized, and further indicate that λ -(BETS)₂FeCl₄ may have a "hidden" superconducting phase that competes with the antiferromagnetic internal field.³⁸

However, it was pointed out previously that the Jaccarino-Peter mechanism is likely not appropriate for UTe_2^4 because this effect requires localized moments and is typically observed in experiment over a narrow angular field range.³⁷ This conclusion is reinforced by the new observations of orphan SC_{FP}. The absence of zero field superconductivity without magnetic order to generate a negative exchange field at H = 0 almost entirely precludes the compensation-effect as the primary field stabilizing mode in UTe₂.

Another possible explanation is that SC_{FP} is stabilized by ferromagnetic fluctuations,³ similar to field-reinforced superconductivity observed in ferromagnetic superconductors UCoGe³⁹ and URhGe⁴⁰(**Fig 3**). In this model, stabilizing longitudinal spin fluctuations arise near a second-order ferromagnetic transition driven by magnetic field.⁴¹ At ambient conditions, UTe₂ is also inferred to lie on the cusp of magnetic order, based on low field magnetometry at ambient²⁷ and high pressure⁴². However, an important caveat is that superconductors described by the spin-fluctuation model exhibit long range magnetic order in zero field, and show low-field superconductivity in addition to a magnetically reinforced superconducting phase.^{39,40} More importantly, experiments show that the high-field phases in the ferromagnetic superconductors are *more readily suppressed* by temperature and disorder than the zero field phases,^{39,40} so it is surprising to see the presumptive fragile phase without its more robust neighbor in UTe₂.

Another mechanism for stabilizing high field superconductivity involves field-induced Landau levels.³³ In this model, the field-induced orbits of conduction electrons are quantized, and eventually the increased cyclotron radii of quasiparticles orbiting the Fermi surface extends the coherence range of paired electrons, and thus the stability field of H_{C2} (**Fig 3**). Hypothetically, superconductivity could be stabilized in this way at any temperature with sufficient field; however, typically the field strength required for this is far beyond the Pauli limit for spin-singlet superconductors.^{33,43} Landau-level stabilization is most likely to be realized in low dimensional spin-triplet superconductors, and high pressure measurements of resistance in typical UTe₂ show phase transitions quantized with the signature 1/H relation.⁴⁴ A low-dimensional electronic structure may be inferred from angle-resolved photoemission

spectroscopy,⁴⁵ and recent de Haas van Alphen oscillation measurements of low-field superconducting UTe₂ suggest quasi-two-dimensional cylindrical electron and hole Fermi surface sections.⁴⁶ However, the Fermi surface has three-dimensional characteristics ^{47,48} and whether the electronic structure has sufficiently low-dimensional character for relevant theories to apply remains an open question. Theoretical analysis has proposed that SC_{FP} in UTe₂ is stabilized near the quantum limit by a Hofstadter butterfly regime of Landau level quantizations with large superlattices.⁴⁹ This stabilization regime implies the existence of an even higher field phase beyond SCFP, located at approximately 90 T.^{44,49} Possible signatures of precursor effects related to Landau level stabilized superconductivity were reported in a previous high-field pressure study (ref 7). However, confirmation of this model would ideally involve observation of superconductivity in multiple Landau levels, requiring challenging measurements performed at significantly higher magnetic fields.

Methods

Single crystals of UTe₂ were grown as thin plates approximately 3 mm in length by chemical vapor transport with iodine as the transport agent. Approximately 1 g total of elemental U and Te in a 2:3 atomic ratio were sealed in an evacuated quartz ampule with 30 mg of iodine. The ampule was loaded into a two-zone horizontal furnace and the temperature was slowly increased to 800 °C and 710 °C in the charge and growth zones, respectively. Temperature was maintained for 1 week, after which transport was quenched by turning off power to the heating elements. Crystals grew as thin black plates in the *ab* plane (**Fig. S.1** in Supplementary Information). Crystallographic orientation was identified from the crystal habit.

Zero-field resistance measurements to 100 mK were performed on a Quantum Design Physical Property Measurement System (PPMS) using the adiabatic demagnetization refrigerator (ADR) option. Crystals were mounted on a cryogenic single axis goniometer,⁵⁰ and high field magnetoresistance measurements were performed at the National High Magnetic Field Laboratory (NHMFL), Los Alamos, NM using a 65 T short-pulse magnet. Identification of commercial equipment does not imply recommendation or endorsement by NIST.

Funding

This work was supported in part by the National Science Foundation under the Division of Materials Research Grant NSF-DMR 2105191. A portion of this work was performed at the National High Magnetic Field Laboratory (NHMFL), which is supported by National Science Foundation Cooperative Agreements DMR-1644779 and DMR-2128556, and the Department of Energy (DOE). JS acknowledges support from the DOE BES program "Science of 100 T", which permitted the design and construction of much of the specialized equipment used in the high-field studies. The authors declare no competing financial interest.

Acknowledgements

The authors would like to express their gratitude to University of Maryland undergraduate students: Patrick Chen, Elan Moskowitz, and Kimia Samieninejad, for their assistance in pulsed field measurement preparations.

Author Contributions

N.P.B. directed the project. C.E.F synthesized single crystalline samples. C.E.F., G.S.S., and S.K.L. oriented and prepared samples for magnetoresistance measurements. C.E.F, S.K.L, and J.S. performed the magnetoresistance measurements in the pulsed field. C.E.F. performed resistivity measurements at zero field. I.H., T.M., and H.Y. performed preliminary measurements. C.E.F. and N.P.B. wrote the manuscript with contributions from all authors.



Figures

Fig. 1 (a) The angle dependence of the magnetoresistance (*b* to *c*, degrees) of orphan superconductivity in UTe₂ by applied field (H) at base temperature (approximately 0.5 K), with color indicating total resistance. Dark blue regions between 30-44° are where the sample resistance falls below the low field normal state value and the darkest color indicates zero resistance. Superconducting transitions (defined by 50% of the transition) are shown as purple hexagons, and transitions from the low field normal state to the field polarized normal state are indicated by blue hexagons. Lines are guides to the eye. (**b**) Magnetoresistance of orphan superconductivity at select angles near the SC_{FP} phase (angles are in degrees from *b* to *c*). The large jumps in resistance near 35 T indicate the metamagnetic transition at applied fields H_m .



Fig. 2 (a) The temperature dependence of the magnetoresistance of orphan superconductivity in UTe₂ at 38.7° between *b* and *c* versus applied field (H). Large jumps in resistance near 45 T indicate the metamagnetic transition. (b) The field-temperature phase diagram of orphan superconductivity. Open circles are features taken from data shown in a), and the R = 0 regions are highlighted in dark blue. Purple, orange barred, and light green crossed circles respectively indicate 50%, 10%, 90% of the transitions between superconducting and normal state or superconducting and field polarized state.



Fig. 3. Magnetic field – temperature schematic phase diagrams for superconductivity stabilized by different possible mechanisms. (3.a) The Jaccarino-Peter compensation effect. An internal exchange field (H_{Ex}, blue) opposes the applied field (H_{App}) resulting in reentrant superconductivity when the total internal field (H_T, purple) is smaller than H_{c2}. (3.b) Stabilization of ferromagnetic superconductivity near a quantum critical point. Strong magnetic fluctuations due to the destabilization of long-range magnetism enhance the superconducting pairing. Superconductivity can survive at and on either side of the QCP. (3c) Landau level stabilized superconductivity. The upper critical field of reentrant superconductivity is oscillatory in inverse field.

References

- 1 Slovyanskikh, V. K., Ellert, G. V., Yarembash, E. I. & Korsakova, M. D. Preparation of single crystals of uranium chalcogenides by chemical transport reactions. *Izvestiya Akademii Nauk SSSR, Neorganicheskie Materialy* **2**, 973-975 (1966).
- 2 Suski, W. Magnetic properties of UTe₂ and U₇Te₁₂. *Phys. Status Solidi (a)* **13**, 675-680, doi:<u>https://doi.org/10.1002/pssa.2210130241</u> (1972).
- 3 Ran, S. *et al.* Nearly ferromagnetic spin-triplet superconductivity. *Science* **365**, 684-687, doi:10.1126/science.aav8645 (2019).
- 4 Ran, S. *et al.* Extreme magnetic field-boosted superconductivity. *Nature Physics* **15**, 1250-1254, doi:10.1038/s41567-019-0670-x (2019).
- 5 Aoki, D., Ishida, K. & Flouquet, J. Review of U-based Ferromagnetic Superconductors: Comparison between UGe₂, URhGe, and UCoGe. *J. Phys. Soc. Jpn.* **88**, 022001, doi:10.7566/JPSJ.88.022001 (2019).
- 6 Knafo, W. *et al.* Comparison of two superconducting phases induced by a magnetic field in UTe₂. *Commun. Phys.* **4**, 40, doi:10.1038/s42005-021-00545-z (2021).
- 7 Aoki, D. *et al.* Unconventional superconductivity in UTe₂. *J. Phys.: Condens. Matter* **34**, 243002, doi:10.1088/1361-648x/ac5863 (2022).
- 8 Beenakker, C. W. J. Search for Majorana Fermions in Superconductors. *Annual Review of Condensed Matter Physics* **4**, 113-136, doi:10.1146/annurev-conmatphys-030212-184337 (2013).
- ⁹ Lian, B., Sun, X.-Q., Vaezi, A., Qi, X.-L. & Zhang, S.-C. Topological quantum computation based on chiral Majorana fermions. *Proc. Natl. Acad. Sci.* **115**, 10938-10942 (2018).
- 10 Hayes, I. M. *et al.* Multicomponent superconducting order parameter in UTe₂. *Science* **373**, 797-801, doi:doi:10.1126/science.abb0272 (2021).
- 11 Fujibayashi, H. *et al.* Superconducting Order Parameter in UTe₂ Determined by Knight Shift Measurement. *J. Phys. Soc. Jpn.* **91**, 043705 (2022).
- 12 Shishidou, T., Suh, H. G., Brydon, P. M. R., Weinert, M. & Agterberg, D. F. Topological band and superconductivity in UTe₂. *Phys. Rev. B* **103**, 104504, doi:10.1103/PhysRevB.103.104504 (2021).
- 13 Machida, K. Violation of the orbital depairing limit in a non-unitary state--on the high field phase in the heavy Fermion superconductor UTe₂. *arXiv preprint arXiv:2301.09035* (2023).
- 14 Mineev, V. P. Reentrant superconductivity in UTe₂. J. Exp. Theor. Phys. Lett **111**, 715-719 (2020).
- Lebed, A. G. Restoration of superconductivity in high magnetic fields in UTe₂. *Mod. Phys. Lett. B* 34, 2030007 (2020).
- 16 Nakamine, G. *et al.* Anisotropic response of spin susceptibility in the superconducting state of UTe₂ probed with ¹²⁵Te NMR measurement. *Phys. Rev. B* **103**, L100503, doi:10.1103/PhysRevB.103.L100503 (2021).
- 17 Kinjo, K. *et al.* Change of superconducting character in UTe₂ induced by magnetic field. *Phys. Rev. B* **107**, L060502, doi:10.1103/PhysRevB.107.L060502 (2023).
- Rosuel, A. *et al.* Field-Induced Tuning of the Pairing State in a Superconductor. *Physical Review X* 13, 011022, doi:10.1103/PhysRevX.13.011022 (2023).
- 19 Sakai, H. *et al.* Single crystal growth of superconducting UTe₂ by molten salt flux method. *Phys. Rev. Mater* **6**, 073401, doi:10.1103/PhysRevMaterials.6.073401 (2022).
- 20 Aoki, D. *et al.* Multiple Superconducting Phases and Unusual Enhancement of the Upper Critical Field in UTe₂. *J. Phys. Soc. Jpn.* **89**, 053705, doi:10.7566/JPSJ.89.053705 (2020).
- 21 Braithwaite, D. *et al.* Multiple superconducting phases in a nearly ferromagnetic system. *Commun. Phys.* **2**, 147, doi:10.1038/s42005-019-0248-z (2019).

- 22 Sundar, S. *et al.* Coexistence of ferromagnetic fluctuations and superconductivity in the actinide superconductor UTe₂. *Phys. Rev. B* **100**, doi:10.1103/physrevb.100.140502 (2019).
- 23 Thomas, S. M. *et al.* Spatially inhomogeneous superconductivity in UTe₂. *Phys. Rev. B* **104**, 224501 (2021).
- 24 Miyake, A. *et al.* Metamagnetic transition in heavy fermion superconductor UTe₂. *J. Phys. Soc. Jpn.* **88**, 063706 (2019).
- 25 Niu, Q. *et al.* Evidence of Fermi surface reconstruction at the metamagnetic transition of the strongly correlated superconductor UTe₂. *Phys. Rev. Res.* **2**, 033179, doi:10.1103/PhysRevResearch.2.033179 (2020).
- 26 Miyake, A. *et al.* Enhancement and discontinuity of effective mass through the first-order metamagnetic transition in UTe₂. *J. Phys. Soc. Jpn.* **90**, 103702 (2021).
- 27 Ikeda, S. *et al.* Single Crystal Growth and Magnetic Properties of UTe₂. *J. Phys. Soc. Jpn.* **75**, 116-118, doi:10.1143/JPSJS.75S.116 (2006).
- 28 Aoki, D., Knafo, W. & Sheikin, I. Heavy fermions in a high magnetic field. *Comptes Rendus Physique* **14**, 53-77, doi:<u>https://doi.org/10.1016/j.crhy.2012.11.004</u> (2013).
- 29 Jiao, L. *et al.* Chiral superconductivity in heavy-fermion metal UTe₂. *Nature* **579**, 523-527, doi:10.1038/s41586-020-2122-2 (2020).
- 30 Butch, N. P. *et al.* Symmetry of magnetic correlations in spin-triplet superconductor UTe₂. *npj Quantum Mater.* **7**, 39, doi:10.1038/s41535-022-00445-7 (2022).
- 31 Knebel, G. *et al.* Field-Reentrant Superconductivity Close to a Metamagnetic Transition in the Heavy-Fermion Superconductor UTe₂. *J. Phys. Soc. Jpn.* **88**, 063707, doi:10.7566/JPSJ.88.063707 (2019).
- Helm, T. *et al.* Suppressed magnetic scattering sets conditions for the emergence of 40 T high-field superconductivity in UTe₂. *arXiv preprint arXiv:2207.08261* (2022).
- 33 Rasolt, M. & Tešanović, Z. Theoretical aspects of superconductivity in very high magnetic fields. *Rev. Mod. Phys.* **64**, 709 (1992).
- 34 Meul, H. *et al.* Observation of magnetic-field-induced superconductivity. *Phys. Rev. Lett.* **53**, 497 (1984).
- Burlet, P. *et al.* Magnetism and superconductivity in the Chevrel phase HoMo₆S₈. *Physica B: Condensed Matter* **215**, 127-133, doi:<u>https://doi.org/10.1016/0921-4526(95)00032-5</u> (1995).
- 36 Hiraki, K.-i. *et al.* ⁷⁷Se NMR evidence for the Jaccarino–Peter mechanism in the field induced superconductor, λ-(BETS)₂FeCl₄. *J. Phys. Soc. Jpn.* **76**, 124708 (2007).
- 37 Hampshire, D. P. in *Handbook of Superconductivity* 178-202 (CRC Press, 2023).
- 38 Uji, S. & S. Brooks, J. Magnetic-Field-Induced Superconductivity in Organic Conductors. *J. Phys. Soc. Jpn.* **75**, 051014, doi:10.1143/JPSJ.75.051014 (2006).
- 39 Huy, N. *et al.* Superconductivity on the border of weak itinerant ferromagnetism in UCoGe. *Phys. Rev. Lett.* **99**, 067006 (2007).
- 40 Aoki, D. *et al.* Coexistence of superconductivity and ferromagnetism in URhGe. *Nature* **413**, 613-616 (2001).
- 41 Slooten, E., Naka, T., Gasparini, A., Huang, Y. K. & de Visser, A. Enhancement of superconductivity near the ferromagnetic quantum critical point in UCoGe. *Phys. Rev. Lett.* **103**, 097003, doi:10.1103/PhysRevLett.103.097003 (2009).
- 42 Li, D. *et al.* Magnetic Properties under Pressure in Novel Spin-Triplet Superconductor UTe₂. *J. Phys. Soc. Jpn.* **90**, 073703, doi:10.7566/JPSJ.90.073703 (2021).
- 43 Gruenberg, L. & Gunther, L. Effect of orbital quantization on the critical field of type-II superconductors. *Phys. Rev.* **176**, 606 (1968).
- 44 Ran, S. *et al.* Expansion of the high field-boosted superconductivity in UTe₂ under pressure. *npj Quantum Mater.* **6**, 75, doi:10.1038/s41535-021-00376-9 (2021).

- 45 Miao, L. *et al.* Low Energy Band Structure and Symmetries of UTe₂ from Angle-Resolved Photoemission Spectroscopy. *Phys. Rev. Lett.* **124**, 076401, doi:10.1103/PhysRevLett.124.076401 (2020).
- 46 Aoki, D. *et al.* First Observation of the de Haas–van Alphen Effect and Fermi Surfaces in the Unconventional Superconductor UTe₂. *J. Phys. Soc. Jpn.* **91**, 083704, doi:10.7566/JPSJ.91.083704 (2022).
- 47 Eaton, A. *et al.* Quasi-2D Fermi surface in the anomalous superconductor UTe₂. *arXiv preprint arXiv:2302.04758* (2023).
- 48 Broyles, C. *et al.* Revealing a 3D Fermi Surface and Electron-Hole Tunneling in UTe₂ with Quantum Oscillations. *arXiv preprint arXiv:2303.09050* (2023).
- 49 Park, M. J., Kim, Y. B. & Lee, S. Geometric superconductivity in 3d Hofstadter butterfly. *ArXiv.org* arXiv:2007.16205, doi:<u>https://doi.org/10.48550/arXiv.2007.16205</u> (2020).
- 50 Willis, X., Ding, X., Singleton, J. & Balakirev, F. F. Cryogenic goniometer for measurements in pulsed magnetic fields fabricated via additive manufacturing technique. *Rev. Sci. Instrum.* **91**, 036102, doi:10.1063/1.5125792 (2020).