## Large upper critical fields and dimensionality crossover of superconductivity in infinite-layer nickelate $La_{0.8}Sr_{0.2}NiO_2$

Wei Wei,<sup>1</sup> Wenjie Sun,<sup>2,3</sup> Yue Sun,<sup>1,\*</sup> Yongqiang Pan,<sup>4</sup> Gangjian Jin,<sup>5</sup>

Feng Yang,<sup>6</sup> Yueying Li,<sup>2,3</sup> Zengwei Zhu,<sup>7</sup> Yuefeng Nie,<sup>2,3,†</sup> Zhixiang Shi<sup>1,‡</sup>

<sup>1</sup>Department of Physics, Southeast University, Nanjing 211189, China

<sup>2</sup>National Laboratory of Solid State Microstructures,

Jiangsu Key Laboratory of Artificial Functional Materials,

College of Engineering and Applied Sciences, Nanjing University, Nanjing 210093, P. R. China.

<sup>3</sup>Collaborative Innovation Center of Advanced Microstructures,

Nanjing University, Nanjing 210093, P. R. China.

<sup>4</sup>Key Laboratory of Materials Physics, Institute of Solid State Physics,

Chinese Academy of Sciences, Hefei, 230031, China

<sup>5</sup>School of Electrical and Electronic Engineering,

Huazhong University of Science and Technology, Wuhan 430074, China

<sup>6</sup>School of Physics, Huazhong University of Science and Technology, Wuhan 430074, China

<sup>7</sup>Wuhan National High Magnetic Field Center and School of Physics,

Huazhong University of Science and Technology, Wuhan 430074, China

The recently emerging superconductivity in infinite-layer nickelates, with isostructure and isoelectron of cuprates, provides a new platform to explore the pairing mechanism of high-temperature superconductors. In this work, we studied the upper critical field  $(H_{c2})$  of a high-quality La<sub>0.8</sub>Sr<sub>0.2</sub>NiO<sub>2</sub> thin film with superconducting transition temperature,  $T_c = 18.8$  K, using high magnetic field up to 56 T. A very large  $H_{c2}$ , ~ 40 T for  $H \parallel c$  and ~ 52 T for  $H \parallel ab$ , was confirmed, which suggests that infinite-layer nickelates also have great application potential. The anisotropy of  $H_{c2}$  monotonically decreases from ~ 10 near  $T_c$  to ~ 1.5 at 2 K. Angle dependence of  $H_{c2}$  confirms the crossover of superconductivity from two-dimensional (2D) to three-dimensional (3D) as the temperature decreases. We discussed that the interstitial orbital effect causes the weakening of anisotropy. The observed abnormal upturning of  $H_{c2}$  at low temperatures is found to be a universal behavior independent of film quality and rare earth elements. Therefore, it should not be the Fulde-Ferrell-Larkin-Ovchinnikov (FFLO) state due to the fact that it is in the dirty limit and insensitive to disorder.

Research of the high temperature superconducting (SC) mechanism and possible contributions involved in the pairing process is the foundation for realizing the dream of high-temperature superconductivity (HTSC). Understanding electronic properties of materials similar to the cuprates can provide insight into the mechanism of superconductivity in the cuprates and other high- $T_{\rm c}$  superconductors. The infinite-layer nickel-based 112 thin films consist of square plane-coordinated NiO<sub>2</sub> planes and Ln/Sr/Ca atomic layers, which is the isostructure of cuprates.[1] For the LaNiO<sub>2</sub> and NdNiO<sub>2</sub>, X-ray absorption spectroscopy (XAS) and resonant inelastic X-ray scattering (RIXS) confirmed the nominal 3  $d^9$  electronic configuration, equivalent to  $Cu^{2+}$  in the cuprates.[2] Such isostructural and isoelectronic characteristics show great promise in deconstructing the various cooperative mechanisms responsible for HTSC. However, different from cuprates, the hybridization of Ni 3d and O 2p orbitals decreases and the coupling of Ni 3d and La/Nd 5d states increases.<sup>[2]</sup> In this configuration, the Ni state can have a charge transfer to the rare earth cation, thus leaving holes in Ni orbitals and electrons in R 5d (R = La, Pr, Nd) orbitals, which is known as the self-doping effect. [3, 4] The change in sign of the low-temperature Hall coefficient as a function of Sr doping indicates the presence of multiple bands at the Fermi level. [5, 6] From the theoretical point

of view, electronic structure calculations for the nickelates indicate the presence of a large hole pocket with  $3d_{x^2-y^2}$  character, and electron pockets arising from Nd 5d and Ni 3d hybridization. [1, 7, 8] As is well known, the parent phase of cuprates is depicted as a charge transfer insulator with an antiferromagnetic (AFM) order. [4, 9] In sharp contrast, a definitive resolution of long range AFM in infinite-layer nickelates is still lacking, even though hints of short-range magnetic order or spin glass behavior have been picked up by various measurements. [10–13] Recent STM experiments uncovered a mixed s- and d-wave SC gap feature on the rough surface of  $Nd_{1-x}Sr_xNiO_2$ thin films. [14] At present, the research on nickelates superconductors is still in the exploratory stage. The similarities and differences between the SC mechanisms of nickelates and cuprates, and the reasons for the lack of superconductivity in bulk nickelates are still unclear.

The upper critical field  $(H_{c2})$  is a fundamental parameter for getting information such as pair-breaking mechanism, coherence length  $\xi$ , and pairing symmetry, which plays an important role in the understanding of unconventional superconducting mechanism.[15–17] It has been found that the  $H_{c2}$  of Nd<sub>0.775</sub>Sr<sub>0.225</sub>NiO<sub>2</sub> with SC transition temperature  $(T_c)$  of 8.5 K is surprisingly isotropic at low temperatures despite the layered crystal structure.[18] In addition,  $H_{c2}$  at 0 K for  $H_{c2}^{ab}$   $(H \parallel ab)$ 



FIG. 1. (a) XRD patterns of the perovskite  $La_{0.8}Sr_{0.2}NiO_3$  (red) and infinite-layer thin film  $La_{0.8}Sr_{0.2}NiO_2$  (blue). Inset of a) shows the crystal structure of  $La_{0.8}Sr_{0.2}NiO_2$ . b) Temperature dependence of the in-plane resistance R(T) of thin film. Inset: Zoom-in view of R(T) near the superconducting transition, showing  $T_c^{\text{onset}} = 18.8$  K.

and  $H_{c2}^c$  ( $H \parallel c$ ) estimated by simply linear extrapolating  $H_{c2}(T)$  to 0 K are relatively small ~ 14 T and 11 T. At the same time, a prominent low-temperature upturn in  $H_{c2}(T)$  has been observed.[18] Superconductivity of La-, Pr- and Nd-nickelates has also been investigated.[19–21] The unique polar and azimuthal angle-dependent magnetoresistance observed in Nd-nickelate can be understood as a magnetic contribution from Nd<sup>3+</sup> 4f moments, regardless of the specific doping.[22] It is also striking that  $H_{c2}$  of the La- and Pr-nickelate thin film substantially exceeds the conventional Pauli limit.[22–24] Therefore, the study of La- and Pr-nickelates without the influence from 4f moments can reveal the intrinsic properties of NiO<sub>2</sub> plane.

Until now, the reported values of  $H_{c2}$  for infinite layer nickelates are still relatively small, much lower than those of cuprates and Iron-based superconductors (IBSs).[15, 25, 26] Is the small  $H_{c2}$  the intrinsic characteristic of infinite layer nickelates? Is the upturning behavior of  $H_{c2}$  at low temperature related to rare earth elements or disorder? In this letter, we studied the temperature and polar angle dependence of  $H_{c2}$  in a highquality La<sub>0.8</sub>Sr<sub>0.2</sub>NiO<sub>2</sub> thin film with  $T_c \sim 18.8$  K, by measuring resistance under a pulsed magnetic field up to 56 T. The  $H_{c2}$  at 0 K for  $H_{c2}^{ab}$  and  $H_{c2}^{c}$  are estimated to be  $\sim 52$  T and  $\sim 40$  T, which are the largest among infinite-layer nickelate superconductors reported so far. In addition, the angle-dependent measurements of  $H_{c2}$ 

Thin film of the precursor  $La_{0.8}Sr_{0.2}NiO_3$  with thickness of ~ 6.8 nm was grown by molecular beam epitaxy (MBE) on the TiO<sub>2</sub> - terminated SrTiO<sub>3</sub> (001) substrate, with substrate temperature of 600 °C and an oxidant background pressure of ~ 1 × 10<sup>-5</sup> Torr using the distilled ozone during the reaction. For stoichiometry and growth parameters, we used the optimal conditions previously reported. To obtain the infinite-layer structure, the

mixtures of precursor and CaH<sub>2</sub> powder ( $\sim 0.1$  g) were sintered at 310 °C for 4 h, with warming (cooling) rate of 10 – 15°C/min. The film structure was characterized by X-ray diffraction (XRD) with Cu-K $\alpha$  radiation on a Bruker D8 Discover diffractometer. Electrical resistance was measured up to 9 T on a Quantum Design Physical Property Measurement System (PPMS - 9 T) and in pulsed field up to 56 T at Wuhan National High Magnetic Field Center using a standard four-probe technique.

Figure 1a shows the XRD patterns of the perovskite  $La_{0.8}Sr_{0.2}NiO_3$  (red) and infinite-layer thin film  $La_{0.8}Sr_{0.2}NiO_2$  (blue), with only (00l) peaks observed. The illustration shows the structure of  $La_{0.8}Sr_{0.2}NiO_2$ . The shift of (00l) peaks indicate the transition of perovskite structure to infinite layer structure. Furthermore, we have studied atomic arrangement before using high-angle annular dark-field scanning transmission electron microscopy (HAADF-STEM) and energy-dispersive X-ray spectroscopy (EDS).[24] The Ruddlesden-Popper stacking faults are not observed. Highly ordered arrangements of La, Sr and Ni atoms and sharp interfaces are also observed without obvious defects such as cation intermixing and stacking. The high quality of our thin film is also reflected in the significant enhancement of  $T_{\rm c}$ . The value of  $T_{\rm c}$  is ~ 18.8 K, as shown in Figure 1d, which is more than twice larger than that of  $\sim 8$  K in previous reports.[19, 22, 27]

Temperature dependence of in-plane resistance with  $H \parallel c$  and  $H \parallel ab$  under fields from 0 to 9 T are shown in Figure 2c-d. The resistive transition shifts towards lower T under higher fields. Small broadening is recognized with increasing H, particularly for  $H \parallel ab$ . Figure 2a-b show the in-plane resistance of La<sub>0.8</sub>Sr<sub>0.2</sub>NiO<sub>2</sub> thin film as a function of the magnetic fields. We obtain the  $H_{c2}^{ab}$  (circle symbol) and  $H_{c2}^c$  (diamond symbol) in Figure 2e by the criterion of 50% of the normal-state resistance values  $R_n$ , where the determination of  $R_n$  is shown in



FIG. 2. The magnetic field dependence of resistance for La<sub>0.8</sub>Sr<sub>0.2</sub>NiO<sub>2</sub> with (a)  $H \parallel c$  at 2, 3, 4.2, 5, 6, 8, 10, 12, 14, 16, and 17 K, (b)  $H \parallel ab$  at 2, 3, 4.2, 5, 6, 8, 10, 12, 14, 16, 17, and 18 K. Temperatures dependence of resistance for (c)  $H \parallel c$  and (d)  $H \parallel ab$  under magnetic fields from 0 to 9 T. (e)  $H_{c2}$  represents the upper critical field for  $H \parallel c$  and  $H \parallel ab$  determined by taking a criterion of 50%  $R_n$ ; Black and green lines are WHH and two-band fitting curves, respectively. (f) Anisotropy of the upper critical field  $\gamma = H_{c2}^{ab} / H_{c2}^c$ . (g-h) The  $H_{c2}$  of  $R_{0.8}$ Sr<sub>0.2</sub>NiO<sub>2</sub> (R = La, Pr or Nd) under (g)  $H \parallel ab$ , (h)  $H \parallel c$  are derived from the report of Harold Y. Hwang *et al.*. The obtained data was normalized by  $H_{c2}^{WHH}$  (0 K) and  $H_{c2}^{Two-band}$  (0 K) for comparison. Solid lines represent WHH and two-band fit. The pink area represents the region where anomalous upturns of  $H_{c2}$  are observed.

Figure 2c. Obviously, we observe a linear temperature dependence of  $H_{c2}^c$  and a square root temperature dependence of  $H_{c2}^{ab}$  (see Figure 2e). Similar nearly linear  $H_{c2}^cT$  has been observed in most IBSs, suggesting that the spin paramagnetic effect is negligible when  $H \parallel c$  (or much smaller than  $H \parallel ab$ ) [28–31]. In addition, the  $H_{c2}$  at 0 K for  $H_{c2}^{ab}$  and  $H_{c2}^c$  estimated by simply linear extrapolating  $H_{c2}(T)$  to 0 K are ~ 52 T and 40 T, which are the largest among the reported values in infinite-layer nickelate superconductors. Such value of  $H_{c2}$  is close to that of IBSs "122" sample,[31, 32] which indicates the application potential for the Ni-based superconductors.

In weakly coupled BCS superconductors,  $H_p$  (= 1.86  $\times T_{\rm c}$ ) is the Pauli-limited field, which characterises the binding energy of Cooper pairs.[33] We observed the violations of Pauli-limit ( $H_p = 32.38$  T) in all directions in our work. Ariando et al. observed similar behavior of violating Pauli-limit in the La-nickelates with low  $T_{\rm c}$  [23]. For a spin-singlet superconductor,  $H_{\rm c2}$  is usually smaller than  $H_{\rm p},$  except for some special cases such as the finite-momentum pairing [34], strong spin-orbitcoupling, [35, 36] large pseudogap or strong-coupling exist. Werthamer, Helfand, and Hohenberg (WHH) theory is the most commonly used method to study the behavior of  $H_{c2}$ , taking into account both the spin paramagnetic effect, and the spin-orbit scattering effect. [37] The magnitude of spin paramagnetic effect and spin-orbit scattering are expressed by  $\alpha$  and  $\lambda_{so}$ , respectively.  $H_{c2}^c$ , exhibiting a quasi-linear temperature dependence, can be described better by the two-band model, except for the anomalous upturn at low temperatures.  $H_{c2}^{ab}$  can be fitted well by the WHH mode with  $\alpha = 17$  and  $\lambda_{so} = 0.9$  at T > 5 K. It is interesting to note that when T < 5 K, anomalous upturns of  $H_{c2}^c$  and  $H_{c2}^{ab}$  beyond the upper limit expected from WHH theory are observed. For comparison,  $H_{c2}^{ab}$  normalized by  $H_{c2}^{WHH}$  (0K) and  $H_{c2}^c$  normalized by  $H_{c2}^{Two-band}$  (0K) are shown in Figure 2g-h, respectively. Similar upturn behaviors have also been observed in La<sub>0.8</sub>Sr<sub>0.2</sub>NiO<sub>2</sub> (Cyan Circle) and Pr<sub>0.8</sub>Sr<sub>0.2</sub>NiO<sub>2</sub> (Green diamond).[22]

The anomalous upturns observed in heavy-fermion, [34, 38, 39] organic superconductors, [40, 41] and some IBSs[42] have been discussed to originate from the FFLO state. For conventional s-wave superconductors, the FFLO state is readily destroyed by impurities.[34] In  $La_{0.8}Sr_{0.2}NiO_2$  thin films with different  $T_c$  (i.e. different degrees of disorder), the degree of upturn of  $H_{c2}/H_{c2}^{\rm WHH}$ (0K) is almost the same in the scaled plot (see Figure 2g). Therefore, the high-field SC phase is not related to the degree of disorder. On the other hand, our previous report has estimated that the coherence length  $\xi_0$ is  $\sim 127.6$  Å, much larger than the carrier mean free path  $\lambda_{mfp}$  of 8.2 Å, indicating that the film is in the dirty limit. [24] These evidences suggest that  $H_{c2}$  upturn in nickelate superconductors are not caused by FFLO



FIG. 3. (a-c) Polar angle dependence of  $H_{c2}(\theta)$  at (a) 2 K, (b) 4.2 K and (c) 10 K, respectively. The black solid lines and the green dashed lines are the fitting by 3D GL model and 2D Tinkham model. Inset of (a) shows schematic structure for measurement. Polar plots of the angle-dependent upper critical field at (d) 2 K, (e) 4.2 K and (f) 10 K, respectively.

state. Furthermore, the disorder-independent upturn can also exclude the possibility of Anderson localization effect, but a clean-limit sample is needed for further investigation. Another possible origin of the high-field SC phase is the spin-density wave (SDW). In the heavy-fermion superconductor CeCoIn<sub>5</sub>, an additional SDW was observed to coexist with superconductivity. [43, 44] Hybridization of La 5d and Ni 3d orbital leads to the enhancement of interlayer electron coupling with the decrease of temperature, which may induce the fluctuation of SDW. However, more evidence is needed for the coexistence of SDW and superconductivity in nickelate. The multiple bands effect may also be the origin of low-temperature upwarping, which have been fully discussed in Nd<sub>0.775</sub>Sr<sub>0.225</sub>NiO<sub>2</sub> thin film.[18] Actually,  $H_{c2}^c(T)$  curve could be fitted by the two-band model (see Figure 2e). Until now, the microscopic origin of the high-field phase is still open to debate.

As shown in Figure 2f, the anisotropy  $\gamma \ (= H_{c2}^{ab} / H_{c2}^c)$  monotonically decreases with decreasing temperatures from ~ 10 near  $T_c$  to ~ 1.5 at low temperatures. The value of  $\gamma$  in our high-quality thin film is slightly larger than the previous reports with lower  $T_c$ (7 for La<sub>0.8</sub>Sr<sub>0.2</sub>NiO<sub>2</sub> and 6 for La<sub>0.8</sub>Ca<sub>0.2</sub>NiO<sub>2</sub> near  $T_c$ ).[22] It is worth noting that the large anisotropy observed in La<sub>0.8</sub>Sr<sub>0.2</sub>NiO<sub>2</sub> is different from that of Nd<sub>0.775</sub>Sr<sub>0.225</sub>NiO<sub>2</sub>. For Nd<sub>0.775</sub>Sr<sub>0.225</sub>NiO<sub>2</sub>, isotropic  $H_{c2}$  has been obtained despite the layered crystal structure, quasi-2D band structure  $(d_{x^2-y^2})$  and the thin film geometry. Regarding the Nd<sup>3+</sup> 4f moment's easyplane magneto-anisotropy, the Nd<sup>3+</sup> magnetic susceptibility reaches a peak in plane. [22] This leads to a maximum amplification of local in-plane magnetic field and consequently a stronger suppression of superconductivity. Therefore, the isotropic upper critical field is observed in Nd<sub>0.775</sub>Sr<sub>0.225</sub>NiO<sub>2</sub>.[18] First principle calculations in LaNiO<sub>2</sub> found two small electron-like pockets around the  $\Gamma$  and A points.[4, 45] These electronic pockets are contributed mainly from La-derived orbitals.[4] At about 20%-hole doping, the electron-like pocket around the  $\Gamma$  point nearly disappears, leaving only a diminished three-dimensional (3D) electron pocket around the Apoint.[46] Hence, the anisotropy observed in high-quality  $La_{0.8}Sr_{0.2}NiO_2$  thin films may be an essential feature of infinite-layer nickelate films free from the influence of  $Nd^{3+}$  magnetism. With the decrease of temperatures, orbital hybridization leads to the enhancement of electron coupling strength and the decrease of anisotropy.

To further study the anisotropy, angle dependence of  $H_{c2}$  at 2 K, 4.2 K, and 10 K was measured. Fig. 3 shows the  $H_{c2}(\theta)$  at different temperatures extracted from Figure S1. The polar angle  $\theta$  is defined as the angle between the magnetic field and the *ab* plane. For 3D bulk superconductors, the angle dependence of  $H_{c2}$  can be interpreted by the Ginzburg–Landau (GL) model with formula[47, 48]

$$H_{c2}(\theta) = H_{c2}^{\parallel} / \sqrt{\cos^2 \theta + (H_{c2}^{\parallel} / H_{c2}^{\perp})^2 \sin^2 \theta},$$

where  $H_{c2}^{\perp}$   $(H_{c2}^{\parallel})$  is the upper critical fields with the field

perpendicular (parallel) to the crystal surface. For sufficiently thin films with thickness d satisfying  $d \ll \xi_c$  ( $\xi_c$  is the *c*-axis coherence length), the Tinkham formula is satisfied, which is expressed as[48, 49]

$$\left|\frac{H_{c2}(\theta)sin\theta}{H_{c2}^{\perp}}\right| + \left(\frac{H_{c2}(\theta)cos\theta}{H_{c2}^{\parallel}}\right)^2 = 1$$

Obviously, the 2D Tinkham model fits  $H_{c2}(\theta)$  at 10 K better than the 3D GL model. However, at 4.2 K, the angle dependence of  $H_{c2}$  deviates from the prediction of Tinkham theory. As the temperature decreased to 2 K,  $H_{c2}(\theta)$  conforms to the GL model, manifesting 3D superconducting characteristic. These results suggest the dimensional crossover from 2D to 3D as the temperature decreases.

It is well known that the rare-earth 5*d*-Ni 3*d* orbital hybridization will form an interstitial-*s* orbital, resulting in the existence of extended *s*-wave gaps.[2, 50, 51] The coupling strength between the NiO<sub>2</sub> planes and rare earth spacer planes is enhanced with the decrease of temperature through the establishment of interstitial-*s* orbital, leading to a 2D-to-3D crossover.[52, 53] The multiple bands effect with 2D wave function in high-temperature region and 3D wave function in low-temperature region can also explain the upwarping of  $H_{c2}$  at low temperatures.

For a superconductor to carry the nondissipative supercurrent, the irreversibility field  $H_{irr}$ , is very crucial. As shown in Figure S2, we construct the vortex phase diagram. This phase line actually separates the phase diagram into zero and finite resistive dissipation. The relatively large  $H_{irr}$  of our high-quality thin film confirms the ability to carry lossless current under strong magnetic field, which indicates the great application prospect.

In summary, we reported a high-field study of highquality  $La_{0.8}Sr_{0.2}NiO_2$  thin film with  $T_c^{onset} \sim 18.8$  K. It exhibits large  $H_{c2}$  ( $H_{c2}^{c}(0 \text{ K}) \sim 40 \text{ T}$ ,  $H_{c2}^{ab}(0 \text{ K}) \sim 52 \text{ T}$ ) and  $H_{\rm irr}$ . This combination of high  $T_{\rm c}$ , high  $H_{\rm c2}$  and high  $H_{\rm irr}$  is highly desirable for applications. The anisotropy  $\gamma$  of  $H_{\rm c2}$  decreases monotonically from  $\sim 10$  near  $T_{\rm c}$  to  $\sim$ 1.5 at low temperatures. The evolution of anisotropy is confirmed by the angle dependence measurements of  $H_{c2}$ , which indicates a crossover from 2D to 3D superconducting state. Hybridization of La 5d and Ni 3d orbital leads to the enhancement of interlayer electron coupling with the decrease of temperature, which is thought to be the possible origin of the abnormal upturning of  $H_{c2}$  at low temperatures and 2D-to-3D crossover. These results can help us to compare the nickelates with the cuprates and to understand the high- $T_{\rm c}$  superconducting mechanism.

This work was partly supported by the National Key R&D Program of China (Grant No. 2018YFA0704300), the Strategic Priority Research Program (B) of the Chinese Academy of Sciences (Grant No. XDB25000000), the National Natural Science Foundation of China (Grants No. U1932217).

W.W., W.S. and Y.S. contributed equally to this paper.

- \* Corresponding author: sunyue@seu.edu.cn
- <sup>†</sup> Corresponding author:ynie@nju.edu.cn
- <sup>‡</sup> Corresponding author:zxshi@seu.edu.cn
- A.S. Botana and M. R. Norman. Similarities and differences between LaNiO<sub>2</sub> and CaCuO<sub>2</sub> and implications for superconductivity. *Phys. Rev. X*, 10:011024, Feb 2020.
- [2] C.J. Jia H. Lu E. Paris Y. Tseng X. Feng M. Osada E. Been Y. Hikita Y.D. Chuang Z. Hussain K.J. Zhou A. Nag M. Garcia-Fernandez M. Rossi H.Y. Huang D.J. Huang Z.X. Shen T. Schmitt H.Y. Hwang B. Moritz J. Zaanen T.P. Devereaux M. Hepting, D. Li and W.S. Lee. Electronic structure of the parent compound of superconducting infinite-layer nickelates. *Nature Mater.*, 19(4):381–385, 2020.
- [3] Y. Yang and G. Zhang. Self-doping and the mottkondo scenario for infinite-layer nickelate superconductors. *Frontiers in Physics*, page 783, 2022.
- [4] Q. Gu and H. Wen. Superconductivity in nickel-based 112 systems. *The Innovation*, 3(1):100202, 2022.
- [5] K. Lee S.P. Harvey M. Osada B.H. Goodge L.F. Kourkoutis D. Li, B. Wang and H.Y. Hwang. Superconducting dome in Nd<sub>1-x</sub>Sr<sub>x</sub>NiO<sub>2</sub> infinite layer films. *Phys. Rev. Lett.*, 125:027001, Jul 2020.
- [6] X. Yin C. Li M. Li Z. Huang J. Hu W. Liu G.J. Omar H. Jani Z.S. Lim K. Han D. Wan P. Yang S. Zeng, C.S. Tang, A.T.S. Wee S.J. Pennycook, and A. Ariando. Phase diagram and superconducting dome of infinite-layer Nd<sub>1-x</sub>Sr<sub>x</sub>NiO<sub>2</sub> thin films. *Phys. Rev. Lett.*, 125:147003, Oct 2020.
- [7] S.L. Skornyakov I. Leonov and S.Y. Savrasov. Lifshitz transition and frustration of magnetic moments in infinite-layer NdNiO<sub>2</sub> upon hole doping. *Phys. Rev. B*, 101:241108, Jun 2020.
- [8] M. Osada B.H. Goodge T.C. Wang Y. Lee S. Harvey W.J. Kim Y. Yu C. Murthy S. Raghu L.F. Kourkoutis K. Lee, B. Wang and H.Y. Hwang. Character of the "normal state" of the nickelate superconductors. arXiv:2203.02580, 2022.
- [9] K. Segawa and Y. Ando. Charge localization from local destruction of antiferromagnetic correlation in zndoped YBa<sub>2</sub>Cu<sub>3</sub>O<sub>7-δ</sub>. *Phys. Rev. B*, 59:R3948–R3951, Feb 1999.
- [10] M.M. Martins D. Li M. Osada B. Wang K. Lee Y. Lee Z. Salman T. Prokscha J.M.c Triscone H.Y. Hwang J. Fowlie, M. Hadjimichael and A. Suter. Intrinsic magnetism in superconducting infinite-layer nickelates. *Nat. Phys.*, 18(9):1043–1047, 2022.
- [11] H. Cheng S. Pei X. Zhou J. Chen S. Wang R. Zhao W. Jiang C. Liu M. Huang X. Wang Y. Zhao D. Yu F. Ye-S. Wang Y. Fu, L. Wang and J. Mei. Core-level x-ray photoemission and raman spectroscopy studies on electronic structures in mott-hubbard type nickelate oxide NdNiO<sub>2</sub>. arXiv:1911.03177, 2019.
- [12] A. Nag M. Osada D.F. Li K. Lee B.Y. Wang M. Garcia-Fernandez S. Agrestini Z.X. Shen E.M. Been B. Moritz

T.P. Devereaux J. Zaanen H.Y. Hwang K. Zhou H. Lu, M. Rossi and W. S. Lee. Magnetic excitations in infinitelayer nickelates. *Science*, 373(6551):213–216, 2021.

- [13] M. Klett F. Hotz R.K. Kremer H. Trepka M. Hemmida von Nidda H.A. Krug M. Isobe R. Khasanov H. Luetkens P. Hansmann B. Keimer T. Schäfer R. A. Ortiz, P. Puphal and M. Hepting. Magnetic correlations in infinite-layer nickelates: An experimental and theoretical multimethod study. *Phys. Rev. Res.*, 4:023093, May 2022.
- [14] S. Wan H. Li W. Guo H. Yang Q. Li X. Zhu X. Pan Y. Nie Q. Gu, Y. Li and H. Wen. Single particle tunneling spectrum of superconducting  $Nd_{1-x}Sr_xNiO_2$  thin films. *Nat. Commun.*, 11(1):1–7, 2020.
- [15] A. Gurevich D. C. Larbalestier R. Jin A. S. Sefat M. A. McGuire B. C. Sales D. K. Christen F. Hunte, J. Jaroszynski and D. Mandrus. Two-band superconductivity in LaFeAsO<sub>0.89</sub>F<sub>0.11</sub> at very high magnetic fields. *Nature*, 453(7197):903–905, 2008.
- [16] X. Xu L. Wang W.K. Yeoh X.Z. Xing Z.X.Shi X.L. Wang Y. Du S.X. Dou J.C. Zhuang, Z. Li. Pauli-limited effect in the magnetic phase diagram of  $\text{FeSe}_x \text{Te}_{1-x}$  thin films. *Appl. Phys. Lett.*, 107(22):222601, 2015.
- [17] J. Wang Z. Zhu Y. Zhang N. Zhou B. Qian X. Xu X. Xing, W. Zhou and Z. Shi. Two-band and pauli-limiting effects on the upper critical field of 112-type iron pnictide superconductors. *Sci. Rep.*, 7(1):1–8, 2017.
- [18] B.H. Goodge K. Lee B. Wang, D. Li, L.F. Kourkoutis M.R. Beasley M. Osada, S.P. Harvey, and H.Y. Hwang. Isotropic pauli-limited superconductivity in the infinite-layer nickelate Nd<sub>0.775</sub>Sr<sub>0.225</sub>NiO<sub>2</sub>. *Nat. Phys.*, 17(4):473–477, 2021.
- [19] B.H. Goodge S.P. Harvey K. Lee D. Li L.F. Kourkoutis M. Osada, B. Wang and H.Y. Hwang. Nickelate superconductivity without rare-earth magnetism: (La,Sr)NiO<sub>2</sub>. Adv. Mater., 33(45):2104083, 2021.
- [20] L.E. Chow Y. Cao Z.T. Zhang C.S. Tang X.M. Yin Z.S. Lim J.X. Hu P. Yang S.W. Zeng, C.J. Li and A. Ariando. Superconductivity in infinite-layer nickelate  $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$  thin filmss. arXiv:2105.13492, 2021.
- [21] K. Lee D. Li M. Osada, B.Y. Wang and H.Y. Hwang. Phase diagram of infinite layer praseodymium nickelate  $Pr_{1-x}Sr_xNiO_2$  thin films. *Phys. Rev. Mater.*, 4:121801, Dec 2020.
- [22] Y.T. Hsu M. Osada K. Lee C. Jia C. Duffy D. Li Je. Fowlie M.R. Beasley T.P. Devereaux I.R. Fisher N.E. Hussey B.Y. Wang, T.C. Wang and H.Y. Hwang. Rare-earth control of the superconducting upper critical field in infinite-layer nickelates. arXiv:2205.15355, 2022.
- [23] M. Pierre S.W. Zeng Z.T. Zhang T. Heil J. Deuschle P. Nandi S.K. Sudheesh Z.S. Lim Z.Y. Luo M. Nardone A. Zitouni P.A. van Aken M. Goiran S.K. Goh W. Escoffier L.E. Chow, K.Y. Yip and A. Ariando. Pauli-limit violation in lanthanide infinite-layer nickelate superconductors. arXiv:2204.12606, 2022.
- [24] R. Liu J. Yang J. Li S. Yan H. Sun W. Guo Z. Gu Y. Deng X. Wang W. Sun, Y. Li and Y. Nie. Evidence for quasi-two-dimensional superconductivity in infinite-layer nickelates. arXiv:2204.13264, 2022.
- [25] N. Kozlova G. Behr A. Köhler J. Werner K. Nenkov R. Klingeler J. Hamann-Borrero C. Hess A. Kondrat M. Grobosch A. Narduzzo M. Knupfer J. Freudenberger B. Büchner G. Fuchs, S.L. Drechsler and L. Schultz. High-field pauli-limiting behavior and strongly enhanced

upper critical magnetic fields near the transition temperature of an arsenic-deficient  $LaO_{0.9}\mathbf{F}_{0.1}FeAs_{1-\delta}$  superconductor. *Phys. Rev. Lett.*, 101:237003, Dec 2008.

- [26] M. Cyrot and D. Pavuna. Introduction to superconductivity and high-T<sub>c</sub> materials. World Scientific Publishing Company, 1992.
- [27] Matteo Rossi, Motoki Osada, Jaewon Choi, Stefano Agrestini, Daniel Jost, Yonghun Lee, Haiyu Lu, Bai Yang Wang, Kyuho Lee, Abhishek Nag, et al. A broken translational symmetry state in an infinite-layer nickelate. *Nat. Phys.*, 18(8):869–873, 2022.
- [28] F.F.Balakirev X.C. Wang C.Q.Jin J.L. Zhang, L. Jiao and H.Q. Yuan. Upper critical field and its anisotropy in LiFeAs. *Phys. Rev. B*, 83:174506, May 2011.
- [29] F.F. Balakirev Y. Kohama J. Singleton B. Qian Z.Q. Mao H. Wang M. Fang, J. Yang and H.Q. Yuan. Weak anisotropy of the superconducting upper critical field in Fe<sub>1.11</sub>Te<sub>0.6</sub>Se<sub>0.4</sub> single crystals. *Phys. Rev. B*, 81:020509, Jan 2010.
- [30] E.S. Choi Y. Bang M. Nohara H. Takagi S. Khim, J.W. Kim and K.H. Kim. Evidence for dominant pauli paramagnetic effect in the upper critical field of singlecrystalline FeTe<sub>0.6</sub>Se<sub>0.4</sub>. *Phys. Rev. B*, 81:184511, May 2010.
- [31] F\_F Balakirev S.A. Baily G.F. Chen J.L. Luo H.Q. Yuan, J. Singleton and N.L. Wang. Nearly isotropic superconductivity in (Ba, K) Fe<sub>2</sub>As<sub>2</sub>. *Nature*, 457(7229):565–568, 2009.
- [32] H. Hiramatsu B. Maiorov F.F. Balakirev M. Hirano S.A. Baily, Y. Kohama and H. Hosono. Pseudoisotropic upper critical field in cobalt-doped SrFe<sub>2</sub>As<sub>2</sub> epitaxial films. *Phys. Rev. Lett.*, 102:117004, Mar 2009.
- [33] A.M. Clogston. Upper limit for the critical field in hard superconductors. *Phys. Rev. Lett.*, 9:266–267, Sep 1962.
- [34] Y. Matsuda and H. Shimahara. Fulde-ferrell-larkinovchinnikov state in heavy fermion superconductors. *Journal of the Physical Society of Japan*, 76(5):051005, 2007.
- [35] S.Fujimoto and S.K. Yip. Aspects of spintronics. In Non-Centrosymmetric Superconductors, pages 247–266. Springer, 2012.
- [36] I. Leermakers N.F.Q. Yuan U. Zeitler K.T. Law J.M. Lu, O. Zheliuk and J.T. Ye. Evidence for two-dimensional ising superconductivity in gated MoS<sub>2</sub>. *Science*, 350(6266):1353–1357, 2015.
- [37] K. Maki. Effect of pauli paramagnetism on magnetic properties of high-field superconductors. *Phys. Rev.*, 148:362–369, Aug 1966.
- [38] K. Ishida H.S. Jeevan C. Geibel S. Kitagawa, G. Nakamine and F. Steglich. Evidence for the presence of the fulde-ferrell-larkin-ovchinnikov state in CeCu<sub>2</sub>Si<sub>2</sub> revealed using <sup>63</sup>Cu NMR. *Phys. Rev. Lett.*, 121:157004, Oct 2018.
- [39] C. Capan P.G. Pagliuso A. Bianchi, R. Movshovich and J.L. Sarrao. Possible fulde-ferrell-larkin-ovchinnikov superconducting state in CeCoIn<sub>5</sub>. *Phys. Rev. Lett.*, 91:187004, Oct 2003.
- [40] M.S. Nam A. Ardavan M. Kurmoo J. Singleton, J.A. Symington and P. Day. Observation of the fulde-ferrell-larkin-ovchinnikov state in the quasitwo-dimensional organic superconductor κ-(BEDT-TTF)<sub>2</sub>Cu(NCS)<sub>2</sub> (BEDT-TTF= bis (ethylene-dithio) tetrathiafulvalene). Journal of Physics: Condensed Matter, 12(40):L641, 2000.

- [41] K. Cho C.C. Agosta B. Fravel W.A. Coniglio, L.E. Winter and L.K. Montgomery. Superconducting phase diagram and fflo signature in  $\lambda$ -(BETS)<sub>2</sub>GaCl<sub>4</sub> from rf penetration depth measurements. *Phys. Rev. B*, 83:224507, Jun 2011.
- [42] N.F.Q. Yuan J. Shen T. Wolf C. Cho, J. H. Yang and R. Lortz. Thermodynamic evidence for the fulde-ferrelllarkin-ovchinnikov state in the KFe<sub>2</sub>As<sub>2</sub> superconductor. *Phys. Rev. Lett.*, 119:217002, Nov 2017.
- [43] C. Niedermayer M. Sigrist B. Padmanabhan M. Zolliker A.D. Bianchi R. Movshovich E.D. Bauer-J.L. Sarrao M. Kenzelmann, Th. Straessle and J.D. Thompson. Coupled superconducting and magnetic order in CeCoIn<sub>5</sub>. *Science*, 321(5896):1652–1654, 2008.
- [44] N. Egetenmeyer J.L. Gavilano Th. Strašsle A.D. Bianchi E. Ressouche R. Movshovich E.D. Bauer-J.L. Sarrao M. Kenzelmann, S. Gerber and J.D. Thompson. Evidence for a magnetically driven superconducting Q phase of CeCoIn<sub>5</sub>. *Phys. Rev. Lett.*, 104(12):127001, 2010.
- [45] K. Suzuki T. Kotani H. Aoki H. Sakakibara, H. Usui and K. Kuroki. Model construction and a possibility of cupratelike pairing in a new d<sup>9</sup> nickelate superconductor (Nd, Sr)NiO<sub>2</sub>. *Phys. Rev. Lett.*, 125:077003, Aug 2020.
- [46] Y. Lu F. Deng, P. Jiang and Z. Zhong. First-principle study of Sr-doping effect in  $Nd_{1-x}Sr_xNiO_2$ . Europhysics Letters, 135(6):67001, nov 2021.

- [47] W. Zhou X. Zhou Q.P. Ding K. Iida R. Hühne L. Schultz T. Tamegai F.F.Yuan, Y. Sun and Z.X. Shi. Anisotropy of iron-platinum-arsenide Ca<sub>10</sub>(Pt<sub>n</sub>As<sub>8</sub>)(Fe<sub>2-x</sub>Pt<sub>x</sub>As<sub>2</sub>)<sub>5</sub> single crystals. Appl. Phys. Lett., 107(1):012602, 2015.
- [48] H. Zhao J. Feng Y. Pan N. Zhou Y. Zhang B. Qian W. Zhou, X. Xing and Z. Shi. Anomalous electron doping independent two-dimensional superconductivity. *New Journal of Physics*, 19(7):073014, jul 2017.
- [49] F.E. Harper and M. Tinkham. The mixed state in superconducting thin films. *Phys. Rev.*, 172:441–450, Aug 1968.
- [50] Y. Yang Z. Wang, G.M. Zhang and F.C. Zhang. Distinct pairing symmetries of superconductivity in infinite-layer nickelates. *Phys. Rev. B*, 102:220501, Dec 2020.
- [51] X. Wang J. Hu Y. Gu, S. Zhu and H. Cheni. A substantial hybridization between correlated Ni-d orbital and itinerant electrons in infinite-layer nickelates. *Communications Physics*, 3(1):84, 2020.
- [52] D. Salloum P. Gougeon M. Potel J.X. Zhu C. Panagopoulos E.E.M. Chia S. Mitra, A.P. Petrovi ć. Dimensional crossover in the quasi-one-dimensional superconductor Tl<sub>2</sub>Mo<sub>6</sub>Se<sub>6</sub>. *Phys. Rev. B*, 98:054507, Aug 2018.
- [53] P. Nandi S.W. Zeng Z.T. Zhang X.M. Du Z.S. Lim Elbert E. M. Chia L.E. Chow, S. Kunniniyil Sudheesh and A. Ariando. Pairing symmetry in infinite-layer nickelate superconductor. arXiv:2201.10038, 2022.

## Supplemental information

The magnetoresistance measurements of  $La_{0.8}Sr_{0.2}NiO_2$  at different angles are shown in Figs. S1(a-c), (a) T = 2 K, (b) T = 4.2 K and (c) T = 10 K. The polar angle  $\theta$  is defined as the angle between the field and the ab plane.

In Fig. S2, we determined  $H_{c2}$  and irreversibility field  $H_{irr}$  by taking the criterions of 90%  $R_n$  and 1%  $R_n$ , and

construct the vortex phase diagram. The following three different regimes are clearly distinguishable: (1) Normal state, the region above  $H_{c2}$ . (2) Vortex-liquid phase, which governs the region between the  $H_{irr}$  line and the  $H_{c2}$  line. (3) Vortex-glass state. The relatively large  $H_{irr}$  of our high-quality thin film confirms the ability to carry lossless current under strong magnetic field, which indicates the great application prospect.



FIG. S1. Magnetoresistance at different angles at (a) 2 K, (b) 4.2 K and (c) 10 K respectively.



FIG. S2. Vortex phase diagram for  $La_{0.8}Sr_{0.2}NiO_2$  thin film with (a)  $H \parallel ab$  and (b)  $H \parallel c$ .  $H_{c2}$  represents the upper critical field obtained from the 90% of the normal state resistance.  $H_{irr}$  is an irreversible field obtained by 1% of the normal resistance.