arXiv:2401.13318v1 [cond-mat.str-el] 24 Jan 2024

Magnetic structure and Ising-like antiferromagnetism in the bilayer triangular lattice compound NdZnPO

Han Ge,¹ Tiantian Li,¹ S. E. Nikitin,² Nan Zhao,¹ Fangli Li,¹ Huanpeng Bu,¹ Jiayue

Yuan,¹ Jian Chen,¹ Ying Fu,^{1,3} Jiong Yang,⁴ Le Wang,^{5,6} Ping Miao,^{7,8} Qiang Zhang,⁹ Inés Puente-Orench,^{10,11} Andrey Podlesnyak,⁹ Jieming Sheng,^{12,13,*} and Liusuo Wu^{1,3,14,†}

¹Department of Physics, Southern University of Science and Technology, Shenzhen 518055, China ²Laboratory for Neutron Scattering and Imaging,

Paul Scherrer Institut, CH-5232 Villigen-PSI, Switzerland

³Quantum Science Center of Guangdong-Hong Kong-Macao Greater Bay Area (Guangdong), Shenzhen 518045, China

⁴Department of Chemistry, Southern University of Science and Technology, Shenzhen 518055, China

⁵Shenzhen Institute for Quantum Science and Engineering,

Southern University of Science and Technology, Shenzhen 518055, China

⁶International Quantum Academy, Shenzhen 518048, China

⁷Institute of High Energy Physics, Chinese Academy of Sciences, Beijing 100049, China

⁸Spallation Neutron Source Science Center, Dongguan 523803, China

⁹Neutron Scattering Division, Oak Ridge National Laboratory, Oak Ridge, Tennessee 37831, USA

¹⁰Instituto de Nanociencia y Materiales de Aragón (INMA),

CSIC-Universidad de Zaragoza, Zaragoza 50009, Spain

¹¹Institut Laue-Langevin, 71 Avenue des Martyrs, CS 20156, CEDEX 9, 38042 Grenoble, France

¹²School of Physical Sciences, Great Bay University, Dongguang 523000, China

¹³Great Bay Institute for Advanced Study, Dongguang 523000, China

¹⁴Shenzhen Key Laboratory of Advanced Quantum Functional Materials and Devices,

Southern University of Science and Technology, Shenzhen 518055, China

(Dated: January 25, 2024)

The complex interplay of spin frustration and quantum fluctuations in low-dimensional quantum materials leads to a variety of intriguing phenomena. This research focuses on a detailed analysis of the magnetic behavior exhibited by NdZnPO, a bilayer spin-1/2 triangular lattice antiferromagnet. The investigation employs magnetization, specific heat, and powder neutron scattering measurements. At zero field, a long-range magnetic order is observed at $T_{\rm N}$ = 1.64 K. Powder neutron diffraction experiments show the Ising-like magnetic moments along the *c*-axis, revealing a stripe-like magnetic structure with three equivalent magnetic propagation vectors. Application of a magnetic field along the *c*-axis suppresses the antiferromagnetic order, leading to a fully polarized ferromagnetic state above $B_{\rm c} = 4.5$ T. This transition is accompanied by notable enhancements in the nuclear Schottky contribution. Moreover, the absence of spin frustration and expected fieldinduced plateau-like phases are remarkable observations. Detailed calculations of magnetic dipolar interactions revealed complex couplings reminiscent of a honeycomb lattice, suggesting the potential emergence of Kitaev-like physics within this system. This comprehensive study of the magnetic properties of NdZnPO highlights unresolved intricacies, underscoring the imperative for further exploration to unveil the underlying governing mechanisms.

INTRODUCTION I.

Geometrically frustrated quantum magnets have drawn significant interest over the past few decades [1– 5]. The two-dimensional (2D) triangular antiferromagnetic (AFM) spin lattice serves as a prototype example among different models of frustrated spins. Subsequent theoretical and numerical studies have been conducted to reveal the ground state of the two-dimensional triangular antiferromagnet [6-9]. Nevertheless, there are still many problems to be solved, and further efforts are necessary to address the challenges.

Previous studies have been focused on the d-electron based systems, such as the organic Mott insulator κ -

 $(BEDT-TTF)_2Cu_2(CN)_3$ with a nearly isotropic triangular lattice [10], the orthorhombic perovskite compounds Cs_2CuBr_4 with an anisotropic triangular lattice [11], and the Co-based compound Ba₃CoSb₂O₉ with an ideal equilateral triangular lattice [12]. Many of these compounds have very high critical fields, making it challenging to carefully investigate the complete phase diagram through thermodynamic techniques and neutron scattering experiments [13–15]. On the other hand, rare-earth based compounds typically exhibit relatively smaller critical fields due to the large effective g-factor arising from strong spin-orbit coupling [16, 17]. In addition, the crystalline electrical field (CEF) usually results in a degenerate doublet ground state, which allows us to describe it by a Hamiltonian with an effective spin $S_{eff} = 1/2$ [18, 19]. In recent years, significant focus has turned to rareearth-based quantum magnets like $RMgGaO_4$ (R = Yb, Tm) [20, 21] and AYbCh₂ (A=Na, K, Cs; Ch = O, S,

^{*} Corresponding author: shengjm@gbu.edu.cn

[†] Corresponding author: wuls@sustech.edu.cn

Se) [22–26]. These materials have garnered attention due to the observation of various novel phenomena, such as Kosterlitz-Thouless phase transitions, broad continuumlike excitations featuring a spinon Fermi surface, quantum spin liquid ground state, field-tunable quantum disordered ground state, etc.

In addition to this, another example of achieving robust spin frustration within a two-dimensional lattice is the Kitaev model. This model involves interacting spins positioned on a honeycomb lattice, characterized by the bond-directional exchange interaction [27]. What makes this model particularly intriguing is its exact solution, offering the initial concrete demonstration of how a quantum spin liquid with fractionalized excitations can arise in a two-dimensional spin model. In recent years, many 4d and 5d materials with 2D honeycomb lattices have been explored, including the iridates, α -Na₂IrO₃ [28], α -Li₂IrO₃ [29], and H₃LiIr₂O₆ [30], and the halide α -RuCl₃ [31]. These compounds exhibit stronger spinorbital couplings than 3d systems, and they were believed to have Kitaev-like anisotropic exchange interactions [28-31]. Particularly, recent studies on the honeycomb halide compound α -RuCl₃ reveal that it can approximately realize the Kitaev spin liquid phase in an intermediate field region between the low-field zigzag ordered state and the high-field polarized phase [32, 33]. Additionally, the thermal Hall conductivity measurements indicate a half-integer quantized state in these intermediate fields. Although the precise nature of this state is still under debate, the underlying physics has become increasingly important. Furthermore, the bilayer structure of the rare-earth isotropic triangular lattice compound YbOCl, where Yb³⁺ ions can be considered as a honeycomb lattice, positions it as a promising candidate for probing the Kitaev quantum spin liquid [34, 35].

Motivated by these studies, we explored a spin lattice consisting of two magnetic triangular layers arranged in an A-B stacking configuration. In this bilayer structure, the lattice sites of one triangular layer project to the centers of the other triangular plaquettes next to it. This is equivalent to a honeycomb lattice with nearest and next-nearest neighbor interaction, and each triangular laver can be treated as one of the two sublattices of the honeycomb lattice [36]. The ground state of this bilayer triangular lattice is highly degenerated, and strong spin frustration and related phenomena are then expected. It was reported that the rare-earth based family compound RZnPO (R=rare earth) adopted a trigonal crystal structure, where the magnetic rare-earth ions form two-dimensional bilayer triangular lattices [37-39]. In this manuscript, our attention is directed towards the Neodymium (Nd) based compound NdZnPO. We observed a long-range stripe-like order below $T_{\rm N} = 1.64$ K, and the magnetic structure of NdZnPO was thoroughly examined through powder neutron scattering experiments. We constructed a field-temperature phase diagram utilizing magnetization and specific heat measurements, extending our analysis to temperatures as low as

60 mK. Simultaneously, CEF analysis was conducted, uncovering an Ising-like magnetic ground state.

II. EXPERIMENTAL METHOD

NdZnPO single crystals were grown using the flux method [37]. High-purity starting materials, including zinc oxide [ZnO, Aladdin, 99.999%], neodymium [Nd, Alfa Aesar, 99.9%], and phosphorus [P, Aladdin, 99.999%], were mixed in an alumina crucible with NaCl/KCl as the flux. The mixture was heated up to 900°C and then slowly cooled down to 300°C at a rate of 5°C/hour. The excess flux was removed with distilled water. Hexagonal-shaped NdZnPO single crystals with sizes around $0.2 \times 0.2 \times 0.05 \text{ mm}^3$ were obtained. The crystal structure of NdZnPO was verified using the Bruker D8 VENTURE diffractometer. Measurements of magnetization, magnetocaloric effect (MCE), and specific heat were carried out using the commercial Quantum Design Magnetic Property Measurement System and the Physical Property Measurement System with the dilution refrigerator insert.

Inelastic neutron scattering experiment was performed at the Swiss spallation neutron source (SINQ), hosted at the Paul Scherrer Institute (PSI). The experiment utilized a thermal neutron triple-axis spectrometer EIGER with fixed $E_{\rm f}$ = 14.68 meV. A pyrolotic graphite filter was installed between the sample and the analyzer to suppress higher-order scattering. The powder sample with $m \approx 2$ g, was enclosed in a 10 mm aluminum can and cooled down using an orange cryostat. Neutron powder diffraction experiment was carried out using the high-intensity two-axis powder diffractometer, D1B, at the Institut Laue-Langevin (ILL). The neutron wavelength was fixed at $\lambda = 2.52$ Å, with a full width at half maximum (FWHM) of $\sim 0.3^{\circ}$ [40]. The powder sample, ~ 2 g in mass, was cooled down to 60 mK using a dilution refrigerator insert. The dataset is available from the ILL database [41].

III. RESULTS AND DISCUSSIONS

A. Crystal structure, CEF and single-ion anisotropy

NdZnPO exhibits a trigonal crystal structure characterized by the space group $R\bar{3}m$ (No.166), featuring refined lattice parameters of a = b = 3.976 Å and c = 30.955 Å [37]. As shown in Fig. 1(a), the magnetic Nd³⁺ ions are located at the center of the Nd-P-O polyhedron, forming a bilayer triangular network in the crystal *ab* plane. Within each triangular layer, the nearest neighbor distance is 3.976 Å, while the nearest neighbor distance between adjacent layers is 3.748 Å. Within this bilayer structure, the upper triangular layer is center-stacked on top of the lower triangular layer



FIG. 1. (a) Crystal structure of NdZnPO. (b) The bilayer triangular lattice of magnetic Nd³⁺ ions in the *ab* plane. (c) Representation of an equivalent honeycomb lattice structure illustrating the nearest-neighbor (*J*) and next-nearest neighbor (*J'*) interactions. Each triangular layer serves as a sublattice within the honeycomb lattice. (d) Nd-P-O polyhedron with local point symmetry $C_{3v}(3m)$ at the Nd site. (e) Inelastic scattering over the wave vector Q = 3 Å⁻¹ at different temperatures, demonstrating the first CEF level around 9.06 meV. The elastic peak and the first excited CEF peak have been fitted with a Gaussian function, as indicated by the solid lines. Inset: A scheme of five isolated CEF doublets. (f) Inelastic scattering intensity at 10 K as a function of the wave vector with a constant energy transfer of $\hbar \omega = 9$ meV. (g) Temperature dependence of the magnetic susceptibility $\chi(T)$ measured in a field of 0.1 T along the *c* direction and in the ab-plane. The solid red lines are the fits using the Curie-Weiss law. (h) Isothermal magnetization M(B) measured at 2 K with the field applied along and perpendicular to the *c* axis.

(Fig. 1(b)), which is equivalent with a 2D honeycomblike lattice with nearest-neighbor interactions (J) and next-nearest-neighbor interactions (J') from the topside view (Fig. 1(c)). These bilayer triangular planes are then alternatively stacked with a 'CA''AB''BC''CA' type sequence along the c-axis. The non-magnetic Zn and P ions are stuffed in between these bilayer planes, resulting in well-separated double magnetic triangular layers with an inter-double layer distance of about 7.356 Å.

Quantum fluctuations are usually more pronounced for magnetic ions with small spin values, such as S = 1/2. The angular momentum J in rare-earth ions is often regarded as a 'classical' moment due to its large angular moment. However, as these rare-earth ions form crystals, the situation can be quite different. In the local crystalline environment of NdZnPO, the magnetic Nd³⁺ ions are surrounded by four nearby O²⁻ ions and three P⁴⁺ ions, resulting in a local point symmetry $C_{3v}(3m)$ (Fig. 1(d)). In this local point symmetry, the degenerate 2J + 1 = 10 (L = 6, S = 3/2, and J = 9/2) multiplet states of Nd³⁺ split into five doublet CEF states. To describe these CEF states, calculations based on the point-charge model have been performed using the software package MCPHASE [42, 43]. By choosing the local z-axis along the crystal c axis, the calculated ground doublet states are

$$|E_{0\pm}\rangle = 0.955 |\pm 9/2\rangle \mp 0.268 |\pm 3/2\rangle + 0.128 |\mp 3/2\rangle.$$
 (1)

These ground doublet states are dominated by wave functions $|\pm 9/2\rangle$, suggesting an Ising-like character with moments mainly along the easy *c*-axis. The other four excited doublet states are located at 13.7, 19.6, 26.5, and 42.7 meV, respectively, which are all well separated from the ground doublet states. Thus, the magnetic properties are mainly governed by the ground doublet states at sufficiently low temperatures, and the low-temperature properties can be described using an effective model of spin $S_{\rm eff} = 1/2$. However, we have to notice that, in the case of a nearly pure Ising-like ground state with wave functions (1), the term that flips the upside and downside spins is negligibly small,

$$\langle E_{0\mp} | S^{\pm} | E_{0\pm} \rangle \simeq 0. \tag{2}$$

This indicates that neutrons can neither flip these Isinglike Nd^{3+} moments nor make them propagate, resulting



FIG. 2. (a) Temperature-dependent specific heat C of NdZnPO (black circles, $C_{\rm Nd}$) and YZnPO (green circles, $C_{\rm Y}$) in zero field. (b) Temperature dependence of the magnetic specific heat (red circles, $C_{\rm M} = C_{\rm Nd} - C_{\rm Y}$) with nonmagnetic contributions removed. The temperature-dependent normalized integrated magnetic entropy $S_{\rm M}/\rm{Rln2}$ is shown on the right axis (blue line). A total entropy of $R\rm{ln2}$ is released around 7 K.

in an effective Ising-like spin Hamiltonian. Similar situations have been found in the rare-earth perovskites, where spin waves or any excitations within the ground doublet states are missing [44, 45]. However, the CEF excitation from the ground doublet to the first excited states is still allowed.

Figure 1(e) displays the inelastic neutron spectra taken at T = 10, 50 and 100 K. A single excitation centered around $\Delta_1 = 9.06$ meV was observed for all temperatures (Fig. 1(e)), which is close to the location of the first excited states calculated from the point charge model. Additionally, the scattering intensity at this center position decreases with increasing the wave vector $|\mathbf{Q}|$, confirming the magnetic origin of this excitation (Fig. 1(f)). Fitting the spectra with a Gaussian function (solid line), we found that the elastic peak is resolution-limited with the FWHM around 0.79 meV. However, the FWHM of the inelastic peak around 9.06 meV is about 1.93 meV (the instrumental resolution is 1.2 meV at 9 meV energy transfer), indicating that there might exist a weak spin wave dispersion at the first excited state, CEF-phonon hybridization or disorder. These two scenarios are often considered together with spin-wave dispersion mentioned above, when a CEF peak is not resolution-limited. Also, no other spin excitations were observed at lower energy within the resolution of our setup as expected for an Ising-like spin Hamiltonian [44, 45].

The temperature-dependent magnetic susceptibility of NdZnPO is shown in Fig. 1(g), with the external magnetic field applied in the *ab*-plane (B||ab) and along the *c*-axis (B||c). The Curie-Weiss law does not apply here due to the effect of the CEF excitations at low energy. Instead, significant single-ion anisotropy was observed between the two field directions, which is also evident in the field-dependent magnetization (Fig. 1(h)). The magnetization measured at 7 T for B||c is about twice as large as the measured value for B||ab, which is consistent with the calculated single ion ground states with Ising-like moments along the *c*-axis.

B. Zero field antiferromagnetic ground state

Specific heat measurements down to 0.1 K have been conducted to investigate the low-temperature magnetic properties of NdZnPO. Figure 2(a) displays the zerofield temperature-dependent specific heat C(T) (black circles), while the nonmagnetic isostructural compound YZnPO was employed to estimate the specific heat of lattice contributions (green circles). The magnetic specific heat $C_{\rm M}$ was then obtained by subtracting the lattice contributions (red circles in Fig. 2(b)). A sharp peak was observed at 1.64 K, indicating the establishment of long-range magnetic order. The integrated magnetic entropy exhibits a full entropy of $R \ln 2$ around 7 K, confirming a doublet ground state (blue line in Fig. 2(b)). Additionally, the integrated magnetic entropy becomes larger than $R \ln 2$ above 7 K. These contributions are likely from the first excited CEF levels. However, we noticed that only about 40% of the full entropy is released at $T_{\rm N} = 1.64$ K. This observation is similar to many other low-dimensional quantum magnets, indicating that the magnetic moments are not completely frozen in the ordered states [46]. In other words, many moments fluctuate even in the magnetically ordered state.

Powder neutron diffraction experiments were performed to determine the magnetic structure of NdZnPO. Figure 3(a,b) presents the powder diffraction patterns measured at 2 K and 0.3 K, respectively. The diffraction pattern measured at 2 K can be well refined with the trigonal rhombohedral crystal structure of the space group $R\bar{3}m$ (No.166), consistent with our single-crystal X-ray diffraction results. Only 0.42% P₂O₅ has been identi-



FIG. 3. Rietveld refinement of neutron powder diffraction patterns for NdZnPO at (a) 2 K and (b) 0.3 K. The red points represent actual data, and the black lines represent the Rietveld fitting to the data. The difference curve is shown in the blue line. (c) Schematic of three equivalent magnetic propagation vectors $\mathbf{Q_1} = (0.5, 0, 0.5)$, $\mathbf{Q_2} = (0, -0.5, 0.5)$, and $\mathbf{Q_3} = (-0.5, 0.5, 0.5)$, from Γ point to M point. The black hexagon represents the Brillouin zone in reciprocal space. (d) Neutron powder diffraction pattern of NdZnPO at different temperatures with the first two peaks (0,0,3) and (0.5,0,0.5). The circles represent actual data, and the black lines depict Gaussian fitting to the data. Temperature evolution of (e) the integrated intensity and (f) the fitted FWHM (Γ) of the two peaks.

fied as an additional impurity phase within the powder sample. However, an additional reflection located at $Q = 0.916 \text{ Å}^{-1}$ was observed in the powder neutron diffraction data at 0.3 K, indicating the magnetic origin. Using the K-search program of the FullProf Suite, we found that this magnetic reflection can be indexed with three equivalent commensurate magnetic propagation vectors: $\mathbf{Q_1} = (1/2, 0, 1/2), \ \mathbf{Q_2} = (0, -1/2, 1/2),$ and $Q_3 = (-1/2, 1/2, 1/2)$, as illustrated in Fig. 3(c). Figure 3(d) shows powder diffraction patterns taken at several different temperatures between 0.3 K and 2 K. Both the magnetic and nuclear peaks are well described by Gaussian functions. The temperature-dependent peak intensity and the FWHM (Γ) of the peak are presented in Fig. 3(e)-(f). The magnetic reflection disappears at the transition temperature around 1.6 K, consistent with our specific heat observations. The peak intensity of the (0.0.3) nuclear reflection at $Q = 0.606 \text{ Å}^{-1}$ does not change with temperature. As the temperature decreases, the Γ of the nuclear peak is limited by instrument resolution, maintaining a constant value. In contrast, the Γ of the magnetic peak is larger and shows an increase as the transition temperature is approached (Fig. 3(f)). Note, that at the lowest temperature we measured, ~ 60 mK, the intensity of the magnetic peak is still not saturated, meaning that the magnetic structure may have some thermal fluctuations or the transition is not finished.

Representation analysis was applied to explore the potential magnetic structures in NdZnPO. Four different irreducible representations (IRs) describe the possible spin configurations for Nd³⁺ ions located at (0,0,0.38118) with the propagation vector $\mathbf{Q}_1 = (1/2, 0, 1/2)$. The basis vectors for IRs $\Gamma_1, \Gamma_2, \Gamma_3$, and Γ_4 are listed in Table I. Among them, IRs Γ_2 and Γ_3 permit the orientation of moments within the *ab* plane only, contradicting the results of magnetization measurements. IRs Γ_1 and Γ_4 allow the magnetic moment to have both in-plane and out-plane components, consistent with the experimental data. Rietveld refinement indicates that IRs Γ_4 could

TABLE I. Basis vectors of the irreducible representations (IR) for NdZnPO with magnetic wave-vector $\mathbf{Q_1} = (0.5, 0, 0.5)$ and Nd site at (0,0,0.38118).

IR	Basis vector	$Nd_1(0,0,0.38118)$			$Nd_2(0,0,0.61882)$		
		m_x	m_y	m_z	m_x	m_y	m_z
Γ_1	ψ_1	2	1	0	-2	-1	0
	ψ_2	0	0	2	0	0	-2
Γ_2	ψ_3	0	-2	0	0	-2	0
Γ_3	ψ_4	0	-2	0	0	2	0
Γ_4	ψ_5	2	1	0	2	1	0
	ψ_6	0	0	2	0	0	2



FIG. 4. (a) The magnetic structure of NdZnPO below the ordering temperature refined from the neutron data. The red arrows indicate the ordered Nd spins. (b-d) The spin configuration of the bilayer triangular lattice of Nd³⁺ ions projected onto the ab-plane with the magnetic propagation vectors \mathbf{Q}_1 , \mathbf{Q}_2 , and \mathbf{Q}_3 , respectively. The regular triangle in solid lines and the inverted triangle in dotted lines represent the upper and lower triangular lattice layers respectively. The yellow/blue bar represents the spin-up and spin-down respectively. (e) Possible triple-Q spin configuration in the honeycomb lattice. The yellow symbol +/- represents spin-up and spin-down respectively.

provide the best fit, yielding $R_p = 2.15\%$ and $R_{wp} = 3.04\%$ (Fig. 3(b)). Through the Rietveld refinement, we determine the magnetic structure, which is presented in Fig. 4(a). The ordered magnetic moment is about 1.81(1) μ_B/Nd . All the moments are predominantly aligned along the *c*-axis, displaying a small inclination angle of 1.5° to the *c*-axis.

Based on the three equivalent magnetic propagation vectors $\mathbf{Q_1} = (1/2, 0, 1/2), \ \mathbf{Q_2} = (0, -1/2, 1/2), \ \text{and}$ $\mathbf{Q_3} = (-1/2, 1/2, 1/2)$, there could potentially exist three different magnetic domains for NdZnPO, depicted in Fig. 4(b-d) respectively. Within these magnetic domains, adjacent Nd³⁺ ions (from two different triangular layers) arrange into zig-zag ferromagnetic (FM) stripes along the [010], [100], and [110] crystallographic directions respectively. These stripes then exhibit AFM alignment along the [100], [010], and [1-10] directions. Additionally, due to the three-fold rotation symmetry C_3 for the crystal structure, the magnetic ground state of NdZnPO can be also described by a triple-Q magnetic order which could be understood as a vector sum of the above three magnetic domains, as shown in Fig. 4(e). A honeycomb ring of six Nd³⁺ ions forms a magnetic unit at the position marked by the black circle. The total magnetic moment

inside the black circle is zero. However, since both magnetic ground states show the same diffraction patterns, the triple-Q and single-Q (three magnetic domains) magnetic order cannot be distinguished by zero-field neutron diffraction [47]. To distinguish these two magnetic structures, future studies, such as single-crystal neutron diffraction experiment with magnetic field, are needed.

C. Field-temperature phase diagram of NdZnPO

The field-dependent magnetization at various temperatures below $T_{\rm N}$ with $B \parallel c$ was performed as presented in Fig. 5. A distinct slope change in the magnetization curve was observed at the base temperature of 60 mK (Fig. 5(a)), signifying the transition into a fully polarized state. Accordingly, a peak-like feature was observed at $B_{\rm s} = 4.5$ T in the differential susceptibility, dM/dB, as indicated in Fig. 5(b). To further validate this transition, MCE measurements were conducted. The sample was mounted on a platform made of Sapphire crystal in a high vacuum, and the sample temperature was recorded while sweeping the magnetic field up and down at a rate of 10 Oe/s. The heat was ab-



FIG. 5. (a) Field-dependent magnetization, and (b) magnetic susceptibility dM/dB, measured at 0.06 K with an applied field along the c axis. (c) Magnetocaloric effect measured at a constant system temperature of approximately 90 mK by sweeping the magnetic field up (red) and down (blue) with an applied field along the c direction. (d) Field dependence of magnetization, (e) differential magnetic susceptibility, dM/dB, at different temperatures with the field along the c-axis. (f) Temperature dependence of susceptibility $\chi(T)$ at different fields with the field along the c-axis. (g) The field-temperature magnetic phase diagram overlaid on the contour plots of the magnetic susceptibility dM/dB with the field along the c direction. The magnetic phase boundaries were extracted through M(T) and M(B) measurements, with the saturation field $B_s = 4.5$ T for $B \parallel c$.

sorbed or released at the phase transition, and kink-like anomalies were observed in the field-temperature curve at the phase boundaries (Fig. 5(c)). The critical field determined from the MCE measurements was consistent with the phase boundary established from the differential susceptibility, dM/dB. To illustrate the temperature evolution, field-dependent magnetization was systematically measured at different temperatures, as shown in Fig. 5(d). The peak-like anomalies in dM/dB observed at the phase boundary gradually became smeared with increasing temperature and finally vanished at temperatures above $T_{\rm N}$ (Fig. 5(e)). The temperature dependence of the magnetic susceptibility, $\chi(T)$, is shown in Fig. 5(f). Cusp-like anomalies were observed, signaling the establishment of long-range AFM order. The overall phase diagram under the field was summarized in Fig. 5(g). The phase boundary extracted from the peak positions in the dM/dB and $d\chi/dT$ curves is over-plotted on the contour plot of the differential susceptibility. The AFM order at $T_{\rm N} = 1.64$ K is gradually suppressed to zero temperature at the critical field $B_{\rm s} = 4.5$ T.

Figure 6(a) shows the temperature-dependent specific

heat under different magnetic fields. The sharp, peak-like anomalies indicate the establishment of long-range order. These peaks shift towards lower temperatures as the magnetic field increases. Simultaneously, the peak height is suppressed, indicating that less entropy is released at the transition. This suppression is also apparent in the integrated magnetic entropy, as illustrated in Fig. 6(b). The integrated entropy was about half of the full entropy of $R \ln 2$ at T_N in zero fields. However, as the critical field is approached, the integrated magnetic entropy reduces to only about 10% of $R \ln 2$ at 4.0 T. This hints that the residual entropy might be released at temperatures beyond the transition, possibly implying the persistence of strong short-range correlations near the critical field. However, confirmation of magnetic diffuse scattering at temperatures above the phase transition would require future single-crystal neutron scattering experiments.

Field-dependent specific heat was also measured at various temperatures, as shown in Fig. 6(c) and (d). A broad Schottky-like anomaly was observed at temperatures above $T_{\rm N}$, with the peak positions extending linearly to lower temperatures as the field decreases (blue



FIG. 6. (a) The magnetic specific heat $C_{\rm M}$ and (b) the normalized integrated magnetic entropy $S_{\rm M}/{\rm Rln2}$ as a function of temperature at different magnetic fields with the field along the c-axis. (c-d) Field-dependent magnetic specific heat at different temperatures with the field along the c direction. (e) The field-temperature magnetic phase diagram overlaid on the contour plots of the magnetic heat capacity with the field along the c direction. The magnetic phase boundaries were extracted through $C_{\rm M}(T)$ and $C_{\rm M}(B)$ measurements, with the critical field $B_{\rm c} = 4.5$ T for $B \parallel c$. (f) A magnified phase diagram around the critical point.

stars in Fig. 6(c) and (e)). The Schottky anomaly in the specific heat is a general feature of two-level systems. In the case of NdZnPO, the doublet ground state splits in fields due to the Zeeman effect. Typically, for a system with two discrete flat levels, the peak value in the specific heat of the Schottky anomaly is fixed to be close to 3.6 J/mol K. However, we noticed that the measured peak values in specific heat show a significant deviation as the temperature and field decrease. This indicates that weak dispersion persists in the system, and these discrete levels are not completely flat. This weak dispersion becomes increasingly significant as the Zeeman gap closes when $B \to B_s$. As the measuring temperature was lower than $T_{\rm N}$, the broad Schottky-like anomaly disappears, and instead, a sharp peak-like feature appears at the critical fields (Fig. 6(d)). The transition gradually approaches the saturation field $B_{\rm s} = 4.5$ T as the temperature further decreases. The contour plot of the magnetic phase diagram established by the specific heat measurements is presented in Fig. 6(e). The phase boundaries extracted from the specific heat and the magnetization are consistent with each other.

Additionally, a 'peculiar' feature appears below about

0.3 K. We noticed that the sharp peak-like feature gradually evolves into a broad maximum near the critical field at the base temperature (the bottommost curve in Fig. 6(d)). This broad maximum-like feature extends over a wide field range from about 4 T to 5 T. This is also evident in the contour plot of the temperaturedivided specific heat $C_{\rm M}/T$, as shown in Fig. 6(f). At first glance, it seems like a new 'dome'-shaped phase was induced at the critical field. However, our observations hint that this additional contribution might be attributed to the nuclear Schottky effect. Upon thorough examination, we noticed that this specific field range exactly corresponds to the maximum of the differential susceptibility dM/dB [48], as depicted in Fig. 5(e) and (g). As a result, the internal field, which correlates with the differential susceptibility, is significantly enhanced within this field range. Consequently, it appears that the nuclear moments are polarized by the internal field rather than the external field. This explains why this contribution decreases again when the field exceeds 5 T. Similar behavior has been observed in other rare-earth-based compounds near the saturation field, as documented in previous studies [45]. Furthermore, this effect holds potential for the use of nuclear adiabatic demagnetization cooling techniques under moderate external fields in future applications [48].

IV. CONCLUSION AND DISCUSSION

To conclude, we successfully synthesized high-quality single crystals of NdZnPO, which adopt well-separated bilayer triangular lattices composed of magnetic Nd^{3+} ions. Thermal property measurements, including magnetization and specific heat, have been performed. The experimental results, together with the CEF analysis, revealed a doublet ground state with Ising-like moments aligned along the *c*-axis. In zero magnetic field, a longrange AFM order was established at $T_{\rm N} = 1.64$ K. The magnetic structure has been refined by the powder neutron diffraction measurements. These Ising moments form into FM stripes in the *ab*-plane, with three equivalent magnetic propagation vectors ($\mathbf{Q}_1 = (1/2, 0, 1/2)$), $\mathbf{Q_2} = (0, -1/2, 1/2), \text{ and } \mathbf{Q_3} = (-1/2, 1/2, 1/2)).$ With the external field applied along the easy *c*-axis, this longrange magnetic order was gradually suppressed with a saturation field $B_{\rm s} = 4.5$ T. Additionally, we also noticed that the nuclear Schottky contribution was greatly enhanced by the internal field arising from the 4f-electrons, resulting in a dome-shaped anomaly in specific heat centered around $B_{\rm s}$.

Although the magnetic structure and the magnetic phase diagram of NdZnPO have been established with detailed thermodynamic characterizations, several key issues still need to be clarified in the future. As we mentioned in Section III A, NdZnPO hosts well-separated 2D bilayer triangular lattices with the nearest neighbor distances between these bilayers larger than 7 Å. In this case, even the long-range dipolar interactions between these Ising-like Nd³⁺ spins in different bilayers are negligibly small (around 10 mK). Moreover, considering the considerable separation between localized 4f-electrons, it becomes challenging to envision the exchange interaction playing a significant role. Besides, the Ruderman-Kittel-Kasuya-Yosida interactions are absent since NdZnPO is a transparent insulator. According to the Mermin-Wanger theorem, it is hard to imagine that the long-range magnetic order can build up at temperature $T_{\rm N} = 1.64$ K for such well separated 2D bilayer trianglular lattices? An likely senario is that, the strong Ising-like anisotropy has helped to stabilize the magnetic ground state. In addition, the Ising-like single ion anisotropy results in a large saturation moment, and thus the long-range dipolar intra-plane interactions are also enhanced. This longrange interaction also makes the Mermin-Wanger theorem fail in the case of NdZnPO. We also noticed that a long-range magnetic order was also established at 1.3 K

in the compound YbOCl with similar bilayer triangular lattices [34, 35]. These resembling phenomena in these two systems might indicate that the magnetic order may be stabilized by similar mechanisms.

Additionally, the magnetic dipolar interaction calculation between near neighbors indicates that these moments are AFM coupled $(J' = 0.196 \ K)$ in the single triangular layer, while they are FM coupled $(J = -0.102 \ K)$ between these bilayers. Alternatively, this is equivalent to a honeycomb lattice with FM nearest-neighbor interactions (J) and AFM nextnearest-neighbor interactions (J'). For Ising moments in this honeycomb lattice with next-nearest-neighbor interactions, strong quantum fluctuations are expected due to geometric spin frustration. Assuming the static magnetic structure could be stabilized by a delicate balance of these nearest-neighbor and next-nearest-neighbor interactions, it is still likely that the ordered moment would be greatly reduced due to the strong quantum fluctuations. However, in contrast to our expectation, the ordered moments 1.81 $\mu_{\rm B}/{\rm Nd}$ refined from the powder neutron diffraction experiments are very close to the saturation moment 1.68 $\mu_{\rm B}/{\rm Nd}$ at 7 T observed in the magnetization measurements. This suggests that most of the spin frustration has been released in the magnetic ordering state. Besides, fractional states such as 1/3 plateau phases are usually induced under fields for triangular lattices with Ising-like moments. However, we did not find any field-induced plateau-like phases down to the base temperature in NdZnPO. To explain these observations and to check if Kitaev-like physics could emerge in this system, further investigations such as single-crystal neutron scattering experiments are still needed.

ACKNOWLEDGMENTS

We would like to thank Shu Guo for the help with the single crystal growth, Nikita Andriushin for assisting in the neutron scattering experiment, and Zhentao Wang for useful discussions.

The research was supported by the National Key Research and Development Program of China (Grant No. 2021YFA1400400), the National Natural Science Foundation of China (Grants No. 12134020, No. 12374146, No. 12104255, No. 12005243 and No. 11974157), the Open Fund of the China Spallation Neutron Source Songshan Lake Science City (Grant No. KFKT2023A06), and the Guangdong Basic and Applied Basic Research Foundation (Grant No. 2021B1515120015 and No. 2022B1515120014). Part of this work is based on experiments performed at the Swiss spallation neutron source SINQ, Paul Scherrer Institute, Villigen, Switzerland.

- L. Balents, Spin liquids in frustrated magnets, Nature 464, 199 (2010).
- [2] P. A. Lee, An End to the Drought of Quantum Spin

Liquids, Science 321, 1306 (2008).

- [3] Y. Zhou, K. Kanoda, and T.-K. Ng, Quantum spin liquid states, Rev. Mod. Phys. 89, 025003 (2017).
- [4] L. Savary and L. Balents, Quantum Spin Liquids: A Review, Rep. Prog. Phys. 80, 016502 (2017).
- [5] C. Broholm, R. J. Cava, S. A. Kivelson, D. G. Nocera, M. R. Norman, and T. Senthil, Quantum Spin Liquids, Science 367, eaay0668 (2020).
- [6] P. W. Anderson, Resonating valence bonds: a new kind of insulator?, Mater. Res. Bull. 8, 153 (1973).
- [7] B. Bernu, C. Lhuillier, and L. Pierre, Signature of Néel order in exact spectra of quantum antiferromagnets on finite lattices, Phys. Rev. Lett. 69, 2590 (1992).
- [8] L. Capriotti, A. E. Trumper, and S. Sorella, Long-range Néel order in the triangular Heisenberg model, Phys. Rev. Lett. 82, 3899 (1999).
- [9] Tao Xie, S. Gozel, Jie Xing, Nan Zhao, S. M. Avdoshenko, Liusuo Wu, Athena S. Sefat, A. L. Chernyshev, A. M. Läuchli, A. Podlesnyak, S. E. Nikitin, Quantum spin dynamics due to strong Kitaev interactions in the triangular-lattice antiferromagnet CsCeSe₂, Condmatter archive, arXiv:2311.13146 (2023).
- [10] Y. Shimizu, K. Miyagawa, K. Kanoda, M. Maesato, and G. Saito, Spin Liquid State in an Organic Mott Insulator with a Triangular Lattice, Phys. Rev. Lett. 91, 107001 (2003).
- [11] T. Ono, H. Tanaka, H. A. Katori, F. Ishikawa, H. Mitamura, T. Goto, Magnetization plateau in the frustrated quantum spin system Cs₂CuBr₄, Phys. Rev. B 67, 104431 (2003).
- [12] Y. Shirata, H. Tanaka, A. Matsuo, and K. Kindo, Experimental Realization of a Spin-1/2 Triangular-Lattice Heisenberg Antiferromagnet, Phys. Rev. Lett. 108, 057205 (2012).
- [13] N. A. Fortune, S. T. Hannahs, Y. Yoshida, T. E. Sherline, T. Ono, H. Tanaka, Y. Takano, Cascade of magneticfield-induced quantum phase transitions in a spin-1/2 triangular-lattice antiferromagnet, Phys. Rev. Lett. 102, 257201 (2009).
- [14] H. D. Zhou, C. K. Xu, A. M. Hallas, H. J. Silverstein, C. R. Wiebe, I. Umegaki, J. Q. Yan, T. P. Murphy, J.-H. Park, Y. M. Qiu, J. R. D. Copley, J. S. Gardner, Y. Takano, Successive phase transitions and extended spin-excitation continuum in the S = 1/2 triangularlattice antiferromagnet Ba₃CoSb₂O₉, Phys. Rev. Lett. 109, 267206 (2012).
- [15] T. Susuki, N. Kurita, T. Tanaka, H. Nojiri, A. Matsuo, K. Kindo, H. Tanaka, Magnetization process and collective excitations in the S = 1/2 triangular-lattice Heisenberg antiferromagnet Ba₃CoSb₂O₉, Phys. Rev. Lett. 110, 267201 (2013).
- [16] J. D. Rinehart and J. R. Long, Exploiting Single-Ion Anisotropy in the Design of f-Element Single-Molecule Magnets, Chem. Sci. 2, 2078 (2011).
- [17] S.-D. Jiang and S.-X. Qin, Prediction of the Quantized Axis of Rare-Earth Ions: The Electrostatic Model with Displaced Point Charges, Inorg. Chem. Front. 2, 613 (2015).
- [18] L. S. Wu, W. J. Gannon, I. A. Zaliznyak, A. M. Tsvelik, M. Brockmann, J.-S. Caux, M. S. Kim, Y. Qiu, J. R. D. Copley, G. Ehlers, A. Podlesnyak, M. C. Aronson, Orbital-Exchange and Fractional Quantum Number Excitations in an f-Electron Metal, Yb₂Pt₂Pb, Science 352, 1206 (2016).

- [19] S. Onoda and Y. Tanaka, Quantum Melting of Spin Ice: Emergent Cooperative Quadrupole and Chirality, Phys. Rev. Lett. 105, 047201 (2010).
- [20] Y. Shen, Y.-D. Li, H. Wo, Y. Li, S. Shen, B. Pan, Q. Wang, H. C. Walker, P. Steffens, M. Boehm, Y. Hao, D. L. Quintero-Castro, L. W. Harriger, M. D. Frontzek, L. Hao, S. Meng, Q. Zhang, G. Chen, J. Zhao, Evidence for a spinon Fermi surface in a triangular-lattice quantum-spin-liquid candidate, Nature 540, 559 (2016).
- [21] H. Li, Y. D. Liao, B.-B. Chen, X.-T. Zeng, X.-L. Sheng, Y.Qi, Z. Y. Meng, and W. Li, Kosterlitz-Thouless Melting of Magnetic Order in the Triangular Quantum Ising Material TmMgGaO₄, Nat Commun 11, 1111 (2020).
- [22] M. M. Bordelon, E. Kenney, C. Liu, T. Hogan, L. Posthuma, M. Kavand, Y. Lyu, M. Sherwin, N. P. Butch, C. Brown, M. J. Graf, L. Balents, S. D. Wilson, Field-tunable quantum disordered ground state in the triangular-lattice antiferromagnet NaYbO₂, Nat. Phys. 15, 1058 (2019).
- [23] M. Baenitz, Ph. Schlender, J. Sichelschmidt, Y. A. Onykiienko, Z. Zangeneh, K. M. Ranjith, R. Sarkar, L. Hozoi, H. C. Walker, J.-C. Orain, H. Yasuoka, J. Van Den Brink, H. H. Klauss, D. S. Inosov, Th. Doert, NaYbS₂: A Planar Spin-¹/₂ Triangular-Lattice Magnet and Putative Spin Liquid, Phys. Rev. B 98, 220409 (2018).
- [24] P.-L. Dai, G. Zhang, Y. Xie, C. Duan, Y. Gao, Z. Zhu, E. Feng, Z. Tao, C.-L. Huang, H. Cao, A. Podlesnyak, G. E. Granroth, M. S. Everett, J. C. Neuefeind, D. Voneshen, S. Wang, G. Tan, E. Morosan, X. Wang, H.-Q. Lin, L. Shu, G. Chen, Y. Guo, X. Lu, P. Dai, Spinon Fermi Surface Spin Liquid in a Triangular Lattice Antiferromagnet NaYbSe₂, Phys. Rev. X 11, 021044 (2021).
- [25] A. O. Scheie, E. A. Ghioldi, J. Xing, J. A. M. Paddison, N. E. Sherman, M. Dupont, L. D. Sanjeewa, S. Lee, A. J. Woods, D. Abernathy, D. M. Pajerowski, T. J. Williams, S.-S. Zhang, L. O. Manuel, A. E. Trumper, C. D. Pemmaraju, A. S. Sefat, D. S. Parker, T. P. Devereaux, R. Movshovich, J. E. Moore, C. D. Batista, D. A. Tennant, Proximate spin liquid and fractionalization in the triangular antiferromagnet KYbSe₂, Nat. Phys. 20, 74 (2024).
- [26] T. Xie, A. A. Eberharter, J. Xing, S. Nishimoto, M. Brando, P. Khanenko, J. Sichelschmidt, A. A. Turrini, D. G. Mazzone, P. G. Naumov, L. D. Sanjeewa, N. Harrison, A. S. Sefat, B. Normand, A. M. Lauchli, A. Podlesnyak, S. E. Nikitin, Complete field-induced spectral response of the spin-1/2 triangular-lattice antiferromagnet CsYbSe₂, npj Quantum Mater. 8, 48 (2023).
- [27] A. Kitaev, Anyons in an Exactly Solved Model and Beyond, Annals of Physics 321, 2 (2006).
- [28] Y. Singh and P. Gegenwart, Antiferromagnetic Mott Insulating State in Single Crystals of the Honeycomb Lattice Material Na₂IrO₃, Phys. Rev. B 82, 064412 (2010).
- [29] Y. Singh, S. Manni, J. Reuther, T. Berlijn, R. Thomale, W. Ku, S. Trebst, and P. Gegenwart, Relevance of the Heisenberg-Kitaev Model for the Honeycomb Lattice Iridates A₂IrO₃, Phys. Rev. Lett. 108, 127203 (2012).
- [30] K. Kitagawa, T. Takayama, Y. Matsumoto, A. Kato, R. Takano, Y. Kishimoto, S. Bette, R. Dinnebier, G. Jackeli, and H. Takagi, A Spin–Orbital-Entangled Quantum Liquid on a Honeycomb Lattice, Nature 554, 341 (2018).
- [31] K. W. Plumb, J. P. Clancy, L. J. Sandilands, V. V. Shankar, Y. F. Hu, K. S. Burch, H.-Y. Kee, and Y.-J. Kim, α-RuCl₃: A Spin-Orbit Assisted Mott Insulator on a Honeycomb Lattice, Phys. Rev. B 90, 041112 (2014).

- [32] T. Yokoi et al., Half-Integer Quantized Anomalous Thermal Hall Effect in the Kitaev Material Candidate α -RuCl₃, Science 373, 568 (2021).
- [33] Y. Kasahara et al., Majorana Quantization and Half-Integer Thermal Quantum Hall Effect in a Kitaev Spin Liquid, Nature 559, 227 (2018).
- [34] J. Ji, M. Sun, Y. Cai, Y. Wang, Y. Sun, W. Ren, Z. Zhang, F. Jin, and Q. Zhang, Rare-Earth Chalcohalides: A Family of van Der Waals Layered Kitaev Spin Liquid Candidates, Chinese Phys. Lett. 38, 047502 (2021).
- [35] Z. Zhang, Y. Cai, J. Kang, Z. Ouyang, Z. Zhang, A. Zhang, J. Ji, F. Jin, and Q. Zhang, Anisotropic Exchange Coupling and Ground State Phase Diagram of Kitaev Compound YbOCl, Phys. Rev. Research 4, 033006 (2022).
- [36] G. Chen, M. Hermele, and L. Radzihovsky, Frustrated Quantum Critical Theory of Putative Spin-Liquid Phenomenology in 6H-B-Ba₃NiSb₂O₉, Phys. Rev. Lett. 109, 016402 (2012).
- [37] A. T. Nientiedt and W. Jeitschko, Equiatomic Quaternary Rare Earth Element Zinc Pnictide Oxides RZnPO and RZnAsO, Inorg. Chem. 37, 386 (1998).
- [38] H. Lincke, T. Nilges, and R. Pöttgen, Dimorphic CeZnPO and PrZnPO, Z. Anorg. Allg. Chem. 632, 1804 (2006).
- [39] H. Lincke, R. Glaum, V. Dittrich, M. Tegel, D. Johrendt, W. Hermes, M. H. Möller, T. Nilges, and R. Pöttgen, Magnetic, Optical, and Electronic Properties of the Phosphide Oxides REZnPO (RE = Y, La–Nd, Sm, Gd, Dy, Ho), Z. Anorg. Allg. Chem. 634, 1339 (2008).
- [40] I. P. Orench, J. F. Clergeau, S. Martínez, M. Olmos, O. Fabelo, and J. Campo, The New Powder Diffractometer D1B of the Institut Laue Langevin, J. Phys.: Conf. Ser. 549, 012003 (2014).

- [41] N. Andriushin, S. Nikitin, A. Podlesnyak, I. Puente-Orench and A. Sukhanov, Magnetic structure of the bilayer triangular lattice antiferromagnet NdZnPO. (2023) Institut Laue-Langevin (ILL) doi:10.5291/ILL-DATA.5-31-2923
- [42] M. T. Hutchings, Point-Charge Calculations of Energy Levels of Magnetic Ions in Crystalline Electric Fields, in Solid State Physics, Vol. 16 (Elsevier, 1964), pp. 227–273.
- [43] M. Rotter, Using McPhase to Calculate Magnetic Phase Diagrams of Rare Earth Compounds, Journal of Magnetism and Magnetic Materials 272–276, E481 (2004).
- [44] L. S. Wu, S. E. Nikitin, M. Frontzek, A. I. Kolesnikov, G. Ehlers, M. D. Lumsden, K. A. Shaykhutdinov, E.-J. Guo, A. T. Savici, Z. Gai, A. S. Sefat, and A. Podlesnyak, Magnetic Ground State of the Ising-like Antiferromagnet DyScO₃, Phys. Rev. B 96, 144407 (2017).
- [45] N. Zhao, J. Sheng, J. Wang, H. Ge, T. Li, J. Yang, S. Wang, P. Miao, H. He, X. Tong, W. Bao, E. Guo, R. Mole, D. Yu, A. Podlesnyak, and L. Wu, Quasi-One-Dimensional Ising-like Antiferromagnetism in the Rare-Earth Perovskite Oxide TbScO₃, Phys. Rev. Materials 7, 034401 (2023).
- [46] L. S. Wu, S. E. Nikitin, Z. Wang, W. Zhu, C. D. Batista, A. M. Tsvelik, A. M. Samarakoon, D. A. Tennant, M. Brando, L. Vasylechko, M. Frontzek, A. T. Savici, G. Sala, G. Ehlers, A. D. Christianson, M. D. Lumsden, A. Podlesnyak, Tomonaga–Luttinger Liquid Behavior and Spinon Confinement in YbAlO₃, Nat Commun 10, 698 (2019).
- [47] W. Yao, Y. Zhao, Y. Qiu, C. Balz, J. R. Stewart, J. W. Lynn, Y. Li, Magnetic ground state of the Kitaev Na₂Co₂TeO₆ spin liquid candidate, Phys. Rev. Research 5, L022045 (2023).
- [48] K. Andres, Hyperfine Enhanced Nuclear Magnetic Cooling, Cryogenics 18, 473 (1978).