Achiral nanostructures: perturbative harmonic generation and dichroism under vortex and vector beams illumination

Anastasia Nikitina^{*1} and Kristina Frizyuk^{†2}

¹The School of Physics and Engineering, ITMO University, Saint-Petersburg, Russia ²Department of Information Engineering, University of Brescia, Brescia, Italy

Abstract

In this study, we investigate the nonlinear optical phenomena emerging from the interaction of vortex and vector beams with achiral nanoparticles or nanostructures. We reveal the conditions under which linear or nonlinear dichroism can be observed. Despite the achiral symmetry of the nanostructure, the interplay between the symmetries of the vortex beam, the nanostructure, and the crystalline lattice of the nanostructure material may result in circular dichroism in the nonlinear regime. We derive a formula that describes the conditions for the appearance of circular dichroism across a broad range of scenarios, taking into account all the symmetries. Building on these findings, we have determined the conditions for both linear and nonlinear dichroism when illuminated by vector beams. We believe that this work provides important insights that can enhance the design of chiral sensors and optical traps, making them more versatile and effective.

Contents

2	Theoretical framework					
	2.1 Incident beams					
	2.2 Multipolar content of the vortex beams					
	2.3 Perturbative harmonic generation					

ก

duction

^{*}Email: anastasia.nikitina@metalab.ifmo.ru

[†]Email: frzyuk@gmail.com

4	Ana	alysing	particular cases	9
	4.1	Second	ł harmonic circular dichroism in $GaAs[111] \ z C_{3v}$ nanostructure .	10
		4.1.1	Nonlinear polarization	10
		4.1.2	Eigenmode presentations	10
		4.1.3	Coupling integrals	11
		4.1.4	Excitation of the modes by different angular momentum	14
		4.1.5	Total integral second harmonic intensity	17
		4.1.6	Second-harmonic circular dichroism	18
	4.2	Second	l harmonic in GaAs[111] $\ z C_{4v}$ nanostructure (no dichroism)	19
		4.2.1	Eigenmode presentations	20
		4.2.2	Coupling integrals	21
		4.2.3	Excitation of the modes by different angular momentum	25
		4.2.4	Second-harmonic electric field	28
		4.2.5	Total integral second harmonic intensity	29
		4.2.6	Second-harmonic circular dichroism	30
5	Der	ivation	of the main condition for a general case	31
6	Nur	nerical	Calculations	32
7	Dise	cussion	IS	33
	7.1	Cascad	led generation	33
	7.2	Angula	ar incidence and substrate	34
	7.3	Other	subtleties	35
	7.4	Other	definitions of dichroism	35
8	Dic	hroism	under vector beams illumination	36
9	Cor	clusion	ns	37
10	Ack	nowled	lgements	38
Α	App	oendix	ł	50
	A.1	On not	n-perturbative harmonic generation	50
	A.2	$\hat{\chi}^{(3)}$ te	nsor in cylindrical coordinates	50
	A.3	Vector	spherical harmonics	51
	A.4	On spe	ecific multipolar combinations and vortex beams	52
	A.5	Extra	technical derivations	54
		A.5.1	Multipolar content of the eigenmodes of C_{3v} nanostructure	54
		A.5.2	Expression for the total intensity	55

1 Introduction

Chirality, being a natural characteristic, is crucial in various scientific fields such as physics and biology [1–3]. It's often observed in natural structures like amino acids or proteins. Circular dichroism spectroscopy is a well-known method for investigating



$s = \Delta m_{\chi} = \mathfrak{n} \nu$	
$eta eq rac{\pi u}{s}$	

Figure 1: Schematic of the concept. Incident vortex beam, characterized by an angular momentum projection $\pm m$ is depicted using higher order Poincare sphere [4, 5]. The value m = 3 is taken, as an example. The circular dichroism in high-harmonic generation can be obtained when we excite the nanoparticle of an achiral symmetry D_{nh} or C_{nv} by either $|R_m\rangle$ or $|L_m\rangle$ beam. Another two states which are shown with the black lines (polarization ellipses with one zero axis) are vector beams [6]. The nanoparticle generates high harmonic due to material properties, where q is an order of high harmonic. The crystalline lattice is rotated with respect to the nanoparticle symmetry axis by an angle β and characterized by differences Δm_{χ} determined by $\hat{\chi}^{(q)}$ tensor. The main result is shown in a box, where $\nu \in \mathbb{Z}$.

the properties of chiral substances. While it is commonly defined as a difference in the absorption of a left- and right-circularly polarized light [7, 8], it can be generalized for more complex systems [9–12], including nonlinear circular dichroism [13–18] or circular dichroism under excitation by light beams with angular momentum [19–23]. Previously, various types of circular dichroism were investigated for continuous media, and focused studies on individual nanoparticles or metamaterials have only recently begun to emerge [24–30]. In recent works, we have demonstrated the existence of nonlinear, particularly second-harmonic circular dichroism (SH-CD) in achiral dielectric nanostructures [31, 32] with intrinsic nonlinearity. In fact, it was defined as the difference between values of second-harmonic intensity for right- and left-circularly polarized plane wave excitation, and it was proven that this nonlinear effect appears under certain conditions on the orientation of the nanoparticle relative to its material's lattice.

Here, we show that these results can be generalized to the case of any high-harmonic generation as well as any excitation by a vortex beam with an angular momentum (See Fig. 1) proposing a generalized framework for understanding nonlinear circular dichroism in complex light-matter interactions. These results can be of particular importance for chiral sensing enhancement by nanoparticles, since we show that in some cases, the dichroic signal of the nanoparticle itself cannot be neglected. We primarily focus on this case, as it provides a general framework for studying many different systems.

Another scenario is analogous to linear dichroism in the linear regime, i.e. the dichroism under vector beams illumination [6, 33]. Here, the dichroism is possible even in the linear regime, and we provide the conditions, under which it can or can not be observed.

This work is organized as follows. In Section 2, we give a general framework of the problem. Section 3 contains the main result: the formula, which describes the conditions of dichroism occurrence in all cases. Section 4 provides the strict consideration of the second-harmonic generation for particular materials and shapes of the nanostructures in terms of modal and multipolar analysis. The first case 4.1 is one in which dichroism is possible, and the second 4.2 is one in which it is not. This approach leads to the derivation of the main formula (17), in Section 5 and also shows the variety of options and interactions that arise in intermediate processes. Section 6 provides the numerical calculations to support the theoretical predictions. Section 7 gives discussions of some important subtleties. In Section 8 we discuss the conditions for observing dichroism under vector beam illumination in linear (101) and nonlinear regimes (105). In Section 9, we give a brief conclusion.

2 Theoretical framework

2.1 Incident beams

Before introducing the formula for general notation of the nonlinear circular dichroism, we describe the nature of vortex beams. We consider the following description for vortex beams in cylindrical coordinates, for which a higher-order Poincare sphere can be introduced [4, 5, 34, 35]. In paraxial regime, they can be described as:

$$|R_m\rangle \sim \exp(+\mathrm{i}(m-1)\varphi)(\hat{\mathbf{x}}+\mathrm{i}\hat{\mathbf{y}})/\sqrt{2},$$
 (1)

$$|L_m\rangle \sim \exp(-\mathrm{i}(m-1)\varphi)(\hat{\mathbf{x}} - \mathrm{i}\hat{\mathbf{y}})/\sqrt{2},$$
 (2)

where $|R_m\rangle$ and $|L_m\rangle$ are related to the right- and left-handed beam, respectively, which are mirror images of each other. Here $m \in \mathbb{Z}$, φ is the azimuthal angle, and $\hat{\mathbf{x}}$ and $\hat{\mathbf{y}}$ are unit basis vectors. A detailed description of the properties of vortex beams and the connection between angular momentum and topological charge can be found in the Appendix A.4. We omit the dependence of the radial coordinate r [36] because it does not change the general symmetry, in which we are interested. We also use

$$(\hat{\mathbf{x}} \pm i\hat{\mathbf{y}}) = e^{\pm i\varphi} (\hat{\boldsymbol{\rho}} \pm i\hat{\boldsymbol{\varphi}}) \tag{3}$$

and rewrite:

$$|R_m\rangle = e^{+\mathrm{i}m\varphi} \frac{\hat{\boldsymbol{\rho}} + \mathrm{i}\hat{\boldsymbol{\varphi}}}{\sqrt{2}},\tag{4}$$

$$|L_m\rangle = e^{-\mathrm{i}m\varphi} \frac{\hat{\boldsymbol{\rho}} - \mathrm{i}\hat{\boldsymbol{\varphi}}}{\sqrt{2}}.$$
(5)

Note that $\pm m$ refers to the total angular momentum projection on the z-axis and plays the important role in our considerations. Handedness refers to the helicity of the beam [37]. We consider this problem by implementing the multipolar decomposition because, for the multipoles, total angular momentum projection is well-defined [38]. We use vector spherical harmonics [39, 40] (spherical multipoles), although their application may seem redundant in this context. However, in fact, employing any kind of cylindrical harmonics [41] does not necessarily simplify or clarify the problem, as we are only interested in the total angular momentum projection m regardless of the basis used.

Another type of beams we are interested in are vector beams, related to the diameter of the generalized Poincaré sphere (see Fig. 1). They are introduced as:

$$|\mathbf{B}_{me}\rangle \propto |L_m\rangle + |R_m\rangle$$
 (6)

$$|\mathbf{B}_{mo}\rangle \propto |L_m\rangle - |R_m\rangle.$$
 (7)

Indexes e and o denote the parity under reflection in y = 0 plane.

2.2 Multipolar content of the vortex beams

For further convenience, we introduce $m^{\text{in}} = |m|$. The multipolar content of vortex beams with particular helicity [37] and total angular momentum projection is known from literature (Eq. (4) in [42] and Eq. (53) in [43]). Thus, we are interested in the following combinations of vector spherical harmonics defined in [40] (see Appendix A.3):

$$(\mathbf{N}_{em^{\mathrm{in}}n} \pm \mathrm{i} \mathbf{N}_{om^{\mathrm{in}}n}) + (\pm \mathbf{M}_{em^{\mathrm{in}}n} + \mathrm{i} \mathbf{M}_{om^{\mathrm{in}}n}) \sim e^{\pm \mathrm{i} m^{\mathrm{in}}\varphi} (\hat{\boldsymbol{\rho}} \pm \mathrm{i} \hat{\boldsymbol{\varphi}}), \tag{8}$$

which also can be compared with multipolar content of circularly polarized plane wave for $m^{\text{in}} = 1$ [40], and also

$$(\mathbf{N}_{em^{\mathrm{in}}n} \mp \mathrm{i} \mathbf{N}_{om^{\mathrm{in}}n}) - (\mp \mathbf{M}_{em^{\mathrm{in}}n} + \mathrm{i} \mathbf{M}_{om^{\mathrm{in}}n}) \sim e^{\mp \mathrm{i} m^{\mathrm{in}}\varphi} (\hat{\boldsymbol{\rho}} \pm \mathrm{i} \hat{\boldsymbol{\varphi}}), \tag{9}$$

where ρ and φ are unit basis vectors in cylindrical coordinates. Here we use the sign \sim which shows that such linear combinations contribute to the multipolar content of the corresponding beam, and also possess the same symmetry behavior under rotations around the z-axis. Further analysis is applicable to all potential incident beams that can be expressed via these multipolar combinations. We have addressed paraxial approximation as commonly employed and familiar; however, it is the analysis of the multipolar composition that yields the conclusive answer.

Importantly, when nanostructures are excited by a vortex beam, combinations as described in equations (8) and (9) do not occur for internal or scattered fields [40] due to the resonant excitation of the eigenmodes. Additionally, the resonant frequencies

of magnetic and electric multipoles are generally different, except in helicity-preserving systems where $\varepsilon/\mu = \text{const} [44-47]$.

Thus, we further prove that we can just consider the total angular momentum projection of a beam m^{in} (except the case $m^{\text{in}} = 0$, which is commented in discussions), which obeys a "modified by nanostructure" conservation law, and the problem becomes almost fully analogous to the one considered in [32]. Now we can move to the discussion of the nonlinear response.

2.3 Perturbative harmonic generation

We consider achiral nanoparticles or nanostructures, which can be of C_{nv} , D_{nh} symmetry (Schoenflies notation). The nanoparticles are made from a material with a noncentrosymmetric crytalline lattice (e.g., GaAs, BaTiO₃, or LiNbO₃). In such dielectric nanostructures, second harmonic generation is commonly described by the nonlinear susceptibility tensor $\hat{\chi}^{(2)}$ [48]:

$$P_i^{2\omega}(\mathbf{r}) = \varepsilon_0 \chi_{ijk}^{(2)} E_j^{\omega}(\mathbf{r}) E_k^{\omega}(\mathbf{r}), \qquad (10)$$

where $P_i^{2\omega}(\mathbf{r})$ is a nonlinear polarization, and $\mathbf{E}^{\omega}(\mathbf{r})$ is a fundamental field inside the nanoparticle or nanostructure. The second-harmonic generation is given separately as a most common case and will be further considered in some examples. For the perturbative (See discussion in Appendix A.1) high-harmonic generation of order q, the nonlinear polarization $P_i^{q\omega}(\mathbf{r})$ can be defined as [49]:

$$P_i^{q\omega}(\mathbf{r}) = \varepsilon_0 \chi_{ijk\dots h}^{(q)} \underbrace{E_j^{\omega}(\mathbf{r}) E_k^{\omega}(\mathbf{r}) \dots E_h^{\omega}(\mathbf{r})}_{q}, \qquad (11)$$

The far-field outside the nanoparticle can be described with the help of Green's function [50, 51]:

$$\mathbf{E}^{q\omega}(\mathbf{r}) = (q\omega)^{2}\mu_{0} \int_{V} dV' \hat{\mathbf{G}}(q\omega, \mathbf{r}, \mathbf{r}') \mathbf{P}^{q\omega}(\mathbf{r}') =$$

$$= (q\omega)^{2}\mu_{0} \int_{V} dV' \sum_{j} \frac{\mathbf{E}_{j}^{q\omega}(\mathbf{r}) \otimes \mathbf{E}_{j}^{q\omega}(\mathbf{r}')}{2k(k-k_{j})} \mathbf{P}^{q\omega}(\mathbf{r}') =$$

$$= (q\omega)^{2}\mu_{0} \sum_{j} \frac{1}{2k(k-k_{j})} \mathbf{E}_{j}^{q\omega}(\mathbf{r}) \int_{V} dV' \mathbf{E}_{j}^{q\omega}(\mathbf{r}') \mathbf{P}^{q\omega}(\mathbf{r}'),$$
(12)

where ω is the fundamental frequency, μ_0 is the vacuum permeability, and $\mathbf{E}_j^{q\omega}(\mathbf{r})$ is the field of the system's quasi-normal mode (eigenfrequency $\omega_j = ck_j$) [51–53] at the appropriate frequency $q\omega = ck$. The integration is over the particle's volume. Green's function is defined as $\nabla \times \nabla \times \hat{\mathbf{G}}(\omega, \mathbf{r}, \mathbf{r}') = \left(\frac{\omega}{c}\right)^2 \varepsilon(\mathbf{r}, \omega) \hat{\mathbf{G}}(\omega, \mathbf{r}, \mathbf{r}') + \hat{\mathbf{I}}\delta(\mathbf{r} - \mathbf{r}')$ [50], where $\hat{\mathbf{I}}$ is the unit dyadic, $\varepsilon(\mathbf{r}, \omega) = \varepsilon_2(\omega)$ for nanostructure, and $\varepsilon(\mathbf{r}) = 1$ for vacuum. We assume $\varepsilon_2(\omega)$ to be a scalar quantity, and the structure is not birefringent (which is rigorous for cubic lattices). Note that strictly speaking, the equation (12) converges only for the region inside the nanoparticle, and $\mathbf{E}^{q\omega}(\mathbf{r})$ in the outer region should be replaced by its analytic continuation (See e.g. [54] or SI in [55, 56]). However, this detail is omitted subsequently, as the symmetry of the fields remains unchanged after this procedure. In this work, we assume that the incident beam has a certain azimuthal symmetry.

Circular dichroism in the second-harmonic signal can be defined as:

$$\text{SH-CD}_{m,\lambda} = \frac{\left(I_{R_m}^{2\omega} - I_{L_m}^{2\omega}\right)}{\left(I_{R_m}^{2\omega} + I_{L_m}^{2\omega}\right)},\tag{13}$$

where $I_{R_m}^{2\omega}$, $I_{L_m}^{2\omega}$ is the corresponding total intensity of a second-harmonic described by $\mathbf{E}^{q\omega}(\mathbf{r})$, excited by a right- or left-handed beam, respectively, and integrated over the sphere in the far-field (the center of the sphere should coincide with the center of the nanostructure). This definition is analogous to circular-helical dichroism [57] or circular-vortex dichroism [58], which can be found in literature. We can introduce analogously higher-order nonlinear circular dichroism [59, 60]:

$$\text{HH-CD}_{m,\lambda} = \frac{(I_{R_m}^{q\omega} - I_{L_m}^{q\omega})}{(I_{R_m}^{q\omega} + I_{L_m}^{q\omega})}.$$
(14)

In the previous work [32], the general form of the decomposition of the nonlinear polarization $\mathbf{P}^{2\omega}(\mathbf{r})$ (10) has been obtained for an achiral nanostructure with C_{nv} or D_{nh} symmetry irradiated by a normally incident circularly polarized plane wave. To obtain polarization in the general case, two steps are necessary. Firstly, one should describe the field inside the nanostructure on the fundamental frequency: its multipolar decomposition contains the functions with m equal to the sum of the total angular momentum projection of the incident field and additional momentum projections, $\mathfrak{n}\nu$ (where $\nu \in \mathbb{Z}$), which are multiples of the rotational symmetry of the nanoparticle characterized by the number \mathfrak{n} . Secondly, it is required to rewrite the $\hat{\chi}^{(q)}$ tensor in cylindrical coordinates, as it was done, e.g. in [61, 62] for $\hat{\chi}^{(2)}$ or for $\hat{\chi}^{(3)}$ in the Appendix A.2. After that, we get all possible additional momentum projections m_{χ} (it is the multiplier which stands in the terms like $\exp(m_{\chi}\varphi)$ if one looks at the tensor components written in cylindrical coordinates), as well as differences $\Delta m_{\chi} = m_{\chi} - m'_{\chi}$ between all possible different values. Note that the values of the m_{χ} are related to the rotational symmetry of the lattice, but in fact, the symmetry of the tensor is in some sense "higher" than the symmetry of the lattice itself, being restricted by the tensor transformation properties and its rank. Now, due to the fact that the geometry of the problem is the same but nanostructures are irradiated by a vortex beam, we can introduce the same expression as in [32] with only one generalization: the projection of the momentum of the incident vortex $\pm m^{\text{in}}$ instead of the values ± 1 , as it was for the plane wave. Thus, the decomposition of the nonlinear polarization $\mathbf{P}^{2\omega}(\mathbf{r})$ for the second-harmonic can be written in the cylindrical coordinates r, z, φ in the following form:

$$\mathbf{P}^{2\omega}(\mathbf{r}) \propto \sum_{m_{\chi},\nu} \mathrm{e}^{-m_{\chi}\mathrm{i}\beta} \left[\mathbf{P}^{2\omega}_{(m_{\chi}+2m^{\mathrm{in}}),\nu}(r,z) \mathrm{e}^{(m_{\chi}\pm 2m^{\mathrm{in}}+\mathfrak{n}\nu)\mathrm{i}\varphi} \right],\tag{15}$$

where \mathfrak{n} describes the symmetry group of a nanostructure ($C_{\mathfrak{nv}}$ or $D_{\mathfrak{nh}}$), $\nu \in \mathbb{Z}$, and β is a relative angle between the nanoparticle and its crystalline lattice, as it shown

in Fig. 1. The values m_{χ} reflect the lattice symmetry, while the value m^{in} characterizes the incident vortex. Here we explicitly separate the dependence of the nonlinear polarization $\mathbf{P}^{q\omega}(\mathbf{r})$ on coordinate φ . In a similar way, the high-harmonic nonlinear polarization $\mathbf{P}^{q\omega}(\mathbf{r})$ can be written as:

$$\mathbf{P}^{q\omega}(\mathbf{r}) \propto \sum_{m_{\chi},\nu} \mathrm{e}^{-m_{\chi}\mathrm{i}\beta} \left[\mathbf{P}^{q\omega}_{(m_{\chi}+qm^{\mathrm{in}}),\nu}(r,z) \mathrm{e}^{(m_{\chi}\pm qm^{\mathrm{in}}+\mathfrak{n}\nu)\mathrm{i}\varphi} \right].$$
(16)

In the equations (15) and (16) we use the proportionality sign to emphasize the symmetrical nature of the phenomenon and the insignificance of constants and other dependencies, such as dependency on wavelength. Nevertheless, this consideration is justified because, for determining the multipolar content in an axially symmetric system, we mainly need the dependence on φ (See Suppl. Info. in [62]).

3 Conditions for the high harmonic circular dichroism

Surprisingly, despite the particular complexity and tremendous construction of intermediate calculations, the final expression for the possibility of circular dichroism can be written in a short and elegant form. Moreover, the formula applies universally across all cases, regardless of the incident beam, nanostructure symmetry, or high-order of harmonic generation. Consequently, it aligns precisely with the one presented in [32], and proving its universality is the main result of our work. The theoretical investigation shows independence of the obtained results on the angular momentum projection absolute value $|m^{in}|$ of the incident optical vortex.

Let us here recall that Δm_{χ} being one of the possible differences between m_{χ} of a $\hat{\chi}^{(q)}$ tensor written in cylindrical coordinates, generally reflects the crystalline lattice symmetry, and **n** reflects the rotational symmetry of a nanoparticle. Thus, the HH- $CD_{m,\lambda}$ can be obtained if:

1. $\exists \nu \in \mathbb{Z}$ such that $\Delta m_{\chi} = \nu \mathfrak{n}$, so we introduce the number s:

$$s = \Delta m_{\chi} = \nu \mathfrak{n}. \tag{17}$$

2. The relative angle β of a crystalline lattice rotation with respect to nanoparticle is:

$$\beta \neq \frac{\pi\nu}{s} \quad \forall \nu \in \mathbb{Z}.$$
 (18)

3. If there are several possible s in (17), one should prohibit only those angles $\beta = \pi \nu / s$ in (18) that coincide for all $s = \Delta m_{\chi}$.

Note that this formula does not know anything about the value of the total angular momentum of the incident beam, but for the high-harmonic generation, the result can depend on q. The difference will be in the nonlinear susceptibility tensor $\hat{\chi}^{(q)}$ and, as a consequence, the values of the difference between the angular momentum projections Δm_{χ} . Overall, the introduced rule in (17) and (18) can be used for nonlinear circular dichroism in high-harmonic generation in nanostructures with any achiral symmetry and material characterized by the nonlinear susceptibility tensor $\hat{\chi}^{(q)}$ irradiated by any optical vortex. We also note that for the second harmonic generation, the maximum value of Δm_{χ} is equal to 6, thus, according to the rule (17), circular dichroism in the second-harmonic signal is possible only for C_{nv} , D_{nh} symmetries with $n \leq 6$. In a more general q-order harmonic generation case, the maximum value of Δm_{χ} is equal to 2(q+1), thus circular dichroism in the q-order harmonic signal is possible only for C_{nv} , D_{nh} symmetries with

$$\mathfrak{n} \le 2(q+1). \tag{19}$$

In what follows, we consider some examples to show the variety of cases that may arise when all the intermediate calculations are carefully and rigorously considered and show that they will indeed lead to the same result in the end.

4 Analysing particular cases

To provide a clue as to how the main formula works and offer a proof, we investigate specific cases. Through these examinations, we identify patterns that ultimately lead us to derive the general formula. It is done in the following steps:

- 1. Find the nonlinear polarization induced inside the nanoparticle with a particular symmetry made of particular material by a particular vortex.
- 2. Find the symmetry of the eigenmodes of the nanoparticle that can be excited by this nonlinear polarization using the equation (12).
- 3. Analyze the phases of the excited modes as well as their dependence on the incident light polarization and angle β .
- 4. Calculate the total integral intensity $I^{q\omega}$, where the integral is taken by the sphere in the faf-field. For that, the two-mode approximation when two modes of the same symmetry are excited with a phase α between them can be used.
- 5. Analyze the dependence of the total integral intensity on the sign of the incident beam. If the case of left- and right-handed beams don't exactly mirror each other, then the nonlinear circular dichroism exists.
- 6. Find conditions for the appearance of the nonlinear circular dichroism in the particular nanostructure.

In what follows, we analyse the second harmonic, but to generalize the results for the higher harmonic, one should substitute q instead of 2, and consider another (in many cases, similar) set of m_{χ} values, which could be obtained as in Appendix A.2.

4.1 Second harmonic circular dichroism in $GaAs[111]||z C_{3v}$ nanostructure

In this section, we show that in the nanostructure GaAs[111]||z with symmetry C_{3v} nonlinear circular dichroism appears in the second-harmonic signal for angles $\beta \neq \pi \nu/3$, where $\nu \in \mathbb{Z}$, regardless of the absolute value of the angular momentum projection $|m_{in}|$.

4.1.1 Nonlinear polarization

The second-order polarization $\mathbf{P}^{2\omega}(\mathbf{r})$ for the nanostructure GaAs[111]||z (15) reads as follows [32]

$$\mathbf{P}^{2\omega}(r,z,\varphi) \propto \left\{ \sum_{\nu} \mathbf{P}^{2\omega}_{(3+2m^{\mathrm{in}}),\nu}(r,z) \mathrm{e}^{\pm(3+2m^{\mathrm{in}})\mathrm{i}\varphi+\mathfrak{n}\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{\mp 3\mathrm{i}\beta} + \left\{ \sum_{\nu} \mathbf{P}^{2\omega}_{(-3+2m^{\mathrm{in}}),\nu}(r,z) \mathrm{e}^{\pm(-3+2m^{\mathrm{in}})\mathrm{i}\varphi+\mathfrak{n}\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{\pm 3\mathrm{i}\beta} + \left\{ \sum_{\nu} \mathbf{P}^{2\omega}_{2m^{\mathrm{in}},\nu}(r,z) \mathrm{e}^{\pm 2m^{\mathrm{in}}\mathrm{i}\varphi+\mathfrak{n}\nu\mathrm{i}\varphi} \right\},$$
(20)

because for the $\hat{\chi}^{(2)}$ tensor for GaAs[111]||z projections $m_{\chi} = 0, \pm 3$, as it was shown in the previous work [32]. We are interested in the group symmetry C_{3v} , e.g., a trimer of cylinders or a prism with a right triangle at the base, thus the index **n** is equal to 3. For convenience, we will call it trimer further. We also note that in $\mathbf{P}_{m\nu}^{2\omega}(r, z)$ sign of φ -component depends on the handedness, but one can check (See Suppl. Info. in [31]) that it does not alter the general result. We omit the notation, which contains this difference. Nonlinear polarization $\mathbf{P}^{2\omega}(\mathbf{r})$ (20) excites in the trimer its eigenmodes at the second harmonic frequency 2ω . Depending on the momentum projection m^{in} of an incident field, the excited modes can be of any possible symmetry, i.e., transformed under all possible irreducible representations A_1 , A_2 , or E of a C_{3v} group [63, 64]. Specifically, with the help of coupling integrals $D_j = \int_V dV' \mathbf{E}_j^{2\omega}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}')$ (see (12)),

we will prove that modes transformed under E can be excited only if $m^{\text{in}} = 3s - 2$ and $m^{\text{in}} = 3s - 1$, and modes transformed under A₁ and A₂ can be excited only if $m^{\text{in}} = 3s$ where $s \in \mathbb{Z}_+$.

4.1.2 Eigenmode presentations

For that, let us write down the expansions of trimer's eigenmodes transformed under E, and A₁, A₂ in magnetic and electric vector spherical harmonics $\mathbf{M}_{\varepsilon mn}$, $\mathbf{N}_{\varepsilon mn}$ one by one, which definition can be found in Appendix A.3. One should pay attention to the multipolar content of the modes. Importantly, each mode of a particular symmetry consist of the multipoles, which ms differ by \mathfrak{n} .

Eigenmodes, which are transformed under E irrep Decomposition of the eigenmodes transformed under E, according to the tables with a given multipolar content of the eigenmodes [63, 64] consists only of the vector spherical harmonics with the

projections of the angular momentum m = 3s - 1 and m = 3s - 2, where $s \in \mathbb{Z}_+$ with, in general, complex coefficients. However, we note that E is a 2-dimensional irreducible representation, thus there are two orthogonal eigenmodes transformed under this representation. We defer further discussion to Appendix A.5.1 and present here the expansions of the two orthogonal modes $\mathbf{E}_{j}^{2\omega,x\pm iy}(\mathbf{r}')$ transformed under E representation:

$$\mathbf{E}_{j}^{2\omega,x\pm iy}\left(\mathbf{r}'\right) = \sum_{n} \left\{ \mathbf{E}_{j,1n}(r,z) \mathrm{e}^{\pm 1\mathrm{i}\varphi} + \mathbf{E}_{j,2n}(r,z) \mathrm{e}^{\mp 2\mathrm{i}\varphi} + \mathbf{E}_{j,4n}(r,z) \mathrm{e}^{\pm 4\mathrm{i}\varphi} + \mathbf{E}_{j,5n}(r,z) \mathrm{e}^{\mp 5\mathrm{i}\varphi} + \dots \right\},$$
(21)

where index j denotes a specific eigenmode and coefficients $\mathbf{E}_{j,mn}(r,z)$ contain complex constants used in the expansions of the eigenmodes and all other functions and constants independent on coordinate φ , originating from expressions for the magnetic $\mathbf{M}_{\varepsilon mn}(r,z)$ and electric $\mathbf{N}_{\varepsilon mn}(r,z)$ vector spherical harmonics. Note that detailed derivations can be found in Appendix A.5.1.

Eigenmodes, which are transformed under A_1 and A_2 irrep Decompositions of eigenmodes transformed under irreducible representations A_1 and A_2 contain vector spherical harmonics $\mathbf{M}_{\tilde{o}(3s)n}$ and $\mathbf{N}_{\tilde{o}(3s)n}$, where $s \in \mathbb{Z}_+$. Eigenmodes transformed under A_1 are even under reflection in the plane XZ (for a particular orientation of a trimer), while eigenmodes transformed under A_2 are odd. Following the same method used for eigenmodes transformed under E representation, we can derive expressions for eigenmodes transformed under A_1 and A_2 representations. They will take the following form:

$$\mathbf{E}_{j}^{2\omega,\mathrm{A}_{1}}\left(\mathbf{r}'\right) = \sum_{n} \left\{ \left[E_{j,e3n}^{r}\left(r,z\right)\hat{\mathbf{e}}_{r} + E_{j,e3n}^{z}\left(r,z\right)\hat{\mathbf{e}}_{z} \right]\cos 3\varphi + \left. \left. + E_{j,e3n}^{\varphi}\left(r,z\right)\hat{\mathbf{e}}_{\varphi}\sin 3\varphi + \ldots \right] \right\},$$
(22)

$$\mathbf{E}_{j}^{2\omega,A_{2}}\left(\mathbf{r}'\right) = \sum_{n} \left\{ \left[E_{j,o3n}^{r}\left(r,z\right) \hat{\mathbf{e}}_{r} + E_{j,o3n}^{z}\left(r,z\right) \hat{\mathbf{e}}_{z} \right] \sin 3\varphi + \left. + E_{j,o3n}^{\varphi}\left(r,z\right) \hat{\mathbf{e}}_{\varphi} \cos 3\varphi + \dots \right\},$$

$$(23)$$

where coefficients $E_{j,\varepsilon_{3n}}^r(r,z)$, $E_{j,\varepsilon_{3n}}^z(r,z)$, $E_{j,\varepsilon_{3n}}^{\varphi}(r,z)$ contain all functions and constants independent on coordinate φ . For transparency, we have included all intermediate steps of the calculations relevant to this case in Appendix A.5.1.

4.1.3 Coupling integrals

Next, we calculate coupling integrals $D_j = \int_{C_{3v}} dV' \mathbf{E}_j^{2\omega,x\pm iy}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}')$ for all eigenmodes to understand which of them are excited.

Eigenmodes, which are transformed under E irrep Let us use expressions (21) for eigenmodes $\mathbf{E}_{j}^{2\omega,x\pm iy}(\mathbf{r}')$ and decomposition of nonlinear polarization $\mathbf{P}^{2\omega}(\mathbf{r})$ (20) to calculate the coupling integrals D_{j} . Overall, we get four distinct coupling integrals D_{j} . In particular, there are two integrals for eigenmode $\mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}')$ excited by left- and right-handed circularly polarized beam:

$$|L_{m}\rangle: D_{j} = \int_{C_{3v}} dV' \mathbf{E}_{j}^{2\omega,x+iy} (\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{C_{3v}} dV' \sum_{n,\nu} \left(\left[\mathbf{E}_{j,1n} \mathrm{e}^{+1i\varphi} + \mathbf{E}_{j,2n} \mathrm{e}^{-2i\varphi} + \mathbf{E}_{j,4n} \mathrm{e}^{+4i\varphi} + \mathbf{E}_{j,5n} \mathrm{e}^{-5i\varphi} + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{+(3+2m^{\mathrm{in}})i\varphi + 3\nu i\varphi} \right\} \mathrm{e}^{-3i\beta} + \left\{ \mathbf{P}_{(-3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{+(-3+2m^{\mathrm{in}})i\varphi + 3\nu i\varphi} \right\} \mathrm{e}^{+3i\beta} + \left\{ \mathbf{P}_{2m^{\mathrm{in}},\nu}^{2\omega} \mathrm{e}^{+2m^{\mathrm{in}}i\varphi + 3\nu i\varphi} \right\} \right] \right),$$

$$(24)$$

$$|R_{m}\rangle: D_{j} = \int_{C_{3v}} dV' \mathbf{E}_{j}^{2\omega,x+iy} (\mathbf{r}') \mathbf{P}^{2\omega} (\mathbf{r}') \propto$$

$$\propto \int_{C_{3v}} dV' \sum_{n,\nu} \left(\left[\mathbf{E}_{j,1n} \mathrm{e}^{+1i\varphi} + \mathbf{E}_{j,2n} \mathrm{e}^{-2i\varphi} + \mathbf{E}_{j,4n} \mathrm{e}^{+4i\varphi} + \mathbf{E}_{j,5n} \mathrm{e}^{-5i\varphi} + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{-(3+2m^{\mathrm{in}})i\varphi+3\nu i\varphi} \right\} \mathrm{e}^{+3i\beta} + \left\{ \mathbf{P}_{(-3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{-(-3+2m^{\mathrm{in}})i\varphi+3\nu i\varphi} \right\} \mathrm{e}^{-3i\beta} + \left\{ \mathbf{P}_{2m^{\mathrm{in}},\nu}^{2\omega} \mathrm{e}^{-2m^{\mathrm{in}}i\varphi+3\nu i\varphi} \right\} \right] \right),$$

$$(25)$$

and there are two other integrals for eigenmode $\mathbf{E}_{j}^{2\omega,x-\mathrm{i}y}(\mathbf{r}')$ excited by left- and right-handed circularly polarized beams:

$$|L_{m}\rangle: D_{j} = \int_{C_{3v}} dV' \mathbf{E}_{j}^{2\omega,x-iy} (\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{C_{3v}} dV' \sum_{n,\nu} \left(\left[\mathbf{E}_{j,1n} \mathrm{e}^{-1i\varphi} + \mathbf{E}_{j,2n} \mathrm{e}^{+2i\varphi} + \mathbf{E}_{j,4n} \mathrm{e}^{-4i\varphi} + \mathbf{E}_{j,5n} \mathrm{e}^{+5i\varphi} + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{+(3+2m^{\mathrm{in}})i\varphi+3\nu i\varphi} \right\} \mathrm{e}^{-3i\beta} + \left\{ \mathbf{P}_{(-3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{+(-3+2m^{\mathrm{in}})i\varphi+3\nu i\varphi} \right\} \mathrm{e}^{+3i\beta} +$$

$$\left\{ \mathbf{P}_{(-3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{+(-3+2m^{\mathrm{in}})i\varphi+3\nu i\varphi} \right\} \mathrm{e}^{+3i\beta} +$$

$$\left\{ \mathbf{P}_{(-3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{+(-3+2m^{\mathrm{in}})i\varphi+3\nu i\varphi} \right\} \mathrm{e}^{+3i\beta} +$$

$$+ \left\{ \mathbf{P}_{2m^{\text{in}},\nu}^{2\omega} \mathrm{e}^{+2m^{\text{in}}\mathrm{i}\varphi+3\nu\mathrm{i}\varphi} \right\} \right] \right), \qquad (27)$$

$$|R_m\rangle: D_j = \int_{\mathrm{C}_{3v}} \mathrm{d}V' \mathbf{E}_j^{2\omega,x-\mathrm{i}y} \left(\mathbf{r}'\right) \mathbf{P}^{2\omega}(\mathbf{r}') \propto \qquad (27)$$

$$\propto \int_{\mathrm{C}_{3v}} \mathrm{d}V' \sum_{n,\nu} \left(\left[\mathbf{E}_{j,1n} \mathrm{e}^{-1\mathrm{i}\varphi} + \mathbf{E}_{j,2n} \mathrm{e}^{+2\mathrm{i}\varphi} + \mathbf{E}_{j,4n} \mathrm{e}^{-4\mathrm{i}\varphi} + \mathbf{E}_{j,5n} \mathrm{e}^{+5\mathrm{i}\varphi} + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{\text{in}}),\nu}^{2\omega} \mathrm{e}^{-(3+2m^{\text{in}})\mathrm{i}\varphi+3\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{+3\mathrm{i}\beta} + \left\{ \mathbf{P}_{(3+2m^{\text{in}}),\nu}^{2\omega} \mathrm{e}^{-(-3+2m^{\text{in}})\mathrm{i}\varphi+3\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{-3\mathrm{i}\beta} + \left\{ \mathbf{P}_{(-3+2m^{\text{in}}),\nu}^{2\omega} \mathrm{e}^{-2m^{\text{in}}\mathrm{i}\varphi+3\nu\mathrm{i}\varphi} \right\} \right] \right).$$

Eigenmodes, which are transformed under \mathbf{A}_1 and \mathbf{A}_2 irrep Next, let us use expressions (22) and (23) for eigenmodes $\mathbf{E}_j^{2\omega,A_1}(\mathbf{r}')$ and $\mathbf{E}_j^{2\omega,A_2}(\mathbf{r}')$ and again the decomposition of nonlinear polarization $\mathbf{P}^{2\omega}(\mathbf{r})$ (20) to calculate the coupling integrals D_j for this case. There are two integrals for eigenmode $\mathbf{E}_j^{2\omega,A_1}(\mathbf{r}')$ excited by left- and right-handed circularly polarized beams:

$$|L_{m}\rangle: D_{j} = \int_{C_{3v}} dV' \mathbf{E}_{j}^{2\omega,A_{1}} (\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{C_{3v}} dV' \sum_{n,\nu} \left(\left[\left[E_{j,e3n}^{r} \left(r,z \right) \hat{\mathbf{e}}_{r} + E_{j,e3n}^{z} \left(r,z \right) \hat{\mathbf{e}}_{z} \right] \cos 3\varphi + E_{j,e3n}^{\varphi} \left(r,z \right) \hat{\mathbf{e}}_{\varphi} \sin 3\varphi + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{in}),\nu}^{2\omega} \mathbf{e}^{+(3+2m^{in})\mathbf{i}\varphi+3\nu\mathbf{i}\varphi} \right\} \mathbf{e}^{-3\mathbf{i}\beta} + \left\{ \mathbf{P}_{(-3+2m^{in}),\nu}^{2\omega} \mathbf{e}^{+(-3+2m^{in})\mathbf{i}\varphi+3\nu\mathbf{i}\varphi} \right\} \mathbf{e}^{+3\mathbf{i}\beta} + \left\{ \mathbf{P}_{2m^{in},\nu}^{2\omega} \mathbf{e}^{+2m^{in}\mathbf{i}\varphi+3\nu\mathbf{i}\varphi} \right\} \right] \right),$$

$$(28)$$

$$|R_{m}\rangle: D_{j} = \int_{C_{3v}} dV' \mathbf{E}_{j}^{2\omega,A_{1}}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{C_{3v}} dV' \sum_{n,\nu} \left(\left[E_{j,e3n}^{r}(r,z) \,\hat{\mathbf{e}}_{r} + E_{j,e3n}^{z}(r,z) \,\hat{\mathbf{e}}_{z} \right] \cos 3\varphi + E_{j,e3n}^{\varphi}(r,z) \,\hat{\mathbf{e}}_{\varphi} \sin 3\varphi + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{in}),\nu}^{2\omega} \mathrm{e}^{-(3+2m^{in})i\varphi+3\nu i\varphi} \right\} \mathrm{e}^{+3i\beta} + \left\{ \mathbf{P}_{(-3+2m^{in}),\nu}^{2\omega} \mathrm{e}^{-(-3+2m^{in})i\varphi+3\nu i\varphi} \right\} \mathrm{e}^{-3i\beta} +$$

$$\left\{ \mathbf{P}_{(-3+2m^{in}),\nu}^{2\omega} \mathrm{e}^{-(-3+2m^{in})i\varphi+3\nu i\varphi} \right\} \mathrm{e}^{-3i\beta} +$$

$$\left\{ \mathbf{P}_{(-3+2m^{in}),\nu}^{2\omega} \mathrm{e}^{-(-3+2m^{in})i\varphi+3\nu i\varphi} \right\} \mathrm{e}^{-3i\beta} +$$

$$+\left\{\mathbf{P}_{2m^{\mathrm{in}},\nu}^{2\omega}\mathrm{e}^{-2m^{\mathrm{in}}\mathrm{i}\varphi+3\nu\mathrm{i}\varphi}\right\}\right]\right),$$

and there are two other integrals for the eigenmode $\mathbf{E}_{j}^{2\omega,A_{2}}(\mathbf{r}')$ excited by left- and right-handed circularly polarized beams:

$$|L_{m}\rangle: D_{j} = \int_{C_{3v}} dV' \mathbf{E}_{j}^{2\omega,A_{2}}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$
(30)

$$\propto \int_{C_{3v}} dV' \sum_{n,\nu} \left(\left[\left[E_{j,o3n}^{r}(r,z) \,\hat{\mathbf{e}}_{r} + E_{j,o3n}^{z}(r,z) \,\hat{\mathbf{e}}_{z} \right] \sin 3\varphi + E_{j,o3n}^{\varphi}(r,z) \,\hat{\mathbf{e}}_{\varphi} \cos 3\varphi + \dots \right] \cdot \right) \cdot \left[\left\{ \mathbf{P}_{(3+2m^{\text{in}}),\nu}^{2\omega} \mathbf{e}^{+(3+2m^{\text{in}})\mathbf{i}\varphi+3\nu\mathbf{i}\varphi} \right\} \mathbf{e}^{-3\mathbf{i}\beta} + \left\{ \mathbf{P}_{(-3+2m^{\text{in}}),\nu}^{2\omega} \mathbf{e}^{+(-3+2m^{\text{in}})\mathbf{i}\varphi+3\nu\mathbf{i}\varphi} \right\} \mathbf{e}^{+3\mathbf{i}\beta} + \left\{ \mathbf{P}_{2m^{\text{in}},\nu}^{2\omega} \mathbf{e}^{+2m^{\text{in}}\varphi+3\nu\mathbf{i}\varphi} \right\} \right] \right),$$

$$|R_{m}\rangle: D_{j} = \int dV' \mathbf{E}_{j}^{2\omega,A_{2}}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$
(31)

$$\propto \int_{\mathcal{C}_{3v}} \mathrm{d}V' \sum_{n,\nu} \left(\left[\left[E_{j,o3n}^{r}(r,z) \,\hat{\mathbf{e}}_{r} + E_{j,o3n}^{z}(r,z) \,\hat{\mathbf{e}}_{z} \right] \sin 3\varphi + E_{j,o3n}^{\varphi}(r,z) \,\hat{\mathbf{e}}_{\varphi} \cos 3\varphi + \dots \right] \cdot \right. \\ \left. \left. \left. \left[\left\{ \mathbf{P}_{(3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{-(3+2m^{\mathrm{in}})\mathrm{i}\varphi + 3\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{+3\mathrm{i}\beta} + \right. \\ \left. + \left\{ \mathbf{P}_{(-3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{-(-3+2m^{\mathrm{in}})\mathrm{i}\varphi + 3\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{-3\mathrm{i}\beta} + \right. \\ \left. + \left\{ \mathbf{P}_{2m^{\mathrm{in}},\nu}^{2\omega} \mathrm{e}^{-2m^{\mathrm{in}}\mathrm{i}\varphi + 3\nu\mathrm{i}\varphi} \right\} \right] \right).$$

4.1.4 Excitation of the modes by different angular momentum

Let us find out, which of the expressions (24), (25), (26), (27), (28), (29), (30), and (31) for coupling integrals D_j give nontrivial answer. For the integral to be non-zero, the integrand should be transformed under the trivial irreducible representation, i.e. A_1 irrep of C_{3v} group [65]. In the group C_{3v} , if the integrand contains exponents $e^{\pm 3is\varphi}$, where $s \in \mathbb{Z}_+$, then the integral expression can be non-zero. Given the above, there will be three different cases dependent on the value of the index m^{in} of incident vortex:

1. $m^{\text{in}} = 3s$, where $s \in \mathbb{Z}_+$

Eigenmodes, which are transformed under E irrep Coupling integrals (24) and (25) for the eigenmode $\mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}')$, as well as (26) and (27) for the eigenmode $\mathbf{E}_{j}^{2\omega,x-iy}(\mathbf{r}')$ can only give zero. Thus, modes transformed under E irrep aren't excited.

Eigenmodes, which are transformed under \mathbf{A}_1 and \mathbf{A}_2 irrep Coupling integrals (28), (29) for the eigenmode $\mathbf{E}_j^{2\omega,A_1}(\mathbf{r}')$ give nonzero results:

$$|L_m\rangle: D_j \propto c_j^{A_1} e^{-3i\beta} + c_j'^{A_1} e^{+3i\beta} + c_j''^{A_1}, \qquad (32)$$
$$|R_m\rangle: D_j \propto c_j^{A_1} e^{+3i\beta} + c_j'^{A_1} e^{-3i\beta} + c_j''^{A_1},$$

in turn, coupling integrals (30) and (31) for the eigenmode $\mathbf{E}_{j}^{2\omega,A_{2}}(\mathbf{r}')$ also give nonzero results:

$$|L_m\rangle : D_j \propto c_j^{A_2} e^{-3i\beta} + c_j'^{A_2} e^{+3i\beta} + c_j''^{A_2}, \qquad (33)$$
$$|R_m\rangle : D_j \propto c_j^{A_2} e^{+3i\beta} + c_j'^{A_2} e^{-3i\beta} + c_j''^{A_2},$$

where coefficients $c_j^{A_1}, c_j'^{A_1}, c_j''^{A_1}$, and $c_j^{A_2}, c_j'^{A_2}, c_j''^{A_2}$ were introduced, and, importantly, they are equal for different polarizations. Substituting the expression (32) for the coupling integral D_j with the eigenmode $\mathbf{E}_j^{2\omega,A_1}(\mathbf{r}')$ into the decomposition of the second harmonic electric field (12):

$$|L_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) \propto \sum_j \mathbf{E}_j^{2\omega,A_1}(\mathbf{r}) \left(c_j^{A_1} \mathrm{e}^{-3\mathrm{i}\beta} + c_j'^{A_1} \mathrm{e}^{+3\mathrm{i}\beta} + c_j''^{A_1} \right), \qquad (34)$$
$$|R_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) \propto \sum_j \mathbf{E}_j^{2\omega,A_1}(\mathbf{r}) \left(c_j^{A_1} \mathrm{e}^{+3\mathrm{i}\beta} + c_j'^{A_1} \mathrm{e}^{-3\mathrm{i}\beta} + c_j''^{A_1} \right),$$

and the expression (33) for the coupling integral D_j with the eigenmode $\mathbf{E}_j^{2\omega,A_2}(\mathbf{r}')$:

$$|L_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) \propto \sum_{j} \mathbf{E}_{j}^{2\omega, A_2}(\mathbf{r}) \left(c_j^{A_2} \mathrm{e}^{-3\mathrm{i}\beta} + c_j'^{A_2} \mathrm{e}^{+3\mathrm{i}\beta} + c_j''^{A_2}\right), \qquad (35)$$
$$|R_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) \propto \sum_{j} \mathbf{E}_{j}^{2\omega, A_2}(\mathbf{r}) \left(c_j^{A_2} \mathrm{e}^{+3\mathrm{i}\beta} + c_j'^{A_2} \mathrm{e}^{-3\mathrm{i}\beta} + c_j''^{A_2}\right).$$

Thus, modes transformed under A_1 and A_2 irrep are excited and the fields are of the form (34) and (35). Note that total electric field $\mathbf{E}^{2\omega}(\mathbf{r})$ is the sum of all excited eigenmodes transformed under different irreducible representations but in equations above (34) and (35), as well as below we write only sum of eigenmodes transformed under the particular irreducible representation that we consider at the moment. We can do it because only modes with the same symmetry can interfere with each other, thus at one moment we can pay attention only to eigenmodes transformed under the same irrep in order to avoid unnecessarily long formulae.

2. $m^{\text{in}} = 3s - 2$, where $s \in \mathbb{Z}_+$

Eigenmodes, which are transformed under E irrep Coupling integrals (24) and (25) with the eigenmode $\mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}')$ give the values:

$$|L_m\rangle$$
: $D_j \propto c_j^+ e^{-3i\beta} + c_j'^+ e^{+3i\beta} + c_j''^+,$ (36)

$$|R_m\rangle$$
: $D_j = 0$,

where coefficients $c_j^+, c_j'^+, c_j''^+$ were introduced. Analogously, expressions (26) and (27) with the eigenmode $\mathbf{E}_j^{2\omega,x-\mathrm{i}y}(\mathbf{r}')$ take the form:

$$|L_m\rangle$$
: $D_j = 0,$ (37)
 $|R_m\rangle$: $D_j \propto c_j^- e^{+3i\beta} + c_j'^- e^{-3i\beta} + c_j''^-,$

where new coefficients $c_j^-, c_j'^-, c_j''^-$ equal up to a sign to the old coefficients $c_j^+, c_j'^+, c_j''^+$ from the expression (36), respectively. It can be proved by changing the $\varphi \to -\varphi$ in the expression (27). Next, we substitute the obtained expression (36) with the eigenmode $\mathbf{E}_j^{2\omega,x+iy}(\mathbf{r}')$ into the decomposition of the second harmonic electric field (12):

$$|L_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) \propto \sum_j \mathbf{E}_j^{2\omega, x+iy}(\mathbf{r}) \left(c_j^+ \mathrm{e}^{-3\mathrm{i}\beta} + c_j'^+ \mathrm{e}^{+3\mathrm{i}\beta} + c_j''^+\right), \qquad (38)$$
$$|R_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) = 0,$$

as well as expression (37) for the coupling integral D_j with the eigenmode $\mathbf{E}_j^{2\omega,x-iy}(\mathbf{r}')$:

$$|L_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) = 0, \qquad (39)$$
$$|R_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) \propto \sum_j \mathbf{E}_j^{2\omega,x-iy}(\mathbf{r}) \left(c_j^+ e^{+3i\beta} + c_j'^+ e^{-3i\beta} + c_j''^+\right).$$

Thus, modes transformed under E irrep are excited and their fields have the forms (38) and (39).

Eigenmodes, which are transformed under \mathbf{A}_1 and \mathbf{A}_2 irrep Coupling integrals (28) and (29) for the eigenmode $\mathbf{E}_j^{2\omega,A_1}(\mathbf{r}')$, and (30) and (31) for the eigenmode $\mathbf{E}_j^{2\omega,A_2}(\mathbf{r}')$ give only zero answers. Thus, modes transformed under these irreps aren't excited.

3. $m^{\text{in}} = 3s - 1$, where $s \in \mathbb{Z}_+$

Eigenmodes, which are transformed under E irrep Coupling integrals (24) and (25) for the eigenmode $\mathbf{E}_{j}^{2\omega,x+\mathrm{i}y}(\mathbf{r}')$ give nonzero values:

$$|L_m\rangle: D_j = 0,$$

$$|R_m\rangle: D_j \propto \tilde{c}_j^+ e^{+3i\beta} + \tilde{c}_j'^+ e^{-3i\beta} + \tilde{c}_j''^+.$$
(40)

Analogously, expressions (26) and (27) for the eigenmode $\mathbf{E}_{j}^{2\omega,x-iy}(\mathbf{r}')$ take the form:

$$|L_m\rangle$$
: $D_j \propto \tilde{c}_j^- e^{-3i\beta} + \tilde{c}_j'^- e^{+3i\beta} + \tilde{c}_j''^-,$ (41)

$$|R_m\rangle$$
: $D_j = 0$

where new coefficients $\tilde{c}_j^-, \tilde{c}_j^{\prime -}, \tilde{c}_j^{\prime -}$ equal up to a sign to the old coefficients $\tilde{c}_j^+, \tilde{c}_j^{\prime +}, \tilde{c}_j^{\prime +}, \tilde{c}_j^{\prime +}$ from the expression (40), due to the same reasons as for coefficients c_j^{\pm} . Next, we substitute the obtained expression (40) for the coupling integral D_j with the eigenmode $\mathbf{E}_j^{2\omega,x+\mathrm{i}y}(\mathbf{r}')$ into (12):

$$|L_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) = 0, \qquad (42)$$
$$|R_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) \propto \sum_j \mathbf{E}_j^{2\omega, x+iy}(\mathbf{r}) \left(\tilde{c}_j^+ \mathrm{e}^{+3\mathrm{i}\beta} + \tilde{c}_j'^+ \mathrm{e}^{-3\mathrm{i}\beta} + \tilde{c}_j''^+\right).$$

and for the coupling integral D_j (41) with the eigenmode $\mathbf{E}_j^{2\omega,x-iy}(\mathbf{r'})$:

$$|L_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) \propto \sum_j \mathbf{E}_j^{2\omega, x-iy}(\mathbf{r}) \left(\tilde{c}_j^+ \mathrm{e}^{-3i\beta} + \tilde{c}_j'^+ \mathrm{e}^{+3i\beta} + \tilde{c}_j''^+\right), \qquad (43)$$
$$|R_m\rangle: \mathbf{E}^{2\omega}(\mathbf{r}) = 0,$$

Thus, modes transformed under E have the form (42) and (43).

Eigenmodes, which are transformed under \mathbf{A}_1 and \mathbf{A}_2 irrep Coupling integrals (28) and (29) with the eigenmode $\mathbf{E}_j^{2\omega,A_1}(\mathbf{r}')$, and (30) and (31) with the eigenmode $\mathbf{E}_j^{2\omega,A_2}(\mathbf{r}')$ give zero. Thus, modes transformed under these irreps aren't excited.

To summarize, dependent on the value of the projection of the angular momentum m^{in} of the incident vortex we have three cases, but despite this we can consider only one of them because electric field $\mathbf{E}^{2\omega}(\mathbf{r})$ always looks the same, i.e., contains three items proportional to the exponents $e^{\pm 3i\beta}$, $e^{\mp 3i\beta}$, or just constant, where the sign depends on the sign of the polarization of the incident vortex. We can relate these terms to the terms in polarization (20).

4.1.5 Total integral second harmonic intensity

We calculate the total integral second harmonic intensity $I^{2\omega}$ in a two modes approximation for the second case, where $m^{\text{in}} = 3s - 2$, and $s \in \mathbb{Z}_+$. This means that we use decompositions of the fields (38) and (39) and take a sum only of two modes with indexes *i* and *j*. Thus, according to the equations, a left-handed beam excites the eigenmodes $\mathbf{E}_j^{2\omega,x+iy}(\mathbf{r})$, while a right-handed beam excites the eigenmodes $\mathbf{E}_j^{2\omega,x-iy}(\mathbf{r})$, and the total integral second harmonic intensity $I^{2\omega}$ for the left- and right-handed beams can be written in the following form:

$$I_{|L_m\rangle,|R_m\rangle}^{2\omega} \propto \int_{\mathrm{sph}} \mathrm{d}V \left| \mathbf{E}_j^{2\omega,x\pm \mathrm{i}y}(\mathbf{r}) \left(a_j^+ \mathrm{e}^{\mp 3\mathrm{i}\beta} + a_j'^+ \mathrm{e}^{\pm 3\mathrm{i}\beta} + a_j''^+ \right) + \left(44 \right) \right.$$

$$\left. + \mathrm{e}^{\mathrm{i}\alpha} \mathbf{E}_i^{2\omega,x\pm \mathrm{i}y}(\mathbf{r}) \left(a_i^+ \mathrm{e}^{-3\mathrm{i}\beta} + a_i'^+ \mathrm{e}^{+3\mathrm{i}\beta} + a_i''^+ \right) \right|^2,$$

where the integral is taken over the big sphere in the far-field, containing the nanostructure. Frequency-dependent phase α between the eigenmodes $\mathbf{E}_{i,j}^{2\omega,x\pm iy}(\mathbf{r})$ which is related to the resonant excitation of the modes is isolated from complex coefficients $c_{j,i}^+, c_{j,i}'^+, c_{j,i}''^+$, and new coefficients $a_{j,i}^+, a_{j,i}''^+$ are introduced.

To avoid cluttering the main text with lengthy technical derivations, we have transferred them to Appendix A.5.2 and present here the final expression for the interference terms $I_{|L_m\rangle,|R_m\rangle}^{2\omega,\text{interf.}}$ of the total intensity, in which we are primarily interested:

$$I_{|L_m\rangle,|R_m\rangle}^{2\omega,\text{interf.}} \propto \int_{\text{sph}} dV e^{-i\alpha} \mathbf{E}_j^{2\omega,x\pm iy}(\mathbf{r}) \left(\mathbf{E}_i^{2\omega,x\pm iy}(\mathbf{r}) \right)^* \cdot$$

$$\cdot \left(A_{ji} + B_{ji} e^{\pm 6i\beta} + C_{ji} e^{\mp 6i\beta} + D_{ji} e^{\pm 3i\beta} + E_{ji} e^{\mp 3i\beta} \right) + \text{c.c.},$$
(45)

where, for simplicity, constants $A_{ji}, B_{ji}, C_{ji}, D_{ji}, E_{ji}$ were introduced. We should pay attention to the following:

- 1. The eigenmode is excited simultaneously by several terms of the polarization. It is possible, because Δm_{χ} coincides with $\mathfrak{n}\nu$ for some $\nu \in \mathbb{Z}$.
- 2. The multiplier $e^{-i\alpha}$ does not depend on the polarization.
- 3. The multipliers $e^{i\Delta m_{\chi}\beta}$ appear and change their sign by changing the polarization of the beam.

This behavior is common and appears every time the dichroism is observed.

4.1.6 Second-harmonic circular dichroism

Result The last step of our proof is to examine the dependence of the total intensity $I_{|L_m\rangle,|R_m\rangle}^{2\omega}$ on the sign of the polarization in detail. The expression for the interference terms $I_{|L_m\rangle,|R_m\rangle}^{2\omega,\text{interf.}}$ (45) can be simplified by taking into account that $\mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}) \left(\mathbf{E}_{i}^{2\omega,x+iy}(\mathbf{r})\right)^{*} = \mathbf{E}_{j}^{2\omega,x-iy}(\mathbf{r}) \left(\mathbf{E}_{i}^{2\omega,x-iy}(\mathbf{r})\right)^{*}$: $I_{|L_m\rangle,|R_m\rangle}^{2\omega,\text{interf.}} \propto e^{-i\alpha} \text{const}_{ji} \cdot \left(A_{ji} + B_{ji}e^{\pm 6i\beta} + C_{ji}e^{\mp 6i\beta} + D_{ji}e^{\pm 3i\beta} + E_{ji}e^{\mp 3i\beta}\right) + \text{c.c.},$ (46)

where \pm corresponds to the sign of polarization of the incident beam and const_{ji} does not depend on polarization. Next, we rewrite this expression in more detail, using the fact that complex coefficients $A_{ji}, B_{ji}, C_{ji}, D_{ji}$, and E_{ji} can be expanded as $A_{ji} = A'_{ji} + iA''_{ji}$ through real A'_{ji} and the imaginary part A''_{ji} :

$$I^{2\omega,\text{interf.}}_{|L_m\rangle,|R_m\rangle} \propto 2\text{const}_{ji} \left(A'_{ji}\cos(\alpha) + A''_{ji}\sin(\alpha) + B'_{ji}\cos(\alpha \mp 6\beta) + B''_{ji}\sin(\alpha \mp 6\beta) + C''_{ji}\sin(\alpha \pm 6\beta) + D'_{ji}\cos(\alpha \mp 3\beta) + D''_{ji}\sin(\alpha \mp 3\beta) + E''_{ji}\cos(\alpha \pm 3\beta) + E''_{ji}\sin(\alpha \pm 3\beta) \right).$$

$$(47)$$

Note that interference contribution (46), (47) belonging to the expression for the total integral second harmonic intensity $I_{|L_m\rangle,|R_m\rangle}^{2\omega}$ contains terms like $\cos(\alpha \pm 3\beta)$. These terms are different for different signs of the polarization of the incident beam for the most values of α and β . In other words, the total integral second harmonic intensity $I^{2\omega}$ contains the interference contribution $I^{2\omega,\text{interf.}}$ that depends on the polarization of the incident beam, if angles β are not equal to $\pi\nu/3$, where $\nu \in \mathbb{Z}$. From the above the conclusion follows: SH-CD can appear appear in nanostructure GaAs[111]||z with symmetry C_{3v} , only if angles $\beta \neq \pi\nu/3$, where $\nu \in \mathbb{Z}$.

Comments Let us add some additional comments for better understanding the result.

- 1. Occurrence of the SH-CD in the structure doesn't depend on the absolute value of the angular momentum projection of the incident vortex $|m^{\text{in}}|$. Even though we in details analyzed the case $m^{\text{in}} = 3s - 2$, where $s \in \mathbb{Z}_+$, nothing will change for the two other cases, when $m^{\text{in}} = 3s$ or $m^{\text{in}} = 3s - 1$ because the dependence of the second harmonic electric field and, consequently, of the total integral second harmonic intensity on the sign of the polarization of the incident field are the same for all cases, as it can be seen in expressions (34), (35), (38), (39), (42) and (43). The main thing is the interplay between Δm_{χ} and \mathfrak{n} , which contributes in the same way as it was discussed in [32].
- 2. We calculated total integral intensity only for two modes transformed under the same irreducible representation because only between them interference is possible.
- 3. Coefficients $A_{ji}, B_{ji}, C_{ji}, D_{ji}$, and E_{ji} can be either real or complex coefficients depending upon whether coefficients $a_j^+, a_j'^+, a_j''^+$ from the decomposition of the intensity (44) are all in-phase or not. In the case of the real coefficients we need to use at least two-mode approximation to obtain the condition for the appearance of the SH-CD because noninterference terms from the equation (139) will be just equal to each other for different beam polarizations. However, if coefficients are complex, it's enough to use only single-mode approximation because not only interference but also noninterference terms contribute to the SH-CD and it leads to the same result. The reason why we made all calculations for the two-mode approximation is that interference contribution works in any case regardless of whether coefficients are complex or real.

4.2 Second harmonic in $GaAs[111] \| z C_{4v}$ nanostructure (no dichroism)

In this section, we will show that in the nanostructure with the same crystal lattice GaAs[111]||z with nanoparticle symmetry C_{4v} second-harmonic circular dichroism cannot ever be obtained, using the same theoretical approach, as in the previous subsection 4.1. The decomposition of the nonlinear polarization $\mathbf{P}^{2\omega}(\mathbf{r})$ will be defined as in (20) due to the same crystal lattice but with $\mathbf{n} = 4$. Firstly, as in the previous example, we prove that the excitement of eigenmodes transformed under irreducible

representations of the C_{4v} , i.e. E, A_1, A_2, B_1 , and B_2 depends on the specific value of the projection $m_{\rm in}$. Specifically, modes transformed under E can always be excited, modes transformed under A_1 and A_2 can be excited only if $m^{in} = 4s$ and $m^{in} = 4s - 2$, and modes transformed under B_1 and B_2 can be excited only if $m^{in} = 4s - 3$ and $m^{\text{in}} = 4s - 1$, where $s \in \mathbb{Z}_+$.

4.2.1**Eigenmode** presentations

Let us consider decompositions of eigenmodes transformed under E, and A_1 , A_2 , as well as B_1 and B_2 in magnetic and electric vector spherical harmonics \mathbf{M}_{emn}^{e} , \mathbf{N}_{emn}^{e} one by one.

Eigenmodes, which are transformed under E irrep Eigenmodes transformed under E can be decomposed into series of vector spherical harmonics $\mathbf{M}_{emn}^{e}, \mathbf{N}_{emn}^{e}$ with m = 2s - 1, where $s \in \mathbb{Z}_+$. Recalling that representation E is a 2-dimensional irreducible representation, we can define two orthogonal eigenmodes transformed under this representation in the following form:

$$\mathbf{E}_{j}^{2\omega,x}\left(\mathbf{r}'\right) = a_{e11}\mathbf{N}_{e11} + a_{e12}\mathbf{N}_{e12} + b_{o11}\mathbf{M}_{o11} + \dots,$$
(48)

$$\mathbf{E}_{j}^{2\omega,y}\left(\mathbf{r}'\right) = a_{o11}\mathbf{N}_{o11} + a_{o12}\mathbf{N}_{o12} + b_{e11}\mathbf{M}_{e11} + \dots$$
(49)

Using the same speculations as in the Appendix (A.5.1), we reach the convenient expressions for orthogonal eigenmodes $\mathbf{E}_{j}^{2\omega,x\pm iy}$ transformed under E:

$$\mathbf{E}_{j}^{2\omega,x\pm\mathrm{i}y}\left(\mathbf{r}'\right)=\tag{50}$$

$$=\sum_{n}\left\{\mathbf{E}_{j,1n}(r,z)e^{\pm 1i\varphi}+\mathbf{E}_{j,3n}(r,z)e^{\mp 3i\varphi}+\mathbf{E}_{j,5n}(r,z)e^{\pm 5i\varphi}+\mathbf{E}_{j,7n}(r,z)e^{\mp 7i\varphi}+\dots\right\},\$$

where $\mathbf{E}_{i,mn}(r,z)$ contains linear combinations $\mathbf{N}(\mathbf{M})_{mn}(r,z)$ with complex coefficients a_{mn}, b_{mn} . Note that signs here are related to the specific symmetry behavior of these exponential terms under C_{4v} transformations, i.e. $e^{1i\varphi}$ behaves as $e^{-3i\varphi}$ but not $e^{3i\varphi}$.

Eigenmodes, which are transformed under A_1 **and** A_2 **irrep** Eigenmodes transformed under irreducible representations A_1 and A_2 contain vector spherical harmonics $\mathbf{M}_{e(4s)n}^{e}$ and $\mathbf{N}_{e(4s)n}^{e}$, where $s \in \mathbb{Z}_{+}$. The eigenmodes transformed under A_{1} are invariant under reflection in the plane XZ, and eigenmodes transformed under A_2 are not. Then, their expansions can be written as:

$$\mathbf{E}_{j}^{2\omega,A_{1}}\left(\mathbf{r}'\right) = a_{e01}\mathbf{N}_{e01} + a_{e44}\mathbf{N}_{e44} + b_{o44}\mathbf{M}_{o44} + \dots,$$
(51)

$$\mathbf{E}_{j}^{2\omega,A_{2}}(\mathbf{r}') = b_{e01}\mathbf{M}_{e01} + b_{e44}\mathbf{M}_{e44} + b_{o44}\mathbf{N}_{o44} + \dots,$$
(51)
$$\mathbf{E}_{j}^{2\omega,A_{2}}(\mathbf{r}') = b_{e01}\mathbf{M}_{e01} + b_{e44}\mathbf{M}_{e44} + a_{o44}\mathbf{N}_{o44} + \dots.$$
(52)

Using the explicit form of the vector spherical harmonics (Appendix A.3) and new notations, we rewrite the expressions above (51) and (52) in the following form:

$$\mathbf{E}_{j}^{2\omega,\mathbf{A}_{1}}\left(\mathbf{r}'\right)=\tag{53}$$

$$=\sum_{n}\left\{\left[E_{j,e4n}^{r}\left(r,z\right)\hat{\mathbf{e}}_{r}+E_{j,e4n}^{z}\left(r,z\right)\hat{\mathbf{e}}_{z}\right]\cos4\varphi+E_{j,e4n}^{\varphi}\left(r,z\right)\hat{\mathbf{e}}_{\varphi}\sin4\varphi+\ldots\right\},\right.$$

$$\mathbf{E}_{j}^{2\omega,A_{2}}\left(\mathbf{r}'\right) =$$

$$= \sum_{n} \left\{ \left[E_{j,o4n}^{r}\left(r,z\right) \hat{\mathbf{e}}_{r} + E_{j,o4n}^{z}\left(r,z\right) \hat{\mathbf{e}}_{z} \right] \sin 4\varphi + E_{j,o4n}^{\varphi}\left(r,z\right) \hat{\mathbf{e}}_{\varphi} \cos 4\varphi + \dots \right\},$$
(54)

where coefficients $E_{j,e_{a}4n}^{r}(r,z)$, $E_{j,e_{a}4n}^{z}(r,z)$, $E_{j,e_{a}4n}^{\varphi}(r,z)$ contain all functions and constants independent on φ .

Eigenmodes, which are transformed under B₁ and B₂ irrep Eigenmodes transformed under irreducible representations B₁ and B₂ contain vector spherical harmonics $\mathbf{M}_{e}^{e}(4s-2)n$ and $\mathbf{N}_{e}^{e}(4s-2)n$, where $s \in \mathbb{Z}_{+}$:

$$\mathbf{E}_{j}^{2\omega,\mathrm{B}_{1}}\left(\mathbf{r}'\right) = a_{e22}\mathbf{N}_{e22} + a_{e26}\mathbf{N}_{e26} + b_{o22}\mathbf{M}_{o22} + \dots,$$
(55)

$$\mathbf{E}_{j}^{2\omega,\mathrm{B}_{2}}\left(\mathbf{r}'\right) = b_{e22}\mathbf{M}_{e22} + a_{o22}\mathbf{N}_{o22} + a_{o26}\mathbf{N}_{o26} + \dots$$
(56)

which can be rewritten as

$$\mathbf{E}_{j}^{2\omega,\mathrm{B}_{1}}\left(\mathbf{r}'\right) =$$

$$= \sum_{n} \left\{ \left[E_{j,e2n}^{r}\left(r,z\right) \hat{\mathbf{e}}_{r} + E_{j,e2n}^{z}\left(r,z\right) \hat{\mathbf{e}}_{z} \right] \cos 2\varphi + E_{j,e2n}^{\varphi}\left(r,z\right) \hat{\mathbf{e}}_{\varphi} \sin 2\varphi + \dots \right\},$$
(57)

$$\mathbf{E}_{j}^{2\omega,\mathrm{B}_{2}}\left(\mathbf{r}'\right) =$$

$$= \sum_{n} \left\{ \left[E_{j,o2n}^{r}\left(r,z\right) \hat{\mathbf{e}}_{r} + E_{j,o2n}^{z}\left(r,z\right) \hat{\mathbf{e}}_{z} \right] \sin 2\varphi + E_{j,o2n}^{\varphi}\left(r,z\right) \hat{\mathbf{e}}_{\varphi} \cos 2\varphi + \dots \right\},$$
(58)

where coefficients $E_{j,o^{2}n}^{r}(r,z)$, $E_{j,o^{2}n}^{z}(r,z)$, $E_{j,o^{2}n}^{\varphi}(r,z)$ contain all functions and constants independent on coordinate φ .

4.2.2 Coupling integrals

Eigenmodes, which are transformed under E irrep Using the expressions (50) for eigenmodes $\mathbf{E}_{j}^{2\omega,x\pm iy}(\mathbf{r}')$ and decomposition of nonlinear polarization $\mathbf{P}^{2\omega}(\mathbf{r})$ (20) we obtain four coupling integrals $D_{j} = \int_{C_{4v}} dV' \mathbf{E}_{j}^{2\omega,x\pm iy}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}')$. In particular, there are two integrals for eigenmode $\mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}')$ excited by left- and right-handed circularly polarized beam:

$$|L_m\rangle: \ \mathbf{D}_j = \int_{\mathbf{C}_{4\mathbf{v}}} \mathrm{d}V' \mathbf{E}_j^{2\omega, x+iy} \left(\mathbf{r}'\right) \mathbf{P}^{2\omega}(\mathbf{r}') \propto \tag{59}$$
$$\propto \int_{\mathbf{C}_{4\mathbf{v}}} \mathrm{d}V' \sum_{n, \nu} \left(\left[\mathbf{E}_{j,1n} \mathrm{e}^{+1i\varphi} + \mathbf{E}_{j,3n} \mathrm{e}^{-3i\varphi} + \mathbf{E}_{j,5n} \mathrm{e}^{+5i\varphi} + \mathbf{E}_{j,7n} \mathrm{e}^{-7i\varphi} + \dots \right] \cdot$$

$$\cdot \left[\left\{ \mathbf{P}_{(3+2m^{\text{in}}),\nu}^{2\omega} \mathrm{e}^{+(3+2m^{\text{in}})\mathrm{i}\varphi+4\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{-3\mathrm{i}\beta} + \left\{ \mathbf{P}_{(-3+2m^{\text{in}}),\nu}^{2\omega} \mathrm{e}^{+(-3+2m^{\text{in}})\mathrm{i}\varphi+4\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{+3\mathrm{i}\beta} + \left\{ \mathbf{P}_{2m^{\text{in}},\nu}^{2\omega} \mathrm{e}^{+2m^{\text{in}}\mathrm{i}\varphi+4\nu\mathrm{i}\varphi} \right\} \right] \right),$$

$$|R_{m}\rangle: D_{j} = \int_{C_{4v}} dV' \mathbf{E}_{j}^{2\omega,x+iy} (\mathbf{r}') \mathbf{P}^{2\omega} (\mathbf{r}') \propto$$

$$\propto \int_{C_{4v}} dV' \sum_{n,\nu} \left(\left[\mathbf{E}_{j,1n} \mathrm{e}^{+1i\varphi} + \mathbf{E}_{j,3n} \mathrm{e}^{-3i\varphi} + \mathbf{E}_{j,5n} \mathrm{e}^{+5i\varphi} + \mathbf{E}_{j,7n} \mathrm{e}^{-7i\varphi} + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{-(3+2m^{\mathrm{in}})i\varphi + 4\nu i\varphi} \right\} \mathrm{e}^{+3i\beta} + \left\{ \mathbf{P}_{(-3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{-(-3+2m^{\mathrm{in}})i\varphi + 4\nu i\varphi} \right\} \mathrm{e}^{-3i\beta} + \left\{ \mathbf{P}_{2m^{\mathrm{in}},\nu}^{2\omega} \mathrm{e}^{-2m^{\mathrm{in}}i\varphi + 4\nu i\varphi} \right\} \right] \right),$$

$$(60)$$

and there are two other integrals for eigenmode $\mathbf{E}_{j}^{2\omega,x-\mathrm{i}y}(\mathbf{r}')$ excited by left- and right-handed circularly polarized beam:

$$|L_{m}\rangle: D_{j} = \int_{C_{4v}} dV' \mathbf{E}_{j}^{2\omega,x-iy} (\mathbf{r}') \mathbf{P}^{2\omega} (\mathbf{r}') \propto$$

$$\propto \int_{C_{4v}} dV' \sum_{n,\nu} \left(\left[\mathbf{E}_{j,1n} \mathrm{e}^{-1i\varphi} + \mathbf{E}_{j,3n} \mathrm{e}^{+3i\varphi} + \mathbf{E}_{j,5n} \mathrm{e}^{-5i\varphi} + \mathbf{E}_{j,7n} \mathrm{e}^{+7i\varphi} + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{+(3+2m^{\mathrm{in}})i\varphi + 4\nu i\varphi} \right\} \mathrm{e}^{-3i\beta} + \left\{ \mathbf{P}_{(-3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{+(-3+2m^{\mathrm{in}})i\varphi + 4\nu i\varphi} \right\} \mathrm{e}^{+3i\beta} + \left\{ \mathbf{P}_{2m^{\mathrm{in}},\nu}^{2\omega} \mathrm{e}^{+2m^{\mathrm{in}}i\varphi + 4\nu i\varphi} \right\} \right] \right),$$

$$(61)$$

$$|R_{m}\rangle: D_{j} = \int_{C_{4v}} dV' \mathbf{E}_{j}^{2\omega,x-iy} (\mathbf{r}') \mathbf{P}^{2\omega} (\mathbf{r}') \propto$$

$$\propto \int_{C_{4v}} dV' \sum_{n,\nu} \left(\left[\mathbf{E}_{j,1n} \mathrm{e}^{-1i\varphi} + \mathbf{E}_{j,3n} \mathrm{e}^{+3i\varphi} + \mathbf{E}_{j,5n} \mathrm{e}^{-5i\varphi} + \mathbf{E}_{j,7n} \mathrm{e}^{+7i\varphi} + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{\mathrm{in}}),\nu}^{2\omega} \mathrm{e}^{-(3+2m^{\mathrm{in}})i\varphi + 4\nu i\varphi} \right\} \mathrm{e}^{+3i\beta} + \right]$$

$$(62)$$

$$+ \left\{ \mathbf{P}^{2\omega}_{(-3+2m^{\mathrm{in}}),\nu} \mathrm{e}^{-(-3+2m^{\mathrm{in}})\mathrm{i}\varphi+4\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{-3\mathrm{i}\beta} + \left\{ \mathbf{P}^{2\omega}_{2m^{\mathrm{in}},\nu} \mathrm{e}^{-2m^{\mathrm{in}}\mathrm{i}\varphi+4\nu\mathrm{i}\varphi} \right\} \right] \right).$$

Eigenmodes, which are transformed under \mathbf{A}_1 and \mathbf{A}_2 irrep Next, let us use expressions (53) and (54) for eigenmodes $\mathbf{E}_j^{2\omega,A_1}(\mathbf{r}')$ and $\mathbf{E}_j^{2\omega,A_2}(\mathbf{r}')$ and again the decomposition of nonlinear polarization $\mathbf{P}^{2\omega}(\mathbf{r})$ (20) to obtain four coupling integrals D_j . Two integrals for eigenmode $\mathbf{E}_j^{2\omega,A_1}(\mathbf{r}')$ excited by left- and right-handed circularly polarized beam:

$$|L_{m}\rangle: D_{j} = \int_{C_{4v}} dV' \mathbf{E}_{j}^{2\omega,A_{1}}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{C_{4v}} dV' \sum_{n,\nu} \left(\left[\left[E_{j,e4n}^{r}\left(r,z\right)\hat{\mathbf{e}}_{r} + E_{j,e4n}^{z}\left(r,z\right)\hat{\mathbf{e}}_{z} \right] \cos 4\varphi + E_{j,e4n}^{\varphi}\left(r,z\right)\hat{\mathbf{e}}_{\varphi} \sin 4\varphi + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{in}),\nu}^{2\omega} \mathbf{e}^{+(3+2m^{in})i\varphi+4\nu i\varphi} \right\} \mathbf{e}^{-3i\beta} + \left\{ \mathbf{P}_{(-3+2m^{in}),\nu}^{2\omega} \mathbf{e}^{+(-3+2m^{in})i\varphi+4\nu i\varphi} \right\} \mathbf{e}^{+3i\beta} + \left\{ \mathbf{P}_{2m^{in},\nu}^{2\omega} \mathbf{e}^{+2m^{in}i\varphi+4\nu i\varphi} \right\} \right] \right),$$

$$(63)$$

$$|R_{m}\rangle: D_{j} = \int_{C_{4v}} dV' \mathbf{E}_{j}^{2\omega,A_{1}}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{C_{4v}} dV' \sum_{n,\nu} \left(\left[\left[E_{j,e4n}^{r}\left(r,z\right)\hat{\mathbf{e}}_{r} + E_{j,e4n}^{z}\left(r,z\right)\hat{\mathbf{e}}_{z} \right] \cdot \cos 4\varphi + E_{j,e4n}^{\varphi}\left(r,z\right)\hat{\mathbf{e}}_{\varphi}\sin 4\varphi + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{in}),\nu}^{2\omega} \mathbf{e}^{-(3+2m^{in})i\varphi+4\nu i\varphi} \right\} \mathbf{e}^{+3i\beta} + \left\{ \mathbf{P}_{(-3+2m^{in}),\nu}^{2\omega} \mathbf{e}^{-(-3+2m^{in})i\varphi+4\nu i\varphi} \right\} \mathbf{e}^{-3i\beta} + \left\{ \mathbf{P}_{2m^{in},\nu}^{2\omega} \mathbf{e}^{-2m^{in}i\varphi+4\nu i\varphi} \right\} \right] \right),$$

$$(64)$$

and for the eigenmode $\mathbf{E}_{j}^{2\omega,\mathbf{A}_{2}}\left(\mathbf{r}'\right)$:

$$|L_{m}\rangle: \ \mathbf{D}_{j} = \int_{\mathbf{C}_{4\mathbf{v}}} \mathrm{d}V' \mathbf{E}_{j}^{2\omega,\mathbf{A}_{2}}\left(\mathbf{r}'\right) \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{\mathbf{C}_{4\mathbf{v}}} \mathrm{d}V' \sum_{n,\nu} \left(\left[\left[E_{j,o4n}^{r}\left(r,z\right) \hat{\mathbf{e}}_{r} + E_{j,o4n}^{z}\left(r,z\right) \hat{\mathbf{e}}_{z} \right] \sin 4\varphi + E_{j,o4n}^{\varphi}\left(r,z\right) \hat{\mathbf{e}}_{\varphi} \cos 4\varphi + \dots \right] \cdot$$

$$(65)$$

$$\cdot \left[\left\{ \mathbf{P}_{(3+2m^{\text{in}}),\nu}^{2\omega} \mathrm{e}^{+(3+2m^{\text{in}})\mathrm{i}\varphi+4\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{-3\mathrm{i}\beta} + \left\{ \mathbf{P}_{(-3+2m^{\text{in}}),\nu}^{2\omega} \mathrm{e}^{+(-3+2m^{\text{in}})\mathrm{i}\varphi+4\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{+3\mathrm{i}\beta} + \left\{ \mathbf{P}_{2m^{\text{in}},\nu}^{2\omega} \mathrm{e}^{+2m^{\text{in}}\mathrm{i}\varphi+4\nu\mathrm{i}\varphi} \right\} \right] \right),$$

$$|R_{m}\rangle: D_{j} = \int_{C_{4v}} dV' \mathbf{E}_{j}^{2\omega,A_{2}} (\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{C_{4v}} dV' \sum_{n,\nu} \left(\left[\left[E_{j,o4n}^{r} \left(r,z \right) \hat{\mathbf{e}}_{r} + E_{j,o4n}^{z} \left(r,z \right) \hat{\mathbf{e}}_{z} \right] \sin 4\varphi + E_{j,o4n}^{\varphi} \left(r,z \right) \hat{\mathbf{e}}_{\varphi} \cos 4\varphi + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{in}),\nu}^{2\omega} \mathrm{e}^{-(3+2m^{in})i\varphi + 4\nu i\varphi} \right\} \mathrm{e}^{+3i\beta} + \left\{ \mathbf{P}_{(-3+2m^{in}),\nu}^{2\omega} \mathrm{e}^{-(-3+2m^{in})i\varphi + 4\nu i\varphi} \right\} \mathrm{e}^{-3i\beta} + \left\{ \mathbf{P}_{2m^{in},\nu}^{2\omega} \mathrm{e}^{-2m^{in}i\varphi + 4\nu i\varphi} \right\} \right] \right).$$

$$(66)$$

Eigenmodes, which are transformed under B₁ and B₂ Finally, in similar manner for eigenmodes $\mathbf{E}_{j}^{2\omega,\mathrm{B}_{1}}(\mathbf{r}')$ and $\mathbf{E}_{j}^{2\omega,\mathrm{B}_{2}}(\mathbf{r}')$, using (57) and (58), and again the decomposition of nonlinear polarization $\mathbf{P}^{2\omega}(\mathbf{r})$ (20), we obtain two integrals for eigenmode $\mathbf{E}_{j}^{2\omega,\mathrm{B}_{1}}(\mathbf{r}')$:

$$|L_{m}\rangle: D_{j} = \int_{C_{4v}} dV' \mathbf{E}_{j}^{2\omega,B_{1}}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{C_{4v}} dV' \sum_{n,\nu} \left(\left[\left[E_{j,e2n}^{r}(r,z) \,\hat{\mathbf{e}}_{r} + E_{j,e2n}^{z}(r,z) \,\hat{\mathbf{e}}_{z} \right] \cos 2\varphi + E_{j,e2n}^{\varphi}(r,z) \,\hat{\mathbf{e}}_{\varphi} \sin 2\varphi + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{\text{in}}),\nu}^{2\omega} \mathrm{e}^{+(3+2m^{\text{in}})\mathrm{i}\varphi + 4\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{-3\mathrm{i}\beta} + \left\{ \mathbf{P}_{(-3+2m^{\text{in}}),\nu}^{2\omega} \mathrm{e}^{+(-3+2m^{\text{in}})\mathrm{i}\varphi + 4\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{+3\mathrm{i}\beta} + \left\{ \mathbf{P}_{(2m^{\text{in}},\nu}^{2\omega} \mathrm{e}^{+2m^{\text{in}}\mathrm{i}\varphi + 4\nu\mathrm{i}\varphi} \right\} \right] \right),$$

$$(67)$$

$$|R_{m}\rangle: D_{j} = \int_{C_{4v}} dV' \mathbf{E}_{j}^{2\omega,B_{1}}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{C_{4v}} dV' \sum_{n,\nu} \left(\left[E_{j,e2n}^{r}(r,z) \,\hat{\mathbf{e}}_{r} + E_{j,e2n}^{z}(r,z) \,\hat{\mathbf{e}}_{z} \right] \cos 2\varphi + E_{j,e2n}^{\varphi}(r,z) \,\hat{\mathbf{e}}_{\varphi} \sin 2\varphi + \dots \right] \cdot$$
(68)

$$\cdot \left[\left\{ \mathbf{P}_{(3+2m^{\text{in}}),\nu}^{2\omega} \mathrm{e}^{-(3+2m^{\text{in}})\mathrm{i}\varphi+4\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{+3\mathrm{i}\beta} + \left\{ \mathbf{P}_{(-3+2m^{\text{in}}),\nu}^{2\omega} \mathrm{e}^{-(-3+2m^{\text{in}})\mathrm{i}\varphi+4\nu\mathrm{i}\varphi} \right\} \mathrm{e}^{-3\mathrm{i}\beta} + \left\{ \mathbf{P}_{2m^{\text{in}},\nu}^{2\omega} \mathrm{e}^{-2m^{\text{in}}\mathrm{i}\varphi+4\nu\mathrm{i}\varphi} \right\} \right] \right),$$

and two other integrals for eigenmode $\mathbf{E}_{j}^{2\omega,\mathrm{B}_{2}}(\mathbf{r}')$:

$$|L_{m}\rangle: D_{j} = \int_{C_{4v}} dV' \mathbf{E}_{j}^{2\omega,B_{2}}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{C_{4v}} dV' \sum_{n,\nu} \left(\left[\left[E_{j,o2n}^{r}\left(r,z\right)\hat{\mathbf{e}}_{r} + E_{j,o2n}^{z}\left(r,z\right)\hat{\mathbf{e}}_{z} \right] \sin 2\varphi + E_{j,o2n}^{\varphi}\left(r,z\right)\hat{\mathbf{e}}_{\varphi}\cos 2\varphi + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{in}),\nu}^{2\omega} \mathbf{e}^{+(3+2m^{in})i\varphi+4\nu i\varphi} \right\} \mathbf{e}^{-3i\beta} + \left\{ \mathbf{P}_{(-3+2m^{in}),\nu}^{2\omega} \mathbf{e}^{+(-3+2m^{in})i\varphi+4\nu i\varphi} \right\} \mathbf{e}^{+3i\beta} + \left\{ \mathbf{P}_{2m^{in},\nu}^{2\omega} \mathbf{e}^{+2m^{in}i\varphi+4\nu i\varphi} \right\} \right] \right),$$

$$(69)$$

$$|R_{m}\rangle: D_{j} = \int_{C_{4v}} dV' \mathbf{E}_{j}^{2\omega,B_{2}}(\mathbf{r}') \mathbf{P}^{2\omega}(\mathbf{r}') \propto$$

$$\propto \int_{C_{4v}} dV' \sum_{n,\nu} \left(\left[\left[E_{j,o2n}^{r}\left(r,z\right)\hat{\mathbf{e}}_{r} + E_{j,o2n}^{z}\left(r,z\right)\hat{\mathbf{e}}_{z} \right] \sin 2\varphi + E_{j,o2n}^{\varphi}\left(r,z\right)\hat{\mathbf{e}}_{\varphi}\cos 2\varphi + \dots \right] \cdot \left[\left\{ \mathbf{P}_{(3+2m^{in}),\nu}^{2\omega} \mathbf{e}^{-(3+2m^{in})i\varphi+4\nu i\varphi} \right\} \mathbf{e}^{+3i\beta} + \left\{ \mathbf{P}_{(-3+2m^{in}),\nu}^{2\omega} \mathbf{e}^{-(-3+2m^{in})i\varphi+4\nu i\varphi} \right\} \mathbf{e}^{-3i\beta} + \left\{ \mathbf{P}_{2m^{in},\nu}^{2\omega} \mathbf{e}^{-2m^{in}i\varphi+4\nu i\varphi} \right\} \right] \right).$$

$$(70)$$

4.2.3 Excitation of the modes by different angular momentum

Let us consider, which of the expressions (59), (60), (61), (62), (63), (64), as well as (65), (66), (67), (68), (69), and (70) for coupling integrals D_j give a nontrivial answer. For that, the integrand should be transformed under the trivial irreducible representation, i.e. A_1 of group symmetry C_{4v} . Therefore, if the integrand contains exponents $e^{\pm 4is\varphi}$, where $s \in \mathbb{Z}_+$, then the integral can be nonzero. In view of the above, there will be four different cases dependent on the value of the index m^{in} of the incident vortex:

1. $m^{\text{in}} = 4s$, where $s \in \mathbb{Z}_+$:

Eigenmodes, which are transformed under E irrep Coupling integrals (59), (60) for the eigenmode $\mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}')$ give nonzero results:

$$|L_m\rangle$$
: $D_j \propto c_j e^{-3i\beta}$, (71)
 $|R_m\rangle$: $D_j \propto c'_j e^{-3i\beta}$.

Coupling integrals (61), (62) for the eigenmode $\mathbf{E}_{j}^{2\omega,x-iy}(\mathbf{r}')$ give nonzero results:

$$|L_m\rangle$$
: $D_j \propto c'_j e^{+3i\beta}$, (72)
 $|R_m\rangle$: $D_j \propto c_j e^{+3i\beta}$.

Eigenmodes, which are transformed under \mathbf{A}_1 and \mathbf{A}_2 irrep Coupling integrals (63), (64) for the eigenmode $\mathbf{E}_j^{2\omega,A_1}(\mathbf{r}')$ give nonzero results:

$$|L_m\rangle: D_j \propto c_j^{A_1}, \tag{73}$$
$$|R_m\rangle: D_j \propto c_j^{A_1}.$$

Coupling integrals (65), (66) for the eigenmode $\mathbf{E}_{j}^{2\omega,A_{2}}(\mathbf{r}')$ give nonzero results:

$$|L_m\rangle$$
: $D_j \propto c_j^{A_2}$, (74)
 $|R_m\rangle$: $D_j \propto c_j^{A_2}$.

Eigenmodes, which are transformed under B₁ and B₂ irrep Coupling integrals (67) and (68) for the eigenmode $\mathbf{E}_{j}^{2\omega,B_{1}}(\mathbf{r}')$, as well as (69) and (70) for the eigenmode $\mathbf{E}_{j}^{2\omega,B_{2}}(\mathbf{r}')$ give only trivial answers. Thus, modes transformed under these irrep aren't excited.

Comment: we omit all discussions related to the coefficients because that all was mentioned in the previous section 4.1.

2. $m^{\text{in}} = 4s - 2$, where $s \in \mathbb{Z}_+$:

Eigenmodes, which are transformed under E irrep Coupling integrals (59), (60) for the eigenmode $\mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}')$:

$$|L_m\rangle: D_j \propto \tilde{c}_j e^{-3i\beta},$$

$$|R_m\rangle: D_j \propto \tilde{c}'_j e^{-3i\beta}.$$
(75)

Coupling integrals (61), (62) for the eigenmode $\mathbf{E}_{j}^{2\omega,x-\mathrm{i}y}(\mathbf{r}')$:

$$|L_m\rangle: D_j \propto \tilde{c}'_j e^{+3i\beta}, \qquad (76)$$
$$|R_m\rangle: D_j \propto \tilde{c}_j e^{+3i\beta}.$$

Eigenmodes, which are transformed under \mathbf{A}_1 and \mathbf{A}_2 irrep Coupling integrals (63), (64) for the eigenmode $\mathbf{E}_j^{2\omega, \mathbf{A}_1}(\mathbf{r}')$:

$$|L_m\rangle: D_j \propto \tilde{c}_j^{A_1}, \tag{77}$$
$$|R_m\rangle: D_j \propto \tilde{c}_j^{A_1}.$$

Coupling integrals (65), (66) for the eigenmode $\mathbf{E}_{j}^{2\omega,A_{2}}(\mathbf{r}')$:

$$|L_m\rangle: D_j \propto \tilde{c}_j^{A_2}, \tag{78}$$
$$|R_m\rangle: D_j \propto \tilde{c}_j^{A_2}.$$

Eigenmodes, which are transformed under B₁ and B₂ irrep Coupling integrals (67) and (68) with the eigenmode $\mathbf{E}_{j}^{2\omega,B_{1}}(\mathbf{r}')$, and (69) and (70) for $\mathbf{E}_{j}^{2\omega,B_{2}}(\mathbf{r}')$ give zeros, and these modes aren't excited.

3. $m^{\text{in}} = 4s - 3$, where $s \in \mathbb{Z}_+$:

Eigenmodes, which are transformed under E irrep Integrals (59), (60) with $\mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}')$ are:

$$|L_m\rangle$$
: $D_j \propto C_j e^{+3i\beta}$, (79)
 $|R_m\rangle$: $D_j \propto C'_j e^{+3i\beta}$.

Coupling integrals (61), (62) for the eigenmode $\mathbf{E}_{j}^{2\omega,x-iy}(\mathbf{r}')$ give nonzero results:

$$|L_m\rangle$$
: $D_j \propto C'_j e^{-3i\beta}$, (80)
 $|R_m\rangle$: $D_j \propto C_j e^{-3i\beta}$.

Eigenmodes, which are transformed under \mathbf{A}_1 and \mathbf{A}_2 irrep Integrals (63) and (64) for $\mathbf{E}_j^{2\omega,A_1}(\mathbf{r}')$, and (65), (66) for $\mathbf{E}_j^{2\omega,A_2}(\mathbf{r}')$ give zero.

Eigenmodes, which are transformed under B₁ and B₂ irrep Coupling integrals (67), (68) for the eigenmode $\mathbf{E}_{j}^{2\omega,B_{1}}(\mathbf{r}')$:

$$|L_m\rangle$$
: $D_j \propto c_j^{B_1}$, (81)
 $|R_m\rangle$: $D_j \propto c_j^{B_1}$.

Coupling integrals (69), (70) for the eigenmode $\mathbf{E}_{j}^{2\omega,\mathrm{B}_{2}}(\mathbf{r}')$:

$$|L_m\rangle : D_j \propto c_j^{B_2},$$
 (82)
 $|R_m\rangle : D_j \propto c_j^{B_2}.$

4. $m^{\text{in}} = 4s - 1$, where $s \in \mathbb{Z}_+$:

Eigenmodes, which are transformed under E irrep Coupling integrals (59), (60) for the eigenmode $\mathbf{E}_{j}^{2\omega,x+\mathrm{i}y}(\mathbf{r}')$:

$$|L_m\rangle: D_j \propto \tilde{C}_j e^{+3i\beta}, \qquad (83)$$
$$|R_m\rangle: D_j \propto \tilde{C}'_j e^{+3i\beta}.$$

Coupling integrals (61), (62) for the eigenmode $\mathbf{E}_{j}^{2\omega,x-\mathrm{i}y}(\mathbf{r}')$:

$$|L_m\rangle$$
: $D_j \propto \tilde{C}'_j e^{-3i\beta}$, (84)
 $|R_m\rangle$: $D_j \propto \tilde{C}_j e^{-3i\beta}$.

Eigenmodes, which are transformed under \mathbf{A}_1 and \mathbf{A}_2 irrep Integrals (63), (64) for $\mathbf{E}_j^{2\omega,\mathbf{A}_1}(\mathbf{r}')$, as well as (65), (66) for $\mathbf{E}_j^{2\omega,\mathbf{A}_2}(\mathbf{r}')$ give zero.

Eigenmodes, which are transformed under \mathbf{B}_1 and \mathbf{B}_2 irrep Integrals (67), (68) for the eigenmode $\mathbf{E}_j^{2\omega, \mathbf{B}_1}(\mathbf{r}')$:

$$|L_m\rangle: D_j \propto \tilde{c}_j^{\mathrm{B}_1}, \tag{85}$$
$$|R_m\rangle: D_j \propto \tilde{c}_j^{\mathrm{B}_1}.$$

Integrals (69), (70) for the eigenmode $\mathbf{E}_{j}^{2\omega,\mathrm{B}_{2}}(\mathbf{r}')$:

$$|L_m\rangle : D_j \propto \tilde{c}_j^{B_2},$$
 (86)
 $|R_m\rangle : D_j \propto \tilde{c}_j^{B_2}.$

To summarize, depending on the value of the projection of the angular momentum m^{in} of the incident vortex, we have four cases. However, as in the previous example (Sec. 4.1), due to the somewhat similar expressions for the coupling integrals which are proportional to either the exponents $e^{+3i\beta}$, $e^{-3i\beta}$, or just constants, we can consider only one of them. Let us proceed with further calculations, assuming $m^{\text{in}} = 4s - 3$, where $s \in \mathbb{Z}_+$.

4.2.4 Second-harmonic electric field

Let us obtain expressions for the second-harmonic electric field $\mathbf{E}^{2\omega}$, assuming $m^{\text{in}} = 4s - 3$, where $s \in \mathbb{Z}_+$. This means that we use coupling integrals (79), (80), (81), and (82)

Eigenmodes, which are transformed under E We calculate second-harmonic electric field for the eigenmode $\mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}')$ (79):

$$|L_m\rangle$$
: $\mathbf{E}^{2\omega} \propto \sum_j \mathbf{E}_j^{2\omega, x+iy}(\mathbf{r}) C_j \mathrm{e}^{+3i\beta},$ (87)

$$|R_m\rangle$$
: $\mathbf{E}^{2\omega} \propto \sum_j \mathbf{E}_j^{2\omega, x+\mathrm{i}y}(\mathbf{r}) C'_j \mathrm{e}^{+3\mathrm{i}\beta},$

for the eigenmode $\mathbf{E}_{j}^{2\omega,x-\mathrm{i}y}\left(\mathbf{r}'\right)$ (80):

$$|L_m\rangle: \mathbf{E}^{2\omega} \propto \sum_{j} \mathbf{E}_{j}^{2\omega, x-\mathrm{i}y}(\mathbf{r}) C_{j}' \mathrm{e}^{-3\mathrm{i}\beta}, \qquad (88)$$
$$|R_m\rangle: \mathbf{E}^{2\omega} \propto \sum_{j} \mathbf{E}_{j}^{2\omega, x-\mathrm{i}y}(\mathbf{r}) C_{j} \mathrm{e}^{-3\mathrm{i}\beta},$$

for the eigenmode $\mathbf{E}_{j}^{\mathrm{B}_{1}}\left(\mathbf{r}'\right)$ (81):

$$|L_m\rangle: \mathbf{E}^{2\omega} \propto \sum_{j} \mathbf{E}_{j}^{\mathrm{B}_{1}}(\mathbf{r})c_{j}^{\mathrm{B}_{1}},$$

$$|R_m\rangle: \mathbf{E}^{2\omega} \propto \sum_{j} \mathbf{E}_{j}^{\mathrm{B}_{1}}(\mathbf{r})c_{j}^{\mathrm{B}_{1}},$$
(89)

and, finally, for the eigenmode $\mathbf{E}_{j}^{\mathrm{B}_{2}}(\mathbf{r}')$ (82):

$$|L_m\rangle: \mathbf{E}^{2\omega} \propto \sum_{j} \mathbf{E}_{j}^{\mathrm{B}_{2}}(\mathbf{r}) c_{j}^{\mathrm{B}_{2}}, \qquad (90)$$
$$|R_m\rangle: \mathbf{E}^{2\omega} \propto \sum_{j} \mathbf{E}_{j}^{\mathrm{B}_{2}}(\mathbf{r}) c_{j}^{\mathrm{B}_{2}}.$$

4.2.5 Total integral second harmonic intensity

We calculate the total integral second harmonic intensity $I^{2\omega}$ in a two modes approximation, using the decomposistions of the field above $\mathbf{E}^{2\omega}$ (87), (88), (89), (90). We take a sum only of two modes with indexes *i* and *j*. Recall that we consider eigenmodes transformed under E irrep separately because modes transformed under different irreps don't interfere with each other. A left-handed and right-handed beam excites the eigenmodes $\mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r})$, and the second-harmonic intensity $I_{|L_m\rangle}^{2\omega}$ and $I_{|R_m\rangle}^{2\omega}$ can be written as follows:

$$I_{|L_m\rangle}^{2\omega} \propto \int_{\text{sph}} \mathrm{d}V \left| \mathbf{E}_j^{2\omega,x+\mathrm{i}y}(\mathbf{r}) \widetilde{C}_j \mathrm{e}^{+3\mathrm{i}\beta} + \mathrm{e}^{\mathrm{i}\alpha} \mathbf{E}_i^{2\omega,x+\mathrm{i}y}(\mathbf{r}) \widetilde{C}_i \mathrm{e}^{+3\mathrm{i}\beta} \right|^2, \tag{91}$$

$$I_{|R_m\rangle}^{2\omega} \propto \int_{\text{sph}} dV \left| \mathbf{E}_j^{2\omega,x+iy}(\mathbf{r}) \widetilde{C}_j' \mathrm{e}^{+3\mathrm{i}\beta} + \mathrm{e}^{\mathrm{i}\alpha} \mathbf{E}_i^{2\omega,x+iy}(\mathbf{r}) \widetilde{C}_i' \mathrm{e}^{+3\mathrm{i}\beta} \right|^2, \tag{92}$$

where in the explicit form the phase α between eigenmodes $\mathbf{E}_{i,j}^{2\omega,x+iy}(\mathbf{r})$ was extracted from coefficients $C_{j,i}, C'_{j,i}$, and, as a consequence the new coefficients $\widetilde{C}_{j,i}, \widetilde{C}'_{j,i}$ were introduced. Interference terms are proportional to:

$$I_{|L_m\rangle}^{2\omega,\text{interf.}} \propto \int_{\text{sph}} dV e^{-i\alpha} \mathbf{E}_j^{2\omega,x+iy}(\mathbf{r}) \left(\mathbf{E}_i^{2\omega,x+iy}(\mathbf{r})\right)^* A_{ji} + \text{c.c.}, \tag{93}$$

$$I_{|R_m\rangle}^{2\omega,\text{interf.}} \propto \int_{\text{sph}} dV e^{-i\alpha} \mathbf{E}_j^{2\omega,x+iy}(\mathbf{r}) \left(\mathbf{E}_i^{2\omega,x+iy}(\mathbf{r})\right)^* A'_{ji} + \text{c.c.},$$
(94)

where $I^{2\omega,\text{interf.}}_{|L_m\rangle,|R_m\rangle}$ are related to the interference terms from the expressions (91) and (92) for the total integral second harmonic intensity $I^{2\omega}_{|L_m\rangle,|R_m\rangle}$, and new coefficients A_{ji}, A'_{ji} contain all combinations of the old coefficients $\widetilde{C}_{j,i}, \widetilde{C}'_{j,i}$. Analogously, we obtain the total integral second harmonic intensity $I^{2\omega}_{|L_m\rangle,|R_m\rangle}$ for two eigenmodes $\mathbf{E}_j^{2\omega,x-iy}(\mathbf{r})$ excited by a left-handed and right-handed beam:

$$I_{|L_m\rangle}^{2\omega} \propto \int_{\text{sph}} \mathrm{d}V \left| \mathbf{E}_j^{2\omega,x-\mathrm{i}y}(\mathbf{r}) \widetilde{C}_j' \mathrm{e}^{-3\mathrm{i}\beta} + \mathrm{e}^{\mathrm{i}\alpha} \mathbf{E}_i^{2\omega,x-\mathrm{i}y}(\mathbf{r}) \widetilde{C}_i' \mathrm{e}^{-3\mathrm{i}\beta} \right|^2, \tag{95}$$

$$I_{|R_m\rangle}^{2\omega} \propto \int_{\text{sph}} \mathrm{d}V \left| \mathbf{E}_j^{2\omega,x-\mathrm{i}y}(\mathbf{r}) \widetilde{C}_j \mathrm{e}^{-3\mathrm{i}\beta} + \mathrm{e}^{\mathrm{i}\alpha} \mathbf{E}_i^{2\omega,x-\mathrm{i}y}(\mathbf{r}) \widetilde{C}_i \mathrm{e}^{-3\mathrm{i}\beta} \right|^2.$$
(96)

Interference terms are proportional to:

$$I_{|L_m\rangle}^{2\omega,\text{interf.}} \propto \int_{\text{sph}} dV e^{-i\alpha} \mathbf{E}_j^{2\omega,x-iy}(\mathbf{r}) \left(\mathbf{E}_i^{2\omega,x-iy}(\mathbf{r})\right)^* A'_{ji} + \text{c.c.}, \tag{97}$$

$$I_{|R_m\rangle}^{2\omega,\text{interf.}} \propto \int_{\text{sph}} dV e^{-i\alpha} \mathbf{E}_j^{2\omega,x-iy}(\mathbf{r}) \left(\mathbf{E}_i^{2\omega,x-iy}(\mathbf{r})\right)^* A_{ji} + \text{c.c.},$$
(98)

where we should also note that the terms of the form $\mathbf{E}_{j}^{2\omega,x+\mathrm{i}y}(\mathbf{r}) \left(\mathbf{E}_{i}^{2\omega,x+\mathrm{i}y}(\mathbf{r})\right)^{*} = \mathbf{E}_{j}^{2\omega,x-\mathrm{i}y}(\mathbf{r}) \left(\mathbf{E}_{i}^{2\omega,x-\mathrm{i}y}(\mathbf{r})\right)^{*}$ are equal to each other due to the achiral symmetry of the nanoparticle.

We should pay attention to the following:

- 1. The eigenmode is excited by only one term of the polarization, since Δm_{χ} is never equal to $\mathfrak{n}\nu$, where $\nu \in \mathbb{Z}$.
- 2. The multiplier $e^{i\Delta m_{\chi}\beta}$ finally disappears.
- 3. A lot of coefficients are equal to each other.

4.2.6 Second-harmonic circular dichroism

Therefore, using this equality and comparing expressions above (93), and (98), as well as (94), and (97), we can conclude that interference terms $I^{2\omega,\text{interf.}}$, and, as a consequence, the total integral second harmonic intensity $I^{2\omega}$ look absolutely the same for a left- and right-handed beams.

Comment: the same independence of intensity on the incident vortex polarization can be obtained for interference terms $I^{2\omega,\text{interf.}}$ for interference of two excited eigenmodes transformed under irreducible representation B₁, as well as under irreducible representation B₂ with help of expressions (89), and (90). Consequently, the total integral second harmonic intensity $I^{2\omega}$ doesn't depend on the sign of the polarisation of the incident vortex. Let us remind that despite the fact that all expressions for intensity were obtained for the specific case, when $m^{\text{in}} = 4s - 3$, $s \in \mathbb{Z}_+$, it's not necessary to calculate all other cases because the expressions and the final result will be always the same due to the same expressions for coupling integrals. Overall, the final conclusion can be introduced: circular dichroism in the second-harmonic signal doesn't appear in a nanostructure GaAs[111]||z with symmetry C_{4v} under any circumstances.

5 Derivation of the main condition for a general case

We've presented two examples, the choice of which is linked, firstly, to the popularity of the materials considered, and secondly, to the nontrivial nature of the examples themselves. In this section, we will identify the common patterns observed, ultimately leading to a simple general formula.

- 1. An incident vortex beam excites intrinsic modes, consisting of the same multipoles as the beam itself (with the same m^{in}), as well as those that are transformed under the same irreducible representation. By symmetry considerations (for instance, a function describing the structure's shape expands into series by $\cos(\mathfrak{n}\varphi)$), these will be multipoles with $\pm m^{\text{in}} + \mathfrak{n}\nu$, $\nu \in \mathbb{Z}$. It is important to note that at this stage, a mirror beam excites mirror modes, regardless of whether they were originally degenerate (transformed according to representation E) or not (transformed according to other representations).
- 2. Subsequently, it is necessary to derive an expression for the nonlinear polarization, into which the field inside the particles enters q times. The factor responsible for rotational symmetry, $\sum_{\nu} [...] e^{i(\pm m^{in} + \mathfrak{n}\nu)\varphi}$, $\nu \in \mathbb{Z}$, multiplied by itself q times, yields $\sum_{\nu} [...] e^{i(\pm qm^{in} + \mathfrak{n}\nu)\varphi}$, $\nu \in \mathbb{Z}$.
- 3. At the previous stage, the symmetry of the particle was already considered. We regard the particle as fixed relative to the coordinate system, and the relative rotation of the lattice is represented by the rotation of the tensor describing this lattice. Thus, one of the most important points is that tensor contains terms of the form $\sum_{m_{\chi}} [...] e^{im_{\chi}(\varphi-\beta)}$. This does not depend on the handedness, since it characterizes the lattice. Note that phase differences between such terms are proportional to $\Delta m_{\chi}\beta$.
- 4. Another crucial observation is that nonlinear susceptibility is real (contains rather $\cos(m_{\chi}\varphi)$ or $\sin(m_{\chi}\varphi)$) terms than exponential). Thus polarizability can always be written in a "mirror" form for other handedness (and also terms with $m_{\chi} = 0$). Generally, for some pair with m_{χ} and $-m_{\chi}$:

$$\mathbf{P}^{q\omega}(r,z,\varphi) \propto \left\{ \sum_{\nu} \mathbf{P}^{q\omega}_{(m_{\chi}+qm^{\mathrm{in}}+\mathfrak{n}\nu)} \mathrm{e}^{\pm(m_{\chi}+qm^{\mathrm{in}}+\mathfrak{n}\nu)\mathrm{i}\varphi} \right\} \mathrm{e}^{\mp m_{\chi}\mathrm{i}\beta} + \left\{ \sum_{\nu} \mathbf{P}^{q\omega}_{(-m_{\chi}+qm^{\mathrm{in}}+\mathfrak{n}\nu)} \mathrm{e}^{\pm(-m_{\chi}+qm^{\mathrm{in}}+\mathfrak{n}\nu)\mathrm{i}\varphi} \right\} \mathrm{e}^{\pm m_{\chi}\mathrm{i}\beta}$$
(99)

At this stage it is not clear, how the dichroism could appear. Note that in general case, first and second terms exciting eigenmodes of a different symmetry (with different total m). For example, if $m_{\chi} = 2$, $\mathfrak{n} = 3$, for the first term we have $qm^{\text{in}} + 2 + 3\nu$ and $qm^{\text{in}} - 2 + 3\nu$, which never coincide for $\nu \in \mathbb{Z}$ or any qm^{in} .

5. Let us consider the case, when these terms can coincide, exciting the eigenmodes of the same symmetry, e.g. $m_{\chi} = 2$, $\mathfrak{n} = \Delta m_{\chi} = 4$. This is the stage, where

the dichroism appears. Imagine the first term of the polarization excites one mode, and the second one excites another mode of the same symmetry. One of these two modes can be in the vicinity of resonance, thus assume that the mode, excited by the second term has a relative phase α . Note that α is the same (with the same sign) for both beam handednesses, because these two cases mirror each other. On the other hand, multipliers with β have opposite signs for left and right beams. Thus, in one case, the relative phase will be $\alpha + \Delta m_{\chi}\beta$, and in the other $\alpha - \Delta m_{\chi}\beta$, which provides constructive and destructive interference. Each mode will be excited by both terms of the polarization, which makes the calculations cumbersome, but does not change the general idea.

6. The main formula immediately follows from the fact that to obtain the dichroism, different terms of nonlinear polarization should excite eigenmodes of the same symmetry, and also phases should be different, which does not fulfill for $\beta = \pi \nu/s$.

The two described cases provide the consideration of all these processes in detail, and it can be seen that regardless of the symmetry of the excited eigenmodes on each stage, this general consideration is still applicable. We also note that not the symmetry of the excited eigenmodes that matters, but the difference between the rotational symmetry of different modes excited. Due to the modified law of total angular momentum projection conservation, each mode consists of the multipoles, whose m differs by $\mathfrak{n}\nu$. Different terms of the tensor refer to the excitation of the modes, for which m differs by Δm_{χ} . If the multipolar content of the modes, "excited by different terms of the tensor" coincide, the modes can interact. Mirror reflection of the incident beam changes the sign of additional phase between these modes due to the lattice rotation. Hence, the considerations eventually do not depend on the order of the harmonic or absolute value of the incident angular momentum projection.

6 Numerical Calculations

In Section (5), we introduced a universal recipe for defining the possibility of circular dichroism (CD) appearance in perturbative harmonic generation, based on the illustrative examples previously discussed. Let us apply it to the second-harmonic generation and the nanostructure BaTiO₃[001] $\|x\|$ with symmetry D_{3h} irradiated by an incident vortex beam with the total angular momentum projection on the z-axis $m^{\text{in}} = 3$.

According to the step 1, vortex beam excited intrinsic modes, consisting of the multipoles with $m = \pm 3 + 3\nu$, $\nu \in \mathbb{Z}$. Let us refer to our previous work [32] and find the values m_{χ} for the crystalline lattice BaTiO₃[001]||x: $m_{\chi} \in \{\pm 1, \pm 3\}$. Using it and relying on the general form of the nonlinear vector polarization $\mathbf{P}^{q\omega}(r, z, \varphi)$ (99), we can determine which eigenmodes can be excited at the doubled frequency. In fact, eigenmodes with $\pm m_{\chi} \pm 2m^{\text{in}} + 3\nu = \pm m_{\chi} \pm 6 + 3\nu$, $\nu \in \mathbb{Z}$, with the additional phase $\mp m_{\chi}\beta$, where the sign \pm denotes the handedness of the incident beam, are expected to be excited. Particularly, there are eigenmodes with $\pm 7 + 3\nu$, $\pm 5 + 3\nu$, $\pm 9 + 3\nu$, and $\pm 3 + 3\nu$, and the main thing is which of them can interfere with each other. In this particular case only eigenmodes with $\pm 9 + 3\nu$ and $\pm 3 + 3\nu$ have the same symmetry and interfere. The phase's difference between them is equal to $\mp 6\beta$. Therefore, for the

possibility of SH-CD in considered system it's required to rotate the nanostructure at $\beta \neq \pi/6$ with respect to the crystalline lattice.

For the validation of our theoretical results, we present numerical calculations of the SH intensity in COMSOL Multiphysics[®] for the described system above with the following parameters: a trimer that has the D_{3h} symmetry consisting of three equidistant discs each of which has the diameter equal to 500 nm and height equal to 450 nm. The distance between the discs was equal to 55 nm and refractive index of the material was equal to 3.5 which is close to the typical values of refractive index for dielectric materials. Incident wave was not a particular vortex beam, but just a circularly polarized plane wave, multiplied by $e^{\pm 2i\varphi}/r$, where $r = \sqrt{x^2 + y^2}$. Generally, this choice is arbitrary, and one can take any incident field, which obey the symmetry requirements. Second harmonic computation was conducted, using standard approach, described, e.g. in [62, 66]. In Fig. 2, in the range of 1580–1630 nm, we illustrate the SH intensity in arbitrary units for right- and left-handed beams for angle $\beta = 15^{\circ}$. As expected, SH-CD can be obtained because SH intensity differs for different handednesses. In Fig. 2 (in the insert), absolute value of SH-CD is shown for different values of angle β that we numerically calculated using the eq. (13): SH-CD appears for all $\beta \neq \pi/6$ which is consistent with the speculations described above.

Relatively small values of dichroism are explained by arbitrarily chosen wavelengths, structure, and sizes. Higher values could be achieved if the proper engineering is conducted. Particularly, eigenmodes, which contribute to the dichroism, should be close to their resonances on the SH wavelength.

7 Discussions

7.1 Cascaded generation

Cascading is also possible to achieve high-harmonic generation [67–69] via lower-order nonlinearities. Let us consider the cascading process in stages. In the first step, the condition for the dichroism will be just the same as for the nonlinearity of the considered order, e.g., the second harmonic. If there is a dichroism, there is no need to go further. However, if in the first step, the dichroism does not appear, we should consider the next process with a different incident field. Here, the consideration is more tricky than the usual one.

The simplest example is the third harmonic cascaded process via $\hat{\chi}^{(2)}$. The second step is a sum-frequency process $2\omega + \omega$. One of the fields (2ω) will contain several terms of different symmetry, with m, differing by Δm_{χ} since they are being generated in the first step "by different components of the tensor". They also have corresponding phases, depending on β . Let us again consider (99) (and only one handedness). After the first step, the first term will generate the SH field with the momentum projections $m_{\chi} + 2m^{\text{in}} + \mathfrak{n}\nu$ and phase $-m_{\chi}\beta$, and the second with $-m_{\chi} + 2m^{\text{in}} + \mathfrak{n}\nu$ and phase $m_{\chi}\beta$.

Then these terms participate in the sum-frequency process as a part of the incident field. Let us consider the angular momentum projection, generated by the first term on the second step. It will contain two terms, with $m_{\chi} + m_{\chi} + 2m^{\text{in}} + m^{\text{in}} + \mathfrak{n}\nu$ and phase



Figure 2: Numerically calculated values of SH intensity in arbitrary units for the nanostructure BaTiO₃[001]||x with symmetry D_{3h} for right- and left-handed incident beams with m = 3. The angle β between the structure's symmetry plane and the crystalline lattice was chosen 15°. On the insert: Numerically calculated absolute values of SH-CD depending on angle β . SH-CD is possible for all $\beta \neq \pi/6$.

 $-2m_{\chi}i\beta$ and $-m_{\chi}+m_{\chi}+2m^{in}+m^{in}+\mathfrak{n}\nu$ and phase 0. The second term in the second step will produce $-m_{\chi}+m_{\chi}+2m^{\text{in}}+\mathfrak{n}\nu$ and phase 0 and $-m_{\chi}-m_{\chi}+2m^{\text{in}}+\mathfrak{n}\nu$ and phase $2m_{\chi}i\beta$. Even though two of these four terms will have the same m, and the same symmetry and could be the candidates to produce dichroism, their phase does not depend on β . This will happen to all such terms in other processes, because each m_{χ} carries its corresponding phase, and terms with the same m will thus possess the same phase, which cannot lead to dichroism. The first and fourth terms in general, can have the same symmetry in the second step $(2\Delta m_{\chi} = \mathfrak{n}\nu)$, even if $\Delta m_{\chi} \neq \mathfrak{n}\nu$ (since we restrict ourselves to the case when we do not have dichroism in the first step). However, this does not happen often. For example, if one can imagine the lattice which provides only $\Delta m_{\chi} = 2$, but $\mathfrak{n} = 4$, this will be the case. Another tricky case is when we have $\mathfrak{n} > 6$. For the second harmonic, dichroism is not possible due to (19). But here, for the first and fourth terms we have effectively $2m_{\chi}$ for each one, thus $\Delta m_{\chi}^{\text{eff}} \leq 12$. This difference, though insignificant, does not allow us to apply the same formula for cascade processes directly. However, the selection rules will be still similar, and the method in general is still applicable.

7.2 Angular incidence and substrate

All these considerations are applicable to a normal incidence of a beam, aligned with the z-axis, which is also the symmetry axis of a nanostructure. The inclination of the beam

would break the symmetry. In this case, we suggest considering a perfectly aligned beam, but a rotated nanostructure, which effectively will have a lower symmetry and the crystalline lattice should be rotated (the Matlab code for the tensor rotation could be found in [32]). We also note that the presence of substrate does not alter the results, because it does not change the symmetry which is of interest to us. The dichroism will appear both in transmission and reflection.

7.3 Other subtleties

Throughout the paper, we avoided considering the case $m^{\rm in} = 0$, while the Poincare sphere also exists for this case, and multipolar building blocks of the corresponding beams are $\mathbf{N}_{e01} \pm \mathbf{M}_{e01}$. Initially, it might appear that the nonlinear polarization (99) terms are totally symmetric, and polarization coincides for both handednesses so the circular dichroism can not be obtained. However, this is the case where particular form of $\mathbf{P}_{(\pm m_{\chi} + \mathfrak{n}\nu)}^{q\omega}(r, z)$ plays a role. Such terms are not symmetric in general, reflecting the interplay of the lattice with the field, carrying particular helicity [70, 71], thus our considerations are still valid and main formula applicable. Additionally, we wish to clarify that our analysis and results are not analogous to considering nanoparticles as "big molecules" with their hyperpolarizability [72]. We assume that the nanostructure is large enough so its material is described by nonlinear susceptibility tensor, and surface effects are weak [73]. Thus, even if a "big molecule" can possess no symmetry at all we can still have zero circular dichroism in this approximation.

7.4 Other definitions of dichroism

Circular dichroism under vortex beam illumination can be introduced in several different ways [57]. Besides mirror-reflected vortex beams with opposite signs of m one can consider changing ℓ while keeping λ the same (see Appendix A.4) or changing λ while keeping ℓ the same. However, for both cases, in nanostuctures of considered symmetries a different response will be always observed even in the linear regime. This happens due to the fact that incident beams have different |m| values, but eigenmodes with different |m| belong to different irreps and have different resonance frequencies [63, 64]. Another possible case is considering incident beams not with single m, but some linear combination, e.g. m_1 and m_2 . They can be written in the form $|R_{m_1}\rangle + e^{i\gamma} |R_{m_2}\rangle$ or $|L_{m_1}\rangle + e^{-i\gamma} |L_{m_2}\rangle$. This case is tricky, because we will have many different terms in (99). One can not immediately tell, if the nonlinear dichroism is observable, because in the case, e.g. $m_1 - m_2 = \Delta m_{\chi}$ some terms of the polarization can interfere, even though we didn't have the dichroism for a single m. Such cases should be considered separately even in the linear regime, where the dichroism could also appear if $m_1 - m_2 = \mathfrak{n}\nu$ (this is similar to the results obtained in [74]), depending on the phase γ . Indeed, in this case two terms of the incident field will both excite eigenmodes with the same symmetry, and with a relative phase α , which is the same for $|R\rangle$ and $|L\rangle$ (while the γ has a different sign). Thus, the overall intensity will differ for similar reasons as in the previously discussed nonlinear case, where γ plays similar role as β .

8 Dichroism under vector beams illumination

Another interesting case occurs with vector beam illumination (see (6)) and (7)). This situation is analogous to linear dichroism in the linear regime. Excitation by radial and azimuthal beams is widely studied and has many applications [24, 75–77]. Here, we discuss the general case of such beams. In linear regime, we can have different response to x- and y-polarized plane waves in rectangular particle (C_{2v} or D_{2h}), while we do not have a circular dichroism in this case (when we consider the total intensity of the scattered wave). Due to the similar reasons, one can obtain different response to $|B_{me}\rangle$ and $|B_{mo}\rangle$ in the linear regime:

$$e/o-D_m^{sca} = \frac{(I_{B_{me}}^{sca} - I_{B_{mo}}^{sca})}{(I_{B_{me}}^{sca} + I_{B_{mo}}^{sca})},$$
(100)

where $I_{\mathcal{B}_{me/o}}^{\text{sca}}$ is total scattering intensity, integrated by a sphere in the far-field, as previously, under illumination by the corresponding vector beam. The main condition to obtain this type of dichroism:

$$\exists \nu \in \mathbb{Z}, \ 2m = \mathfrak{n}\nu. \tag{101}$$

One can prove it in two different ways. From the representation theory [64], one can see that if the modes excited by $|B_{me}\rangle$ and $|B_{mo}\rangle$ have different symmetries (are transformed according to different irreps), their resonance frequencies will be different (avoiding specific cases of accidental degeneration). Thus they will be excited with different phases and amplitudes, leading to different responses. When $2m \neq \mathfrak{n}\nu$, both modes are degenerate, and transformed according to the two-dimensional irrep E. Each beam will excite one of two orthogonal degenerate eigenmodes. The second way is to just look at the scattered field symmetry, using the general approach and the total angular momentum projection conservation, modified by a nanostructure. Scattered fields by the $(|L_m\rangle \pm |R_m\rangle)$ will have different intensity in case when the fields produced by the first and the second term interfere. This happens, when they have the same symmetry, i.e. $\exists \nu, \nu': m^{\text{in}} + \mathfrak{n}\nu = -m^{\text{in}} + \mathfrak{n}\nu'$. The condition (101) immediately follows. The relative rotation of the incident beams and nanoparticle will alter the results. At certain angles, the two incident beams are mirror-symmetric with respect to the symmetry plane of a nanostructure, and dichroism will not be observed. We leave a detailed discussion of relative angles beyond the scope of this work.

Let us now assume that $2m \neq \mathfrak{n}\nu$ is satisfied, and look at the nonlinear dichroism, which is defined analogously:

$$e/o-D_m^{q\omega} = \frac{(I_{B_{me}}^{q\omega} - I_{B_{mo}}^{q\omega})}{(I_{B_{me}}^{q\omega} + I_{B_{mo}}^{q\omega})}.$$
(102)

Let us present the incident wave, which contributes q times, as a tensor product:

$$\underbrace{(|L_m\rangle \pm |R_m\rangle) \otimes (|L_m\rangle \pm |R_m\rangle) \cdots \otimes (|L_m\rangle \pm |R_m\rangle)}_{q \text{ times}}.$$
(103)

Expanding the brackets, we obtain several terms, for which we can consider the process separately. Importantly, signs before some of them depend on the incident beam. If the "beam-dependent" terms have the same symmetry as independent ones, they will interfere with each other, leading to the different responses. Let us first consider second harmonic, for the convenience. The terms $|L_m\rangle \otimes |L_m\rangle$ or $|R_m\rangle \otimes |R_m\rangle$ will have the same symmetry as $|L_m\rangle \otimes |R_m\rangle$ or $|R_m\rangle \otimes |L_m\rangle$ if the following condition is satisfied: $\exists \nu, \nu': m_{\chi} + 2 \cdot m^{\text{in}} + \mathfrak{n}\nu = m'_{\chi} + m^{\text{in}} - m^{\text{in}} + \mathfrak{n}\nu'$, which converts into

$$\exists \nu \in \mathbb{Z}, \quad \Delta m_{\chi} + 2m^{\rm in} = \mathfrak{n}\nu. \tag{104}$$

If this condition is satisfied, we may obtain $e/o-D_m^{2\omega}$ for some relative angles. For example, for GaAs C_{3v} trimer with [111]||z we have $\Delta m_{\chi} \in \{\pm 3, \pm 6\}$, and we will not obtain the SH dichroism for $m^{in} = 2$, because $3(6) + 4 \neq 3\nu$. However, for the same trimer but crystalline lattice is oriented as [001]||z, we have $\Delta m_{\chi} = \pm 4$, and -4 + 4 = 0 is satisfied, leading to appearance of the SH dichroism for most relative angles. For high-harmonic generation, the condition is modified as follows:

$$\exists \nu, \nu' \colon \Delta m_{\chi} + 2\nu' m^{\text{in}} = \mathfrak{n}\nu, \quad \nu \in \mathbb{Z},$$

$$\nu' \in 2\mathbb{Z} + 1, \quad \nu' \in [-q...q].$$
(105)

To determine the specific relative angles between the beams, structure, and lattice at which dichroism may be prohibited, it is necessary to accurately account for the relative phases at each step. We leave this discussion beyond the scope of our paper, providing a foundation for further calculations.

Interestingly, this type of dichroism can be even obtained in cylindrically symmetric nanostructure if $\Delta m_{\chi} + 2m^{\text{in}} = 0$ (for the second harmonic). This is obvious, for example, for tensor which only has χ_{yyy} or χ_{xxx} component and linearly polarized plane waves. We've conducted the modelling for this case, and provide the results in Fig. 3. Diameter of the cylinder is 500 nm, height is 450 nm, m^{in} of the incident beams equals 3, and $\Delta m_{\chi} \in \{\pm 3, \pm 6\}$ for GaAs, [111]||z. y = 0 symmetry plane is common for the even beam and a lattice. If $\Delta m_{\chi} + 2m^{\text{in}} \neq 0 \quad \forall \Delta m_{\chi}$, for example, for $m^{\text{in}} = 2$, the dichroism is not observed in the cylindrically-symmetric nanostructure.

9 Conclusions

To conclude, we performed a thoughtful theoretical analysis of nonlinear circular dichroism and provided the complete answer for all possible perturbative harmonic orders, incident vortex beams, and a broad range of materials and achiral nanostructures, which would help to accelerate the further analysis of such structures. Using these findings as a basis, we've discussed the possibility of linear and nonlinear dichroism under vector beams excitation. These results can play a particularly important role for chiral sensing with nanostructures [30, 78–80], since determining the chiral response of the nanoparticle itself is crucial, as well as in nanoparticle fabrication [81], beams generation [82], optical trapping [83–87] and manipulation [88, 89], where the subtleties of the interaction between structured light and nano-objects are critical.



Figure 3: Numerically calculated values of SH intensity in arbitrary units for the GaAs[111]||z| for even and odd incident beams with m = 3.

10 Acknowledgements

We express our gratitude to our readers for their engagement and to ChatGPT for its assistance with linguistic queries. Special thanks are due to Yuri Kivshar, Ivan Fernandez-Corbaton, Ivan Toftul, and Kirill Koshelev for fruitful discussions. Numerical simulations of nonlinear dichroism were supported by the Russian Science Foundation (Project No. 22-12-00204). K.F. would like to acknowledge the financial support from the European Community through the "METAFAST" Project (H2020-FETOPEN-2018-2020, Grant No. 899673) and the Ministero Italiano dell'Istruzione (MIUR) through the "METEOR" Project (No. PRIN-2020, 2020EYLJT_002).

References

- Louis Pasteur. Recherches sur les relations qui peuvent exister entre la forme cristalline, la composition chimique et les sens de la polarisation rotatoire. Ann. Chim. Phys, xxiv(3):442-460, 1848. URL https://wellcomecollection.org/ works/rdepqfzw.
- [2] L. Rosenfeld. Quantenmechanische Theorie der natürlichen optischen Aktivität von Flüssigkeiten und Gasen. Z. Phys., 52(3):161–174, 1929. ISSN 0044-3328. doi: 10.1007/BF01342393. URL https://doi.org/10.1007/BF01342393.
- [3] R. S. Cahn, Christopher Ingold, and V. Prelog. Specification of Molecular Chirality. Angew. Chem., Int. Ed. Engl., 5(4):385-415, 1966. ISSN 0570-0833. doi: 10.1002/anie.196603851. URL https://doi.org/10.1002/anie.196603851.
- M. J. Padgett and J. Courtial. Poincaré-sphere equivalent for light beams containing orbital angular momentum. Opt. Lett., 24(7):430–432, 1999. ISSN 0146-9592. doi: 10.1364/ol.24.000430. URL https://doi.org/10.1364/ol.24.000430.

- [5] Yijie Shen. Rays, waves, SU(2) symmetry and geometry: toolkits for structured light. J. Opt., 23(12):124004, 2021. ISSN 2040-8986. doi: 10.1088/2040-8986/ ac3676. URL https://doi.org/10.1088/2040-8986/ac3676.
- Yi Zhang, Xuyue Guo, Lei Han, Peng Li, Sheng Liu, Huachao Cheng, and Jianlin Zhao. Gouy phase induced polarization transition of focused vector vortex beams. Opt. Express, 25(21):25725-25733, 2017. ISSN 1094-4087. doi: 10.1364/OE.25.
 025725. URL https://doi.org/10.1364/OE.25.025725.
- [7] Alison Rodger and Bengt Nordén. Circular dichroism and linear dichroism, volume 1. Oxford University Press, USA, 1997.
- [8] Gerald D Fasman. Circular dichroism and the conformational analysis of biomolecules. Springer Science & Business Media, 2013.
- [9] P. J. Stephens. Theory of Magnetic Circular Dichroism. J. Chem. Phys., 52 (7):3489–3516, 1970. ISSN 0021-9606. doi: 10.1063/1.1673514. URL https://doi.org/10.1063/1.1673514.
- [10] Lutz Hecht and Laurence D. Barron. Rayleigh and Raman optical activity from chiral surfaces. *Chem. Phys. Lett.*, 225(4):525-530, 1994. ISSN 0009-2614. doi: 10. 1016/0009-2614(94)87122-1. URL https://doi.org/10.1016/0009-2614(94) 87122-1.
- [11] P. J. Stephens and M. A. Lowe. Vibrational Circular Dichroism. Annu. Rev. Phys. Chem., 36(1):213-241, 1985. ISSN 0066-426X. doi: 10.1146/annurev.pc. 36.100185.001241. URL https://doi.org/10.1146/annurev.pc.36.100185. 001241.
- [12] N. L. Manakov, S. I. Marmo, and A. V. Meremianin. A new technique in the theory of angular distributions in atomic processes: the angular distribution of photoelectrons in single and double photoionization. J. Phys. B: At. Mol. Opt. Phys., 29(13):2711, 1996. ISSN 0953-4075. doi: 10.1088/0953-4075/29/13/010. URL https://doi.org/10.1088/0953-4075/29/13/010.
- [13] Kirill Koshelev, Ivan Toftul, Yongsop Hwang, and Yuri Kivshar. Scattering matrix for chiral harmonic generation and frequency mixing in nonlinear metasurfaces. J. Opt., 26(5):055003, 2024. ISSN 2040-8986. doi: 10.1088/2040-8986/ad3a78. URL https://doi.org/10.1088/2040-8986/ad3a78.
- [14] J. D. Byers, H. I. Yee, T. Petralli-Mallow, and J. M. Hicks. Second-harmonic generation circular-dichroism spectroscopy from chiral monolayers. *Phys. Rev. B*, 49(20):14643-14647, 1994. ISSN 2469-9969. doi: 10.1103/PhysRevB.49.14643.
 URL https://doi.org/10.1103/PhysRevB.49.14643.
- [15] Shijie Cai, Jiafei Chen, Xiaoshan Liu, Guolan Fu, Guiqiang Liu, Jing Chen, Chaojun Tang, Wei Du, and Zhengqi Liu. Perfect intrinsic and nonlinear chirality simultaneously driven by half-integer topological charge. *Phys. Rev. B*, 109(16): 165420, 2024. ISSN 2469-9969. doi: 10.1103/PhysRevB.109.165420. URL https://doi.org/10.1103/PhysRevB.109.165420.

- [16] Alexis Chacón, Dasol Kim, Wei Zhu, Shane P. Kelly, Alexandre Dauphin, Emilio Pisanty, Andrew S. Maxwell, Antonio Picón, Marcelo F. Ciappina, Dong Eon Kim, Christopher Ticknor, Avadh Saxena, and Maciej Lewenstein. Circular dichroism in higher-order harmonic generation: Heralding topological phases and transitions in Chern insulators. *Phys. Rev. B*, 102(13):134115, 2020. ISSN 2469-9969. doi: 10.1103/PhysRevB.102.134115. URL https://doi.org/10.1103/ PhysRevB.102.134115.
- [17] Mikko J. Huttunen, Miro Erkintalo, and Martti Kauranen. Absolute nonlinear optical probes of surface chirality. J. Opt. A: Pure Appl. Opt., 11(3):034006, 2009. ISSN 1464-4258. doi: 10.1088/1464-4258/11/3/034006. URL https://doi.org/ 10.1088/1464-4258/11/3/034006.
- [18] Florian Spreyer, Jungho Mun, Hyeohn Kim, Ryeong Myeong Kim, Ki Tae Nam, Junsuk Rho, and Thomas Zentgraf. Second Harmonic Optical Circular Dichroism of Plasmonic Chiral Helicoid-III Nanoparticles. ACS Photonics, 9(3):784– 792, 2022. doi: 10.1021/acsphotonics.1c00882. URL https://doi.org/10.1021/ acsphotonics.1c00882.
- [19] Kayn A. Forbes and Garth A. Jones. Optical vortex dichroism in chiral particles. *Phys. Rev. A*, 103(5):053515, 2021. ISSN 2469-9934. doi: 10.1103/PhysRevA. 103.053515. URL https://doi.org/10.1103/PhysRevA.103.053515.
- [20] Xavier Zambrana-Puyalto, Francesco De Angelis, and Vincenzo D'Ambrosio. Vortex circular dichroism: An experimental technique to assess the scalar/vectorial regime of diffraction. Open Research Europe, 2:142, 2022. URL https://doi. org/10.12688/openreseurope.14916.1.
- [21] Evelina Bibikova, Nazar Al-wassiti, and Nataliya Kundikova. Topological circular dichroism for asymmetric converging light beams. *Opt. Lasers Eng.*, 174:107936, 2024. ISSN 0143-8166. doi: 10.1016/j.optlaseng.2023.107936. URL https://doi.org/10.1016/j.optlaseng.2023.107936.
- [22] Xavier Zambrana-Puyalto, Xavier Vidal, and Gabriel Molina-Terriza. Angular momentum-induced circular dichroism in non-chiral nanostructures. *Nat. Commun.*, 5(4922):1–7, 2014. ISSN 2041-1723. doi: 10.1038/ncomms5922. URL https://doi.org/10.1038/ncomms5922.
- [23] D. L. Andrews, L. C. Dávila Romero, and M. Babiker. On optical vortex interactions with chiral matter. *Opt. Commun.*, 237(1):133-139, 2004. ISSN 0030-4018. doi: 10.1016/j.optcom.2004.03.093. URL https://doi.org/10.1016/j.optcom. 2004.03.093.
- [24] Godofredo Bautista, Mikko J. Huttunen, Jouni Mäkitalo, Juha M. Kontio, Janne Simonen, and Martti Kauranen. Second-Harmonic Generation Imaging of Metal Nano-Objects with Cylindrical Vector Beams. Nano Lett., 12(6):3207-3212, 2012. ISSN 1530-6984. doi: 10.1021/nl301190x. URL https://doi.org/10.1021/ nl301190x.

- [25] Kirill Koshelev, Ivan Toftul, Yongsop Hwang, and Yuri Kivshar. Scattering matrix for chiral harmonic generation and frequency mixing in nonlinear metasurfaces. arXiv, 2023. doi: 10.48550/arXiv.2311.03686. URL https://doi.org/10. 48550/arXiv.2311.03686.
- [26] Alexander O. Govorov, Zhiyuan Fan, Pedro Hernandez, Joseph M. Slocik, and Rajesh R. Naik. Theory of Circular Dichroism of Nanomaterials Comprising Chiral Molecules and Nanocrystals: Plasmon Enhancement, Dipole Interactions, and Dielectric Effects. *Nano Lett.*, 10(4):1374–1382, 2010. ISSN 1530-6984. doi: 10.1021/nl100010v. URL https://doi.org/10.1021/nl100010v.
- [27] Alexander Y. Zhu, Wei Ting Chen, Aun Zaidi, Yao-Wei Huang, Mohammadreza Khorasaninejad, Vyshakh Sanjeev, Cheng-Wei Qiu, and Federico Capasso. Giant intrinsic chiro-optical activity in planar dielectric nanostructures. *Light Sci. Appl.*, 7(2):17158, 2018. ISSN 2047-7538. doi: 10.1038/lsa.2017.158. URL https://doi.org/10.1038/lsa.2017.158.
- [28] Xiaoli Wang and Zhiyong Tang. Circular Dichroism Studies on Plasmonic Nanostructures. *Small*, 13(1):1601115, 2017. ISSN 1613-6810. doi: 10.1002/smll. 201601115. URL https://doi.org/10.1002/smll.201601115.
- [29] Lukas Rebholz, Marjan Krstić, Benedikt Zerulla, Mateusz Pawlak, Wiktor Lewandowski, Ivan Fernandez-Corbaton, and Carsten Rockstuhl. Separating the Material and Geometry Contribution to the Circular Dichroism of Chiral Objects Made from Chiral Media. arXiv, 2024. doi: 10.48550/arXiv.2401.06664. URL https://doi.org/10.48550/arXiv.2401.06664.
- [30] Krzysztof M. Czajkowski and Tomasz J. Antosiewicz. Local versus bulk circular dichroism enhancement by achiral all-dielectric nanoresonators. *Nanophotonics*, 11(18):4287–4297, 2022. ISSN 2192-8614. doi: 10.1515/nanoph-2022-0293. URL https://doi.org/10.1515/nanoph-2022-0293.
- [31] Kristina Frizyuk, Elizaveta Melik-Gaykazyan, Jae-Hyuck Choi, Mihail I. Petrov, Hong-Gyu Park, and Yuri Kivshar. Nonlinear Circular Dichroism in Mie-Resonant Nanoparticle Dimers. *Nano Lett.*, 21(10):4381–4387, May 2021. ISSN 1530-6984. doi: 10.1021/acs.nanolett.1c01025.
- [32] Anastasia Nikitina, Anna Nikolaeva, and Kristina Frizyuk. Nonlinear circular dichroism in achiral dielectric nanoparticles. *Phys. Rev. B*, 107(4):L041405, 2023. ISSN 2469-9969. doi: 10.1103/PhysRevB.107.L041405. URL https://doi.org/10.1103/PhysRevB.107.L041405.
- [33] Carmelo Rosales-Guzmán, Bienvenu Ndagano, and Andrew Forbes. A review of complex vector light fields and their applications. J. Opt., 20(12):123001, 2018. ISSN 2040-8986. doi: 10.1088/2040-8986/aaeb7d. URL https://doi.org/10.1088/2040-8986/aaeb7d.
- [34] Vittorio Aita, Mykyta Shevchenko, Francisco J. Rodríguez-Fortuño, and Anatoly V. Zayats. Propagation of focused scalar and vector vortex beams in

anisotropic media: A semi-analytical approach. *arXiv*, 2024. doi: 10.48550/ arXiv.2402.04349. URL https://doi.org/10.48550/arXiv.2402.04349.

- [35] W. C. Soares, D. P. Caetano, and J. M. Hickmann. Hermite-Bessel beams and the geometrical representation of nondiffracting beams with orbital angular momentum. *Opt. Express*, 14(11):4577–4582, 2006. ISSN 1094-4087. doi: 10.1364/OE.14.004577. URL https://doi.org/10.1364/OE.14.004577.
- [36] Qiwen Zhan. Properties of circularly polarized vortex beams. Opt. Lett., 31 (7):867-869, 2006. ISSN 1539-4794. doi: 10.1364/OL.31.000867. URL https://doi.org/10.1364/OL.31.000867.
- [37] Ivan Fernandez-Corbaton, Xavier Zambrana-Puyalto, and Gabriel Molina-Terriza. Helicity and angular momentum: A symmetry-based framework for the study of light-matter interactions. *Phys. Rev. A*, 86(4):042103, 2012. ISSN 2469-9934. doi: 10.1103/PhysRevA.86.042103. URL https://doi.org/10.1103/ PhysRevA.86.042103.
- [38] A. I. Akhiezer and V. B. Berestetsky. *Quantum Electrodynamics*. Interscience Publishers, Hoboken, NJ, USA, 1965. ISBN 978-0-47001848-4.
- [39] Julius Adams Stratton. Electromagnetic Theory. 2015. ISBN 978-0-47013153-4.
 doi: 10.1002/9781119134640. URL https://doi.org/10.1002/9781119134640.
- [40] Craig F. Bohren and Donald R. Huffman. Absorption and Scattering by a Sphere. John Wiley & Sons, Ltd, 1998. ISBN 978-3-52761815-6. doi: 10.1002/ 9783527618156.ch4. URL https://doi.org/10.1002/9783527618156.ch4.
- [41] Fabrizio Frezza, Fabio Mangini, and Nicola Tedeschi. Introduction to electromagnetic scattering: tutorial. J. Opt. Soc. Am. A, JOSAA, 35(1):163–173, 2018. ISSN 1520-8532. doi: 10.1364/JOSAA.35.000163. URL https://doi.org/10. 1364/JOSAA.35.000163.
- [42] Gabriel Molina-Terriza. Determination of the total angular momentum of a paraxial beam. *Phys. Rev. A*, 78(5):053819, 2008. ISSN 2469-9934. doi: 10.1103/ PhysRevA.78.053819. URL https://doi.org/10.1103/PhysRevA.78.053819.
- [43] Maxim Vavilin and Ivan Fernandez-Corbaton. The polychromatic T-matrix. J. Quant. Spectrosc. Radiat. Transfer, 314:108853, 2024. ISSN 0022-4073. doi: 10.1016/j.jqsrt.2023.108853. URL https://doi.org/10.1016/j.jqsrt.2023. 108853.
- [44] X. Zambrana-Puyalto, I. Fernandez-Corbaton, M. L. Juan, X. Vidal, and G. Molina-Terriza. Duality symmetry and Kerker conditions. *Opt. Lett.*, 38 (11):1857–1859, 2013. ISSN 1539-4794. doi: 10.1364/OL.38.001857. URL https://doi.org/10.1364/OL.38.001857.

- [45] Jon Lasa-Alonso, Chiara Devescovi, Carlos Maciel-Escudero, Aitzol García-Etxarri, and Gabriel Molina-Terriza. On the origin of the Kerker phenomena. arXiv, 2023. doi: 10.48550/arXiv.2306.12762. URL https://doi.org/ 10.48550/arXiv.2306.12762.
- [46] Florian Graf, Joshua Feis, Xavier Garcia-Santiago, Martin Wegener, Carsten Rockstuhl, and Ivan Fernandez-Corbaton. Achiral, Helicity Preserving, and Resonant Structures for Enhanced Sensing of Chiral Molecules. ACS Photonics, 6(2):482–491, 2019. doi: 10.1021/acsphotonics.8b01454. URL https: //doi.org/10.1021/acsphotonics.8b01454.
- [47] Ivan Fernandez-Corbaton. Forward and backward helicity scattering coefficients for systems with discrete rotational symmetry. *Opt. Express*, 21(24):29885–29893, 2013. ISSN 1094-4087. doi: 10.1364/OE.21.029885. URL https://doi.org/10. 1364/OE.21.029885.
- [48] Robert Boyd. Nonlinear Optics. Academic Press, Cambridge, MA, USA, Dec 2002. ISBN 978-0-12121682-5. URL https://www.elsevier.com/books/ nonlinear-optics/boyd/978-0-12-121682-5.
- [49] Maxim R. Shcherbakov, Haizhong Zhang, Michael Tripepi, Giovanni Sartorello, Noah Talisa, Abdallah AlShafey, Zhiyuan Fan, Justin Twardowski, Leonid A. Krivitsky, Arseniy I. Kuznetsov, Enam Chowdhury, and Gennady Shvets. Generation of even and odd high harmonics in resonant metasurfaces using single and multiple ultra-intense laser pulses. *Nat. Commun.*, 12(4185):1–6, 2021. ISSN 2041-1723. doi: 10.1038/s41467-021-24450-9. URL https://doi.org/10.1038/ s41467-021-24450-9.
- [50] L. Novotny and B. Hecht. *Principles of Nano-Optics*. Cambridge University Press, USA, 2006.
- [51] M. B. Doost, W. Langbein, and E. A. Muljarov. Resonant-state expansion applied to three-dimensional open optical systems. *Phys. Rev. A*, 90(1):013834, 2014.
 ISSN 2469-9934. doi: 10.1103/PhysRevA.90.013834. URL https://doi.org/ 10.1103/PhysRevA.90.013834.
- [52] Philippe Lalanne, Wei Yan, Kevin Vynck, Christophe Sauvan, and Jean-Paul Hugonin. Light Interaction with Photonic and Plasmonic Resonances. *Laser Photonics Rev.*, 12(5):1700113, May 2018. ISSN 1863-8880. doi: 10.1002/lpor. 201700113.
- [53] Carlo Gigli, Tong Wu, Giuseppe Marino, Adrien Borne, Giuseppe Leo, and Philippe Lalanne. Quasinormal-Mode Non-Hermitian Modeling and Design in Nonlinear Nano-Optics. ACS Photonics, 7(5):1197–1205, May 2020. doi: 10.1021/acsphotonics.0c00014.
- [54] Tong Wu, Jose Luis Jaramillo, and Philippe Lalanne. Understanding the physics related to the spatial exponential growth of electromagnetic quasinormal modes.

arXiv, 2024. doi: 10.48550/arXiv.2401.15112. URL https://doi.org/10.48550/arXiv.2401.15112.

- [55] Andrey A. Bogdanov, Kirill L. Koshelev, Polina V. Kapitanova, Mikhail V. Rybin, Sergey A. Gladyshev, Zarina F. Sadrieva, Kirill B. Samusev, Yuri S. Kivshar, and Mikhail F. Limonov. Bound states in the continuum and Fano resonances in the strong mode coupling regime. In *Advanced Photonics, Vol. 1, Issue 1*, volume 1, page 016001. SPIE, 2019. doi: 10.1117/1.AP.1.1.016001. URL https: //doi.org/10.1117/1.AP.1.1.016001.
- [56] Maria Poleva, Kristina Frizyuk, Kseniia Baryshnikova, Andrey Evlyukhin, Mihail Petrov, and Andrey Bogdanov. Multipolar theory of bianisotropic response of meta-atoms. *Phys. Rev. B*, 107(4):L041304, 2023. ISSN 2469-9969. doi: 10. 1103/PhysRevB.107.L041304. URL https://doi.org/10.1103/PhysRevB.107. L041304.
- [57] Lyuzhou Ye, Jérémy Rouxel, Shahaf Asban, Benedikt Rösner, and Shaul Mukamel. Probing Molecular Chirality by Orbital-Angular-Momentum-Carrying X-ray Pulses. J. Chem. Theory Comput., 15(7):4180-4186, 2019. ISSN 1549-9618. doi: 10.1021/acs.jctc.9b00346. URL https://doi.org/10.1021/acs.jctc.9b00346.
- [58] Kayn A. Forbes and David L. Andrews. Orbital angular momentum of twisted light: chirality and optical activity. J. Phys.: Photonics, 3(2):022007, 2021. ISSN 2515-7647. doi: 10.1088/2515-7647/abdb06. URL https://doi.org/10.1088/ 2515-7647/abdb06.
- [59] Kirill Koshelev, Yutao Tang, Zixian Hu, Ivan I. Kravchenko, Guixin Li, and Yuri Kivshar. Resonant Chiral Effects in Nonlinear Dielectric Metasurfaces. ACS Photonics, 10(1):298–306, 2023. doi: 10.1021/acsphotonics.2c01926. URL https: //doi.org/10.1021/acsphotonics.2c01926.
- [60] Shumei Chen, Franziska Zeuner, Martin Weismann, Bernhard Reineke, Guixin Li, Ventsislav Kolev Valev, Kok Wai Cheah, Nicolae Coriolan Panoiu, Thomas Zentgraf, and Shuang Zhang. Giant Nonlinear Optical Activity of Achiral Origin in Planar Metasurfaces with Quadratic and Cubic Nonlinearities. Adv. Mater., 28(15):2992–2999, 2016. ISSN 0935-9648. doi: 10.1002/adma.201505640. URL https://doi.org/10.1002/adma.201505640.
- [61] Ivan Toftul, Gleb Fedorovich, Denis Kislov, Kristina Frizyuk, Kirill Koshelev, Yuri Kivshar, and Mihail Petrov. Nonlinearity-Induced Optical Torque. *Phys. Rev. Lett.*, 130(24):243802, 2023. ISSN 1079-7114. doi: 10.1103/PhysRevLett. 130.243802. URL https://doi.org/10.1103/PhysRevLett.130.243802.
- [62] Sergei Gladyshev, Olesia Pashina, Alexey Proskurin, Anna Nikolaeva, Zarina Sadrieva, Mihail Petrov, Andrey Bogdanov, and Kristina Frizyuk. Fast Simulation of Light Scattering and Harmonic Generation in Axially Symmetric Structures in COMSOL. ACS Photonics, 2024, 2024. doi: 10.1021/acsphotonics.3c01166. URL https://doi.org/10.1021/acsphotonics.3c01166.

- [63] Zhongfei Xiong, Qingdong Yang, Weijin Chen, Zhuoran Wang, Jing Xu, Wei Liu, and Yuntian Chen. On the constraints of electromagnetic multipoles for symmetric scatterers: eigenmode analysis. *Opt. Express*, 28(3):3073–3085, 2020. ISSN 1094-4087. doi: 10.1364/OE.382239. URL https://doi.org/10.1364/OE. 382239.
- [64] Sergey Gladyshev, Kristina Frizyuk, and Andrey Bogdanov. Symmetry analysis and multipole classification of eigenmodes in electromagnetic resonators for engineering their optical properties. *Phys. Rev. B*, 102(7):075103, 2020. ISSN 2469-9969. doi: 10.1103/PhysRevB.102.075103. URL https://doi.org/10.1103/ PhysRevB.102.075103.
- [65] L.D. Landau and E.M. Lifshitz. Quantum Mechanics: Non-Relativistic Theory. Course of Theoretical Physics. Elsevier Science, 1981. ISBN 9780080503486. URL https://books.google.ru/books?id=SvdoN3k8EysC.
- [66] Grégoire Saerens, Iek Tang, Mihail I. Petrov, Kristina Frizyuk, Claude Renaut, Flavia Timpu, Marc Reig Escalé, Igor Shtrom, Alexey Bouravleuv, George Cirlin, Rachel Grange, and Maria Timofeeva. Engineering of the Second-Harmonic Emission Directionality with III–V Semiconductor Rod Nanoantennas. *Laser Photonics Rev.*, 14(9):2000028, 2020. ISSN 1863-8880. doi: 10.1002/lpor.202000028. URL https://doi.org/10.1002/lpor.202000028.
- [67] Gerald R. Meredith. Cascading in optical third-harmonic generation by crystalline quartz. *Phys. Rev. B*, 24(10):5522–5532, 1981. ISSN 2469-9969. doi: 10.1103/PhysRevB.24.5522. URL https://doi.org/10.1103/PhysRevB.24.5522.
- [68] Anastasiia Zalogina, Luca Carletti, Anton Rudenko, Jerome V. Moloney, Aditya Tripathi, Hoo-Cheol Lee, Ilya Shadrivov, Hong-Gyu Park, Yuri Kivshar, and Sergey S. Kruk. High-harmonic generation from a subwavelength dielectric resonator. Sci. Adv., 9(17), 2023. ISSN 2375-2548. doi: 10.1126/sciadv.adg2655. URL https://doi.org/10.1126/sciadv.adg2655.
- [69] Michele Celebrano, Andrea Locatelli, Lavinia Ghirardini, Giovanni Pellegrini, Paolo Biagioni, Attilio Zilli, Xiaofei Wu, Swen Grossmann, Luca Carletti, Costantino De Angelis, Lamberto Duò, Bert Hecht, and Marco Finazzi. Evidence of Cascaded Third-Harmonic Generation in Noncentrosymmetric Gold Nanoantennas. Nano Lett., 19(10):7013–7020, 2019. ISSN 1530-6984. doi: 10.1021/acs. nanolett.9b02427. URL https://doi.org/10.1021/acs.nanolett.9b02427.
- [70] Sebastian Klimmer, Omid Ghaebi, Ziyang Gan, Antony George, Andrey Turchanin, Giulio Cerullo, and Giancarlo Soavi. All-optical polarization and amplitude modulation of second-harmonic generation in atomically thin semiconductors. *Nat. Photonics*, 15(11):837–842, 2021. ISSN 1749-4893. doi: 10.1038/ s41566-021-00859-y. URL https://doi.org/10.1038/s41566-021-00859-y.
- [71] Domenico de Ceglia, Laure Coudrat, Iännis Roland, Maria Antonietta Vincenti, Michael Scalora, Rana Tanos, Julien Claudon, Jean-Michel Gérard, Aloyse De-

giron, Giuseppe Leo, and Costantino De Angelis. Nonlinear spin-orbit coupling in optical thin films. *Nat. Commun.*, 15(1625):1–8, 2024. ISSN 2041-1723. doi: 10.1038/s41467-024-45607-2. URL https://doi.org/10.1038/ s41467-024-45607-2.

- [72] Anthony Stone and Anthony Stone. The Theory of Intermolecular Forces. Oxford University Press, Oxford, England, UK, 2013. ISBN 978-0-19967239-4.
- [73] Daniel Timbrell, Jian Wei You, Yuri S. Kivshar, and Nicolae C. Panoiu. A comparative analysis of surface and bulk contributions to second-harmonic generation in centrosymmetric nanoparticles. *Sci. Rep.*, 8(3586):1–9, 2018. ISSN 2045-2322. doi: 10.1038/s41598-018-21850-8. URL https://doi.org/10.1038/ s41598-018-21850-8.
- [74] A. Surzhykov, D. Seipt, V. G. Serbo, and S. Fritzsche. Interaction of twisted light with many-electron atoms and ions. *Phys. Rev. A*, 91(1):013403, 2015.
 ISSN 2469-9934. doi: 10.1103/PhysRevA.91.013403. URL https://doi.org/ 10.1103/PhysRevA.91.013403.
- [75] Tanya Das, Prasad P. Iyer, Ryan A. DeCrescent, and Jon A. Schuller. Beam engineering for selective and enhanced coupling to multipolar resonances. *Phys. Rev. B*, 92(24):241110, 2015. ISSN 2469-9969. doi: 10.1103/PhysRevB.92.241110. URL https://doi.org/10.1103/PhysRevB.92.241110.
- [76] Elizaveta V. Melik-Gaykazyan, Sergey S. Kruk, Rocio Camacho-Morales, Lei Xu, Mohsen Rahmani, Khosro Zangeneh Kamali, Aristeidis Lamprianidis, Andrey E. Miroshnichenko, Andrey A. Fedyanin, Dragomir N. Neshev, and Yuri S. Kivshar. Selective Third-Harmonic Generation by Structured Light in Mie-Resonant Nanoparticles. ACS Photonics, 5(3):728–733, 2018. doi: 10.1021/acsphotonics. 7b01277. URL https://doi.org/10.1021/acsphotonics.7b01277.
- [77] Maria K. Kroychuk, Alexander S. Shorokhov, Damir F. Yagudin, Daniil A. Shilkin, Daria A. Smirnova, Irina Volkovskaya, Maxim R. Shcherbakov, Gennady Shvets, and Andrey A. Fedyanin. Enhanced Nonlinear Light Generation in Oligomers of Silicon Nanoparticles under Vector Beam Illumination. *Nano Lett.*, 20(5):3471–3477, 2020. ISSN 1530-6984. doi: 10.1021/acs.nanolett.0c00393. URL https://doi.org/10.1021/acs.nanolett.0c00393.
- [78] E. Mohammadi, K. L. Tsakmakidis, A. N. Askarpour, P. Dehkhoda, A. Tavakoli, and H. Altug. Nanophotonic Platforms for Enhanced Chiral Sensing. ACS Photonics, 5(7):2669-2675, 2018. doi: 10.1021/acsphotonics.8b00270. URL https://doi.org/10.1021/acsphotonics.8b00270.
- [79] Lucas V. Besteiro, Hui Zhang, Jérôme Plain, Gil Markovich, Zhiming Wang, and Alexander O. Govorov. Aluminum Nanoparticles with Hot Spots for Plasmon-Induced Circular Dichroism of Chiral Molecules in the UV Spectral Interval. Adv. Opt. Mater., 5(16):1700069, 2017. ISSN 2195-1071. doi: 10.1002/adom. 201700069. URL https://doi.org/10.1002/adom.201700069.

- [80] Jose García-Guirado, Mikael Svedendahl, Joaquim Puigdollers, and Romain Quidant. Enhanced Chiral Sensing with Dielectric Nanoresonators. Nano Lett., 20(1):585-591, 2020. ISSN 1530-6984. doi: 10.1021/acs.nanolett.9b04334. URL https://doi.org/10.1021/acs.nanolett.9b04334.
- [81] Kohei Toyoda, Fuyuto Takahashi, Shun Takizawa, Yu Tokizane, Katsuhiko Miyamoto, Ryuji Morita, and Takashige Omatsu. Transfer of Light Helicity to Nanostructures. *Phys. Rev. Lett.*, 110(14):143603, 2013. ISSN 1079-7114. doi: 10.1103/PhysRevLett.110.143603. URL https://doi.org/10.1103/ PhysRevLett.110.143603.
- [82] Rocio Camacho-Morales, Mohsen Rahmani, Sergey Kruk, Lei Wang, Lei Xu, Daria A. Smirnova, Alexander S. Solntsev, Andrey Miroshnichenko, Hark Hoe Tan, Fouad Karouta, Shagufta Naureen, Kaushal Vora, Luca Carletti, Costantino De Angelis, Chennupati Jagadish, Yuri S. Kivshar, and Dragomir N. Neshev. Nonlinear Generation of Vector Beams From AlGaAs Nanoantennas. Nano Lett., 16(11):7191–7197, 2016. ISSN 1530-6984. doi: 10.1021/acs.nanolett.6b03525. URL https://doi.org/10.1021/acs.nanolett.6b03525.
- [83] Jack Ng, Zhifang Lin, and C. T. Chan. Theory of Optical Trapping by an Optical Vortex Beam. *Phys. Rev. Lett.*, 104(10):103601, 2010. ISSN 1079-7114. doi: 10. 1103/PhysRevLett.104.103601. URL https://doi.org/10.1103/PhysRevLett. 104.103601.
- [84] Yuichi Kozawa and Shunichi Sato. Optical trapping of micrometer-sized dielectric particles by cylindrical vector beams. *Opt. Express*, 18(10):10828–10833, 2010. ISSN 1094-4087. doi: 10.1364/OE.18.010828. URL https://doi.org/10.1364/OE.18.010828.
- [85] Olivier Moine and Brian Stout. Optical force calculations in arbitrary beams by use of the vector addition theorem. J. Opt. Soc. Am. B, JOSAB, 22(8):1620– 1631, 2005. ISSN 1520-8540. doi: 10.1364/JOSAB.22.001620. URL https: //doi.org/10.1364/JOSAB.22.001620.
- [86] Yuquan Zhang, Junfeng Shen, Changjun Min, Yunfeng Jin, Yuqiang Jiang, Jun Liu, Siwei Zhu, Yunlong Sheng, Anatoly V. Zayats, and Xiaocong Yuan. Nonlinearity-Induced Multiplexed Optical Trapping and Manipulation with Femtosecond Vector Beams. *Nano Lett.*, 18(9):5538–5543, 2018. ISSN 1530-6984. doi: 10.1021/acs.nanolett.8b01929. URL https://doi.org/10.1021/acs.nanolett. 8b01929.
- [87] Iker Gómez-Viloria, Álvaro Nodar, Martín Molezuelas-Ferreras, Jorge Olmos-Trigo, Ángel Cifuentes, Miriam Martínez, Miguel Varga, and Gabriel Molina-Terriza. On-Axis Optical Trapping with Vortex Beams: The Role of the Multipolar Decomposition. ACS Photonics, 11(2):626–633, 2024. doi: 10. 1021/acsphotonics.3c01499. URL https://doi.org/10.1021/acsphotonics. 3c01499.

- [88] Libang Mao, Ivan Toftul, Sivacarendran Balendhran, Mohammad Taha, Yuri Kivshar, and Sergey Kruk. Switchable optical trapping based on Mie-resonant phase-change nanoparticles. arXiv, 2024. doi: 10.48550/arXiv.2402.08947. URL https://doi.org/10.48550/arXiv.2402.08947.
- [89] Alexis I. Bishop, Timo A. Nieminen, Norman R. Heckenberg, and Halina Rubinsztein-Dunlop. Optical application and measurement of torque on microparticles of isotropic nonabsorbing material. *Phys. Rev. A*, 68(3):033802, 2003. doi: 10.1103/PhysRevA.68.033802. URL https://doi.org/10.1103/PhysRevA.68. 033802.
- [90] Eleftherios Goulielmakis and Thomas Brabec. High harmonic generation in condensed matter. Nat. Photonics, 16(6):411-421, 2022. ISSN 1749-4893. doi: 10.1038/s41566-022-00988-y. URL https://doi.org/10.1038/ s41566-022-00988-y.
- [91] G. Vampa, C. R. McDonald, G. Orlando, D. D. Klug, P. B. Corkum, and T. Brabec. Theoretical Analysis of High-Harmonic Generation in Solids. *Phys. Rev. Lett.*, 113(7):073901, 2014. ISSN 1079-7114. doi: 10.1103/PhysRevLett.113. 073901. URL https://doi.org/10.1103/PhysRevLett.113.073901.
- [92] George Zograf, Kirill Koshelev, Anastasiia Zalogina, Viacheslav Korolev, Richard Hollinger, Duk-Yong Choi, Michael Zuerch, Christian Spielmann, Barry Luther-Davies, Daniil Kartashov, Sergey V. Makarov, Sergey S. Kruk, and Yuri Kivshar. High-Harmonic Generation from Resonant Dielectric Metasurfaces Empowered by Bound States in the Continuum. ACS Photonics, 9(2):567–574, 2022. doi: 10. 1021/acsphotonics.1c01511. URL https://doi.org/10.1021/acsphotonics. 1c01511.
- [93] Yong Sing You, David A. Reis, and Shambhu Ghimire. Anisotropic high-harmonic generation in bulk crystals. *Nat. Phys.*, 13(4):345–349, 2017. ISSN 1745-2481. doi: 10.1038/nphys3955. URL https://doi.org/10.1038/nphys3955.
- [94] Álvaro Jiménez-Galán, Chandler Bossaer, Guilmot Ernotte, Andrew M. Parks, Rui E. F. Silva, David M. Villeneuve, André Staudte, Thomas Brabec, Adina Luican-Mayer, and Giulio Vampa. Orbital perspective on high-harmonic generation from solids. *Nat. Commun.*, 14(8421):1–6, 2023. ISSN 2041-1723. doi: 10.1038/s41467-023-44041-0. URL https://doi.org/10.1038/ s41467-023-44041-0.
- [95] kuyzirf. Calculation of Nonlinearity Tensor Chi3 in Cylindrical Coordinates. https://github.com/kuyzirf/Chi3-in-cylindrical-coordinates/ tree/main, 2024.
- [96] Ivan Fernandez-Corbaton, Xavier Zambrana-Puyalto, and Gabriel Molina-Terriza. On the transformations generated by the electromagnetic spin and orbital angular momentum operators. J. Opt. Soc. Am. B, JOSAB, 31(9): 2136-2141, 2014. ISSN 1520-8540. doi: 10.1364/JOSAB.31.002136. URL https://doi.org/10.1364/JOSAB.31.002136.

- [97] Ivan Fernandez-Corbaton. Helicity and Duality Symmetry in Light Matter Interactions: Theory and Applications. Optica Publishing Group, page LM1H.2, 2015. doi: 10.1364/LS.2015.LM1H.2. URL https://doi.org/10.1364/LS.2015.LM1H.2.
- [98] Konstantin Y. Bliokh, Aleksandr Y. Bekshaev, and Franco Nori. Dual electromagnetism: helicity, spin, momentum and angular momentum. New J. Phys., 15 (3):033026, 2013. ISSN 1367-2630. doi: 10.1088/1367-2630/15/3/033026. URL https://doi.org/10.1088/1367-2630/15/3/033026.
- [99] H. Hopf. Vektorfelder in n-dimensionalen-Mannigfaltigkeiten. Math. Ann., 96: 225-250, 1927. URL https://eudml.org/doc/159166.
- [100] H. Poincaré. Mémoire sur les courbes définies par une équation. J. Math. Pures Appl., 7:375–422, 1881. ISSN 0021-7874. URL https://eudml.org/doc/235914.
- [101] Heinz Hopf. Differential Geometry in the Large. Springer, Berlin, Germany, 1989. ISBN 978-3-540-39482-2. URL https://link.springer.com/book/10. 1007/3-540-39482-6.
- [102] Weijin Chen, Yuntian Chen, and Wei Liu. Singularities and Poincar\'e Indices of Electromagnetic Multipoles. *Phys. Rev. Lett.*, 122(15):153907, 2019. ISSN 1079-7114. doi: 10.1103/PhysRevLett.122.153907. URL https://doi.org/10.1103/ PhysRevLett.122.153907.
- [103] Meng Kang, Li Mao, Shunping Zhang, Meng Xiao, Hongxing Xu, and Che Ting Chan. Merging bound states in the continuum by harnessing higher-order topological charges. *Light Sci. Appl.*, 11(228):1–9, 2022. ISSN 2047-7538. doi: 10.1038/ s41377-022-00923-4. URL https://doi.org/10.1038/s41377-022-00923-4.
- [104] Character table for point group C3v, 2024. URL http://symmetry. jacobs-university.de/cgi-bin/group.cgi?group=403&option=4. [Online; accessed 29. Jan. 2024].
- [105] Huayong Zhang and Yiping Han. Addition theorem for the spherical vector wave functions and its application to the beam shape coefficients. J. Opt. Soc. Am. B, JOSAB, 25(2):255-260, 2008. ISSN 1520-8540. doi: 10.1364/JOSAB.25.000255. URL https://doi.org/10.1364/JOSAB.25.000255.
- [106] Seymour Stein. Addition theorems for spherical wave functions. Quarterly of Applied Mathematics, 19(1):15-24, 1961. ISSN 0033569X, 15524485. URL http: //www.jstor.org/stable/43634833.

A Appendix

A.1 On non-perturbative harmonic generation

Even though high harmonic generation is widely studied and observed in nonperturbative regime [90, 91], our study can be applied to the systems that are still under conditions the perturbative regime, or have a perturbative contribution [49, 68, 92]. The symmetry dependencies in non-perturbative regime should be studied separately [93, 94].

A.2 $\hat{\chi}^{(3)}$ tensor in cylindrical coordinates

By the link [95] we provide a Matlab code to compute the nonlinear susceptibility tensor in cylindrical coordinates for cubic symmetries. It could be easily rewritten for other tensors. One can imagine the procedure as writing tensor in the form of tensor product of basis vectors:

$$\hat{\chi}^{(3)} = \chi^{(3)}_{ijkl} \mathbf{e}_i \otimes \mathbf{e}_j \otimes \mathbf{e}_k \otimes \mathbf{e}_l, \tag{106}$$

where \mathbf{e}_i are $\hat{\mathbf{x}}$, $\hat{\mathbf{y}}$, or $\hat{\mathbf{z}}$ and then rewriting each vector \mathbf{e}_i in cylindrical coordinates according to

$$\hat{\mathbf{x}} = \hat{\boldsymbol{\rho}} \cos \varphi - \hat{\boldsymbol{\varphi}} \sin \varphi$$

$$\hat{\mathbf{y}} = \hat{\boldsymbol{\rho}} \sin \varphi + \hat{\boldsymbol{\varphi}} \cos \varphi$$
(107)

we get the answer. For example, for two of the most common materials, Si $(m\overline{3}m, O_h \text{group})$, and GaAs $(\overline{4}3m, T_d \text{ group})$ we have four independent components [48]:

$$\chi_{xxxx}^{(3)} = \chi_{yyyy}^{(3)} = \chi_{zzzz}^{(3)} \tag{108}$$

$$\chi_{xxyy}^{(3)} = \chi_{yyzz}^{(3)} = \chi_{zzxx}^{(3)} = \chi_{zzyy}^{(3)} = \chi_{yyzz}^{(3)} = \chi_{xxzz}^{(3)}$$
(109)

$$\chi_{xzxz}^{(3)} = \chi_{xyxy}^{(3)} = \chi_{yzyz}^{(3)} = \chi_{yxyx}^{(3)} = \chi_{zyzy}^{(3)} = \chi_{zxzx}^{(3)}$$
(110)

$$\chi_{xyyx}^{(3)} = \chi_{xzzx}^{(3)} = \chi_{yxxy}^{(3)} = \chi_{yzzy}^{(3)} = \chi_{zyyz}^{(3)} = \chi_{zxxz}^{(3)}.$$
 (111)

For example, if we provide them with values 8, 4, 4, 4 respectively, in cylindrical coordinates we obtain

$$\chi_{zzzz}^{(3)} = 8 \tag{112}$$

$$\chi^{(3)}_{\rho\rho\rho\rho} = \chi^{(3)}_{\varphi\varphi\varphi\varphi\varphi} = 9 - \cos 4\varphi \tag{113}$$

$$-\chi^{(3)}_{\rho\varphi\varphi\varphi} = -\chi^{(3)}_{\varphi\rho\varphi\varphi} = -\chi^{(3)}_{\varphi\varphi\rho\varphi} = -\chi^{(3)}_{\varphi\varphi\varphi\rho} =$$
$$= \chi^{(3)} = \chi^{(3)} = \chi^{(3)} = \chi^{(3)} = \sin 4\varphi \qquad (114)$$

$$= \chi_{\varphi\rho\rho\rho} = \chi_{\rho\varphi\rho\rho} = \chi_{\rho\rho\varphi\rho} = \chi_{\rho\rho\varphi\rho} = \chi_{\rho\rho\rho\varphi} = \sin 4\varphi$$
(114)
$$\mathbf{v}^{(3)} = \mathbf{v}^{(3)} = \mathbf{v}^{(3)} = \mathbf{v}^{(3)} = \mathbf{v}^{(3)} = \cos(4\varphi) + 3$$
(115)

$$\chi^{\rho\rho\varphi\varphi}_{\varphi z\varphi z} \chi^{\rho\rho\varphi\varphi}_{\varphi z\varphi z} \chi^{\rho\rho\varphi\varphi}_{\varphi z\varphi z} \chi^{\rho\rho\varphi\varphi}_{\varphi z\varphi z} \chi^{\rho\rho\varphi\varphi}_{\varphi zz} \chi^{(3)}_{\varphi z\varphi z} = \chi^{(3)}_{\varphi z\varphi z} = \chi^{(3)}_{\varphi z\varphi z} = \chi^{(3)}_{\varphi \varphi zz} = \chi^{(3)}_{\varphi zz \varphi} = \chi^{(3)}_{\rho zz \rho} =$$

From above, we see that $m_{\chi} \in \{0, 4, -4\}$, so $\Delta m_{\chi} \in \{\pm 4, \pm 8\}$. Note that the second value ± 8 could not be obtained for $\hat{\chi}^{(2)}$ or any third rank tensor.

A.3 Vector spherical harmonics

Magnetic and electric vector spherical harmonics \mathbf{M}_{emn}^{e} , \mathbf{N}_{emn}^{e} are generated by the scalar functions [40]:

$$\psi_{emn} = \cos m\varphi P_n^m(\cos \vartheta) z_n(kr), \qquad (117)$$

$$\psi_{omn} = \sin m\varphi P_n^m(\cos \vartheta) z_n(kr),$$

where $P_n^m(\cos\theta)$ are associated Legendre polynomials, and $z_n(kr)$ are any of the spherical Bessel functions: $j_n, y_n, h_n^{(1)}, h_n^{(2)}$. They can be defined as:

$$\mathbf{M}_{omn} = \nabla \times \left(\mathbf{r} \psi_{omn} \right), \tag{118}$$
$$\mathbf{N}_{omn} = \frac{\nabla \times \mathbf{M}_{omn}}{\mathbf{k}}.$$

In the component form they can be written as follows:

$$\mathbf{M}_{emn}(k, \mathbf{r}) = \frac{-m}{\sin \theta} \sin m\varphi P_n^m(\cos \theta) z_n(\rho) \hat{\mathbf{e}}_{\theta} -$$
(119)
$$-\cos m\varphi \frac{\mathrm{d}P_n^m(\cos \theta)}{\mathrm{d}\theta} z_n(\rho) \hat{\mathbf{e}}_{\varphi},$$

$$\mathbf{M}_{omn}(k, \mathbf{r}) = \frac{m}{\sin \theta} \cos m\varphi P_n^m(\cos \theta) z_n(\rho) \hat{\mathbf{e}}_{\theta} -$$
(120)
$$-\sin m\varphi \frac{\mathrm{d}P_n^m(\cos \theta)}{\mathrm{d}\theta} z_n(\rho) \hat{\mathbf{e}}_{\varphi},$$

$$\mathbf{N}_{emn}(k, \mathbf{r}) = \frac{z_n(\rho)}{\rho} \cos m\varphi \, n(n+1) P_n^m(\cos\theta) \hat{\mathbf{e}}_r +$$

$$+ \cos m\varphi \frac{\mathrm{d}P_n^m(\cos\theta)}{\mathrm{d}\theta} \frac{1}{\rho} \frac{\mathrm{d}}{\mathrm{d}\rho} \left[\rho z_n(\rho)\right] \hat{\mathbf{e}}_{\theta} -$$

$$- m \sin m\varphi \frac{P_n^m(\cos\theta)}{\sin\theta} \frac{1}{\rho} \frac{\mathrm{d}}{\mathrm{d}\rho} \left[\rho z_n(\rho)\right] \hat{\mathbf{e}}_{\varphi},$$
(121)

$$\mathbf{N}_{omn}(k, \mathbf{r}) = \frac{z_n(\rho)}{\rho} \sin m\varphi \, n(n+1) P_n^m(\cos\theta) \hat{\mathbf{e}}_r +$$

$$+ \sin m\varphi \frac{\mathrm{d}P_n^m(\cos\theta)}{\mathrm{d}\theta} \frac{1}{\rho} \frac{\mathrm{d}}{\mathrm{d}\rho} \left[\rho z_n(\rho)\right] \hat{\mathbf{e}}_{\theta} +$$

$$+ m\cos m\varphi \frac{P_n^m(\cos\theta)}{\sin\theta} \frac{1}{\rho} \frac{\mathrm{d}}{\mathrm{d}\rho} \left[\rho z_n(\rho)\right] \hat{\mathbf{e}}_{\varphi},$$
(122)

where dimensionless variable $\rho = kr$ was introduced.



Figure 4: Visual illustration of the far-field real part of a multipolar combination (124) or (125). The far-field radiation pattern is shown in the center with arrows depicted. For convenience, we provide the view from the top and bottom. Red arrows are a guide for eyes for computing the Hopf index l'.

A.4 On specific multipolar combinations and vortex beams

We provide this appendix for a better understanding of the symmetry properties of the vortex beams building blocks, which are specific multipolar combinations. Recall that in the paraxial approximation beam ((1) and (2)) is often written in the form

$$|R/L_m\rangle \sim \exp(i(m-\lambda)\varphi)(\hat{\mathbf{x}}+\lambda i\hat{\mathbf{y}})/\sqrt{2}$$
 (123)

where opposite signs of total angular momentum projection m and helicity λ [37, 96] refer to the right- and left-handed beams. Usually, the quantity $\ell = m - \lambda$ is introduced, which refers to the number of phase rotations around the singularity (see Fig. 1) and

also to the order of higher-order Poincare sphere. For a circularly polarized plane wave, $\ell = 0$. Let us recall the expressions from (8) and (9) [42], which are the building blocks of vortex beams with m and λ :

$$(\mathbf{N}_{e|m|n} \pm \mathrm{i} \mathbf{N}_{o|m|n}) + (\pm \mathbf{M}_{e|m|n} + \mathrm{i} \mathbf{M}_{o|m|n}), \qquad (124)$$

where upper sign is for $\lambda = 1$ and m = |m|, and the lower sign is for $\lambda = -1$ and m = -|m| and

$$(\mathbf{N}_{e|m|n} \mp \mathrm{i} \mathbf{N}_{o|m|n}) - (\mp \mathbf{M}_{e|m|n} + \mathrm{i} \mathbf{M}_{o|m|n}),$$
(125)

where upper sign is for $\lambda = 1$ and m = -|m|, and the lower sign is for $\lambda = -1$ and m = |m|. These multipolar combinations are eigenvectors of helicity operator [43, 97, 98], and determine the polarization of the beam. Moreover, their total angular momentum projection is also well-defined and equal to m [38]. These functions are complex-valued, thus it is difficult to provide a visual presentation. However, if we depict the real part of the far-field, it provides us with some beautiful insights. Note, that such combinations refer to the building blocks of vector beams $|B_{me}\rangle$ (the imaginary part would refer to $|B_{mo}\rangle$, respectively.) For each smooth vector field on sphere S^2 , according to Hairy ball,



Figure 5: Far-field of the $\mathbf{N}_{em4} + i\mathbf{M}_{om4}$ for different $m \in \{0, 1, 2, 3, 4\}$ and their Hopf indexes l'.

or Poicare-Hopf theorem [99, 100], the sum of Hopf indexes l' [101] of the singularities is equal 2. Hence it is also applicable for multipoles [102]. We can calculate the Hopf index as the number of counterclockwise rotations made by the polarization vector when circling the singularity counterclockwise. For these particular linear combinations, we have two point singularities on the south and north poles, and their Hopf indexes are always equal to either m + 1 and m - 1 (see Fig. 4 and 5). For the linear combinations with m = 1, which contribute to Kerker effect [44], we only have one of them with index 2. For the complex functions, the Hopf index will transform into a number of phase rotations ℓ . These properties could be also useful for engineering, e.g. topological charges of BICs [102, 103].

We should also notice that beams with the same ℓ can have either $m = \ell + 1$ or $m = \ell - 1$. In some papers, the dichroism is defined as a difference between responses for the same ℓ but different λ . However, this would lead to the excitation of symmetrically different resonant modes (with different m), hence different linear response [22].

A.5 Extra technical derivations

A.5.1 Multipolar content of the eigenmodes of C_{3v} nanostructure

Eigenmodes, which are transformed under E irrep Decomposition of the eigenmodes transformed under E, according to the tables with a given multipolar content of the eigenmodes [63, 64] consists only of the vector spherical harmonics with the projections of the angular momentum m = 3s - 1 and m = 3s - 2, where $s \in \mathbb{Z}_+$ with, in general, complex coefficients. However, we note that E is a 2-dimensional irreducible representation, thus there are two orthogonal eigenmodes transformed under this representation. Given the above, eigenmodes can be written in the following form:

$$\mathbf{E}_{j}^{2\omega,x}\left(\mathbf{r}'\right) = a_{e11}\mathbf{N}_{e11} + a_{e12}\mathbf{N}_{e12} + b_{o11}\mathbf{M}_{o11} + \dots, \qquad (126)$$

$$\mathbf{E}_{j}^{2\omega,y}\left(\mathbf{r}'\right) = a_{o11}\mathbf{N}_{o11} + a_{o12}\mathbf{N}_{o12} + b_{e11}\mathbf{M}_{e11} + \dots, \qquad (127)$$

where $\mathbf{E}_{j}^{2\omega,x}(\mathbf{r}')$ and $\mathbf{E}_{j}^{2\omega,y}(\mathbf{r}')$ are orthogonal eigenmodes transformed under irreducible representation E, the first one behaves as a function $f(\mathbf{r}) = x$ and the second as $f(\mathbf{r}) =$ y [104]. To ensure orthogonality, we've exploited the symmetry of the nanostructure under reflection in y = 0 plane. Index j corresponds to the specific eigenmode with such symmetry. For each j the coefficients a and b are different. It's worth mentioning that orthogonal eigenmodes should be transformed through each other in a certain way under transformations of group symmetry C_{3v} , thus coefficients a_{emn} and a_{omn} , as well as b_{emn} and b_{omn} are connected with each other: $a_{e(3s-2)n} = a_{o(3s-2)n} = a_{(3s-2)n}$, $a_{e(3s-1)n} = -a_{o(3s-1)n} = a_{(3s-2)n}$, and $b_{e(3s-2)n} = -b_{o(3s-2)n} = b_{(3s-2)n}$, $b_{e(3s-1)n} =$ $b_{o(3s-1)n} = b_{(3s-1)n}$, where $s \in \mathbb{Z}_+$. These identities can be proved by applying the symmetry transformations of the C_{3v} group to each vector spherical harmonic [105, 106]. Therefore, decompositions of eigenmodes (126) and (127) are written as:

$$\mathbf{E}_{j}^{2\omega,x}\left(\mathbf{r}'\right) = a_{11}\mathbf{N}_{e11} + a_{12}\mathbf{N}_{e12} + b_{11}\mathbf{M}_{o11} + \dots, \qquad (128)$$

$$\mathbf{E}_{j}^{2\omega,y}\left(\mathbf{r}'\right) = a_{11}\mathbf{N}_{o11} + a_{12}\mathbf{N}_{o12} + (-b_{11})\mathbf{M}_{e11} + \dots$$
(129)

Let us change the basis to a circular form, i.e. $\mathbf{E}_{j}^{2\omega,x\pm iy} = (\mathbf{E}_{j}^{2\omega,x} \pm i\mathbf{E}_{j}^{2\omega,y})/2$ and rewrite decompositions as:

$$\mathbf{E}_{j}^{2\omega,x+\mathrm{i}y}\left(\mathbf{r}'\right) = \frac{a_{11}}{2} (\mathbf{N}_{e11} + \mathrm{i}\mathbf{N}_{o11}) + \frac{a_{22}}{2} (\mathbf{N}_{e22} - \mathrm{i}\mathbf{N}_{o22}) + \\ + \frac{a_{12}}{2} (\mathbf{N}_{e12} + \mathrm{i}\mathbf{N}_{o12}) + \frac{b_{11}}{2} (\mathbf{M}_{o11} - \mathrm{i}\mathbf{M}_{e11}) + \dots, \qquad (130)$$

$$\mathbf{E}_{j}^{2\omega,x-\mathrm{i}y}\left(\mathbf{r}'\right) = \frac{a_{11}}{2} (\mathbf{N}_{e11} - \mathrm{i}\mathbf{N}_{o11}) + \frac{a_{22}}{2} (\mathbf{N}_{e22} + \mathrm{i}\mathbf{N}_{o22}) + \\ + \frac{a_{12}}{2} (\mathbf{N}_{e12} - \mathrm{i}\mathbf{N}_{o12}) + \frac{b_{11}}{2} (\mathbf{M}_{o11} + \mathrm{i}\mathbf{M}_{e11}) + \dots, \qquad (131)$$

where $\mathbf{E}_{j}^{2\omega,x\pm iy}$ are also orthogonal eigenmodes. Using the definition of the vector spherical harmonics (See Appendix A.3), we can simplify the expressions (130) and (131) above:

$$\mathbf{E}_{j}^{2\omega,x\pm iy}\left(\mathbf{r}'\right) = \frac{a_{11}}{2}\mathbf{N}_{11}(r,z)e^{\pm 1i\varphi} + \frac{a_{22}}{2}\mathbf{N}_{22}(r,z)e^{\mp 2i\varphi} +$$

+
$$\frac{a_{12}}{2}$$
N₁₂(r, z)e^{±1i\varphi} + $\frac{b_{11}}{2}$ **M**₁₁(r, z)e^{±1i\varphi} + ..., (132)

where $\mathbf{N}(\mathbf{M})_{mn}(r,z)$ do not depend on φ . Note that the functions $\mathbf{N}_{22}(r,z)$ can have a different sign of φ -component for different "polarization" but here we omit it as well as in the polarization, since it doesn't affect the final result (See Suppl. Info in [31]). Finally, combining combinations all $\mathbf{N}(\mathbf{M})_{mn}(r,z)$ with complex coefficients a_{mn}, b_{mn} with the same m into $\mathbf{E}_{j,mn}(r,z)$ we obtain the following decompositions of orthogonal eigenmodes $\mathbf{E}_{j}^{2\omega,x\pm iy}$:

$$\mathbf{E}_{j}^{2\omega,x\pm iy}\left(\mathbf{r}'\right) = \sum_{n} \left\{ \mathbf{E}_{j,1n}(r,z) \mathrm{e}^{\pm 1\mathrm{i}\varphi} + \mathbf{E}_{j,2n}(r,z) \mathrm{e}^{\mp 2\mathrm{i}\varphi} + \mathbf{E}_{j,4n}(r,z) \mathrm{e}^{\pm 4\mathrm{i}\varphi} + \mathbf{E}_{j,5n}(r,z) \mathrm{e}^{\mp 5\mathrm{i}\varphi} + \dots \right\}.$$
(133)

Eigenmodes, which are transformed under A_1 and A_2 irrep Decompositions of eigenmodes transformed under irreducible representations A_1 and A_2 contain vector spherical harmonics $\mathbf{M}_{\mathfrak{G}(3s)n}$ and $\mathbf{N}_{\mathfrak{G}(3s)n}$, where $s \in \mathbb{Z}_+$. Eigenmodes transformed under A_1 are even under reflection in the plane XZ (for a particular orientation of a trimer), while eigenmodes transformed under A_2 are odd. Thus, decompositions can be expressed as follows [64]:

$$\mathbf{E}_{j}^{2\omega,A_{1}}\left(\mathbf{r}'\right) = a_{e01}\mathbf{N}_{e01} + a_{e33}\mathbf{N}_{e33} + b_{o33}\mathbf{M}_{o33} + \dots, \qquad (134)$$

$$\mathbf{E}_{j}^{2\omega,A_{2}}\left(\mathbf{r}'\right) = b_{e01}\mathbf{M}_{e01} + b_{e33}\mathbf{M}_{e33} + a_{o33}\mathbf{N}_{o33} + \dots$$
(135)

Using the explicit form of the vector spherical harmonics (Appendix A.3), and new notations, we can rewrite the expressions above (134) and (135) in the following form:

$$\mathbf{E}_{j}^{2\omega,\mathbf{A}_{1}}\left(\mathbf{r}'\right) =$$

$$= \sum_{n} \left\{ \left[E_{j,e3n}^{r}\left(r,z\right)\hat{\mathbf{e}}_{r} + E_{j,e3n}^{z}\left(r,z\right)\hat{\mathbf{e}}_{z} \right]\cos 3\varphi + E_{j,e3n}^{\varphi}\left(r,z\right)\hat{\mathbf{e}}_{\varphi}\sin 3\varphi + \dots \right\},$$

$$(136)$$

$$\mathbf{E}_{j}^{2\omega,A_{2}}\left(\mathbf{r}'\right) =$$

$$= \sum_{n} \left\{ \left[E_{j,o3n}^{r}\left(r,z\right) \hat{\mathbf{e}}_{r} + E_{j,o3n}^{z}\left(r,z\right) \hat{\mathbf{e}}_{z} \right] \sin 3\varphi + E_{j,o3n}^{\varphi}\left(r,z\right) \hat{\mathbf{e}}_{\varphi} \cos 3\varphi + \dots \right\},$$

$$(137)$$

where coefficients $E_{j,c3n}^r(r,z)$, $E_{j,c3n}^z(r,z)$, $E_{j,c3n}^{\varphi}(r,z)$ contain all functions and constants independent on coordinate φ .

A.5.2 Expression for the total intensity

In the Section (4.1.5), we obtained the following expression for the total integral second harmonic intensity $I^{2\omega}_{|L_m\rangle,|R_m\rangle}$ for the case of the nanostructure GaAs[111]||z with symmetry C_{3v} (44):

$$I_{|L_m\rangle,|R_m\rangle}^{2\omega} \propto \int_{\mathrm{sph}} \mathrm{d}V \left| \mathbf{E}_j^{2\omega,x\pm \mathrm{i}y}(\mathbf{r}) \left(a_j^+ \mathrm{e}^{\mp 3\mathrm{i}\beta} + a_j'^+ \mathrm{e}^{\pm 3\mathrm{i}\beta} + a_j''^+ \right) +$$
(138)

$$+ \operatorname{e}^{\mathrm{i}\alpha} \mathbf{E}_{i}^{2\omega, x \pm \mathrm{i}y}(\mathbf{r}) \left(a_{i}^{+} \operatorname{e}^{-3\mathrm{i}\beta} + a_{i}^{\prime +} \operatorname{e}^{+3\mathrm{i}\beta} + a_{i}^{\prime \prime +} \right) \Big|^{2} = \int_{\mathrm{sph}} \mathrm{d}V \cdot J^{\pm},$$

where, for clarity, we introduce the integrand J^{\pm} .

A left-handed beam Let us precisely calculate the integrand from the expression (138) for the left-handed excitation:

$$J^{+} = \left| \mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}) \left(a_{i}^{+} e^{-3i\beta} + a_{j}^{\prime+} e^{+3i\beta} + a_{j}^{\prime+} \right) +$$
(139)
+ $e^{i\alpha} \mathbf{E}_{i}^{2\omega,x+iy}(\mathbf{r}) \left(a_{i}^{+} e^{-3i\beta} + a_{i}^{\prime+} e^{+3i\beta} + a_{j}^{\prime\prime+} \right) \right|^{2} =$
= $\left[e^{-i\alpha} \mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}) \left(\mathbf{E}_{i}^{2\omega,x+iy}(\mathbf{r}) \right)^{*} \cdot \left(a_{j}^{+} e^{-3i\beta} + a_{j}^{\prime+} e^{+3i\beta} + a_{j}^{\prime\prime+} e^{-3i\beta} + a_{i}^{\prime\prime+*} \right) + c.c. \right] +$
+ $\left(\left| \mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}) \right|^{2} \cdot \left| a_{j}^{+} e^{-3i\beta} + a_{j}^{\prime+} e^{+3i\beta} + a_{j}^{\prime\prime+} \right|^{2} + (j \to i) \right) =$
= $\left[e^{-i\alpha} \mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}) \left(\mathbf{E}_{i}^{2\omega,x+iy}(\mathbf{r}) \right)^{*} \cdot \left(\left\{ a_{j}^{+} a_{i}^{+*} + a_{j}^{\prime+} a_{i}^{\prime+*} e^{+6i\beta} + a_{j}^{\prime} + a_{i}^{\prime+*} e^{-6i\beta} + \right. \right. \right. \right. + \left. \left\{ a_{j}^{+} a_{i}^{+*} + a_{j}^{\prime+} a_{i}^{\prime+*} e^{-3i\beta} \right\} + \left\{ a_{j}^{+} a_{i}^{\prime+*} e^{-3i\beta} + a_{j}^{\prime+} a_{i}^{\prime+*} e^{-3i\beta} \right\} \right) + c.c. \right] +$
+ $\left[\left| \mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}) \right|^{2} \left(\left\{ \left| a_{j}^{+} \right|^{2} + \left| a_{j}^{\prime+} \right|^{2} \right|^{2} \right\} + \left\{ a_{j}^{+} a_{i}^{\prime+*} e^{-6i\beta} + a_{j}^{+} a_{i}^{\prime+*} e^{-6i\beta} + \right. \right. \right. \right. \right. \right. + \left. \left. \left. \left\{ a_{j}^{+} a_{i}^{+*} e^{+3i\beta} + a_{j}^{\prime+} a_{i}^{\prime+*} e^{-3i\beta} \right\} + \left\{ a_{j}^{+} a_{j}^{\prime+*} e^{-3i\beta} \right\} \right\} + \left\{ a_{j}^{\prime+} a_{j}^{+*} e^{-6i\beta} + \left. \left. \left. \left. \left. \left| \mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}) \right|^{2} \left(\left\{ \left| a_{j}^{+} \right|^{2} + \left| a_{j}^{\prime+} \right|^{2} \right\} + \left\{ a_{j}^{+} a_{j}^{\prime+*} e^{-3i\beta} \right\} + \left\{ a_{j}^{\prime+} a_{j}^{\prime+*} e^{-3i\beta} \right\} \right\} + \left(j \to j \right) \right] \right] =$
= $\left[e^{-i\alpha} \mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}) \left(\mathbf{E}_{i}^{2\omega,x+iy}(\mathbf{r}) \right)^{*} \cdot \left. \left. \left. \left(A_{ji} + B_{ji} e^{+6i\beta} + C_{ji} e^{-6i\beta} + D_{ji} e^{+3i\beta} + E_{ji} e^{-3i\beta} \right) + c.c. \right] \right. \right] +$
+ $\left[\left| \mathbf{E}_{j}^{2\omega,x+iy}(\mathbf{r}) \right|^{2} \left(A_{jj} + B_{jj} e^{+6i\beta} + C_{jj} e^{-6i\beta} + D_{jj} e^{+3i\beta} + E_{jj} e^{-3i\beta} \right) + (j \to i) \right] \right]$, where constants $A_{ii} = a_{i}^{+} a_{i}^{+*} + a_{i}^{+} a_{i}^{+} a_{i}^{+*} + a_{i}^{+} a_{i}^{+*} + a_{i}^{++} a_$

where constants $A_{ji} = a_j^+ a_i^{+*} + a_j'^+ a_i'^{+*}$, $B_{ji} = a_j'^+ a_i^{+*} e^{+6i\beta}$, $C_{ji} = a_j^+ a_i'^{+*} e^{-6i\beta}$, $D_{ji} = a_j''^+ a_i'^{+*} e^{+3i\beta} + a_j'^+ a_i'^{+*} e^{+3i\beta}$, and $E_{ji} = a_j^+ a_i''^{+*} e^{-3i\beta} + a_j''^+ a_i'^{+*} e^{-3i\beta}$ were introduced, for simplicity. Substituting the expression for the integrand J^+ (139) into formula for the intensity $I_{|L_m\rangle}^{2\omega}$ (44), we get:

$$I_{|L_m\rangle}^{2\omega,\text{interf.}} \propto \int_{\text{sph}} dV e^{-i\alpha} \mathbf{E}_j^{2\omega,x+iy}(\mathbf{r}) \left(\mathbf{E}_i^{2\omega,x+iy}(\mathbf{r}) \right)^* \cdot$$
(140)
$$\left(A_{ji} + B_{ji} e^{+6i\beta} + C_{ji} e^{-6i\beta} + D_{ji} e^{+3i\beta} + E_{ji} e^{-3i\beta} \right) + \text{c.c.},$$

where we focus only on interference terms of the intensity.

A right-handed beam For the right-handed excitation, we omit the similar calculations (139) and present the interference terms $I_{|R_m\rangle}^{2\omega}$:

$$I_{|R_m\rangle}^{2\omega,\text{interf.}} \propto \int_{\text{sph}} dV e^{-i\alpha} \mathbf{E}_j^{2\omega,x-iy}(\mathbf{r}) \left(\mathbf{E}_i^{2\omega,x-iy}(\mathbf{r}) \right)^* \cdot \left(A_{ji} + B_{ji} e^{-6i\beta} + C_{ji} e^{+6i\beta} + D_{ji} e^{-3i\beta} + E_{ji} e^{+3i\beta} \right) + \text{c.c.}$$
(141)

Finally, these two formulas for the interference terms of the total intensity (140) and (141) can be combined into a single expression that has already been introduced in the Section (4.1.5) (45):

$$I_{|L_m\rangle,|R_m\rangle}^{2\omega,\text{interf.}} \propto \int_{\text{sph}} dV e^{-i\alpha} \mathbf{E}_j^{2\omega,x\pm iy}(\mathbf{r}) \left(\mathbf{E}_i^{2\omega,x\pm iy}(\mathbf{r})\right)^* \cdot$$
(142)
$$\left(A_{ji} + B_{ji} e^{\pm 6i\beta} + C_{ji} e^{\mp 6i\beta} + D_{ji} e^{\pm 3i\beta} + E_{ji} e^{\mp 3i\beta}\right) + \text{c.c.}.$$