# Fluoride Frameworks as Potential Calcium Battery Cathodes

Dereje Bekele Tekliye<sup>1</sup> and Gopalakrishnan Sai Gautam<sup>1,\*</sup>

<sup>1</sup>Department of Materials Engineering, Indian Institute of Science, Bengaluru, 560012,

India

<sup>\*</sup>Email: saigautamg@iisc.ac.in

#### Abstract

Calcium batteries (CBs) are potential next-generation energy storage devices, offering a promising alternative to lithium-ion batteries due to their theoretically high energy density, better safety, and lower costs associated with the natural abundance of calcium. However, the limited availability of positive electrode (cathode) materials has constrained the development of CBs so far. Given the similar ionic radii of Na<sup>+</sup> and Ca<sup>2+</sup>, structures that are effective at reversibly intercalating Na<sup>+</sup> may be able to reversibly intercalate Ca<sup>2+</sup> as well. In this context, transition metal fluorides (TMFs) exhibiting weberite and perovskite structures that are known for intercalating Na<sup>+</sup> form an interesting set of possible CB cathode frameworks. Thus, we use first principles calculations to explore weberite and perovskite TMFs as CB cathodes, of compositions  $Ca_xM_2F_7$  and  $Ca_xMF_3$ , respectively, where M = Ti, V, Cr, Mn, Fe, Co, or Ni. We systematically evaluate key cathode properties, including ground state structure, average Caintercalation voltage, thermodynamic stability (at 0 K), theoretical capacity, and Ca<sup>2+</sup> migration barriers. Importantly, we identify  $Ca_xCr_2F_7$  and  $Ca_xMn_2F_7$  weberite frameworks as promising Ca-cathodes. Our study not only unveils potential CB cathodes but also paves the way for further advancement in TMFbased intercalation cathodes, diversifying the chemical space for next-generation energy storage systems.

### 1 Introduction

The ubiquity of rechargeable Li-ion batteries (LIBs), with their high energy and power density, has emerged as the predominant energy source for numerous applications ranging from portable electronics, electric vehicles, and stationary energy storage. [1–6] However, the growing demand for LIBs across a wide variety of applications raises concern about Li (also Co and Ni) resource availability and associated supplychain constraints [7], necessitating an exploration of alternate solutions to the LIB technology. Off-late, there is growing interest in Calcium batteries (CBs) as a potential next-generation battery technology due to: (i) the low standard reduction potential of Ca (-2.87 V versus standard hydrogen electrode, SHE) approaching that of Li (-3.04 V versus SHE), (ii) the multivalent nature of Ca<sup>2+</sup>, which shuttles two valence electrons at a time, combined with the use of Ca-metal as anode, which can result in an increased volumetric energy density [8–13], (iii) CBs utilize Ca, which is more abundant than Li (Ca: 4.2% versus Li: 0.002% of earth's crust [14]), potentially making CBs less expensive and more sustainable than LIBs.

Despite the inherent advantages, the development of CBs is constrained by the need for suitable electrolytes and positive electrodes (cathodes). While stripping and plating Ca-metal at the negative electrode (anode) has encountered challenges due to electrolyte decomposition [11, 15], recent advances in the electrolyte design have enabled efficient Ca plating/stripping with the formation of a protective layer enhancing electrochemical performance. [16–19] However, the lack of suitable cathode candidates, namely lack of thermodynamic and/or cyclic stability, [13] and poor  $Ca^{2+}$  diffusion, [20] continues to hinder the development of practical CBs.

Previous studies have employed both experimental and computational techniques to explore select chemistries as possible CB cathodes. The set of inorganic cathodes that have been reported with Ca so far include  $CaMo_6X_8$  (X = S, Se, or Te), [21] VOPO<sub>4</sub>·2H<sub>2</sub>O [22],  $Ca_xV_2O_5$ , [23–27]  $CaV_2O_4$ , [28,29]  $CaMn_2O_4$ , [30]  $MoO_3$ , [31–33] NH<sub>4</sub>V<sub>4</sub>O<sub>10</sub>, [34]  $CaCo_2O_4$ , [35,36] NaFePO<sub>4</sub>F, [37] TiS<sub>2</sub>, [38]  $CaV_6O_{16}$ ·2.8H<sub>2</sub>O, [39] Prussianblue analogues (PBA) [40–44], and other polyanionic frameworks. [45–48] However, only a select few of these compounds show reasonable electrochemical performance, with most suffering from inadequate cyclic stability, poor Ca-ion diffusion, and large volume changes during charge/discharge. For instance, VOPO<sub>4</sub>·2H<sub>2</sub>O demonstrates reasonable electrochemical performance against Ca-containing electrolytes, [22] yet its susceptibility to proton intercalation and the undesirable effects of water in organic electrolytes pose challenges for practical cell applications. [49]

Recently, Chando et al. [30] explored the post-spinel phase of  $CaMn_2O_4$  as CB-cathode candidate using both experiments and density functional theory (DFT [50, 51]) calculations, and reported a low cycling capacity of 52 mAh/g at a rate of C/33. Prabakar et al. [26] used a water-free  $\beta$ -phase  $Ca_{0.14}V_2O_5$  as a Ca-cathode and reported a reversible capacity of ~247 mAh/g. The authors stated that unlike conventional layered  $\beta$ -V<sub>2</sub>O<sub>5</sub> and  $\delta$ -Ca<sub>x</sub>V<sub>2</sub>O<sub>5</sub>·nH<sub>2</sub>O cathodes, the  $\beta$ -phase facilitates efficient insertion/extraction of Ca ions, contributing to improved cyclic stability and minimal dimensional changes during charge/discharge cycles. [26]

In terms of polyanionic materials, Vaughey and co-workers [45] reported two phosphates, namely sodium superionic conductor (NaSICON) (NaV<sub>2</sub>(PO<sub>4</sub>)<sub>3</sub>) and olivine (FePO<sub>4</sub>), as high-voltage cathodes for roomtemperature CBs. NaV<sub>2</sub>(PO<sub>4</sub>)<sub>3</sub> demonstrates stable cycling with reversible intercalation of ~0.6 mol of Ca<sup>2+</sup> at 3.2 V vs. Ca, while FePO<sub>4</sub> exhibits reversible intercalation of ~0.2 mol of Ca<sup>2+</sup> at 2.9 V. Subsequently, Kang and co-workers [47] reported a successful extraction/insertion of Ca from/into Na<sub>0.5</sub>VPO<sub>4.8</sub>F<sub>0.7</sub>, exhibiting exceptional cycling stability with 90% capacity retention over 500 cycles and 87 mAh/g capacity. Additionally, Nazar and coworkers [52] investigated the Ca–Na dual cation system, using experimental and computational methods to understand the phase evolution and kinetics of Ca<sub>x</sub>NaV<sub>2</sub>(PO<sub>4</sub>)<sub>3</sub> that takes place during Ca<sup>2+</sup> cycling. The authors reported a reversible Ca<sup>2+</sup> cycling capacity being limited to be x  $\approx 0.65$ in Ca<sub>x</sub>NaV<sub>2</sub>(PO<sub>4</sub>)<sub>3</sub>, attributing the limit due to phase separation into Na-rich and Ca-rich phases. Also, the authors demonstrated that Na<sup>+</sup> migration within the host framework facilitates neighboring Ca<sup>2+</sup> migration, enabling reversible electrochemical activity.

With respect to recent computational identification of promising Ca-cathodes, Lu et al. [28] identified two promising Ca-cathode compositions through a DFT-based high-throughput screening considering average voltages, thermodynamic stability, and migration barriers, namely, post-spinel-CaV<sub>2</sub>O<sub>4</sub> and layered-CaNb<sub>2</sub>O<sub>4</sub>. While a subsequent experimental investigation by Palacín, Arroyo-de Dompablo and coworkers [29] showed promise for reversible Ca intercalation in CaV<sub>2</sub>O<sub>4</sub>, further optimization of the electrode framework is imperative. Additionally, we performed an extensive screening study of NaSICON frameworks as potential Ca-cathodes. [48] Specifically, we used first principles calculations to determine the ground state structure, average intercalation voltage, 0 K thermodynamic stability, and migration barrier, using which we identified three promising candidate Ca-cathodes, namely, Ca<sub>x</sub>V<sub>2</sub>(PO<sub>4</sub>)<sub>3</sub>, Ca<sub>x</sub>Mn<sub>2</sub>(SO<sub>4</sub>)<sub>3</sub>, and  $Ca_xFe_2(SO_4)_3$ . Experimental realization of these predicted NaSICONs, except for  $Ca_xV_2(PO_4)_3$ , is pending.

In the context of using anion chemistry to boost energy density of cathodes, Fluorine's high electronegativity triggers a strong inductive effect on transition-metal (TM) ions within the cathode. [53] As a result of this inductive effect, the electron density on the TM redox center reduces, resulting in a better response to addition or removal of electrons, or a higher voltage with the (de)intercalation of an electroactive ion. [54] In addition, the lower molar mass of F compared to polyanionic groups (e.g., phosphates) can enhance the gravimetric capacity of a given cathode. Thus, fluorine-based frameworks can exhibit higher voltages, on average, compared to oxide or other halide frameworks. As a result, researchers typically utilize  $F^-$  to substitute anionic sites or polyanionic groups, completely/partially, yielding better cathode materials with enhanced properties. [47, 55–58]

Fluorides as a chemical space are a promising, yet overlooked class of host materials as cathodes in intercalation-based electrochemical energy storage systems, especially in CBs. A few fluoride compounds, such as perovskite-type NaMF<sub>3</sub> (M = Fe, Mn, Ni, and Co), have been investigated as cathodes for sodium-ion batteries (NIBs). [59,60] NaFeF<sub>3</sub> showed an initial capacity of 130 mAhg<sup>-1</sup>, yet suffered from high polarization and capacity fading, while the initial charge capacity of NaMnF<sub>3</sub>, NaNiF<sub>3</sub> and NaCoF<sub>3</sub> was limited to 40 mAhg<sup>-1</sup>, largely attributable to side reaction as later demonstrated by Dimov et al. [61] While Ca is known to occupy the perovskite framework among oxides, [62, 63] fluorine-based perovskites have not been rigorously explored for CBs.

Weberite-type fluorides (typically Fe-containing), known for their robust three-dimensional open framework interconnected by FeF<sub>6</sub> octahedra, have been explored computationally as NIB cathodes by Euchner et al. [64] Moreover, weberites can be synthesized from fluoride precursors using topochemical wet chemistry routes, which employ lower temperatures compared to solid-state synthesis routes. [65, 66] Recently, Park et al. [67] investigated trigonal-type fluoride weberite (Na<sub>2</sub>Fe<sub>2</sub>F<sub>7</sub>), using experimental and computational methods. The authors demonstrated a high capacity of 184 mAh/g at C/20 (1C = 184 mA g<sup>-1</sup>), which approaches the theoretical capacity of the weberite and reported a capacity retention over 88% of the initial capacity at 2C after 1000 cycles along with an average operating voltage of  $\sim 3.1$  V. Park et al. attributed this exceptional electrochemical performance to preventing structural changes during Na (de)intercalation and facile Na<sup>+</sup> diffusion. Note that the similarity in size between Na<sup>+</sup> and Ca<sup>2+</sup> (116 and 114 pm in an octahedral coordination environment surrounded by O<sup>2-</sup>, respectively [68, 69]) indicates that cathodes with reversible Na-intercalation may hold promise as CB cathodes as well. Thus, fluoride frameworks, specifically with the weberite and perovskite structures, could be potential Ca-cathodes.

In this work, we use DFT-based calculations to systematically explore the chemical space of weberiteand perovskite-type fluorides, with chemical formula of  $Ca_xM_2F_7$  and  $Ca_xMF_3$ , respectively, as potential CB cathodes. Here, M represents a redox active 3d transition metal, including Ti, V, Cr, Mn, Fe, Co, or Ni, while x represents the Ca composition within a range of  $0 \le x \le 1.5$  for weberites and  $0 \le x \le 0.5$  for perovskites. We calculate the ground state structure (including the stable Ca-vacancy arrangement), 0 K thermodynamic stability, average Ca intercalation voltage and  $Ca^{2+}$  migration barriers upon Ca (de)insertion in the weberite and perovskite fluorides. Importantly, our systematic screening identifies  $Ca_xCr_2F_7$  and  $Ca_xMn_2F_7$ weberites as promising cathode candidates for CBs. Our study marks the first extensive exploration of fluoride frameworks as potential intercalation-type Ca-cathode materials, which can hopefully aid in the practical development of energy dense CBs.



Figure 1: The crystal structure of the conventional cell (panel a) and primitive cell (panel b) of orthorhombic weberite, and conventional cell of trigonal weberite (panel c). Green and purple polyhedra indicate  $MF_6$  octahedral for divalent ( $M^{2+}$ ) and trivalent ( $M^{3+}$ ) transition metals, respectively, where oxygen atoms are represented by grey spheres. Orange, and light blue spheres in panel a, b, c indicate Na1 and Na2 sites (equivalent to Ca1 and Ca2 in Ca-based weberites), respectively, and maroon spheres in panel c indicate Na3 sites (equivalent to Ca3). Dashed black lines indicate the extent of the unit cell.

# 2 Results

### 2.1 Structural Features

#### 2.1.1 Weberites

The weberite structure derives its name from the parent compound, namely the mineral Na<sub>2</sub>MgAlF<sub>7</sub>, and typically crystallizes in an orthorhombic structure [70] with a space group of *Imma* (panels a and b of Figure 1). The weberite framework is considered as a type of anion-deficient fluorite superstructure with a general stoichiometry of  $A^{(4a)}A^{(4d)}M^{(4b)}M^{(4c)}F_7^{(4e,8h,16j)}$ . A and A' usually represent Na occupying two different crystallographic sites, represented by orange (Na1 or 4a sites) and blue (Na2 or 4d) spheres in Figure 1a and b. M and M' represent TM cation with a +2 and a +3 oxidation state, respectively, and are represented by green and purple octahedra in Figure 1. Note that the A and A' represent possible sites for Ca occupation in Ca-containing weberites. The conventional cell of the orthorhombic weberite (Figure 1a) consists of four A<sub>2</sub>M<sub>2</sub>F<sub>7</sub> (A = Na/Ca) formula units, with the MF<sub>6</sub> and M'F<sub>6</sub> octahedra sharing corners to form a three-dimensional framework. The primitive cell of the orthorhombic weberite (Figure 1b) has two A<sub>2</sub>M<sub>2</sub>F<sub>7</sub> formula units. The fluorine atoms, which are represented by grey spheres, occupy three different Wykoff positions, namely F1 (4e), F2 (8h) and F3 (16j).

Both Na1 and Na2 sites coordinate with 6+2 with neighboring fluorine atoms, with Na1 exhibiting a hexgonal bipyramidal coordination and Na2 displaying a distorted cubic (or square prism) coordination. While Na1 coordinates with all three types of F sites, Na2 coordinates with only F1 and F2. The Na2 polyhedra are interconnected via edge-sharing, resulting in a series of chains along [100], as shown in **Figure S1a** of the supporting information (SI). On the other hand, the Na1 polyhedra share corners among each other

along [010] (Figure S1b), with the Na1 polyhedra also sharing some of their edges with Na2 polyhedra (Figure S1a). Note that there exists another orthorhombic weberite structure, with space group Pmnb, which is considered to be a modification of the Imma weberite via tilting of the Na1 polyhedra resulting in a set of non-corner-sharing pentagonal bipyramidal polyhedra (Figure S1c). We will not be considering the distorted Pmnb version of the weberite structure further in our work.

Interestingly, the *Imma* weberite framework can be considered as a repeated stacking of slabs made of (011) planes. Each slab consists of two distinct layers, namely  $A_3M$  (A-rich layer) and  $AM_3$  (TM-rich layer), forming an 'AA' stacking sequence, as depicted in **Figure S2a**. In turn, each layer exhibits a Kagome-like network where majority cations (A in  $A_3M$  and M in  $AM_3$ ) form a continuous network, while minority cations occupy the Kagome ring centers as illustrated in **Figure S2b,c**.

In addition to the orthorhombic crystal structure, weberite can exist as a trigonal and a monoclinic polymorph, which differ in their stacking sequence of the Kagome-type layers. [71,72] **Figure 1c** depicts the conventional cell of trigonal weberite of space group  $P3_121$  and consisting of six formula units of  $A_2M_2F_7$ , depicted including the Wyckoff notation as  $A_2^{(6c)}M^{(3a)}M^{\prime\prime(3b)}M^{\prime\prime(6c)}F_7^{(6c)}$ . In trigonal weberites, there are two distinct sites for trivalent cations M/M' sitting at 3a/3b sites (purple polyhedra in Figure 1c), while the divalent cations (M'') sit in 6c sites (green polyhedra). The TM-F polyhedra are connected to each other through corner sharing to form a three-dimensional open framework. There are 3 distinct sub-sites for Na occupation, namely Na1 (orange spheres in Figure 1c), Na2 (half-blue spheres), and Na3 (half-maroon spheres). There are 6 Na sites of each type in the conventional trigonal cell, with the Na2 and Na3 sites being half-occupied in the stoichiometric (i.e.,  $A_2M_2F_7$ ) weberite. All three Na sites in the trigonal structure can be occupied by Ca, and denoted as Ca1, Ca2, and Ca3 sites in the Ca-containing structures.

The Kagome-type stacking in trigonal weberite follows an 'ABCABC' sequence, compared to the AA sequence in orthorhombic weberite, as depicted in **Figure S3a**. The  $A_3M$  layer in trigonal weberite, which is constructed with four half occupied Na2 and four fully occupied Na1 sites forming an octagonal ring with a trivalent TM at the center is shown in **Figure S3b**. The AM<sub>3</sub> layer consists of four divalent and two trivalent TMs forming a hexagonal ring with two half-occupied Na3 sites within the ring, as displayed in **Figure S3c**. For a point of comparison with the orthorhombic structure, the trigonal weberite with stoichiometric Na site occupancy (i.e., containing 2 Na per formula unit) is illustrated in **Figure S4a**, and the corresponding Kagome-type stacking is depicted in **Figure S4b-c**. The distinctions among the A-, B-, and C-type stacking layers lie in the orientation of the TMs and/or the arrangement of Na sites. For instance, Na1 sites are arranged in identical zigzag fashion along the [100], [110], and [010] directions in the A<sub>3</sub>M layer, within the A-, B-, and C-type stacking slabs, respectively (**Figure S4b**). Note that the monoclinic weberite is reported to exist in two different Kagome-type staking sequences, namely ABAB and AABBAABB with both phases crystallizing in the *C2/c* space group. [73] However, we do not include the monoclinic structure in our study since only the orthorhombic and trigonal weberites have demonstrated electrochemical activity in NIBs. [65,67]

For Ca-containing weberites, we generated the corresponding orthorhombic (O-weberite) and trigonal (T-weberite) compositions and structures (i.e.,  $Ca_xM_2F_7$ ) by substituting  $Ca^{2+}$  at the Na<sup>+</sup> sites and utilising a redox-active 3d TM (Ti, V, Cr, Mn, Fe, Co, or Ni) at the M sites. We considered the charged and discharged weberite compositions to be  $M_2F_7$  (TM oxidation state of +3.5) and  $Ca_{1.5}M_2F_7$  (TM oxidation state of +2) to account for charge-neutrality of the overall composition given most TMs can reversibly access oxidation states between +2 and +4 during a redox reaction. [48] We utilised the primitive cell of O-weberite and conventional cell of T-weberite to calculate the the ground state structure at both charged and discharged

| Compositions  | Ca site occupancy |     |     |  |
|---|-------------------|-----|-----|--|
| Compositions  | Ca1               | Ca2 | Ca3 |  |
| $\overline{\mathrm{Ca}_{1.5}\mathrm{Ti}_{2}\mathrm{F}_{7}}$ | 1/3               | 2/3 | 1/2 |  |
| $Ca_{1.5}M_2F_7$ , $M = V$ , $Cr$ , $Co$                    | 1/3               | 2/3 | 1/2 |  |
| $Ca_{1.5}M_2F_7$ , $M = Mn$ , Fe                            | 2/3               | 1/3 | 1/2 |  |
| $Ca_{1.5}Ni_2F_7$   | 1/2               | 1/2 | 1/2 |  |

Table 1: Site occupancy of the Ca1, Ca2, and Ca3 sites in the calculated T-weberite ground states.

compositions.

Based on calculated DFT total energies, we find the O-weberite to be energetically more favorable than the T-weberite at the charged compositions for V, Fe, and Co compounds, while the T-weberite is more favorable for charged Ti, Cr, Mn, and Ni compounds. In the case of discharged weberite compositions, we find the T-weberite structure to be energetically more favorable for all TMs considered. We have compiled the relative energies between O- and T-weberite structures at both the charged and discharged compositions in **Table S2** of the SI. The occupancy of individual Ca sites in the ground state weberite configurations (i.e., T-weberite for discharged compositions), as calculated by DFT, is compiled in **Table 1**, while a schematic of all ground state configurations is compiled in **Figure S5**. Interestingly, at the discharged composition, we find Ca to partially occupy all three crystallographic sites for all TMs, indicating the lack of a strong preference for a specific site. Note that although the Ca occupancies are identical for Ti and V/Cr/Co T-weberites (**Table 1**), the specific Ca-vacancy arrangements are different (**Figure S5**).

#### 2.1.2 Perovskites

Similar to weberites, we consider perovskites of composition,  $Ca_xMF_3$ , obtained by inserting Ca at possible Na sites in prototypical structures. The charged and discharged compositions of Ca-containing perovskites are MF<sub>3</sub> (TM oxidation state of +3), and Ca<sub>0.5</sub>MF<sub>3</sub> (TM oxidation state of +2), respectively, which satisfies the charge neutrality constraint. Note that Na-containing perovskite-type TM fluorides exhibit different polymorphs depending on the TM. For our investigation, we considered three different perovskite polymorphs, namely cubic ( $Pm\bar{3}m$  space group), orthorhombic (Pnma), and triclinic ( $P\bar{1}$ ). While we used the conventional perovskite cell (containing four Ca<sub>x</sub>MF<sub>3</sub> formula units) for calculations involving orthorhombic and trigonal polymorphs, we used a 2 × 2 × 2 supercell (with eight formula units) for the cubic polymorph. The set of perovskite structures we considered, along with the calculated ground state Ca-vacancy configurations are compiled in **Figure S6**.

For each TM, we considered the experimentally known ground state [61] of the corresponding Nacontaining perovskite for creating the corresponding Ca-perovskite structure. For example, we used the cubic and triclinic structures for  $Ca_xVF_3$  and  $Ca_xCrF_3$ , respectively, since the ground states of the corresponding Na-containing perovskites (i.e., NaVF<sub>3</sub> and NaCrF<sub>3</sub>) are cubic [74] and triclinic [75]. Similarly, we used the orthorhombic polymorph for Mn, [76] Fe, [77] Co, [78] and Ni [78] containing perovskites. For the case of  $Ca_xTiF_3$ , we calculated the total energies of the cubic, orthorhombic, and triclinic structure with composition of  $Ca_{0.5}TiF_3$ , as the ground state of the analogous Na-containing composition is unknown. Subsequently, we found the orthorhombic structure to be energetically preferred for Ti-based perovskite (16.7 and 0.1 meV/atom lower than cubic and triclinic, respectively). For each discharged  $Ca_{0.5}MF_3$  polymorph, we constructed the corresponding charged structure by removing all  $Ca^{2+}$  from the discharged structure.



Figure 2: DFT-calculated energy above or below the ground-state convex hull ( $E^{Hull}$ ) for charged and discharged weberites (first two rows), and perovskites (last two rows). Each column corresponds to a specific 3d TM. Blue (red) squares indicate high degrees of stability (instability), with the specific  $E^{Hull}$  value of each composition listed as text annotation within each square. The green line on the legend bar indicates the rule-of-thumb  $E^{Hull} \sim 50 \text{ meV}/\text{atom threshold for experimental synthesizability}.$ 

### 2.2 Thermodynamic Stabilities

Figure 2 presents the 0 K calculated thermodynamic (in)stability, quantified using energy above or below the convex hull ( $E^{Hull}$  [62]), of the charged and discharged weberite (first two rows) and perovskite (last two rows) fluorides, for all TM-containing systems considered. The  $E^{Hull}$  value for each composition is indicated using a text annotation in the corresponding square of Figure 2, where blue (red) squares indicate stable/metastable (unstable) compositions. Note that values of  $E^{Hull} \ge 100 \text{ meV}/\text{atom}$  ( $E^{Hull} \le$ 0 eV/atom) are depicted by fully red (blue) squares. Given that metastable compounds at 0 K can be synthesized under different experimental conditions, we have used a rule-of-thumb synthesizability threshold of  $E^{Hull} \sim 50 \text{ meV}/\text{atom}$ , [79] as indicated by the green line on the legend bar of Figure 2. Typically compositions with  $0 < E^{Hull} \le 50 \text{ meV}/\text{atom}$  are referred to as metastable, while compositions with  $E^{Hull} > 50 \text{ meV}/\text{atom}$  are considered unstable. The 0 K convex hull of all ternary Ca-M-F weberites and perovskites, which comprise of possible all unary, binary, and ternary compositions that are known to exist in addition to the weberites and perovskites considered here, are compiled in Figures S7, S8. The compounds that are 'adjacent' on the convex hull for all weberites and perovskites, i.e., compounds that thermodynamically compete with stable weberites/perovskites for existence and compounds that are the decomposition products of unstable weberites/perovskites, are compiled in Table S3.

We observe that most of the charged compositions of weberites (first row in **Figure 2**) are metastable with  $E^{Hull}$  (in meV/atom) of 13 (Ti<sub>2</sub>F<sub>7</sub>), 11 (V<sub>2</sub>F<sub>7</sub>), 11 (Cr<sub>2</sub>F<sub>7</sub>), 13 (Mn<sub>2</sub>F<sub>7</sub>), and 26 (Ni<sub>2</sub>F<sub>7</sub>), suggesting that these compounds are potentially synthesizable. In contrast, the charged Fe- and Co-weberites are unstable, exhibiting high  $E^{Hull}$  of 114 and 78 meV/atom, respectively. Note that Fe<sub>2</sub>F<sub>7</sub> is thermodynamically driven to decompose into the stable adjacent compounds on the Ca-Fe-F convex hull, namely F<sub>2</sub> and FeF<sub>3</sub> (**Table S3** and **Figure S8**). Similarly, Co<sub>2</sub>F<sub>7</sub> is expected to decompose into F<sub>2</sub> and CoF<sub>3</sub>.

Interestingly, most of the discharged weberites (second row in Figure 2) are stable compounds with large

negative  $E^{Hull}$  (in meV/atom) of -585 (Ca<sub>1.5</sub>V<sub>2</sub>F<sub>7</sub>), -170 (Ca<sub>1.5</sub>Mn<sub>2</sub>F<sub>7</sub>), -95 (Ca<sub>1.5</sub>Fe<sub>2</sub>F<sub>7</sub>), -565 (Ca<sub>1.5</sub>Co<sub>2</sub>F<sub>7</sub>), and -573 (Ca<sub>1.5</sub>Ni<sub>2</sub>F<sub>7</sub>), suggesting that these compositions should be experimentally synthesizable given their large thermodynamic driving force for formation. While discharged Ti-weberite is metastable ( $E^{Hull} \sim 44 \text{ meV}/\text{atom}$ ), the discharged Cr-weberite is marginally unstable ( $E^{Hull} \sim 57 \text{ meV}/\text{atom}$ , marginally higher than our synthesizability threshold). Nevertheless, both Ca<sub>1.5</sub>Ti<sub>2</sub>F<sub>7</sub> and Ca<sub>1.5</sub>Cr<sub>2</sub>F<sub>7</sub> may be experimentally accessible.

In the case of perovskites, most of the charged fluorides lie marginally above the convex hull and are likely synthesizable, including TiF<sub>3</sub>, VF<sub>3</sub>, CrF<sub>3</sub>, FeF<sub>3</sub>, CoF<sub>3</sub> and NiF<sub>3</sub>, with  $E^{Hull}$  (in meV/atom) of 1, 35, 7, 22, 35, and 7, respectively. Note that these charged perovskites are metastable with respect to their corresponding known trigonal trifluoride polymorphs (with space group of  $R\bar{3}cR$ ), as compiled in **Table S3**. [80] The only charged perovskite that is thermodynamically stable at 0 K is MnF<sub>3</sub>, with  $E^{Hull}$  of -4 eV/atom. On the other hand, several discharged perovskites are unstable, with Ca<sub>0.5</sub>TiF<sub>3</sub>, Ca<sub>0.5</sub>CrF<sub>3</sub>, and Ca<sub>0.5</sub>FeF<sub>3</sub> exhibiting large  $E^{Hull}$  values of 97, 110, and 86 meV/atom, respectively. The metastable discharged perovskites include Ca<sub>0.5</sub>VF<sub>3</sub>, Ca<sub>0.5</sub>CoF<sub>3</sub>, and Ca<sub>0.5</sub>NiF<sub>3</sub>, with  $E^{Hull}$  of 7, 20, and 29 meV/atom, respectively. Similar to charged perovskites, the only discharged perovskite composition that is thermodynamically stable is the Mn-version, with  $E^{Hull}$  of -1 meV/atom.

Generally, it is preferable that both the charged and discharged compositions of an intercalation system are thermodynamic stable (or metastable) to prevent undesirable decomposition or conversion reactions. [81] Thus, we identify  $Ca_xMnF_3$  as a potential Ca-cathode, under the constraint of both charged and discharged phases being stable. Given that there are several examples of metastable cathodes that show good electrochemical performance, [82–85] we can use a constraint of both charged and discharged compositions being at most metastable for identification of candidates. In this context, we identify the following compositions to be candidate cathodes for CBs solely based on our 0 K stability calculations, namely,  $Ca_xTi_2F_7$ ,  $Ca_xV_2F_7$ ,  $Ca_xCr_2F_7$ ,  $Ca_xMn_2F_7$ , and  $Ca_xNi_2F_7$  within weberites and  $Ca_xVF_3$ ,  $Ca_xMnF_3$ ,  $Ca_xCoF_3$ , and  $Ca_xNiF_3$ among perovskites. The other compounds that we predict to be stable, such as  $Ca_{1.5}Fe_2F_7$ , and  $Ca_{1.5}Co_2F_7$ , may be relevant for other non-CB applications.

### 2.3 Average Voltages and Theoretical Capacities

The electrochemical performance of a battery system is primarily quantified by its energy density, a metric determined by the voltage and capacity of electrodes utilised. Thus, we calculated the average Caintercalation voltage of the weberites and perovskites considered using DFT. Note that we computed the average voltage and theoretical capacity irrespective of thermodynamic (in)stabilities of all compositions to analyze the overall voltage-capacity trends. The calculated voltages (versus Ca) and gravimetric capacities are summarized in **Table 2**. The theoretical capacities are calculated with reference to the charged compositions, i.e., MF<sub>3</sub> for perovskites and  $M_2F_7$  for weberites. Note that the calculated capacities decrease monotonically from Ti to Ni for both fluoride frameworks, namely from 351 to 320 mAh g<sup>-1</sup> in weberites, and 255 to 231 mAh g<sup>-1</sup> in perovskites, due to the increase in atomic mass from Ti to Ni. Also, the weberites show higher theoretical capacities compared to the perovskites, due to the higher quantity of Ca<sup>2+</sup> (1.5 moles in weberites versus 0.5 moles in perovskites) per formula unit that can be intercalated.

Figure 3 displays the calculated average intercalation voltages (in Volts versus Ca metal) for all fluoride frameworks considered here. O-weberite (orange symbols), T-weberite (purple symbols) and perovskite (green symbols) represent the calculated voltages for a topotactic intercalation within the orthorhombic weberite, trigonal weberite, and perovskite polymorphs, respectively. The average voltage is calculated across the entire Ca content range, i.e.,  $M_2F_7 \leftrightarrow Ca_{1.5}M_2F_7$  for weberites and  $MF_3 \leftrightarrow Ca_{0.5}MF_3$  for perovskites.



Figure 3: Computed average voltage as a function of transition metal, between the fully charged and discharged orthorhombic weberite (O-weberite, represented by orange triangles), trigonal weberite (T-weberite, purple squares) and perovskite (green circles) fluorides.

Table 2: The calculated average intercalation voltage (in Volts versus Ca) and the theoretical gravimetric capacity (in mAh g<sup>-1</sup>) of the weberites and perovskites considered. O-Weberites and T-weberites represent voltages calculated for topotactic intercalation within the orthorhombic and trigonal weberite polymorphs, respectively. The theoretical capacities are computed with respect to the molar mass of  $M_2F_7$  for weberites and MF<sub>3</sub> for perovskites (M = 3*d* TM).

| М                   | Average Voltage (V) |             |             | Theoretical ( | Theoretical Capacity (mAhg <sup>-1</sup> ) |  |
|---------------------|---------------------|-------------|-------------|---------------|--|--|
| 111                 | O-Weberites         | T-Weberites | Perovskites | Weberites     | Perovskites                                |  |
| Ti                  | 2.4                 | 2.5         | 1.7         | 351           | 255  |  |
| V                   | 3.6                 | 3.6         | 2.8         | 342           | 248  |  |
| $\operatorname{Cr}$ | 3.1                 | 3.2         | 1.8         | 339           | 246  |  |
| Mn                  | 4.8                 | 4.7         | 4.2         | 331           | 239  |  |
| Fe                  | 4.5                 | 4.5         | 3.2         | 328           | 237  |  |
| Co                  | 5.5                 | 5.6         | 4.9         | 320           | 231  |  |
| Ni                  | 5.6                 | 5.5         | 5.0         | 320           | 231  |  |

Notably, we predict the Ca intercalation voltage (in V vs. Ca) to be within the range of 2.4 (Ti) – 5.6 (Ni) for O-weberites, 2.5 V (Ti) -5.6 V (Co) for T-weberites, and 1.7 V (Ti) - 5.0 V (Ni) for perovskites. Clearly, the calculated voltages and trends for both O-weberite and T-weberite are similar across the 3d series, suggesting that both polymorphs may exhibit similar Ca intercalation phase behavior. Additionally, both weberites display consistently higher voltages (by at least 0.5 V) than the corresponding perovskites, which predominantly originates from the charge/discharge process accessing higher TM oxidation states in weberites (+3.5) compared to perovskites (+3).

Across the 3*d* series, both weberites and perovskites show similar non-monotonic trends, i.e., the voltages generally increase from Ti to Ni with local minima at Cr and Fe compositions, similar to trends observed in sulfate-NaSICONs for Ca intercalation. [48] In the case of T-weberites, there is a marginal dip in voltage from Co to Ni (by 0.1 V). The likely reason for the local minima in calculated voltages at Cr and Fe is the high stability of the Cr<sup>3+</sup> and Fe<sup>3+</sup> oxidation states, which are accessed as Ca is deintercalated. Note that Cr<sup>3+</sup> and Fe<sup>3+</sup> are stable due to their high-spin half-filled  $t_{2g}^3$  and half-filled *d* shell ( $t_{2g}^3 e_g^2$ ) electronic

configurations, respectively. [86,87]

In addition to the topotactic voltage, we calculated the non-topotactic average voltage for select weberites that exhibit different ground state polymorphs in their charged and discharged states. For instance, the ground state of charged weberites  $V_2F_7$ ,  $Fe_2F_7$ ,  $Co_2F_7$  are orthorhombic, while the ground state of their corresponding discharged weberites ( $Ca_{1.5}V_2F_7$ ,  $Ca_{1.5}Fe_2F_7$ ,  $Ca_{1.5}Co_2F_7$ ) are the trigonal. Hence, we calculated the average voltage of V-, Fe-, and Co-based weberites between a charged orthorhombic and a discharged trigonal structure, resulting in values of 3.6, 4.5, 5.5 V vs. Ca, respectively. Importantly, the computed non-topotactic voltages are similar to the corresponding topotactic voltages (<0.1 V difference), suggesting insignifcant driving force for any phase transition between the trigonal and orthorhombic structures during Ca (de)intercalation. The similarity between the non-topotactic and topotactic voltages can also be rationalised via the 'small' differences in the DFT-calculated total energies between the orthorhombic and trigonal structures for all TMs (see **Table S2**). Given the marginal thermodynamic driving force for a phase transition between orthorhombic and trigonal weberites during Ca (de)intercalation, we expect the topotactic pathway to be active under electrochemical conditions. Therefore, we take into account topotactic Ca (de)intercalation in the trigonal weberite for further discussions in this manuscript, given the trigonal structure is energetically preferred at the  $Ca_{1.5}M_2F_7$  composition for all TMs considered.

Given the lower voltages with Ti-based weberites and perovskites, and the Cr-perovskite ( $\leq 2.5$  V), these compositions are better suited for anode applications, while the high voltages of Co- and Ni-based fluorides (>5 V) may be beyond the stability limits of available Ca-electrolytes. Despite this concern, it may be possible to operate the Co and Ni fluorides at a reduced voltage by extracting a lower amount of Ca from the cathode, albeit reducing the energy density. For example, the calculated voltage of 4.5 V for Fe<sub>2</sub>F<sub>7</sub>  $\leftrightarrow$ Ca<sub>1.5</sub>Fe<sub>2</sub>F<sub>7</sub> decreases to 3.4 V when considering Ca<sub>0.5</sub>Fe<sub>2</sub>F<sub>7</sub>  $\leftrightarrow$  Ca<sub>1.5</sub>Fe<sub>2</sub>F<sub>7</sub>, where only one mole of Ca is extracted per weberite formula unit. Thus, all weberites except Ti and all perovskites except Ti and Cr are candidate CB cathodes, based solely on our voltage calculations.

However, including both voltage and stability data reduces the set of possible candidates. For example, the low voltages of Ti- and Cr-perovskites may appear to be suitable for anode applications, but the high thermodynamic instability of the discharged Ti- and Cr-perovskites ( $E^{Hull}>95 \text{ meV}/\text{atom}$ , **Figure 2**) may impede any practical deployment. Similarly, Fe-based weberites and perovskites are constrained by high instabilities of the charged and discharged compositions, respectively. In contrast, Mn-weberite, Mn-perovskite, and Ni-weberite are highly promising both due to their high voltages (>4 V) and thermodynamic (meta)stabilities. Thus, combining our voltage and stability data, we identify weberites containing Ti, V, Cr, Mn, and Ni, and perovskites containing V, Mn, Co, and Ni to be suitable for CB electrode applications. Nevertheless, the practical feasibility of any of these identified materials to function as a CB electrode depends on their corresponding bulk Ca<sup>2+</sup> diffusivities (*vide infra*).

#### 2.4 Migration Barriers

Typically, the mobility of  $Ca^{2+}$  in solids is lower compared to monovalent active ions, such as Li<sup>+</sup>, and Na<sup>+</sup>, due to the strong electrostatic interaction of the divalent  $Ca^{2+}$  with the neighboring anions while migrating through a host framework. [20] Subsequently, we computed the migration barriers ( $E_m$ ) of  $Ca^{2+}$  using the nudged elastic band (NEB [88,89]) framework and the generalized gradient approximation (GGA [90]) exchange-correlation functional in the five weberite and four perovskite candidates that we had shortlisted based on our voltage and stability calculations. Note that the diffusivity of  $Ca^{2+}$  depends exponentially on  $E_m$ , via the well-known Arrhenius relationship. [91]



Figure 4: Calculated  $Ca^{2+} E_m$  in the Ti-, V-, Cr-, Mn-, and Ni-weberite frameworks, indicated as text annotations. In each weberite structure, we calculated the  $E_m$  across three different migration pathways, namely Path1 (top row), Path2 (middle row), and Path3 (bottom row). Bottom and top triangles within each square indicate high (charged state) and low (discharged) Ca-vacancy concentrations. Green line on the legend bar indicates the tolerance limit on  $E_m$  (~1000 meV) for enabling  $Ca_{2+}$  diffusion. Due to convergence difficulties, we are unable to calculate a  $E_m$  for V<sub>2</sub>F<sub>7</sub> along Path3 (solid black line).

Table 3: Calculated  $Ca^{2+} E_m$  in perovskites considered, at charged and discharged states. Solid lines represent absence of reliable  $E_m$  for MnF<sub>3</sub> and Ca<sub>0.5</sub>CoF<sub>3</sub> due to convergence difficulties.

| Compounds                      | Migration energy (meV) |            |  |
|--------------------------------|------------------------|------------|--|
|                                | Charged                | Discharged |  |
| $\overline{\mathrm{Ca_xVF}_3}$ | 2875                   | 1832       |  |
| $Ca_{x}MnF_{3}$                |                        | 1980       |  |
| $Ca_{x}CoF_{3}$                | 1666                   |            |  |
| $\mathrm{Ca_xNiF_3}$           | 2445                   | 2120       |  |

Figure 4 depicts the calculated  $E_m$  in weberites across three different migration pathways, namely Path1 (top row), Path2 (middle row) and Path3 (bottom row) at the charged (bottom triangles) and discharged (top triangles) compositions. The individual pathways are depicted in Figure 5, wherein any of the three pathways can facilitate macroscopic  $Ca^{2+}$  diffusion within the three-dimensional trigonal weberite framework. The green line on the legend bar indicates the tolerance limit of ~1000 meV for the  $E_m$ , which corresponds to maintaining a reasonable electrochemical rate performance in a potential Ca-cathode. [48] A brown (purple) triangle in Figure 4 represents a low (high)  $E_m$  thereby indicating a facile (poor)  $Ca^{2+}$  migration. The calculated  $E_m$  in perovskites are compiled in Table 3. Due to convergence difficulties with our NEB calculations, we are unable to provide an accurate  $E_m$  for the charged  $Ca_xV_2F_7$  weberite along Path3 (solid black line). The minimum energy pathways for all weberite and perovskite structures are presented in Figure S9 and S10 of the SI, respectively.

Unsurprisingly, our calculations predict fairly high  $Ca^{2+} E_m$  for most of the weberites considered. For instance, the  $E_m$  across all three paths in  $Ca_xV_2F_7$ , at both the charged and discharged compositions are above the 1000 meV threshold, suggesting that the V-weberite is likely infeasible to be used as a CB cathode. In the case of Ti-weberite, the  $E_m$  along Path1, Path2, and Path3 are within a wide range of 641 to 1929 meV. Particularly, the  $E_m$  of the charged  $Ca_xTi_2F_7$  along Path2 (641 meV) and Path3 (880 meV), are well within the tolerance limit. However, the  $E_m$  at the discharged limit are above the 1000 meV tolerance for all three paths in the discharged  $Ca_xTi_2F_7$  weberite, suggesting limitations with using the Ti-weberite as a CB anode. Similarly, the Ni-weberite shows reasonable  $E_m$  in its charged state along Path1 (881 meV) and Path2 (1042 meV), but the  $E_m$  is above the 1000 meV tolerance in the discharged state of the Ni-weberite for all pathways, making it unsuitable as a CB cathode.

In the case of Cr- and Mn-weberites, we find at least one pathway within the corresponding structures that can facilitate  $Ca^{2+}$  diffusion. For instance, the  $E_m$  in  $Ca_xCr_2F_7$  exceeds the 1000 meV threshold along both Path1 (842-1376 meV) and Path3 (1238-1992 meV), suggesting the unavailability of these pathways for  $Ca^{2+}$  motion. However, the  $E_m$  along Path2 is in the range of 877-1052 meV, which is only marginally above the 1000 meV tolerance, suggesting that Path2 may be open for  $Ca^{2+}$  diffusion within the Cr-weberite. Considering the ground-state Ca-vacancy configuration of  $Ca_{1.5}Cr_2F_7$  trigonal weberite (**Figure S5d**), the fact that only Path2 remains open for  $Ca^{2+}$  diffusion possibly limits the amount of Ca that can be reversibly exchanged with the weberite structure to 0.83 moles per formula unit, corresponding to a capacity of ~164 mAhg<sup>-1</sup>, instead of the full 1.5 moles of Ca (~339 mAhg<sup>-1</sup>).

In the Mn-weberite, the  $E_m$  along both Path1 (1025-1045 meV) and Path2 (1020-1051 meV) are only marginally above the threshold, suggesting the feasibility of Ca<sup>2+</sup> migration along both paths. However, Path3 is likely closed for Ca<sup>2+</sup> motion in the Mn-weberite, since the  $E_m$  in the charged state (1810 meV) is significantly above the threshold despite the low  $E_m$  in the discharged state (704 meV). Given that two out of three pathways are active for Ca<sup>2+</sup> motion in the Mn-weberite, based on the Ca-vacancy ground state configuration of Ca<sub>1.5</sub>Mn<sub>2</sub>F<sub>7</sub> (**Figure S5g**), we conclude that the amount of Ca that can be reversibly exchanged is 1 mole per formula unit, corresponding to a capacity of ~212 mAhg<sup>-1</sup>) instead of the maximum of 1.5 moles (~331 mAhg<sup>-1</sup>). Thus, we find both Cr-, and Mn-based weberites to be feasible to be used as CB cathodes, based on our combined set of thermodynamic stability, voltage, and Ca-mobility calculations.

With respect to perovskites, we find that the calculated  $E_m$  in the V-, Mn-, Co-, and Ni-based fluorides are all significantly above the 1000 meV threshold, namely 1832-2875 meV, 1980 meV, 1666 meV, and 2120-2455 meV. Therefore, despite their promising thermodynamic stability, average voltage, and theoretical capacity, we don't expect any of the perovskite fluorides to be CB cathode candidates due to their prohibitive  $Ca^{2+}_{x} E_{m}$ . Note that we are unable to obtain reliable  $E_{m}$  values for charged  $Ca_{x}MnF_{3}$  and discharged  $Ca_{x}CoF_{3}$  compositions, due to convergence difficulties, but we do not expect any  $E_{m}$  that is eventually calculated for these compositions to change our conclusions.

### 3 Discussion

In this work, we used DFT-based calculations to explore the chemical space of 3d TM-containing weberite and perovskite fluoride frameworks as potential intercalation cathodes for CBs. Specifically, we calculated the ground state Ca-vacancy configurations, 0 K thermodynamic stabilities, average intercalation voltages, theoretical capacities, and Ca<sup>2+</sup> E<sub>m</sub> in several weberite and perovskite fluorides. We considered compositions of Ca<sub>x</sub>M<sub>2</sub>F<sub>7</sub> for weberites (with  $0 \le x \le 1.5$ ), and Ca<sub>x</sub>MF<sub>3</sub> for perovskites (with  $0 \le x \le 0.5$ ), where M = Ti, V, Cr, Mn, Fe, Co, or Ni. Besides obtaining several qualitative trends in stabilities, voltages, and Ca<sup>2+</sup> mobilities, we identify two weberite frameworks, namely Cr- and Mn-based compositions, to be promising Ca-cathodes.

While we employed the SCAN+U functional for average voltage and thermodynamic stability calculations, we chose GGA for  $E_m$  calculations, due to lower computational costs, better numerical convergence, and reliability in providing qualitative trends compared to SCAN. [92] For calculating the  $E_m$  in  $Ca_{1.5}V_2F_7$ along Path3 and  $Cr_2F_7$  along Path2, we initialized our NEB with five instead of the typical seven images since we experienced convergence difficulties with seven images. Further, in  $Mn_2F_7$  (along Path2),  $Ni_2F_7$  (all paths),  $Ca_{0.5}VF_3$  and  $MnF_3$  we used a higher spring force constant of 10 eV/Å between images than the usual value of 5 eV/Å to mitigate convergence difficulties. Note that the  $E_m$  usually does not change significantly with varying the spring force constant, as demonstrated by our calculations in the discharged  $Ca_xNi_2F_7$ system, which displays near-identical  $E_m$  of 2190 and 2189 meV (along Path3) using force constants of 5 and 10 eV/Å, respectively.

Recently, Long et al., demonstrated that SCAN+U exhibits good qualitative trends in average voltages, but tends to overestimate the absolute voltage values and also the thermodynamic instabilities in Li-ion cathodes. [93] We expect similar overestimation of voltages and instabilities to extend to fluoride Ca-cathodes as well, which is why we used a slightly higher  $E^{Hull}$  stabilization threshold (~50 meV/atom) compared to previous studies (~25 meV/atom). Nevertheless, the majority of the fluorides considered here (~57%) exhibit  $E^{Hull}$  lower than 25 meV/atom, suggesting that these fluorides should be synthesizable experimentally.

In terms of structures considered for the fluorides, we included orthorhombic and trigonal polymorphs for weberites and cubic, orthorhombic, and triclinic polymorphs for perovskites. The choice of the polymorphs for both weberites and perovskites was largely motivated by experimental and/or electrochemical observations in the Na-systems. Another constraint influencing the choice of polymorphs is the computational cost of considering different combinations of TMs and Ca-vacancy arrangements in each structure. For instance, perovskites in general can exist in tetragonal, rhombohedral, hexagonal, and monoclinic polymorphs as well, [62] which were not considered as possible structures here. While we hope to extend our Ca-cathode search space to other possible polymorphs in the fluoride chemical space in the future, we are optimistic that our search strategy and identification of candidates in this work are quite useful.

Although Fe-based fluoride weberite exhibits attractive electrochemical performance as a NIB cathode, [67] we do not find the Fe-based weberite to be a feasible candidate for CB, largely due to the instability of the charged (Fe<sub>2</sub>F<sub>7</sub>) phase, which exhibits a high  $E^{Hull}$  of 114 meV/atom. The instability of the Fe<sub>2</sub>F<sub>7</sub> composition can be rationalised based on the instability of the 4+ oxidation state of Fe. Hence, we explored the stability of the charged Fe-weberite state with Ca already present in it such that the 4+ oxidation state is not accessed, i.e., a charged composition of  $Ca_{0.5}Fe_2F_7$ . Although the  $E^{Hull}$  reduces to 71 meV/atom with increasing Ca content in the charged state, the  $Ca_{0.5}Fe_2F_7$  phase remains above the stability threshold of ~50 meV/atom, highlighting the instability of Fe-weberite even with introduction of significant residual Ca content in the structure.

Given the electrochemical accessibility of the charged phase, NaFe<sub>2</sub>F<sub>7</sub> in NIBs, and the stability of the discharged phase, Ca<sub>1.5</sub>Fe<sub>2</sub>F<sub>7</sub>, in the Ca-Fe-F ternary space, insertion of Na within the Fe-weberite as a 'stuffing' cation may stabilize Ca-deficient compositions and enable electrochemical exchange of Ca. This is similar to the role that Na plays in the exchange of Ca in V-based NaSICON electrodes. [52] Also, we predict a drop in average Ca (de)intercalation voltage from 4.5 V in the Fe<sub>2</sub>F<sub>7</sub>  $\leftrightarrow$  Ca<sub>1.5</sub>Fe<sub>2</sub>F<sub>7</sub> range to 3.4 V in the Ca<sub>0.5</sub>Fe<sub>2</sub>F<sub>7</sub>  $\leftrightarrow$  Ca<sub>1.5</sub>Fe<sub>2</sub>F<sub>7</sub> range, which should be in line with stability windows of existing Ca electrolytes. Thus, systems containing residual Na and/or Ca in the weberite structure may be worth exploring both computationally and experimentally.

One strategy to further explore for designing CB cathodes utilising fluoride frameworks is to explore oxyfluoride compositions, i.e., substitution of  $O^{2-}$  on F<sup>-</sup> sites. Introducing a mixed anion system unlocks the potential for voltage modulation and fine-tuning other properties (such as phase behavior). Also, substituting O at F sites will likely increase the theoretical concentration of Ca<sup>2+</sup> that can be accommodated in a weberite structure and potentially lower the E<sub>m</sub> due to slightly weaker Ca-O ionic bonds than Ca-F. Another strategy is to utilise weberite structures with multiple TMs present, similar to prior studies on Na-based weberites. [64, 94, 95] For instance, Ni addition to the Cr-weberite, which is a candidate identified in this work, could enhance the voltage and mitigate E<sub>m</sub> of Ca<sup>2+</sup> since the Ni-weberite exhibits high voltage and reasonable E<sub>m</sub> along Path1 and Path2 at the charged limit.

# 4 Conclusion

As an alternative to the state-of-the-art LIBs, Ca-based electrochemical systems are a promising pathway to develop batteries with high energy density, safety, and lower cost. However, the development of practical CBs so far has been limited by the lack of suitable cathodes. Hence, we have used DFT-based calculations to systematically explore TMFs exhibiting weberite and perovskite structures, as potential CB cathodes. Specifically, we evaluated key metrics, such as thermodynamic stabilities, average Ca-intercalation voltages. theoretical capacities, and  $Ca^{2+}$  migration barriers, across weberites of composition  $Ca_x M_2 F_7$  and perovskites of composition Ca<sub>x</sub>MF<sub>3</sub>, where M = Ti, V, Cr, Mn, Fe, Co, or Ni. Notably, we predict a majority of the TMFs to be stable/metastable at 0 K, indicating the potential synthesizability of the TMFs considered. Our calculated average voltages exhibit higher values in weberites than perovskites, since we access higher TM oxidation states in the weberite (up to 4+) compared to perovskies (3+). Combining our stability and voltage data, we shortlisted Ti, V, Cr, Mn, and Ni weberites, and V, Mn, Co, and Ni perovskites for Camobility evaluation. Subsequently, our  $E_m$  calculations indicate potential for trigonal weberites,  $Ca_x Cr_2 F_7$ and  $Ca_x Mn_2 F_7$ , to be candidate CB cathodes, while none of the perovskites can facilitate Ca diffusion under reasonable electrochemical conditions. We hope that our work will inspire further computational and experimental efforts into the usage of TMFs for CB cathodes, eventually resulting in the practical deployment of CBs.

### 5 Methods

### 5.1 First Principles Calculations

We used spin-polarized DFT [50,51]) and projector augmented wave (PAW [96,97]) potentials, as implemented in the Vienna *ab initio* Simulation Package (VASP [98,99]) in all our calculations. The list of PAW potentials used in our calculations are compiled in **Table S1** of the SI. We described the valence electrons using a plane-wave basis, expanded up to a kinetic energy cutoff of 520 eV. We employed  $\Gamma$ -point-centered, Monkhorst-Pack [100] *k*-point meshes with a minimum of 48 subdivisions along each unit reciprocal lattice vector for geometry relaxations and a Gaussian smearing (of 0.05 eV) to integrate the Fermi surface. We used a Hubbard *U* corrected strongly constrained and appropriately normed (i.e., SCAN+*U* [101–105]) functional to describe the electronic exchange and correlation. We used *U* values of (in eV) 4.5 (Ti), 4.2 (V), 1.5 (Cr), 3.8 (Mn), 5.6 (Fe), and 4.0 (Co), as derived in our previous work. [80] We utilised total energy and force convergence criteria of 10<sup>-5</sup> eV and |0.03| eV/Å. For all structure relaxations, we relaxed the cell shape, volume, and ionic positions, without preserving any underlying symmetry.

### 5.2 Structure Generation

We have generated crystal structures for weberites and perovskites considered in this work by including the constraint of charge neutrality. Note that stable ionic crystals are typically charge neutral. In intercalation systems that contain 3d TMs, the oxidation state of the TM sets the limits on the content of the intercalant ion within the structure. Given that 3d TMs can reversibly change their oxidation states from +4 to +2 during (de)intercalation, the Ca content corresponding to a +4 (+2) oxidation state represents the charged (discharged) composition of the structure. For example, the highest oxidation state that a TM can acquire in a weberite is +3.5, corresponding to a composition of  $Ca_0M_2F_7$ , which in turn represents the charged state. Similarly, the lowest (+2) oxidation state that a TM can exhibit in a weberite is at a composition of  $Ca_{1.5}M_2F_7$ , which represents the discharged state. In the case of perovskites, MF<sub>3</sub> (M<sup>3+</sup>), and  $Ca_{0.5}MF3$  (M<sup>2+</sup>) represent the charged and discharged compositions, respectively. Thus, the maximum amount of Ca that can be exchanged per formula unit of weberite and perovskite is 1.5 and 0.5 moles, which is the value we have used in our theoretical capacity calculations of **Table 2**.

To generate structures for our DFT calculations, we obtained starting configurations from the international crystal structure database (ICSD [106]). Specifically, we used the conventional cell of Na<sub>2</sub>Fe<sub>2</sub>F<sub>7</sub> [67] as a template for trigonal weberites, while we employed the primitive cell of Na<sub>2</sub>NiFeF<sub>7</sub> [107] as a template for orthorhombic weberites. We substituted Fe/Ni cites in our template structures with the relevant 3dTM, while Na sites were substituted with Ca. After performing elemental substitutions, we scaled the lattice parameters of the theoretically generated structures using the "RLSVolumePredictor" [108] class of the pymatgen package. [109] Subsequently, we used the "enumlib" library [110–113] to generate symmetrically distinct Ca-vacancy arrangements within each structure. In total, we generated 70 trigonal-Ca<sub>1.5</sub>M<sub>2</sub>F<sub>7</sub> (10 per TM), 7 trigonal-M<sub>2</sub>F<sub>7</sub> (one per TM), 14 orthorhombic-Ca<sub>1.5</sub>M<sub>2</sub>F<sub>7</sub> (2 per TM), and 7 orthorhombic-M<sub>2</sub>F<sub>7</sub> (one per TM) Ca-vacancy weberite configurations.

Similar to weberites, we followed the elemental substitution, lattice parameter scaling, and Ca-vacancy ordering enumeration to generate Ca-containing fluoride perovskites. In total, we generated 35 configurations for  $Ca_{0.5}MF_3$  compositions, including 13 for Ti, 6 for V, 4 for Cr, and 3 each for Mn, Fe, Co, and Ni and 7 MF<sub>3</sub> (one per TM) configurations. Note that the discharged phase of perovskites exhibit different number

of distinct Ca-vacancy configurations depending on the crystal structure. For instance, the orthorhombic  $Ca_{0.5}MF_3$  perovskite with (M = Ti, Mn, Fe, Co, or Ni) exhibits three possible Ca-vacancy configurations, while the cubic and triclinic versions exhibit six and four distinct configurations, respectively. We obtained a total of 13  $Ca_{0.5}TiF_3$  configurations since we considered all three polymorphs (i.e., cubic, orthorhombic, and triclinic) for identifying the ground state configuration of the Ti-perovskite.

#### 5.3 Average Voltage Calculations

In a reversible intercalation battery, where  $Ca^{2+}$  is inserted/extracted into/from a cathode material of composition  $Ca_yM_2F_7$  (in a weberite structure) or  $Ca_yMF_3$  (in a perovskite structure), the overall redox reaction can be expressed as Eq. 1 and Eq. 2, respectively.

$$\operatorname{Ca}_{y} \operatorname{M}_{2} \operatorname{F}_{7} + (x - y) \operatorname{Ca}^{2+} + 2 (x - y) \operatorname{e}^{-} \rightleftharpoons \operatorname{Ca}_{x} \operatorname{M}_{2} \operatorname{F}_{7}$$
(1)

$$\operatorname{Ca}_{y}\operatorname{MF}_{3} + (x-y)\operatorname{Ca}^{2+} + 2(x-y)e^{-} \rightleftharpoons \operatorname{Ca}_{x}\operatorname{MF}_{3}$$
 (2)

y and x are the concentrations of Ca in the charged and discharged weberite or perovskite fluorides, respectively. The average intercalation voltage for a given cathode material upon intercalation of (y-x) moles of Ca can be calculated using the Nernst equation (Eq. 3), as below. [114]

$$\langle V \rangle = -\frac{\Delta G}{2(x-y)F}$$

$$\approx -\frac{E(\operatorname{Ca_x M_2 F_7 / Ca_x MF_3}) - [E(\operatorname{Ca_y M_2 F_7 / Ca_y MF_3}) + (x-y)\mu_{\operatorname{Ca}}]}{2(x-y)F}$$
(3)

 $\Delta G$  is the Gibbs energy change of the redox reaction, which is approximated as the total energy calculated using DFT ( $\Delta G \approx \Delta E$ ), ignoring the p - V and entropic contributions. F in Eq. 3 is the Faraday constant and  $\mu_{Ca}$  is the Ca chemical potential in pure Ca metal (i.e., in its ground state face-centered-cubic structure).

#### 5.4 Ab initio Thermodynamics

The 0 K thermodynamic stability of the weberite and perovskite fluorides considered were evaluated with respect to the corresponding elemental, binary, and ternary compounds, as obtained from the ICSD, followed by DFT total energy calculations. For estimating stability, we exclusively considered only ordered structures that are available in the ICSD, to reduce computational complexity. In addition to the ICSD compounds, we included the theoretically obtained weberite (perovskite) compositions for estimating the stability of perovskite (weberite) compositions, since both weberites and perovskites occupy the same Ca-TM-F ternary chemical space. We used the pymatgen [109] package to construct the 0 K convex hull and calculate the  $E^{Hull}$  for all Ca-TM-F ternary systems. Note that we used the SCAN functional without any U corrections for total energy calculations of all unary systems (i.e., Ca, TMs, and F<sub>2</sub>).

### 5.5 Migration Barrier Calculations

We used DFT-based NEB [88,89] to evaluate the  $Ca^{2+} E_m$  in select weberite and perovskite fluorides. We used the GGA exchange-correlation functional instead of SCAN/SCAN+U to calculate  $E_m$  to minimize



Figure 5:  $Ca^{2+}$  migration pathways in trigonal weberite, including Path1, Path2 (panel a), and Path3 (panels b and c). Purple polyhedra indicate MF<sub>6</sub> octahedra and F atoms are represented by grey spheres. Orange, and light blue spheres in panel a, b, c indicate Ca1 and Ca2 sites, respectively, while maroon spheres in panel b and c indicate Ca3 sites.

computational costs and mitigate convergence difficulties. [92] For all structures, we calculated  $E_m$  at both the charged (low Ca concentration) and the discharged (high Ca concentration) states. We considered a vacancy-mediated Ca<sup>2+</sup> migration mechanism in all structures. We converged the atomic forces to |0.03|eV/Å within the endpoint structures of each NEB. Subsequently, we initialized the minimum energy path (MEP) of the NEB calculation by linearly interpolating the lattice vectors and atomic positions to create seven intermediate images between the endpoints, with a spring constant of 5 eV/Å between images. For select structures, we used five intermediate images and/or a spring constant of 10 eV/Å (see Section 3). We sampled the irreducible Brillouin zone of all endpoint and NEB calculations with  $\Gamma$ -centered Monkhorst-Pack [100] k-point meshes with a minimum of 32 sub-divisions across each unit reciprocal lattice vector. The NEB calculations were converged until the perpendicular component of the band force between images reduced to < |0.05| eV/Å.

Within the trigonal weberite, we identified three possible  $Ca^{2+}$  migration pathways with distinct local environments, namely Path1 (Ca1-Ca1), Path2 (Ca2-Ca1), and Path3 (Ca3-Ca1), as depicted in **Figure 5**. The same pathways for Na<sup>+</sup> migration were explored by Lu et al. [94] in a recent study. Note that the Na arrangement along the B-type slab (within the ABCABC stacking sequence) is equivalent to the Na arrangement in the A- and C-type slabs, but along different directions. Therefore, the type of paths considered change their direction depending on the type of slab considered. For example, Path1 is along the *a*-axis or [100] direction in the A<sub>3</sub>M layer of the B-type slab, which is analogous to Path1 along the [110] direction in the A-type and [010] direction in the C-type slabs.

Notably, Path1 and Path2 migration pathways lie on the a-b plane (across all A-, B-, and C-type slabs) allowing accessibility of Ca<sup>2+</sup> at the Ca1 and Ca2 sites (within the A<sub>3</sub>M layers), as shown in **Figure 5a**. Specifically, all the Ca1 sites can be accessed through Path 1, while the Ca at Ca2 sites can be accessed through Path2. The Ca<sup>2+</sup> at Ca3 sites on the AM<sub>3</sub> layer can migrate along Path3, if both E<sub>m</sub> from Ca3 to Ca1 and Ca3 to Ca2 are reasonable. Note that the Ca1-Ca3-Ca2 chains along the *c*-axis are connected via Path3, which is independent of Path1 and Path2. In case only one E<sub>m</sub>, i.e., Ca3-Ca1 or Ca3-Ca2, is reasonable, Ca<sup>2+</sup> at Ca3 sites can migrate to available Ca1 or Ca2 sites on the A<sub>3</sub>M layer, and subsequently use Path1 or Path2 for macroscopic diffusion. However, Lu et al. [94] have shown that the MEP and E<sub>m</sub> for a Na hop from Na3 to Na1 sites are similar to a Na hop from Na3 to Na2 sites. Given the similarity between the migration paths from Na3 (Ca3) to Na1 (Ca1) and Na2 (Ca2) sites, we evaluated the  $E_m$  for Ca<sup>2+</sup> migration from Ca3 to Ca1 sites along Path3 (see panels b and c of **Figure 5**). Thus, depending upon the magnitude of  $E_m$ , we can conclude that either Path3 will be fully open or fully closed to Ca-diffusion.

# Acknowledgments

G.S.G. acknowledges financial support from the Indian Institute of Science (IISc) and support from the Science and Engineering Research Board (SERB) of Government of India, under Sanction Numbers SRG/2021/000201 and IPA/2021/000007. D.B.T. acknowledges financial support from Indian Institute of Science. The authors acknowledge the computational resources provided by the Supercomputer Education and Research Centre (SERC), IISc. A portion of the calculations in this work used computational resources of the supercomputer Fugaku provided by RIKEN through the HPCI System Research Project (Project ID hp220393). We acknowledge National Supercomputing Mission (NSM) for providing computing resources of 'PARAM Siddhi-AI', under National PARAM Supercomputing Facility (NPSF), C-DAC, Pune, and the resources of 'Param Utkarsh' at CDAC Knowledge Park, Bengaluru. Both PARAM Siddhi-AI and PARAM Utkarsh are implemented by CDAC and supported by the Ministry of Electronics and Information Technology (MeitY) and Department of Science and Technology (DST), Government of India. The authors gratefully acknowledge the computing time provided to them on the high-performance computer noctual and noctua2 at the NHR Center PC2. This was funded by the Federal Ministry of Education and Research and the state governments participating on the basis of the resolutions of the GWK for the national high-performance computing at universities (www.nhr-verein.de/unsere-partner). The computations for this research were performed using computing resources under project hpc-prf-emdft.

#### Author Contributions

GSG: Conceptualization, Supervision, Methodology, Writing, and Editing. DBT: Data generation and curation, Visualization, Writing, and Editing.

#### **Conflicts of Interest**

There are no conflicts to declare.

# Supplementary Materials

Electronic Supporting Information is available online at , Projector augmented wave potentials used, structural features of orthorhombic and trigonal weberites, ground state Ca-vacancy configurations in both weberites and perovskites, 0 K phase diagrams, and minimum energy pathways of  $Ca^{2+}$  migration in select structures.

# References

[1] Noorden R Van. The rechargeable revolution: A better battery. Nature, 507(7490):26-28, 2014.

- [2] M Stanley Whittingham. Ultimate limits to intercalation reactions for lithium batteries. *Chemical Reviews*, 114(23):11414–11443, 2014.
- Björn Nykvist and Måns Nilsson. Rapidly falling costs of battery packs for electric vehicles. Nature Climate Change, 5(4):329–332, 2015.
- [4] Jean-Marie Tarascon. Is lithium the new gold? Nature Chemistry, 2(6):510–510, 2010.
- [5] Dominique Larcher and Jean-Marie Tarascon. Towards greener and more sustainable batteries for electrical energy storage. *Nature Chemistry*, 7(1):19–29, 2015.
- [6] Zachary P Cano, Dustin Banham, Siyu Ye, Andreas Hintennach, Jun Lu, Michael Fowler, and Zhongwei Chen. Batteries and fuel cells for emerging electric vehicle markets. *Nature Energy*, 3(4):279–289, 2018.
- [7] Elsa A Olivetti, Gerbrand Ceder, Gabrielle G Gaustad, and Xinkai Fu. Lithium-ion battery supply chain considerations: analysis of potential bottlenecks in critical metals. *Joule*, 1(2):229–243, 2017.
- [8] Pieremanuele Canepa, Gopalakrishnan Sai Gautam, Daniel C Hannah, Rahul Malik, Miao Liu, Kevin G Gallagher, Kristin A Persson, and Gerbrand Ceder. Odyssey of multivalent cathode materials: open questions and future challenges. *Chemical Reviews*, 117(5):4287–4341, 2017.
- [9] M Rosa Palacin, Patrik Johansson, Robert Dominko, Ben Dlugatch, Doron Aurbach, Zhenyou Li, Maximilian Fichtner, Olivera Lužanin, Jan Bitenc, Zhixuan Wei, et al. Roadmap on multivalent batteries. Journal of Physics: Energy, 2024.
- [10] Alexandre Ponrouch, Jan Bitenc, Robert Dominko, Niklas Lindahl, Patrik Johansson, and M Rosa Palacín. Multivalent rechargeable batteries. *Energy Storage Materials*, 20:253–262, 2019.
- [11] M Elena Arroyo-de Dompablo, Alexandre Ponrouch, Patrik Johansson, and M Rosa Palacín. Achievements, challenges, and prospects of calcium batteries. *Chemical Reviews*, 120(14):6331–6357, 2019.
- [12] Alexandre Ponrouch, Carlos Frontera, Fanny Bardé, and M Rosa Palacín. Towards a calcium-based rechargeable battery. *Nature Materials*, 15(2):169–172, 2016.
- [13] Rosalind J Gummow, George Vamvounis, M Bobby Kannan, and Yinghe He. Calcium-ion batteries: current state-of-the-art and future perspectives. Advanced Materials, 30(39):1801702, 2018.
- [14] Hans E Suess and Harold C Urey. Abundances of the elements. *Reviews of Modern Physics*, 28(1):53, 1956.
- [15] Damien Monti, Alexandre Ponrouch, Rafael B Araujo, Fanny Barde, Patrik Johansson, and M Rosa Palacín. Multivalent batteries—prospects for high energy density: Ca batteries. Frontiers in Chemistry, 7:79, 2019.
- [16] Da Wang, Xiangwen Gao, Yuhui Chen, Liyu Jin, Christian Kuss, and Peter G. Bruce. Plating and stripping calcium in an organic electrolyte. *Nature Materials*, 17(1):16–20, 2018.
- [17] Zhenyou Li, Olaf Fuhr, Maximilian Fichtner, and Zhirong Zhao-Karger. Towards stable and efficient electrolytes for room-temperature rechargeable calcium batteries. *Energy & Environmental Science*, 12(12):3496–3501, 2019.

- [18] Shengda D Pu, Chen Gong, Xiangwen Gao, Ziyang Ning, Sixie Yang, John-Joseph Marie, Boyang Liu, Robert A House, Gareth O Hartley, Jun Luo, et al. Current-density-dependent electroplating in ca electrolytes: From globules to dendrites. ACS Energy Letters, 5(7):2283–2290, 2020.
- [19] Abhinandan Shyamsunder, Lauren E Blanc, Abdeljalil Assoud, and Linda F Nazar. Reversible calcium plating and stripping at room temperature using a borate salt. ACS Energy Letters, 4(9):2271–2276, 2019.
- [20] Ziqin Rong, Rahul Malik, Pieremanuele Canepa, Gopalakrishnan Sai Gautam, Miao Liu, Anubhav Jain, Kristin Persson, and Gerbrand Ceder. Materials design rules for multivalent ion mobility in intercalation structures. *Chemistry of Materials*, 27(17):6016–6021, 2015.
- [21] Manuel Smeu, Md Sazzad Hossain, Zi Wang, Vladimir Timoshevskii, Kirk H Bevan, and Karim Zaghib. Theoretical investigation of chevrel phase materials for cathodes accommodating ca2+ ions. *Journal of Power Sources*, 306:431–436, 2016.
- [22] Junjun Wang, Shuangshuang Tan, Fangyu Xiong, Ruohan Yu, Peijie Wu, Lianmeng Cui, and Qinyou An. Vopo 4. 2h 2 o as a new cathode material for rechargeable ca-ion batteries. *Chemical communications*, 56(26):3805–3808, 2020.
- [23] Gopalakrishnan Sai Gautam, Pieremanuele Canepa, Rahul Malik, Miao Liu, Kristin Persson, and Gerbrand Ceder. First-principles evaluation of multi-valent cation insertion into orthorhombic v 2 o 5. Chemical communications, 51(71):13619–13622, 2015.
- [24] Boosik Jeon, Hunho H Kwak, and Seung-Tae Hong. Bilayered ca0. 28v205 h20: High-capacity cathode material for rechargeable ca-ion batteries and its charge storage mechanism. *Chemistry of Materials*, 34(4):1491–1498, 2022.
- [25] Xiao Zhang, Xiaoming Xu, Bo Song, Manyi Duan, Jiashen Meng, Xuanpeng Wang, Zhitong Xiao, Lin Xu, and Liqiang Mai. Towards a stable layered vanadium oxide cathode for high-capacity calcium batteries. *Small*, 18(43):2107174, 2022.
- [26] Samuel Jayaraj Richard Prabakar, Amol Bhairuba Ikhe, Woon-Bae Park, Docheon Ahn, Kee-Sun Sohn, and Myoungho Pyo. Ultra-high capacity and cyclability of  $\beta$ -phase ca0. 14v2o5 as a promising cathode in calcium-ion batteries. *Advanced Functional Materials*, 33(29):2301399, 2023.
- [27] Xiaoming Xu, Manyi Duan, Yunfan Yue, Qi Li, Xiao Zhang, Lu Wu, Peijie Wu, Bo Song, and Liqiang Mai. Bilayered mg0. 25v2o5· h2o as a stable cathode for rechargeable ca-ion batteries. ACS Energy Letters, 4(6):1328–1335, 2019.
- [28] Wang Lu, Juefan Wang, Gopalakrishnan Sai Gautam, and Pieremanuele Canepa. Searching ternary oxides and chalcogenides as positive electrodes for calcium batteries. *Chemistry of Materials*, 33(14):5809– 5821, 2021.
- [29] Ashley P Black, Carlos Frontera, Arturo Torres, Miguel Recio-Poo, Patrick Rozier, Juan D Forero-Saboya, François Fauth, Esteban Urones-Garrote, M Elena Arroyo-de Dompablo, and M Rosa Palacín. Elucidation of the redox activity of ca2mno3. 5 and cav2o4 in calcium batteries using operando xrd: charge compensation mechanism and reversibility. *Energy Storage Materials*, 47:354–364, 2022.

- [30] Paul Alexis Chando, Sihe Chen, Jacob Matthew Shellhamer, Elizabeth Wall, Xinlu Wang, Robson Schuarca, Manuel Smeu, and Ian Dean Hosein. Exploring calcium manganese oxide as a promising cathode material for calcium-ion batteries. *Chemistry of Materials*, 35(20):8371–8381, 2023.
- [31] Marta Cabello, Francisco Nacimiento, Ricardo Alcántara, Pedro Lavela, Carlos Perez Vicente, and José L Tirado. Applicability of molybdite as an electrode material in calcium batteries: a structural study of layer-type ca x moo3. *Chemistry of Materials*, 30(17):5853–5861, 2018.
- [32] Tomohiro Tojo, Hayato Tawa, Noriyuki Oshida, Ryoji Inada, and Yoji Sakurai. Electrochemical characterization of a layered  $\alpha$ -moo3 as a new cathode material for calcium ion batteries. Journal of Electroanalytical Chemistry, 825:51–56, 2018.
- [33] Munseok S Chae, Hunho H Kwak, and Seung-Tae Hong. Calcium molybdenum bronze as a stable highcapacity cathode material for calcium-ion batteries. ACS Applied Energy Materials, 3(6):5107–5112, 2020.
- [34] Thuan Ngoc Vo, Hyeongwoo Kim, Jaehyun Hur, Wonchang Choi, and Il Tae Kim. Surfactant-assisted ammonium vanadium oxide as a superior cathode for calcium-ion batteries. *Journal of materials chemistry A*, 6(45):22645–22654, 2018.
- [35] Marta Cabello, Francisco Nacimiento, José R González, Gregorio Ortiz, Ricardo Alcántara, Pedro Lavela, Carlos Pérez-Vicente, and José L Tirado. Advancing towards a veritable calcium-ion battery: Caco2o4 positive electrode material. *Electrochemistry Communications*, 67:59–64, 2016.
- [36] Haesun Park, Christopher J Bartel, Gerbrand Ceder, and Peter Zapol. Layered transition metal oxides as ca intercalation cathodes: A systematic first-principles evaluation. Advanced Energy Materials, 11(48):2101698, 2021.
- [37] Albert L Lipson, Soojeong Kim, Baofei Pan, Chen Liao, Timothy T Fister, and Brian J Ingram. Calcium intercalation into layered fluorinated sodium iron phosphate. *Journal of Power Sources*, 369:133–137, 2017.
- [38] Deyana S Tchitchekova, Alexandre Ponrouch, Roberta Verrelli, Thibault Broux, Carlos Frontera, Andrea Sorrentino, Fanny Bardé, Neven Biskup, M Elena Arroyo-de Dompablo, and M Rosa Palacin. Electrochemical intercalation of calcium and magnesium in tis2: fundamental studies related to multivalent battery applications. *Chemistry of Materials*, 30(3):847–856, 2018.
- [39] Junjun Wang, Jianxiang Wang, Yalong Jiang, Fangyu Xiong, Shuangshuang Tan, Fan Qiao, Jinghui Chen, Qinyou An, and Liqiang Mai. Cav6o16 · 2.8 h2o with ca2+ pillar and water lubrication as a highrate and long-life cathode material for ca-ion batteries. Advanced Functional Materials, 32(25):2113030, 2022.
- [40] Neal Kuperman, Prasanna Padigi, Gary Goncher, David Evans, Joseph Thiebes, and Raj Solanki. High performance prussian blue cathode for nonaqueous ca-ion intercalation battery. *Journal of Power Sources*, 342:414–418, 2017.
- [41] Tohru Shiga, Hiroki Kondo, Yuichi Kato, and Masae Inoue. Insertion of calcium ion into prussian blue analogue in nonaqueous solutions and its application to a rechargeable battery with dual carriers. The Journal of Physical Chemistry C, 119(50):27946–27953, 2015.

- [42] Prasanna Padigi, Gary Goncher, David Evans, and Raj Solanki. Potassium barium hexacyanoferrate-a potential cathode material for rechargeable calcium ion batteries. *Journal of Power Sources*, 273:460– 464, 2015.
- [43] Tomohiro Tojo, Yosuke Sugiura, Ryoji Inada, and Yoji Sakurai. Reversible calcium ion batteries using a dehydrated prussian blue analogue cathode. *Electrochimica Acta*, 207:22–27, 2016.
- [44] Albert L Lipson, Baofei Pan, Saul H Lapidus, Chen Liao, John T Vaughey, and Brian J Ingram. Rechargeable ca-ion batteries: a new energy storage system. *Chemistry of Materials*, 27(24):8442– 8447, 2015.
- [45] Sanghyeon Kim, Liang Yin, Myeong Hwan Lee, Prakash Parajuli, Lauren Blanc, Timothy T. Fister, Haesun Park, Bob Jin Kwon, Brian J. Ingram, Peter Zapol, Robert F. Klie, Kisuk Kang, Linda F. Nazar, Saul H. Lapidus, and John T. Vaughey. High-voltage phosphate cathodes for rechargeable ca-ion batteries. ACS Energy Letters, 5(10):3203–3211, 10 2020.
- [46] Boosik Jeon, Jongwook W. Heo, Jooeun Hyoung, Hunho H. Kwak, Dongmin M. Lee, and Seung-Tae Hong. Reversible calcium-ion insertion in nasicon-type nav2(po4)3. *Chemistry of Materials*, 32(20):8772–8780, 10 2020.
- [47] Zheng-Long Xu, Jooha Park, Jian Wang, Hyunseok Moon, Gabin Yoon, Jongwoo Lim, Yoon-Joo Ko, Sung-Pyo Cho, Sang-Young Lee, and Kisuk Kang. A new high-voltage calcium intercalation host for ultra-stable and high-power calcium rechargeable batteries. *Nature communications*, 12(1):3369, 2021.
- [48] Dereje Bekele Tekliye, Ankit Kumar, Xie Weihang, Thelakkattu Devassy Mercy, Pieremanuele Canepa, and Gopalakrishnan Sai Gautam. Exploration of nasicon frameworks as calcium-ion battery electrodes. *Chemistry of Materials*, 34(22):10133–10143, 2022.
- [49] Gopalakrishnan Sai Gautam, Pieremanuele Canepa, William Davidson Richards, Rahul Malik, and Gerbrand Ceder. Role of structural h20 in intercalation electrodes: the case of mg in nanocrystalline xerogel-v205. Nano Letters, 16(4):2426–2431, 2016.
- [50] Pierre Hohenberg and Walter Kohn. Inhomogeneous electron gas. Physical review, 136(3B):B864, 1964.
- [51] Walter Kohn and Lu Jeu Sham. Self-consistent equations including exchange and correlation effects. *Physical review*, 140(4A):A1133, 1965.
- [52] Lauren E. Blanc, Yunyeong Choi, Abhinandan Shyamsunder, Baris Key, Saul H. Lapidus, Chang Li, Liang Yin, Xiang Li, Bharat Gwalani, Yihan Xiao, Christopher J. Bartel, Gerbrand Ceder, and Linda F. Nazar. Phase stability and kinetics of topotactic dual ca2+-na+ ion electrochemistry in nasicon nav2(po4)3. *Chemistry of Materials*, 35(2):468-481, 2023.
- [53] R Bralsford, PV Harris, and William Charles Price. The effect of fluorine on the electronic spectra and ionization potentials of molecules. Proceedings of the Royal Society of London. Series A. Mathematical and Physical Sciences, 258(1295):459–469, 1960.
- [54] AK Padhi, V Manivannan, and JB Goodenough. Tuning the position of the redox couples in materials with nasicon structure by anionic substitution. *Journal of the Electrochemical Society*, 145(5):1518, 1998.

- [55] Xiao Hua, Alexander S Eggeman, Elizabeth Castillo-Martínez, Rosa Robert, Harry S Geddes, Ziheng Lu, Chris J Pickard, Wei Meng, Kamila M Wiaderek, Nathalie Pereira, et al. Revisiting metal fluorides as lithium-ion battery cathodes. *Nature materials*, 20(6):841–850, 2021.
- [56] Xiulin Fan, Enyuan Hu, Xiao Ji, Yizhou Zhu, Fudong Han, Sooyeon Hwang, Jue Liu, Seongmin Bak, Zhaohui Ma, Tao Gao, et al. High energy-density and reversibility of iron fluoride cathode enabled via an intercalation-extrusion reaction. *Nature communications*, 9(1):2324, 2018.
- [57] Bin Ouyang, Nongnuch Artrith, Zhengyan Lun, Zinab Jadidi, Daniil A Kitchaev, Huiwen Ji, Alexander Urban, and Gerbrand Ceder. Effect of fluorination on lithium transport and short-range order in disordered-rocksalt-type lithium-ion battery cathodes. *Advanced Energy Materials*, 10(10):1903240, 2020.
- [58] RJ Clément, Z Lun, and G Ceder. Cation-disordered rocksalt transition metal oxides and oxyfluorides for high energy lithium-ion cathodes. *Energy & Environmental Science*, 13(2):345–373, 2020.
- [59] Irina D Gocheva, Manabu Nishijima, Takayuki Doi, Shigeto Okada, Jun-ichi Yamaki, and Tetsuaki Nishida. Mechanochemical synthesis of namf3 (m= fe, mn, ni) and their electrochemical properties as positive electrode materials for sodium batteries. *Journal of Power Sources*, 187(1):247–252, 2009.
- [60] Ayuko Kitajou, Yuji Ishado, Tomoki Yamashita, Hiroyoshi Momida, Tamio Oguchi, and Shigeto Okada. Cathode properties of perovskite-type namf3 (m= fe, mn, and co) prepared by mechanical ball milling for sodium-ion battery. *Electrochimica Acta*, 245:424–429, 2017.
- [61] Nikolay Dimov, Akihiro Nishimura, Kuniko Chihara, Ayuko Kitajou, Irina D Gocheva, and Shigeto Okada. Transition metal namf3 compounds as model systems for studying the feasibility of ternary li-mf and na-mf single phases as cathodes for lithium–ion and sodium–ion batteries. *Electrochimica Acta*, 110:214–220, 2013.
- [62] Gopalakrishnan Sai Gautam, Ellen B Stechel, and Emily A Carter. Exploring ca-ce-m-o (m= 3d transition metal) oxide perovskites for solar thermochemical applications. *Chemistry of Materials*, 32(23):9964–9982, 2020.
- [63] Robert B Wexler, Gopalakrishnan Sai Gautam, Robert T Bell, Sarah Shulda, Nicholas A Strange, Jamie A Trindell, Joshua D Sugar, Eli Nygren, Sami Sainio, Anthony H McDaniel, et al. Multiple and nonlocal cation redox in ca-ce-ti-mn oxide perovskites for solar thermochemical applications. *Energy* & Environmental Science, 16(6):2550-2560, 2023.
- [64] Holger Euchner, Oliver Clemens, and M Anji Reddy. Unlocking the potential of weberite-type metal fluorides in electrochemical energy storage. *npj Computational Materials*, 5(1):31, 2019.
- [65] Utsav Kumar Dey, Nabadyuti Barman, Subham Ghosh, Shreya Sarkar, Sebastian C Peter, and Premkumar Senguttuvan. Topochemical bottom-up synthesis of 2d-and 3d-sodium iron fluoride frameworks. *Chemistry of Materials*, 31(2):295–299, 2019.
- [66] Arindam Ghosh, Dereje Bekele Tekliye, Emily E. Foley, Varimalla Raghavendra Reddy, Raphaële J. Clémenta, Gopalakrishnan Sai Gautam, and Premkumar Senguttuvan. Topochemical modulations from 1d iron fluoride precursor to 3d frameworks. Under review, 2024.

- [67] Hyunyoung Park, Yongseok Lee, Min-kyung Cho, Jungmin Kang, Wonseok Ko, Young Hwa Jung, Tae-Yeol Jeon, Jihyun Hong, Hyungsub Kim, Seung-Taek Myung, et al. Na 2 fe 2 f 7: a fluoride-based cathode for high power and long life na-ion batteries. *Energy & Environmental Science*, 14(3):1469– 1479, 2021.
- [68] RD T Shannon and C Tfc Prewitt. Effective ionic radii in oxides and fluorides. Acta Crystallographica Section B: Structural Crystallography and Crystal Chemistry, 25(5):925–946, 1969.
- [69] Robert D Shannon. Revised effective ionic radii and systematic studies of interatomic distances in halides and chalcogenides. Acta crystallographica section A: crystal physics, diffraction, theoretical and general crystallography, 32(5):751–767, 1976.
- [70] Osvald Knop, T Stanley Cameron, and Klaus Jochem. What is the true space group of weberite? Journal of Solid State Chemistry, 43(2):213–221, 1982.
- [71] Lu Cai and Juan C Nino. Complex ceramic structures. i. weberites. Acta Crystallographica Section B: Structural Science, 65(3):269–290, 2009.
- [72] O Yakubovich, V Urusov, W Massa, G Frenzen, and D Babel. Structure of na2fe2f7 and structural relations in the family of weberites na2miimiiif7. Zeitschrift für anorganische und allgemeine Chemie, 619(11):1909–1919, 1993.
- [73] IE Grey, WG Mumme, TJ Ness, Robert S Roth, and KL Smith. Structural relations between weberite and zirconolite polytypes—refinements of doped 3t and 4m ca2ta2o7 and 3t cazrti2o7. *Journal of Solid State Chemistry*, 174(2):285–295, 2003.
- [74] MW Shafer. The synthesis and characterization of vanadium difluoride, navf3, kvf3, and rbvf3. Materials Research Bulletin, 4(12):905–912, 1969.
- [75] Fabian LM Bernal, Jonas Sottmann, David S Wragg, Helmer Fjellvåg, Øystein S Fjellvåg, Christina Drathen, Wojciech A Sławiński, and Ole Martin Løvvik. Structural and magnetic characterization of the elusive jahn-teller active nacrf 3. *Physical Review Materials*, 4(5):054412, 2020.
- [76] Alicja Ratuszna, Katarzyna Majewska, and Tadeusz Lis. Structure of namnf3 at room temperature. Acta Crystallographica Section C: Crystal Structure Communications, 45(4):548–551, 1989.
- [77] G Benner and R Hoppe. Uber fluoride des zweiwertigen eisens [1]: zum aufbau von nafef3 [1]. Journal of fluorine chemistry, 46(2):283–295, 1990.
- [78] Hitoshi Yusa, Yuichi Shirako, Masaki Akaogi, Hiroshi Kojitani, Naohisa Hirao, Yasuo Ohishi, and Takumi Kikegawa. Perovskite-to-postperovskite transitions in nanif3 and nacof3 and disproportionation of nacof3 postperovskite under high pressure and high temperature. *Inorganic Chemistry*, 51(12):6559–6566, 2012.
- [79] Wenhao Sun, Stephen T Dacek, Shyue Ping Ong, Geoffroy Hautier, Anubhav Jain, William D Richards, Anthony C Gamst, Kristin A Persson, and Gerbrand Ceder. The thermodynamic scale of inorganic crystalline metastability. *Science advances*, 2(11):e1600225, 2016.
- [80] Dereje Bekele Tekliye and Gopalakrishnan Sai Gautam. Accuracy of metagga functionals in describing transition metal fluorides. *arXiv preprint arXiv:2401.10832*, 2024.

- [81] Daniel C Hannah, Gopalakrishnan Sai Gautam, Pieremanuele Canepa, and Gerbrand Ceder. On the balance of intercalation and conversion reactions in battery cathodes. Advanced Energy Materials, 8(20):1800379, 2018.
- [82] Gopalakrishnan Sai Gautam, Pieremanuele Canepa, Aziz Abdellahi, Alexander Urban, Rahul Malik, and Gerbrand Ceder. The intercalation phase diagram of mg in v2o5 from first-principles. *Chemistry* of Materials, 27(10):3733–3742, 2015.
- [83] GG Amatucci, JM Tarascon, and LC Klein. Coo2, the end member of the li x coo2 solid solution. Journal of The Electrochemical Society, 143(3):1114, 1996.
- [84] Doron Aurbach, Z Lu, Alex Schechter, Yossef Gofer, H Gizbar, R Turgeman, Y Cohen, Mordechay Moshkovich, and El Levi. Prototype systems for rechargeable magnesium batteries. *Nature*, 407(6805):724–727, 2000.
- [85] Rahul Malik, Aziz Abdellahi, and Gerbrand Ceder. A critical review of the li insertion mechanisms in lifepo4 electrodes. *Journal of the electrochemical society*, 160(5):A3179, 2013.
- [86] Rubicelia Vargas and Marcelo Galván. On the stability of half-filled shells. The Journal of Physical Chemistry, 100(35):14651–14654, 1996.
- [87] Saul I Shupack. The chemistry of chromium and some resulting analytical problems. Environmental Health Perspectives, 92:7–11, 1991.
- [88] Graeme Henkelman and Hannes Jónsson. Improved tangent estimate in the nudged elastic band method for finding minimum energy paths and saddle points. *The Journal of chemical physics*, 113(22):9978– 9985, 2000.
- [89] Daniel Sheppard, Rye Terrell, and Graeme Henkelman. Optimization methods for finding minimum energy paths. *The Journal of chemical physics*, 128(13), 2008.
- [90] John P Perdew, Kieron Burke, and Matthias Ernzerhof. Generalized gradient approximation made simple. *Physical review letters*, 77(18):3865, 1996.
- [91] Yirong Gao, Tara P Mishra, Shou-Hang Bo, Gopalakrishnan Sai Gautam, and Pieremanuele Canepa. Design and characterization of host frameworks for facile magnesium transport. Annual Review of Materials Research, 52:129–158, 2022.
- [92] Reshma Devi, Baltej Singh, Pieremanuele Canepa, and Gopalakrishnan Sai Gautam. Effect of exchange-correlation functionals on the estimation of migration barriers in battery materials. npj Computational Materials, 8(1):160, 2022.
- [93] Olivia Y Long, Gopalakrishnan Sai Gautam, and Emily A Carter. Assessing cathode property prediction via exchange-correlation functionals with and without long-range dispersion corrections. *Physical Chemistry Chemical Physics*, 23(43):24726–24737, 2021.
- [94] Tenglong Lu, Sheng Meng, and Miao Liu. Weberite na \_2 mm'f \_7(m, m'= redox-active metal) as promising fluoride-based sodium-ion battery cathodes. arXiv preprint arXiv:2310.04222, 2023.

- [95] Jiaying Liao, Jingchen Han, Jianzhi Xu, Yichen Du, Yingying Sun, Liping Duan, and Xiaosi Zhou. Scalable synthesis of na 2 mvf 7 (m= mn, fe, and co) as high-performance cathode materials for sodium-ion batteries. *Chemical Communications*, 57(87):11497–11500, 2021.
- [96] Georg Kresse and Daniel Joubert. From ultrasoft pseudopotentials to the projector augmented-wave method. *Physical Review B*, 59(3):1758, 1999.
- [97] Peter E Blöchl, Ove Jepsen, and Ole Krogh Andersen. Improved tetrahedron method for brillouin-zone integrations. *Physical Review B*, 49(23):16223, 1994.
- [98] Georg Kresse and Jürgen Hafner. Ab initio molecular dynamics for liquid metals. Physical review B, 47(1):558, 1993.
- [99] Georg Kresse and Jürgen Furthmüller. Efficient iterative schemes for ab initio total-energy calculations using a plane-wave basis set. *Physical Review B*, 54(16):11169, 1996.
- [100] Hendrik J Monkhorst and James D Pack. Special points for brillouin-zone integrations. *Physical Review B*, 13(12):5188, 1976.
- [101] Jianwei Sun, Adrienn Ruzsinszky, and John P Perdew. Strongly constrained and appropriately normed semilocal density functional. *Physical Review Letters*, 115(3):036402, 2015.
- [102] Sergei L Dudarev, Gianluigi A Botton, Sergey Y Savrasov, CJ Humphreys, and Adrian P Sutton. Electron-energy-loss spectra and the structural stability of nickel oxide: An LSDA+U study. *Physical Review B*, 57(3):1505, 1998.
- [103] Vladimir I Anisimov, Jan Zaanen, and Ole K Andersen. Band theory and mott insulators: Hubbard U instead of stoner I. Physical Review B, 44(3):943, 1991.
- [104] Gopalakrishnan Sai Gautam and Emily A Carter. Evaluating transition metal oxides within DFT-SCAN and SCAN+U frameworks for solar thermochemical applications. *Physical Review Materials*, 2(9):095401, 2018.
- [105] Olivia Y Long, Gopalakrishnan Sai Gautam, and Emily A Carter. Evaluating optimal U for 3d transition-metal oxides within the SCAN+U framework. *Physical Review Materials*, 4(4):045401, 2020.
- [106] Mariette Hellenbrandt. The inorganic crystal structure database (ICSD)—present and future. Crystallography Reviews, 10(1):17–22, 2004.
- [107] Y Laligant, Y Calage, G Heger, J Pannetier, and G Ferey. Ordered magnetic frustration: Vii. na2nifef7: Reexamination of its crystal structure in the true space group after corrections from renninger effect and refinement of its frustrated magnetic structure at 4.2 and 55 k. Journal of Solid State Chemistry, 78(1):66–77, 1989.
- [108] Iek-Heng Chu, Sayan Roychowdhury, Daehui Han, Anubhav Jain, and Shyue Ping Ong. Predicting the volumes of crystals. *Computational Materials Science*, 146:184–192, 2018.

- [109] Shyue Ping Ong, William Davidson Richards, Anubhav Jain, Geoffroy Hautier, Michael Kocher, Shreyas Cholia, Dan Gunter, Vincent L Chevrier, Kristin A Persson, and Gerbrand Ceder. Python materials genomics (pymatgen): A robust, open-source python library for materials analysis. Computational Materials Science, 68:314–319, 2013.
- [110] Gus LW Hart and Rodney W Forcade. Algorithm for generating derivative structures. *Physical Review B*, 77(22):224115, 2008.
- [111] Gus LW Hart and Rodney W Forcade. Generating derivative structures from multilattices: Algorithm and application to HCP alloys. *Physical Review B*, 80(1):014120, 2009.
- [112] Gus LW Hart, Lance J Nelson, and Rodney W Forcade. Generating derivative structures at a fixed concentration. *Computational Materials Science*, 59:101–107, 2012.
- [113] Wiley S Morgan, Gus LW Hart, and Rodney W Forcade. Generating derivative superstructures for systems with high configurational freedom. *Computational Materials Science*, 136:144–149, 2017.
- [114] Fei Zhou, Matteo Cococcioni, Chris A Marianetti, Dane Morgan, and G Ceder. First-principles prediction of redox potentials in transition-metal compounds with lda+ u. *Physical Review B*, 70(23):235121, 2004.