arXiv:2407.16325v1 [cond-mat.str-el] 23 Jul 2024

Ground-State Properties of the t-J Model for the CuO Double-Chain Structure

Tatsuya Kaneko,¹ Satoshi Ejima,² Koudai Sugimoto,³ and Kazuhiko Kuroki¹

Department of Physics, Osaka University, Toyonaka, Osaka 560-0043, Japan

 $^2 {\it Institut ~f\"ur ~Software technologie,~Abteilung~High-Performance~Computing,}$

Deutsches Zentrum für Luft- und Raumfahrt (DLR), 22529 Hamburg, Germany

³Department of Physics, Keio University, Yokohama, Kanagawa 223-8522, Japan

(Dated: July 24, 2024)

We investigate the ground-state properties of a correlated model for the double-chain structure in cuprates. We consider the t-J model, in which the nearest-neighbor spin interaction J_1 is smaller than the next-nearest-neighbor interaction J_2 corresponding to the CuO double-chain structure. We vary J_1 from antiferromagnetic to ferromagnetic values and calculate the correlation functions including the superconducting pair correlation function. Employing the density-matrix renormalization group method, we show that the ground state for antiferromagnetic J_1 exhibits the hallmarks of the Luther–Emery liquid phase, in which the spin-singlet pair and charge-density-wave correlations exhibit power-law decays against distance, and the spin correlation function decays exponentially. Its signatures are gradually dismissed as J_1 approaches the ferromagnetic regime. Our findings suggest that the antiferromagnetic double-chain structure without ferromagnetic bonds is favorable for superconductivity.

I. INTRODUCTION

Low-dimensional correlated electron systems are one of the most attractive research fields in condensed matter physics. One representative example is high-temperature superconductivity (SC) in cuprates. The unconventional superconducting properties of cuprates have been investigated in the doped Mott insulators described by the Hubbard and t-J models [1–4]. Density-matrix renormalization group (DMRG) calculations enable us to obtain nearly unbiased numerical results, which have recently revealed, e.g., robust *d*-wave-like SC on a square lattice [5, 6] and possible topological SC on a frustrated triangular lattice [7–9]. In systems belonging to onedimensional (1D) structures (e.g., cylinders used in these DMRG simulations), a hallmark of SC is given by the emergence of the Luther–Emery (LE) liquid state [10], which has the gapped-spin and gapless-charge modes with quasi-long-range SC pair correlations. Although the SC correlation competes with the charge-density-wave (CDW) correlation, a finding of the LE liquid phase may provide helpful insights into the material design of unconventional superconductors.

SC on the CuO₂ layer, which consists of corner-sharing square-planar units, has been investigated extensively. On the other hand, cuprates containing edge-sharing square-planar units also have the potential to show SC. For example, $Pr_2Ba_4Cu_7O_{15-\delta}$ composed of multiple copper oxide chain structures shows SC with a moderate number of oxygen defects [11–20], where a double-chain structure (see Fig. 1) is expected to be responsible for SC [21–28]. The electronic properties in the edge-sharing structure have crucial differences from those in the corner-sharing structure. In the double-chain structure shown in Fig. 1, whereas the hopping t_2 between next-nearest-neighboring (NNN) Cu sites is composed of the Cu-O-Cu (*d-p-d*) process as in the corner-sharing structure, the hopping t_1 between nearest-neighboring

(NN) Cu sites has no *d-p-d* contribution when the p_x and p_y orbitals in the shared O site are orthogonal. Hence, $|t_2| > |t_1|$ [22, 23], i.e., two CuO chains are weakly connected via a small t_1 .

As for magnetism, the double-chain (zigzag chain) model at half-filling can be mapped to the frustrated J_1 - J_2 Heisenberg chain [26]. Because edge-sharing NN clusters have the ferromagnetic contribution $J_1^{(FM)}$ mediated by the spin interaction at the ligand site [29–32], the Heisenberg model with ferromagnetic J_1 and antiferromagnetic J_2 for quasi-1D cuprates has been studied in detail [33–38]. In the double-chain structure shown in Fig. 1, the superexchange mechanism attributed to the straight-line d-p-d process gives a large antiferromagnetic J_2 . On the other hand, the direct d-d and detouring d-p-p-d processes (included in t_1) can lead to the antiferromagnetic contribution $J_1^{(AFM)}$. Hence, the competing $J_1^{(AFM)}$ and $J_1^{(FM)}$ may result in a small J_1 $(= J_1^{(AFM)} + J_1^{(FM)})$, and $J_2 > J_1$ is expected in the zigzag chain structure. The magnetism and possible SC



FIG. 1. CuO double-chain structure and zigzag chain.

in the CuO double-chain structure have been investigated in the t_1 - t_2 Hubbard model [22, 26]. However, the simple *d*-orbital-based Hubbard model does not consider the ferromagnetic contribution $J_1^{(FM)}$ attributed to the ligand *p* orbitals. Although possible SC has also been studied in the *d*-*p* model and its effective *t*-*J* model [21, 23, 25], long-range properties of correlation functions have not been explicitly investigated in large systems including the case of ferromagnetic J_1 .

In this paper, we investigate the ground-state properties of the double-chain structure employing the DMRG method. In particular, we consider the t-J model to incorporate the ferromagnetic contribution in J_1 . Our calculations of the correlation functions including the SC pair correlation function show that the ground state for antiferromagnetic J_1 exhibits the hallmarks of the LE liquid phase, whereas the signatures of the LE liquid gradually vanish as J_1 approaches the ferromagnetic value. Our DMRG calculations provide insights into the SC state possibly emerging on the CuO double-chain structure.

The rest of this paper is organized as follows. In Sect. II, we introduce the model and method. In Sect. III, we present the results of our DMRG calculations, where we show the spin, charge, and pair correlation functions for various J_1 values. Our conclusions are presented in Sect. IV.

II. MODEL AND METHOD

The Hamiltonian of the t-J model on the zigzag chain structure shown in Fig. 1 reads

$$\hat{\mathcal{H}} = -t_1 \sum_{j,\sigma} \left(\hat{\hat{c}}_{j,\sigma}^{\dagger} \hat{\hat{c}}_{j+1,\sigma} + \text{H.c.} \right) - t_2 \sum_{j,\sigma} \left(\hat{\hat{c}}_{j,\sigma}^{\dagger} \hat{\hat{c}}_{j+2,\sigma} + \text{H.c.} \right)$$
$$+ J_1 \sum_j \left(\hat{\boldsymbol{S}}_j \cdot \hat{\boldsymbol{S}}_{j+1} - \frac{1}{4} \hat{n}_j \hat{n}_{j+1} \right)$$
$$+ J_2 \sum_j \left(\hat{\boldsymbol{S}}_j \cdot \hat{\boldsymbol{S}}_{j+2} - \frac{1}{4} \hat{n}_j \hat{n}_{j+2} \right).$$
(1)

 $\hat{c}_{j,\sigma} = \hat{c}_{j,\sigma}(1 - \hat{n}_{j,\bar{\sigma}})$ is the constrained annihilation operator of $\hat{c}_{j,\sigma}$ for a fermion with spin σ (= \uparrow,\downarrow) at site j, where $\hat{n}_{j,\sigma} = \hat{c}_{j,\sigma}^{\dagger}\hat{c}_{j,\sigma}$ and $\bar{\sigma}$ denotes the opposite spin of σ . The constrained hopping using the operators $\hat{c}_{j,\sigma}^{\dagger}$ and $\hat{\bar{c}}_{j,\sigma}$ prohibits the creation of a doubly occupied site. \hat{S}_j is the spin operator, and \hat{n}_j (= $\sum_{\sigma} \hat{n}_{j,\sigma}$) is the number operator. t_1 and t_2 are the transfer integrals of the NN and NNN hoppings, respectively. t_1 (t_2) corresponds to the interchain (intrachain) hopping (see Fig. 1). J_1 and J_2 are the NN and NNN spin interactions, respectively. In the L site zigzag chain, the filling of the N-particle system is defined as $n = N/L = (N_{\uparrow} + N_{\downarrow})/L$, where N_{σ} is the number of spin σ .

We consider the *t-J* model underlying the *d-p* structure in the CuO double chains, e.g., in $Pr_2Ba_2Cu_7O_{15-\delta}$ [21– 23]. Although the electron filling of the double-chain structure in $Pr_2Ba_4Cu_7O_{15-\delta}$ has not been specified in experiments, it is expected to be slightly above quarterfilling (n = 0.5) [21, 22]. Hence, in this paper, we set n = 0.6. The hopping t_2 between NNN Cu sites is larger than t_1 between NN Cu sites because the $d_{x^2-y^2}$ $p_x - d_{x^2 - y^2}$ network leads to a large effective d-d hopping for t_2 but it is absent in t_1 (see Fig. 1). The superexchange in the strong $d_{x^2-y^2}-p_x-d_{x^2-y^2}$ bond leads to a large antiferromagnetic NNN interaction J_2 (> 0). On the other hand, the direct d-d hopping and detouring dp-p-d processes can yield the antiferromagnetic NN contribution $J_1^{(AFM)}$ (> 0). The NN interaction J_1 also includes the ferromagnetic contribution $J_1^{(\text{FM})}$ (< 0) be-cause of Hund's coupling between the p_x and p_y orbitals at a shared O site [29–32]. Hence, $J_1 = J_1^{(AFM)} + J_1^{(FM)}$, i.e., the antiferromagnetic and ferromagnetic contributions are competing in the NN interaction. If $|J_1^{(FM)}| >$ $J_1^{(AFM)}$, J_1 can be negative. In this paper, assuming $|t_2| > |t_1|$ and $J_2 > J_1$, we investigate the ground-state properties at various J_1 values. We set J_2 (> 0) as the unit of energy and use $t_2 = 3J_2$. Referring to the values of hoppings used in previous studies [22, 23], we set t_1/t_2 $= 0.2 (t_1 = 0.6J_2).$

We employ the DMRG method [39, 40] to obtain the ground state in the t-J model. We apply open boundary conditions (OBCs) to the L site zigzag chain and perform DMRG calculations in the $S_{\text{tot}}^z = 0$ (i.e., $N_{\uparrow} = N_{\downarrow}$) sector. The bond dimension is up to m = 10000, where the largest truncation error is on the order of 10^{-7} . As discussed in Appendix A, the ground state at $J_1 < 0$ can be a $\langle \hat{S}_{\text{tot}}^2 \rangle = S_{\text{tot}}(S_{\text{tot}} + 1) > 0$ state (where $\hat{S}_{\text{tot}} = \sum_j \hat{S}_j$) depending on the system size and boundary conditions. In this paper, we address the parameter regime, in which the ferromagnetic contribution to J_1 is small and small differences in S_{tot} do not change our main conclusion. Unless otherwise noted, we show the results using the L = 200 site zigzag chain at n = 0.6, in which $S_{\text{tot}} = 0$ under OBCs.

To assess ground-state properties, we compute the local charge density $n(j) = \langle \hat{n}_j \rangle$ and three types of correlation function. The charge-density and spin correlation functions are defined as

$$C(r) = \langle \hat{n}_{j_0} \hat{n}_{j_0+r} \rangle - \langle \hat{n}_{j_0} \rangle \langle \hat{n}_{j_0+r} \rangle, \qquad (2)$$

and

$$S(r) = \langle \hat{S}_{j_0}^z \hat{S}_{j_0+r}^z \rangle, \qquad (3)$$

respectively, where j_0 is the reference site. In addition, to obtain pairing properties, we calculate the pair correlation function

$$P(r) = \langle \hat{\Delta}_{j_0}^{\dagger} \hat{\Delta}_{j_0+r} \rangle, \qquad (4)$$

where $\hat{\Delta}_j$ is the spin-singlet pair operator defined as $\hat{\Delta}_j = (\hat{c}_{j,\uparrow}\hat{c}_{j+1,\downarrow} - \hat{c}_{j,\downarrow}\hat{c}_{j+1,\uparrow})/\sqrt{2}$. In the model shown



FIG. 2. Pair correlation function P(r) for various J_1 values at n = 0.6 filling, where the system size is L = 200 and the reference site is $j_0 = L/4$.

in Fig. 1, $\hat{\Delta}_j$ corresponds to a pair of fermions between NN sites, i.e., an inter-CuO-chain pair. To avoid boundary effects, we set $j_0 = L/4$ as the reference site.

III. RESULTS

First, we show the pair correlation function P(r) for various J_1 values. As shown in Fig. 2, the pair correlations show power-law decays. P(r) at $J_1/J_2 = 0.4$ exhibits a large magnitude and a slow decay. However, the pair correlation decreases as J_1 decreases. All P(r) values at $J_1/J_2 = 0.2$ and 0.4 are positive, whereas the correlations at $J_1/J_2 = -0.2$ and 0.0 partially have negative values. These J_1 -dependent properties suggest that the antiferromagnetic (ferromagnetic) J_1 regime is favorable (unfavorable) for spin-singlet SC.

When the ground state is in the LE liquid phase, the charge density potentially shows a CDW-like signature [41-44]. In Fig. 3, we plot the local charge density n(j) for various J_1 values. n(j) at $J_1/J_2 = 0.4$ exhibits a clear density oscillation even around the center of the chain, where the wavenumber of the oscillation is consistent with $q = \pi n$. The amplitude of the oscillation decreases as J_1 decreases. Similarly to the pair correlations, the CDW is unfavorable when J_1 is ferromagnetic.

The tendencies of the pair correlation P(r) and the local charge density n(j) suggest that the ground states at $J_1 > 0$ are in the LE liquid phase and its signatures gradually disappear as J_1 approaches zero. To collect the hallmarks of the LE liquid phase at $J_1 > 0$, we present other supporting quantities in Fig. 4. In Fig. 4(a), we plot the spin correlation function S(r). At $J_1/J_2 = 0.4$, S(r) exhibits an exponential decay, implying the presence of a spin gap, consistent with a property of the LE liquid (i.e., C1S0) phase. To confirm the spin gap opening, in the inset of Fig. 4(a), we show the spin gap $\Delta_{\rm s}(L) = E_0(L, S_{\rm tot}^z = 1) - E_0(L, S_{\rm tot}^z = 0)$, where $E_0(L, S_{\rm tot}^z)$ is the lowest energy of the fixed system size



FIG. 3. Local charge density n(j) for various J_1 values. Squares and circles indicate the densities at the odd (chain 1) and even (chain 2) sites, respectively. The thin gray line is the fitting curve of Eq. (5) for $J_1/J_2 = 0.4$.

L with S_{tot}^z . Extrapolating the computed data of $\Delta_s(L)$ to the thermodynamic limit $L \to \infty$, we indeed find that the spin gap at $J_1/J_2 = 0.4$ is open.

The decaying behavior of the CDW correlation in the LE liquid phase is often evaluated using the local charge density n(j) [41–44]. In Fig. 4(b), we plot the calculated n(j) and show a schematic figure of the charge density distribution around the center of the zigzag chain. We find that the charge density n(j) at $J_1/J_2 = 0.4$ can be fitted by the function

$$n(j) = n + \delta n \frac{\cos(\pi n j + \phi)}{\left[\sin(\pi j/L)\right]^{K_c/2}},\tag{5}$$

where δn is the amplitude of the oscillating term and ϕ is the phase shift. K_c may correspond to the decay exponent of the charge density correlation. Note that the fitting function of Eq. (5) is modified from the function used in the two-leg ladder [41, 42] because we label the site index as in the 1D chain (see Fig. 1). As shown in Fig. 3 (thin line) and Fig. 4(b) (lower panel), the calculated n(j) shows good agreement with the fitting curve of Eq. (5). When the data at $50 < j \le 150$ are used in the fitting, we obtain $K_c \simeq 1.05$. In Fig. 4(c), we compare the charge-density correlation function C(r) with the decay line expected from the exponent $K_{\rm c}$. The decay of C(r) in the long-range part (at $r \gg 1$) shows good agreement with the r^{-K_c} decay (black dashed line) when using K_c extracted from n(j). Hence, K_c in Eq. (5) gives a reasonable decay exponent for the correlation function C(r).

The decay exponent of the pair correlation function P(r) is evaluated by the function

$$P(r) = \frac{A_0}{r^{\kappa_0}} + \frac{A_1 \cos(\pi nr + \phi_1)}{r^{\kappa_1}}.$$
 (6)

 A_0 is dominant in P(r), whereas a small A_1 gives a weak oscillation of P(r). Indeed, as shown in the inset of Fig. 4(c), the weak oscillation of the calculated



FIG. 4. (a) Spin correlation function S(r) at $J_1/J_2 = 0.4$. Squares and circles indicate the correlations at odd and even distances, respectively, away from the reference site $j_0 = L/4$. Inset: system size dependence of the spin gap $\Delta_s(L)$ measured in units of J_2 . The line denotes the second-order polynomial fit of $\Delta_s(L)$. (b) Local charge density n(j) around the center of the zigzag chain. The squares and circles in the lower panel of (b) indicate the densities at the odd (chain 1) and even (chain 2) sites, respectively. The upper figure of (b) schematically represents the charge density distribution on the zigzag chain. (c) Pair and charge correlation functions. The solid and dashed lines indicate the power-law decays of the pair and charge correlation functions, respectively. The inset shows the pair correlation function P(r) and its fitting line.

P(r) at $J_1/J_2 = 0.4$ is well fitted by the second term of Eq. (6), where $\phi_1 = \pi/2$ gives a reasonable fitting curve. Since the dominant contribution is attributed to the first term in Eq. (6), κ_0 may correspond to the decay exponent of the pair correlation $K_{\rm sc}$ [42–46]. When the data at 30 $\leq r \leq$ 100 are used in the fitting, we obtain $K_{\rm sc} = \kappa_0 \simeq 1.04$. Compared with the calculated P(r) shown in Fig. 4(c), the $A_0 r^{-K_{\rm sc}}$ term (black solid line) reproduces the decay of P(r). As shown in Appendix **B**, the size dependence of P(r) at $J_1/J_2 = 0.4$ is small, and thus the pair correlations may show the same decaying behavior even in larger systems. In the LE liquid phase, K_c and K_{sc} satisfy $K_c K_{sc} = 1$ [42–44]. This relation is almost satisfied by $K_{\rm c}$ and $K_{\rm sc}$ extracted from our finite-size DMRG calculation at $J_1/J_2 = 0.4$. Hence, we conclude that the ground state of the zigzag chain at $J_1/J_2 = 0.4$ is in the LE liquid phase.

On the other hand, the decaying behaviors of the cor-



FIG. 5. Spin, charge, and pair correlation functions for $J_1/J_2 = -0.2$. The dashed (black) line indicates a r^{-2} decay as a guide to the eye.

relation functions at $J_1/J_2 = -0.2$ are different from those at $J_1/J_2 = 0.4$. In Fig. 5, we plot the spin, charge, and pair correlation functions at $J_1/J_2 = -0.2$. In addition to the charge and pair correlation functions, the spin correlation function S(r) also shows a power-law decay. As a guide to the eye, we plot a r^{-2} decay line (dashed line) in Fig. 5. The decays of all functions are close to the r^{-2} decay. This may be a signature of a gapless Tomonaga–Luttinger liquid (i.e., both charge and spin sectors are gapless) [43]. Therefore, the ground state in the ferromagnetic J_1 regime is no longer LE liquid and is unfavorable for the substantial development of the spinsinglet pair correlation.

IV. SUMMARY AND DISCUSSION

We have investigated the correlation functions in the t-J model for the CuO double-chain structure. In particular, we have focused on the roles of the NN, i.e., the interchain, spin exchange interaction J_1 . Employing the DMRG method, we have demonstrated that the ground state for the antiferromagnetic J_1 shows the signatures of the LE liquid: the power-law decays of the pair and charge correlations and the exponential decay of the spin correlation. On the other hand, in the ferromagnetic J_1 regime, the pair correlation and charge density oscillation are suppressed, and the spin, charge, and pair correlation functions show similar power-law decays, implying that the ground state is no longer in the LE liquid phase.

Our numerical demonstrations suggest that the antiferromagnetic NN interaction $(J_1 > 0)$ favors SC in the CuO double-chain structure, e.g., in Pr₂Ba₄Cu₇O_{15- δ}. To realize $J_1 > 0$, the antiferromagnetic contribution mainly originating from the electron exchange between the NN Cu sites must be larger than the ferromagnetic contribution mainly originating from Hund's coupling among the ligand p orbitals. In the structure consisting of edge-sharing square-planar units, the direct d-d hopping and detouring d-p-p-d processes can contribute to the antiferromagnetic $J_1^{(AFM)}$, whereas the contribution of the d-p-d process to $J_1^{(AFM)}$ is zero. However, if CuO_4 in the double-chain structure is distorted (as in $Pr_2Ba_4Cu_7O_{15-\delta}$), the *d-p-d* process may contribute to $J_1^{(AFM)}$. The quantitative estimation of J_1 including all spin-exchange processes in a realistic structure is an open issue for the future. As seen in our numerics in Fig. 4(c), although the magnitude of P(r) is larger than that of C(r), the decay exponents of P(r) and C(r) are comparable $(K_{\rm sc} \sim K_{\rm c})$ at $r \gg 1$. These correlation properties and local density in Fig. 4(b) imply that the SC pairing appears on the weak charge density modulation (i.e., SC coexists with CDW). This tendency can cause the suppression of the critical temperature in the CuO doublechain structure (e.g., $T_c \sim 20$ K in $Pr_2Ba_4Cu_7O_{15-\delta}$). A finding of an SC dominant regime without charge density modulation is an important open issue that should be addressed to obtain insights into high-temperature SC in the CuO double-chain structure.

ACKNOWLEDGMENTS

We thank M. Ochi and T. Yagi for useful discussions. This work was supported by JSPS KAKENHI Grant Nos. JP24K06939, JP24H00191 (T.K.), JP23K03286, JP24K01329 (K.S.), JP22K04907 (K.K.), JP20H01849 (T.K. and K.S.), and JP24K01333 (T.K. and K.K.) and by JST COI-NEXT Program Grant No. JPMJPF2221 (K.S.). The DMRG calculations were performed using the ITensor library [47].

Appendix A: Total spin S_{tot} in the ground state

The total spin in the ground state at $J_1 < 0$ (ferromagnetic) has the potential to be $S_{\text{tot}} > 0$ [48]. Here,



FIG. 6. (a) S_{tot} for L = 20 and 30 at n = 0.6 under PBCs. (b) Pair correlation function P(r) at $J_1/J_2 = -0.2$ for various system size L and boundary conditions. $j_0 = 7$ is used as the reference site when L = 30, whereas $j_0 = L/4$ is used when L = 20 and L = 200.

we examine the total spin $S_{\rm tot}$ obtained by calculating $\langle \hat{S}_{\text{tot}}^2 \rangle = S_{\text{tot}}(S_{\text{tot}} + 1)$. The ground states for L = 200with OBCs used in the main text have $S_{\text{tot}} = 0$ even at $J_1/J_2 = -0.2$. However, S_{tot} at $J_1 < 0$ can be nonzero depending on the conditions in finite-size systems. In Fig. 6(a), we plot S_{tot} as a function of J_1 for L = 20and L = 30 (at n = 0.6) under periodic boundary conditions (PBCs). Note that the DMRG calculations under PBCs are more expensive than those under OBCs. and the largest truncation error in the calculations under PBCs is on the order of 10^{-6} (when the bond dimension is up to m = 10000). As shown in Fig. 6(a), $S_{\text{tot}} = 0$ for L = 20, whereas $S_{\text{tot}} > 0$ at $J_1/J_2 \le -0.1$ when L = 30. Note that S_{tot} at $J_1/J_2 = -0.2$ is also nonzero when L = 30 under OBCs. Although the results are not presented, for L = 16 and L = 32 at n = 0.625, $S_{\text{tot}} > 0$ under PBCs, whereas $S_{\text{tot}} = 0$ under OBCs at $J_1/J_2 = -0.2$. In finite-size systems, S_{tot} at $J_1 < 0$ is sensitive to the system size, filling, and boundary conditions.

Although $S_{\rm tot}$ has the potential to be nonzero at $J_1 < 0$, the small difference in S_{tot} in the ground state around $J_1 = 0$ may not improve the pair correlation. In Fig. 6(b), we plot the pair correlation functions at $J_1/J_2 = -0.2$ with different system sizes and boundary conditions, where $S_{\text{tot}} = 1$ when L = 30 and $S_{\text{tot}} = 0$ otherwise. Although the accessible range is limited in small systems, the decaying behavior of P(r) in the $S_{tot} = 1$ state (L = 30) is not markedly different from that in the $S_{\text{tot}} = 0$ state. Hence, even in the $S_{\text{tot}} = 1$ state, the ferromagnetic J_1 regime is unfavorable for developing P(r). This is consistent with our main conclusion. A large ferromagnetic J_1 (< 0) may lead to the strongly spin-polarized ground state (with $S_{\text{tot}} \gg 1$). However, if S_{tot} is small around $J_1 = 0$, the ground-state properties are not markedly modified from those in the $S_{\text{tot}} = 0$ state.



FIG. 7. Pair correlation function P(r) at $J_1/J_2 = 0.4$ for L = 120 (green squares), L = 160 (blue pentagons), and L = 200 (red circles) under OBCs.

Appendix B: Size dependence of the pair correlation function in the LE liquid phase

In Fig. 7, we present the pair correlation function P(r) at $J_1/J_2 = 0.4$ for various system sizes to examine a finite-size effect in the LE liquid phase. The deviation of the pair correlations between the smaller systems (L < 200) and the L = 200 system used in the main text

- [1] E. Dagotto, Rev. Mod. Phys. **66**, 763 (1994).
- [2] M. Imada, A. Fujimori, and Y. Tokura, Rev. Mod. Phys. 70, 1039 (1998).
- [3] P. A. Lee, N. Nagaosa, and X.-G. Wen, Rev. Mod. Phys. 78, 17 (2006).
- [4] B. Keimer, S. A. Kivelson, M. R. Norman, S. Uchida, and J. Zaanen, Nature 518, 179 (2015).
- [5] H.-C. Jiang and T. P. Devereaux, Science **365**, 1424 (2019).
- [6] S. Gong, W. Zhu, and D. N. Sheng, Phys. Rev. Lett. 127, 097003 (2021).
- [7] Y.-F. Jiang and H.-C. Jiang, Phys. Rev. Lett. 125, 157002 (2020).
- [8] Y. Huang and D. N. Sheng, Phys. Rev. X 12, 031009 (2022).
- [9] Y. Huang, S.-S. Gong, and D. N. Sheng, Phys. Rev. Lett. 130, 136003 (2023).
- [10] A. Luther and V. J. Emery, Phys. Rev. Lett. 33, 589 (1974).
- [11] M. Matsukawa, Y. Yamada, M. Chiba, H. Ogasawara, T. Shibata, A. Matsushita, and Y. Takano, Physica C 411, 101 (2004).
- [12] Y. Yamada and A. Matsushita, Physica C 426-431, 213 (2005).
- [13] M. Hagiwara, T. Shima, T. Sugano, K. Koyama, and M. Matsuura, Physica C 445-448, 111 (2006).
- [14] F. Ishikawa, K. Fukuda, S. Sekiya, A. Kaeriyama, Y. Yamada, and A. Matsushita, J. Phys. Soc. Jpn. 76, 92 (2007).
- [15] Y. Wakisaka, K. Takubo, T. Sudayama, J.-Y. Son, T. Mizokawa, M. Arita, H. Namatame, M. Taniguchi, S. Sekiya, K. Fukuda, F. Ishikawa, and Y. Yamada, J. Phys. Soc. Jpn. **77**, 074710 (2008).
- [16] T. Chiba, M. Matsukawa, J. Tada, S. Kobayashi, M. Hagiwara, T. Miyazaki, K. Sano, Y. Ono, T. Sasaki, and J. Echigoya, J. Phys. Soc. Jpn. 82, 074706 (2013).
- [17] J. Tada, M. Matsukawa, T. Konno, S. Kobayashi, M. Hagiwara, T. Miyazaki, K. Sano, Y. Ono, and A. Matsushita, J. Phys. Soc. Jpn. 82, 105003 (2013).
- [18] M. Kuwabara, M. Matsukawa, K. Sugawara, H. Taniguchi, A. Matsushita, M. Hagiwara, K. Sano, Y. Ōno, and T. Sasaki, J. Phys. Soc. Jpn. 85, 124704 (2016).
- [19] H. Taniguchi, Y. Nakarokkaku, R. Takahashi, M. Murakami, A. Nakayama, M. Matsukawa, S. Nakano, M. Hagiwara, and T. Sasaki, J. Phys. Soc. Jpn. 90, 015001 (2021).
- [20] M. Hagawa, M. Matsukawa, K. Niinuma, R. Kudo, Y. Mizushima, N. Kawarada, H. Yamamoto, K. Sano, Y. Ōno, and T. Sasaki, J. Phys. Soc. Jpn. **93**, 044705 (2024).

- [21] K. Sano, Y. Ono, and Y. Yamada, J. Phys. Soc. Jpn. 74, 2885 (2005).
- [22] T. Nakano, K. Kuroki, and S. Onari, Phys. Rev. B 76, 014515 (2007).
- [23] K. Sano and Y. Ōno, J. Phys. Soc. Jpn. 76, 113701 (2007).
- [24] K. Okunishi, Phys. Rev. B 75, 174514 (2007).
- [25] E. Berg, T. H. Geballe, and S. A. Kivelson, Phys. Rev. B 76, 214505 (2007).
- [26] S. Nishimoto, K. Sano, and Y. Ohta, Phys. Rev. B 77, 085119 (2008).
- [27] T. Habaguchi, Y. Ono, H. Ying Du Gh, K. Sano, and Y. Yamada, J. Phys. Soc. Jpn. 80, 024708 (2011).
- [28] S. Nishioka, S. Sasaki, S. Nakagawa, M. Yashima, H. Mukuda, M. Yogi, and J. Shimoyama, Appl. Phys. Express 15, 023001 (2022).
- [29] T. M. Rice, S. Gopalan, and M. Sigrist, Europhys. Lett. 23, 445 (1993).
- [30] R. Arita, K. Kuroki, H. Aoki, and M. Fabrizio, Phys. Rev. B 57, 10324 (1998).
- [31] S. V. Streltsov and D. I. Khomskii, Phys. Usp. 60, 1121 (2017).
- [32] C. Autieri, G. Cuono, C. Noce, M. Rybak, K. M. Kotur, C. Agrapidis, K. Wohlfeld, and M. Birowska, J. Phys. Chem. C 126, 6791 (2022).
- [33] S.-L. Drechsler, O. Volkova, A. N. Vasiliev, N. Tristan, J. Richter, M. Schmitt, H. Rosner, J. Málek, R. Klingeler, A. A. Zvyagin, and B. Büchner, Phys. Rev. Lett. 98, 077202 (2007).
- [34] T. Hikihara, L. Kecke, T. Momoi, and A. Furusaki, Phys. Rev. B 78, 144404 (2008).
- [35] J. Sudan, A. Lüscher, and A. M. Läuchli, Phys. Rev. B 80, 140402 (2009).
- [36] S. Furukawa, M. Sato, S. Onoda, and A. Furusaki, Phys. Rev. B 86, 094417 (2012).
- [37] C. E. Agrapidis, S.-L. Drechsler, J. van den Brink, and S. Nishimoto, SciPost Phys. 6, 019 (2019).
- [38] T. Yamaguchi, S.-L. Drechsler, Y. Ohta, and S. Nishimoto, Phys. Rev. B 101, 104407 (2020).
- [39] S. R. White, Phys. Rev. Lett. 69, 2863 (1992).
- [40] S. R. White, Phys. Rev. B 48, 10345 (1993).
- [41] S. R. White, I. Affleck, and D. J. Scalapino, Phys. Rev. B 65, 165122 (2002).
- [42] M. Dolfi, B. Bauer, S. Keller, and M. Troyer, Phys. Rev. B 92, 195139 (2015).
- [43] X. Lu, D.-W. Qu, Y. Qi, W. Li, and S.-S. Gong, Phys. Rev. B 107, 125114 (2023).
- [44] Y. Shen, G.-M. Zhang, and M. Qin, Phys. Rev. B 108, 165113 (2023).
- [45] M. Fabrizio, Phys. Rev. B 54, 10054 (1996).

- [46] K. Kuroki, R. Arita, and H. Aoki, J. Phys. Soc. Jpn. 66, 3371 (1997).
- [47] M. Fishman, S. R. White, and E. M. Stoudenmire, Sci-Post Phys. Codebases , 4 (2022).
- [48] I. Doi, K. Sano, and K. Takano, Phys. Rev. B 45, 274 (1992).