# Enhanced Phonon-Phonon Interactions and Weakened Electron-Phonon Coupling in Charge-Density-Wave Topological Semimetal EuAl<sub>4</sub> with a Possible Intermediate Electronic State

Shize Cao<sup>1,2</sup>, Feng Jin<sup>1</sup>, Yun-Ze Long<sup>2,†</sup>, Jianlin Luo<sup>1,3</sup>, Qingming Zhang<sup>1,4</sup> and Zhi-Guo Chen<sup>1,3,\*</sup>

 Beijing National Laboratory for Condensed Matter Physics, Institute of Physics, Chinese Academy of Sciences Beijing 100190, China

> College of Physics, Qingdao University,
>  Qingdao 266071, China

 Songshan Lake Materials Laboratory, Dongguan, Guangdong, 523808, China

4. School of Physical Science and Technology,

Lanzhou University,

Lanzhou 730000, China

\*Email: zgchen@iphy.ac.cn \*Email: yunze.long@qdu.edu.cn The origin of charge density wave (CDW) is a long-term open issue. Furthermore, the evolution of phonon-phonon interactions (PPI) across CDW transitions has rarely been investigated. Besides, whether electron-phonon coupling (EPC) would be weakened or enhanced after CDW transitions is still under debate. Additionally, CDW provides a fertile ground for uncovering intriguing intermediate electronic states. Here, we report a Raman spectroscopy study of the PPI and EPC in topological semimetal EuAl4 exhibiting a CDW phase below temperature  $T_c \sim 145$  K. The free-charge-carrier-density ( $n_c$ ) and temperature dependences of the Fano asymmetric factors (1/|q|) of the two phonon modes  $A_{1g}$  and  $B_{1g}$  indicates that below  $T_c$ , the EPC becomes weakened probably due to the reduction of the n<sub>c</sub>. Interestingly, in the temperature range 50—145 K, the steep growth of the 1/|q| leading to the significant deviation from the linear dependence on the  $n_c$ , together with the shoulder-like features in the temperature evolutions of the 1/|q| and the  $n_c$  around 50 K, implies the possible existence of an intermediate electronic state with the EPC distinctly larger than the CDW ground state in EuAl<sub>4</sub>. Furthermore, below  $T_c$ , the faster decrease in the full width at half maxima of the B<sub>1g</sub> phonon mode representing the collective vibrations of the CDW-modulated Al<sup>1</sup> atoms suggests that a remarkable growth of the PPI for the B<sub>1g</sub> phonon mode after the CDW phase transition, which is in contrast to the weakening of the EPC and thus may mainly arise from the strengthening of lattice anharmonicity in EuAl<sub>4</sub>. Our results not only highlight the significance of the enhanced PPI and the weakened EPC in completely understanding the formation of the CDW phase but also initiate the exploration of novel intermediate electronic states in EuAl4.

## 1. Introduction

Charge density wave (CDW), which represents a quantum state of matter with the charge density and underlying lattice periodically modulated, has generated enormous interest in the scientific community because it provides a platform for realizing a variety of quantum phenomena, such as electronic nematic state<sup>[1-8]</sup>, axion insulator state<sup>[9-13]</sup>, superconductivity<sup>[14-22]</sup> and anomalous Hall effect<sup>[23]</sup>. Therein, electronic nematic state, which was revealed to show an intriguing entanglement with unconventional superconductivity<sup>[24-29]</sup>, is a type of

intermediate electronic states adjacent to CDW ground state. Revealing the mechanism of the formation of CDW states is an important step towards not only searching for new CDW materials but also achieving interesting quantum phenomena. However, the driving mechanism for the formation of CDW remains elusive. For one-dimensional systems, the Fermi surface nesting was proposed to cause the divergence of the Lindhard response function, which can result in the presence of CDW order<sup>[30-31]</sup>. Nonetheless, since small deviation from perfect Fermi nesting would greatly suppress the divergence of the Lindhard response function, Fermisurface-nesting induced CDW were observed in few realistic materials. Many-body interactions including phonon-phonon interactions (PPI) and electron-phonon coupling (EPC) play crucial roles in the emergence of various quantum states in condensed matter<sup>[32-33]</sup>. Therein, a sufficiently strong momentum-dependent EPC was suggested to trigger Kohn anomaly (or phonon softening), which can also induce a CDW phase transition<sup>[34]</sup>. It is a pity that a consensus on the evolution of the strength of EPC across CDW transitions has not been reached, e.g., the EPC strength decreases in  $ZrTe_3^{[35]}$  but increases in  $La_{1,8-x}Eu_{0,2}Sr_xCuO_{4+\delta}^{[33]}$  upon entering the CDW state. In addition, the change in the strength of phonon-phonon interactions (PPI) across CDW transitions has rarely been reported<sup>[32]</sup>.

A rare-earth intermetallic EuAl<sub>4</sub> crystallizes in the centrosymmetric tetragonal structure (the space group *I*4/*mmm*) with two types of Al atoms—Al<sup>1</sup> and Al<sup>2</sup>. Below a critical temperature  $T_c \sim 145$  K, EuAl<sub>4</sub> was revealed to undergo an incommensurate CDW order with the positions of the Al<sup>1</sup> and Eu atoms modulated<sup>[36-41]</sup>. Besides, at  $T_{\chi} \sim 10.1$  K in the helical spin-density-wave state of EuAl<sub>4</sub>, a first-order phase transition gives rise to a spontaneous flipping of spin chirality<sup>[42-43]</sup>. Moreover, nontrivial topology including topological non-trivial bands in momentum space<sup>[44-45]</sup> and topological spin textures—skyrmion in real space was proposed to exist in EuAl<sub>4</sub><sup>[46]</sup>. Furthermore, topological Hall effect is likely to accompany with the CDW in EuAl<sub>4</sub><sup>[47]</sup>. Therefore, EuAl<sub>4</sub> can serve as a platform for studying the interplay between CDW and nontrivial topology. Clarifying the microscopic mechanism for the formation of the CDW entangled with nontrivial topology in EuAl<sub>4</sub> would lay a solid foundation for exploring exotic effects arising from the combination of CDW and nontrivial topology. Previous investigations

indicate that the softening of a transverse acoustic phonon mode in EuAl<sub>4</sub> is a crucial driving force for the presence of its CDW order<sup>[48]</sup>. Nonetheless, the evolutions of the EPC and PPI across CDW transitions in EuAl<sub>4</sub>, which is expected to offer significant information for completely understanding microscopic mechanism for its CDW formation, were seldom investigated by experiments.

Raman spectroscopy is an efficient experimental technique for probing phonon modes which include the information about PPI and EPC in solids<sup>[32, 35, 49-52]</sup>. Thus, a Raman spectroscopy study of the temperature evolutions of the Raman-active phonons across the CDW transition in topological semimetal EuAl<sub>4</sub>, which has yet been performed up to now, would shed light on the evolutions of PPI and EPC. Here, we performed the Raman spectroscopy measurements of the (001) faces of the EuAl<sub>4</sub> single crystals in the temperature range from 15 to 300 K in the backscattering configuration on a Horiba Jobin Yvon LabRAM HR Evolution micro-Raman spectrometer using the 473 nm laser as the light source (see the details about the single-crystal growth, and the X-ray-diffraction characterization in Experimental Section). The EuAl<sub>4</sub> single crystals were cooled using low-temperature helium exchange gas in an AttoDRY 2100 cryostat.

## 2. Results and Discussion

**Figure 1**a and 1b depict two asymmetric peak-like features around 247 cm<sup>-1</sup> and 390 cm<sup>-1</sup> in the Raman spectra of the EuAl<sub>4</sub> single crystals at different temperatures. To study the nature of the observed peak-like features, we analyzed the *I*4/*mmm* space group of its crystal structure. The phonon modes of EuAl<sub>4</sub> at the  $\Gamma$  point can be decomposed into the following irreducible representations:  $[A_{1g}+B_{1g}+2E_g] + [2A_{2u}+2E_u] + [A_{2u}+E_u]$ , where the first, second, and third terms represent the Raman-active, infrared-active, and the acoustic phonon modes, respectively. The corresponding Raman tensors of the *I*4/*mmm* space group can be expressed as:

$$A_{1g} = \begin{pmatrix} a & 0 & 0 \\ 0 & a & 0 \\ 0 & 0 & b \end{pmatrix} \qquad \qquad B_{1g} = \begin{pmatrix} c & 0 & 0 \\ 0 & -c & 0 \\ 0 & 0 & 0 \end{pmatrix} \tag{1}$$

$$E_g = \begin{pmatrix} 0 & 0 & 0 \\ 0 & 0 & d \\ 0 & d & 0 \end{pmatrix} \qquad E_g = \begin{pmatrix} 0 & 0 & -d \\ 0 & 0 & 0 \\ -d & 0 & 0 \end{pmatrix}$$
(2)

where the *a*, *b*, *c* and *d* are the tensor elements and their values depend on the cross-section of Raman scattering. Considering that the energies of two peak-like features in the Raman spectra of the EuAl<sub>4</sub> single crystals are quite close to those of the previously reported phonon modes  $B_{1g}$  (around 229.7 cm<sup>-1</sup>) and  $A_{1g}$  (around 359.9 cm<sup>-1</sup>) of its counterpart SrAl<sub>4</sub> with isostructure and isovalence (see **Table 1**). Thus, the asymmetric peak-like features around 247 cm<sup>-1</sup> and 390 cm<sup>-1</sup> in Figure 1a and 1b can be assigned as the  $B_{1g}$  and  $A_{1g}$  phonon modes, respectively. Therein, the  $B_{1g}$  and  $A_{1g}$  phonon modes separately represent the collective vibrations of the Al<sup>1</sup> and Al<sup>2</sup> atoms (see **Figure 2**a and 2b).

As is well known, fitting an asymmetric phonon mode using Breit-Wigner-Fano (i.e., BWF) line shape can yield the asymmetric factor 1/|q|, which quantifies the strength of EPC. To obtain the temperature dependences of the EPC strength of the asymmetric B<sub>1g</sub> and A<sub>1g</sub> phonon modes, we fit these two phonon modes using BWF line shapes<sup>[53-54]</sup>:

$$I(\omega) = I_0 \frac{\left(1 + \frac{\omega - \omega_{ph}}{q\Gamma}\right)^2}{1 + \left(\frac{\omega - \omega_{ph}}{\Gamma}\right)^2}$$
(3)

where  $I_0$ ,  $\omega_{ph}$ ,  $\Gamma$  and 1/|q| are the maximal intensity, energy, full width at half maxima (i.e., FWHM), and asymmetric factors of the BWF line shapes, respectively (see the fitting parameters at different temperatures in Table S1 of Supporting Information). The upper and lower panels of **Figure 3**a and 3b depict the BWF fits to the B<sub>1g</sub> and A<sub>1g</sub> phonon modes at two typical temperatures T = 15 K and 300 K, respectively. The asymmetric factors (i.e.,  $1/|q|(B_{1g}, 15 \text{ K}) \sim 0.012)$  for the BWF fits to the B<sub>1g</sub> and A<sub>1g</sub> phonon modes at T = 15 K is distinctly smaller than those (i.e.,  $1/|q|(B_{1g}, 300 \text{ K}) \sim 0.075$  and  $1/|q|(A_{1g}, 300 \text{ K}) \sim 0.055)$  at T = 300 K, which suggests that the EPC in EuAl<sub>4</sub> at T = 15 K is weaker than that at T = 300 K. To get the temperature evolution of the EPC, we plotted the two 1/|q| for the B<sub>1g</sub> and A<sub>1g</sub> phonon modes in the temperature range from 15 to 300 K in Figure 3c. Above  $T_c$ , the two 1/|q| show weak temperature dependences, but below  $T_c$ , the two 1/|q| decrease sharply with lowering temperature, which indicates that EPC is weakened after the CDW transition.

Figure 3c displays that the previously reported relative Drude weight  $S_D(T)/S_D(300 \text{ K})$  of EuAl<sub>4</sub> which is proportional to the free charge carrier density  $n_c$  as a function of temperature<sup>[55]</sup>. The significant suppression of the  $S_D(T)/S_D(300 \text{ K})$  below  $T_c$  manifests that the free charge carrier density is dramatically lowered after the CDW phase transition in EuAl<sub>4</sub>. Figure 3d shows that the two 1/|q| of the B<sub>1g</sub> and A<sub>1g</sub> phonon modes decrease with the lowering of the free charge carrier density, which suggests that the weakening of EPC after the CDW transition in EuAl<sub>4</sub> is likely to be caused by the reduction of the carrier density. In addition, as shown by the dashed line in Figure 3d, both the two 1/|q| of the B<sub>1g</sub> and A<sub>1g</sub> phonon modes below 50 K can be linearly extrapolated to zero at  $S_D(T)/S_D(300 \text{ K}) = 0$  (see the black dashed line in Figure 3d), which implies that in EuAl<sub>4</sub>, the vanishing of free charge carriers would make the B<sub>1g</sub> and A<sub>1g</sub> phonon modes recover their Lorentzian line shapes with 1/|q| = 0. Surprisingly, in the temperature from 50 to 145 K, on the right side of the red dashed vertical line in Figure 3d, the two 1/|q| of the B<sub>1g</sub> and A<sub>1g</sub> phonon modes grow steeply and deviate significantly from the linear dependence on the  $S_D(T)/S_D(300 \text{ K})$ . It is well known that the BWF line shapes of the phonon modes in solids arise from the coupling between phonons and electron-hole pair excitations due to EPC<sup>[53-54]</sup>. The abrupt growth of the two 1/|q| of the B<sub>1g</sub> and A<sub>1g</sub> phonon modes with increasing temperature from 50 to 145 K suggests that in EuAl<sub>4</sub>, an intermediate electronic state with distinctly larger EPC than the incommensurate CDW ground state may exists in the temperature range 50—145 K, which is supported by the presence of the shoulder-like features around  $T \sim$ 50 K in the temperature dependences of the 1/|q| here (see the purple down arrow in Figure 3c) and the previously reported  $S_D(T)/S_D(300 \text{ K})$  (see the red up arrow in Figure 3c).

To estimate the evolution of the PPI across the CDW phase transition in EuAl<sub>4</sub>, we studied the temperature evolutions of the FWHMs and energies of its  $B_{1g}$  and  $A_{1g}$  phonon modes. Figure 4a and 4b show that the FWHM of the  $B_{1g}$  phonon mode drops more fastly below  $T_c$  than above  $T_c$ , while the FWHM of the  $A_{1g}$  phonon mode shows unobvious anomaly. Given the anharmonic and harmonic contributions to the FWHMs of the  $B_{1g}$  and  $A_{1g}$  phonons, the temperature dependence of the FWHM of  $A_{1g}$  phonon above and below  $T_c$  can be fit well using one PPI

parameter ( $\lambda_{ph-ph} \sim 0.38$ ) in the temperature range 15—300 K based on the following relationship<sup>[32, 56-57]</sup>:

$$\Gamma(T) = \Gamma_0 \left[ 1 + \frac{2\lambda_{ph-ph}}{\exp\left(\frac{\hbar\omega_0}{2k_BT}\right) - 1} \right]$$
(4)

where  $\omega_0$  and  $\Gamma_0$  are the energy and linewidth of phonon at 0 K (see the fitting parameters in Table S2 of Supporting Information). By contrast, the PPI parameter for fitting the temperature evolution of the B<sub>1g</sub> phonon FWHM increases from 0.04 to 0.31 upon entering the CDW state (see the fitting parameters in Table S2). Considering that the B<sub>1g</sub> phonon, rather than the A<sub>1g</sub> phonon, corresponds to the collective vibrations of the Al<sup>1</sup> atoms which are modulated periodically after the CDW transition, the CDW phase transition in EuAl<sub>4</sub> leads to a remarkable growth of the PPI for the B<sub>1g</sub> phonon below *T<sub>c</sub>*.

To check the enhancement of the phonon-phonon interactions in EuAl<sub>4</sub> after the CDW transition, we plotted the energies of the B<sub>1g</sub> and A<sub>1g</sub> phonon modes as a function of temperature in Figure 4c and 4d, respectively. Generally, phonon-mode energy can be given by the following relationships which contain anharmonic ( $\omega_{ah}(T)$ ), quasi-harmonic ( $\omega_{qh}(T)$ ) and harmonic (i.e.,  $\omega_0$ ) terms<sup>[32, 56-57]</sup>:

$$\omega(T) = \omega_h + \omega_{qh}(T) + \omega_{ah}(T)$$
(5)

$$\omega_{ah}(T) = -\omega_0 \left\{ \left( \frac{\Gamma_0}{\sqrt{2}\omega_0} \right)^2 \left[ 1 + \frac{4\lambda_{ph-ph}}{\exp\left(\frac{\hbar\omega_0}{2k_BT}\right) - 1} \right] \right\}$$
(6)

$$\omega_{qh}(T) = \omega_0 \left\{ \exp\left[ -3\gamma \int_0^T \alpha_i(T') dT' \right] - 1 \right\}$$
(7)

where  $\gamma$  is the Grüneisen parameter of a phonon mode and  $\alpha_i(T')$  is the coefficient of the linear thermal expansion at temperature T'. Here, the temperature dependences of the quasiharmonic terms of the B<sub>1g</sub> and A<sub>1g</sub> phonon energies are given by the product of the Grüneisen constant  $\gamma$  and the integral of the linear expansion coefficient up to a temperature T (see the integral of the linear expansion coefficient in Figure S1 of Supporting Information)<sup>[58]</sup>. Therein, the temperature dependence of the linear expansion coefficient of EuAl<sub>4</sub> were obtained by the previously reported thermodynamic investigation. Thus, fitting the temperature dependences of the B<sub>1g</sub> and A<sub>1g</sub> phonon energies based on Equation (5)-(7) yields the Grüneisen constants (for the B<sub>1g</sub> phonon,  $\gamma_{B_{1g}} = 1.9$  above  $T_c$  and  $\gamma_{B_{1g}} = 6.1$  below  $T_c$  and for the A<sub>1g</sub> phonon,  $\gamma_{A_{1g}} =$ 1.8 above and below  $T_c$ ) and the PPI parameters (for the B<sub>1g</sub> phonon,  $\lambda \frac{B_{1g}}{ph-ph} = 0.04$  above  $T_c$ and  $\lambda \frac{B_{1g}}{ph-ph} = 0.31$  below  $T_c$ , while for the A<sub>1g</sub> phonon,  $\lambda \frac{A_{1g}}{ph-ph} = 0.38$  above and below  $T_c$ ), which are consistent with the PPI parameters obtained via fitting the temperature dependences of the FWHMs of the B<sub>1g</sub> and A<sub>1g</sub> phonons based on Equation (4) (see the fitting parameters in Table S2 of Supporting Information).

It is worth noticing that PPI not only can be mediated by electrons due to  $EPC^{[59]}$  but also can come from lattice anharmonicity<sup>[32, 57, 60]</sup>. If the PPI in EuAl<sub>4</sub> are mediated by electrons, the decrease in the EPC strengths estimated from the two 1/|q| of the B<sub>1g</sub> and A<sub>1g</sub> phonon modes upon entering the CDW state should correspond to the weakening of the PPI. On the contrary, after the CDW phase transition in EuAl<sub>4</sub>, the PPI parameter for the B<sub>1g</sub> phonon is enhanced from 0.04 to 0.31. Thus, the PPI in EuAl<sub>4</sub> should mainly arise from lattice anharmonicity. Moreover, the remarkable growth of the PPI for the B<sub>1g</sub> phonon below  $T_c$  implies the strengthening of lattice anharmonicity after the CDW phase transition in EuAl<sub>4</sub>.

#### 3. Conclusion

In summary, using Raman spectroscopy, we have investigated the PPI and EPC in CDW topological semimetal EuAl<sub>4</sub>. Two asymmetric peak-like features in the Raman spectra of the EuAl<sub>4</sub> single crystals are assigned to the Raman-active phonon modes  $A_{1g}$  and  $B_{1g}$ . Below  $T_c$ , the reduction of the Fano asymmetric factors (1/|q|) of the two phonon modes  $A_{1g}$  and  $B_{1g}$  indicates that the EPC becomes weakened after the CDW phase transition. Moreover, the decrease in the Fano asymmetric factors (1/|q|) is accompanied with the suppression of free charge carrier density  $(n_c)$ , which suggests that the weakening of the EPC in EuAl<sub>4</sub> is likely caused by the reduction of the  $n_c$ . Unexpectedly, in the temperature range 50—145 K, the two 1/|q| grow steeply and deviate significantly from the linear dependences on the  $n_c$ . The steep

growth of the 1/|q|, combined with the shoulder-like features in the temperature evolutions of the 1/|q| and the  $n_c$  around 50 K, implies the possible existence of an intermediate electronic state with the EPC distinctly larger than the CDW ground state in EuAl<sub>4</sub>. Furthermore, the FWHM of the B<sub>1g</sub> phonon mode representing the collective vibrations of the CDW-modulated Al<sup>1</sup> atoms decreases more fastly below  $T_c$  than above  $T_c$ , which manifests that a remarkable growth of the PPI for the B<sub>1g</sub> phonon mode after the CDW phase transition. Since the remarkable growth of the PPI for the B<sub>1g</sub> phonon mode is in contrast to the weakening of the EPC below  $T_c$ , the PPI enhancement may mainly originate from the strengthening of lattice anharmonicity in EuAl<sub>4</sub>. Our work not only establishes the importance of the enhanced PPI and the weakened EPC for revealing the formation mechanism of the CDW phase but also offers a clue to discovering exotic intermediate electronic states in EuAl<sub>4</sub>.

#### **Experimental Section**

*Synthesis of the EuAl<sub>4</sub> single crystals*: The EuAl<sub>4</sub> single crystals were prepared by aluminum self-flux methods<sup>[36-38, 58]</sup>. Eu pieces and Al spheres with a molar ratio of 1:9 were put into the alumina crucible. The alumina crucible was then sealed in an evacuated quartz tube. The ampoule was heated to 1173 K within 10 h, held for 10 h to melt the Eu pieces and Al spheres, and then cooled to 973 K as a rate of 2 K/h. The hot ampoule was placed in the centrifuge to separate the EuAl<sub>4</sub> single crystals from the Al molten liquid.

*X-ray-diffraction characterization*: The crystal structure of the EuAl<sub>4</sub> single crystals was characterized using powder X-ray diffractometer (Rigaku) equipped with a Cu K $\alpha$  X-ray source (wavelength  $\lambda = 1.5406$ Å) at room temperature in the Bragg-Brentano geometry. The measured X-ray-diffraction spectra was put in Figure S2 of Supporting Information in which the vertical magenta lines show the angle positions of the diffraction peaks of EuAl<sub>4</sub> in the standard card.

#### Acknowledgements

The authors acknowledge support from the Guangdong Basic and Applied Basic Research Foundation (Project No. 2021B1515130007), the National Natural Science Foundation of China (Project No. U21A20432 and 12274186), the strategic Priority Research Program of Chinese Academy of Sciences (Project No. XDB33000000), the National Key Research and Development Program of China (Grant No. 2022YFA1403800, 2024YFA1408301 and 2022YFA1402704) and the Synergetic Extreme Condition User Facility (SECUF, https://cstr.cn/31123.02.SECUF).

# **Conflict of Interest**

The authors declare no conflict of interest.

## **Author Contributions**

Z.-G.C. conceived and supervised this project; S.C. grew the single crystals; F.J. and Q.Z. built up the Raman measurement system; S.C. carried out the Raman measurements with the assistance of F.J.; Z.-G.C., S.C., Y.L. and J.L. analyzed the data; Z.-G.C. wrote the paper with the input from S.C..

#### References

[1] A. J. Achkar, M. Zwiebler, C. McMahon, F. He, R. Sutarto, I. Djianto, Z. Hao, M. J. P. Gingras, M. Hücker, G. D. Gu, A. Revcolevschi, H. Zhang, Y. J. Kim, J. Geck, D. G. Hawthorn, *Science* **2016**, *351* (6273), 576.

[2] T. Asaba, A. Onishi, Y. Kageyama, T. Kiyosue, K. Ohtsuka, S. Suetsugu, Y. Kohsaka, T. Gaggl, Y. Kasahara, H. Murayama, K. Hashimoto, R. Tazai, H. Kontani, B. R. Ortiz, S. D. Wilson, Q. Li, H. H. Wen, T. Shibauchi, Y. Matsuda, *Nat. Phys.* 2024, 20 (1), 40.

[3] W. Chen, W. Ren, N. Kennedy, M. H. Hamidian, S. Uchida, H. Eisaki, P. D. Johnson, S. M. O'Mahony, J. C. S. Davis, *Proc. Natl. Acad. Sci.U.S.A.* 2022, *119* (31), e2206481119.

[4] C.-w. Cho, J. Lyu, L. An, T. Han, K. T. Lo, C. Y. Ng, J. Hu, Y. Gao, G. Li, M. Huang, N. Wang, J. Schmalian, R. Lortz, *Phys. Rev. Lett.* 2022, *129* (8), 087002.

[5] C. Eckberg, D. J. Campbell, T. Metz, J. Collini, H. Hodovanets, T. Drye, P. Zavalij, M. H. Christensen, R. M. Fernandes, S. Lee, P. Abbamonte, J. W. Lynn, J. Paglione, *Nat. Phys.* 2020, 16 (3), 346.

- [6] Z. Jiang, H. Ma, W. Xia, Z. Liu, Q. Xiao, Z. Liu, Y. Yang, J. Ding, Z. Huang, J. Liu, Y. Qiao, J. Liu, Y. Peng, S. Cho, Y. Guo, J. Liu, D. Shen, *Nano Lett.* **2023**, *23* (12), 5625.
- [7] L. Nie, K. Sun, W. Ma, D. Song, L. Zheng, Z. Liang, P. Wu, F. Yu, J. Li, M. Shan, *Nature* 2022, 604 (7904), 59.
- [8] Y. Yao, R. Willa, T. Lacmann, S.-M. Souliou, M. Frachet, K. Willa, M. Merz, F. Weber, C. Meingast, R. Heid, A.-A. Haghighirad, J. Schmalian, M. Le Tacon, *Nat. Commun.* 2022, *13* (1), 4535.
- [9] B. Cheng, D. Cheng, T. Jiang, W. Xia, B. Song, M. Mootz, L. Luo, I. E. Perakis, Y. Yao, Y.
  Guo, J. Wang, *Nat. Commun.* 2024, *15* (1), 785.
- [10] J. Gooth, B. Bradlyn, S. Honnali, C. Schindler, N. Kumar, J. Noky, Y. Qi, C. Shekhar, Y.
- Sun, Z. Wang, B. A. Bernevig, C. Felser, Nature 2019, 575 (7782), 315.
- [11] M. D. Redell, S. Mukherjee, W.-C. Lee, Phys. Rev. B 2016, 93 (24), 241201.
- [12]B. Roy, J. D. Sau, *Phys. Rev. B* 2015, *92* (12), 125141.
- [13]Z. Wang, S.-C. Zhang, Phys. Rev. B 2013, 87 (16), 161107.
- [14]C. A. Balseiro, L. M. Falicov, Phys. Rev. B 1979, 20 (11), 4457.
- [15] A. H. Castro Neto, *Phys. Rev. Lett.* **2001**, *86* (19), 4382.
- [16] J. Chang, E. Blackburn, A. T. Holmes, N. B. Christensen, J. Larsen, J. Mesot, R. Liang, D.

A. Bonn, W. N. Hardy, A. Watenphul, M. v. Zimmermann, E. M. Forgan, S. M. Hayden, *Nat. Phys.* **2012**, *8* (12), 871.

- [17] E. Morosan, H. W. Zandbergen, B. S. Dennis, J. W. G. Bos, Y. Onose, T. Klimczuk, A. P.
- Ramirez, N. P. Ong, R. J. Cava, Nat. Phys. 2006, 2 (8), 544.
- [18] M. Naito, S. Tanaka, J. Phys. Soc. Jpn. 1982, 51 (1), 219.
- [19] B. R. Ortiz, L. C. Gomes, J. R. Morey, M. Winiarski, M. Bordelon, J. S. Mangum, I. W. H.

Oswald, J. A. Rodriguez-Rivera, J. R. Neilson, S. D. Wilson, E. Ertekin, T. M. McQueen, E. S. Toberer, *Phys. Rev. Mater.* **2019**, *3* (9), 094407.

- [20]B. R. Ortiz, S. M. L. Teicher, Y. Hu, J. L. Zuo, P. M. Sarte, E. C. Schueller, A. M. M. Abeykoon, M. J. Krogstad, S. Rosenkranz, R. Osborn, R. Seshadri, L. Balents, J. He, S. D. Wilson, *Phys. Rev. Lett.* **2020**, *125* (24), 247002.
- [21]Q. Wang, P. Kong, W. Shi, C. Pei, C. Wen, L. Gao, Y. Zhao, Q. Yin, Y. Wu, G. Li, H. Lei,

- J. Li, Y. Chen, S. Yan, Y. Qi, Adv. Mater. 2021, 33 (42), 2102813.
- [22] X. Xi, Z. Wang, W. Zhao, J.-H. Park, K. T. Law, H. Berger, L. Forró, J. Shan, K. F. Mak, *Nat. Phys.* **2016**, *12* (2), 139.
- [23]G. Zheng, C. Tan, Z. Chen, M. Wang, X. Zhu, S. Albarakati, M. Algarni, J. Partridge, L.
- Farrar, J. Zhou, W. Ning, M. Tian, M. S. Fuhrer, L. Wang, Nat. Commun. 2023, 14 (1), 678.
- [24] Y. Cao, D. Rodan-Legrain, J. M. Park, N. F. Q. Yuan, K. Watanabe, T. Taniguchi, R. M. Fernandes, L. Fu, P. Jarillo-Herrero, *Science* **2021**, *372* (6539), 264.
- [25] R. M. Fernandes, A. J. Millis, *Phys. Rev. Lett.* **2013**, *111* (12), 127001.
- [26]S. Kasahara, H. J. Shi, K. Hashimoto, S. Tonegawa, Y. Mizukami, T. Shibauchi, K. Sugimoto, T. Fukuda, T. Terashima, A. H. Nevidomskyy, Y. Matsuda, *Nature* 2012, *486* (7403), 382.
- [27]K. Nakayama, Y. Miyata, G. N. Phan, T. Sato, Y. Tanabe, T. Urata, K. Tanigaki, T. Takahashi, *Phys. Rev. Lett.* **2014**, *113* (23), 237001.
- [28] T. Shimojima, Y. Motoyui, T. Taniuchi, C. Bareille, S. Onari, H. Kontani, M. Nakajima, S. Kasahara, T. Shibauchi, Y. Matsuda, S. Shin, *Science* 2021, *373* (6559), 1122.
- [29]Q. Wang, Y. Shen, B. Pan, Y. Hao, M. Ma, F. Zhou, P. Steffens, K. Schmalzl, T. R. Forrest,
  M. Abdel-Hafiez, X. Chen, D. A. Chareev, A. N. Vasiliev, P. Bourges, Y. Sidis, H. Cao, J. Zhao, *Nat. Mater.* 2016, *15* (2), 159.
- [30] J. Lindhard, Kgl. Danske Videnskab. Selskab Mat.-Fys. Medd. 1954, 28.
- [31] R. E. Peierls, *Quantum theory of solids*, Clarendon Press, 1964.
- [32]G. He, L. Peis, E. F. Cuddy, Z. Zhao, D. Li, Y. Zhang, R. Stumberger, B. Moritz, H. Yang,H. Gao, T. P. Devereaux, R. Hackl, *Nat. Commun.* 2024, *15* (1), 1895.
- [33] Y. Y. Peng, A. A. Husain, M. Mitrano, S. X. L. Sun, T. A. Johnson, A. V. Zakrzewski, G. J.
  MacDougall, A. Barbour, I. Jarrige, V. Bisogni, P. Abbamonte, *Phys. Rev. Lett.* 2020, *125* (9), 097002.
- [34] W. Kohn, Phys. Rev. Lett. 1959, 2 (9), 393.
- [35] Y. Hu, F. Zheng, X. Ren, J. Feng, Y. Li, Phys. Rev. B 2015, 91 (14), 144502.
- [36] J. H. Wernick, H. J. Williams, A. C. Gossard, J. Phys. Chem. Solids 1967, 28 (2), 271.
- [37] S. Araki, Y. Ikeda, T. C. Kobayashi, A. Nakamura, Y. Hiranaka, M. Hedo, T. Nakama, Y.

Ōnuki, J. Phys. Soc. Jpn. 2014, 83 (1), 015001.

[38]A. Nakamura, Y. Hiranaka, M. Hedo, T. Nakama, Y. Miura, H. Tsutsumi, A. Mori, K. Ishida, K. Mitamura, Y. Hirose, K. Sugiyama, F. Honda, T. Takeuchi, T. D. Matsuda, E. Yamamoto, Y.

Haga, Y. nuki, in JPS Conference Proceedings, Vol. 3 J. Phys. Soc. Jpn., 2014.

- [39] A. Nakamura, T. Uejo, F. Honda, T. Takeuchi, H. Harima, E. Yamamoto, Y. Haga, K. Matsubayashi, Y. Uwatoko, M. Hedo, *J. Phys. Soc. Jpn.* **2015**, *84* (12), 124711.
- [40]S. Ramakrishnan, S. R. Kotla, T. Rekis, J.-K. Bao, C. Eisele, L. Noohinejad, M. Tolkiehn,C. Paulmann, B. Singh, R. Verma, *IUCrJ* 2022, 9 (3), 378.
- [41]S. Shimomura, H. Murao, S. Tsutsui, H. Nakao, A. Nakamura, M. Hedo, T. Nakama, Y. Ōnuki, J. Phys. Soc. Jpn. 2019, 88 (1), 014602.
- [42]H. Miao, J. Bouaziz, G. Fabbris, W. R. Meier, F. Z. Yang, H. X. Li, C. Nelson, E. Vescovo,S. Zhang, A. D. Christianson, H. N. Lee, Y. Zhang, C. D. Batista, S. Blügel, *Physical Review X*

2024, 14 (1), 011053.

[43] A. M. Vibhakar, D. D. Khalyavin, F. Orlandi, J. M. Moya, S. Lei, E. Morosan, A. Bombardi, *Commun. Phys.* **2024**, *7* (1), 313.

- [44] M. Kobata, S.-i. Fujimori, Y. Takeda, T. Okane, Y. Saitoh, K. Kobayashi, H. Yamagami, A. Nakamura, M. Hedo, T. Nakama, Y. Ōnuki, *J. Phys. Soc. Jpn.* **2016**, *85* (9), 094703.
- [45]L.-L. Wang, N. K. Nepal, P. C. Canfield, Commun. Phys. 2024, 7 (1), 111.

[46] R. Takagi, N. Matsuyama, V. Ukleev, L. Yu, J. S. White, S. Francoual, J. R. L. Mardegan,

S. Hayami, H. Saito, K. Kaneko, K. Ohishi, Y. Ōnuki, T.-h. Arima, Y. Tokura, T. Nakajima, S. Seki, *Nat. Commun.* **2022**, *13* (1), 1472.

- [47] T. Shang, Y. Xu, D. J. Gawryluk, J. Z. Ma, T. Shiroka, M. Shi, E. Pomjakushina, *Phys. Rev.* B 2021, 103 (2), L020405.
- [48] A. N. Korshunov, A. S. Sukhanov, S. Gebel, M. S. Pavlovskii, N. D. Andriushin, Y. Gao, J. M. Moya, E. Morosan, M. C. Rahn, *Phys. Rev. B* 2024, *110* (4), 045102.
- [49] Y. Chen, L. Wu, H. Xu, C. Cong, S. Li, S. Feng, H. Zhang, C. Zou, J. Shang, S. A. Yang,
  K. P. Loh, W. Huang, T. Yu, *Adv. Mater.* 2020, *32* (45), 2003746.
- [50]H. Wang, Y. Chen, M. Duchamp, Q. Zeng, X. Wang, S. H. Tsang, H. Li, L. Jing, T. Yu, E.
- H. T. Teo, Z. Liu, Adv. Mater. 2018, 30 (8), 1704382.

- [51]B. Su, Y. Song, Y. Hou, X. Chen, J. Zhao, Y. Ma, Y. Yang, J. Guo, J. Luo, Z.-G. Chen, *Adv. Mater.* **2019**, *31* (44), 1903498.
- [52]B. Su, Y. Huang, Y. H. Hou, J. Li, R. Yang, Y. Ma, Y. Yang, G. Zhang, X. Zhou, J. Luo, Z.-G. Chen, *Adv. Sci.* 2022, 9 (5), 2101532.
- [53]U. Fano, Phys. Rev. 1961, 124 (6), 1866.
- [54] P. Eklund, K. Subbaswamy, Phys. Rev. B 1979, 20 (12), 5157.
- [55] R. Yang, C. C. Le, P. Zhu, Z. W. Wang, T. Shang, Y. M. Dai, J. P. Hu, M. Dressel, *Phys. Rev. B* 2024, *109* (4), L041113.
- [56]H. M. Eiter, P. Jaschke, R. Hackl, A. Bauer, M. Gangl, C. Pfleiderer, *Phys. Rev. B* 2014, *90*(2), 024411.
- [57] P. G. Klemens, Phys. Rev. 1966, 148 (2), 845.
- [58] W. R. Meier, J. R. Torres, R. P. Hermann, J. Zhao, B. Lavina, B. C. Sales, A. F. May, *Phys. Rev. B* 2022, *106* (9), 094421.
- [59] D. Novko, M. Alducin, J. I. Juaristi, Phys. Rev. Lett. 2018, 120 (15), 156804.
- [60] N. K. Ravichandran, D. Broido, Phys. Rev. X 2020, 10 (2), 021063.



**Figure 1.** Two asymmetric Raman-active phonon modes  $B_{1g}$  and  $A_{1g}$  in the Raman spectra of EuAl<sub>4</sub> at different temperatures. The dashed curves in a) and b) are guides to the eye for the temperature evolutions of the  $B_{1g}$  and  $A_{1g}$  phonon modes, respectively.



**Figure 2.** Schematics of the collective vibrations of the  $Al^1$  and  $Al^2$  atoms in EuAl<sub>4</sub>, which separately correspond to the  $B_{1g}$  and  $A_{1g}$  phonon modes.



**Figure 3.** Strength of the Electron-phonon coupling in EuAl<sub>4</sub>. a) BWF fits to the B<sub>1g</sub> phonon mode at T = 15 K and 300 K. b) BWF fits to the A<sub>1g</sub> phonon mode at T = 15 K and 300 K. c) Temperature dependences of the asymmetric factors 1/|q| for the B<sub>1g</sub> and A<sub>1g</sub> phonon modes and the previously reported relative Drude weight  $S_D(T)/S_D(300$  K). The purple down arrow and the red up arrow in c) indicate the shoulder-like features in the temperature dependences of the 1/|q| and the  $S_D(T)/S_D(300$  K) around 50 K, respectively. d) Two 1/|q| of the B<sub>1g</sub> and A<sub>1g</sub> phonon modes as a function of the  $S_D(T)/S_D(300$  K). The red dashed vertical line in d) shows that on its right side (i.e., in the temperature range 50—145 K), the 1/|q| of the B<sub>1g</sub> and A<sub>1g</sub> phonon modes grow steeply and deviate significantly from the linear dependence on the  $S_D(T)/S_D(300$  K) (see the black dashed line), which can be linearly extrapolated to zero.



**Figure 4.** Full widths at half maxima (i.e., FWHMs) and energies of the B<sub>1g</sub> and A<sub>1g</sub> phonon modes in the Raman spectra of EuAl<sub>4</sub> as a function of temperature. a) Temperature dependence of the FWHM of the B<sub>1g</sub> phonon mode. The green and purple dashed lines in a) shows the fits to the temperature dependence of the FWHM below and above  $T_c$  based on Equation (4). The fitting yields the phonon-phonon interaction (PPI) parameters for the B<sub>1g</sub> phonon mode:  $\lambda_{ph-ph}$ ~ 0.31 at  $T < T_c$  and  $\lambda_{ph-ph} \sim 0.04$  at  $T > T_c$ . b) Temperature dependence of the FWHM of the A<sub>1g</sub> phonon mode. The PPI parameter for the A<sub>1g</sub> phonon mode  $\lambda_{ph-ph} \sim 0.38$  in the temperature range 15—300 K was obtained via the fitting shown by the purple dashed line in b). c) Temperature evolution of the B<sub>1g</sub> phonon energy. The fitting based on Equation (5)-(7) with the PPI parameters for the B<sub>1g</sub> phonon mode  $\lambda_{ph-ph} \sim 0.04$  and  $\lambda_{ph-ph} \sim 0.31$  yields the Grüneisen parameters  $\gamma = 1.9$  at  $T > T_c$  and  $\gamma = 6.1$  at  $T < T_c$ , respectively. d) Temperature evolution of the A<sub>1g</sub> phonon energy. The green and purple dashed lines in a) shows the fits to the temperature dependence of the A<sub>1g</sub> phonon energy based on Equation (5)-(7) with  $\gamma = 1.8$  and  $\lambda_{ph-ph} \sim 0.38$ .

Symmetry	Active	Calculated energy [SrAl4]	Experimental energy [EuAl4]
A <sub>1g</sub>	Raman	229.7 cm <sup>-1</sup>	246 cm <sup>-1</sup>
$B_{1g}$	Raman	359.9 cm <sup>-1</sup>	390 cm <sup>-1</sup>

Table 1. Energies of the Raman-active phonon modes  $B_{1g}$  and  $A_{1g}$  of EuAl\_4 and SrAl\_4