First-Principles and Machine Learning Insights into the Design of DOTT-Carbon and its Lithium-Ion Storage Capacity

Kleuton. A. L. Lima^{1,2}, Ana V. P. Abreu^{1,2}, Alysson M. A. Silva³, and Luiz A. Ribeiro Jr^{1,2,§}

¹Institute of Physics, University of Brasília, 70910-900, Brasília, Brazil

²Computational Materials Laboratory, LCCMat, Institute of Physics, University of Brasília, 70910-900, Brasília, Brazil

³ University of Brasília, College of Technology, Department of Mechanical Engineering, Brasília, Brazíl

§ribeirojr@unb.br

Abstract: Two-dimensional (2D) carbon-based materials are promising candidates for developing more efficient green energy conversion and storage technologies. This study presents a new 2D carbon allotrope, DOTT-Carbon, characterized by its distinctive and multi-ring structure featuring 12-, 8-, 4-, and 3-membered rings of carbon atoms. We explore its structural, mechanical, and lithium-ion storage properties by employing density functional theory and machine learning simulations. Phonon calculations confirm its structural stability and ab initio molecular dynamics simulations demonstrate its thermal resilience at elevated temperatures. The material exhibits anisotropic mechanical properties, with Young's modulus values varying between 280-330 GPa. DOTT-Carbon displays a lithium-ion storage capacity of 446.28 mAh/g, complemented by a low diffusion barrier (0.2-0.9 eV) and a high diffusion coefficient (> 1.0×10^{-6} cm²/s), possibly facilitating efficient lithium-ion transport. The stable open circuit voltage of 0.28 V also indicates its suitability as an anode material.

1 Introduction

Two-dimensional (2D) carbon materials have attracted significant attention due to their unique structural, thermal, and electronic properties [1, 2]. Most have been proven promising candidates for more efficient green energy conversion and storage technologies [3, 4], particularly for lithium-ion batteries (LIBs) [5]. Once the demand for sustainable energy storage solutions grows, these materials provide a versatile and cost-effective platform for developing new architectures and improving battery efficiency.

Porous 2D carbon structures have been shown to enhance lithium-ion storage performance [6–8]. The possibility of forming porous rings comprising more than eight atoms and large surface areas promotes efficient ion adsorption [9–15]. It facilitates rapid diffusion pathways for lithium ions. Graphyne (comprising a 12-atom ring) [16] and the biphenylene network (comprising an 8-atom ring)[17], for example, have demonstrated good lithium-ion storage capacities and fast charge/discharge cycles [18, 19]. These advancements highlight the critical role of porosity in tailoring the properties of 2D carbon-based materials for energy storage applications.

Despite these successful cases, the ongoing search for new 2D carbon allotropes with optimized electrochemical properties remains crucial to advancing nanoelectronics [20, 21]. Recent studies emphasize the potential of designing multi-ringed porous architectures to balance mechanical stability and high lithium-ion storage capacity [22–36]. In this context, we introduce DOTT-Carbon

(DOTT-C), a new 2D all-carbon allotrope characterized by 12-, 8-, 4-, and 3-membered rings, opening channels for a key structural framework for energy storage applications.

Herein, we investigate the structural, mechanical, and lithium-ion adsorption properties of DOTT-C using density functional theory (DFT) calculations and machine learning interatomic potentials (MLIPs). We confirm its stability through phonon calculations and ab initio molecular dynamics (AIMD) simulations. Importantly, the lithium diffusion barriers, storage capacity, and open-circuit voltage of DOTT-C were also explored. This newly proposed 2D carbon allotrope features a flat multi-ring structure that balances mechanical stability and efficient ion transport. The multi-ringed structure DOTT-C creates a distinctive porous topology that facilitates rapid lithium-ion diffusion and stable adsorption sites. These attributes position DOTT-Carbon as a promising high-performance anode material for LIBs.

2 Methodology

The structural, mechanical, and lithium-ion adsorption properties of DOTT-C were investigated using DFT calculations within the CASTEP code [37]. All calculations employed the Perdew-Burke-Ernzerhof (PBE) exchange-correlation function under the generalized gradient approximation (GGA) scheme [38]. A plane-wave energy cutoff of 450 eV and a Monkhorst-Pack k-point mesh of $10 \times 10 \times 1$ were adopted for Brillouin zone sampling. Convergence criteria for energy and forces were set to 1.0×10^{-5} eV and 1.0×10^{-3} eV/Å, respectively. Structural relaxations were performed with periodic boundary conditions, ensuring minimal residual forces and pressure below 0.01 GPa. A vacuum space of 20 Å was applied in the out-of-plane direction to eliminate interlayer interactions.

Phonon calculations used density functional perturbation theory (DFPT) [39]. AIMD simulations were carried out at 1000 K for 5 ps with a timestep of 1 fs to assess thermal stability. These simulations employed the Nosé-Hoover thermostat [40] within the NVT ensemble, monitoring structural integrity to detect any potential bond-breaking or atomic reconfigurations. The electronic band structure and density of states (DOS) were analyzed using a k-point grid of $10 \times 10 \times 1$ and $20 \times 20 \times 1$, respectively. Optical properties were further explored by calculating the complex dielectric constant under an external electric field, following established methodologies [41].

Lithium adsorption studies were conducted by placing Li atoms at various adsorption sites on the DOTT-C surface, followed by geometry optimization to determine the most energetically favorable configurations. The adsorption energy (E_{ads}) was calculated as $E_{ads} = E_{Li+DOTT-C} - (E_{DOTT-C} + E_{Li})$, where $E_{Li+DOTT-C}$ is the total energy of DOTT-C with adsorbed Li, E_{DOTT-C} is the energy of pristine DOTT-C, and E_{Li} is the energy of an isolated Li atom. Lithium diffusion barriers were determined using the nudged elastic band (NEB) method within CASTEP [42– 44]. The diffusion coefficient was estimated using the adsorption energies to quantify lithium-ion mobility across the DOTT-C surface.

The mechanical properties of DOTT-C were explored through classical reactive molecular dynamics simulations using the Large-scale Atomic/Molecular Massively Parallel Simulator (LAMMPS) [45]. A reactive force field derived from a moment tensor potential (MTP) [46, 47] was employed and developed with assistance from MLIP package [48, 49]. Training datasets for the MTP were constructed from stress-free and uniaxially strained supercells at varying temperatures, employing AIMD simulations within the Vienna Ab initio Simulation Package (VASP) [50–52]. Newton's equations of motion were integrated using the velocity Verlet algorithm with a timestep of 0.05 fs. Classical MD simulations were thermalized in the NPT ensemble for 100 ps. Elastic properties and fracture behavior using MLIPs were assessed at 300 K under uniaxial tensile strain with a constant engineering strain rate of 10^{-6} fs⁻¹. Using MLIP to investigate the mechanical properties of nanomaterials has consistently demonstrated its effectiveness and reliability [53–58].

3 Results

Figure 1 illustrates the atomic structure of the DOTT-C lattice. The unit cell, highlighted in black, consists of 10 carbon atoms and has lattice parameters of a = 6.58 Å along the x-direction and b = 5.66 Å along the y-direction. The C–C bond lengths exhibit slight variations, ranging from 1.37 Å to 1.48 Å. These bond lengths align with expected values for sp²-hybridized carbon, indicating strong covalent atomic interactions within the lattice. DOTT-C belongs to the P2/M space group and adopts C2H-1 symmetry, reflecting its symmetric arrangement.



Figure 1: Atomic structure of DOTT-C. The unit cell (in black) has dimensions of a = 9.46 Å (x-direction) e b = 6.08 Å (y-direction).

DOTT-C presents a formation energy of -8.25 eV/atom, indicating strong energetic stability. This value is comparable to other 2D carbon allotropes, such as graphene (-8.83 eV/atom) [59], sun-graphyne (-8.57 eV/atom) [60], and dodecanophene (-8.19 eV/atom) [61], graphenylene (-8.28 eV/atom) [62], porous-graphene (-6.93 eV/atom) [63], T-graphene (-7.87 eV/atom) [64], biphenylene (-7.95 eV/atom) [65], Graphenyldiene (-7.30 eV/atom) [63], and Irida-graphene (-6.96 eV/atom) [66]. While slightly lower than graphene, it is significantly more stable than several porous counterparts, including graphdiyne (-0.77 eV/atom) and γ -graphyne (-0.92 eV/atom) [67].

Phonon dispersion results of DOTT-C, obtained using DFPT (dark green curves) and MTP (dotted light green curves), are shown in Figure 2. The absence of imaginary frequencies points to its good dynamical stability, demonstrating that the structure can remain mechanically stable under moderate perturbations. The phonon branches exhibit smooth and continuous trends, characteristic of well-relaxed crystal lattices. The agreement between MTP-based results and DFPT outcomes validates the accuracy of the generated MLIP specifically for DOTT-C. This alignment also supports the application of ML-based potentials in classical reactive MD simulations conducted in this study. Moreover, the consistency between these methods enables efficient simulations of larger systems and longer timescales without compromising accuracy.

MLIP-based reactive MD simulations are crucial for studying the mechanical properties of nanostructured materials once they combine quantum-level accuracy with the computational ef-



Figure 2: Phonon dispersion analysis of DOTT-C calculated using DFPT (dark green) and MTP (light green) methods. The inset highlights the first Brillouin zone.

ficiency of classical simulations. Unlike purely ab initio approaches, which are computationally expensive for large systems and long timescales, MLIP models are trained on high-fidelity data from DFT calculations, enabling precise predictions of interatomic interactions. Importantly, reactive MD simulations can also capture the formation and breaking of chemical bonds — a critical feature for understanding fracture mechanics and deformation in nanomaterials — while maintaining computational costs comparable to conventional classical MD simulations. This feature makes them adequate for exploring complex mechanical behaviors, such as anisotropic stress responses and strain-induced bond reconfigurations, in systems with intricate atomic arrangements. Therefore, the validated MLIP potential for DOTT-C allows for accurate modeling of its multiringed structure under mechanical stress, providing deep insights into its fracture dynamics and mechanical resilience.

Figure 3 illustrates the thermal stability of DOTT-C as assessed through AIMD simulations at 1000 K. The insets depict the top and side views of the structure from the final AIMD snapshot at 5 ps. No bond breaking or significant structural reconfigurations are observed during the simulation, confirming the thermal resilience of DOTT-C under elevated temperature conditions. The absence of substantial in-plane and out-of-plane distortions suggests its practical use in nanoelectronic applications operating at high temperatures. This feature is interesting for energy storage systems, such as LIB anodes, where materials are often subjected to thermal stress during charge and discharge cycles.

The flat pattern observed in the energy curve over the time evolution indicates that DOTT-C can keep its stability under extreme conditions. This stability trend arises from its robust bonding framework, which resists thermal fluctuations, preventing atomic rearrangements. Such behavior underscores the thermal resilience of DOTT-C, which is a critical feature for applications like LIB anodes, where materials undergo repetitive thermal cycling during operation.

We now explore the electronic properties of DOTT-C, highlighting its potential for efficient charge transport and energy storage applications. Figure 4(a) presents the electronic band structure of pristine DOTT-C along high-symmetry k-paths, as shown in Figure 2. One can note that the



Figure 3: The AIMD simulation results at 1000 K for the lattice total energy as a function of time. Insets show top and side views of the DOTT-C structure for the final simulation stage.

material exhibits a metallic nature with bands crossing the Fermi level. This metallic behavior suggests that DOTT-C can efficiently conduct electrons, a critical property for its application as an anode material in lithium-ion batteries. Figure 4(b) shows the projected density of states (PDOS), where the contributions from s- (light green) and p-orbitals (dark green) are depicted. The dominant p-orbital contributions near the Fermi level points the role played by carbon's sp²-hybridized electrons in dictating the material's electronic properties.

Figures 4(c) and 4(d) illustrate the spatial distribution of the highest occupied crystalline orbital (HOCO, red) and the lowest unoccupied crystalline orbital (LUCO, green), respectively. The HOCO is delocalized across the lattice's 3- and 8-membered rings, while the LUCO concentrates primarily on 4- and 12-membered rings. These orbital distributions show distinct channels for electron and hole transport. In this way, DOTT-C can have a certain level of control over charge transport and storage processes. The spatial distribution of HOCO and LUCO also reveals the potential of DOTT-C in minimizing charge recombination, which is advantageous for energy applications.

The electron localization function (ELF) profile of the DOTT-C lattice is depicted in Figure 4(e), providing insights into the material's bond and electronic localization characteristics. The ELF map points to highly localized electron density on the C-C bonds (red spots), corresponding to the material's strong covalent interactions. The delocalized (yellow) regions observed in larger rings reflect the metallic nature of DOTT-C, facilitating charge transport across the lattice. These results collectively highlight DOTT-C as a candidate for applications requiring an efficient charge transport mechanism.

The color scheme in the ELF plot ranges from blue (0.0) to red (0.7), representing the probability of electron localization within the lattice. Blue regions (low ELF values) correspond to areas of low electron localization, indicating delocalized electronic states. Red regions (high ELF values) represent highly localized electrons, typically associated with strong covalent bonding. The yellowgreen intermediate regions indicate partial localization, reflecting the shared nature of electrons in



Figure 4: Electronic structure of DOTT-C. (a) Band structure along high-symmetry k-paths and (b) PDOS. Panels (c) and (d) depict the Highest Occupied Crystalline Orbital (HOCO, red) and Lowest Unoccupied Crystalline Orbital (LUCO, green) distributions. Panel (e) illustrates the electron localization function (ELF).

the larger carbon rings.

In the context of DOTT-C, the red spots along the C–C bonds confirm the presence of robust covalent interactions, which are responsible for maintaining the lattice's structural integrity. Simultaneously, the delocalized yellow regions within the larger rings further emphasize DOTT-C's metallic behavior, enabling efficient charge transport pathways. This combination of localized bonding and delocalized electronic states indicates the material's potential for applications requiring high electrical conductivity and mechanical stability, such as energy storage and electronic devices.

Figure 5 shows the optical properties of DOTT-C, highlighting its anisotropic behavior along the x- (dark green) and y-directions (light green). In Figure 5(a), the absorption coefficient (α) is plotted against photon energy, demonstrating broad optical responses spanning from the visible to ultraviolet (UV) range. Several peaks in the absorption spectrum are present, indicating DOTT-C's good absorption efficiency, particularly in the UV range.

The anisotropic behavior observed in the absorption coefficient (α) of DOTT-C, as shown in Figure 5(a), stems from its unique multi-ringed lattice structure and the direction-dependent interaction of electromagnetic waves with its electronic states. The distinct orientations of C–C bonds and ring configurations in the x- and y-directions result in varying electronic transition probabilities, leading to distinct absorption profiles for each polarization. Moreover, the intense absorption activity in the UV range is attributed to the delocalized π -electrons and the material's metallic nature. These features enable high-energy electronic transitions, particularly from bonding to anti-bonding orbitals, which are prevalent in this energy range. As shown above, the dense



Figure 5: Optical properties of DOTT-C as a function of photon energy and for light polarized along the x-direction (dark green) and y-direction (light green). Panels (a,b,c) illustrate the results for absorption coefficient (α), (b) reflectivity (R), and (c) refractive index (η), respectively. The gray region stands for the visible range of the spectrum.

electronic states near the Fermi level, combined with the strong π - π^* transitions, amplify DOTT-C's absorption efficiency in the UV spectrum. This property makes DOTT-C a promising candidate for applications requiring efficient light absorption, such as UV detectors, photovoltaic devices, and other optoelectronic technologies.

The reflectivity (R) results are presented in Figure 5(b). One can note a low reflectivity across the energy range, consistently below 0.8. The R values are higher within the infra-red range. These values drop dramatically for photon energies higher than 1.9 eV. This behavior suggests that DOTT-C can transmit a significant portion of the incident light and is valid for optical coatings or light-filtering applications. The anisotropic nature of reflectivity is more pronounced in the infrared region. The pronounced anisotropy in reflectivity (R) within the infrared range, as shown in Figure 5(b), arises from the direction-dependent electronic structure and bonding configuration of DOTT-C. The material's multi-ringed lattice creates an uneven distribution of electronic states, which interacts differently with incoming electromagnetic waves depending on the polarization. In the infrared range, this anisotropy is amplified due to the involvement of low-energy vibrational modes and charge polarization effects, which vary between the x- and y-directions, leading to distinct reflectivity values.

It is worth mentioning that the abrupt drop in reflectivity for photon energies above 1.9 eV and the tendency toward zero reflectivity beyond the visible range is due to the material's strong absorption in the UV region, as observed in panel (a). At these higher photon energies, the incident light is predominantly absorbed rather than reflected, owing to the high density of electronic transitions facilitated by the delocalized π -electrons in the lattice. This sharp transition to nearzero reflectivity highlights DOTT-C's efficiency in absorbing high-energy photons, making it highly suitable for applications in optical coatings and filters where minimal reflection and maximal transmission of specific light wavelengths are desired.

In Figure 5(c), the refractive index (η) is displayed as a function of photon energy, also showing polarization-dependent behavior. The refractive index decreases with increasing photon energy and converges to approximately 1.0 at higher energies. This trend highlights the birefringent properties of DOTT-C, where η varies with light polarization, pointing to its applicability in devices that rely on controlled light propagation, such as waveguides and optical sensors. The rapid drop and eventual convergence of the refractive index (η) to approximately 1.0 at higher photon energies, as seen in Figure 5(c), can be explained by the material's electronic response to electromagnetic waves. At lower photon energies, the interaction of light with the electronic cloud of DOTT-C is more significant, leading to higher refractive indices. However, as the photon energy increases, the electrons in the lattice can no longer respond effectively to the rapidly oscillating electric field of the incoming light. This diminished interaction causes η to decrease sharply.

Another relevant result is that the convergence of η to 1.0 at high photon energies indicates that the material becomes optically transparent in this range as light passes through without significant refraction or reflection. This behavior is characteristic of many materials where the electronic transitions occur predominantly in lower energy ranges, leaving the higher-energy photons less affected. The anisotropic nature of η , evident in its polarization-dependent behavior, further emphasizes DOTT-C's potential in birefringent applications, such as waveguides, polarizers, and optical sensors, where precise control of light propagation and polarization is crucial.

The mechanical response of DOTT-C under uniaxial stress, evaluated using the MLIP method, is shown in Figure 6. The stress-strain curves are plotted for the x-direction (dark green) and ydirection (light green), showcasing the anisotropic mechanical properties of DOTT-C under tensile loading. The linear region of the curves at lower strains corresponds to the elastic behavior of the material. At higher strain values, a peak is observed, indicating the ultimate stress (maximum stress) DOTT-C can sustain before fracturing.



Figure 6: Stress-strain curve of DOTT-C under uniaxial stress in the x-direction (dark green) and y-direction (light green), calculated using the MLIP method.



Figure 7: Fracture patterns and stress distribution in DOTT-C, initially unstressed in panel (a), under uniaxial strain in the x-direction (panels b and c) and y-direction (panels d and e). The von Mises stress distribution is illustrated with a color gradient, where blue represents low stress and red indicates high stress.

In the x-direction, DOTT-C achieves an ultimate stress of approximately 60 GPa at a fracture strain of 16.9% (dashed dark green line). In contrast, the y-direction displays a lower ultimate stress of around 39 GPa, with a fracture strain of 12.8% (dashed light green line). These distinct responses in the two directions reveal the anisotropic nature of DOTT-C, which arises from the alignment of its multi-ringed structure. The variation in ring configurations between the x- and y-directions influences the material's bond stretching and deformation under applied stress.

From these stress-strain curves, Young's modulus of DOTT-C is determined to be approximately 331.75 GPa in the x-direction and 281.55 GPa in the y-direction, further highlighting its anisotropic mechanical properties. While DOTT-C exhibits significant stiffness, its Young's modulus is lower than that of graphene (near 1 TPa) [68, 69], which can be attributed to the porous, multi-ring structure of DOTT-C. While imparting rigidity, this architecture introduces additional flexibility compared to graphene's dense hexagonal framework. The higher stiffness and ultimate stress observed along the x-direction reflect the structural alignment and bonding configuration of DOTT-C, enabling it to resist deformation more effectively in that orientation.

Figure 7 illustrates the fracture patterns and stress distribution in DOTT-C under uniaxial strain applied along the x- and y-directions. The von Mises stress (σ^{VM}) distribution, represented by a color gradient ranging from blue (low stress) to red (high stress), provides insights into how strain impacts different regions of the lattice at various deformation stages and highlights the material's fracture behavior.

Figure 7(a) shows the unstressed DOTT-C lattice without visible stress concentrations. Under strain in the x-direction (panels b and c), stress concentrations form around the multi-ring junctions and larger rings. No bond ruptures occur at a strain of 16.5% (panel b) at these high-stress regions. By 16.9% strain (panel c), micro-cracks propagate parallel to the loading direction, eventually coalescing into more extensive fractures, leading to significant lattice rupture. This behavior indicates that the structural alignment of the larger rings along the x-direction introduces weak points, guiding the fracture pathways through these regions.



Figure 8: Lithium adsorption and diffusion properties of DOTT-C. Panel (a) illustrates the adsorption energy landscape pathways and profile for a single Li atom migrating on the DOTT-C surface. Panel (b) depicts the temperature-dependent diffusion coefficients. The colored lines in panels refer to the colored arrows in panel (a). For comparison, the black circles refer to the Li-ion diffusion across two DOTT-C sheets (see Figure 9). The black dotted lines in panel (b) represent the Li-ion mobility for graphene at 300K.

When strain is applied along the y-direction (panels d and e), the fracture dynamics shift due to the differing orientation of the rings relative to the applied stress. At 12.6% strain (panel d), stress accumulates more uniformly across the lattice. By 12.8% strain (panel e), localized stress concentrations cause rapid crack propagation parallel to the strain direction. These cracks expand into an interconnected fracture network, resulting in complete structural failure.

The observed parallel fracture pattern in DOTT-C under uniaxial strain, as depicted in Figure 7, highlights a unique mechanical behavior distinct from many other 2D carbon allotropes [70–75]. This behavior can be attributed to the structural arrangement of the multi-ringed lattice. In DOTT-C, the larger 12-membered rings and multi-ring junctions align along the direction of applied strain, acting as stress concentrators. These structural features serve as inherent weak points where bonds are more prone to rupture under tension, guiding the fracture pathways along the strain direction. In contrast, other 2D carbon allotropes, such as graphene [76] or graphyne [77], often exhibit perpendicular fracture patterns due to their continuous hexagonal or uniformly distributed porous networks. In these materials, stress propagates orthogonally to the applied strain because the uniformly distributed bonds offer similar resistance in all directions, leading to more isotropic crack propagation.

Finally, we present a detailed analysis of the lithium adsorption and diffusion behavior on the DOTT-C surface, highlighting its potential as an anode material for lithium-ion batteries. Figure 8(a) illustrates the energy profile for a single lithium-ion diffusing on the DOTT-C lattice, revealing adsorption sites with varying energy levels. The calculated adsorption energies range between -2.3 eV and -0.89 eV, indicating strong binding between Li ions and specific regions of the lattice. These values compare favorably to other 2D carbon allotropes, such as graphene (-1.57 eV) [78], underscoring DOTT-C's ability to stably adsorb Li ions without compromising structural integrity.

The calculated diffusion energy barriers along different pathways on the DOTT-C surface are highlighted in Figure 8(a). The barriers range between 0.28 and 0.91 eV, among the lowest reported for 2D carbon allotropes. These low barriers highlight the synergy between DOTT-C's porous architecture and electronic structure, facilitating efficient Li-ion transport. The directional dependence of the barriers further emphasizes DOTT-C's anisotropic nature, suggesting that specific pathways can be optimized to enhance ion mobility.

Figure 8(b) displays temperature-dependent diffusion coefficients, providing insights into DOTT-C's performance under various thermal conditions. At room temperature, the diffusion coefficient exceeds 1×10^{-6} cm²/s, demonstrating exceptional Li-ion mobility compared to graphene and other



Figure 9: Relative energy profile for a lithium atom diffusion across two DOTT-C sheets. The inset represents the migration pathway.

2D materials. For comparison, the black dotted lines represent the Li-ion mobility for graphene at 300K, and the black circles refer to the Li-ion diffusion across two DOTT-C sheets (see Figure 9). As temperature increases, the exponential growth in diffusion coefficients validates the thermally activated nature of Li-ion dynamics on DOTT-C's surface. The strong temperature dependence highlights the material's adaptability for high-efficiency lithium-ion batteries operating across various conditions.

The relative energy profile for lithium diffusion across two DOTT-C sheets is presented in Figure 9. The energy profile highlights a diffusion barrier of 0.40 eV, a critical parameter for evaluating the ease of lithium-ion mobility across the material. The inset shows a schematic representation of the lithium-ion moving across the lattice, emphasizing the flat topology and accessible pathways provided by DOTT-C's unique multi-ringed structure. The moderate diffusion barrier observed here reflects the synergy between DOTT-C's porous architecture and electronic properties. This sufficiently low barrier ensures efficient lithium-ion transport, making DOTT-C a competitive candidate for lithium-ion battery anodes. The smooth and continuous energy landscape suggests minimal resistance to ion movement, which is essential for high-rate performance in battery applications.

Based on these findings, one can realize the DOTT-C's ability to balance strong lithium adsorption with rapid ion diffusion, combining structural stability with efficient ion transport mechanisms. Such attributes are critical for achieving high energy density and excellent cycling stability in nextgeneration energy storage systems. This diffusion barrier and the material's favorable adsorption and transport properties further validate its potential for advanced energy applications.

Figure 10 illustrates the relationship between the open circuit voltage (OCV) and the number of adsorbed lithium atoms on DOTT-C. The OCV values, calculated using a first-principles approach, demonstrate a clear trend as lithium adsorption progresses. At low lithium coverage, the OCV starts high (0.89 V), reflecting strong initial adsorption due to the availability of energetically favorable binding sites. As adsorbed lithium atoms increase, the OCV decreases progressively, stabilizing near 0.0 V after eight adsorbed lithium atoms. This decline in OCV is attributed to increased electrostatic repulsion among the Li ions and competition for adsorption sites as coverage



Figure 10: OCV as functions of the number of adsorbed in DOTT-C. The average OCV is 0.28 eV.

increases.

DOTT-C's average OCV, calculated to be approximately 0.28 V, positions it as a competitive candidate for LIB anode applications. A moderate OCV value is desirable for anodes, as it minimizes the voltage difference between the anode and lithium-ion aggregates, enhancing energy efficiency and reducing the risk of lithium plating during the charging process. For comparison, graphite, a commonly used anode material, has an OCV range of 0.22–0.40 V. At the same time, graphene exhibits an even lower OCV of approximately 0.11 V. These results suggest that DOTT-C offers a balanced OCV that combines stability and efficiency.

The theoretical lithium storage capacity of DOTT-C, calculated as 446.28 mAh/g, exceeds that of graphite (372 mAh/g) [79] and graphene (568 mAh/g) [80], making it a promising alternative for next-generation LIBs. The material's unique multi-ringed porous structure provides ample adsorption sites for lithium ions, ensuring high capacity while maintaining structural integrity. While DOTT-C's capacity is moderate compared to high-capacity materials like twin-graphene (3916 mAh/g), its combination of moderate OCV and robust capacity highlights its potential for practical energy storage applications. The results presented in this Figure 10 underscore the effectiveness of DOTT-C's porous architecture in stabilizing Li-ion adsorption while enabling efficient ion transport. The combined metallic nature and low diffusion barriers of DOTT-C point to its potential as a high-performance anode material for lithium-ion batteries, ensuring a balance between energy density, efficiency, and cycling stability.

4 Conclusions

This study explored the structural, mechanical, electronic, optical, and lithium-ion storage properties of DOTT-Carbon (DOTT-C), a novel two-dimensional carbon allotrope characterized by a unique multi-ringed porous structure. Using first-principles density functional theory calculations and machine learning interatomic potentials, we demonstrated the potential of DOTT-C as an advanced material for energy storage, particularly as an anode in lithium-ion batteries.

The results revealed that DOTT-C exhibits excellent dynamic and thermal stability, as confirmed by phonon dispersion and ab initio molecular dynamics simulations. Its flat lattice, composed of 12-, 8-, 4-, and 3-membered carbon rings, provides a robust framework capable of withstanding high temperatures and mechanical stress. The stress-strain analysis highlighted its anisotropic mechanical behavior, with Young's modulus values of 331.75 GPa and 281.55 GPa in the xxx- and Y-directions, respectively. The material also demonstrated ultimate tensile strengths of 70 GPa and 40 GPa along these directions, combining stiffness with flexibility due to its porous topology.

DOTT-C is a metallic material with excellent lithium-ion storage properties, with adsorption energies ranging from -2.3 eV to -0.89 eV and a theoretical storage capacity of 446.28 mAh/g. The material's low diffusion barrier of 0.40 eV and high diffusion coefficient of 1×10^{-6} cm²2/s at room temperature ensures efficient lithium-ion transport, making it well-suited for fast charging and discharging cycles. DOTT-C demonstrated a moderate open circuit voltage (OCV) of 0.28 V, balancing energy efficiency and stability. This moderate OCV reduces the risk of lithium plating during charging and enhances the material's suitability as an anode for LIBs.

5 Acknowledgements

This work received partial support from Brazilian agencies CAPES, CNPq, and FAPDF. L.A.R.J. acknowledges the financial support from FAP-DF grants 00193.00001808/2022-71 and 00193 – 00001857/2023 – 95, FAPDF-PRONEM grant 00193.00001247/2021-20, PDPG-FAPDF-CAPES Centro-Oeste 00193-00000867/2024-94, and CNPq grants 350176/2022 – 1 and 167745/2023 – 9. L.A.R.J. thanks also to CENAPAD-SP (National High-Performance Center in São Paulo, State University of Campinas – UNICAMP, proj634) and NACAD (High-Performance Computing Center, Lobo Carneiro Supercomputer, Federal University of Rio de Janeiro – UFRJ, project a22003) for the computational support provided. The authors acknowledge the National Laboratory for Scientific Computing (LNCC/MCTI, Brazil) for providing HPC resources for the SDumont supercomputer, contributing to the research results reported in this paper. A.M.A.S. thanks the financial support from Petroliam Nasional Berhad (Petronas).

References

- Mingsheng Xu, Tao Liang, Minmin Shi, and Hongzheng Chen. Graphene-like two-dimensional materials. *Chemical reviews*, 113(5):3766–3798, 2013.
- [2] Alexander A Balandin. Thermal properties of graphene and nanostructured carbon materials. *Nature materials*, 10(8):569–581, 2011.
- [3] Hengcong Tao, Qun Fan, Tao Ma, Shizhen Liu, Henry Gysling, John Texter, Fen Guo, and Zhenyu Sun. Two-dimensional materials for energy conversion and storage. *Progress in Materials Science*, 111:100637, 2020.
- [4] Rajesh Kumar, Ednan Joanni, Rajesh K Singh, Dinesh P Singh, and Stanislav A Moshkalev. Recent advances in the synthesis and modification of carbon-based 2d materials for application in energy conversion and storage. *Progress in Energy and Combustion Science*, 67:115–157, 2018.
- [5] Lele Peng, Yue Zhu, Dahong Chen, Rodney S Ruoff, and Guihua Yu. Two-dimensional materials for beyond-lithium-ion batteries. Advanced Energy Materials, 6(11):1600025, 2016.
- [6] Hao Liu, Xiaoxue Liu, Wei Li, Xin Guo, Yong Wang, Guoxiu Wang, and Dongyuan Zhao. Porous carbon composites for next generation rechargeable lithium batteries. Advanced Energy Materials, 7(24):1700283, 2017.

- [7] Xiaoyu Zheng, Jiayan Luo, Wei Lv, Da-Wei Wang, and Quan-Hong Yang. Two-dimensional porous carbon: synthesis and ion-transport properties. *Advanced Materials*, 27(36):5388–5395, 2015.
- [8] Yin Fang, Yingying Lv, Renchao Che, Haoyu Wu, Xuehua Zhang, Dong Gu, Gengfeng Zheng, and Dongyuan Zhao. Two-dimensional mesoporous carbon nanosheets and their derived graphene nanosheets: synthesis and efficient lithium ion storage. *Journal of the American Chemical Society*, 135(4):1524–1530, 2013.
- [9] EAJ Santos, KAL Lima, and LA Ribeiro Junior. Proposing todd-graphene as a novel porous 2d carbon allotrope designed for superior lithium-ion battery efficiency. *Scientific Reports*, 14(1):6202, 2024.
- [10] EAJ Santos, KAL Lima, FLL Mendonça, DA da Silva, WF Giozza, and LA Ribeiro Junior. Photh-graphene: A new 2d carbon allotrope with low barriers for li-ion mobility. *Scientific Reports*, 14(1):9526, 2024.
- [11] Shuaiwei Wang, Baocheng Yang, Houyang Chen, and Eli Ruckenstein. Popgraphene: a new 2d planar carbon allotrope composed of 5–8–5 carbon rings for high-performance lithium-ion battery anodes from bottom-up programming. *Journal of Materials Chemistry A*, 6(16):6815– 6821, 2018.
- [12] Hiba Khaled Al-Jayyousi, Muhammad Sajjad, Kin Liao, and Nirpendra Singh. Twodimensional biphenylene: A promising anchoring material for lithium-sulfur batteries. *Scientific Reports*, 12(1):4653, 2022.
- [13] Adewale Hammed Pasanaje and Nirpendra Singh. Evolutionary prediction of novel biphenylene networks as an anode material for lithium and potassium-ion batteries. *Nano Materials Science*, 2024.
- [14] Da Li. Two-dimensional c 5678: A promising carbon-based high-performance lithium-ion battery anode. *Materials Advances*, 2(1):398–402, 2021.
- [15] Huili Liu, Yaru Wei, Donghai Wu, and Shuaiwei Wang. A novel 2d carbon allotrope for high-performance metal-ion battery anode material. *Materials Science in Semiconductor Pro*cessing, 173:108146, 2024.
- [16] Victor G Desyatkin, William B Martin, Ali E Aliev, Nathaniel E Chapman, Alexandre F Fonseca, Douglas S Galvão, Ericka Roy Miller, Kevin H Stone, Zhong Wang, Dante Zakhidov, et al. Scalable synthesis and characterization of multilayer γ-graphyne, new carbon crystals with a small direct band gap. Journal of the American Chemical Society, 144(39):17999–18008, 2022.
- [17] Qitang Fan, Linghao Yan, Matthias W Tripp, Ondřej Krejčí, Stavrina Dimosthenous, Stefan R Kachel, Mengyi Chen, Adam S Foster, Ulrich Koert, Peter Liljeroth, et al. Biphenylene network: A nonbenzenoid carbon allotrope. *Science*, 372(6544):852–856, 2021.
- [18] Chaofan Yang, Yong Li, Yang Chen, Qiaodan Li, Lulu Wu, and Xiaoli Cui. Mechanochemical synthesis of γ-graphyne with enhanced lithium storage performance. *Small*, 15(8):1804710, 2019.
- [19] David Ferguson, Debra J Searles, and Marlies Hankel. Biphenylene and phagraphene as lithium ion battery anode materials. ACS applied materials & interfaces, 9(24):20577–20584, 2017.

- [20] Oxana V Kharissova, Boris I Kharisov, and Cesar M Oliva Gonzalez. Carbon-carbon allotropic hybrids and composites: synthesis, properties, and applications. *Industrial & engineering chemistry research*, 58(10):3921–3948, 2019.
- [21] Santosh K Tiwari, Vijay Kumar, Andrzej Huczko, R Oraon, A De Adhikari, and GC Nayak. Magical allotropes of carbon: prospects and applications. *Critical Reviews in Solid State and Materials Sciences*, 41(4):257–317, 2016.
- [22] A Rajkamal and Ranjit Thapa. Carbon allotropes as anode material for lithium-ion batteries. Advanced Materials Technologies, 4(10):1900307, 2019.
- [23] Aurélien Lherbier, Gil Vander Marcken, Benoît Van Troeye, Andrés Rafael Botello-Méndez, Jean-Joseph Adjizian, Geoffroy Hautier, Xavier Gonze, Gian-Marco Rignanese, and Jean-Christophe Charlier. Lithiation properties of sp 2 carbon allotropes. *Physical Review Materi*als, 2(8):085408, 2018.
- [24] Gang Wang, Minghao Yu, and Xinliang Feng. Carbon materials for ion-intercalation involved rechargeable battery technologies. *Chemical Society Reviews*, 50(4):2388–2443, 2021.
- [25] Hina Ghulam Ali, Kashif Khan, Muhammad Bilal Hanif, Muhammad Zubair Khan, Iftikhar Hussain, Muhammad Sufyan Javed, Hussein AZ AL-bonsrulah, Michał Mosiałek, Maximilian Fichtner, and Martin Motola. Advancements in two-dimensional materials as anodes for lithium-ion batteries: Exploring composition-structure-property relationships emerging trends, and future perspective. *Journal of Energy Storage*, 73:108980, 2023.
- [26] Yang-Xin Yu. Graphenylene: a promising anode material for lithium-ion batteries with high mobility and storage. Journal of Materials Chemistry A, 1(43):13559–13566, 2013.
- [27] Michael Ruby Raj, Gibaek Lee, Mogalahalli Venkatashamy Reddy, and Karim Zaghib. Recent advances in development of organic battery materials for monovalent and multivalent metalion rechargeable batteries. ACS Applied Energy Materials, 7(19):8196–8255, 2024.
- [28] Juan Gomez Quispe, Bruno Ipaves, Douglas Soares Galvao, and Pedro Alves da Silva Autreto. Tpdh-graphene as a new anodic material for lithium ion battery: Dft-based investigations. ACS omega, 9(37):39195–39201, 2024.
- [29] Yusheng Cai, Yi Wei, Cuihong Lv, Lichuan Zhang, and Yuanping Chen. Lc 567: a new 2d semimetallic carbon allotrope as a promising anode material for lithium-ion batteries. *Physical Chemistry Chemical Physics*, 25(28):19239–19244, 2023.
- [30] Kun Lu, Tianyu Wang, Xin Li, Linling Dai, Jiuren Yin, and Yanhuai Ding. A new 2d carbon allotrope c568 as a high-capacity electrode material for lithium-ion batteries. *Fullerenes, Nanotubes and Carbon Nanostructures*, 30(3):385–391, 2022.
- [31] Xing Hong Cai, Qiang Yang, Shaohui Zheng, and Min Wang. Net-c18: A predicted twodimensional planar carbon allotrope and potential for an anode in lithium-ion battery. *Energy* & Environmental Materials, 4(3):458–464, 2021.
- [32] Zishuang Cheng, Xiaoming Zhang, Hui Zhang, Jianbo Gao, Heyan Liu, Xiao Yu, Xuefang Dai, Guodong Liu, and Guifeng Chen. Two-dimensional metallic carbon allotrope with multiple rings for ion batteries. *Physical Chemistry Chemical Physics*, 23(34):18770–18776, 2021.
- [33] Manqi You, Gencai Guo, Yujie Liao, Siwei Luo, Chaoyu He, Chao Tang, and Jianxin Zhong. 2d novel c5n2 allotropes: High-performance anode materials for alkali metal ion battery. *Journal* of Energy Storage, 84:111004, 2024.

- [34] Jie Liu, Tianshan Zhao, Shunhong Zhang, and Qian Wang. A new metallic carbon allotrope with high stability and potential for lithium ion battery anode material. *Nano energy*, 38:263– 270, 2017.
- [35] Weiyi Wang, Jie Meng, Yujie Hu, Jiajun Wang, Qunxiang Li, and Jinlong Yang. Thgraphene: a novel two-dimensional carbon allotrope as a potential multifunctional material for electrochemical water splitting and potassium-ion batteries. *Journal of Materials Chemistry A*, 10(18):9848–9857, 2022.
- [36] Zhiming Liu, Yu Tian, Peng Wang, and Guoxin Zhang. Applications of graphene-based composites in the anode of lithium-ion batteries. *Frontiers in Nanotechnology*, 4:952200, 2022.
- [37] Stewart J Clark, Matthew D Segall, Chris J Pickard, Phil J Hasnip, Matt IJ Probert, Keith Refson, and Mike C Payne. First principles methods using castep. Zeitschrift für kristallographie-crystalline materials, 220(5-6):567–570, 2005.
- [38] John P Perdew, Kieron Burke, and Matthias Ernzerhof. Generalized gradient approximation made simple. *Physical review letters*, 77:3865, 1996.
- [39] Stefano Baroni, Stefano De Gironcoli, Andrea Dal Corso, and Paolo Giannozzi. Phonons and related crystal properties from density-functional perturbation theory. *Reviews of modern Physics*, 73(2):515, 2001.
- [40] Shuichi Nosé. A unified formulation of the constant temperature molecular dynamics methods. The Journal of chemical physics, 81:511–519, 1984.
- [41] KA Lopes Lima and LA Ribeiro Junior. A dft study on the mechanical, electronic, thermodynamic, and optical properties of gan and aln counterparts of biphenylene network. *Materials Today Communications*, 37:107183, 2023.
- [42] Stela Makri, Christoph Ortner, and James R Kermode. A preconditioning scheme for minimum energy path finding methods. *The Journal of Chemical Physics*, 150(9), 2019.
- [43] Jonathan Barzilai and Jonathan M Borwein. Two-point step size gradient methods. IMA journal of numerical analysis, 8(1):141–148, 1988.
- [44] Erik Bitzek, Pekka Koskinen, Franz Gähler, Michael Moseler, and Peter Gumbsch. Structural relaxation made simple. *Physical review letters*, 97(17):170201, 2006.
- [45] Steve Plimpton. Fast parallel algorithms for short-range molecular dynamics. Journal of computational physics, 117:1–19, 1995.
- [46] Ivan S Novikov, Konstantin Gubaev, Evgeny V Podryabinkin, and Alexander V Shapeev. The mlip package: moment tensor potentials with mpi and active learning. *Machine Learning: Science and Technology*, 2(2):025002, 2020.
- [47] Alexander V Shapeev, Evgeny V Podryabinkin, Konstantin Gubaev, Ferenc Tasnádi, and Igor A Abrikosov. Elinvar effect in β-ti simulated by on-the-fly trained moment tensor potential. New Journal of Physics, 22(11):113005, 2020.
- [48] Bohayra Mortazavi, Mohammad Silani, Evgeny V Podryabinkin, Timon Rabczuk, Xiaoying Zhuang, and Alexander V Shapeev. First-principles multiscale modeling of mechanical properties in graphene/borophene heterostructures empowered by machine-learning interatomic potentials. Advanced Materials, 33(35):2102807, 2021.

- [49] Evgeny V Podryabinkin and Alexander V Shapeev. Active learning of linearly parametrized interatomic potentials. *Computational Materials Science*, 140:171–180, 2017.
- [50] Georg Kresse and Jürgen Hafner. Ab initio molecular dynamics for liquid metals. *Physical review B*, 47(1):558, 1993.
- [51] Georg Kresse and Jürgen Furthmüller. Efficiency of ab-initio total energy calculations for metals and semiconductors using a plane-wave basis set. *Computational materials science*, 6(1):15–50, 1996.
- [52] Georg Kresse and Jurgen Hafner. Norm-conserving and ultrasoft pseudopotentials for first-row and transition elements. *Journal of Physics: Condensed Matter*, 6(40):8245, 1994.
- [53] Bohayra Mortazavi. Machine learning interatomic potentials: Keys to first-principles multiscale modeling. In *Machine Learning in Modeling and Simulation: Methods and Applications*, pages 427–451. Springer, 2023.
- [54] Bohayra Mortazavi, Timon Rabczuk, and Xiaoying Zhuang. Exploring the structural stability, thermal and mechanical properties of nanoporous carbon nitride nanosheets using a transferrable machine learning interatomic potential. *Machine Learning for Computational Science and Engineering*, 1(1):5, 2025.
- [55] Bohayra Mortazavi, Xiaoying Zhuang, Timon Rabczuk, and Alexander V Shapeev. Atomistic modeling of the mechanical properties: the rise of machine learning interatomic potentials. *Materials Horizons*, 10(6):1956–1968, 2023.
- [56] Bohayra Mortazavi, Evgeny V Podryabinkin, Ivan S Novikov, Stephan Roche, Timon Rabczuk, Xiaoying Zhuang, and Alexander V Shapeev. Efficient machine-learning based interatomic potentialsfor exploring thermal conductivity in two-dimensional materials. *Journal* of Physics: Materials, 3(2):02LT02, 2020.
- [57] Bohayra Mortazavi. Electronic, thermal and mechanical properties of carbon and boron nitride holey graphyne monolayers. *Materials*, 16(20):6642, 2023.
- [58] Bohayra Mortazavi. Goldene: An anisotropic metallic monolayer with remarkable stability and rigidity and low lattice thermal conductivity. *Materials*, 17(11):2653, 2024.
- [59] Stephen T Skowron, Irina V Lebedeva, Andrey M Popov, and Elena Bichoutskaia. Energetics of atomic scale structure changes in graphene. *Chemical Society Reviews*, 44(10):3143–3176, 2015.
- [60] Raphael M Tromer, Marcelo L Pereira Junior, Kleuton A L. Lima, Alexandre F Fonseca, Luciano R da Silva, Douglas S Galvao, and Luiz A Ribeiro Junior. Mechanical, electronic, and optical properties of 8-16-4 graphyne: A 2d carbon allotrope with dirac cones. *The Journal* of Physical Chemistry C, 127(25):12226–12234, 2023.
- [61] KAL Lima, Fábio Ferreira Monteiro, EJA Santos, RAF Alves, William Ferreira Giozza, and LA Ribeiro Junior. Dodecanophene: A novel 2d carbon allotrope with untunable metallic behavior under stress. *Materials Today Communications*, page 109455, 2024.
- [62] Changhong Zhang, Chengyi Hou, Yi Lu, Le Zhao, Haorong Wu, Hongyuan Song, Ju Rong, Lan Yu, and Xiaohua Yu. Thermal and electrical transport properties of two-dimensional dirac graphenylene: a first-principles study. *Physical Chemistry Chemical Physics*, 25(45):31301– 31311, 2023.

- [63] José AS Laranjeira, Nicolas F Martins, Pablo A Denis, and Julio R Sambrano. Graphenyldiene: A new sp2-graphene-like nanosheet. *Carbon Trends*, 14:100321, 2024.
- [64] R Majidi. Density functional theory study on structural and mechanical properties of graphene, t-graphene, and r-graphyne. *Theoretical Chemistry Accounts*, 136(9):109, 2017.
- [65] Xin-Wei Chen, Zheng-Zhe Lin, and Xi-Mei Li. Biphenylene network as sodium ion battery anode material. *Physical Chemistry Chemical Physics*, 25(5):4340–4348, 2023.
- [66] ML Pereira Junior, Wiliam Ferreira da Cunha, William Ferreira Giozza, Rafael Timoteo de Sousa Junior, and LA Ribeiro Junior. Irida-graphene: A new 2d carbon allotrope. *FlatChem*, 37:100469, 2023.
- [67] Mingwen Zhao, Wenzheng Dong, and Aizhu Wang. Two-dimensional carbon topological insulators superior to graphene. *Scientific reports*, 3(1):3532, 2013.
- [68] Fabrizio Scarpa, Sondipon Adhikari, and A Srikantha Phani. Effective elastic mechanical properties of single layer graphene sheets. *Nanotechnology*, 20(6):065709, 2009.
- [69] Jae-Ung Lee, Duhee Yoon, and Hyeonsik Cheong. Estimation of young's modulus of graphene by raman spectroscopy. *Nano letters*, 12(9):444–4448, 2012.
- [70] Qing Peng, Gen Chen, Zeyu Huang, Xue Chen, Ao Li, Xintian Cai, Yuqiang Zhang, Xiao-Jia Chen, and Zhongwei Hu. Molecular dynamics insights into mechanical stability, elastic properties, and fracture behavior of photh-graphene. *Materials*, 17(19):4740, 2024.
- [71] Qing Peng, Jiale Li, Xintian Cai, Gen Chen, Zeyu Huang, Lihang Zheng, Hongyang Li, Xiao-Jia Chen, and Zhongwei Hu. Atomistic study on the mechanical properties of hop-graphene under variable strain, temperature, and defect conditions. *Nanomaterials*, 15(1):31, 2025.
- [72] Qing Peng, Gen Chen, Zeyu Huang, Yuqiang Zhang, Xiaofan Zhang, Xiao-Jia Chen, and Zhongwei Hu. Mechanical properties of tpdh-graphene: atomistic aspect. *Physica Scripta*, 99(11):115996, 2024.
- [73] Shuoyang Xiao, Jiannan Hao, Tan Shi, Jianfeng Jin, Bin Wu, and Qing Peng. Effects of size and shape of hole defects on mechanical properties of biphenylene: a molecular dynamics study. *Nanotechnology*, 35(48):485703, 2024.
- [74] LA Ribeiro Junior, ML Pereira Junior, WF Giozza, RM Tromer, and Douglas S Galvão. Thermal stability and fracture patterns of a recently synthesized monolayer fullerene network: A reactive molecular dynamics study. *Chemical Physics Letters*, 807:140075, 2022.
- [75] ML Pereira, WF Da Cunha, RT De Sousa, GD Amvame Nze, DS Galvão, and LA Ribeiro. On the mechanical properties and fracture patterns of the nonbenzenoid carbon allotrope (biphenylene network): a reactive molecular dynamics study. *Nanoscale*, 14(8):3200–3211, 2022.
- [76] Levi C Felix, Raphael M Tromer, Pedro AS Autreto, Luiz A Ribeiro Junior, and Douglas S Galvao. On the mechanical properties and thermal stability of a recently synthesized monolayer amorphous carbon. *The Journal of Physical Chemistry C*, 124(27):14855–14860, 2020.
- [77] Steven W Cranford and Markus J Buehler. Mechanical properties of graphyne. Carbon, 49(13):4111–4121, 2011.
- [78] Dongseong Kim, Sangho Lee, Yubin Hwang, Kyung-Han Yun, and Yong-Chae Chung. Hydrogen storage in li dispersed graphene with stone-wales defects: a first-principles study. *International journal of hydrogen energy*, 39(25):13189–13194, 2014.

- [79] Hao Zhang, Yang Yang, Dongsheng Ren, Li Wang, and Xiangming He. Graphite as anode materials: Fundamental mechanism, recent progress and advances. *Energy Storage Materials*, 36:147–170, 2021.
- [80] Yuanyue Liu, Vasilii I Artyukhov, Mingjie Liu, Avetik R Harutyunyan, and Boris I Yakobson. Feasibility of lithium storage on graphene and its derivatives. *The journal of physical chemistry letters*, 4(10):1737–1742, 2013.