Decoupling Coherent and Particle-like Phonon Transport through Bonding Hierarchy in Soft Superionic Crystals

Wenjie Xiong,¹ Hao Huang,² Yu Wu,^{3,*} Xinji Xu,¹

Geng Li,^{4,5} Zonglin Gu,^{1,†} and Shuming Zeng^{1,‡}

¹College of Physics Science and Technology, Yangzhou University, Jiangsu 225009, China ²Advanced Copper Industry College,

Jiangxi University of Science and Technology, Yingtan 335000, China

³Micro- and Nano-scale Thermal Measurement and Thermal Management Laboratory, School of Energy and Mechanical Engineering,

Nanjing Normal University, Jiangsu, Nanjing 210023, China

⁴China Rare Earth Group Research Institute, Ganzhou, 341000, China

⁵Key Laboratory of Rare Earths, Ganjiang Innovation Academy,

Chinese Academy of Sciences, Ganzhou, 341000, China

(Dated: April 4, 2025)

Abstract

Within the framework of the unified theory thermal transport model, the competing contributions of coherent and incoherent terms create a trade-off relationship, posing substantial challenges to achieving a reduction in overall $\kappa_{\rm L}$. In this work, we theoretically demonstrate that the superionic crystals X₆Re₆S₈I₈ (X = Rb, Cs) exhibit ultralow glass-like and particle-like thermal conductivities. The weak interactions between free alkali metal ions X⁺ (X = Rb, Cs) and I⁻ anions induce pronounced lattice anharmonicity, which enhances phonon scattering and suppresses group velocities, thereby reducing the particle-like thermal conductivity ($\kappa_{\rm p}$). Concurrently, the significant bonding heterogeneity within the [Re₆S₈I₆]⁴⁻ clusters promotes phonon dispersion flattening and low-frequency phonon localization. The resulting discretized phonon flat bands substantially diminish the glass-like thermal conductivity ($\kappa_{\rm c}$). At room temperature, the total $\kappa_{\rm L}$ of X₆Re₆S₈I₈ (X = Rb, Cs) falls below 0.2 Wm⁻¹K⁻¹. Furthermore, the bonding characteristics between X⁺ and I⁻¹ anions induce an anomalous cation mass-independent stiffening of low-frequency phonon branches in this system, resulting in counterintuitive thermal transport behavior. This work elucidates fundamental mechanisms governing heat transfer in ultralow $\kappa_{\rm L}$ materials and establishes novel pathways for transcending conventional thermal conductivity limitations.

I. INTRODUCTION

The exploration of materials with ultralow lattice thermal conductivity $\kappa_{\rm L}$ holds significant importance in both fundamental research and technological applications, such as thermal barrier coatings¹ and thermoelectrics². Materials with intrinsically low $\kappa_{\rm L}$, typically governed by phonon-phonon scattering mechanisms, exhibit several distinctive features such as intrinsic rattling³, lattice anharmonicity⁴, ferroelectric instability⁵, and structural complexity⁶. Based on these principles, a series of materials with low $\kappa_{\rm L}$ at room temperature such as Tl₃VSe₄ (0.30 Wm⁻¹K⁻¹)⁷, TlSe (0.62 Wm⁻¹K⁻¹)⁸, and Cu₁₂Sb₄S₁₃ (0.67 Wm⁻¹K⁻¹)⁶ have been discovered. In addition, strategies like nanostructuring and entropydriven point defect engineering can further suppress $\kappa_{\rm L}^{9}$. The advent of machine learning methods has enabled efficient exploration of low $\kappa_{\rm L}$ materials across vast chemical and structural spaces¹⁰. However, the $\kappa_{\rm L}$ of crystalline materials cannot be arbitrarily low-it is fundamentally bounded¹¹. To date, the experimentally measured $\kappa_{\rm L}$ of crystals at room temperature has not fallen below 0.2 Wm⁻¹K⁻¹, the search for materials with ultralow $\kappa_{\rm L}$ remains an active research frontier.

In the unified theory of lattice thermal conductivity proposed by Simoncelli et al.^{12,13}, heat transport is governed by dual contributions from localized diffusions (glass-like thermal conductivity $\kappa_{\rm c}$) and propagating phonons (particle-like thermal conductivity $\kappa_{\rm p}$). Generally, in simple lattices with few atoms per primitive cell (PC), $\kappa_{\rm L}$ is dominated by propagating phonons. However, in complex crystals with many atoms per PC, the contribution of localized diffusons becomes significant and cannot be neglected. For example, at 300 K, PbTe (2 atoms per PC) exhibits a total $\kappa_{\rm L}$ of 2 Wm⁻¹K⁻¹, which is almost entirely contributed by κ_p^{14} . In contrast, the complex crystal Ag₈GeS₆ (60 atoms per PC) demonstrates an ultralow κ_p of merely 0.04 Wm⁻¹K⁻¹, which comparable to that of air, while its κ_c reaches 0.43 Wm⁻¹K⁻¹, significantly exceeding $\kappa_{\rm p}^{11}$. A viable strategy for discovering materials with ultralow $\kappa_{\rm L}$ involves either minimizing $\kappa_{\rm p}$ in simple lattices or suppressing $\kappa_{\rm c}$ in complex crystal structures. For the former case, Zeng et al. identified $AgTII_2$ (I4/mcm) as a rare simple crystalline system simultaneously exhibiting low $\kappa_{\rm p}$ and suppressed $\kappa_{\rm c}^{11}$, achieving an unprecedented room-temperature $\kappa_{\rm L}$ of 0.25 Wm⁻¹K⁻¹. For the latter case (complex crystals), whether materials with intrinsically low $\kappa_{\rm c}$ exist remains an open fundamental question in thermal transport physics.

In this work, we systematically investigate the lattice thermal conductivity of the recently discovered superionic compounds^{15–17} $X_6 Re_6 S_8 I_8$ (X = Rb, Cs)¹⁸ using first-principles calculations combined with the temperature-dependent effective potential (TDEP) method. By rigorously treating three- and four-phonon scattering processes within the unified theory of lattice thermal transport, we reveal exceptionally suppressed contributions from both $\kappa_{\rm p}$ and $\kappa_{\rm c}$, leading to an ultralow $\kappa_{\rm L}$ below 0.2 Wm⁻¹K⁻¹. The quasi zero-dimensional (0D) structure of $X_6 Re_6 S_8 I_8$ consists of isolated $[Re_6 S_8 I_6]^{4-}$ clusters embedded in a threedimensional ionic framework formed by Rb⁺/Cs⁺ cations and bridging I⁻ anions. Strong phonon anharmonicity and localization in this architecture generate extensive optical flat bands that suppress both particle-like and wave-like thermal transport. Counterintuitively, despite the heavier atomic mass of Cs-which typically reduces phonon group velocities (v_g) -our calculations reveal higher thermal conductivity in Cs-based compounds than in their Rb analogs. This anomaly arises from distinct X-I interactions that reshape local lattice dynamics and bonding, unexpectedly enhancing phonon lifetimes and propagation in Cs variants. These results defy the conventional "liquid-like thermal conduction" model and establish new principles for engineering ultralow $\kappa_{\rm L}$ materials.

II. COMPUTATIONAL METHODS

All first-principles calculations were performed using the Vienna *Ab Initio* Simulation Package (VASP)¹⁹, based on density functional theory (DFT)^{20,21}. The projector augmented wave (PAW) method²² with a plane-wave basis set was employed to describe ion-electron interactions, while exchange-correlation effects were treated within the revised Perdew-Burke-Ernzerhof functional optimized for solids (PBEsol)²³. A plane-wave energy cutoff of 520 eV was imposed throughout the calculations. Structural relaxations utilized a $6 \times 6 \times 6$ Monkhorst-Pack **k**-mesh for Brillouin zone sampling, with convergence thresholds of 10^{-8} eV for energy and 10^{-4} eV/Å for atomic forces. Born effective charge tensors and dielectric constants were computed via density functional perturbation theory (DFPT)²⁴, incorporating nonanalytic corrections to the dynamical matrix. To determine interatomic force constants (IFCs), we conducted *ab initio* molecular dynamics (AIMD) simulations in the NVT ensemble using a $2 \times 2 \times 2$ supercell containing 224 atoms. The system was equilibrated for 20 ps with a timestep of 1 fs. Temperature-dependent effective potential (TDEP) methodology²⁵ was subsequently applied to extract second-, third-, and fourth-order IFCs at varying temperatures, employing cutoff radii of 8 Å, 6 Å, and 4 Å respectively. These cutoff values ensured comprehensive inclusion of atomic interactions governing the material's dynamical response.

Within the Wigner formalism, the lattice thermal conductivity tensor $\kappa_{\rm L}^{\alpha\beta}$ decomposes into two contributions:

$$\kappa_{\rm L}^{\alpha\beta} = \kappa_{\rm p}^{\alpha\beta} + \kappa_{\rm c}^{\alpha\beta},\tag{1}$$

where the particle-like term $\kappa_{p}^{\alpha\beta}$ describes semiclassical phonon transport:

$$\kappa_{\rm p}^{\alpha\beta} = \frac{1}{N_{\rm q}V} \sum_{\rm qs} C_{\rm q}^{\rm s} \nu_{\rm q,\alpha}^{\rm s} \nu_{\rm q,\beta}^{\rm s} \tau_{\rm q}^{\rm s}.$$
 (2)

Here, $C_q^s = \hbar \omega_q^s \partial n_q^s / \partial T$ denotes the mode-resolved heat capacity, with n_q^s being the Bose– Einstein distribution. The coherence contribution $\kappa_c^{\alpha\beta}$ captures wave-like tunneling effects between distinct phonon branches s and s':

$$\kappa_{c}^{\alpha\beta} = \frac{\hbar^{2}}{k_{B}T^{2}VN_{q}} \sum_{q} \sum_{s\neq s'} \frac{\omega_{q}^{s} + \omega_{q}^{s'}}{2} \nu_{q,\alpha}^{s,s'} \nu_{q,\beta}^{s,s'} \times \frac{\omega_{q}^{s}n_{q}^{s}(n_{q}^{s}+1) + \omega_{q}^{s'}n_{q}^{s'}(n_{q}^{s'}+1)}{4(\omega_{q}^{s} - \omega_{q}^{s'})^{2} + (\Gamma_{q}^{s} + \Gamma_{q}^{s'})^{2}} (\Gamma_{q}^{s} + \Gamma_{q}^{s'}) \quad (3)$$

where $\nu_{q,\alpha}^{s,s'}$ represents the interband velocity matrix element. The Cartesian indices $\alpha, \beta \in \{x, y, z\}$ span spatial dimensions, V is the unit cell volume, and N_q enumerates sampled phonon wavevectors in the Brillouin zone. Scattering rates Γ_q^s quantify phonon lifetime broadening. This dual formulation reconciles semiclassical transport (κ_p) with quantum coherence effects (κ_c), particularly significant in materials exhibiting phonon branch degeneracies or strong anharmonicity. The $\kappa_L^{\alpha\beta}$ was computed using an in-house modified version of the FourPhonon code^{26–29}, incorporating three- and four-phonon scattering processes, and performed in a q-mesh of $10 \times 10 \times 10$.

III. RESULTS AND DISCUSSIONS

The superionic crystals $X_6Re_6S_8I_8$ (X = Rb, Cs) adopt a cubic 0D perovskite structure¹⁸, with Rb₆Re₆S₈I₈ having been experimentally synthesized³⁰. As shown in Fig. 1(a), $X_6Re_6S_8I_8$ crystallizes in the space group $Fm\overline{3}m$, comprising alkali metal ions (X⁺), iodide ions (I⁻), and discrete [Re₆S₈I₆]⁴⁻ clusters. The [Re₆S₈I₆]⁴⁻ cluster (Fig. 1(b)) serves as the fundamental building unit, featuring an octahedral Re₆ core stabilized by direct metal-metal bonds (Re-Re: 2.60 Å). Each face of the Re₆ octahedron is capped by a sulfur atom in μ_3 coordination (Re-S: 2.41 Å), forming a [Re₆S₈]²⁺ core. Peripheral iodides coordinate to the octahedron through Re-I bonds (2.76 Å), completing the [Re₆S₈I₆]⁴⁻ cluster. Alkali metal atoms (X) occupy interstitial sites between clusters, exhibiting weak X-I interactions (Rb-I: 3.94 Å) that stabilize the crystal framework. Additional X-I-X bridging motifs (Rb-I: 3.88 Å) fill structural voids, forming ionic coordination networks. Optimized structural parameters for Rb₆Re₆S₈I₈ (Re-Re: 2.60 Å, Re-S: 2.40 Å, Re-I: 2.77 Å) show agreement with experimental data³⁰. Detailed structural parameters for both Rb and Cs analogs are provided in Table S1 (see supplementary information). The system exemplifies a rattling model, where X atoms (Rb/Cs) behave as loosely bound "rattler" guests within the rigid [Re₆S₈I₆]⁴⁻ host framework.



FIG. 1. (a)The crystal structure of $X_6 Re_6 S_8 I_8$ (X = Rb, Cs); (b) The Isolated $[Re_6 S_8 I_6]^{4-}$ cluster; (c) The total lattice thermal conductivities (κ_L), the particle-like lattice thermal conductivities (κ_p) and the glass-like lattice thermal conductivities (κ_c) of $X_6 Re_6 S_8 I_8$ (X = Rb, Cs) from 100K to 900K.

The electronic structures of $X_6 \text{Re}_6 S_8 I_8$ are presented in Fig. S1. Both $\text{Rb}_6 \text{Re}_6 S_8 I_8$ and $\text{Cs}_6 \text{Re}_6 S_8 I_8$ exhibit indirect bandgap semiconductor behavior, with valence band maxima (VBM) at the Γ -point and conduction band minima (CBM) at the *L*-point, yielding bandgaps (E_g) of 2.42 eV and 2.45 eV, respectively. Atomic projected electronic density of states (EDOS) analysis reveals dominant contributions from S and I atomic orbitals near the VBM, while Re atomic orbitals primarily constitute the CBM. To assess thermal stability, we performed 20 ps NVT-ensemble AIMD simulations at varying temperatures (see Fig. S2). Remarkably, both compounds maintain structural integrity up to 800 K, evidenced by minimal fluctuations in total energy. Phonon dispersion calculations within the harmonic approximation confirm dynamical stability, showing no imaginary frequencies across the Brillouin zone (Fig. S3). This stability persists under finite-temperature conditions as validated by TDEP calculations up to 800 K. Notably, temperature evolution induces distinct phonon renormalization: mid-to-high-frequency optical branches soften with increasing temperature, whereas low-frequency optical modes exhibit hardening behavior. This anomalous temperature dependence correlates with atomic vibration patterns – mid/high-frequency modes predominantly involve Re-S framework vibrations, while low-frequency modes arise from I-Rb/I-Cs interactions. The hardening of low-frequency optical branches suggests enhanced anharmonic coupling between Rb⁺ and I⁻ ionic bonds at elevated temperatures.

The cage-like crystal structure of $X_6 \text{Re}_6 \text{S}_8 \text{I}_8$ (X = Rb, Cs) engenders distinctive thermal transport characteristics³¹. Figure 1(c) presents the temperature-dependent κ_{L} ($\kappa_{\text{L}} = \kappa_{\text{p}}$ + κ_{c}) decomposition, revealing particle-like κ_{p} and coherent κ_{c} contributions. At 300 K, Cs₆Re₆S₈I₈ and Rb₆Re₆S₈I₈ exhibit ultralow κ_{L} values of 0.19 and 0.17 W m⁻¹ K⁻¹, respectively, surpassing recently reported ultralow κ_{L} materials including Ag₈GeTe₆ and AgTII₂, as well as conventional thermoelectric materials (see Table I). Notably, both compounds demonstrate weak temperature dependence with $\kappa_{\text{L}} \propto T^{-0.51}$ (Cs) and $T^{-0.49}$ (Rb), signaling strong lattice anharmonicity. The particle contribution dominates the thermal transport, accounting for 90.2% (Cs) and 87.9% (Rb) of κ_{L} at 300 K. This hierarchy suggests that diffusive phonon transport governs heat conduction in these superionic crystals. Intriguingly, the heavier Cs analog exhibits higher κ_{L} than its Rb counterpart – a mass dependence reversal contradicting conventional Slack formalism predictions^{32,33}. Structural analysis (SI Table 1) reveals significant lattice parameter and bond length variations between the analogs. These structural distinctions likely modify interatomic force constants, thereby altering phonon scattering phase space.

For cubic symmetry systems, the independent elastic tensor components reduce to C_{11} , C_{12} , and C_{44} , as presented in Table I. The elastic anisotropy factor (A), characterizing mechanical property variations along different crystallographic directions, is defined as: $A = \frac{2C_{44}}{C_{11}-C_{12}}$. Our calculations yield A = 1.58 for Rb₆Re₆S₈I₈ and A = 1.10 for Cs₆Re₆S₈I₈, both approaching unity, indicative of quasi-isotropic mechanical behavior. Notably, the larger anisotropy in Rb₆Re₆S₈I₈ suggests directional constraints in phonon propagation that

Material	C_{11}	C_{12}	C_{44}	В	G	E
$\mathrm{Rb}_6\mathrm{Re}_6\mathrm{S}_8\mathrm{I}_8$	14.54	7.75	5.36	10.01	4.58	11.91
$\mathrm{Cs}_6\mathrm{Re}_6\mathrm{S}_8\mathrm{I}_8$	16.69	5.55	6.11	9.27	5.90	14.59

TABLE I. The elastic constants (C_{ij}) , the bulk modulus (B), shear modulus (G), Young's modulus (Y), and average wave velocity (v) of $X_6Re_6S_8I_8$, unit in GPa.

may enhance scattering processes. Comparative analysis of elastic moduli reveals weaker interatomic bonding and a more loosely packed structure in $Rb_6Re_6S_8I_8$, as evidenced by its lower elastic modulus. This structural characteristic correlates with enhanced lattice anharmonicity, which restricts phonon transport velocities . Supporting this interpretation, Table II demonstrates substantially reduced sound velocities in $Rb_6Re_6S_8I_8$ compared to its cesium counterpart. Significantly, the $X_6Re_6S_8I_8$ system exhibits a remarkably low κ_L comparable to traditional thermoelectric materials, suggesting promising potential for energy conversion applications.

Material	Sound velocity $v \text{ (m s}^{-1})$	$\kappa_L \; (\mathrm{W} \; \mathrm{m}^{-1} \mathrm{K}^{-1})$	
$\mathbf{Rb}_{6}\mathbf{Re}_{6}\mathbf{S}_{8}\mathbf{I}_{8}$ (this work)	1040.78	0.17	
Ag_8GeTe_6	1099	0.25	
$\mathbf{Cs}_{6}\mathbf{Re}_{6}\mathbf{S}_{8}\mathbf{I}_{8}$ (this work)	1163.06	0.19	
$Ag_8SnSe_6^{\dagger}$	1494	0.36	
${\rm Cu}_8{\rm GeSe_6}^\dagger$	1793	0.3	
PbSe^\dagger	1805	1.5	
$PbTe^{\dagger}$	1814	1.9	

TABLE II. Comparative sound velocities (v) and lattice thermal conductivities at 300 K

[†] Values from literature references^{34,35}

To elucidate the origin of the low lattice thermal conductivity $\kappa_{\rm L}$ in X₆Re₆S₈I₈ compounds, we take Rb₆Re₆S₈I₈ as a prototype system. Figure 2(a) displays the projected phonon group velocities $v_{\rm g}$ along the phonon dispersion at 300 K. The phonon dispersion exhibits remarkable flatness across the entire frequency spectrum, particularly in optical branches, indicating spatially localized vibrational modes that hinder efficient energy prop-



FIG. 2. (a)The phonon dispersion of $Rb_6Re_6S_8I_8$ at 300 K with group velocities v_g projection; (b) The projected phonon dispersion with atomic projection of $Rb_6Re_6S_8I_8$ at 300 K; (c) The electronic localization function (ELF) corresponding to the (0,1,1), (1,2,1), and (-1,2,-1) planes of $Rb_6Re_6S_8I_8$; (d) The norm of the second-order force constants $|\Phi_2|$ for the top three strongest bonds in $X_6Re_6S_8I_8$ (X = Rb, Cs). The center is the results of the relative value of the norm of the $|\Phi_2|$ in $X_6Re_6S_8I_8$ (X = Rb, Cs).

agation. All phonon modes demonstrate exceptionally low $v_{\rm g}$, with maximum values below $2 \,\rm km \, s^{-1}$ and majority below $0.5 \,\rm km \, s^{-1}$, signifying sluggish heat transfer kinetics. The projected phonon eigenvectors in Fig. 2(b) reveal distinct vibrational characteristics: acoustic branches primarily involve I atoms, while low-frequency optical branches (<2.5 THz) arise from coupled vibrations of Rb and I atoms. Notably, these low-frequency modes (<2.5 THz) dominate thermal transport, suggesting significant contributions from Rb–I vibrations to

 $\kappa_{\rm L}$. Both phonon dispersion and group velocity characteristics correlate strongly with interatomic bonding environments. Figure 2(c) and Fig.S4 present the electron localization function (ELF) analysis, complemented by Bader charge calculations in Table III. Clearly, two distinct iodine species emerge: (1) Covalent I1 within the $[\text{Re}_6\text{S}_8\text{I}_6]^{4-}$ octahedral clusters shows moderate electron localization (ELF ≈ 0.5) with incomplete charge transfer from Re, and (2) Ionic I exhibits negligible electron localization (ELF ≈ 0). The $[\text{Re}_6\text{S}_8\text{I}_6]^{4-}$ clusters maintain partial covalent bonding (Re–S/I ELF ≈ 0.5), while Rb atoms demonstrate complete electron transfer (ELF ≈ 0) characteristic of ionic bonding. This dual bonding architecture – stable covalent clusters interspersed with ionic Rb⁺ and I⁻ species – creates weakly bonded structural frameworks. The resulting soft inter-cluster interactions promote extensive phonon band flattening, particularly in optical branches, ultimately suppressing $\kappa_{\rm L}$ through enhanced phonon scattering and reduced phonon group velocities.

Element Formal charge Bader effective charge						
		$\mathbf{X} = \mathbf{R}\mathbf{b}$	$\mathbf{X} = \mathbf{C}\mathbf{s}$			
$\rm Rb/Cs$	+1	0.836	0.999			
Re	+3	0.784	0.603			
S	-2	-0.668	-0.648			
I_1	-1	-0.480	-0.456			
I_2	-1	-0.751	-0.850			

TABLE III. Bader effective charges of constituent atoms in $X_6Re_6S_8I_8$ (X = Rb, Cs), unit in e⁻.

The strength of interatomic interactions can be characterized through force constants. Figure 2(d) displays the second-order average interaction force constants ($|\Phi_2|$) between key atomic pairs. Both Re–S and Re–I1 pairs exhibit large $|\Phi_2|$, confirming the formation of stable [Re₆S₈I₆]⁴⁻ octahedral clusters. In contrast, the weak interactions between alkali metal cations X⁺ and ionic I⁻ suggest that X₆Re₆S₈I₈ can be viewed as mobile X⁺ cations and ionic I₂⁻ species within the rigid [Re₆S₈I₆]⁴⁻ framework. To explicitly demonstrate the origin of phonon band flattening, we reconstructed phonon spectra by selectively retaining specific interatomic force constants, as shown in Fig. 3(a-c). Notably, all retained interactions produce exceptionally flat phonon dispersions except for Re–S-derived optical branches above 10 THz, where stronger bonding induces greater dispersion. Figure 3(d) illustrates characteristic optical phonon modes across frequency domains at Γ point. The low-frequency modes primarily correspond to the relative vibrations between Rb and I, the mid-frequency modes are attributed to the vibrations of I relative to the $[\text{Re}_6\text{S}_8\text{I}_6]^{4-}$ cluster, and the highfrequency modes arise from the internal atomic vibrations within the $[\text{Re}_6\text{S}_8\text{I}_6]^{4-}$ cluster. This mode localization hierarchy directly correlates with the hierarchy of bonding strengths revealed by $|\Phi_2|$ analysis.



FIG. 3. (a) The phonon dispersion between Rb and I, (b) between Rb and S, and (c)between Re and S for $Rb_6Re_6S_8I_8$ at 300 K. The visualization of phonon mode at point in (e) low-frequency $\omega=0.87$ THz, (f) low-medium-frequency $\omega=3.47$ THz, and (g) high-frequency $\omega=8.08$ THz optical branches.v is the v-th phonon branch.

Figures 4(a,b) presents the potential energy curves for atomic displacements along the a-axis in X₆Re₆S₈I₈(X = Rb, Cs). The steepest potential energy curves correspond to Re and S atoms, indicating strong resistance to displacement from their local environments. In contrast, remarkably flat potential energy curves are observed for X and I2 atoms, suggesting their high mobility within the lattice. The overall lattice anharmonicity primarily stems from the motion of X and I atoms. Notably, the potential energy landscapes surrounding each atom type in Rb₆Re₆S₈I₈ and Cs₆Re₆S₈I₈ exhibit nearly identical chemical environments. Figures 4(c,d) display the diffusion coefficients at 300 K, revealing that X and I atoms. This further

confirms the loosely bound nature of Rb and I atoms moving between $[\text{Re}_6\text{S}_8\text{I}_6]^{4-}$ clusters, while Re and S atoms remain constrained within the clusters. The temperature-dependent mean square displacements (MSDs) are shown in Figs. 4(e,f). All atoms demonstrate increased MSDs at higher temperatures, with X and I2 atoms showing particularly large displacements in x, y, and z directions. Interestingly, I1 exhibits anisotropic behavior small MSD along x-direction but large along y and z-directions, reflecting distinct chemical environments. Compared with Cs₆Re₆S₈I₈, the Rb₆Re₆S₈I₈ compound demonstrates greater temperature-induced variations in MSDs, consistent with its softer lattice dynamics as evidenced by sound velocity and $|\Phi_2|$ analysis.



FIG. 4. The potential energy as a function of the atomic displacement of (a) $Rb_6Re_6S_8I_8$, and (b) $Cs_6Re_6S_8I_8$ along the a-direction. The diffusion coefficient of (c) $Rb_6Re_6S_8I_8$, and (d) $Cs_6Re_6S_8I_8$ (d) at 300 K. The temperature-dependent atomic mean square displacements (MSD) of (e) $Rb_6Re_6S_8I_8$, and (f) $Cs_6Re_6S_8I_8$ (f).

As shown in Fig. 5(b) and Fig. S6(b), the calculated differential and cumulative κ_p of $X_6 Re_6 S_8 I_8$ (X = Rb, Cs) at 300 K is derived using temperature-dependent force constants.

The particle-like thermal conductivity component $\kappa_{\rm p}^{\rm 3ph}$ for Rb₆Re₆S₈I₈ and Cs₆Re₆S₈I₈ under pure three-phonon (3ph) scattering are 0.17 and 0.18 W m⁻¹ K⁻¹, respectively. Upon inclusion of four-phonon (4ph) scattering, the $\kappa_{\rm p}^{\rm 3ph+4ph}$ values decrease to 0.15 and 0.17 W m⁻¹ K⁻¹, with the Rb-analogue exhibiting a reduction exceeding 10%, indicating the non-negligible contribution of four-phonon scattering. The $\kappa_{\rm p}^{\rm 3ph+4ph}$ values of X₆Re₆S₈I₈ are significantly lower than those of other superionic crystals, e.g., the reported $\kappa_{\rm p}^{\rm 3ph+4ph}$ is 0.32 W m⁻¹ K⁻¹ for Re₆Se₈Cl₂³⁶. This reduction can be attributed to the structural complexity of the primitive cell. Specifically, Rb₆Re₆S₈I₈ exhibits a more complex primitive cell containing 28 atoms³⁷, compared to only 16 atoms in Re₆Se₈Cl₂. The $\kappa_{\rm p}$ generally decreases with increasing number of atoms per primitive cell, as exemplified by Ag₉GaS₆ containing 56 atoms per primitive cell, which exhibits an ultralow $\kappa_{\rm p} = 0.031$ W·m⁻¹·K⁻¹³⁸. This negative correlation arises from enhanced phonon scattering channels in systems with larger primitive cells.

Figure 5(b) reveals two distinct growth regions of $\kappa_p^{3ph+4ph}$ in Rb₆Re₆S₈I₈: a low-frequency regime (0–0.8 THz) contributing 83% of the total thermal conductivity, dominated by acoustic branches and the three lowest-frequency optical branches, followed by a low-frequency regime (0.8–1.7 THz) contributing 11% from low-lying optical modes. A similar frequency dependence is observed in Cs₆Re₆S₈I₈, where phonons below 2.5 THz account for 95% of $\kappa_p^{3ph+4ph}$. The phonon lifetime (τ) distributions at 300 K, presented in Fig. 5(a) and Supplementary Fig. S6(a), demonstrate significant four-phonon scattering effects. Most phonons exhibit lifetimes below 10 ps, coupled with low group velocities, collectively suppressing κ_p . In contrast, low-frequency phonons maintain extended lifetimes (>10 ps) and higher group velocities, leading to their dominant contributions to κ_p .

Within the framework of the unified lattice thermal transport theory^{12,13}, the structural complexity of crystals inherently generates substantial off-diagonal thermal conductivity components κ_c arising from wave-like phonon tunneling. As shown in Figs. 5(a) and S6(a), phonon modes with lifetimes exceeding the Wigner limit ($\tau > \Delta \omega_{avg}^{-1}$) predominantly contribute to the particle-like thermal conductivity κ_p , while those with lifetimes between the Wigner and Ioffe-Regel limits ($\omega^{-1} < \tau < \Delta \omega_{avg}^{-1}$) primarily govern the wave-like tunneling component κ_c . Here, $\Delta \omega_{avg}$ is the average phonon band spacing, defined as $\Delta \omega_{avg} = \frac{\omega_{max}}{3N}$, ω_{max} is the highest phonon frequency, and N is the number of atoms in the primitive cell. In the inclusion of 4ph scattering significantly reduces phonon lifetimes in Rb₆Re₆S₈I₈, driving



FIG. 5. (a) The phonon lifetimes of the 3ph and 4ph as a function of phonon frequencies for $Rb_6Re_6S_8I_8$ at 300 K. Where the Ioffe-Regel ($\tau_{Ioffe-Regel} = \frac{1}{\omega}$) and Wigner ($\tau_{Wigner} = \frac{1}{\Delta\omega_{avg}}$) limits are represented by dotted yellow lines and green lines. (b) Calculated cumulative and differential κ_p as a function of phonon frequencies for $Rb_6Re_6S_8I_8$ at 300 K.(c) Calculated cumulative and differential differential κ_c as a function of phonon frequencies for $Rb_6Re_6S_8I_8$ at 300 K.(d) The resolved κ_c associated with various pairs of phonon frequencies (ω_s and $\omega_{s'}$).

numerous optical branches into the wave-like tunneling regime, which results in a pronounced reduction in $\kappa_p^{3ph+4ph}$. Despite the abundance of phonon modes in the wave-like tunneling regime, their contributions to κ_c remain negligible due to the predominance of mid- to highfrequency optical modes characterized by flat phonon dispersion and large frequency gaps. This is quantitatively demonstrated in Figs. 5(c) and S6(c), which present the frequencyresolved cumulative κ_c spectrum, its differential contribution, and atom-projected phonon density of states (DOS) at 300 K. Both Rb₆Re₆S₈I₈ and Cs₆Re₆S₈I₈ exhibit remarkably small κ_c values of 0.02 and 0.018 W·m⁻¹·K⁻¹, respectively, constituting only 12% and 10% of their total lattice thermal conductivity. The primary κ_c contributions in Rb₆Re₆S₈I₈ originate from phonon modes below 2.5 THz, as evidenced by three distinct spectral peaks. To elucidate their origins, Fig. 5(d) maps the pairwise frequency combinations (ω_s , $\omega_{s'}$) contributing to κ_c . The three peaks respectively arise from interactions between: (i) acoustic and the lowest optical branches, (ii) acoustic and low-lying optical branches, and (iii) low-lying optical branches themselves. DOS analysis reveals these spectral features predominantly stem from vibrations involving Rb and I atoms. Notably, high-frequency optical modes above 11 THz exhibit non-negligible κ_c contributions due to their dispersive phonon band structures and strong mode hybridization. While Cs₆Re₆S₈I₈ shows similar κ_c characteristics, so it will not be discussed repeatedly.

A notable thermal transport anomaly emerges in X₆Re₆S₈I₈: Despite heavier atomic mass, $Cs_6Re_6S_8I_8$ exhibits lower lattice thermal conductivity than $Rb_6Re_6S_8I_8$. Mass perturbation tests reveal negligible $\kappa_{\rm L}$ change ($\Delta \kappa_{\rm L} \approx 0.001 \ {\rm Wm^{-1}K^{-1}}$) when replacing Rb mass with Cs in $Rb_6Re_6S_8I_8$, indicating dominant interatomic interaction effects. Figure 2(d) reveals minimal changes in Φ_2 (Re-S) and Φ_2 (Re-I1) from Rb₆Re₆S₈I₈ to Cs₆Re₆S₈I₈, while Φ_2 (Re-I2) decreases by 9.7%. In contrast, Φ_2 (Cs-I1) and Φ_2 (Cs-I2) increase by 16.5% and 23.6% compared to Φ_2 (Rb-I1) and Φ_2 (Rb-I2), respectively. As Re-I1 interactions mainly affect mid-frequency optical branches with negligible $\kappa_{\rm L}$ contribution, the anomaly originates from enhanced X-I interactions. Bader charge analysis confirms stronger ionic bonding in $Cs_6Re_6S_8I_8$, with greater charge transfer between Cs and I2. X-I interactions predominantly modify acoustic and low-frequency optical branches (Fig. 6(a,b)). Rb₆Re₆S₈I₈ displays a small bandgap near 0.8 THz, flattening the lowest three optical branches and reducing phonon group velocities below 1 THz (Fig. 6(c)). Substituting Φ_2 (Cs-I) in Cs₆Re₆S₈I₈ with Φ_2 (Rb-I) softens phonon spectra (Fig. S7). Weaker Rb-I interactions enhance anharmonicity, evidenced by higher C_v and $|\gamma|$ values in Rb₆Re₆S₈I₈ compared to Cs₆Re₆S₈I₈ at identical temperatures (Fig. 6(d)).

The coexistence of ultralow particle-like κ_p and wave-like κ_c in X₆Re₆S₈I₈ represents a rare phenomenon in crystalline materials. While complex crystal structures generally exhibit suppressed κ_p through enhanced phonon scattering (due to increased number of atoms in PC and Brillouin zone folding effects), excessive structural complexity may paradoxi-

FIG. 6. The low-frequency atomic projected phonon dispersion of (a) $Rb_6Re_6S_8I_8$, and (b) $Cs_6Re_6S_8I_8$ at 300 K. (c) The phonon group velocities as functions of the phonon frequency for $X_6Re_6S_8I_8$ (X = Rb, Cs) at 300 K. (d) The gruneisen parameter ($|\gamma|$) and the heat capacity (C_v) for $X_6Re_6S_8I_8$ (X = Rb, Cs) at 300 K.

cally enhance κ_c . For instance, skutterudite YbFe₄Sb₁₂ (17 atoms in PC)³⁹ shows $\kappa_p = 0.83 \text{ Wm}^{-1} \text{ K}^{-1}$, and Bi₄O₄SeCl₂ (22 atoms in PC)⁴⁰ achieves $\kappa_p = 0.23 \text{ Wm}^{-1} \text{ K}^{-1}$. However, further increasing crystal complexity (e.g., Cu₇PS₆ with 56 atoms/primitive cell³⁸) reduces the average phonon band spacing $\Delta \omega_{\text{avg}}$, leading to non-negligible κ_c contributions exceeding 87%. Figure 7 maps the room-temperature κ_p and κ_c values against primitive cell atom counts for various materials. Although X₆Re₆S₈I₈ (28 atoms in PC) does not exhibit the lowest κ_p , its unique combination of high symmetry , moderate anharmonicity, and distinctive phonon flat bands which arising from bonding heterogeneity and guest-host architecture, enables unprecedented suppression of $\kappa_{\rm c}$ (< 0.02 Wm⁻¹K⁻¹). This contrasts with systems like AgTII₂¹¹ where balanced $\kappa_{\rm p}/\kappa_{\rm c}$ contributions (~50% each) yield $\kappa_{\rm L} = 0.25$ W·m⁻¹·K⁻¹, demonstrating the critical role of selective phonon engineering in achieving ultralow thermal conductivity.

FIG. 7. Potential pathways for pushing κ to its lower limit in inorganic materials. The dashed red line represents the current protocol to find materials with lower thermal conductivity. Lattice thermal conductivities are extracted from previous studies based on unified theory^{11,12,40-49}.

IV. CONCLUSION

In conclusion, based on the unified theory of lattice thermal transport, we have demonstrated that the superionic crystals $Rb_6Re_6S_8I_8$ and $Cs_6Re_6S_8I_8$ achieve ultralow lattice thermal conductivity κ_L of 0.17 and 0.19 Wm⁻¹K⁻¹ at 300 K, respectively, with weak temperature dependence. This exceptional behavior stems from their unique hierarchical architecture: strongly bonded $[\text{Re}_6\text{S}_8\text{I}_6]^{4-}$ clusters interconnected via weak ionic interactions between X⁺ (X = Rb, Cs) and I⁻ ions. The relative vibrations between clusters generate extensive optical phonon flat bands, suppressing coherent thermal transport ($\kappa_c \approx 0.02 \text{ Wm}^{-1} \text{ K}^{-1}$). Concurrently, the soft X⁺-I⁻ interactions depress both lowfrequency acoustic branches and optical modes, resulting in diminished particle-like conductivity ($\kappa_p = 0.15$ and 0.17 W m⁻¹ K⁻¹). Notably, Rb₆Re₆S₈I₈ exhibits anomalous thermal transport characteristics despite its lower atomic mass compared to the Cs analogue. The weaker Rb⁺-I⁻ coupling enhances lattice anharmonicity, reduces average phonon group velocities, and introduces a phonon band gap that further restricts dispersion in low-lying optical branches. These synergistic effects collectively yield the record-low κ_L in Rb₆Re₆S₈I₈. Our findings establish a new paradigm for phonon engineering through cluster-based anharmonicity tuning, providing a roadmap to develop ultralow κ_L materials for thermoelectric and thermal barrier applications.

ACKNOWLEDGMENTS

This research was supported by the National Natural Science Foundation of China under Grants No. 12204402, 12304038, and the Scientific Research Foundation for Doctor of Jiangxi University of Science and Technology (jxxjbs18044); the Science and Technology Plan Project of Yingtan (202412-18904); Jiangxi Key Laboratory of Advanced Copper-based Materials (2024SSY05021).

³ Mogens Christensen, Asger B Abrahamsen, Niels B Christensen, Fanni Juranyi, Niels H Andersen, Kim Lefmann, Jakob Andreasson, Christian RH Bahl, and Bo B Iversen. Avoided crossing

^{*} wuyu9573@qq.com

[†] guzonglin@yzu.edu.cn

[‡] zengsm@yzu.edu.cn

¹ Nitin P Padture, Maurice Gell, and Eric H Jordan. Thermal barrier coatings for gas-turbine engine applications. *Science*, 296(5566):280–284, 2002.

² Jian He and Terry M Tritt. Advances in thermoelectric materials research: Looking back and moving forward. *Science*, 357(6358):eaak9997, 2017.

of rattler modes in thermoelectric materials. Nat. Mater., 7(10):811-815, 2008.

- ⁴ Bingchao Qin, Dongyang Wang, Xixi Liu, Yongxin Qin, Jin-Feng Dong, Jiangfan Luo, Jing-Wei Li, Wei Liu, Gangjian Tan, Xinfeng Tang, et al. Power generation and thermoelectric cooling enabled by momentum and energy multiband alignments. *Science*, 373(6554):556–561, 2021.
- ⁵ Debattam Sarkar, Tanmoy Ghosh, Subhajit Roychowdhury, Raagya Arora, Sandra Sajan, Goutam Sheet, Umesh V Waghmare, and Kanishka Biswas. Ferroelectric instability induced ultralow thermal conductivity and high thermoelectric performance in rhombohedral p-type GeSe crystal. J. Am. Chem. Soc., 142(28):12237–12244, 2020.
- ⁶ Yi Xia, Vidvuds Ozoliņš, and Chris Wolverton. Microscopic mechanisms of glasslike lattice thermal transport in cubic Cu₁₂Sb₄S₁₃ tetrahedrites. *Phys. Rev. Lett.*, 125:085901, Aug 2020.
- ⁷ Saikat Mukhopadhyay, David S Parker, Brian C Sales, Alexander A Puretzky, Michael A McGuire, and Lucas Lindsay. Two-channel model for ultralow thermal conductivity of crystalline Tl₃VSe₄. *Science*, 360(6396):1455–1458, 2018.
- ⁸ Moinak Dutta, Shidaling Matteppanavar, Matukumilli VD Prasad, Juhi Pandey, Avinash Warankar, Pankaj Mandal, Ajay Soni, Umesh V Waghmare, and Kanishka Biswas. Ultralow thermal conductivity in chain-like TlSe due to inherent Tl⁺ rattling. J. Am. Chem. Soc., 141(51):20293–20299, 2019.
- ⁹ Binbin Jiang, Yong Yu, Juan Cui, Xixi Liu, Lin Xie, Jincheng Liao, Qihao Zhang, Yi Huang, Shoucong Ning, Baohai Jia, et al. High-entropy-stabilized chalcogenides with high thermoelectric performance. *Science*, 371(6531):830–834, 2021.
- ¹⁰ Shuming Zeng, Lei Fang, Zonglin Gu, Xinming Wang, Yinchang Zhao, Geng Li, Yusong Tu, and Jun Ni. Ultralow lattice thermal conductivities and excellent thermoelectric properties of hypervalent triiodides XI₃ (X= Rb, Cs) discovered by machine learning method. J. Chem. Phys., 159(1), 2023.
- ¹¹ Zezhu Zeng, Xingchen Shen, Ruihuan Cheng, Olivier Perez, Niuchang Ouyang, Zheyong Fan, Pierric Lemoine, Bernard Raveau, Emmanuel Guilmeau, and Yue Chen. Pushing thermal conductivity to its lower limit in crystals with simple structures. *Nat. Commun.*, 15(1):3007, 2024.
- ¹² Michele Simoncelli, Nicola Marzari, and Francesco Mauri. Unified theory of thermal transport in crystals and glasses. *Nat. Phys.*, 15(8):809–813, 2019.

- ¹³ Michele Simoncelli, Nicola Marzari, and Francesco Mauri. Wigner formulation of thermal transport in solids. *Phys. Rev. X*, 12:041011, Oct 2022.
- ¹⁴ Zhiting Tian, Jivtesh Garg, Keivan Esfarjani, Takuma Shiga, Junichiro Shiomi, and Gang Chen.
 Phonon conduction in PbSe, PbTe, and PbTe_{1-x}Se_x from first-principles calculations. *Phys. Rev. B*, 85:184303, May 2012.
- ¹⁵ Noriaki Kamaya, Kenji Homma, Yuichiro Yamakawa, Masaaki Hirayama, Ryoji Kanno, Masao Yonemura, Takashi Kamiyama, Yuki Kato, Shigenori Hama, Koji Kawamoto, et al. A lithium superionic conductor. *Nat. Mater.*, 10(9):682–686, 2011.
- ¹⁶ Yan Wang, William Davidson Richards, Shyue Ping Ong, Lincoln J Miara, Jae Chul Kim, Yifei Mo, and Gerbrand Ceder. Design principles for solid-state lithium superionic conductors. *Nat. Mater.*, 14(10):1026–1031, 2015.
- ¹⁷ Huili Liu, Xun Shi, Fangfang Xu, Linlin Zhang, Wenqing Zhang, Lidong Chen, Qiang Li, Ctirad Uher, Tristan Day, and G Jeffrey Snyder. Copper ion liquid-like thermoelectrics. *Nat. Mater.*, 11(5):422–425, 2012.
- ¹⁸ Siqi Sun, Min Lu, Xupeng Gao, Zhifeng Shi, Xue Bai, William W Yu, and Yu Zhang. 0d perovskites: unique properties, synthesis, and their applications. *Adv. Sci.*, 8(24):2102689, 2021.
- ¹⁹ Georg Kresse and Jürgen Furthmüller. Efficient iterative schemes for ab initio total-energy calculations using a plane-wave basis set. *Phys. Rev. B*, 54(16):11169, 1996.
- ²⁰ P Hohenberg and WJPR Kohn. Density functional theory (dft). *Phys. Rev.*, 136(1964):B864, 1964.
- ²¹ Walter Kohn and Lu Jeu Sham. Self-consistent equations including exchange and correlation effects. *Phys. Rev.*, 140(4A):A1133, 1965.
- ²² Georg Kresse and Daniel Joubert. From ultrasoft pseudopotentials to the projector augmentedwave method. *Phys. Rev. B*, 59(3):1758, 1999.
- ²³ John P Perdew, Kieron Burke, and Matthias Ernzerhof. Generalized gradient approximation made simple. *Phys. Review Lett.*, 77(18):3865, 1996.
- ²⁴ Stefano Baroni, Stefano De Gironcoli, Andrea Dal Corso, and Paolo Giannozzi. Phonons and related crystal properties from density-functional perturbation theory. *Rev. Mod. Phys.*, 73(2):515, 2001.

- ²⁵ Olle Hellman and Igor A Abrikosov. Temperature-dependent effective third-order interatomic force constants from first principles. *Phys. Rev. B*, 88(14):144301, 2013.
- ²⁶ Wu Li, Lucas Lindsay, David A Broido, Derek A Stewart, and Natalio Mingo. Thermal conductivity of bulk and nanowire Mg₂Si_xSn_{1-x} alloys from first principles. *Phys. Rev. B*, 86(17):174307, 2012.
- ²⁷ Wu Li, Jesús Carrete, Nebil A Katcho, and Natalio Mingo. Shengbte: A solver of the boltzmann transport equation for phonons. *Comput. Phys. Commun.*, 185(6):1747–1758, 2014.
- ²⁸ Zherui Han, Xiaolong Yang, Wu Li, Tianli Feng, and Xiulin Ruan. Fourphonon: An extension module to shengbte for computing four-phonon scattering rates and thermal conductivity. *Comput. Phys. Commun.*, 270:108179, 2022.
- ²⁹ Linxuan Ji, Anqi Huang, Yiqi Huo, Yi-min Ding, Shuming Zeng, Yu Wu, and Liujiang Zhou. Influence of four-phonon scattering and wavelike phonon tunneling effects on the thermal transport properties of TlBiSe₂. *Phys. Rev. B*, 109:214307, Jun 2024.
- ³⁰ Craig C Laing, Daehan Kim, Jinu Park, Jiahong Shen, Ido Hadar, Justin M Hoffman, Jiangang He, Byungha Shin, Chris Wolverton, and Mercouri G Kanatzidis. Solution-processable mixed-anion cluster chalcohalide Rb₆Re₆S₈I₈ in a light-emitting diode. *Nat. Mater.*, 23(2):230–236, 2024.
- ³¹ Cheng Chang and Li-Dong Zhao. Anharmoncity and low thermal conductivity in thermoelectrics. *Mater. Today Phys.*, 4:50–57, 2018.
- ³² Glen A Slack. Nonmetallic crystals with high thermal conductivity. J. Phys. Chem. Solids, 34(2):321–335, 1973.
- ³³ Glen A Slack. The thermal conductivity of nonmetallic crystals. Solid State Phys., 34:1–71, 1979.
- ³⁴ Wen Li, Siqi Lin, Binghui Ge, Jiong Yang, Wenqing Zhang, and Yanzhong Pei. Low sound velocity contributing to the high thermoelectric performance of Ag₈SnSe₆. Adv. Sci., 3(11):1600196, 2016.
- ³⁵ TJ Zhu, SN Zhang, SH Yang, and XB Zhao. Improved thermoelectric figure of merit of selfdoped Ag_{8-x}GeTe₆ compounds with glass-like thermal conductivity. *Phys. Status Solidi-R.*, 4(11):317–319, 2010.
- ³⁶ Xiangyu Zeng, Guangming Niu, Xiaowei Wang, Jutao Jiang, Laizhi Sui, Yutong Zhang, Anmin Chen, Mingxing Jin, and Kaijun Yuan. Strain-engineered thermoelectric performance in super-

atomic semiconductor $\operatorname{Re}_6\operatorname{Se}_8\operatorname{C}_{l2}$: The role of four-phonon scattering and coherent phonons. J. Phys. Chem. Lett., 16:3122–3132, 2025.

- ³⁷ Yi Xia, Dale Gaines, Jiangang He, Koushik Pal, Zhi Li, Mercouri G Kanatzidis, Vidvuds Ozoliņš, and Chris Wolverton. A unified understanding of minimum lattice thermal conductivity. *Proc. Nat. Acad. Sci.*, 120(26):e2302541120, 2023.
- ³⁸ Niuchang Ouyang, Dongyi Shen, Chen Wang, Ruihuan Cheng, Qi Wang, and Yue Chen. Positive temperature-dependent thermal conductivity induced by wavelike phonons in complex Ag-based argyrodites. *Phys. Rev. B*, 111:064307, Feb 2025.
- ³⁹ Enrico Di Lucente, Michele Simoncelli, and Nicola Marzari. Crossover from boltzmann to wigner thermal transport in thermoelectric skutterudites. *Phys. Rev. Res.*, 5(3):033125, 2023.
- ⁴⁰ Zhen Tong, Alessandro Pecchia, ChiYung Yam, Traian Dumitrica, and Thomas Frauenheim. Glass-like transport dominates ultralow lattice thermal conductivity in modular crystalline Bi₄O₄SeCl₂. Nano Lett., 23(20):9468–9473, 2023.
- ⁴¹ Yi Xia, Vidvuds Ozoliņš, and Chris Wolverton. Microscopic mechanisms of glasslike lattice thermal transport in cubic Cu₁₂Sb₄S₁₃ tetrahedrites. *Phys. Rev. Lett.*, 125(8):085901, 2020.
- ⁴² Qing-Yu Xie, Peng-Fei Liu, Jiang-Jiang Ma, Li-Ming Wu, Kai-Wang Zhang, and Bao-Tian Wang. Microscopic mechanisms of glasslike lattice thermal conductivity in tetragonal α-CsCu₅Se₃. *Phys. Rev. B*, 108(1):014302, 2023.
- ⁴³ Xingchen Shen, Niuchang Ouyang, Yuling Huang, Yung-Hsiang Tung, Chun-Chuen Yang, Muhammad Faizan, Nicolas Perez, Ran He, Andrei Sotnikov, Kristin Willa, et al. Amorphouslike ultralow thermal transport in crystalline argyrodite Cu₇PS₆. Advanced Science, page 2400258, 2024.
- ⁴⁴ Ankit Jain. Multichannel thermal transport in crystalline Tl₃VSe₄. Phys. Rev. B, 102(20):201201, 2020.
- ⁴⁵ Jingyu Li, Liuming Wei, Zhuoyang Ti, Jianbo Zhu, Wenya Zhai, Hang Li, and Peng-Fei Liu. Ultralow two-channel thermal conductivity in aikinite. *Mater. Today Phys.*, 45:101454, 2024.
- ⁴⁶ Qing-Yu Xie, Feng Xiao, Kai-Wang Zhang, and Bao-Tian Wang. Anharmonic phonon selfenergy and anomalous thermal transport in the quaternary compound BaAg₂SnSe₄. *Phys. Rev. B*, 110(4):045203, 2024.
- ⁴⁷ T Pandey, Mao-Hua Du, David S Parker, and L Lindsay. Origin of ultralow phonon transport and strong anharmonicity in lead-free halide perovskites. *Mater. Today Phys.*, 28:100881, 2022.

- ⁴⁸ Fan Li, Xin Liu, Jiawei Yang, Xin-Ye Wang, Yi-Chang Yang, Ni Ma, Ling Chen, and Li-Ming Wu. Long-range anion correlations mediating dynamic anharmonicity and contributing to glassy thermal conductivity in well-ordered K₂Ag₄Se₃. *Small*, 21(4):2409524, 2025.
- ⁴⁹ Jingyu Li, Xiyang Li, Yongsheng Zhang, Jianbo Zhu, Enyue Zhao, Maiko Kofu, Kenji Nakajima, Maxim Avdeev, Peng-Fei Liu, Jiehe Sui, et al. Crystal-liquid duality driven ultralow two-channel thermal conductivity in α-MgAgSb. Appl. Phys. Rev, 11(1), 2024.