Heat Capacity of the Pressure-Induced Superconductivity in Itinerant Ferromagnet UGe₂

Naoyuki TATEIWA^{*}, Tatsuo C KOBAYASHI¹, Kiichi AMAYA, Yoshinori HAGA², Rikio SETTAI³ and Yoshichika ŌNUKI³

Department of Physical Science, Grasuate School of Engineering Science, Osaka University, Toyonaka, Osaka 560-8531, Japan

¹Research Center for Materials Science at Extreme Conditions, Osaka University, Toyonaka, Osaka 560-8531, Japan

Japan

² Advanced Science Research Center, Japan Atomic Energy Research Institute, Tokai-mura, Naka-Gun, Ibaraki, 319-1195, Japan

³ Department of Physics, Graduate School of Science, Osaka University, Toyonaka, Osaka 560-0043, Japan

(Received November 7, 2018)

Recently co-existence of the ferromagnetism and superconductivity was reported in the highpressure region (1.0-1.6 GPa) in UGe₂. We performed the heat capacity measurement on UGe₂ under high pressure. At 1.13 GPa, we found a peak corresponding to the superconducting transition. The superconducting temperature $T_{\rm SC}$ and $\Delta C/(\gamma T_{\rm SC})$ are 0.6 K and 0.25, respectively. The superconducting transition was also confirmed by the appearance of the Meissner effect in the *ac* susceptibility. From these results, we confirm a bulk nature of the superconductivity in UGe₂. The value of C/T (~ 95 mJ/moleK²) just above $T_{\rm SC}$ at 1.15 GPa is as much as 3 times larger than that at ambient pressure, which indicates a large mass enhancement of quasiparticles under high pressure.

KEYWORDS: UGe2, Ferromagnetism, Superconductivity

§1. Introduction

UGe₂ is a metallic ferromagnet with a Curie temperature $T_{\rm C} = 52$ K and the spontaneous moment 1.4 $\mu_{\rm B}/{\rm U}$ at ambient pressure.^{1,2)} The magnetization is highly anisotropic along the easy *a*-axis in orthorhombic crystal structure. Recently it was reported that UGe₂ is a pressure-induced superconductor.^{3–5)} Superconductivity was observed in the pressure range from 1.0 to 1.6 GPa. Surprisingly, in this pressure range UGe₂ is still in the ferromagnetic state. We have preformed the heat capacity measurement on UGe₂ in order to confirm the bulk nature of the superconductivity.

§2. Experimental

A single crystal was grown by the Czochralski pulling method in a tetra-arc furnace as described in ref. 5. The residual resistivity ratio RRR of the present sample were 600 at ambient pressure. The heat capacity and the *ac* susceptibility were measured by the adiabatic heat pulse and Hartshorn bridge methods, respectively. The lowtemperature range of 0.18-6K was generated by ³He-⁴He dilution refrigerator. Pressure was applied by utilizing a Cu-Be piston-cylinder cell with a Daphne oil (7373) as a pressure-transnitting medium.

§3. Result and Discussion

Figure 1 shows temperature dependence of C/T for P = 0 and 1.15 GPa, together with the *ac* susceptibility.



Fig. 1. Temperature dependence of the heat capacity in the form of C/T at 0 and 1.15 GPa, together with the *ac* susceptibility at 1.15 GPa in UGe₂.

The *ac* susceptibility was measured for the same sample, simultaneously with the heat capacity measurement. At ambient pressure, C/T is almost constant at low temperature and the γ value is determined to be about 30 mJ/moleK², which is consistent with the previous report.¹) At 1.15 GPa, we found a peak in C/T around 0.6

^{*} E-mail:tateiwa@djebel.mp.es.osaka-u.ac.jp



Fig. 2. Pressure phase diagram and pressure dependence of the γ value in UGe2.

K corresponding to the superconducting transition. The superconducting transition temperature $T_{\rm SC}$ is about 0.6 K. The superconducting transition was also confirmed by the appearance of the Meissner effect in the *ac* susceptibility below $T_{\rm SC}$. From these results, it was concluded that the superconductivity in UGe₂ was a bulk phenomenon.

The peak of C/T at $T_{\rm SC}$ is weak as $\Delta C/(\gamma T_{\rm SC}) =$ 0.25, which is smaller than a BCS value of 1.45. Here ΔC is the jump of the heat capacity at $T_{\rm SC}$. The residual γ value of 65 mJ/moleK² is large. Machida *et al.* discussed the superconductivity of UGe₂ on the basis of a non-unitary triplet paring.⁶⁾ In this mechanism, only the Fermi surface of the majority band opens the gap and the minority band remains normal state below $T_{\rm SC}$. Recent band calculations suggest that there is substantial contibution to the density of state at the Fermi energy from the minority band.^{7,8} Thus present large residual γ value might be explained by this scenario. However we suggest that the large residual γ is a consequence of the sample quality because the superconducting peak is broad. Considering that the present sample is a high quality single crystal sample with RRR = 600, the superconductivity in UGe₂ seems to be very sensitive to small amount impurities. It suggests the unconventional nature of the superconductivity and the pairing symmetry is not s-wave but possibly p-wave.

The γ value at 1.15 GPa was determined to be 95 mJ/moleK² from the value of C/T just above $T_{\rm SC}$. This γ value is about three times larger than that at ambient pressure. Figure 2 shows the pressure dependence of the



Fig. 3. Temperature dependence of the heat capacity in the form of C/T at 1.15 GPa under the magnetic field up to 6 T in UGe₂.

 γ value, together with the phase diagram in UGe₂. $T_{\rm C}$ is the Curie temperature. T^* is another characteristic temperature where the resistivity and the magnetization show an anomaly.^{4,9)} The detailed nature of the transition at T^* is not known at present. The γ value increases steeply above 1.0 GPa, where superconductivity starts to appear, and has a shoulder at 1.2 GPa where T^* becomes zero and $T_{\rm SC}$ shows maximum. This suggests that a large γ value originated from the low energy magnetic fluctuation related to the phase transition at T^* and this magnetic fluctuation might be driving force for the formation of Cooper pairs.

Figure 3 shows the temperature dependence of C/T at 1.15 GPa under the magnetic field up to 6 T along the a axis (easy axis). The superconducting peak was not observed in the mangetic field of 1 T. C/T was strongly depressed by the appplication of magnetic fields. It suggests that a low energy magnetic fluctuiation, which is the origin of the large γ , is suppressed by the magnetic field.

In conclusion, we confirm the bulk superconductivity in UGe₂ by the heat capacity measurement. The large γ value observed in the pressure region where superconductivity appears suggests the superconductivity of heavy quasiparticles.

Ackonowledgement

This work was financially supported by the Grant-in Aid for COE Research (No. 10CE2004) of the Ministry of Education, Science, Sports and Culture, and by CREST, Japan Science and Technology Corporation.

- 1) Y. Ōnuki et al., J. Phys. Soc. Jpn. 61 (1992) 293.
- 2) P. Boulet et al., J. Alloys. Compounds 247 (1997) 104.
- 3) S. S. Saxena *et al.*, Nature **604** (2000) 587.
- 4) A. Huxley et et al., Phys. Rev. B 63 (2001) 144519.
- 5) N. Tateiwa et al., J. Phys.:Condense. Matter 13 (2001) L17.
- 6) K. Machida et al., Phys. Rev. Lett. 86 (2001) 850.

- 7) A. B. Shick *et al.*, Phys. Rev. Lett. **86** (2001) 300.
- 8) S. Tejima *et al.*, to be published.
- 9) N. Tateiwa et al., submitted to J. Phys. Soc. Jpn.