Photoinduced Changes of Reflectivity in Single Crystals of $YBa_2Cu_3O_{6.5}$ (Ortho II)

G. P. Segre, N. Gedik, J. Orenstein

Materials Sciences Division, Lawrence Berkeley National Laboratory and Physics Department, University of California, Berkeley, California 94720

> D.A. Bonn, Ruixing Liang, W.N. Hardy University of British Columbia, Vancouver, Canada (October 26, 2018)

We report measurements of the photoinduced change in reflectivity of an untwinned single crystal of $YBa_2Cu_3O_{6.5}$ in the ortho II structure. The decay rate of the transient change in reflectivity is found to decrease rapidly with decreasing temperature and, below T_c , with decreasing laser intensity. We interpret the decay as a process of thermalization of antinodal quasiparticles, whose rate is determined by an inelastic scattering rate of quasiparticle pairs.

74.25.Gz, 78.47.+p

Much of current researchon cuprate superconductivity focuses on the low-energy electronic structure. Perhaps the most pressing question is whether the pseudogap is a precursor of the superconducting gap, or has an entirely different origin. Another key question is whether quasiparticles live in a two-dimensional environment, or one with pronounced one-dimensional properties on short length and time scales.

The relaxation dynamics of non-equilibrium quasiparticles can be extremely sensitive to such local electronic properties [1,2]. A promising technique to study quasiparticle relaxation is optical pump and probe spectroscopy. In this type of experiment a pulse of light stimulates a non-equilibrium state with excess energy and quasiparticle density. A weaker pulse, which is delayed relative to the pump, probes the nonequilibrium state by detecting changes in the absorptance or reflectance. Dynamics can be measured with sub-picosecond time resolution while anisotropy can be explored by varying the polarization of the pump and probe beams.

In this paper we report pump and probe measurements performed on an untwinned single crystal of $YBa_2Cu_3O_{6.5}$ (Ortho II). In this material the charge reservoir layer is an ordered array of alternating filled and empty copper oxygen chains. Together with $YBa_2Cu_4O_8$ it is one of two underdoped materials in which doping does not introduce disorder. We find, in contrast with an earlier report [3] on underdoped films, that the decay rate of the photoinduced change in reflectivity depends strongly on the excitation density and temperature. Because it vanishes in the limit that both tend to zero, we interpret the decay rate as an inelastic scattering rate of quasiparticle pairs. We present evidence that the decay corresponds to a process of thermalization, rather than recombination, of the nonequilibrium quasiparticle population. The dynamics of thermalization change suddenly upon crossing from the pseudogap regime to the superconducting state.

We measured the decay of the change in reflectivity at a photon energy of 1.5 eV due to excitation with photons of the same energy. The optical pulses, produced by a mode-locked Ti:Sapphire laser, have duration of 100 fs, repetition rate 12 ns, and center wavelength 800 nm. Both the pump and probe beams were focused onto the sample with a 20 cm focal length lens, yielding a spot size of 75 μ diameter. A photoelastic modulator varied the pump intensity at 100 kHz and a vibrating mirror oscillating at 40 Hz varied the time delay between pump and probe. This double modulation provides sensitivity to the fractional change in reflectivity $\Delta R/R$ of 10^{-7} .



FIG. 1. (a) $\Delta R/R vs. t$ at constant pump intensity for different temperatures (polarization perpendicular to chains). (b) Maximum amplitude of $\Delta R/R vs. T$ for both polarization parallel and perpendicular to the chains.

Fig. 1a shows $\Delta R/R$ due to absorption of a pump pulse of energy 0.07 nJ vs. time (t), at several temperatures. These reflectivity transients were measured with pump and probe polarization each aligned perpendicular to the chain axis but the decay rate is the same when measured with polarization along the chains. The amplitude of $\Delta R/R$ increases and the decay rate decreases as the temperature is lowered. Fig. 1b shows the temperature dependence of the maximum amplitude $(\Delta R/R)_{max}$. The reflectivity change is smaller when measured with pump and probe parallel to the chains, particularly above T_c .

The T dependence shown in Fig. 1 is consistent with earlier reports of $\Delta R/R$ in underdoped (twinned) thin films excited at 1.5 eV and probed at either near-infrared [1] or far-infrared [4] frequencies. These data have revealed a strong correlation of $\Delta R/R$ with the strength of spin and current fluctuations at the characteristic energy scale for superconductivity in the cuprates. As emphasized in Ref. [4], the increase of $\Delta R/R$ with decreasing T tracks the growth of a spin resonance peak seen by neutron scattering [5,6] and a gap-like feature seen in optical conductivity [7,8]. Furthermore, $\Delta R/R$ shows the same behavior with varying carrier concentration as do these spectroscopic features, namely abrupt onset at T_c for near optimal doping [9] and a slow onset above T_c for underdoped materials [1,4]. Such considerations suggest that 1.5 eV photons ultimately generate low-energy excitations, despite the fact that they initially create an electron-hole pair whose energy is much larger than the maximum gap energy Δ_0 .

It is generally agreed that the generation of low energy quasiparticles occurs via a rapid cascade process, in which the parent electron-hole pair creates a large number of excitations at much lower energy. What has remained less clear is the mechanism by which this nonequilibrium population of quasiparticles causes a change in reflectivity in the visible region of the spectrum. However, recent measurements [4] of the photoinduced change in far-IR reflectivity point to a mechanism for changes in reflectivity at 1.5 eV. Because it is crucial to understanding the decay of $\Delta R/R$ with time, we describe this mechanism below.

The far-IR measurements reveal that photoexcitation shifts conductivity spectral weight from low energies (most likely the condensate contribution at zero energy) to ~100 meV. This change corresponds to filling in the gap feature in the optical conductivity. The Kramers-Kronig relations dictate that this redistribution of spectral weight changes the real part of the dielectric function at much higher frequencies (ω) according to:

$$\Delta \epsilon_1(\omega) = -\frac{8}{\omega^4} \int d\omega' \Delta \sigma_1(\omega') \omega'^2 \tag{1}$$

where $\Delta \sigma_1$ is the change in the real part of the optical conductivity. Eq. 1 shows that $\Delta \epsilon_1$ is proportional to the second moment of the change in the conductivity, or $\Sigma^{(2)}$. Because the spectral weight shifts from zero to ~100 meV, we can relate the second moment to the spectral weight shift, *i.e.*, $\Sigma^{(2)} \approx (100 meV)^2 \int_{0^+} d\omega \Delta \sigma_1(\omega)$. Finally, using literature [10] values $\epsilon_1 = 1.1$ and $\epsilon_2 = 2.7$ at 1.5 eV, we can establish an approximate calibration between $\Delta R/R$ and $\int_{0^+} d\omega \Delta \sigma_1(\omega)$.

The data shown in Fig. 2 provide a test of this mechanism for reflectivity change at 1.5 eV. We plot $(\Delta R/R)_{max}$ at 15 K vs. excitation density expressed in units of photons per planar Cu. The right-hand scale shows the spectral weight shift that, according to the preceding analysis, generates the change in reflectivity shown on the left-hand scale. The spectral weight is normalized to the condensate spectral weight assuming a penetration depth of 1600 Å [11]. Notice that $\Delta R/R$ departs from linearity at $\sim 1.5 \times 10^{-4}$, which corresponds to a shift of 30% of the condensate spectral weight. This reasonable value for the onset of nonlinearity lends credibility to the calibration. It is important to note that a measurable reflectivity change occurs only if spectral weight shifts to frequencies of the order of Δ_0 . If instead the spectral weight were shifted to the quasiparticle Drude peak, $\Delta R/R$ would be smaller by the factor $(1/\tau\Delta_0)^2$, which is ~ 10⁶ for these exceptionally clean ortho II crystals [13].



FIG. 2. $\Delta R/R$ (black circles) vs. excitation density. Right-hand scale shows the spectral weight shift necessary to produce the reflectivity change on the left.

Given this interpretation of the change in reflectivity, we now turn to the central result of this paper, namely the rate of decay of $\Delta R/R$ measured as a function of Tand pump intensity I. We have seen in Fig. 1 that the decay of $\Delta R/R$ becomes slower as T decreases. Fig. 3a, a plot of the reflectivity change at 15 K created by pulses of varying intensity, shows that the decay rate also slows as the excitation density decreases.

The decays shown in Fig. 3a are non-exponential in that the instantaneous rate of decay, $\gamma(t) \equiv$ $-dln(\Delta R)/dt$, decreases as t increases. To characterize the intensity dependence of the decay rate in a relatively simple way, we focus on the initial decay rate, or $\gamma(0)$. We estimate $\gamma(0)$ from the slope of a linear fit to $\Delta R/R$ between 100% and 75% of $(\Delta R/R)_{max}$, normalized by



FIG. 3. (a) Decay of $\Delta R/R$ for several pump intensities at 15K (b)Initial decay rate $\gamma(0)$ vs. $(\Delta R/R)_{max}$.

the average value of $\Delta R(t)/R$ in that interval. Given our time resolution, this procedure provides a good estimate of $\gamma(0)$ for rates slower than $\sim 1ps^{-1}$. Fig. 3b shows $\gamma(0)$ as a function of $(\Delta R/R)_{max}$, obtained by analysis of the curves similar to the ones in Fig. 3a. $\gamma(0)$ decreases linearly with $(\Delta R/R)_{max}$ and extrapolates to a nonzero intercept as the excitation density approaches zero.

The dependence of $\gamma(0)$ on excitation density is consistent with two-particle kinetics, for example a process in which a pair of quasiparticles scatter off of each other. For high excitation densities the rate of such scattering is proportional to the nonequilibrium density. As the excitation density decreases, becoming smaller than the thermal population, $\gamma(0)$ approaches the equilibrium scattering rate at that temperature [12].

Fig. 4 presents the intensity dependence of the decay rate for a range of temperatures, in the form of a logarithmic plot of $\gamma(0)$ vs. *T*. Points with the same (open) symbol show $\gamma(0)$ measured at the same excitation density, but at different temperatures. The data sets coincide at high temperatures but diverge suddenly at T_c , showing that the dependence of $\gamma(0)$ on I starts abruptly upon crossing from the pseudogap to the superconducting state. The solid symbols show the decay rate in the limit of zero excitation density, γ_{th} , as determined from the intercept of plots such as in Fig. 3b. The same quantity is plotted on linear axes in the inset. With decreasing temperature γ_{th} begins to decrease in the normal state and is proportional to T^3 for temperatures less than ~40 K.



FIG. 4. Initial decay rate $\gamma(0)$ vs. T at fixed I (open symbols). Decay rate in low I limit, γ_{th} , vs. T (solid symbols in main panel and inset).

Several aspects of the decay rate of $\Delta R/R$ suggest a strong connection to quasiparticle dynamics, as well as structure in the low-energy density of states. For example, the decay rate appears sensitive to the opening of the pseudogap, decreasing near T^* in a manner which is remarkably similar to the nuclear spin relaxation rate in underdoped YBCO [14]. The onset of superconductivity also affects the decay dynamics — the decay rate depends on excitation density only below T_c . Finally the T^3 dependence of γ_{th} is consistent with the prediction of a theoretical analysis [15] of quasiparticle scattering and recombination in the presence of antiferromagnetic correlations. Although the rates were calculated within the random phase approximation, the asymptotic T^3 behavior is a universal feature of quasiparticle scattering in a d-wave superconductor [15].

The simplest interpretation of the connection between $\gamma(0)$ and quasiparticle dynamics is that $\Delta R(t)/R$ reflects the decay of the nonequilibrium quasiparticle density. According to this view, $\gamma(0)$ is the rate at which quasiparticle pairs scatter into the condensate and γ_{th} is its value in thermal equilibrium. Although such an interpretation appears to be consistent with the prediction of Ref. 16, this description of the decay of $\Delta R/R$ is not

internally consistent. The inconsistency arises because quasiparticle interactions alone cannot reduce either the excess particle or energy density. For quasiparticles to scatter into the condensate they must shed their excess energy, which for antiferromagnetic interactions appears as a spin fluctuation. However, in the low-energy regime $(\omega \ll J)$ the spin fluctuation is essentially the same entity as a quasiparticle-hole pair. Therefore such a 'recombination' process actually scatters one pair into another, with no net change in the number or energy density. This is analogous to a problem in the interpretation of transport experiments, where quasiparticle scattering alone cannot reduce the total momentum [16].

The 'true' recombination rate, in the sense of recovery of the of equilibrium quasiparticle density, would likely differ markedly from the reflectivity decay rates shown in Fig. 4. Relaxation of the quasiparticle density requires that excess energy flow irreversibly from the electrons to the lattice [17]. We expect that process to be extremely slow on the time scale of quasiparticle scattering and to exhibit single rather than two-particle kinetics. This expectation is based on the physics of the 'phonon bottleneck' in s-wave superconductors [12], an effect which may be even more restrictive in d-wave superconductors.

The bottleneck arises because the process in which a quasiparticle pair emits a phonon and scatters into the condensate is reversible — the emitted phonon can immediately regenerate the quasiparticle pair. The quasiparticle density relaxes at the rate at which the typical phonon energy decreases below the threshold for pair creation. Not only is this rate slower than the quasiparticle scattering rate, it is also approximately independent of the excess quasiparticle density.

The relaxation of the quasiparticle density may be even slower in the cuprates than in conventional superconductors. In s-wave superconductors the phonons decouple from the electrons when their energy becomes less than 2Δ . In the d-wave superconductors, where there is no threshold for pair creation, the typical phonon energy must degrade to $\sim k_B T$ in order for the electronic system to reach equilibrium. The extremely weak coupling between nodal quasiparticles and phonons compounds this effect. The decay of a quasiparticle pair into an acoustic phonon is kinematically forbidden because the quasiparticle velocity is larger than the sound velocity [17].

If recombination is extremely slow, why does $\Delta R/R$ decay on a picosecond time scale? The remaining possibility is that the decay corresponds to thermalization, rather than recombination. If $\Delta R/R$ is not a direct measure of the quasiparticle density, but proportional instead to the $\Sigma^{(2)}$ as we have argued previously, it can decrease during thermalization, despite a constant, or even increasing, density of quasiparticles. Microwave measurements show that $\Sigma^{(2)}$ for nodal particles is small, because their spectral weight is confined to a very narrow (~10 μ eV) Drude peak [18]. The observed ~100 meV spectral weight shifts [4], and consequently large values of $\Sigma^{(2)}$, are likely due to the antinodal quasiparticles. These considerations suggest that the decay of $\Delta R/R$ measured at 1.5 eV tracks the conversion of quasiparticles from a nonthermal distribution, which has substantial $\Sigma^{(2)}$, to a quasithermal distribution in which $\Sigma^{(2)}$ is a factor 10^6 smaller. Measurements in which the nonequilibrium state is probed in the frequency range of the Drude conductivity [17] show much longer decay times (typically milliseconds), consistent with an experiment which selectively probes the nodal quasiparticle density.

In summary, we present measurements of the photoinduced change in reflectivity in an underdoped crystal of YBCO, and discuss a new perspective on this effect. We interpret the decay rate of $\Delta R/R$ as the inelastic scattering rate of quasiparticle pairs, which sets the time scale for thermalization of the nonequilibrium population. The thermalization rate decreases with the development of the pseudogap, becomes excitation density dependent in the superconducting state, and varies as T^3 in the low excitation limit. Coordinated measurements of photoinduced changes in optical response over a broad spectral range, from terahertz to visible frequencies, are needed to test this perspective.

We acknowledge valuable discussions with D.J. Scalapino. This work was supported under NSF-9870258, DOE-DE-AC03-76SF00098, Canadian Institute for Advanced Research and NSERC.

- [1] V.V. Kabanov et al., Phys. Rev. B. 59, 1497 (1999).
- [2] J. Demsar *et al.*, Phys. Rev. Lett. **83**,800 (1999).
- [3] D. Mihailovic and J. Demsar in "Spectroscopy of Superconducting Materials," ACS Symposium 730, ed. E. Faulges.
- [4] R. Kaindl et al., Science 287, 5452 (2000).
- [5] J. Rossat-Mignod, et al., Physica C 185-189, 86 (1991).
- [6] H.A. Mook *et al.*, Phys. Rev. Lett. **70**, 3490 (1993); H.F. Fong *et al.*, ibid. **75**, 316 (1995).
- [7] J. Orenstein et al., Phys. Rev. B. 42, 6342 (1990).
- [8] L.D. Rotter *et al.*, Phys. Rev. Lett. **67**, 2741 (1991).
- [9] J.M.Chwalek et al., App. Phys. Lett. 57, 980 (1990).
- [10] S.L. Cooper *et al.*, Phys. Rev. B. **47**, 8233 (1993).
- [11] D.N. Basov et al., Phys. Rev. Lett. 74, 598 (1995).
- [12] K.E. Gray, in Nonequilibrium superconductivity, phonons, and Kapitza boundaries, ed. K.E. Gray (Plenum Press, New York, 1981).
- [13] D.A. Bonn, private communication.
- [14] W.W. Warren et al., Phys. Rev. Lett. 62, 1193 (1989).
- [15] S.M. Quinlan et al., Phys. Rev. B. 49, 1470 (1994).
- [16] M.B. Walker and M.F. Smith, Phys. Rev. B. 61, 11285 (2000).
- [17] B.J. Feenstra et al., Phys. Rev. Lett. 79, 4890 (1997).
- [18] A. Hosseini et al., Phys. Rev. B. 60, 1349 (1999).