## Magnetic Field Effects in the Pseudogap Phase: A Precursor Superconductivity Scenario

Andrew P. Iyengar, Ying-Jer Kao, Qijin Chen, K. Levin

## Abstract

We demonstrate that the observed dependences of  $T_c$  and  $T^*$  on small magnetic fields can be readily understood in a precursor superconductivity approach to the pseudogap phase. In this approach, the presence of a pseudogap at  $T_c$  (but not at  $T^*$ ) and the associated suppression of the density of states lead to very different sensitivities to pair-breaking perturbations for the two temperatures. Our semi-quantitative results address the puzzling experimental observation that the coherence length  $\xi$  is weakly dependent on hole concentration x throughout most of the phase diagram. We present our results in a form which can be compared with the recent experiments of Shibauchi et al, and argue that orbital effects contribute in an important way to the H dependence of  $T^*$ .

Key words: superconductivity, pseudogap, magnetic fields

In the pseudogap phase, there are pronounced differences between the behavior of the pseudogap onset temperature  $T^*$  and the superconducting transition temperature  $T_c$  with respect to magnetic fields. In the underdoped regime,  $T_c$  is far more field sensitive than is  $T^*$ , and it has been argued that this lends support for the notion that the pseudogap is unrelated to the superconductivity. Contrary to this inference, we demonstrate here that these field dependences can be readily explained as a direct consequence of the pseudogap in a precursor superconductivity approach. In this approach, the presence of a pseudogap at  $T_c$  (but not at  $T^*$ ) and the associated suppression of the density of states lead to very different sensitivities to pair-breaking perturbations for the two temperatures. Another effect of the pseudogap is that the coherence length  $\xi$  does not necessarily coincide with other length scales in the system, as occurs in BCS theory. In this paper, we illustrate these pseudogap effects at

\*

 $T_c$  from the standpoint of Landau-Ginsberg theory and give a comparison of semi-quantitative results with recent experiments.

The various approaches to understanding the pseudogap phase of the high temperature superconductors seem to be divided roughly into two schools: those in which the pseudogap is associated with a competing energy gap (or hidden order parameter[17]) and those in which the pseudogap derives from the superconductivity itself. This latter "precursor superconductivity" school has multiple interpretations as well. The phase fluctuation[3] and the spincharge separation schools [28] are to be distinguished from the present scheme in which the pseudogap arises in a mean-field generalization of BCS theory that allows the consideration of a strong pairing attraction. In contrast, the phase fluctuation school builds on strict BCS theory, but adds fluctuation effects which we neglect here. Our approach is often referred to as a BCS-Bose Einstein crossover scenario, since a sufficiently strong attractive interaction allows pairs to form at a temperature  $T^*$  which is higher than the  $T_c$  at which they Bose condense. In the present paper, we use a formalism for treating the BCS-BEC crossover which we have extensively discussed and developed previously[16,13,14].

A fundamental feature of the crossover scenario is that increasing the attractive coupling strength g introduces bosonic as well as fermionic excitations. The presence of nonzero-momentum bosonic pair excitations is responsible for both the pseudogap that develops for temperatures  $T_c < T < T^*$  as well as for the fact that below  $T_c$ , the excitation gap  $\Delta$  is distinct from the superconducting order parameter  $\Delta_{sc}$ . The dispersion relation for fermions below  $T_c$  has the BCS form with the full excitation gap  $\Delta$  given by

$$\Delta^2 = \Delta_{sc}^2 + \Delta_{pq}^2 \tag{1}$$

We will not give the self-consistency condition on  $\Delta_{pg}(T)$  here. Notably,  $\Delta_{pg}$  vanishes at zero temperature (yielding  $\Delta = \Delta_{sc}$ ) due to the total Bose condensation of all pairs. From this point of view, BCS theory is a weak coupling limit in which there are no non-zero-momentum pair excitations and consequently  $T^*$  coincides with  $T_c$  and  $\Delta = \Delta_{sc}$  at all temperatures below  $T_c$ .

We associate over- and under- doping with small and large normalized coupling constants, respectively. In all our calculations the coupling g enters in a dimensionless ratio with the bandwidth. It is presumed that as the Mott insulator is approached, the characteristic electronic energy scales decrease—so that even if g is relatively x-independent, its effectiveness increases with underdoping. The existence of a pseudogap above  $T_c$  which develops as the coupling is increased differentiates the physics of the underdoped cuprates from that of the overdoped (BCS) state.

We characterize the field sensitivity of  $T_c$  through the coherence length  $\xi$  defined by

$$-\frac{1}{T_c} \frac{dT_c}{dH} \bigg|_{H=0} = \frac{2\pi}{\Phi_0} \xi^2$$
 (2)

Similarly, we define a length scale  $\xi^*$  for  $T^*$ . In the case of  $T_c$ , where there is a true phase transition, we consider the free energy density of a linearized Landau-Ginsberg theory near  $T_c$ :

$$F = \left[ -\tau \left( 1 - \frac{T}{T_c} \right) + \eta^2 (-i\nabla - 2\frac{e}{c}A)^2 \right] |\Delta_{sc}|^2$$
 (3)

The stiffness of the superconducting order parameter with respect to spatial variations is characterized by  $\eta^2$ , whereas  $\tau$  essentially measures the density of states at the Fermi surface. As in BCS theory,  $\xi^2 = \eta^2/\tau$ , although we must now consider the effect of the pseudogap on  $\eta^2$  and  $\tau$ . In our formalism, the calculation of the (coupling dependent) parameters  $\eta^2$  and  $\tau$  is based on the application of the semi-classical phase approximation to evaluate the pairing susceptibility in a small magnetic field H [25]; the details are given in [1]. Although there is no phase transition at  $T^*$ , the pairing susceptibility provides natural analogs  $\eta^{*2}$ ,  $\tau^*$  with  $\xi^{*2} = \eta^{*2}/\tau^*$ . In BCS theory,  $\tau$  merely cancels the density of states appearing in  $\eta^2$ , resulting in a coherence length  $\xi = C \cdot v_F/T_c$ , where C is a universal constant [2]. In the pseudogap phase, this cancellation no longer occurs, and  $\tau$  plays a more interesting role in determining  $\xi$ . In general, we find that  $\xi$  is different from  $C \cdot v_F/T_c$ .

The doping dependence of  $\xi$  and  $\xi^*$  can be understood first from the fact that the spatial stiffness  $\eta^2$  (as well as  $\eta^{*2}$ ) decreases with underdoping because the stonger pairing interaction reduces the pair size [26]. Second,  $\tau$  and  $\tau^*$  measure the density of states at the Fermi energy at the respective temperatures. The pseudogap present at  $T_c$  (but not  $T^*$ ) suppresses the density of states, causing  $\tau$  to decrease rapidly with underdoping relative to  $\tau^*$ . There is no analogous suppression of  $\eta$  relative to  $\eta^*$ , allowing  $\xi$  to differ from  $\xi^*$  in the pseudogap phase. We find that  $\xi^*$  decreases with underdoping, while the competition between the spatial stiffness and the density of states at  $T_c$  results in a broad doping range over which  $\xi$  is relatively constant, with a dramatic increase in  $\xi$  as the superconductor-insulator boundary is approached. Quantitative results for the behavior of  $\xi$ ,  $\xi^*$  as functions of hole concentration x are given elsewhere [1].

In this paper we concentrate on an alternative representation of these calculations, defining characteristic magnetic fields  $H_{sc} = \Phi_0/2\pi\xi^2$  and  $H_{pg} = \Phi_0/2\pi\xi^{*2}$ . By assuming straight-line extrapolations on the H-T phase diagram, we may interpret these as the fields required at zero temperature to




Fig. 1. Magnetic fields required at T=0 to destroy superconductivity  $(H_{sc} \text{ or } H_{c2})$  and the pseudogap  $(H_{pg})$  as extrapolated from (left) a calculation of  $\xi$ ,  $\xi^*$  and (right) experiment [29], plotted vs. hole concentration. Insets plot  $H_{pg}$  vs.  $T^*$ .

destroy superconductivity and close the pseudogap, respectively. This allows us to compare with the recent study of BSSCO 2212 by Shibauchi et al [29]. Figure 1 demonstrates that our calculation (left) captures the convergence of  $H_{pq}$  and  $H_{sc}$  in the overdoped region as well as the divergence of these fields on the underdoped side as a consequence of the opening of the pseudogap at  $T_c$ . The figure indicates that on the overdoped side,  $T_c$  and  $T^*$  are both sensitive to magnetic fields, whereas  $T^*$  is far less field sensitive than  $T_c$  on the underdoped side. We plot  $H_{pq}$  versus  $T^*$  (left, inset,) and in this way we can compare the apparent "Zeeman scaling" reported by Shibauchi et al[29]  $(g\mu_0H_{pq}=k_BT^*)$  with our calculations, which include only orbital magnetic effects. (One might expect that as the temperature is lowered, and because the appropriate critical fields become stronger, Zeeman coupling effects will also need to be ultimately incorporated into a more complete theoretical treatment). However, in the doping region corresponding to the three data points shown, there is reasonable agreement between the two insets. More experimental data points at lower  $T^*$  will ultimately be needed to determine the relative importance of orbital and Zeeman coupling in the magnetic field related pseudogap energy scales.

In conclusion, we have demonstrated that a precursor pairing scenario is associated with very different magnetic field sensitivities for  $T^*$  and  $T_c$ . This observation is contrary to the widely held belief that if the pseudogap is associated with superconducting pairing, then  $T^*$  and  $T_c$  should be similarly dependent on the magnetic field strength. Here we associate the different H dependences with the fact that a pseudogap is present at  $T_c$  and absent at  $T^*$ . The former observation leads to a modification of the Landau Ginsberg coefficients from their BCS counterparts. Moreover, the calculated field dependences of the two different energy scales ( $T^*$  and  $T_c$ ) appear to be in reasonable accord with experimental data.

## References

- [1] Y. J. Kao, A. P. Iyengar, Q. J. Chen, K. Levin, condmat/0103614 (2001).
- [2]  $\xi_{BCS}^2 = 7\zeta(3)/48\pi^2(v_F/T_c)^2$  in 3D and  $7\zeta(3)/32\pi^2(v_F/T_c)^2$  in 2D.
- [3] V. J. Emery, S. A. Kivelson, Nature **374**, 434 (1995).
- [4] J. L. Tallon and J. W. Loram, Physica C **349**, 53 (2001).
- [5] V. M. Krasnov et al., Phys. Rev. Lett. 84, 5860 (2000).
- [6] C. Renner *et al.*, Phys. Rev. Lett. **80**, 3606 (1998).
- [7] K. Gorny et al., Phys. Rev. Lett. 82, 177 (1999).
- [8] G. Zheng et al., Phys. Rev. Lett. 85, 405 (2000).
- [9] V. M. Krasnov, A. E. Kovalev, A. Yurgens, and D. Winkler, Phys. Rev. Lett. 86, 2657 (2001).
- [10] P. Nozières and S. Schmitt-Rink, J. Low Temp. Phys. **59**, 195 (1985).
- [11] Randeria, Physica B 198, 373 (1994).
- [12] I. Kosztin, Q. J. Chen, B. Janko, and K. Levin, Phys. Rev. B 58, R5936 (1998).
- [13] Q. J. Chen, I. Kosztin, B. Janko, and K. Levin, Phys. Rev. Lett. 81, 4708 (1998).
- [14] Q. J. Chen, I. Kosztin, and K. Levin, Phys. Rev. Lett. 85, 2801 (2000).
- [15] J. Maly, B. Janko, and K. Levin, Phys. Rev. B **59**, 1354 (1999).
- [16] Q. J. Chen, I. Kosztin, B. Janko, and K. Levin, Phys. Rev. B 59, 7083 (1999).
- [17] S. Chakravarty, R. B. Laughlin, D. K. Morr, and C. Nayak, Phys. Rev. B 63, 094503 (2001).
- [18] J. W. Loram et al., J. Supercond. 7, 243 (1994).
- [19] A. S. Alexandrov, W. H. Beere, V. V. Kabanov, and W. Y. Liang, Phys. Rev. Lett. 79, 1551 (1997); M. R. Schafroth, Phys. Rev. 100, 463 (1955).
- [20] L. P. Kadanoff and P. C. Martin, Phys. Rev. **124**, 670 (1961).
- [21] A. J. Leggett, in *Modern Trends in the Theory of Condensed Matter* (Springer-Verlag, Berlin, 1980), pp. 13–27.
- [22] B. Janko, J. Maly, and K. Levin, Phys. Rev. B 56, R11407 (1997).
- [23] J. Maly, B. Jankó, and K. Levin, Physica C 321, 113 (1999).
- [24] E. Helfand and N. R. Werthamer, Phys. Rev. 147, 288 (1966).
- [25] P. A. Lee and M. G. Payne, Phys. Rev. B 5, 923 (1972).

- [26] Y. Yanase and K. Yamada, J. Phys. Soc. Jap. 69, 2209 (2000).
- [27] H. H. Wen, X. H. Chen, W. L. Yang, and Z. X. Zhao, Phys. Rev. Lett. 85, 2805 (2000).
- [28] P. A. Lee and X.-G. Wen, Phys. Rev. Lett. 78, 4111 (1997).
- [29] T. Shibauchi et al., Phys. Rev. Lett. 86, 5763 (2001).