G apless M agnetic and Q uasi-particles Excitations due to the C oexistence of A ntiferrom agnetism and Superconductivity in C eR hIn₅: ¹¹⁵In-N Q R Study under P ressure

S.K awasaki¹, T.M ito^{1;}, Y.K awasaki^{1;}, G.-q.Zheng¹, Y.K itaoka¹, D.A oki^{2;}, Y.Haga³, and Y.O nuki^{2;3} ¹D epartment of Physical Science, G raduate School of Engineering Science, O saka University, Toyonaka, O saka 560-8531,

Japan

²D epartm ent of P hysics, G raduate School of Science, O saka U niversity, Toyonaka, O saka 560-0043, Japan

³Advanced Science Research Center, Japan Atom ic Energy Research Institute, Tokai, Ibaraki 319–1195, Japan

(M ay 22, 2019)

We report system atic measurements of ac-susceptibility, nuclear-quadrupole-resonance (NQR) spectrum, and spin-lattice-relaxation time (T_1) on the pressure (P)-induced heavy-fermion (HF) superconductor CeRhIn₅. The tem perature (T) dependence of 1=T₁ at P = 1.6 GPa has revealed that antiferrom agnetism (AFM) and superconductivity (SC) coexist microscopically, exhibiting the respective transition at $T_N = 2.8$ K and T_c (M F) = 0.9 K. It is demonstrated that SC does not yield any trace of gap opening in low-lying excitations below the onset tem perature T_c (onset) = 2 K, but T_c (M F) = 0.9 K, followed by a $T_1T = const$. law in low T regime. These results point to the unconventional characteristics of SC coexisting with AFM. We highlight that both of the results deserve theoretical work on the gapless nature in low-lying excitation spectrum due to the coexistence of AFM and SC and the lack of the mean- eld regime below T_c (on set) = 2 K.

PACS: 74.25 Ha, 74.62 Fj, 74.70.Tx, 75.30 Kz, 76.60 Gv

In recent years, an intim ate interplay between antiferrom agnetism (AFM) and superconductivity (SC) has been the most interesting and outstanding issue in cerium (Ce)-based heavy-ferm ion (HF) system s. It is believed that the SC in $CeCu_2Si_2$ [1], $CeIrIn_5$ [2], and $CeCoIn_5$ [3] emerges at the border of AFM even at P = 0. The nding of P-induced SC in CeCu₂Ge₂ [4], CeIn₃, CePd₂Si₂ [5,6] and CeRhIn₅ [7] strongly suggest that AFM and SC are related to each other because P -induced SC occurs either when AFM vanishes or coexists with it [8]. Am ong them, the study on the cubic $C \in In_3$ and the quasitwo dim ensional tetragonal C eR h In₅ is prom ising for system atic investigation of an intim ate interplay between AFM and SC.A new HF antiferrom agnetic compound CeRhIn₅ consisting of alternating layers of CeIn₃ and RhIn₂ revealed an antiferrom agnetic to superconducting transition at a relatively low ercritical pressure $P_c = 1.63$ GPa and higher $T_c = 22$ K than in previous examples. [4,5,6,7]

At P = 0, a previous NQR study below the N eel temperature $T_N = 3.8$ K indicated the rapid development of an internal eld H_{int} induced by the Ce spontaneousmoments that has an incommensurate wave vector $q_M = (1=2;1=2;0.297)$ [9]. A neutron experiment revealed the reduced Cemagnetic moments $M_s = 0.8_B$ in the antiferrom agnetic ordered state [10,11]. Our previous NQR study showed that T_N gradually increases up to 4 K as P increases up to P = 1.0 GPa and decreases with further increasing P [8,12,13] (see Fig.1). In addition, the temperature (T) dependence of nuclear-spin

-lattice-relaxation rate 1=T1 has probed pseudogap behavior at P = 1.23 and 1.6 GPa [13]. This suggests that CeRhIn₅ m ay resemble other strongly correlated electron system s [14,15]. At P = 2:1 G P a beyond P_c , 1=T₁ reveals a T³ dependence below T_c, consistent with the existence of line-node gap below T_c [12,16]. This was also corroborated by the speci c-heat m easurem ent under P [17]. M ost remarkably, at P = 1.75 GPa, the onset of AFM is evidenced from a clear split in ¹¹⁵In-NQR spectrum due to the spontaneous internal eld below $T_N = 2.5$ K.Simultaneously, bulk SC below $T_c = 2.0$ K is demonstrated by the observation of the M eissner diam agnetism signal whose size is the same as in the exclusively superconducting phase. These results have dem onstrated that AFM coexists hom ogeneously with the SC at a microscopic level at the border where both SC and AFM meet one another [8].

In this letter, we report system atic measurements of ac-susceptibility (ac-) in P = 1.12 - 2.0 GPa and focus on novel superconducting characteristics in the coexistent state of AFM and SC for CeRhIn₅ at P = 1.6 GPa.

Single crystal of CeRhIn₅ was grown by the self- ux m ethod, and wasm oderately crushed into grains in order to m ake rfpulses penetrate into sam ples easily. CeRhIn₅ consists of alternating layers of CeIn₃ and RhIn₂ and hence has two inequivalent In sites per unit cell. The ¹¹⁵In-NQR m easurem ents were m ade at the In(1) site [8,9,12,13] which is located on the top and bottom faces of the tetragonal unit cell. The NQR spectrum was obtained by plotting the intensity of spin-echo signal as a

function of frequency. The high-frequency ac- was carried out by measuring the inductance of an in situ NQR coil with the frequency 2:5 M H z that is not far from the NQR frequency o 6.5 MHz. Note that the skin depth for the NQR and ac- measurements is comparable to a size of grains (0.1mm) and the magnetic penetration depth is estimated to be typically an order of 5000–7000 A for the superconducting CeT In₅ (T = Ir, Co) [18]. So, the present ac- measurement is compatible to the dc- one in detecting a bulk SC. Measurem ent of $1=T_1$ was made by the conventional saturationrecovery m ethod. The 115 In-NQR 1=T₁ was measured at the transition of 2 $_{\circ}$ (3=2 \$ 5=2) above T = 1.4 K, but at 1 $_{\circ}$ (1=2 \$ 3=2) below T = 1.4 K. The hydrostatic pressure was applied by utilizing BeCu pistoncylinder cell, lled with Daphne oil (7373) as a pressuretransmitting medium. For our pressure cells, an extent of the spatially distribution in values of pressure P = P is estimated to be 3% from a broadening in the linewidth in NQR spectrum.

Fig. 1 indicates a rich P T phase diagram of CeR hIn₅ near the quantum criticality referred from the previous report [8]. The SC seem s to survive under AFM near the m agnetic criticality of CeR hIn₅. Note that the present m easurem ent of ac- unravels progressive reduction in the value of T_c as shown by closed circle.

Figs. 2a and 2b indicate the respective T dependencies of ac- 's and their T derivatives in P = 1.12 - 2.0 GPa. The ac- at P = 1.12 GPa is unchanged down to 0.05 K at allw it hout any trace for SC . As P increases up to a range P = 1.53 - 2.0 GPa, bulk SC is demonstrated by the observation of the M eissner diam agnetism signal whose size is the same as in the exclusively superconducting phase. Thus, the SC in CeRhIn₅ emerges at pressures exceeding P_c (SC) 15 GPa as seen in Fig.1. This is also in good agreem ent with the speci c-heat result under P that suggests Pc (SC) 1:5 GPa as a critical pressure at which bulk SC sets in [17]. As seen in Fig. 2a, it should be noted that the volume fraction of diam agnetism is alm ost unchanged over the measured P range, but the transition width for SC becomes signi cantly broader as P decreases. A similar behavior is also seen in the P dependence of resistivity over the same P range. A 1though zero resistance is observed at T_c (zero), the decrease in resistance towards T_c (zero) becom es broadest at P = 1:63 GPa (see Fig.5b) [7]. This is indicative of novel superconducting characteristics inherent to the microscopic coexisting state of AFM and SC at pressures lower than P = 1.9 GPa. As seen in Fig.2a, T_c (on set) is de ned as a tem perature below which diam agnetism starts to appearC whereas a peak of T derivative of acas T_c (MF) as seen in Fig 2b.

Next we present microscopic evidence for novel superconducting characteristics at the coexisting state of AFM and SC in CeRhIn₅ at P = 1.6 GPa. The inset of Fig.3 displays NQR spectrum above and below $T_{\rm N}$ at P = 1:6 GPa. Below $T_{\rm N}$ = 2:8 K, the NQR spectrum splits into two peaks due to the appearance of H $_{\rm int}$ at the In site. This is clear evidence for the occurrence of AFM at P = 1.6 GPa as well as reported in the previous result at P = 1:75 GPa [8]. The plots of H $_{\rm int}$ (T)=H $_{\rm int}$ (4.2) = M $_{\rm s}$ (T)=M $_{\rm s}$ (4.2) vs (T=T_N) at P = 0 and 1.6 GPa are compared in Fig.3, showing nearly the same behavior. Here H $_{\rm int}$ (4.2) is the value at T = 4.2 K and M $_{\rm s}$ (T) is the T dependence of spontaneous staggered magnetic moment. The character of AFM at P = 1:6 GPa is expected to be not so much di erent from that at P = 0.

Fig. 4 indicates the T dependence of $1=T_1$ at P=1.6 GPa. A clear peak in $1=T_1$ is due to critical magnetic uctuations at $T_N=2.8~{\rm K}$. Below $T_N=2.8~{\rm K}$, $1=T_1$ continues to decrease moderately down to $T_c~{\rm (M}~{\rm F}$) = 0.9 K even though passing across $T_c~{\rm (onset)}$ $2~{\rm K}$. This relaxation behavior suggests that the SC does not develop follow ing the mean-eld approximation below $T_c~{\rm (onset)}$. M ost remarkably, $1=T_1$ decreases below $T_c~{\rm (M}~{\rm F}$), exhibiting a faint T 3 behavior in a narrow T range. W ith further decreasing T , $1=T_1$ becomes proportional to the temperature, indicative of a gapless nature in low -lying excitation spectrum in the microscopically coexisting state of SC and AFM . Thus the T_1 measurem ent unravels that an intim ate interplay between AFM and SC emerges between $T_c~{\rm (onset)}$ and $T_c~{\rm (M}~{\rm F}$), giving rise to some amplitude

uctuations of superconducting order parameter. Such uctuations may be responsible for the broad transition in resistance and ac- measurements. Furthermore, the $T_1T = \text{const.}$ behavior well below $T_c M F$) evidences the gapless nature in the coexisting state of AFM and SC. This result is consistent with those in $C \in C u_2 S i_2$ at the border of AFM [19] and a series of $C \in Cu_2$ (Si₁ x $G \in L_2$)₂ compounds that show the coexistence of AFM and SC [20,21]. The speci c-heat result, that probed a nite value of its T-linear contribution, $_0$ 100m J/m oK² at P = 1.65 G Pa, is now understood due not to a rst-order like transition to SC [17], but to the gap less nature in the coexisting state of AFM and SC. It is noteworthy that such the $T_1T = const.$ behavior is not observed below T_c at P = 2:1 G Pa [12], consistent with the speci c-heat result under P as well [17]. This novel feature di ers from the uranium (U)-based HF-antiferrom agnetic superconductor UPd₂A b that exhibits a superconducting transition at $T_c = 1.8$ K wellbelow $T_N = 14.3$ K [22,23]. In UPd_2Ab_1 , it is suggested that two of 5f electrons, that possess a localized character, are responsible for AFM, whereas the rem aining 5f electrons, which are hybridized with conduction electrons and become heavy, are responsible for SC. The 27 A HNQR-T₁ results in UPd₂A b are indicated in the inset of Fig.4 [24]. $1=T_1$ decreases obeying a T^3 law over three orders of magnitude below the onset of T_c without any trace for $1=T_1T = const.$ behavior. This is consistent with the line-node gap in the coexisting state of AFM and SC below T_c .

In order to highlight the novel superconducting nature in a microscopic level, the T dependence of $1=T_1T$ is shown in Fig.5a at P = 1.6 GPa in T = 0.05 - 6 K and is compared with the T dependence of the resistance R(T) at P = 1.63 GPa referred from the literature [7]. A lthough each value of pressure is not exactly the sam e, they only di erby 3%. W erem ark that the T dependence of $1=T_1T$ points to the pseudogap behavior around $T_{PG} =$ 4.2 K, the AFM at $T_N = 2.8$ K, and the SC at T_c (M F) = 0.9 K at which the T derivative of ac- has a peak as seen in Fig.5b. This result itself evidences the microscopic coexistent state of AFM and SC.A comparison of $1=T_1T$ with the R (T) at P = 1.63 GPa in Fig.5b is informative in shedding light on the uniqueness of superconducting and m agnetic characteristics. Below $T_{P\,G}$, R (T) starts to decrease m ore rapidly than a T-linear variation extrapolated from high T side. It continues to decrease across $T_{\rm N} = 2.8 \,\text{K}$, reaching zero resistance at $T_{\rm c}$ (zero) 1.5K. The resistive transition width for SC becomes broader. Unexpectedly, T_c (on set) 2 K, that is de ned as the tem perature below which the diam agnetism starts to appear, is higher than T_c (zero) 1.5 K. Any signature for the onset of SC from the $1=T_1$ measurement is not evident in between T_c (onset) and T_c (M F), demonstrating that the mean-eld type of gap does not grow up down to $T_c (M F) = 0.9 K$. The existence of uctuations due to the interplay of AFM and SC is responsible for the broad transition towards SC that coexists with AFM .

Finally, we remark that recent neutron-di raction experim ent suggests alm ost the P independent size of staggered m om ent M $_{\rm s}$ in the antiferrom agnetic ordered state [11], in contrast to the large P dependence of H $_{\rm int}$ as seen in Fig.1. Its relatively large size of m om ent with $0:8_{\rm B}$ seems to support such a picture that the Мs sam e f-electron exhibits simultaneously itinerant and localized dual nature because there is only one 4f-electron per Ce^{3+} ion. In this context, it is natural to consider that the superconducting nature in the coexisting state of AFM and SC belongs to a novel class of phase which di ers from the conventional d-wave SC with the linenode gap. As a matter of fact, a theoretical model has been recently put forth to address the underlying issue in the coexistent state of AFM and SC [25].

In conclusion, we have reported the m icroscopic coexistence of AFM and SC from the system atic measurements of the T dependencies of $1=T_1$ and the internal eld for C eRhIn₅ at P = 1.6 GPa. A loo, the coexistent state is suggested to persist down to P 1.5 GPa at least from the measurement of ac-. The detailed measurement of $1=T_1$ has revealed that SC does not yield any trace of gap opening in low -lying excitations below the onset temperature T_c (onset) = 2 K, but T_c (M F) = 0.9 K, followed by the $1=T_1T$ = const. law in low T regime. These results di er from any previous examples, pointing to the unconventional characteristics of SC coexisting with AFM. W e highlight that both of the results deserve theoretical

work on the gapless nature in low -lying excitation spectrum due to the coexistence of AFM and SC and the lack of the mean-eld regime below T_c (on set) = 2 K.

O ne of authors (SK.) thanks K. Ishida and H.Kotegawa for useful discussions and experimental helps. This work was supported by the COE Research grant (10CE2004) of G rant-in-A id for Scienti c Research from the M inistry of Education, Culture, Sports, Science and Technology of Japan.

* Present address: Department of Physics, Faculty of Science, Kobe University, Nada, Kobe 657-8501, Japan ** Present address: Department of Physics, Faculty of Engineering, Tokushim a University, Tokushim a 770-8506, Japan *** Present address: CEA, Department de Recherche Fondamentale sur la Matiere Condensee, SP SM S, 38054 Grenoble Cedex 9, France

- [1] F.Steglich et al., Phys.Rev.Lett. 43, 1892 (1979).
- [2] C.Petrovic et al, Europhys. Lett. 53, 354-359 (2001)
- [3] C. Petrovic et al., J. Phys.: Condens. M atter 13, L337 (2001)
- [4] D. Jaccard, K. Behnia, and J. Sierro, Phys. Lett. A 163, 475 (1992).
- [5] N.D.M athur et al., Nature 394, 39 (1998).
- [6] F.M. Grosche et al., J. Phys. Condens. M atter 13, 2845 (2001).
- [7] H.Hegger et al, Phys. Rev. Lett. 84, 4986 (2000).
- [8] T.M ito et al, Phys. Rev. Lett. 90, 077004 (2003).
- [9] N.J.Cumo et al, Phys. Rev. B 62, R6100 (2001).
- [10] A.D.Christianson et al, Phys. Rev. B 66, 193102 (2002).
- [11] W eiBao et al., unpublished.
- [12] T.M ito et al, Phys. Rev. B. 63, 220507 (R) (2001).
- [13] S.Kawasakietal, Phys.Rev.B 65, 020504(R) (2002).
- [14] For review see, T. Timusk and B. Statt, Rep. Prg. Phys 62, 61 (1999).
- [15] K.Kanoda, Physica (Am sterdam) 282-287C, 299 (1997).
- [16] Y.Kohorietal, Eur.Phys.J.B 18, 601-604 (2000).
- [17] R A . Fisher et al, Phys. Rev. B 65, 224509-1 (2002).
- [18] W .Higem oto et al, J.Phys. Soc. Jpn 71, 1024 (2002).
- [19] Y.Kawasakietal, Phys.Rev.B 63, 140501(R) (2001).
- [20] Y. Kitaoka et al, J. Phys. Condense. Matter 13, L79 (2001).
- [21] Y.Kawasakietal, Phys.Rev.B 66, 224502 (2002).
- [22] C.Geibelet al., Z Phys. B 83, 305 (1991).
- [23] F.Steglich et al., Proc. Physical Phenom ena at High M agnetic Fields-II (eds Z.Fisk, L.Gor'kov, D.M eltzer, and R.Schrie er) 125 (W orld Scienti c, Singapore, 1996).
- [24] H. Tou et al, J. Phys. Soc. Jpn. 64, 725 (1995).
- [25] Y.Fuseya, H.Kohno and K.M iyake, cond-m att/0302532

(2003).

FIG.1. The pressure (P)-tem perature (T) phase diagram for C eR hIn₅. The respective m arks denoted by square, triangle and cross correspond to the pseudogap tem perature $T_{P~G}$, the antiferrom agnetic ordering tem perature T_N and the internal eld H_{int} at the In site. The closed and open circles are the superconducting transition tem perature determined by the measurem ents of ac-[8,12,13] and resistance [7]. D otted line points a value of P = 1:6 GPa.

FIG.2. (a) The T dependencies of ac- and (b) the T derivatives of ac- at P = 1:12 2:0 GPa. A rrows indicate $T_{\rm c}$ (M F) (see text).

FIG.3. Plots of H $_{\rm int}$ (T)=H $_{\rm int}$ (4.2) vs T=T_N at P = 0 and 1.6 GPa. Here H $_{\rm int}$ (4.2) is the value of internal eld H $_{\rm int}$ at T = 4.2 K.N ote that H $_{\rm int}$ is proportional to the staggered m agnetic m om ent in the antiferrom agentically ordered state. Inset show sthe 115 In-NQR spectra of1 $_{\rm Q}$ (1=2 3=2 transition for I = 9/2) at P = 1.6 GPa above and below $T_{\rm N}$ = 2.8 K.

FIG.4. The T dependence of $1=T_1$ at P = 1.6 GPa.Both dotted lines correspond to $1=T_1 / T$ and $1=T_1 / T^3$. Inset indicates the T dependence of ${}^{27}A + N QR$ $1=T_1$ of UPd₂A l_8 cited from the literature [24]. Dotted line corresponds to $1=T_1 / T^3$.

FIG.5. (a) The T dependence of $1=T_1T$ at P = 1.6 GPa. (b) The T dependencies of T derivative of ac- (d =dT) at P = 1.6 GPa and resistance at P = 1.63 GPa cited from the literature [7]. T_c (M F) and T_c^{onset} correspond to the respective temperatures at which d =dT has a peak and below which ac- starts to decrease. T_N corresponds to the antiferrom agnetic ordering temperature at which $1=T_1T$ exhibits a peak and to the pseudogap temperature below which it starts to decrease. A solid line is an eye guide for the T-linear variation in resistance at temperatures higher than T_{PG} .









