Surface pinning of fluctuating charge order: an "extraordinary" surface phase transition.

Stuart E. Brown,¹ Eduardo Fradkin,² and Steven A. Kivelson^{3, 1}

¹Department of Physics and Astronomy, UCLA, Los Angeles, CA 90095-1547

²Department of Physics, University of Illinois, 1110 W. Green St., Urbana, Illinois 61801-3080, USA

³Department of Physics and Astronomy, Stanford University, Stanford CA 94305

(Dated: May 18, 2018)

We study the mean-field theory of charge-density wave (CDW) order in a layered system, including the effect of the long-range Coulomb interaction and of screening by uncondensed electrons. We particularly focus on the conditions necessary for an "extraordinary" transition, in which the surface orders at a higher temperature, and is more likely to be commensurate, than the bulk. We interpret recent experiments on $Ca_{2-x}Na_xCuO_2Cl_2$ as indicating the presence of commensurate CDW at the surface that is *not* present in the bulk. More generally, we show that poor screening of the Coulomb interaction tends to stabilize incommensurate order, possibly explaining why the CDW order in $La_{2-x}Sr_xCuO_4$ and NbSe₂ remains incommensurate to $T \to 0$, despite the small magnitude of the incommensurability.

PACS numbers:

With the advent of high resolution angle resolved photoemission (ARPES) and scanning tunneling spectroscopy (STS), there is increasing interest in looking for evidence of novel order or incipient order in strongly correlated electron systems by studying the electronic structure of the surface layer – some of the most interesting recent evidence that charge order plays a critical role in the physics of the cuprate high temperature superconductors (HTC) comes from such studies^{1,2,3,4}. A persistent question about such studies arises, "Is the surface electronic structure the same as the bulk?"

In the present note, we outline some of the possibilities for transitions to ordered states at the surface of a bulk system, where the surface order reflects, but in somewhat subtle and indirect ways, the character of the bulk. In particular, we argue that the "commensurate checkerboard order" recently discovered⁴ in $Ca_{2-x}Na_xCuO_2Cl_2$ (NaCCOC) is very likely *not* directly representative of charge order in the bulk of the sample. However, we describe suggestive, but not conclusive reasons to believe that this surface order *is* a pinned relative of fluctuating charge order in the bulk - probably related to the fluctuating charge stripe order seen in bulk measurements on $La_{2-x}Sr_{x}CuO_{4}(LSCO)$. This work extends earlier investigations by two of us⁵ of general strategies for observing correlations - "fluctuating order" - which reflect the proximity in a generalized phase diagram of a true ordered state.

When a bulk system undergoes a phase transition to a broken symmetry state, such as a charge-density wave (CDW) state, the surface of the system must reflect the broken symmetry, as well. However, one might expect order to be weaker at the surface. Nonetheless, there are known cases of *surface phase transitions* in which an "extraordinary transition" occurs⁶, *i.e.* a phase transition in which the surface orders at a higher temperature than the bulk.

In the present paper, we consider the case of a CDW

in a layered (quasi 2D) material with a smooth surface obtained by cleaving between two layers, for which:

1) We analyze the circumstances under which an extraordinary surface phase transition can occur. We show that if the couplings within each layer, including the surface layer, are identical, the surface is unlikely to order before the bulk. However, phonon modes associated with the motion of atoms transverse to the layers tend to be softer at the surface than in the bulk. If the coupling to such modes is sufficiently strong, an extraordinary surface phase transition occurs. An example of such a phonon mode is the apical O or Cl modes in LSCO and NaCCOC, respectively, which independent studies suggest are strongly coupled to the charge density in the Cu-O planes.

2) Under circumstances in which an anomalous transition occurs, one expects from simple Landau-Ginzburg considerations, the following hierarchy of transition temperatures: $T_{sI} \ge T_{sC}$ and $T_{sI} \ge T_I$, where T_{sI} , T_{sC} , and T_I are the transition temperatures at which surface incommensurate CDW order, surface commensurate CDW order, and bulk incommensurate order onsets, respectively. Moreover, as is generally the case, $T_I \ge T_C$, where T_C marks the bulk transition to a commensurate CDW. The extraordinary transition is particularly dramatic when T_C and even T_I are zero, *i.e.* when the bulk system is in a quantum disordered phase, but possibly with a commensurate CDW on the surface layer. This sequence of transitions is shown schematically in Fig. 1.

3) We interpret the STS experiments⁴ on NaCCOC as being indicative of a commensurate CDW phase on the surface (although the large effect of quenched disorder apparent in the STS images make this conclusion far from certain). We show that bulk measurements appear inconsistent with the existence of a commensurate CDW



FIG. 1: Schematic one-parameter cut of the phase diagram for a CDW system with a surface: r and r_0 measure the strength of the quadratic term in the McMillan free energy in the bulk and on the surface. The full and broken lines represent the bulk and surface phase transitions respectively: T_I and T_C are the bulk critical temperatures for the disordered-incommensurate and for the bulk incommensurate-commensurate phase transitions; T_{sI} and T_{sC} are the corresponding surface phase transitions. The extraordinary surface transitions for r_0/r are shown. SI: surface incommensurate CDW; SC: surface commensurate CDW. Other surface orderings (e.g. "ordinary" surface transitions) are possible but are not shown.

in the bulk. Thus, it is possible that either the order on the surface has no relation to the electronic properties of the bulk, or that there is an extraordinary surface phase transition which reflects the existence of bulk electronic correlations corresponding to a nearly ordered CDW in the bulk. By comparing the character of the observed surface order with modulations with similar periodicity (but rather different character) seen in STS studies of Bi₂Sr₂CaCu₂O_{8+ δ}(BSCCO) surfaces^{1,2,3}, and with stripe order and fluctuating order seen in bulk diffraction studies of LSCO and YBa₂Cu₃O_{6+y}(YBCO), we tentatively favor the latter interpretation.

4) In the course of this study, we have been forced to study the non-local Coulomb interaction. Under most circumstances – certainly, at any finite temperature or when the Fermi surface is incompletely gapped by the CDW – the Coulomb interactions between CDW fluctuations are screened, with a screening length ξ . While when ξ is small, the usual Landau-Ginzburg theory is recovered, we have found that poor screening (large ξ) substantially stabilizes the incommensurate CDW – it both tends to increase T_I and decrease T_C . It is possible that this explains the remarkable stability of the incommensurate phase in some systems, despite very small values of the incommensurability. For instance, the ordering wave vector in NbSe₂ is roughly 1% incommensurate, but there is apparently no transition to a commensurate state even in the limit $T \rightarrow 0$.

The paper is organized as follows. In Section I we introduce a Landau-Ginzburg theory of quasi-2D CDW order, including the effects of Coulomb interactions and screening on the bulk CDW phase transitions. In Section II we discuss the extraordinary surface phase transition. In Section III we discuss the role of surface phonons in the "mechanism." In Section IV we discuss the case of NaCCOC and other cuprates. Readers who are exclusively interested in the application of these ideas to the experimental system can skip directly to this section.

I. LANDAU-GINZBURG MODEL OF QUASI 2D CDW ORDER

To discuss these issues in the context of an explicit model, we consider the case of a CDW in a quasi 2D (layered) system with tetragonal symmetry⁷. We consider the case in which the local considerations in each plane favor density wave order with two, mutual orthogonal ordering vectors, \vec{Q}_1 and \vec{Q}_2 , $(|\vec{Q}_1| = |\vec{Q}_2|$ since they are related by rotation by $\pi/2$) which lie along a preferred symmetry axis of the crystal. We then express the theory in terms of two complex order parameter fields, $\psi_{1,n}$ and $\psi_{2,n}$, such that the local charge density $\rho_n(\vec{x})$ in plane *n* is

$$\rho_n(\vec{x}) = \rho_n^N(\vec{x}) + \sum_j \left[i\Lambda \ \psi_{j,n}^*(\vec{x}) \hat{Q}_j \cdot \vec{\nabla} \psi_{j,n}(\vec{x}) + \psi_{j,n}(\vec{x}) \ e^{i\vec{Q}_j \cdot \vec{x}} + \text{c.c.} \right]$$

+higher harmonics (1.1)

where ρ_n^N is the "normal" component of the charge density, *i.e.* the part which is not tied to the CDW, and $\hat{Q}_j = \vec{Q}_j / |\vec{Q}_j|$ are two unit vectors along the two CDW ordering directions. The terms represented as "higher harmonics" refer to components of the density at higher harmonics of the fundamental periods, $n_1\vec{Q}_1 + n_2\vec{Q}_2$ with $|n_1| + |n_2| > 1$; we will simply assume that these harmonics can be integrated out, and their effects captured by non-linear couplings to the fundamentals. The dimensionless parameter Λ reflects the change of the density which results from a compression of the CDW.

We are going to consider the case in which the CDW is commensurate or weakly incommensurate, and with the situation relevant to NaCCOC in mind, we have considered the case in which the CDW is near commensurability 4. In this case, it is convenient to take $4\vec{Q}_j = \vec{G}_j$ where \vec{G}_j is a reciprocal lattice vector. Hence, a uniform amplitude for the CDW order parameter $\psi = \text{const. cor-}$ responds to a *commensurate* CDW while $\psi \propto \exp[i\delta x]$ corresponds to an *incommensurate* CDW, where δ (which

will be derived by minimizing the effective Hamiltonian) is the "incommensurability." The case in which the CDW is far from being commensurate involves no new physics, so we will not discuss it explicitly.

In terms of the order parameters ψ_1 and ψ_2 , we can write a McMillan (Landau-Ginzburg) type effective free energy functional^{8,9,10} suitable for a CDW in a layered system (keeping lowest order terms in gradients and all terms allowed by symmetry through order ψ^4):

$$\begin{aligned} \mathcal{F} &= \sum_{n} \int d^{2}x \left\{ \mathcal{L}_{0} + \mathcal{L}_{1} + \mathcal{L}_{c} \right\} + \mathcal{F}_{coul} + F_{N} \\ \mathcal{L}_{0} &= \frac{1}{2} \sum_{j} \left\{ K | (i\hat{Q}_{j} \cdot \vec{\nabla} + \delta_{0})\psi_{j,n}(\vec{x})|^{2} \\ &+ K' |\hat{Q}_{j} \times \vec{\nabla}\psi_{j,n}(\vec{x})|^{2} + r |\psi_{j,n}(\vec{x})|^{2} \right\} \\ \mathcal{L}_{1} &= u(|\psi_{1,n}(\vec{x})|^{2} + |\psi_{2,n}(\vec{x})|^{2})^{2} + \gamma |\psi_{1,n}(\vec{x})|^{2} |\psi_{2,n}(\vec{x})|^{2} \\ \mathcal{L}_{c} &= V_{c} \sum_{j} \left\{ \psi_{j,n}(\vec{x})^{4} + c.c. \right\} \\ \mathcal{F}_{coul} &= \frac{e^{2}}{2\epsilon} \sum_{n,n'} \int d^{2}x \ d^{2}x' \frac{[\rho_{n}(\vec{x}) - \bar{\rho}][\rho_{n'}(\vec{x}\,') - \bar{\rho}]}{\sqrt{(\vec{x} - \vec{x}\,')^{2} + a^{2}(n - n')^{2}}} \end{aligned}$$
(1.2)

where n = 0, 1, ... labels the layers with n = 0 being the surface layer of a semi-infinite system; j = 1, 2 labels the two CDW order parameters. In Eq.(1.2), r, u and γ are phenomenological couplings which depend weakly on the temperature T. As usual, r changes from positive to negative with decreasing temperature, and so is the one parameter whose temperature dependence will be explicitly considered, $r = \alpha_0 (T - T_I^0)$. Moreover, near the surface, the various parameters could also depend on the layer index, n. For simplicity, we will assume that only the surface layer (n = 0) is distinct, and that the most important difference between the surface layer and the bulk is an additive correction to $r_0 = r + \delta r = \alpha_0 (T - T_{sI}^0)$, *i.e.* a distinct mean-field transition at the surface.

In Eq.(1.2) we have assumed that we can neglect all inter-plane interactions except the Coulomb coupling, $\mathcal{F}_{\text{coul}}$. In Eq.(1.2) $\bar{\rho}$ is a uniform background charge density, K and K' are the CDW stiffnesses, and a is the lattice spacing between planes. Here, the shear stiffness, K' will play little role in the present discussion. The sign of γ determines whether the ordered state is a unidirectional CDW, $\gamma > 0$, or an isotropic checkerboard, $\gamma < 0$. To simplify explicit expressions, we will assume that $|\gamma|$ is small, although so long as $\gamma > -2u$ (necessary for stability). No qualitative results depend on this assumption. Finally, \mathcal{L}_c is the lock-in potential which favors a (period 4) CDW, V_c is the strength of the commensurability, and e^2/ε is the strength of the Coulomb interaction.

We introduced a term in Eq.(1.2), F_N , which governs the fluctuations of the normal density; for our purposes, what is important is the preferred density, $\bar{\rho}^N$, and the small fluctuations about it (which lead to screening), so

we take

$$F_N = \sum_{n=0}^{\infty} \int d^2x \frac{\kappa_0}{2} [\rho_n^N(\vec{x}) - \bar{\rho}^N]^2$$
(1.3)

where κ_0 is the inverse compressibility of the normal fluid. Notice that the normal density and the CDW order parameters are coupled through the Coulomb interaction in the Landau-Ginzburg effective theory, as given by Eq.(1.1) and Eq.(1.2). Integrating out the fluctuations of the normal excitations, parametrized by $\rho_n^N(\vec{x})$, result in an effectively screened Coulomb interaction with a screening length $\xi = (4\pi e^2/\varepsilon\kappa_0)^{-1/2}$, and with the density expressed as in Eq.(1.1) with the replacement $\rho_n^N(\vec{r}) \to \bar{\rho}^N.$

Before we proceed further, it is worth commenting on the ways in with the present free energy differs from the usual Landau-Ginzburg treatment (obtained by taking the limit $\kappa_0 \to 0$ in the above), which does not treat the effects of the non-local Coulomb interactions. For $\kappa_0 = 0$, the incommensurability is determined directly by $\delta = \delta_0$, and so has no interesting temperature dependence that is not put in by hand, and the mean-field transition to the incommensurate state occurs just where r changes sign, $T_I = T_I^0$, or at the surface at $T_{sI} = T_{sI}^0$. For imperfectly screened Coulomb interactions, however, the situation is more complex. The optimal value of δ is determined by a combination of δ_0 and $\Delta \bar{\rho} \equiv \bar{\rho} - \bar{\rho}^N$. In the limit of no screening, $\kappa_0 \to \infty$, the incommensurate state is stable at all temperatures $(T_I \to \infty)$, and at long distances, the incommensurability is set by the *con*straint, $\delta = -\Delta \bar{\rho} [2\Lambda |\psi|^2]^{-1}$. For intermediate values of the screening, the behavior is intermediate between these two limits. Finally, since the Coulomb interaction couples different planes, the surface transition temperature is not determined solely by the values of the parameters in the surface layer, but depends on the coupling between the surface and the bulk in a non-trivial fashion.

Since our principal focus is on the possibility of surface transitions, we will treat the bulk properties cursorily. Just to be specific, we consider the case of a striped phase $(\gamma > 0)$ in which $\psi_2 = 0$, but the generalization to checkerboard phases, which occur for $\gamma < 0$, is straightforward. In order to determine the bulk (mean field) phase diagram we compare the energies of three different forms of the order parameter to get a sense of the bulk phase diagram:

1) The disordered state, $\psi_{1,n} = 0$. The mean-field free energy density of the disordered state is

$$F_{\rm dis} = (1/2)\kappa_0 \ (\Delta\bar{\rho})^2.$$
 (1.4)

2) The commensurate solution, $\psi_{1,n}(\vec{r}) = \psi$. The free energy of the commensurate state is

$$F_{\rm c} = F_{\rm dis} + (1/2) \left[r + K \delta_0^2 V_Q \right] |\psi|^2 + \left[u - 2V_{\rm c} \right] |\psi_j|^4,$$

where $V_Q = 4\pi e^2/(\epsilon [Q^2 + \xi^{-2}])$. 3) The harmonic incommensurate state, $\psi_{j,n}(\vec{r}) =$

 $\psi_j \exp[i\delta \hat{Q}_j \cdot \vec{r}]$. (We know from the work of McMillan⁹ that, especially near the commensurate to incommensurate transition, the structure of the incommensurate state is highly anharmonic, and this anharmonicity has a significant quantitative effect on the phase diagram, but one can understand much of the qualitative physics ignoring this.) The optimal incommensurability and free energy of this state are, respectively,

$$\delta = \delta_0 [1 + A^{-1}] \left[1 + 2A^{-1} |\tilde{\psi}|^2 \right]^{-1}$$
(1.5)

$$F_I = F_{\text{dis}} + \frac{r + V_Q}{2} |\psi|^2 + u |\psi|^4$$
$$- \frac{\kappa_0 (\Delta \bar{\rho})^2}{2} \left[\frac{1 + 2A - |\tilde{\psi}|^2}{1 + A |\tilde{\psi}|^2} \right] |\tilde{\psi}|^2$$
(1.6)

where $\tilde{\psi} = [2\Lambda\delta_0/\Delta\bar{\rho}]\psi$ and $A = K\delta_0/2\kappa_0\Lambda\Delta\bar{\rho}$.

One interesting consequence of these expressions is that they imply a non-trivial temperature dependence of the incommensurability as the order parameter grows. This is a general feature of an incommensurate state, but what is new here is the singular temperature dependence inherited from the T dependence of $|\psi|^2$. The other important observation is that a more poorly screened the Coulomb interaction (larger κ_0), generally tends to stabilize the incommensurate phase. This can be seen from the fact that, the final term in Eq. (1.6) is generally negative. Since T_I is the first temperature at which the quadratic term (in powers of ψ) in Eq. (1.6) becomes negative, it is manifest that T_I is an increasing function of κ_0 . However, even for finite ψ , this term is negative so long as $|\tilde{\psi}|^2 < 1 + 2A$, and so it generally tends to favor the incommensurate over the commensurate phase, as well.

This final observation may be significant for understanding the remarkable stability of weakly incommensurate CDW states. When the Coulomb interaction is fully screeened ($\kappa_0 = 0$), the commensurate to incommensurate transition occurs when the gain in commensurability energy, equals the loss in elastic energy, $2V_c |\psi|^4 = (1/2)K\delta^2 |\psi|^2$. Since both V_c and K are typically determined by the electronic structure, unless either δ is large or ψ is small (which typically means that T is close to T_I), we expect universally to see only commensurate states. However, where the Coulomb interactions are poorly screened (κ_0 large), there is an additional energetic cost $\sim (1/2)\kappa_0(\Delta\bar{\rho})^2$ for the commensurate state, which could stabilize the incommensurate state to low temperatures, even if $\delta \ll 1$.

In the above we have kept only terms to order ψ^4 and lowest order in the density fluctuations. Near a continuous transition between a disordered phase and an incommensurate CDW, this is justified, at least at mean-field level, on the basis of the small magnitude of the order parameter. Since the incommensurate to commensurate transition occurs only when the order parameter exceeds a critical magnitude, the above treatment is only valid when δ is small enough. More generally, at temperatures well below T_I , the low energy physics, and the commensurate to incommensurate transition in particular, should be treated in terms of a phase-only model. Thus, as long as we are comfortably below the mean-field transition temperature, we can integrate out the amplitude modes of the CDW order parameters (and the fluctuations of ρ_N , as well), and concentrate on the low-energy physics of the phase degrees of freedom. Thus, we set $\psi_{jn}(\vec{r}) = |\psi_j| \exp[i\theta_{jn}(\vec{r})]$. To begin with, again consider the stripe case, in which $\psi_1 = \psi$ and $\psi_2 = 0$; then, the effective free energy for the phase degrees of freedom is

$$\mathcal{F}_{\text{eff}}[\theta] = \sum_{n} \int d^2x \left\{ \frac{\kappa_{\parallel}}{2} \left(\partial_x \theta_n - \delta_0 \right)^2 + \frac{\kappa_{\perp}}{2} \left(\partial_y \theta_n \right)^2 - U \cos[4\theta_n] \right\} + \frac{g}{2} \sum_{n,n'} \int d^2x \ d^2x' \left(\partial_x \theta_n - \delta_0' \right) \widetilde{V}(\vec{x} - \vec{x}\,', n - n') \left(\partial_{x'} \theta_n - \delta_0' \right)$$
(1.7)

where $\tilde{V}(\vec{x} - \vec{x}', n - n')$ is the screened Coulomb interaction potential. In what follows we will find it convenient to use a form of the screened interaction potential which is the solution of

$$\left\{ -\left(a_z^{-2} \bigtriangleup + \nabla^2\right) + \xi_s^{-2} \right\} \quad \widetilde{V} \left(\mathbf{x} - \mathbf{x}'; n - n'\right) = a_z^{-1} \delta_{n,n'} \delta(\mathbf{x} - \mathbf{x}')$$

$$(1.8)$$

where we have set $\triangle f(n) \equiv f(n+1) + f(n-1) - 2f(n)$, and ξ_s is the screening length. The expression for $\mathcal{F}_{\text{eff}}[\theta]$, the effective free energy for the phase degrees of freedom, Eq.(1.7), can be derived from the Landau-Ginzburg theory above, Eq.(1.2), which results in expressions for the effective stiffness constants κ_{α} , the commensurability potential, U, and the second incommensurability, δ'_0 , in terms of the parameters of the Landau-Ginzburg model. The only important aspect of this for our purposes is that $U \propto \psi^4$, $\kappa_{\alpha} \propto K_{\alpha}\psi^2$, and $g \propto (e^2/\varepsilon)\psi^4$. It is also important to note that in the neighborhood of a surface, the parameters in $\mathcal{F}_{\text{eff}}[\theta]$ inherit layer index, n, dependence.

We conclude with a final observation concerning the checkerboard phase. The Landau-Ginzburg free energy in Eq.(1.2) has no direct coupling between the phase of ψ_1 and that of ψ_2 . Thus, to this order, $\mathcal{F}_{\text{eff}}[\theta]$ for the checkerboard phase is simply two, totally independent copies of the above effective free energy. In the incommensurate phase, this reflects an exact symmetry - the origin of the two components of the CDW can be shifted relative to each other with no cost in energy. This has implications for the fluctuation spectrum of an incommensurate checkerboard phase. (For the commensurate phase, the phase is locked to the underlying crystalline lattice, in any case, so although there are higher order couplings that link the two phases, they are not important.)

II. THE NATURE OF THE EXTRAORDINARY COMMENSURATE-INCOMMENSURATE TRANSITION

There are two cases of interest. In the first case, we can envisage a situation in which the coefficient r for the surface layer is different than in the bulk, and such that the surface orders while the bulk remains disordered. This is the direct analog of the "ordinary extraordinary" surface phase transition, which has been well studied in magnetic systems⁶. (In the next section we give a brief discussion of the microscopic physics that can lead to this situation.) A mean-field state of this type has the form $\psi_n(\vec{x}) \sim A_n \exp[i(1+\delta_n)\vec{Q}\cdot\vec{x}]$ where $\lim_{n\to\infty} A_n = 0$ exponentially fast (on a length scale of the order of the bulk correlation length.) The only difference from the ordinary case is that, because of the Coulomb interaction, the incommensurability, δ_n , varies from plane to plane, approaching an asymptotic value $\lim_{n\to\infty} \delta_n = \delta_0$. It is straightforward to construct this state using the Landau-Ginzburg theory of Eq.(1.2).

The second case of interest, which is the focus of this section, does not have an obvious analog in surface phase transitions in magnetic systems (although it may happen in incommensurate spin-density-wave systems as well.) Here we imagine that the temperature is well below the critical temperature for bulk incommensurate order so both in the bulk and at the surface, the magnitude of the order parameter is large and essentially fixed. We can now ask if it is possible for the commensurateincommensurate transition to occur at the surface at a higher critical temperature than in the bulk. We can discuss the physics of this state in the simpler phase-only model of Eq.(1.7). To simplify the analysis, in what follows we will focus on the special case $\delta'_0 = \delta_0 = \delta$ as this does not change the qualitative properties of the solutions, and it greatly simplifies the algebra.

We construct this inhomogeneous state as follows: We first note that for the bulk homogeneous commensurate state $\theta_n(\vec{x}) = 0$ everywhere, while for the bulk

homogeneous incommensurate state $\theta_n(\vec{x}) = \delta x$ everywhere (assuming stripe order perpendicular to the x axis). As in the previous section, we have thus neglected the physics of near-commensurability, *i.e.* discommensurations, within a given plane - including this physics greatly complicates the analysis without changing the qualitative conclusions. We will construct an inhomogeneous state which is commensurate at the surface, and hence we set $\theta_0(\vec{x}) = 0$, but incommensurate everywhere else, $\partial_x \theta_n(\vec{x}) \neq 0$ for $n = 1, 2, \ldots$

In short, we need to study the circumstances under which there exists an approximate mean-field state (which minimizes $\mathcal{F}_{\text{eff}}[\theta]$) in which (by assumption) the phase field on each plane has a constant gradient, $\partial_x \theta_n(\vec{x}) \equiv f_n + \delta$ (discommensuration-free), but which varies from plane to plane. This solution must satisfy the boundary conditions $f_0 = -\delta$, *i.e.* commensurate at the n = 0 layer, and $\lim_{n\to\infty} f_n = 0$, *i.e.* the bulk incommensurate state. It should be stressed that while approximate, these configurations are upper bounds to the actual non-linear solutions. The effective free energy (per unit area) for configurations of this type is readily found from Eq.(1.7) to be

$$\mathcal{F}_{\text{eff}}[f] = \frac{\kappa_{\parallel}}{2} \sum_{n=0}^{\infty} f_n^2 - \sum_{n=0}^{\infty} U_n + \frac{g}{2} \sum_{n,m=0}^{\infty} f_n f_m G_{1D}(n-m)$$
(2.1)

where $G_{1D}(n-m)$ is given by

$$G_{1\mathrm{D}}(n-m) = \left(\frac{\mu}{\mu^2 - 1}\right) \ \mu^{-|n-m|}$$
 (2.2)

with

$$\mu = \frac{1}{2} \left\{ 2 + (a/\xi_s)^2 + \left[(2 + (a/\xi_s)^2 - 4) \right]^{1/2} \right\}$$
(2.3)

For configurations of this type, the contribution of the pinning potential vanishes for all $n \geq 1$ (as they are incommensurate), while on the commensurate surface layer, n = 0, it contributes with the surface value of the pinning potential, U_s . Hence, $U_n = U_s \delta_{n,0}$.

The unique configuration f_n which minimizes $\mathcal{F}_{\text{eff}}[f]$ and satisfies the boundary conditions is

$$f_n = -\delta \left(1 - \frac{\gamma}{\mu}\right) \gamma^{-n} \tag{2.4}$$

where γ satisfies the identity

$$\left(\gamma + \frac{1}{\gamma}\right) = \left(\mu + \frac{1}{\mu}\right) + \frac{g}{\kappa_{\parallel}} \tag{2.5}$$

Since $\gamma > \mu > 1$, the solution decays to the bulk value on a scale $a/\log \gamma$ shorter than the length scale of the screened interaction. The free energy (per unit area) of this solution is

$$\mathcal{F} = U_s^{\text{crit}} - U_s, \quad U_s^{\text{crit}} \equiv \frac{1}{2} \delta^2 g\left(\frac{\gamma}{\mu}\right) \left(\frac{g}{\kappa_{\parallel}}\right).$$
 (2.6)

Thus, if the surface value of the pinning potential U_s is greater than $U_s^{\rm crit}$, the uniform incommensurate CDW state is unstable at the surface. Moreover, since $U^{\rm crit} \propto \delta^2$, for the case of a system which is only *weakly* incommensurate in the bulk, it requires a very small value of the surface commensurability coupling to stabilize a commensurate state, there.

This is not quite the whole story. The same analysis can be applied to look for a bulk, inhomogeneous state, in which a periodic arrangement of (possibly far separated) planes are commensurate, while the intervening planes have incommensurabilities that can be obtained in similar fashion by minimizing Eq. 2.1. An upper- bound to the energy of such an inhomogeneous bulk state is given by using the surface solution we have just described, but with an arbitrary layer in the bulk taken to be the layer which is commensurate - it is in fact possible to do somewhat better than this. Thus, there is a critical value, $U^{\text{crit}} < U^{\text{crit}}_{s}$, such that when $U > U^{\text{crit}}$, there is a bulk instability of the uniform state. To find a circumstance in which there is a surface instability, but no bulk instability, it is necessary that U is larger in the surface layer than in the bulk, so that $U_s > U_s^{\text{crit}} > U^{\text{crit}} > U$. As we will see in the next section, this is possible when a surface phonon results in an enhanced magnitude of the CDW in the surface layer, and hence an enhanced tendency toward commensurability.

III. A POSSIBLE PHONON "MECHANISM" OF AN EXTRAORDINARY TRANSITION

In this section, we discuss a simple model, motivated by the structure of NaCCOC, in which an electronphonon coupling can lead to an enhancement of the surface tendency to CDW order and commensurability. Of course, there are many possible surface effects, so this discussion should be taken as illustrative rather than "realistic."

Each Cu site in NaCCOC sits at the center of an octahedron, with the apical (out of plane) sites occupied by a Cl, instead of the O that appears there in LSCO. It is known that NaCCOC cleaves such that the surface layer is a Ca-O layer, so the topmost Cl is exposed at the surface. It is thus highly plausible that the motion of the apical Cl is less constrained due to the absence of material above it. It is known¹¹, moreover, that the motion of the apical atom is strongly coupled to the charge density in the copper-oxide plane – the apical O moves 0.013 Å closer to the Cu in optimally doped LSCO than in undoped La₂CuO₄ (in YBCO, the apical O displacement is even larger¹² ~ 0.15 Å.)

We therefore consider the effect of coupling to an Einstein phonon corresponding to the motion of the local charge density in the plane,

$$H_{\rm el-ph} = \frac{P^2}{2M} + \frac{1}{2}M\omega_0^2 X^2 + \lambda X [\rho(\vec{x}) - \bar{\rho}]. \quad (3.1)$$

Here P and X are the phonon momentum and displacement, ω_0 is the phonon frequency, λ is the electronphonon coupling, and $\rho(\vec{x})$ is the local electron density. If we further assume that the phonon is "fast" (ω_0 large compared to the frequency scales of interest), we can integrate it out to obtain an effective attraction

$$H_{\rm eff} = -\frac{\lambda^2}{2M\omega_0^2} \, [\rho(\vec{x}) - \bar{\rho}]^2 \tag{3.2}$$

when we further substitute the expression in Eq. (1.1) for ρ in terms of the CDW order parameter, we see that the electron-phonon coupling leads to a renormalization of the various parameters that enter the Landau-Ginzburg free energy functional, but most importantly, it leads to a negative additive shift of r

$$r \to r - 2 \, \frac{\lambda^2}{2M\omega_0^2} \tag{3.3}$$

or equivalently, to an upward renormalization of the mean-field ordering temperature. If the surface phonon is softer than in the bulk (*i.e.* the elastic constant $k = M\omega_0^2$ is smaller on the surface), as the above discussion suggests, then this renormalization is larger at the surface than in the bulk. This implies both that the ordering temperature at the surface is enhanced, and at a given temperature, the magnitude of the order parameter is increased, thereby increasing the chance of a commensurate lock-in.

It is important to note that a large shift in the CDW ordering can occur for rather small displacements of the apical Cl positions. To make a dimensional estimate of the expected magnitude of this displacement, we note that the contribution of this interaction to the condensation energy is $E_{el-ph} \sim M\omega_0^2(\Delta X)^2$; this must be less than or equal to the full condensation energy, and hence we can make an upper-bound estimate, $E_{el-ph} \sim \rho(E_F)T_c^2$. If we further crudely estimate that $M\omega_0^2 \sim E_F/a^2$, we find that $\Delta X \sim a(T_c/E_F)$, which is generally small.

IV. EXPERIMENTS IN THE CUPRATES

Dramatic evidence of CDW order in a high temperature superconductor was recently obtained from low temperature (T = 4K) STS experiments of Hanaguri and coworkers⁴ on NaCCOC with x = 0.08, 0.10, and 0.12. All of these doping levels are less than the optimal value x = 0.15, where T_c reaches 20K; for x = 0.08 there is no bulk superconductivity at all. For all doping levels, the tunneling conductances exhibit a pseudogap structure for energies less than about 150meV, but no sign of the coherence peaks at lower energies that have been identified with the superconducting gap in earlier STS studies of BSCCO^{2,13}. Although high-energy topographic maps do not exhibit any periodic modulations other than those associated with the underlying crystal structure, within the pseudogap, STS reveals large amplitude (order 1) spatial modulations of the local density of states (LDOS) with a checkerboard pattern. Fourier transforms of the STS maps reveal peaks corresponding to a commensurate modulation with a $4a_0 \times 4a_0$ periodicity and peak widths of order of one tenth of the Brillouin Zone dimensions.

The large amplitude LDOS modulations observed at low energies are reminiscent of those seen in conventional CDW systems such as the dichalcogenides¹⁴. In those systems, the CDW also shows up in the topographic maps. Correspondingly, in NaCCOC, one might have expected a signal from the height modulations of the surface Cl atoms to show up in the high-energy topographs as a result of CDW-induced atomic displacements. However, according to the estimates in the previous section, for a range of plausible $T_c/T_F \sim 10^{-1} - 10^{-2}$, the expected magnitude of these displacements is in the range 0.1 - 0.01 Å, which probably would be undetectable on the grev-scale maps in Ref. 4. Another difference with conventional CDW behavior is the doping independence of the ordering vector in NaCCOC. In conventional CDW systems, the CDW ordering vector changes as the location of the Fermi surface changes. Finally, whereas the STS modulations seen in the dichalcogenides are highly coherent, the correlation length of about 10 lattice constants found in NaCCOC is less than 3 periods, making any definitive statements about the character of the order difficult.

To determine whether the observed modulations are indicative of bulk CDW order, we need to consider what other signatures of CDW order would be expected. There are presently no high resolution STS studies on NaCCOC at higher temperatures, so little is directly known about the thermal evolution of the checkerboard order. X-ray or neutron diffraction are the traditional sources of definitive evidence for charge order; the in-plane components of the wavevector are well-defined by the STS experiments, but the body-centered tetragonal coordination of the the Cu atoms gives little reason to suspect significant coherence between planes. As a result, peaks in the scattering intensity should form rods at wave-vectors $\mathbf{Q} = (2\pi/a)(1/4, 0, \ell)$. However, we are not aware of any reports of any such diffraction peaks in NaCCOC.

A phase transition to a density wave state is expected to affect the resistivity, in general, by removing some part of the Fermi surface (FS) and by modifying scattering rates on the remaining FS. This expectation is generally realized in conventional CDW systems. The effect on the resistivity is especially strong in cases in which the CDW order is sufficiently strong that there is a low temperature commensurate lock-in. In contrast, the temperature dependence of the resistivity of NaCCOC¹⁵ does not exhibit any distinct features we can associate with a phase transition below 300K. Moreover, the magnitude of the in-plane resistivities are close to what is reported¹⁶ for LSCO and YBCO, where there is little or no static CDW order.

More evidence against the existence of a bulk CDW

comes from an examination of the electromagnetic response. Optical conductivities of conventional CDW systems show a shift of (typically most of the) oscillator strength to energies above the single-particle gap, whereas there is no evidence for such a shift in NaCCOC¹⁵. If there were bulk CDW order in NaC-COC with an ordering temperature below 300K, surely it would have produced a detectable feature in the electromagnetic response. If the ordering temperature were above 300K, surely it would have produced a large quantitative change of the resistivity. (Note: it is usual in CDW systems that the ratio of the CDW gap to T_c is large, $2\Delta/kT_c \sim 10$, see Ref. 17. For a gap size of $\Delta \sim 150 \ meV$, one might therefore expect a bulk ordering temperature of around 300K.)

The one caveat on this argument is that, already in earlier studies of the onset of stripe order in LNSCO, it was observed that while there is a characteristic signature in the temperature dependence of the resistivity¹⁸ and a "localization" like suppression¹⁹ of the low frequency optical conductivity associated with the onset of charge order, these features are considerably more muted than in conventional CDW systems. Presumably, the difference reflects the different origins of the charge order. In conventional CDW systems, the ordering is at least loosely associated with Fermi surface nesting, and hence the fluctuations above T_c cause singular scattering of the quasi-particles across these nested portions, and a gap is opened on the Fermi surface in the low temperature phase. In contrast, in the cuprates, the charge ordering is a strong coupling $effect^5$, not directly associated with any identifiable Fermi surface nesting vector, and hence the effect of the onset of order on the low energy quasiparticle dynamics is much more subtle. (The fact that the quasiparticles are always relatively short-lived, in any case, may exacerbate this effect.) It is thus possible that in NaCCOC, the effect of the CDW ordering on the electrodynamics is simply so small as to have escaped detection. However, given that the order is commensurate (while that in LNSCO is incommensurate and weak), and that the charge order in NaCCOC apparently produces a pseudo-gap in which the density of states essentially vanishes at zero energy, we conclude that it is unlikely that this order, if present in the bulk, would not produce a detectable signature in the electrodynamics.

We conclude that it is likely that the commensurate CDW order in NaCCOC resides only on the surface as an extraordinary state of the type described in Section II. This conclusion is suggested by the absence of any evidence of bulk density wave order, the absence of the expected evolution of the CDW periodicity with doping level, and the absence of superconducting coherence peaks at the surface²⁰.

Is the checkerboard order, then, simply a surface artifact, from which we learn nothing about a bulk tendency toward charge order? We think a more plausible interpretation is that density wave order, already incipient in the bulk, is stabilized at the surface, most probably by a softening of a surface phonon.

In the first place, modulations of the low energy LDOS with similar period, although somewhat incommensurate and much smaller in magnitude than those seen in NaC-COC, have been documented^{1,2,3} on BSCCO surfaces, with a long correlation length of the order of 80 Å, and interpreted (rightly we believe) as being induced by the disorder pinning of some form of incipient (fluctuating) CDW order. In the case of BSCCO, the relevant Cu-O planes are not exposed on cleaving the crystal, but are rather buried under a Bi-O layer. Thus, there is more reason to hope that the surface electronic structure is similar to that in the bulk. Moreover, clear signatures of the superconducting gap have been reported in STS studies of BSCCO surfaces¹³, again suggesting that the bulk electronic structure is well preserved at the surface. The fact that the periodicity of the observed modulations is similar (although not equal) to those in NaCCOC, suggests that they are related phenomena, and so supports the notion that they both reflect interesting bulk correlations.

Secondly, neutron scattering studies of LSCO and YBCO reveal ubiquitous evidence of fluctuating stripe $\operatorname{order}^{5,21,22,23,24,25,\overline{2}6}$ (that is, a strong enhancement of the dynamical structure factor at low ω and at the characteristic, stripe ordering wave-vector, $\vec{q}_{\text{stripe}}[x]$, smoothly dependent on the doping fraction x) and a weak (possibly extrinsically stabilized) tendency toward static spin-stripe order. In LSCO, $\vec{q}_{\text{stripe}}[x]$ is incommensurate in the relevant range of doping, a fact which can be inferred from its absolute magnitude, its continuous x dependence, and the small rotation from the Cu-O direction induced by the weak orthorhombicity of $LSCO^{27}$. Nevertheless, in the relevant range of doping, the implied periodicity is only slightly greater than $4a_0$. Similar statements apply to the bulk properties of YBCO, with the difference that there is still less tendency toward static CDW order. The fact that the structures seen in diffraction correspond to unidirectional density wave order (stripes) while the checkerboards preserve the point-group symmetry of the tetragonal lattice, would seem to differentiate these two phenomena. However, it is a rather subtle energy which leads to the selection of

- ¹ J.E. Hoffman, E.W. Hudson, K.M. Lang, V. Madhavan, H. Eisaki, S. Uchida and J.C. Davis, Science **295**, 466-9 (2002).
- ² C. Howald, H. Eisaki, N. Kaneko, M. Gerven, A. Kapitulnik, Phys. Rev. B **67**, 014533 (2003); C. Howald, H. Eisaki, N. Kaneko, and A. Kapitulnik, Proc. Natl. Acad. Sci. U.S.A. **100**, 9705 (2003).
- ³ M. Vershinin, S. Misra, S. Ono, Y. Abe, Y. Ando, and A. Yazdani, Science **303**, 1005 (2004).
- ⁴ T. Hanaguri, C. Lupien, Y. Kohsaka, D.-H. Lee, M. Azuma, M. Takano, H. Takagi and J. C. Davis, Nature **430**, 1001 (2004).

stripe vs checkerboard order, while the basic tendency to charge order and the characteristic ordering wave-vector is considerably more robust. This is certainly the case, as stressed previously^{5,22}, when the charge order results from a form of Coulomb frustrated phase separation.

Finally, we turn to speculation concerning possible surface phenomena in BSCCO. BSCCO is highly micaceous, and the top bilayer is concealed below a Bi-O layer. Thus, there is good reason to think that the properties of this top bilayer resemble the properties of the bulk. However, there is one effect, which even if weak, may be important since it breaks a symmetry of the bulk. In the bulk, the two layers of the bilayer are equivalent, so that in the absence of bilaver splitting there should be a single, doubly degenerate band. At the surface, this symmetry is broken, in that the upper layer is closer to the surface. Thus means that, even absent bilayer splitting, there should be two distinct bands. This effect may need to be considered when discussing evidence of bilayer splitting from ARPES studies of $BSCCO^{28}$.

Acknowledgments

We are grateful to Peter Armitage, J.C. Séamus Davis, T. Hanaguri, Aharon Kapitulnik, Dung-Hai-Lee, Subir Sachdev, John Tranquada, Ali Yazdani and Shoucheng Zhang for many illuminating conversations. We are also grateful to Adrian del Maestro and Subir Sachdev for communicating their unpublished results with us. This work was supported in part by the National Science Foundation through the grants NSF DMR-04-42537 at the University of Illinois (EF), NSF DMR-04-21960 at UCLA/Stanford (SAK), NSF DMR-02-03806 at UCLA (SEB), and NSF PHY-99-07949 at the Kavli Institute for Theoretical Physics, UCSB, where EF and SAK where participants at the KITP Program on *Exotic Order and Criticality in Quantum Matter*. EF and SAK thank KITP Director David Gross for his kind hospitality.

- ⁵ S.A. Kivelson, E. Fradkin, I.P. Bindloss, V. Oganesyan, J.M. Tranquada, A. Kapitulnik, and C. Howald, Rev. Mod. Phys. **75**, 1201 (2003).
- ⁶ K. Binder, Critical behavior at surfaces, in Phase Transitions and Critical Phenomena, Vol. 8, Eds. C. Domb and J.L. Lebowitz (Academic Press, London 1983).
- ⁷ A similar system has been considered independently by Adrian del Maestro and Subir Sachdev who studied the phase diagram associated with the thermal melting of a "checkerboard" ordered CDW state in the bulk, S. Sachdev, private communication; Adrian del Maestro and Subir Sachdev, Thermal melting of density waves on the

square lattice, arXiv:cond-mat/0412498. They find that at an intermediate temperature range there is a stripe-like phase due to a dislocation driven partial melting mechanism. This phase has long range commensurate order in one direction and incommensurate along the perpendicular direction, with only power law correlations. This phase has the same symmetries and Goldstone modes as the smectic metal, or sliding Luttinger liquid array, of Refs. 29 and 30. This stripe phase, which has a single Goldstone mode (as it should for a smectic), it is smoothly connected to the stripe phase we are discussing in this paper.

- ⁸ W.L. McMillan, Phys. Rev. B **12**, 1187 (1975).
- ⁹ W.L. McMillan, Phys. Rev. B **14**, 1496 (1976).
- ¹⁰ Per Bak, Rep. Prog. Phys. **45**, 587 (1982).
- ¹¹ P. G. Radaelli, D. G. Hinks, A. W. Mitchell, B. A. Hunter, J. L. Wagner, B. Dabrowski, K. G. Vandervoort, H. K. Viswanathan, and J. D. Jorgensen, Phys. Rev. B 49, 4163 (1994).
- ¹² R. J. Cava, A.W. Hewat, E.A. Hewat, B. Batlogg, M. Maurizio, K.M. Rabe, J.J. Krajewski, W.F. Peck Jr., and L.W. Rupp Jr., Physica C **165**, 419 (1990); J.D. Jorgensen, B.W. Veal, A.P. Paulikas, L.J. Nowicki, G.W. Crabtree, H. Claus, and W.K. Kwok, Phys. Rev. B **41**, 1863 (1990).
- ¹³ Ch. Renner, B. Revaz, K. Kadowaki, I. Maggio-Aprile, and Ø. Fisher, Phys. Rev. Lett. 80, 3606 (1998).
- ¹⁴ C. Wang, B. Giambattista, C.G. Slough, and R. V. Coleman, Phys. Rev. B **42**, 8890 (1990).
- ¹⁵ K. Waku, T. Katsufuji, Y. Kohsaka, T. Sasagawa, H. Takagi, H. Kishida, H. Okamoto, M. Azuma, and M. Takano, Phys. Rev. B **70**, 134501 (2004)
- ¹⁶ Y. Ando, S. Komiya, K. Segawa, S. Ono, and Y. Kurita, Phys. Rev. Lett. **93**, 267001 (2004).
- ¹⁷ G. Grüner, Rev. Mod. Phys. **60**, 1129 (1988).
- ¹⁸ N. Ichikawa, S. Uchida, J. M. Tranquada, T. Niemöller, P. M. Gehring, S.-H. Lee, and J. R. Schneider, Phys. Rev. Lett. 85, 1738 (2000)
- ¹⁹ M. Dumm, D. N. Basov, Seiki Komiya, Yasushi Abe, and Yoichi Ando, Phys. Rev. Lett. **88**, 147003 (2002); M. Dumm, Seiki Komiya, Yoichi Ando, and D. N. Basov, Phys. Rev. Lett. **91**, 077004 (2003).

- ²⁰ Not only do the STS spectra of NaCCOC not show sharp coherence peaks even in doping regimes in which it is a bulk superconductor⁴, but they also show a marked particlehole asymmetry down to the lowest bias voltages. In contrast, the STS spectra in nearly optimally doped BSCCO show a clear particle-hole symmetry below the energy scale of the (well defined) coherence peaks. On the other hand, in very underdoped BSCCO there is little evidence of coherence paks and the STS spectra is similarly asymmetric as in NaCCOC³¹.
- ²¹ J.M. Tranquada, B.J. Sternlieb, J.D. Axe, Y. Nakamura and S. Uchida, Nature **375**, 561 (1995).
- ²² V.J.Emery and S.A.Kivelson, Physica C **209**, 597 (1993).
- ²³ V.J. Emery, S. A. Kivelson and J. M. Tranquada, Proc. Natl. Acad. Sci. U.S.A. 96, 8814-8817 (1999).
- ²⁴ B. Lake, H. M. Rønnow, N. B. Christensen, G. Aeppli, K. Lefmann, D. F. McMorrow, P. Vorderwisch, P. Smeibidl, N. Mangkorntong, T. Sasagawa, M. Nohara, H. Takagi and T. E. Mason, Nature **415**, 299-302 (2002).
- ²⁵ J. Zaanen, Physica C **317-318**, 217 (1999).
- ²⁶ See S. Sachdev, Quantum phases and phase transitions of Mott insulators, in "Quantum magnetism", U. Schollwöck, J. Richter, D. J. J. Farnell and R. A. Bishop eds., Lecture Notes in Physics, Springer, Berlin (2004), and references therein.
- ²⁷ H. Kimura, H. Matsushita, K. Hirota, Y. Endoh, Y. Yamada, G. Shirane, Y.S. Lee, M.A. Kastner, and R. J. Birgeneau, Phys. Rev. B **61**, 14366 (2000).
- ²⁸ A. Kapitulnik, private communication.
- ²⁹ Victor J. Emery, Eduardo Fradkin, Steven A. Kivelson and Tom C. Lubensky, Phys. Rev. Lett. 85, 2160 (2000).
- ³⁰ A. Vishwanath and D. Carpentier, Phys. Rev. Lett. 86, 676 (2001).
- ³¹ K. McElroy, D.-H. Lee, J. E. Hoffman, K. M Lang, J. Lee, E. W. Hudson, H. Eisaki, S. Uchida, and J.C. Davis, Destruction of antinodal state coherence via 'checkerboard' charge ordering in strongly underdoped superconducting $Bi_2Sr_2CaCu_2O_{8+\delta}$, unpublished (2004); arXiv: cond-mat/0406491.