

Making spherical GEMs

Serge Duarte Pinto^{ab*}, Marco Villa^{ab}, Matteo Alfonsi^a, Ian Brock^b, Gabriele Croci^a, Eric David^a, Rui de Oliveira^a, Leszek Ropelewski^a, Miranda van Stenis^a, Hans Taureg^a

^aCERN,

Geneva, Switzerland.

^bPhysikalisches Institut der Universität Bonn,

Bonn, Germany.

ABSTRACT: We developed a method to make GEM foils with a spherical geometry. Tests of this procedure and with the resulting spherical GEMs are presented. Together with a spherical drift electrode, a spherical conversion gap for x-rays can be formed. This would eliminate the *parallax error* in an x-ray diffraction setup, which limits the spatial resolution at wide diffraction angles. The method is inexpensive and flexible towards possible changes in the design.

We show advanced plans to make a prototype of an entirely spherical triple-GEM detector, including a spherical readout structure. This detector will have a superior position resolution, also at wide diffraction angles, and a high rate capability. A completely spherical gaseous detector has never been made before.

KEYWORDS: gaseous detectors, gas electron multipliers, GEM, gaseous imaging and tracking detectors.

*Corresponding author: Serge.Duarte.Pinto@cern.ch

Contents

1. Introduction	1
2. Procedure & tooling	2
3. Properties of spherical GEMs	4
4. Work in progress	5
5. Conclusions and outlook	6

1. Introduction

Position sensitive radiation detectors with a spherical geometry can be attractive for various applications, for several reasons. The most common motivation to make gas detectors for x-ray scattering spherical is to eliminate the *parallax error*. This error is caused by the uncertainty of where an incoming x-ray converts in a gas detector, due to the limited absorption efficiency of gases, see figure 1. If the electric field in the drift region is not parallel to the trajectory of the x-ray photon, an uncertain conversion depth will give rise to an error in position reconstruction, see figure 2. Methods that have been used to suppress parallax error include:

- Arranging small area flat detectors in such positions as to approximate a spherical shape [2].
- Creating an almost spherical conversion region with foils and meshes, then transferring the charge to a planar wire chamber [3, 4].
- Having a spherical cathode with an otherwise flat detector, while reducing the conversion depth by using an efficient x-ray conversion gas (xenon) at a high pressure (~ 3 bar) [5, 6].
- Imitating a spherical cathode by dividing a flat electrode into concentric circular segments and controlling the voltage applied to each sector with a resistive divider [7].




Figure 1. X-ray absorption length of several noble gases as a function of x-ray photon energy. Calculated from x-ray cross-section data [1]

Each of these methods has its limitations. In all cases the challenge of making a fully spherical detector, however desirable, is avoided. We started an effort that should lead to the first entirely parallax-free gas detector, based on spherical GEMs, cathode and readout board. We developed a method that allows us to make a spherical GEM from a flat standard GEM [8], apparently without affecting its properties significantly.




Figure 2. The cause of a parallax error in a gas detector with a homogeneous drift field.

First performance tests of single spherical GEMs will be done in a setup with a spherical entrance window (which serves as drift electrode as well) and a flat readout structure, see the left side of Fig. 3. The electric field in the conversion region is truly radial. The amplitude of signals from conversions in the non-radial induction region will be suppressed by the gain of the GEM.

Designs are being prepared to make a prototype of a wide-angle spherical triple GEM, see the right side of Fig. 3. This will be the very first entirely spherical gaseous detector. Additional challenges of this design compared to the one on the left are the spherical readout structure and the narrow spacing between GEMs, for which curved spacers will be developed.




Figure 3. Schematic composition of two prototypes based on spherical GEMs. Left: single spherical GEM with spherical drift electrode but flat readout structure. Right: an entirely spherical triple GEM detector

2. Procedure & tooling

For the manufacturing of a spherical GEM we start with a flat GEM foil. The shape of the electrodes is designed for the purpose; otherwise the foils used are no different from GEMs used for other applications. Thus, our base material is of proven reliability and we know its properties well. Starting with this flat GEM foil we use a method similar to thermoplastic heat forming; the foil is forced into a new shape by stretching it over a spherical mold, see figure 4. After a heat cycle it keeps this spherical shape.




Figure 4. The setup built to remold a flat GEM into a spherical one.

Heat forming is routinely done with thermoplastic polymers, where above the so-called *glass transition temperature* monomers can migrate freely, and polymerize again upon cooling down. However the polyimide substrate of GEMs is a thermoset polymer which has no well-defined glass transition temperature. Strongly heating a polyimide leaves the polymer chains intact, but allows cross-links between chains to break or dislocate, thus relieving mechanical stresses. Starting from a certain temperature the polyimide will start to degrade irreversibly; it becomes weak, brittle and dark-colored, see figure 5. We found that 350° C is the highest temperature we can apply to foils without damaging the quality of the polymer significantly.




Figure 5. The result of overheating a foil when trying to form it. The electrodes of this GEM were removed beforehand to avoid their oxidation. During the forming procedure it was heated up to 400° C.

Figure 4 shows the simple setup designed for forming GEMs spherically. It consists of a spherical mold, a ring-and-plate structure to hold the foil to be formed, and four axes along which the plate can slide down toward the mold. Weights are applied to the plate to control the force that stretches the foil over the mold. Note that, contrary to thermoplastic heat forming, the foil cannot be allowed to slip between the ring and plate where it is mounted. The degree to which monomers migrate during the forming is much less than for thermoplastics; foils that accidentally slipped during forming were consistently wrinkled. Also, the forming process for polyimide is apparently very slow: we found that the shortest heat cycle that gave satisfying results took 24 hours.

Partly due to this long heating time, the copper electrodes get fully oxidized in the process. From such deep oxidation, electrodes cannot be recovered by etching. The oxidation also causes some delamination of copper from the polyimide substrate. Therefore the procedure should be carried out in an oxygen free atmosphere.

Tests performed in a gas-tight enclosure with a constant flow of argon show that oxidation can indeed be almost completely avoided. However, after forming the electrodes are covered with a loosely attached thin layer of some polymer, see figure 6. As this must be the result of outgassing of the polyimide substrate, this layer is presumably a polyimide or very similar polymer (it has the same brownish color). These deposits can be removed afterwards, but as it involves mechanical brushing or rather strong spraying this is likely to affect the spherical shape and should better be avoided.



Figure 6. Polymeric deposits on the electrode.



Figure 7. Spherical GEM made in a vacuum of ~ 10 mbar.

To avoid formation of these deposits as much as possible the procedure should be carried out in a vacuum. A test done in a moderate vacuum of ~ 10 mbar gave encouraging results, see figure 7. However, outgassing and deposition of polymers still cause the foil to stick to the mold, making it difficult to dismount the GEM from the setup without damaging it. Therefore, foils must be heated under a vacuum before they are mounted in the setup, until the outgassing process diminishes. Outgassing studies on polyimides [9] suggest that this point is reached after ~ 10 hours, at a temperature of 150°C . This procedure need not be a great complication; contrary to the spherical forming this can be done with many foils at the same time. In addition, GEMs treated in this way have such benign outgassing behavior that they can be used in *sealed* detectors, where the gas is not flowing [10]. This opens the way to use more efficient gases such as xenon (see figure 1), which would otherwise be prohibitively expensive.

3. Properties of spherical GEMs

GEMs bent with the methods described above hold high voltages up to ~ 650 V in air with a few nA leakage current, just like before the forming procedure. When discharges occur, they are randomly distributed over the area of the foil. This suggests that deformations due to the change in shape are spread homogeneously over the foil. Observing holes at various locations on a spherical GEM

through a microscope confirms that, although they must have become wider, their shape has not become elliptical.

Assuming homogeneous stretching, one can estimate the change in relevant dimensions. The active area of the foil before (flat) and after stretching (curved) is:

$$A_{\text{flat}} = \frac{\pi d^2}{4} = \pi r^2 \sin^2 \theta_{1/2} \quad (3.1)$$

$$A_{\text{curved}} = 2\pi \int_0^{\theta_{1/2}} r^2 \sin \theta d\theta = 2\pi r^2 (1 - \cos \theta_{1/2}) \quad (3.2)$$

Where r is the radius of curvature of the sphere, and $\theta_{1/2}$ is half the opening angle as indicated in figure 3. Then the surface stretching factor is:

$$\frac{A_{\text{curved}}}{A_{\text{flat}}} = 2 \frac{1 - \cos \theta_{1/2}}{1 - \cos^2 \theta_{1/2}} \quad (3.3)$$

It depends only on the opening angle. If we substitute the numbers from figure 3, we obtain 10.7% and 24.9% of increase in area for the left and right detectors respectively.

These stretching factors will have an effect on the aspect ratio of GEM holes (defined as *depth/width* of a hole), which in turn influences the amplifying behavior of the GEM. The change in width of a hole is proportional to the square root of the stretching factor, and the change in depth is inversely proportional to the stretching factor. This results in aspect ratios reduced to 86% and 72% respectively, compared to their state before forming. This will be compensated by changing the diameter and pitch of holes from the standard 140/70 microns to 120/60 and 100/50 microns respectively.

Another effect to be taken into account is the increase in capacitance of a foil due to stretching, as this will also increase the power generated in a discharge. As the area of the foil increases with the stretching factor, the thickness of the dielectric decreases with the same factor. Hence the capacitance increases with the square of the stretching factor: 23% and 56% respectively.

4. Work in progress

At the time of writing the detectors shown in figure 3 are in the design phase. Simulation studies are being made to understand the charge transfer between the spherical GEM and the flat readout board (figure 3, left). For instance, figure 8 shows how the electrostatic field just below the spherical GEM decreases at wider angle. This is the extraction field for secondary electrons from the holes, which influences the effective gain of the GEM. The resulting θ -dependence of the gain can be corrected for numerically.




Figure 8. Extraction field versus angle for the spherical GEM with planar readout of figure 3.

The field quality in the drift region is more critical, as the elimination of the parallax error depends on it. Therefore a spherical field cage is designed to maintain a good radial field until the edge of the active area. This field cage is a conical enclosure



Figure 9. A conical field cage made from a multilayer PCB.

of the conversion region, and will be made from a standard multilayer PCB. A resistive divider will define the voltages supplied to each layer. It will also serve as a rigid mechanical fixture to which the GEM can be glued, and as a high voltage distributor which supplies the GEM. The use of spacers in the drift region is considered, in case the spherical GEM is not sufficiently self-supporting.




Figure 10. Principle of spiral-pattern readout structure for a spherical gas detector.

In order to arrive at a fully spherical detector, a spherical readout board must be developed. This is a considerable technical challenge, as many possibilities are excluded: vias will crack, adhesives for multi-laminates do not support the high forming temperatures, standard rigid substrates cannot be formed like GEMs. We foresee a strip readout in a spiral pattern, where strips printed on top and bottom of a GEM-like structure are mutually orthogonal (i.e. clockwise and counter-clockwise spirals), see figure 10. The sharing of charge between top and bottom strips can be tuned by varying a low voltage between the sides.

5. Conclusions and outlook

We have shown that it is feasible to make spherical GEMs, using a reasonably inexpensive method. Many forming tests have been done to gain a good understanding of the parameters that lead to satisfying results, in a reproducible way. The GEMs made this way hold high voltage with the same low leakage as ordinary flat foils. They will soon be tested with a spherical cathode and a planar readout structure.

The next challenge will be to develop a spherical readout board and make a fully spherical detector. Detailed designs have already been prepared for this detector (see figure 11), which will be the first entirely parallax free gas detector.



Figure 11. 3D design of a spherical triple GEM detector from various points of view. The spherical active area has a diameter of ~ 17 cm, the whole structure is ~ 40 cm high.

References

- [1] E. Storm and H.I. Israel, *Photon cross sections from 1 keV to 100 MeV for elements Z=1 to Z=100*. Nuclear Data Tables, A7, 1970, 565–681.
- [2] J.K. Black et al., *The imaging x-ray detector for Lobster-ISS*. Nucl. Inst. & Meth. A, vol. 513, 2003, pp. 123–126.
- [3] Z. Hajduk, G. Charpak, A. Jeavons, R. Stubbs, *The spherical drift chamber for x-ray imaging applications*. Nucl. Inst. & Meth. I22, 1974, pp. 307–312.
- [4] P.F. Christie, E. Mathieson and K.D. Evans, *An x-ray imaging proportional chamber incorporating a radial field drift chamber*. Journal of Physics E: Scientific Instruments, vol. 9, 1976, pp. 673–676.
- [5] S.P. Chernenko et al., *Test results of the parallax-free x-ray area detector CD-1000 in the diffractometer CARD-7*. Nucl. Inst. & Meth. A, vol. 367, 1995, pp. 76–78.
- [6] Y. Diawara et al., *A parallel-plate resistive-anode gaseous detector for x-ray imaging*. IEEE transactions on nuclear science, vol. 51, June 2004.
- [7] P. Rehak, G.C. Smith, B.Yu, *a method for reduction of parallax broadening in gas-based position sensitive detectors*. IEEE transactions on nuclear science, Vol. 44, June 1997.
- [8] F. Sauli, *GEM: A new concept for electron amplification in gas detectors*. Nucl. Inst. & Meth. A, vol. 386, issues 2–3, 21/2/1997, pp. 531–534.
- [9] K. Kurvinen et al., *Outgassing analysis of various detector materials*. IEEE-NSS 2003 conference record, vol. 5, pp. 3726–3730. DOI:10.1109/NSSMIC.2003.1352716.
- [10] K. Kurvinen et al., *GEM detectors for x-ray astronomy*. Nucl. Instr. & Meth. A, vol. 513, issues 1–2, 1 November 2003, pp. 155–158. DOI:10.1016/j.nima.2003.08.022.