## Bruggeman formalism vs. 'Bruggeman formalism': Particulate composite materials comprising oriented ellipsoidal particles

Tom G. Mackay<sup>1</sup>

School of Mathematics and Maxwell Institute for Mathematical Sciences University of Edinburgh, Edinburgh EH9 3JZ, UK

and

NanoMM — Nanoengineered Metamaterials Group Department of Engineering Science and Mechanics Pennsylvania State University, University Park, PA 16802–6812, USA

Akhlesh Lakhtakia<sup>2</sup>

NanoMM — Nanoengineered Metamaterials Group Department of Engineering Science and Mechanics Pennsylvania State University, University Park, PA 16802, USA

## Abstract

Two different formalisms for the homogenization of composite materials containing oriented ellipsoidal particles of isotropic dielectric materials are being named after Bruggeman. Numerical studies reveal clear differences between the two formalisms which may be exacerbated: (i) if the component particles become more aspherical, (ii) at mid-range values of the volume fractions, and (iii) if the homogenized component material is dissipative. The correct Bruggeman formalism uses the correct polarizability density dyadics of the component particles, but the other formalism does not.

keywords: Bruggeman homogenization formalism, homogenized composite materials, ellipsoidal particles

The Bruggeman formalism provides a well-established technique for estimating the effective constitutive parameters of homogenized composite materials (HCMs) [1, 2, 3]. The scope of its applicability is not restricted to dilute composite materials and it is easy to implement numerically, both of which contribute to its enduring popularity.

The Bruggeman formalism was originally devised for isotropic dielectric HCMs, comprising two (or more) isotropic dielectric component materials distributed randomly as electrically small spherical particles [4]. Generalizations of the Bruggeman formalism which accommodate anisotropic and bianisotropic HCMs have been developed [5]. A rigorous basis for the Bruggeman formalism—for isotropic dielectric [6], anisotropic dielectric [7, 8], and bianisotropic [9, 10] HCMs—is provided by the strong-property-fluctuation theory, whose lowest-order formulation is the Bruggeman formalism.

Our focus in this letter is on HCMs arising from two isotropic dielectric component materials, labeled a and b. Their relative permittivities are  $\epsilon^a$  and  $\epsilon^b$ , while their volume fractions are  $f_a$  and  $f_b \equiv 1 - f_a$ . Both component materials are assumed to be randomly distributed as electrically small ellipsoidal particles. For simplicity, all component particles have the same shape and orientation. The surface of each ellipsoid,

<sup>&</sup>lt;sup>1</sup>E-mail: T.Mackay@ed.ac.uk

<sup>&</sup>lt;sup>2</sup>E–mail: akhlesh@psu.edu

relative to its centroid, may be represented by the vector

$$\underline{r}_{e}(\theta,\phi) = \eta \, \underline{U} \, \bullet \, \underline{\hat{r}}(\theta,\phi), \tag{1}$$

with  $\underline{\hat{r}}$  being the radial unit vector from the ellipsoid's centroid, specified by the spherical polar coordinates  $\theta$  and  $\phi$ . The linear dimensions of each ellipsoid, as determined by the parameter  $\eta$ , are assumed to be small relative to the electromagnetic wavelength(s). Let us choose our coordinate system to be such that the Cartesian axes are aligned with the principal axes of the ellipsoids. Then the ellipsoidal shape is captured by the dyadic

$$\underline{\underline{U}} = U_x \, \underline{\hat{x}} \, \underline{\hat{x}} + U_y \, \underline{\hat{y}} \, \underline{\hat{y}} + U_z \, \underline{\hat{z}} \, \underline{\hat{z}},\tag{2}$$

wherein the shape parameters  $U_{x,y,z} > 0$  and  $\{\underline{\hat{x}}, \underline{\hat{y}}, \underline{\hat{z}}\}$  are unit vectors aligned with the Cartesian axes.

The ellipsoidal shape of the component particles results in the corresponding HCM being an orthorhombic biaxial dielectric material. That is, the Bruggeman estimate of the HCM relative permittivity dyadic has the form

$$\underline{\underline{\epsilon}}^{Br1} = \epsilon_x^{Br1} \underline{\hat{x}} \underline{\hat{x}} + \epsilon_y^{Br1} \underline{\hat{y}} \underline{\hat{y}} + \epsilon_z^{Br1} \underline{\hat{z}} \underline{\hat{z}}.$$
(3)

The relative permittivity parameters  $\epsilon_{x,y,z}^{Br1}$  are given implicitly by the three coupled equations [11]

$$\frac{\epsilon^a - \epsilon_\ell^{Br1}}{1 + D_\ell \left(\epsilon^a - \epsilon_\ell^{Br1}\right)} f_a + \frac{\epsilon^b - \epsilon_\ell^{Br1}}{1 + D_\ell \left(\epsilon^b - \epsilon_\ell^{Br1}\right)} f_b = 0, \qquad (\ell \in \{x, y, z\}).$$

$$\tag{4}$$

Herein  $D_{\ell}$  are components of the depolarization dyadic

$$\underline{\underline{D}} = D_x \underline{\hat{x}} \, \underline{\hat{x}} + D_y \underline{\hat{y}} \, \underline{\hat{y}} + D_z \underline{\hat{z}} \, \underline{\hat{z}},\tag{5}$$

where the double integrals<sup>[5]</sup>

$$D_{x} = \frac{1}{4\pi} \int_{0}^{2\pi} d\phi \int_{0}^{\pi} d\theta \frac{\sin^{3}\theta \cos^{2}\phi}{U_{x}^{2}\rho}$$

$$D_{y} = \frac{1}{4\pi} \int_{0}^{2\pi} d\phi \int_{0}^{\pi} d\theta \frac{\sin^{3}\theta \sin^{2}\phi}{U_{y}^{2}\rho}$$

$$D_{z} = \frac{1}{4\pi} \int_{0}^{2\pi} d\phi \int_{0}^{\pi} d\theta \frac{\sin\theta \cos^{2}\theta}{U_{z}^{2}\rho}$$

$$\left.\right\}, \qquad (6)$$

involve the scalar parameter

$$\rho = \frac{\sin^2 \theta \cos^2 \phi}{U_x^2} \epsilon_x^{Br1} + \frac{\sin^2 \theta \sin^2 \phi}{U_y^2} \epsilon_y^{Br1} + \frac{\cos^2 \theta}{U_z^2} \epsilon_z^{Br1}.$$
(7)

The coupled nature of the three eqns. (4) means that numerical methods are generally needed to extract the relative permittivity parameters  $\epsilon_{x,y,z}^{Br1}$  from them. An alternative formalism for the homogenization of the same composite material as in the foregoing

An alternative formalism for the homogenization of the same composite material as in the foregoing paragraph is also referred to as the Bruggeman formalism [12, 13, 14, 15]. Let us write the estimate of the HCM's relative permittivity dyadic provided by this alternative formalism as

$$\underline{\underline{\epsilon}}^{Br2} = \epsilon_x^{Br2} \, \underline{\hat{x}} \, \underline{\hat{x}} + \epsilon_y^{Br2} \, \underline{\hat{y}} \, \underline{\hat{y}} + \epsilon_z^{Br2} \, \underline{\hat{z}} \, \underline{\hat{z}}. \tag{8}$$

The relative permittivity parameters  $\epsilon^{Br2}_{x,y,z}$  are given by the three equations

$$\frac{\epsilon^a - \epsilon_\ell^{Br2}}{\epsilon_\ell^{Br2} + L_\ell \left(\epsilon^a - \epsilon_\ell^{Br2}\right)} f_a + \frac{\epsilon^b - \epsilon_\ell^{Br2}}{\epsilon_\ell^{Br2} + L_\ell \left(\epsilon^b - \epsilon_\ell^{Br2}\right)} f_b = 0, \qquad (\ell \in \{x, y, z\}), \tag{9}$$

wherein the depolarization factors [16]

$$L_{\ell} = \frac{U_x U_y U_z}{2} \int_0^\infty ds \frac{1}{(s + U_{\ell}^2) \sqrt{(s + U_x^2) (s + U_y^2) (s + U_z^2)}}, \qquad (\ell \in \{x, y, z\})$$
(10)

are components of the depolarization dyadic

$$\underline{\underline{L}} = L_x \underline{\hat{x}} \, \underline{\hat{x}} + L_y \underline{\hat{y}} \, \underline{\hat{y}} + L_z \underline{\hat{z}} \, \underline{\hat{z}}.$$
(11)

Each of the three eqns. (9) is a quadratic equation in  $\epsilon_{\ell}^{Br2}$  whose solution may be explicitly expressed as

$$\epsilon_{\ell}^{Br2} = \frac{-\beta \pm \sqrt{\beta^2 - 4\alpha\gamma}}{2\alpha}, \qquad (\ell \in \{x, y, z\}), \tag{12}$$

with  $\alpha = L_{\ell} - 1$ ,  $\beta = \epsilon^a (f_a - L_{\ell}) + \epsilon^b (f_b - L_{\ell})$ , and  $\gamma = L_{\ell} \epsilon^a \epsilon^b$ . The sign of the square root term in the solution (12) may be determined by appealing to the anisotropic dielectric generalization of the Hashin–Shtrikman bounds [17], for example.



Figure 1: The estimates  $\epsilon_x^{Br1,2}$  (blue, dashed curves),  $\epsilon_y^{Br1,2}$  (green, solid curves), and  $\epsilon_z^{Br1,2}$  (red, broken dashed curves) plotted versus the asphericity parameter  $\Delta \in (0, 4.5)$ . The  $\epsilon_{x,y,z}^{Br1}$  estimates are represented by thick curves and the  $\epsilon_{x,y,z}^{Br2}$  estimates are represented by thin curves. The ellipsoidal shapes of the component material particles are described by shape parameters  $U_x = 1$ ,  $U_y = 1 + (\Delta/3)$ , and  $U_z = 2\Delta$ . The relative permittivities of the component materials are  $\epsilon^a \in \{0.5, 1.5\}$  and  $\epsilon^b = 12$ ; and the volume fraction  $f_a = 0.5$ .



Figure 2: As Fig. 1 except that  $\Delta = 4.5$  and the estimates  $\epsilon_{x,y,z}^{Br1,2}$  are plotted versus the volume fraction  $f_a \in (0,1)$ .



Figure 3: As Fig. 1 except that  $\Delta = 4.5$ ,  $\epsilon^a \in \{0.5 + i\delta, 1.5 + i\delta\}$ , and the real and imaginary parts of the estimates  $\epsilon_{x,y,z}^{Br1,2}$  are plotted versus the dissipation parameter  $\delta \in (0,2)$ .

Let us illustrate the differences between the estimates  $\underline{\epsilon}^{Br1}$  and  $\underline{\epsilon}^{Br2}$  by means of some representative numerical results. Suppose that the shape parameters describing the component ellipsoids have the form  $U_x = 1, U_y = 1 + (\Delta/3)$ , and  $U_z = 2\Delta$ . Thus, the asphericity of the ellipsoids is governed by the scalar parameter  $\Delta$ . We begin with the nondissipative scenario wherein  $\epsilon^a \in \{0.5, 1.5\}$  and  $\epsilon^b = 12$ . Also, we fix  $f_a = 0.5$ . Plots of the relative permittivity parameters  $\epsilon^{Br1,Br2}_{x,y,z}$  versus the asphericity parameter  $\Delta$ are presented in Fig. 1. The estimates  $\underline{\epsilon}^{Br1}$  and  $\underline{\epsilon}^{Br2}$  are identical for the limiting case represented by  $U_x = U_y = U_z = 1$  (i.e., for isotropic dielectric HCMs), but differences emerge as the asphericity of the component particles intensifies. The difference between  $\epsilon^{Br1}_x$  and  $\epsilon^{Br2}_x$  grows steadily as  $\Delta$  increases, reaches a maximum for  $1 < \Delta < 2$ , and then slowly shrinks as  $\Delta$  increases beyond 2. The difference between  $\epsilon^{Br1}_z$  and  $\epsilon^{Br2}_z$  follows a similar pattern. However, in the case of  $\epsilon^{Br1}_y$  and  $\epsilon^{Br2}_y$ , the difference increases uniformly as  $\Delta$  increases. The differences between  $\epsilon^{Br1}_{x,y,z}$  are generally greater for  $\epsilon^a = 0.5$  than for  $\epsilon^a = 1.5$ . In the former case the maximum difference is approximately 15%, whereas in the latter case it is approximately 5%.

We turn now to the effect of volume fraction. The calculations of Fig. 1 are repeated for Fig. 2 except that here the relative permittivity parameters  $\epsilon_{x,y,z}^{Br1,Br2}$  are plotted versus the volume fraction  $f_a$ , while the asphericity parameter is fixed at  $\Delta = 4.5$ . The differences between the estimates of the two formalisms are clearly greatest at mid-range values of  $f_a$ , and they are generally greater for  $\epsilon^a = 0.5$  than for  $\epsilon^a = 1.5$ .

Lastly, the effects of dissipation are considered. We repeated the calculations of Fig. 1 but with  $\Delta = 4.5$ and  $\epsilon^a \in \{0.5 + i\delta, 1.5 + i\delta\}$ . Here  $\delta > 0$  governs the degree of dissipation exhibited by component material a. The real and imaginary parts of the relative permittivity parameters  $\epsilon^{Br1,Br2}_{x,y,z}$  are plotted versus the dissipation parameter  $\delta$  in Fig. 3. The differences between the real parts of the estimates  $\epsilon^{Br1}_{x,y,z}$  and  $\epsilon^{Br2}_{x,y,z}$  are largest when component material a is nondissipative and they decrease uniformly as  $\delta$  increases. In contrast, the differences between the imaginary parts of the estimates  $\epsilon^{Br1}_{x,y,z}$  increase as  $\delta$  increases. These differences in the imaginary parts generally reach a maximum for mid-range values of  $\delta$  and thereafter decrease as  $\delta$  increases. For both the real and imaginary parts of the estimates  $\epsilon^{Br1}_{x,y,z}$  and  $\epsilon^{Br2}_{x,y,z}$ , generally larger differences arise for  $\epsilon^a = 0.5 + \delta i$  than for  $\epsilon^a = 1.5 + \delta i$ .

Thus, there are significant differences between the estimates  $\underline{\epsilon}^{Br1}$  and  $\underline{\epsilon}^{Br2}$  when ellipsoidal component particles are considered. These differences may be exacerbated: (i) if the component particles become more aspherical, (ii) at mid-range values of the volume fractions of the component materials, and (iii) if the HCM is dissipative. The differences between the two estimates may be further exacerbated if one of the component materials has a positive-valued relative permittivity which is less than unity (or a relative permittivity whose real part is positive-valued and less than unity).<sup>3</sup> Relative permittivities in this range are associated with novel materials possessing engineered nanostructures; these artificial materials have been the subject of intense research lately [19, 20, 21].

The differences between the two formalisms stem from the differences between the depolarization dyadics  $\underline{\underline{D}}$  and  $\underline{\underline{L}}$ . The Bruggeman formalism conceptually employs an average–polarizability–density approach [22]: Suppose the composite material has been homogenized into an HCM. Into this HCM, let the particles of the two component materials be dispersed in such a way as to maintain the overally volume fractions of a and b. But this dispersal must not change the effective properties of the HCM. In computing the polarizability density dyadic of each particle, it must therefore be assumed that the particle is surrounded by the HCM. This fact legitimizes the use of  $\underline{\underline{D}}$ , which indeed contains the anisotropic HCM's effective constitutive properties via the scalar  $\rho$  of eqn. (7). On the other hand, use of  $\underline{\underline{L}}$  to compute the polarizability density dyadic of a particle implies that it is surrounded by an isotropic HCM, which is clearly incorrect. Indeed, the alternative formalism that delivers  $\underline{\underline{e}}^{Br2}$  is an extrapolation of the Bruggeman formalism for isotropic dielectric HCMs [12, 13], and it lacks the rigorous basis that underpins the estimate of  $\underline{\underline{e}}^{Br1}$ .

We have thus delineated the differences between the two formalisms and identified one of them as the correct Bruggeman formalism. We hope that this exposition will prevent confusion between the two formalisms from perpetuating.

## References

- L. Ward, The Optical Constants of Bulk Materials and Films, 2nd ed., Institute of Physics, Bristol, UK (2000).
- [2] A. Lakhtakia, Ed., Selected Papers on Linear Optical Composite Materials, SPIE Optical Engineering Press, Bellingham, WA (1996).
- [3] T. G. Mackay, "Effective constitutive parameters of linear nanocomposites in the long-wavelength regime," J. Nanophoton. 5, 051001 (2011) [doi:10.1117/1.3626857].
- [4] D.A.G. Bruggeman, "Berechnung verschiedener physikalischer Konstanten von heterogenen Substanzen, I. Dielektrizitätskonstanten und Leitfähigkeiten der Mischkörper aus isotropen Substanzen," Ann. Phys. Lpz. 24, 636–679 (1935). (Reproduced in [2]).
- W. S. Weiglhofer, A. Lakhtakia, and B. Michel, "Maxwell Garnett and Bruggeman formalisms for a particulate composite with bianisotropic host medium," *Microw. Opt. Technol. Lett.* 15, 263–266 (1997) [doi:10.1002/(SICI)1098-2760(199707)15:4<263::AID-MOP19>3.0.CO;2-8 ]; erratum: *Microw. Opt. Technol. Lett.* 22, 221 (1999) [doi:10.1002/(SICI)1098-2760(19990805)22:3<221::AID-MOP21>3.0.CO;2-R].
- [6] L. Tsang and J. A. Kong, "Scattering of electromagnetic waves from random media with strong permittivity fluctuations," *Radio Sci.* 16, 303–320 (1981). (Reproduced in [2]).

 $<sup>^{3}</sup>$ The parameter regime wherein one of the component materials has a positive-valued relative permittivity while the other has a negative-valued relative permittivity (or likewise for the real parts of the relative permittivities in the case of dissipative HCMs) is avoided here because the Bruggeman formalism can deliver estimates in this regime which are not physically plausible [18].

- [7] Z. D. Genchev, "Anisotropic and gyrotropic version of Polder and van Santen's mixing formula," Waves Random Media 2, 99–110 (1992)<sup>4</sup> [doi:10.1088/0959-7174/2/2/001].
- [8] N. P. Zhuck, "Strong-fluctuation theory for a mean electromagnetic field in a statistically homogeneous random medium with arbitrary anisotropy of electrical and statistical properties," *Phys. Rev. B* 50, 15636–15645 (1994) [doi:10.1103/PhysRevB.50.15636].
- [9] T. G. Mackay, A. Lakhtakia, and W. S. Weiglhofer, "Strong-property-fluctuation theory for homogenization of bianisotropic composites: formulation," *Phys. Rev. E* 62, 6052– 6064 (2000) [doi:10.1103/PhysRevE.62.6052]; corrections: *Phys. Rev. E* 63, 049901 (2001) [doi:10.1103/PhysRevE.63.049901].
- [10] T. G. Mackay, A. Lakhtakia, and W. S. Weiglhofer, "Third-order implementation and convergence of the strong-property-fluctuation theory in electromagnetic homogenisation," *Phys. Rev. E* 64, 066616 (2001) [doi:10.1103/PhysRevE.64.066616].
- T. G. Mackay and A. Lakhtakia, "Electromagnetic fields in linear bianisotropic mediums," Prog. Optics 51, 121–209, (2008) [doi:10.1016/S0079-6638(07)51003-6].
- [12] G. B. Smith, "Effective medium theory and angular dispersion of optical constants in films with oblique columnar structure," Opt. Commun. 71, 279–284 (1989) [doi:10.1016/0030-4018(89)90008-4]. (Reproduced in [2]).
- [13] C. G. Granqvist, D. Le Bellac, and G. A. Niklasson, "Angular selective window coatings: Effective medium theory and experimental data on sputter-deposited films," *Renewable Energy* 8, 530–539 (1996) [doi: 10.1016/0960-1481(96)88913-0]
- [14] D. Schmidt, E. Schubert, and M. Schubert, "Optical properties of cobalt slanted columnar thin films passivated by atomic layer deposition," *Appl. Phys. Lett.* 100, 011912 (2012) [doi: 10.1063/1.3675549].
- [15] T. Hofmann, D. Schmidt, A. Boosalis, P. Kühne, R. Skomski, C. M. Herzinger, J. A. Woollam, M. Schubert, and E. Schubert, "THz dielectric anisotropy of metal slanted columnar thin films," *Appl. Phys. Lett.* **99**, 081903 (2011) [doi: 10.1063/1.3626846].
- [16] D. Polder and J. H. van Santen, "The effective permeability of mixtures of solids, *Physica* 12, 257–271 (1946). (Reproduced in [2]).
- [17] Z. Hashin and S. Shtrikman, "A variational approach to the theory of the effective magnetic permeability of multiphase materials," J. Appl. Phys. 33, 3125–3131 (1962) [doi:10.1063/1.1728579]. (Reproduced in [2]).
- [18] T. G. Mackay, "On the effective permittivity of silver-insulator nanocomposites," J. Nanophoton. 1, 019501 (2007) [doi:10.1117/1.2472372].
- [19] A. Alù, M. Silveirinha, A. Salandrino, and N. Engheta, "Epsilon-near-zero metamaterials and electromagnetic sources: Tailoring the radiation phase pattern," *Phys. Rev. B* 75, 426–432 (2007) [doi:10.1103/PhysRevB.75.155410].
- [20] G. Lovat, P. Burghignoli, F. Capolino, and D. R. Jackson, "Combinations of low/high permittivity and/or permeability substrates for highly directive planar metamaterial antennas," *IET Microw. An*tennas Propagat. 1, 177–183 (2007) [doi:10.1049/iet-map:20050353].
- [21] M. N. Navarro-Cía, M. Beruete, I. Campillo, and M. Sorolla, "Enhanced lens by  $\epsilon$  and  $\mu$  nearzero metamaterial boosted by extraordinary optical transmission," *Phys. Rev. B* 83, 115112 (2011) [doi:10.1103/PhysRevB.83.115112].

 $<sup>^{4}</sup>$ The formula of Polder and van Santen, for the effective relative permittivity of an isotropic dielectric HCM, yields the same results as the formula of Bruggeman [4].

[22] B. M. Ross and A. Lakhtakia, "Bruggeman approach for isotropic chiral mixtures revisited," Microw. Opt. Technol. Lett. 44, 524–527 (2005) [doi:10.1002/mop.20685].