Band gap tuning and orbital mediated electron – phonon coupling in HoFe_{1-x}Cr_xO₃ ($0 \le x \le 1$)

Ganesh Kotnana¹ and S. Narayana Jammalamadaka^{1*}

¹Magnetic Materials and Device Physics Laboratory, Department of Physics, Indian Institute of Technology Hyderabad, Hyderabad, India – 502 205.

*Corresponding author: surya@iith.ac.in

Abstract:

We report on the evidenced orbital mediated electron – phonon coupling and band gap tuning in HoFe_{1-x}Cr_xO₃ ($0 \le x \le 1$) compounds. From the room temperature Raman scattering, it is apparent that the electron-phonon coupling is sensitive to the presence of both the Fe and Cr at the B-site. Essentially, an Ag like local oxygen breathing mode is activated due to the charge transfer between Fe³⁺ - Cr³⁺ at around 670 cm⁻¹, this observation is explained on the basis of Franck-Condon (FC) mechanism. Optical absorption studies infer that there exists a direct band gap in the HoFe_{1-x}Cr_xO₃ ($0 \le x \le 1$) compounds. Decrease in band gap until x = 0.5 is ascribed to the broadening of the oxygen *p* - orbitals as a result of the induced spin disorder due to Fe³⁺ and Cr³⁺ at B-site. In contrast, the increase in band gap above x = 0.5 is explained on the basis of the reduction in the available unoccupied *d* - orbitals of Fe³⁺ at the conduction band. We believe that above results would be helpful for the development of the optoelectronic devices based on the ortho-ferrites.

Key words: Charge transfer, electron phonon coupling, optical absorption, band gap tuning PACS: 63., 63.20.-e, 63.20.kd, 71.35.Cc, 71.20.Nr

Introduction:

The band gap engineering may play a significant role in the future spin-photonic and ultraviolet (UV) photonic devices such as laser diodes, solar blind UV photo-detectors lightemitting diodes (LED), and transparent electronic devices. In order to fulfil the above requirement, there is a quest for development of the new materials and engineer the band gap selectively based on the requirement. In search of the new materials, materials based on the rare earth ortho-ferrites RFeO₃ (R - rare earth metal and the Fe - transition metal) have appealed continued experimental and theoretical interest as a result of their impressive magnetic and structural changes¹⁻³. Technologically these ortho – ferrites have gained much attention in solid oxide fuel cells⁴, magneto optic devices⁵, gas sensors⁶ and for the detection of ozone in monitoring environment⁷. On top of that these compounds also have much potential for the photocatalytic activity⁸ and the multiferroic behaviour⁹.

Electron – lattice dynamics are very important in the rare earth-transition metal oxides to understand the phenomenon of the colossal magnetoresistance¹⁰. On the other hand, exploring the correlation between the structural, magnetic and orbital ordering is very much essential to understand the charge transfer mechanism which is base for the electron – phonon coupling¹¹. It has been believed that in the cubic perovskites, due to the distortion of the lattice, symmetry of the structure lowers and this leads to the appearance of the Raman-active phonons¹². The influence of the electronic configuration and orbital ordering on the Raman spectra of these distorted perovskites has been addressed by Allen *et. al.*¹³. Local oxygen breathing mode in the Raman scattering has been observed in the distorted perovskite compound based on the mixed Fe and Cr ions at B – site. Such intriguing phenomenon has been explained on the basis of the Franck-Condon picture following a photon induced transfer of an electron from Fe to adjacent Cr ion¹¹. Similar behaviour has been observed on the other compound La_{1-v}Sr_vMn_{1-x}M_xO₃ (M=Cr, Co, Cu, Zn, Sc or Ga)¹⁴. To our knowledge,

until now the electron - phonon coupling has been observed only in the Jahn – Teller active compounds. However, it would be very interesting if we can observe the electron - phonon coupling in the Jahn – Teller inactive compound. For this purpose we choose the HoFeO₃ which is a Jahn – Teller inactive and may become Jahn – Teller active by substituting Cr. We anticipate that electron transfer mechanism can takes place from the Fe site to the Cr site when the incident photon energy equals to the ground state energy gap between Fe³⁺ and Cr³⁺

Interestingly, HoFeO₃ has been believed to possess the canted G-type antiferromagnetism and a potential candidate for the ultrafast recording¹⁶ with a magnetic ordering temperature around 641 K¹⁷. On the other hand, the rare earth ortho-chromites of the formula RCrO₃ (R = Ho, Er, Yb, Lu, Y) have been believed to exhibit the multiferroicity with a canted antiferromagnetic behaviour in the temperature range of 113-140 K (T_N) and a dielectric transition in the temperature range of 472 - 516 K¹⁸. In contrary, ortho-ferrites and orthochromites have been believed to possess a p – type semiconducting behaviour¹⁹, which may be very much useful in developing the optoelectronic devices. However, to the best of our knowledge, detailed information on the band gap values is not available in the literature neither on the HoFeO₃ nor on the HoCrO₃. In addition, it would also be of great interest to monitor the change in the band gap value by applying the chemical pressure either at the Fe site or the Cr site. To achieve our goal, in the present work, Cr is chosen to apply the chemical pressure at the Fe-site in HoFeO₃. Essentially, the fact that both the Fe and Cr are having same ionic state (in 3⁺ valence state) and the smaller ionic radius of the Cr³⁺ compared with the Fe³⁺ may influence the optical properties by occupying the octahedral Fe³⁺ site.

As x - rays and the Raman scattering are very much sensitive for the structural changes and the local environment in an unit cell respectively, one can get precise information about the atomic positions and information about the Raman active modes. Hence, the first aim of our manuscript is to study the interplay between the electron and lattice dynamics using the Raman scattering in the HoFe_{1-x}Cr_xO₃ [x = 0, 0.25, 0.5, 0.75 and 1]. Secondly, we also would like to understand how the band gap value varies by applying the chemical pressure at Fe site.

Experimental Details:

Polycrystalline compounds of HoFe_{1-x}Cr_xO₃ ($0 \le x \le 1$) were prepared by the conventional solid state reaction method. High purity oxide powders of Ho₂O₃, Fe₂O₃, and Cr₂O₃ (purity > 99.9%) (Sigma-Aldrich chemicals India) were used as starting raw materials and were mixed together in stoichiometric ratios. The mixture thus obtained was thoroughly and repeatedly ground in the isopropanol alcohol using an agate mortar and pestle to ensure the homogeneity. Pellets were prepared using the resultant powder and sintered sequentially at 1000°C for 12 h, 1200°C for 12 h and 1250°C for 24 h respectively. The phase purity or the structural analysis was carried out at room temperature using the powder x - ray diffraction (XRD) (Panalytical X-ray diffractometer) with Cu K_a radiation ($\lambda = 1.5406$ Å) and with a step size of 0.017° in the wide range of the Bragg angles 20 (20° - 80°). Raman spectra was measured at room temperature using the powder (Bruker, Senterra) with an excitation source of 535 nm and with a power of 10 mW. Optical absorbance of the samples were measured at room temperature using the Perkin Elmer Lambda 1050 UV-Vis-NIR spectrophotometer in the wavelength range of 200 – 800 nm.

Results and Discussion:

Phase purity of the HoFe_{1-x}Cr_xO₃ ($0 \le x \le 1$) compounds is confirmed with the room temperature XRD. Intense reflections that are present in Fig. 1 are allowed reflections for a GdFeO₃ type disordered pervoskite structure described by the orthorhombic with a space group of the Pbnm. We do not see any impurity phase apart from the parent phase within the detectable limits of the XRD. In order to get more insights about the structural aspects, we

also have performed the Rietveld refinement using the General Structural Analysis System $(GSAS)^{20}$. Information extracted from the refinement is depicted in the Table. 1. From the Rietveld refinement data, small χ^2 values of all the compounds infer that there exists a good agreement between the observed and the calculated diffraction patterns. As it is evident from the Fig. 2(a) that extracted lattice parameter values from the refinement indicates a tendency towards decrement, which is consistent with the fact that the ionic radius of the Fe³⁺ (0.645 Å) is larger than that of the Cr³⁺ (0.615 Å)²¹. It is worth noting that the change in the position and the shape of the diffraction peaks with Cr concentration is minimal, hinting that there exists no structural transformation as a result of the Cr dopants. This mismatch in ionic radii can leads to a distortion of the lattice and such distortion can be quantified using the Goldschmidt's tolerance factor (GTF). In general, the GTF can be defined as

$$t = \frac{r_A + r_O}{\sqrt{2}(r_B + r_O)} \tag{1}$$

Where r_A , r_B , and r_O are the radii of Ho³⁺, Fe³⁺/Cr³⁺, and O²⁻ respectively, where $r_B = (1-x)r_{Fe} + xr_{Cr}$. Calculated GTF for all the compounds in the present investigation are found to be in the range of 0.848 – 0.868, the range for a compound to be in an orthorhombic structure. The variation of the GTF with respect to the Cr composition is depicted in Fig. 2(b). Upon closer observation, the GTF is found to increase as a function of the chromium content, hinting that the increase in stability and tendency towards the cubic structure upon Cr doping. We have also calculated the average tilt angle $\langle \phi \rangle$ of FeO₆ octahedral around the pseudo cubic [111] direction using the geometric relation that has been proposed by O'Keefe and Hyde²² and the two super exchange angles $\theta_1 = \text{Fe}$ (Cr)-O₁-Fe (Cr), $\theta_2 = \text{Fe}$ (Cr)-O₂-Fe (Cr). Both the above angles Fe (Cr)-O₁-Fe (Cr) and Fe (Cr)-O₂-Fe (Cr) are extracted from the structural refinement. From Fig. 2(b) it is evident that average tilt angle $\langle \phi \rangle$ of the FeO₆ octahedral decreases with an increase in Cr content. It is apparent that the tolerance factor

increases whereas the tilt angle diminishes, hinting that the internal stresses as a result of the chemical pressure (via Cr^{3+} doping) leads to a distortion of the lattice.

Table 1: Lattice parameters, cell volumes, selected bond lengths, bond angles from Rietveldrefinement of $HoFe_{1-x}Cr_xO_3$.

Compounds	HoFeO ₃	HoFe _{0.75} Cr _{0.25} O ₃	HoFe _{0.5} Cr _{0.5} O ₃	HoFe _{0.25} Cr _{0.75} O ₃	HoCrO ₃
Space group	Pbnm	Pbnm	Pbnm	Pbnm	Pbnm
Lattice Parameters					
a (A ^o)	5.28339(6)	5.27487(6)	5.26645(6)	5.25658(7)	5.25009(8)
b (A ^o)	5.59100(6)	5.57407(6)	5.55568(6)	5.53709(7)	5.51635(8)
c (A ^o)	7.60986(8)	7.59292(8)	7.57590(8)	7.55790(10)	7.54373(11)
Cell Volume (A ^{o3})	224.7909	223. 2507	221.6610	219.9814	218.4764
Selected bong angles (°)					
Fe(Cr) - O1 - Fe(Cr)	144.2(5)	144.0(5)	145.3(4)	145.8(4)	146.2(4)
Fe(Cr) - O2 - Fe(Cr)	144.7(4)	145.5(4)	144.45(33)	145.47(31)	146.13(34)
Selected bond lengths (A ^o)					
Fe(Cr) – O1	1.9990(30)	1.9959(28)	1.9840(23)	1.9767(21)	1.9708(23)
Fe(Cr) – O2	2.037(9)	2.033(8)	2.035(8)	2.015(6)	2.005(7)

Now we discuss the results pertinent to the Raman scattering which essentially gives the local structure, shift and distortion of the modes as a result of the chemical doping (here Cr^{3+} doping). In addition, we also would like to correlate our structural information with the Raman data that we obtained. For this purpose the room temperature Raman spectroscopy was used on the HoFe_{1-x}Cr_xO₃ ($0 \le x \le 1$) compounds to understand the aforesaid properties.

It has been observed that in an ideal perovskite (ABO₃), the B-site transition metal cation locates at the centre of the oxygen octahedral and A-site cation locates at the corners of the cube²³. However, due to the displacement of the crystallographic sites from the ideal cubic positions, most perovskites show the symmetry breaking which results the appearance of the Raman active modes in the Raman spectra. The rare earth ortho-ferrite HoFeO₃ is an orthorhombically distorted perovskite with a space group of D_{2h}^{16} (Pbnm). The irreducible representations corresponding to the phonon modes at the Brillouin zone center²⁴ can be defined as follows

$$7A_{g} + 7B_{1g} + 5B_{2g} + 5B_{3g} + 8A_{u} + 8B_{1u} + 10B_{2u} + 10B_{3u}$$

Here, A_g , B_{1g} , B_{2g} , B_{3g} are the Raman active mode species, B_{1u} , B_{2u} , B_{3u} are the infrared mode species and A_u is the inactive mode. Among them the modes which are above 300 cm⁻¹ are related to the vibrations of oxygen and the modes below the wave number 300 cm⁻¹ are associated with the rare earth ions²⁵. However, the Raman vibrational modes corresponding to an orthorhombic structure are: $A_g + B_{1g}$ and $2B_{2g} + 2B_{3g}$, which are symmetric and antisymmetric modes respectively; In contrast, $A_g + 2B_{1g} + B_{3g}$, $2A_g + 2B_{2g} + B_{1g} + B_{3g}$, and $3A_g + B_{2g} + 3B_{1g} + B_{2g}$ are associated with the bending modes, rotation and tilt mode of the octahedral and for the changes in the rare earth movements respectively²⁶. Fig. 3 shows results pertinent to the Raman Spectra of HoFe_{1-x}Cr_xO₃ ($0 \le x \le 1$) samples recorded at room temperature and with the wavenumber in the range of 50 to 800 cm⁻¹. Peaks with the high intensities are evident at 109, 137, 158, 337, 423 and 494 cm⁻¹ which is normal for a typical orthoferrite²⁴. Apart from aforesaid modes, a mode at 670 cm⁻¹ prevailed in the compounds with the Cr^{3+} ion. However, the peak which is evident at 670 cm⁻¹ consists very less intensity in the parent HoFeO₃ and HoCrO₃. Basically, such peak picks intensity only if we have the combination of both the Fe and Cr at the B site. Such intriguing phenomenon may be correlated to the orbital mediated electron – phonon coupling like in case of $LaFe_{1-x}Cr_xO_3^{11}$.

The Raman active modes of the samples are designated according to the method proposed by Gupta^{27} *et. al*,. The appearance of an A_g like mode with observable intensity at high frequency of around 670 cm⁻¹ can be attributed to an in-phase stretching (breathing) mode of oxygen in the close vicinity of the substituted Cr³⁺ ion. Essentially the oxygen breathing mode is activated by the charge transfer between the Fe³⁺ and Cr³⁺ through an orbital mediated electron-phonon coupling mechanism¹¹.

In HoFe_{1-x}Cr_xO₃ compounds, the ground state electron configuration of Fe³⁺ does not support orbital mediated electron-phonon coupling due to the lack of strongly interacting half-filled e_g levels in both the Fe³⁺ (d^5) and Cr³⁺ (d^3). To facilitate such an orbital mediated electronphonon coupling, the electronic configuration of Fe³⁺ must contain partially filled e_g orbital (like Fe⁴⁺) such that d^4 electron of the Fe⁴⁺ ion can move to the upper e_g levels of the Cr²⁺ to create electronic excitation as shown in LaMnO₃²⁸. Fig. 4 explains the mechanism for the orbital mediated electron-phonon coupling. The left part of Fig. 4(a) shows electronic states of Fe³⁺ and Cr³⁺ ions. v_{g,0}, v_{g,1}, v_{g,2}, ..., v_{g,n} and v_{e,0}, v_{e,1}, v_{e,2}, ..., v_{e,n} represents the vibrational states of the Fe³⁺ and the Cr³⁺ respectively. Right part of the Fig. 4(a) reveals electronic states of the Fe⁴⁺ and Cr²⁺ ions. Arrows on both Fig. 4(a) and 4(b) represents various transitions between Fe³⁺ \rightarrow Cr³⁺ and Fe⁴⁺ \rightarrow Cr²⁺ respectively.

It has been reported that the photon mediated charge transfer can takes place between the Fe^{3+} and Cr^{3+} ions upon irradiation with a laser of wavelength 535 nm^{11, 15}. In this process, the overlap between the *d*-orbitals of Cr^{2+} and the *p*-orbitals of the oxygen couples through a lattice distortion, causing a self-trapping motion. Evidently, this motion increases the lifetime of excited Cr^{2+} electronic ground state long enough to interact with the intrinsic phonon mode. Essentially, during the charge transfer mechanism (CT), when the photon energy equals to the CT energy gap between the two transition metal ions Fe^{3+} and Cr^{3+} , electrons in the Fe^{3+} excite to the Cr^{3+} ion and leaves them in a strongly coupled d^4-d^4 configuration with

the half-filled bands. The change in the charge density of e_g orbital of transition metal surrounded by the oxygen octahedral activates a breathing distortion of O_6 around the transition metal cation which appears in the Raman spectrum at around 670 cm⁻¹. This configuration is Jahn-Teller active, hence, that it leads to a volume preserving lattice distortion (δ), involves a stretching of Fe (Cr)-O bonds along *z* - direction and a compression in x-y plane. As a result of the Jahn - Teller effect, an electron in e_g orbital collapse into the lower energy state which produces a potential minimum. This minimum potential traps the electron in that orbital (self-trapping) and increases its life time in the excited Cr^{2+} state long enough for it to interact with intrinsic phonon mode/lattice distortion. In the perturbed state, indeed there exists a contraction of the oxygen octahedral surrounding to the Fe⁴⁺ ion and leads to an expansion in the adjacent octahedron surrounding to Cr^{2+} ion as shown in Fig. 4(b). The oxygen lattice relaxes back to its unperturbed state when the electron transfers back to Fe³⁺ state. In this fashion, the charge transfer of an electron from Fe³⁺ to the Cr³⁺ ion activates an oxygen breathing mode of A_g symmetry through orbital mediated electron-lattice coupling.

The increase in the intensity of the peak at around 670 cm⁻¹ is observed only in doped samples as shown in Fig. 5 (a). This effect can be related to the increase in the degree of disorder, which can be supported by an increase in the tolerance factor as a function of the Cr content. This is a striking coincidence between our structural and Raman studies. As the Cr content increases, there would indeed be an increase in the degree of disorder, which may enhance the interaction between the lattice distortion and the charges transferred between Fe³⁺ - Cr³⁺. Eventually as a result of this there would be an enhancement in the electron-phonon coupling which leads to increase in the intensity of the peak at 670 cm⁻¹. The broadening of the peak at 670 cm⁻¹ with an increase in the amount of the Cr³⁺ ions at the Fe³⁺ site can correlate with the structural disorder. This is confirmed by the observed change in the

lattice parameters by the substitution of the Cr^{3+} ions at the Fe site. The observed shift in the wave number towards the higher values (Blue shift) in the doped compounds shown in Fig 5(b) can correlate to the compressive strain produced in the compounds by the incorporation of the Cr^{3+} ion at the Fe site. This effect is supported by the change in Fe (Cr) – O bond lengths as well as FeO₆ octahedral tilt angle with respect to the chromium content at Fe site as shown in the Table **1**.

The optical absorbance of the HoFe_{1-x}Cr_xO₃ ($0 \le x \le 1$) compounds was recorded at room temperature and is shown in Fig. 6. Indeed there exists a direct band gap and the value of gap is determined using the Tauc's equation²⁹. Essentially this equation relates the optical absorption coefficient (α), photon energy (*hv*) and the energy gap E_g as given below

$$\alpha h v = \left(h v - E_g\right)^{1/2}$$

Optical band gaps of the HoFe_{1-x}Cr_xO₃ ($0 \le x \le 1$) compounds are obtained using the above equation and by extrapolating the linear region of the curve to the zero in the $(\alpha hv)^2$ vs. hv graph as shown in Fig. 7 (a). The direct band gap value for HoFeO₃ and HoCrO₃ is calculated as 2.07 eV and 3.26 eV respectively. From the Fig. 7(b) and for the compounds with the combination of Fe and Cr, it is evident that the band gap decreases with Cr content, and reached a minimum value of 1.94 eV at x = 0.5. Further increase in Cr content results in increase of the band gap value and reached a maximum value of 3.26 eV at x = 1. In order to explain the observed band gap variation we would like to propose a possible mechanism using energy diagram of HoFeO₃, HoCrO₃ and HoFe_{1-x}Cr_xO₃. Fig. 8 (a) shows the energy diagram of HoFeO₃ with the band gap value of 2.07 eV (b) the energy diagram of HoCrO₃ for which the band gap varies between 2.07 – 3. 26 eV. The variation of the band gap with Cr concentration could be due to a complex interplay between the Fe³⁺ and the Cr³⁺ electronic

levels mediated by oxygen through superexchange interaction. From the Fig. 8(c) it is evident that when x < 0.5, the valance band maxima (VBM) and conduction band minima (CBM) shifts to higher energy (dark red colour). The shift in VBM may be explained on the basis of the hybridization of *d* - orbitals of Fe and Cr with *p* - orbitals of oxygen in the valance band. Essentially, the ferrimagnetically¹⁵ coupled Fe³⁺ and Cr³⁺ induce a spin disorder on oxygen which can enhance the broadening of oxygen *p* - orbitals and valance band edges of Fe³⁺ and Cr^{3+ 30, 31}, hinting a smaller band gap until x = 0.5. When x > 0.5, the width of available un occupied *d* - orbitals of Fe³⁺ at the conduction band reduces, which can leads to a shift of the conduction band minima to higher energies (as shown in fig 8(c) (purple colour)). As a result, the band gap in HoFe_{1-x}Cr_xO₃ increases above x = 0.5 and reaches a maximum value of 3.26 eV at x = 1. From the above results, indeed it is possible to tune the band gap in rare earth ortho-ferrites and the other compounds with a similar structure by controlling the Fe/Cr ratio.

In summary, we have explored the orbital mediated electron – phonon coupling mechanism in the compounds $HoFe_{1-x}Cr_xO_3$ ($0 \le x \le 1$). There is a striking coincidence between our structural and Raman studies. Raman studies infer that, A_g like symmetric oxygen breathing mode at around 670 cm⁻¹ in the compounds with both the Fe and Cr. The decrease in optical band gap is ascribed to the induced spin disorder due to the Fe³⁺ and the Cr³⁺ on oxygen, which can leads to broadening of the oxygen *p*-orbitals. On the other hand, increase in band gap value explained on the basis of the reduction in the available unoccupied *d*-orbitals of Fe³⁺ at the conduction band. The present results would indeed be helpful in understanding and to develop optoelectronic devices based on orthoferrites.

We would like to acknowledge Indian Institute of Technology, Hyderabad and Department of Science and Technology (DST) (Project #SR/FTP/PS-190/2012) for the financial support.

References:

(1) M. Eibschütz, S. Shtrikman, and D. Treves, Phys. Rev. 156, 562 (1967).

(2) R. L. White, J. Appl. Phys. 40, 1061 (1969).

(3) N. S. Ovanesyan and V. A. Trukhtanov, JETP Lett. Engl. Transl. 17, 67 (1973).

(4) M. Gateshki, L. Suescun, S. Kolesnik, J. Mais, K. Świerczek, S. Short, B. Dabrowski, *Journal of Solid State Chemistry* **181**, 1833 (2008).

(5) N. Singh, J. Y. Rhee, S. Auluck, J. Korean Phys. Soc. 53, 806 (2008).

(6) Xiutao Ge, Yafei Liu, Xingqin Liu, Sensors and Actuators B 79, 171 (2001).

(7) Yuuki Hosoya, Yoshiteru Itagaki, Hiromichi Aono, Yoshihiko Sadaoka, *Sensors and Actuators B* **108**, 198 (2005).

(8) Xinshu Niu, Honghua Li, Guoguang Liu, *Journal of Molecular Catalysis A: Chemical*232, 89 (2005).

(9) S. Acharya, J. Mondal, S. Ghosh, S.K. Roy, P.K. Chakrabarti, *Materials Letters* 64, 415 (2010).

(10) A. P. Ramirez, J. Phys.: Condens. Matter 9, 8171 (1997).

(11) Jacob Anderasson, Joakim Holmund, Christopher S. Knee, Mikael Käll, Lars Börjesson, Stefan Naler, Joakim Bäckström, Michael Rübhausen, Abul Kalam Azad, and Sten-G. Eriksson, *Phys. Rev. B* **75**, 104302 (2007).

(12) V. Gnezdilov, P. Lemmens, Yu. G. Pashkevich, Ch. Payen, K. Y. Choi, J. Hemberger,A. Loidl, and V. Tsurkan, *Phys. Rev. B* 84, 045106 (2011).

(13) P. B. Allen and V. Perebeinos, Phys. Rev. Lett. 83, 4828 (1999).

(14) A. Dubroka, J. Humliček, M. V. Abrashev, Z. V. Popović, F. Sapiña, and A. Cantarero, *Phys. Rev. B* 73, 224401 (2006).

(15) K. Miura and K. Terakura, Phys. Rev. B 63, 104402 (2001).

(16) A. V. Kimel, B. A. Ivanov, R. V. Pisarev, P. A. Usachev, A. Kirilyuk and Th. Rasing, *Nature Physics* 5, 727 (2009).

(17) Zhiqiang Zhou, Li Guo, Haixia Yang, Qiang Liu, Feng Ye, Journal of Alloys and Compounds 583, 21 (2014).

(18) Jyoti Ranjan Sahu, Claudy Rayan Serrao, Nirat Ray, Umesh V. Waghmare and C. N. R. Rao, *J. Mater. Chem.* **17**, 42 (2007).

(19) Maike Siemons, Ulrich Simon, Sensors and Actuators B 126, 181 (2007).

(20) A.C. Larson and R.B. Von Dreele, *General Structure Analysis System* (GSAS), Los Alamos National Laboratory Report LAUR 86–748 (2004).

(21) R.D.Shannon, Acta Cryst. A 32, 751 (1976).

(22) Tapan Chatterji, Bachir Ouladdiaf, P. Mandal, B. Bandyopadhyay, and B. Ghosh, *Phys. Rev. B* 66, 054403 (2002).

(23) M. A. Peña and J. L. G. Fierro, Chem Rev. 101, 1981 (2001).

(24) S. Venugopalan, M. Dutta, A. K. Ramdas, J. P. Remeika, Phys. Rev. B 31, 1490 (1985).

(25) Manoj K. Singh, Hyun M. Jang, H. C. Gupta and Ram S. Katiyar, *J. Raman Spectrosc.***39**, 842 (2008).

(26) M. N. Iliev, M. V. Abrashev, H. -G. Lee, V. N. Popov, Y. Y. Sun, C. Thomsen, R. L. Meng, C. W. Chu, *Phys. Rev. B* 57, 2872 (1998).

(27) H. C. Gupta, Manoj Kumar Singh and L. M. Tiwari, J. Raman Spectrosc. 33, 67 (2002).

- (28) Vasili Perebeinos and Philip B. Allen, Phys. Rev. B 64, 085118 (2001).
- (29) Anders hagfeldt and Michael Grätzel, Chem. Rev. 95, 49 (1995).
- (30) T. Arima, Y. Tokura, and J.B. Torrance, Phys. Rev. B 48, 17006 (1993).
- (31) Yong Wang, Kenneth Lopata, Scott A. Chambers, Niranjan Govind, and Peter V. Sushko, J. Phys. Chem. C 117, 25504 (2013).

Figure captions

Fig. 1: Powder x-ray diffraction patterns of HoFe_{1-x}Cr_xO₃ ($0 \le x \le 1$). It is evident that all the

compounds are formed in single phase.

Fig. 2: (a) Variation of lattice parameter with Cr composition. (b) Variation of tolerance factor (circle symbol) and FeO₆ average tilt angle (square symbol) with Cr composition.

Fig. 3: Room temperature Raman spectra of $HoFe_{1-x}Cr_xO_3$ ($0 \le x \le 1$) compounds with an excitation of 535 nm.

Fig. 4: (a) Franck-Condon (FC) mechanism for Jahn-Teller active perovskites. $v_{g,0}$, $v_{g,1}$, $v_{g,2}$, ..., $v_{g,n}$ and $v_{e,0}$, $v_{e,1}$, $v_{e,2}$, ..., $v_{e,n}$ represents the vibrational states of Fe³⁺ and Cr³⁺ respectively. For FC mechanism to happen for a vibrational mode, the virtual state $|v_r\rangle$ of Raman process must coincide with any vibrational state of electronically excited state. δ indicates lattice distortion due to Jahn - Teller effect as a result of charge transfer mechanism (b) Octahedral sites of Fe⁴⁺ and Cr²⁺ respectively. Dotted arrow in the figure indicates charge transfer mechanism and lattice relaxation.

Fig. 5: (a) Intensity variation of A_g peak and (b) wave number shift of A_g peak for the HoFe₁₋ $_x$ Cr_xO₃ (0 ≤ x ≤ 1) compounds.

Fig. 6: Absorption spectra of HoFe_{1-x} Cr_xO_3 ($0 \le x \le 1$) compounds.

Fig. 7: (a) Tauc's plots to determine the band gap values of $HoFe_{1-x}Cr_xO_3$ ($0 \le x \le 1$) compounds. (b) Variation of the band gap with respect to Cr composition.

Fig. 8: (a) Shows the energy diagram of HoFeO₃ (b) Energy diagram of HoCrO₃ (c) probable energy diagram for HoFe_{1-x}Cr_xO₃. It is evident from the frame (c) that when x < 0.5, the valance band maxima (VBM) and conduction band minima (CBM) shifts to higher energy (dark red color). However, the shift in VBM is due to strong hybridization of d orbitals of Fe & Cr with *p* - orbitals of oxygen in valance band. When x > 0.5, band gap is dominated by unoccupied *d* - orbitals of Cr in conduction band which leads to increase in band gap (purple color).



Fig. 1: Powder x-ray diffraction patterns of $HoFe_{1-x}Cr_xO_3$ ($0 \le x \le 1$). It is evident that all the compounds are formed in single phase.



Fig. 2: (a) Variation of lattice parameter with Cr composition. (b) Variation of tolerance factor (circle symbol) and FeO_6 average tilt angle (square symbol) with Cr composition.



Fig. 3: Room temperature Raman spectra of $HoFe_{1-x}Cr_xO_3$ ($0 \le x \le 1$) compounds with an excitation of 535 nm.



Fig. 4: (a) Franck-Condon (FC) mechanism for Jahn-Teller active perovskites. $v_{g,0}$, $v_{g,1}$, $v_{g,2}$, ..., $v_{g,n}$ and $v_{e,0}$, $v_{e,1}$, $v_{e,2}$, ..., $v_{e,n}$ represents the vibrational states of Fe³⁺ and Cr³⁺ respectively. For FC mechanism to happen for a vibrational mode, the virtual state $|v_r\rangle$ of Raman process must coincide with any vibrational state of electronically excited state. δ indicates lattice distortion due to Jahn - Teller effect as a result of charge transfer mechanism (b) Octahedral sites of Fe⁴⁺ and Cr²⁺ respectively. Dotted arrow in the figure indicates charge transfer mechanism and lattice relaxation.



Fig. 5: (a) Intensity variation of A_g peak and (b) wave number shift of A_g peak for the HoFe₁₋ $_xCr_xO_3$ ($0 \le x \le 1$) compounds.



Fig. 6: Absorption spectra of HoFe_{1-x} Cr_xO_3 ($0 \le x \le 1$) compounds.



Fig. 7: (a) Tauc's plots to determine the band gap values of $HoFe_{1-x}Cr_xO_3$ ($0 \le x \le 1$) compounds. (b) Variation of the band gap with respect to Cr composition.



Fig. 8: (a) Shows the energy diagram of HoFeO₃ (b) Energy diagram of HoCrO₃ (c) probable energy diagram for HoFe_{1-x}Cr_xO₃. It is evident from the frame (c) that when x < 0.5, the valance band maxima (VBM) and conduction band minima (CBM) shifts to higher energy (dark red color). However, the shift in VBM is due to strong hybridization of d orbitals of Fe & Cr with *p* - orbitals of oxygen in valance band. When x > 0.5, band gap is dominated by unoccupied *d* - orbitals of Cr in conduction band which leads to increase in band gap (purple color).