A magnetostatic energy formula arising from the L^2 -orthogonal decomposition of the stray field

Lukas Exl *1,2,3

¹Faculty of Mathematics, University of Vienna, Oskar-Morgenstern-Platz 1, 1090 Wien, Austria.

²Institute for Analysis and Scientific Computing, Vienna University of Technology, Wiedner Hauptstraße 8-10, 1040, Vienna.

³WPI c/o Faculty of Mathematics, University of Vienna, Oskar-Morgenstern-Platz 1, 1090 Wien, Austria.

March 9, 2022

Abstract. A formula for the magnetostatic energy of a finite magnet is proven. In contrast to common approaches, the new energy identity does not rely on evaluation of a nonlocal boundary integral inside the magnet or the solution of an equivalent Dirichlet problem. The formula is therefore computationally efficient, which is also shown numerically. Algorithms for the simulation of magnetic materials could benefit from incorporating the presented representation of the energy. In addition, a natural analogue for the energy via the magnetic induction is given. Proofs are carried out within a setting which is suitable for common discretizations in computational micromagnetics.

Keywords: micromagnetics, magnetostatics, boundary integral operators, stray field energy, single layer potential

1 Introduction

The magnetostatic energy of a magnet $\Omega \subset \mathbb{R}^3$ is, up to a constant, given as

$$e_d = -\int_{\Omega} \boldsymbol{m} \cdot \boldsymbol{h}_s \, dx = \int_{\Omega} \boldsymbol{m} \cdot \nabla u \, dx, \tag{1}$$

where the magnetization \boldsymbol{m} is defined in Ω and zero elsewhere, $\boldsymbol{h}_s = -\nabla u$ is the stray field and u its scalar potential satisfying $\Delta u = \nabla \cdot \boldsymbol{m}$ in \mathbb{R}^3 [4]. In micromagnetic simulations the self-energy (1) is known to be the most time-consuming part due to its nonlocal nature [1]. Our main contribution is the derivation and proof of the following energy identity

$$e_d = \int_{\Omega} |\nabla u_0|^2 dx + \frac{1}{4\pi} \int_{\partial \Omega} \int_{\partial \Omega'} \frac{(\boldsymbol{m} \cdot \boldsymbol{n} - \partial_{\boldsymbol{n}} u_0) (\boldsymbol{m}' \cdot \boldsymbol{n}' - \partial_{\boldsymbol{n}'} u_0')}{|\boldsymbol{x} - \boldsymbol{x}'|} ds_{x'} ds_{x},$$
(2)

^{*}lukas.exl@univie.ac.at

where

$$-\Delta u_0 = -\nabla \cdot \boldsymbol{m} \quad \text{in } \Omega \tag{3}$$

$$u_0 = 0 \quad \text{on } \partial\Omega.$$
 (4)

The key observation which leads to the expression (2) is the L^2 -orthogonal decomposition of the magnetic field in Ω . Note, that neither evaluations of a nonlocal boundary integral inside the domain Ω nor the solution of an equivalent Dirichlet problem is required to obtain the energy from (2). This is an interesting observation, since most numerical methods in micromagnetics implement the magnetic self-energy in the form (1) with first computing the nonlocal field via the convolution with the Green's kernel $G(x) = \frac{1}{4\pi} \frac{1}{|x|} [1, 11]$

$$\boldsymbol{h}_{s}(\boldsymbol{x}) = -\nabla u(\boldsymbol{x}) = \int_{\Omega} \nabla G(\boldsymbol{x} - \boldsymbol{x}') \, \nabla \cdot \boldsymbol{m}' \, dx' - \int_{\partial \Omega} \nabla G(\boldsymbol{x} - \boldsymbol{x}') \, \boldsymbol{m}' \cdot \boldsymbol{n}' \, ds_{x'}$$
 (5)

or the solution of the PDE

$$\Delta u = \nabla \cdot \boldsymbol{m} \text{ in } \mathbb{R}^3 \tag{6}$$

with the help of boundary integral operators, which account for the contribution of the field in the external region $\mathbb{R}^3 \setminus \overline{\Omega}$. In any of these cases, the computation of the energy requires the evaluation of a part of the field by nonlocal convolutions evaluated on the boundary and inside the magnet or an additional Dirichlet problem. The evaluation of the presented formula, and the analogue to the energy via the vector potential, gets along without these computational tasks. Besides the solution of one Dirichlet problem, only the single layer potential has to be evaluated on the boundary, where efficient numerical techniques are already available, e.g. [6]. This leads to computational advantages if the energy has to be computed directly without relying on the stray field several times in a simulation, as in parts of energy minimization algorithms, e.g., derivative-free line search [9, 14], or derivative-free methods like simulated annealing [12, 20]. In the following sections we give the main results along with related definitions and illustrate and exemplify the usefulness of the new energy formula numerically. Proofs are given in the final section.

2 Main results

In the following we will use smoothness assumptions which are sufficient to ensure the existence of a unique solution of the stray field problem (compare with Def. 1). This is also a suitable setting for common discretization schemes in numerical micromagnetics. However, the results presented here are certainly compatible with higher order regularity assumptions. For a rigorous presentation of the following definitions we refer to the literature [13, 15, 19]. Let $\Omega \subset \mathbb{R}^3$ be a bounded Lipschitz-domain with boundary $\Gamma := \partial \Omega$. We denote the exterior domain with $\Omega^{ext} := \mathbb{R}^3 \setminus \overline{\Omega}$. We will make use of the Sobolev spaces $H^1(\Omega) := W^{1,2}(\Omega) = \{u \in L^2(\Omega) : \text{weak derivatives } \partial_q u \in L^2(\Omega), \ q = 1, 2, 3\}$ and $H^1_{loc}(\Omega^{ext}) := \{u \in H^1(C) : C \subset \Omega^{ext} \text{ compact}\}$. For the definition of the Sobolev spaces on manifolds, in particular $H^{1/2}(\Gamma)$ and its dual space $H^{-1/2}(\Gamma)$, we refer to the literature. We denote $H^1_0(\Omega) := \{u \in H^1(\Omega) : \gamma_0 u = 0 \text{ on } \Gamma\}$, where $\gamma_0 : H^1(\Omega) \to H^{1/2}(\Gamma)$ is the trace. Further, we use the short notation $\langle u, v \rangle_{\Gamma} = (u, v)_{L^2(\Gamma)}$. The conormal derivative $\gamma_1^{int} u \in H^{-1/2}(\Gamma)$ is defined as the solution of the variational problem $\langle \gamma_1^{int} u, \gamma_0^{int} v \rangle_{\Gamma} = (\nabla u, \nabla v)_{L^2(\Omega)} - \langle f, v \rangle$ for all $v \in H^1(\Omega)$, where $u \in H^1(\Omega)$ satisfies $\Delta u = f$, $f \in H^1(\Omega)^*$, in the sense of distributions; the exterior conormal derivative $\gamma_1^{ext} : H^1_{loc}(\Omega^{ext}) \to H^{-1/2}(\Gamma)$ is defined accordingly. The expression on the boundary $m \cdot n$, where n is the outer normal, is defined by the bounded linear map $\gamma_n : (H^1(\Omega))^3 \to H^{-1/2}(\Gamma)$, $\gamma_n(m) = m \cdot n$ [8]. The scalar potential can be characterized via the following transmission problem.

Definition 1 (Transmission problem). Let $\mathbf{m} \in (H^1(\Omega))^3$. Then the scalar potential $u = (u^{int}, u^{ext}) \in H^1(\Omega) \times H^1_{loc}(\Omega^{ext})$ is the unique solution [5] of

$$-\Delta u^{int} = -\nabla \cdot \boldsymbol{m} \quad in \ \Omega$$

$$\gamma_0^{int} u^{int} = \gamma_0^{ext} u^{ext} \quad on \ \Gamma$$

$$\gamma_1^{int} u^{int} = \gamma_1^{ext} u^{ext} + \boldsymbol{m} \cdot \boldsymbol{n} \quad on \ \Gamma$$

$$-\Delta u^{ext} = 0 \quad in \ \Omega^{ext}$$

$$u^{ext} = \mathcal{O}(|\boldsymbol{x}|^{-1}) \quad |\boldsymbol{x}| \to \infty,$$

$$(7)$$

where n denotes the outer normal vector. The stray field is $h_s = -\nabla u$.

A solution of (7) can be represented with the help of the *single layer potential*.

Definition 2 (Single layer potential [19]). The single layer potential $\widetilde{\mathcal{V}}: H^{-1/2}(\Gamma) \to H^1_{loc}(\mathbb{R}^3)$ is

$$(\widetilde{\mathcal{V}}\phi)(\boldsymbol{x}) := \int_{\Gamma} G(\boldsymbol{y} - \boldsymbol{x})\phi(\boldsymbol{y})ds_{y}, \tag{8}$$

where $G(x) = \frac{1}{4\pi} \frac{1}{|x|}$ is the Green's function of the Laplacian in \mathbb{R}^3 .

There holds [19]

$$\Delta \widetilde{\mathcal{V}} \phi = 0 \quad \text{in } \Omega \cup \Omega^{ext}. \tag{9}$$

The linear operator $\widetilde{\mathcal{V}}$ is continuous, while the conormal derivative jumps on Γ , i.e.,

$$\gamma_0^{int}\widetilde{\mathcal{V}}\phi - \gamma_0^{ext}\widetilde{\mathcal{V}}\phi = 0 \tag{10}$$

$$\gamma_1^{int}\widetilde{\mathcal{V}}\phi - \gamma_1^{ext}\widetilde{\mathcal{V}}\phi = \phi. \tag{11}$$

There holds $\widetilde{\mathcal{V}}(\boldsymbol{x}) = \mathcal{O}(|\boldsymbol{x}|^{-1})$ as $|\boldsymbol{x}| \to \infty$. We define the trace of the single layer potential $\mathcal{V} := \gamma_0 \widetilde{\mathcal{V}} : H^{-1/2}(\Gamma) \to H^{1/2}(\Gamma)$, which is then a bounded linear operator.

The following can be verified, by using the above mentioned properties of the single layer potential.

Proposition 1 ([7]). The solution to (7) is given by $u = (u_0 + \widetilde{\mathcal{V}}(\boldsymbol{m} \cdot \boldsymbol{n} - \gamma_1^{int}u_0), \widetilde{\mathcal{V}}(\boldsymbol{m} \cdot \boldsymbol{n} - \gamma_1^{int}u_0))$, where

$$-\Delta u_0 = -\nabla \cdot \boldsymbol{m} \quad in \ \Omega$$

$$\gamma_0^{int} u_0 = 0 \quad on \ \Gamma.$$
 (12)

Hence, the stray field in whole space is given as

$$\boldsymbol{h}_s = \boldsymbol{h}_{s,0} + \boldsymbol{h}_{s,1} := -\nabla u_0 - \nabla \widetilde{\mathcal{V}}(\boldsymbol{m} \cdot \boldsymbol{n} - \gamma_1^{int} u_0), \tag{13}$$

where u_0 satisfies (12) in Ω and is extended with zero to the exterior domain.

The main result is the following energy identity corresponding to formula (2).

Theorem 2 (Energy formula). Let $\mathbf{h}_{s,0} = -\nabla u_0$ with $u_0 \in H_0^1(\Omega)$ fulfilling the Dirichlet problem (12). Then the magnetostatic energy is given by

$$e_d = -(\boldsymbol{h}_s, \boldsymbol{m})_{(L^2(\Omega))^3} = \|\boldsymbol{h}_{s,0}\|_{(L^2(\Omega))^3}^2 + \langle (\boldsymbol{m} \cdot \boldsymbol{n} - \gamma_1^{int} u_0, \mathcal{V}(\boldsymbol{m} \cdot \boldsymbol{n} - \gamma_1^{int} u_0) \rangle_{\Gamma}.$$
(14)

3

An analog energy formula can be derived via the magnetic induction and its vector potential.

Definition 3 (Transmission problem for the vector potential). Let $m \in (H^1(\Omega))^3$. Then the vector potential $\mathbf{A} = (\mathbf{A}^{int}, \mathbf{A}^{ext}) \in (H^1(\Omega))^3 \times (H^1_{loc}(\Omega^{ext}))^3$ is the unique solution of

$$\Delta \mathbf{A}^{int} = -\nabla \times \mathbf{m} \qquad in \ \Omega, \tag{15a}$$

$$\Delta A^{ext} = \mathbf{0} \qquad in \ \Omega^{ext}, \tag{15b}$$

$$\Delta A^{ext} = \mathbf{0} \qquad in \ \Omega^{ext}, \tag{15b}$$

$$\gamma_0^{int} A^{int} = \gamma_0^{ext} A^{ext} \qquad on \ \Gamma, \tag{15c}$$

$$\gamma_1^{int} \mathbf{A}^{int} = \gamma_1^{ext} \mathbf{A}^{ext} + \mathbf{m} \times \mathbf{n} \ on \ \Gamma, \tag{15d}$$

$$A_i^{ext} = O(|x|^{-1}), \ j = 1...3 \quad in \ \Omega^{ext},$$
 (15e)

where n denotes the outer normal vector. The trace operators and conormal derivatives are applied component-wisely.

The analogue to Thm. 2 is given next.

Theorem 3 (Energy formula). Let $b_0' = \nabla \times A_0$ with $A_0 \in (H_0^1(\Omega))^3$ fulfilling the Dirichlet problem (38). Then the magnetostatic energy is given by

$$e_d = \|\boldsymbol{m}\|_{(L^2(\Omega))^3}^2 - (\|\nabla \boldsymbol{A}_0\|_{L^2(\Omega)^{3\times 3}}^2 + \langle \boldsymbol{m} \times \boldsymbol{n} - \gamma_1^{int} \boldsymbol{A}_0, \mathcal{V}(\boldsymbol{m} \times \boldsymbol{n} - \gamma_1^{int} \boldsymbol{A}_0) \rangle_{\Gamma^3}.$$
(16)

3 Numerical validation

In the following we will give numerical results that demonstrate that the presented formulation in Eqn. (2) leads to properly calculated magnetostatic energy. We perform our computations on finite element grids with P1-elements and compare with FEM/BEM for (7) via the representation in Prop. 1 using a mass-lumped stray field for the energy computation [17] via Eqn. (1). This approach is common in micromagnetics [6, 7] and requires the solution of two Dirichlet problems, the one in Eqn. (12) and a second one with zero right hand side and Dirichlet data obtained from the evaluation of the single layer potential on the boundary nodes. In contrast to that, the new energy formula does not require solving the latter. For the efficient computation of the single layer potential on the boundary nodes in (quasi) linear time (and linear memory consumption) the NUFFT method in [6] is used. In all computations the normal component of the magnetization in the source term of the single layer potential was projected onto the space of piecewise constant functions (L^2 -projection). Likewise, the L^2 -projection is used for a piecewise constant approximation of the V-surface values in the trace product, cf. Eqn. (14). In the FEM/BEM approach a nodal interpolation of the \mathcal{V} -surface values for the Dirichlet data is used for the sake of effectiveness. The Dirichlet problems are solved with an ILU preconditioned conjugate gradient method. Computations were performed on the Vienna Scientific Cluster 3 (VSC3). Mesh generation was done with help of NETGEN [16]. Results for the uniformly magnetized unit cube are given in Tab. 1, for a uniformly magnetized sphere in Tab. 2 and for some random configuration in the cube in Tab. 3. For the cases of a uniformly magnetized sphere or cube the results are also compared with the analytical values. All test cases show accurate results for the new formula and a gain in efficiency from 12-25% relative to the FEM/BEM approach. This mostly amounts to the cost of solving one additional inhomogeneous Dirichlet problem in the FEM/BEM approach, which is particularly apparent for bulk material, but gets less relevant for, e.g., thin film geometries.

Table 1: Errors and timings for uniformly magnetized unit cube with analytical value $1/6 \, [\mu_0 M_s^2]$ (including a factor 1/2 in formula (1), μ_0 denotes the vacuum permeability and M_s the saturation magnetization). Mesh data: number of nodes (#nodes), number of surface nodes (#snodes), number of surface triangles (#stri) and number of tetrahedral elements (#tets). Energies: Energy value computed with formula (2) (E_{new}) and with FEM/BEM (E_{FB}). Deviations/Errors: Relative deviation of energies computed with new formula (2) and FEM/BEM (dNewFB), reference value and FEM/BEM (dRefFB) and reference value and new formula (dRefNew). Timings: Computation time via FEM/BEM (t_{FB}), computation time for formula (2) (t_{new}) and gain (in %).

#nodes	# snodes	#stri	#tets	E_{new}	E_{FB}	dNewFB	dRefFB	dRefNew	$t_{FB}\left[s\right]$	$t_{new}\left[s\right]$	gain
2744	1016	2028	13182	1.652E-01	1.652E-01	0	8.32E-03	8.32E-03	0.19	0.17	12%
9261	2402	4800	48000	1.659E-01	1.659E-01	0	4.05E-03	4.05E-03	0.31	0.27	12%
19683	4058	8112	105456	1.662E-01	1.662E-01	5.96E-05	2.49E-03	2.43E-03	0.47	0.39	17%
68921	9602	19200	384000	1.665E-01	1.665E-01	1.38e-05	1.13E-03	1.11E-03	1.28	0.97	25%

Table 2: Errors and timings for uniformly magnetized sphere with radius 0.5 with analytical value 8.727-E02 $[\mu_0 M_s^2]$ (including a factor 1/2 in formula (1), μ_0 denotes the vacuum permeability and M_s the saturation magnetization). Mesh data: number of nodes (#nodes), number of surface nodes (#snodes), number of surface triangles (#stri) and number of tetrahedral elements (#tets). Energies: Energy value computed with formula (2) (E_{new}) and with FEM/BEM (E_{FB}) . Deviations/Errors: Relative deviation of energies computed with new formula (2) and FEM/BEM (dNewFB), reference value and FEM/BEM (dRefFB) and reference value and new formula (dRefNew). Timings: Computation time via FEM/BEM (t_{FB}) , computation time for formula (2) (t_{new}) and gain (in %).

#nodes	#snodes	#stri	#tets	E_{new}	E_{FB}	dNewFB	dRefFB	dRefNew	$t_{FB}[s]$	$t_{new}[s]$	gain
2824	891	1778	14156	8.642E-02	8.642E-02	1.35e-05	9.60E-03	9.61E-03	0.19	0.16	14%
4749	1295	2586	24474	8.669E-02	8.669E-02	8.15E-06	6.64E-03	6.63E-03	0.21	0.18	15%
9084	2031	4058	48111	8.689E-02	8.689E-02	1.79E-08	4.23E-03	4.23E-03	0.34	0.29	15%
13837	4098	8192	70144	8.709E-02	8.709E-02	1.79e-07	2.07E-03	2.07E-03	0.58	0.49	15 %

Table 3: Errors and timings for randomly magnetized unit cube, deviating from uniform magnetization at nodes by normally distributed polar angle with zero mean and standard deviation of 20 degrees. Mesh data: number of nodes (#nodes), number of surface nodes (#snodes), number of surface triangles (#stri) and number of tetrahedral elements (#tets). Energies: Energy value computed with formula (2) (E_{new}) and with FEM/BEM (E_{FB}) . Deviations: Relative deviation of energies computed with new formula (2) and FEM/BEM (dNewFB). Timings: Computation time via FEM/BEM (t_{FB}) , computation time for formula (2) (t_{new}) and gain (in %).

# nodes	# snodes	$\#\mathrm{stri}$	#tets	E_{new}	E_{FB}	dNewFB	$t_{FB}\left[s\right]$	$t_{new}\left[s\right]$	gain
2744	1016	2028	13182	1.491E-01	1.491E-01	1.82E-04	0.19	0.17	12%
9261	2402	4800	48000	1.502E-01	1.503E-01	1.00E-03	0.30	0.26	12%
19683	4058	8112	105456	1.503E-01	1.506E-01	1.90E-03	0.46	0.39	15%
68921	9602	19200	384000	1.505E-01	1.507E-01	1.97E-03	1.57	1.16	26%

4 Proofs of the energy identities

There holds the following L^2 -orthogonality.

Lemma 4 (L^2 -orthogonality). Let $u_0 \in H_0^1(\Omega)$ be the solution to the Dirichlet problem (12) and $\mathbf{h}_0 = -\nabla u_0 \in (L^2(\Omega))^3$ the corresponding field. Let further $\mathbf{h}_{\Delta} \in (L^2(\Omega))^3$ be a Laplace field, i.e., $\nabla \cdot \mathbf{h}_{\Delta} = 0$ in Ω . Then

$$(\boldsymbol{h}_0, \boldsymbol{h}_{\Delta})_{(L^2(\Omega))^3} := \int_{\Omega} \boldsymbol{h}_0 \cdot \boldsymbol{h}_{\Delta} \, dx = 0. \tag{17}$$

Proof. By partial integration on gets

$$(-\nabla u_0, \mathbf{h}_{\Delta})_{(L^2(\Omega))^3} = (u_0, \nabla \cdot \mathbf{h}_{\Delta})_{L^2(\Omega)} - \langle \gamma_0^{int} u_0, \mathbf{h}_{\Delta} \cdot \mathbf{n} \rangle_{\Gamma}.$$
(18)

Both terms on the r.h.s. are zero.

For the components in Eqn. (13) we conclude.

Corollary 5. For the solution to (7) given by $u = u_0 + u_1$ with $u_1 := \widetilde{\mathcal{V}}(\boldsymbol{m} \cdot \boldsymbol{n} - \gamma_1^{int}u_0)$ and u_0 from (12) the corresponding fields $\boldsymbol{h}_{s,0} = -\nabla u_0$ and $\boldsymbol{h}_{s,1} = -\nabla u_1$ are L^2 -orthogonal, i.e.,

$$(\boldsymbol{h}_{s,0}, \boldsymbol{h}_{s,1})_{(L^2(\mathbb{R}^3))^3} = (\boldsymbol{h}_{s,0}, \boldsymbol{h}_{s,1})_{(L^2(\Omega))^3} = 0.$$
 (19)

The formula (2) (Theorem 2) follows with help of Cor. 5.

Proof of Thm. 2 By Thm. 2.7.7 in [15] we get from (12) with $v \in H^1(\Omega)$

$$\langle \gamma_1^{int} u_0, \gamma_0^{int} v \rangle_{\Gamma} = (\nabla u_0, \nabla v)_{(L^2(\Omega))^3} + (\nabla \cdot \boldsymbol{m}, v)_{L^2(\Omega)}.$$
 (20)

Now, applying Green's first identity gives

$$\langle \gamma_1^{int} u_0, \gamma_0^{int} v \rangle_{\Gamma} = (\nabla u_0, \nabla v)_{(L^2(\Omega))^3} - (\boldsymbol{m}, \nabla v)_{(L^2(\Omega))^3} + \langle \boldsymbol{m} \cdot \boldsymbol{n}, v \rangle_{\Gamma}.$$
 (21)

Rearranging terms gives

$$\langle \gamma_1^{int} u_0 - \boldsymbol{m} \cdot \boldsymbol{n}, \gamma_0^{int} v \rangle_{\Gamma} = (\nabla u_0, \nabla v)_{(L^2(\Omega))^3} - (\boldsymbol{m}, \nabla v)_{(L^2(\Omega))^3}. \tag{22}$$

We insert $v := u = u_0 + u_1 \in H^1(\Omega)$ with $u_1 := \widetilde{\mathcal{V}}(\boldsymbol{m} \cdot \boldsymbol{n} - \gamma_1^{int} u_0)$ and u_0 from (12) and use the zero-boundary condition of u_0 and the orthogonality from Cor. 5. This yields

$$\langle \gamma_1^{int} u_0 - \boldsymbol{m} \cdot \boldsymbol{n}, \gamma_0^{int} u_1 \rangle_{\Gamma} = \|\nabla u_0\|_{(L^2(\Omega))^3}^2 - (\boldsymbol{m}, \nabla u)_{(L^2(\Omega))^3}, \tag{23}$$

which immediately gives formula (14).

There is an alternative derivation of (14) via the magnetic induction.

Alternative proof of Thm. 2 We use the fundamental Helmholtz decomposition (omitting constants) [2, 4]

$$\boldsymbol{m} = \boldsymbol{b}' - \boldsymbol{h}_s \quad \text{in } \mathbb{R}^3, \tag{24}$$

where b' is the divergence-free magnetic induction (not including the part corresponding to the external field). The fields $h_s, b' \in (L^2(\mathbb{R}^3))^3$ are L^2 - orthogonal [4]. A consequence of this is that the energy can be written as

$$e_d = -\int_{\Omega} \boldsymbol{m} \cdot \boldsymbol{h}_s \, dx = \int_{\mathbb{R}^3} |\boldsymbol{h}_s|^2 \, dx. \tag{25}$$

We can now use the representation $\mathbf{h}_s = \mathbf{h}_{s,0} + \mathbf{h}_{s,1} := -\nabla u_0 - \nabla u_1$, $u_1 = \widetilde{\mathcal{V}}(\mathbf{m} \cdot \mathbf{n} - \gamma_1^{int} u_0)$ for the stray field in whole space, where u_0 is extended with zero in the exterior domain Ω^{ext} . Cor. 5 yields

$$e_{d} = \int_{\Omega} |\boldsymbol{h}_{s,0}|^{2} dx + \int_{\mathbb{R}^{3}} |\boldsymbol{h}_{s,1}|^{2} dx = \|\nabla u_{0}\|_{(L^{2}(\Omega))^{3}}^{2} + \int_{\Omega} |\boldsymbol{h}_{s,1}|^{2} dx + \int_{\Omega^{ext}} |\boldsymbol{h}_{s,1}|^{2} dx.$$
(26)

By applying Green's first formula we get [19, Ch. 6.6.1]

$$\int_{\Omega} |\boldsymbol{h}_{s,1}|^2 dx = \langle \gamma_1^{int} u_1, \gamma_0 u_1 \rangle_{\Gamma}$$
(27)

$$\int_{\Omega^{ext}} |\boldsymbol{h}_{s,1}|^2 dx = \langle -\gamma_1^{ext} u_1, \gamma_0 u_1 \rangle_{\Gamma}$$
(28)

The jump of the conormal derivative $\gamma_1^{int}u_1 - \gamma_1^{ext}u_1 = \boldsymbol{m}\cdot\boldsymbol{n} - \gamma_1^{int}u_0$ leads to the result. \square

We derive and proof now the analog Thm. 3.

Proof of Thm. 3 Maxwell's equations for magnetostatics read

$$\nabla \cdot \mathbf{b} = 0, \tag{29}$$

$$\nabla \times \mathbf{h} = \mathbf{j},\tag{30}$$

where **j** is the current density. Excluding the divergence free part h_{ext} : $\nabla \times h_{ext} = \mathbf{j}$ from $h = h_s + h_{ext}$ gives together with $\mathbf{m} = \mathbf{b}' - \mathbf{h}_s$

$$\nabla \cdot \mathbf{b}' = 0, \tag{31}$$

$$\nabla \times \mathbf{b}' = \nabla \times \mathbf{m}. \tag{32}$$

By introducing a vector potential $\mathbf{b}' = \nabla \times \mathbf{A}$ with gauge condition $\nabla \cdot \mathbf{A} = 0$ [10], we get

$$\nabla \times (\nabla \times \mathbf{A}) = \nabla(\nabla \cdot \mathbf{A}) - \Delta \mathbf{A} = \nabla \times \mathbf{m}, \tag{33}$$

and hence

$$\Delta \mathbf{A} = -\nabla \times \mathbf{m} \quad \text{in } \mathbb{R}^3. \tag{34}$$

For a finite magnet $\Omega \subset \mathbb{R}^3$ this gives the boundary conditions [3]

$$\gamma_0 \mathbf{A}^{ext} - \gamma_0 \mathbf{A}^{int} = \mathbf{0}, \tag{35}$$

$$\gamma_1 \mathbf{A}^{ext} - \gamma_1 \mathbf{A}^{int} = -\mathbf{m} \times \mathbf{n}. \tag{36}$$

The analogy of the transmission problem in Def. 3 to that of Def. 1 gives rise to the representation of the solution for the magnetic induction

$$\mathbf{b}' = \mathbf{b}'_0 + \mathbf{b}'_1 := \nabla \times \mathbf{A}_0 + \nabla \times \mathbf{A}_1 \text{ with } \mathbf{A}_1 = \widetilde{\mathcal{V}}(\mathbf{m} \times \mathbf{n} - \gamma_1^{int} \mathbf{A}_0), \tag{37}$$

where $\widetilde{\mathcal{V}}$ is applied component-wisely and $A_0 \in \left(H_0^1(\Omega)\right)^3$ fulfilling

$$\Delta \mathbf{A}_0 = -\nabla \times \mathbf{m} \quad \text{in } \Omega$$
$$\gamma_0^{int} \mathbf{A}_0 = \mathbf{0} \quad \text{on } \Gamma.$$
 (38)

The magnetostatic energy can be expressed in terms of the vector potential by using the decomposition (24)

$$e_d = -\int_{\Omega} \boldsymbol{m} \cdot \boldsymbol{h}_s \, dx = \int_{\Omega} |\boldsymbol{m}|^2 \, dx - \int_{\Omega} \boldsymbol{m} \cdot \boldsymbol{b}' \, dx. \tag{39}$$

The rest of the proof of Thm. 3 goes along the same lines as that of Thm. 2 but using the orthogonality

$$(\nabla \mathbf{A}_0, \nabla \mathbf{A}_1)_{L^2(\Omega)^{3\times 3}} = 0, \tag{40}$$

and the Green's identity (e.g. [18]) for $\mathbf{V} \in (H^1(\Omega))^3$

$$(\nabla \times \boldsymbol{m}, \boldsymbol{V})_{L^{2}(\Omega)^{3}} = (\nabla \times \boldsymbol{V}, \boldsymbol{m})_{L^{2}(\Omega)^{3}} - \langle \boldsymbol{m} \times \boldsymbol{n}, \boldsymbol{V} \rangle_{\Gamma^{3}}.$$
(41)

5 Conclusion

We have derived, proven and numerically validated a new formula for the stray field energy. Computation of the energy only requires the solution of a Dirichlet problem and the evaluation of the single layer potential on the boundary. The efficiency is illustrated by means of numerical examples indicating a gain up to 25% compared to a FEM/BEM approach with quasi-optimally scaling BEM part. The setting was chosen to be suitable for common discretizations in numerical micromagnetics. The presented energy formula has an analogue via the magnetic induction. Numerical software for simulation of magnetic materials could benefit in terms of efficiency from incorporating the presented formulas.

Acknowledgments

Financial support by the Austrian Science Fund (FWF) via the SFB "ViCoM" under grant No. F41, via the SFB "Complexity in PDEs" under grant F65 and the project "ROAM" under grant No. 31140 is acknowledged. The computations were achieved by using the Vienna Scientific Cluster (VSC) via the funded project No. 71140.

References

- [1] C. Abert, L. Exl, G. Selke, A. Drews, and T. Schrefl. Numerical methods for the stray-field calculation: A comparison of recently developed algorithms. *Journal of Magnetism and Magnetic Materials*, 326:176–185, 2012.
- [2] A. Aharoni. *Introduction to the Theory of Ferromagnetism*, volume 109. Clarendon Press, 2000.
- [3] W. F. Brown. Magnetostatic principles. In *Ferromagnetism*. North-Holland Amsterdam, 1962.
- [4] W. F. Brown. *Micromagnetics*. Number 18. Interscience Publishers, 1963.
- [5] C. Carstensen and E. P. Stephan. Adaptive coupling of boundary elements and finite elements. RAIRO-Modélisation mathématique et analyse numérique, 29(7):779–817, 1995.
- [6] L. Exl and T. Schrefl. Non-uniform FFT for the finite element computation of the micromagnetic scalar potential. *Journal of Computational Physics*, 270:490–505, 2014.
- [7] C. J. Garcia-Cervera and A. M. Roma. Adaptive mesh refinement for micromagnetics simulations. *Magnetics, IEEE Transactions on*, 42(6):1648–1654, 2006.
- [8] V. Girault and P.-A. Raviart. Finite element methods for Navier-Stokes equations: theory and algorithms, volume 5. Springer Science & Business Media, 2012.
- [9] A. Griewank. The "global" convergence of broyden-like methods with suitable line search. *The ANZIAM Journal*, 28(1):75–92, 1986.
- [10] J. D. Jackson. Classical electrodynamics (Third edition). Wiley, 1999.
- [11] H. Kronmüller and S. Parkin. Handbook of magnetism and advanced magnetic materials. Spintronics and Magnetoelectronics, 5, 2008.
- [12] M. Luskin and L. Ma. Numerical optimization of the micromagnetics energy. *Mathematics in Smart Materials*, pages 19–29, 1993.
- [13] W. C. H. McLean. Strongly elliptic systems and boundary integral equations. Cambridge university press, 2000.
- [14] H. Oezelt, A. Kovacs, J. Fischbacher, S. Bance, M. Gubbins, and T. Schrefl. Transition jitter in heat-assisted magnetic recording by micromagnetic simulation. *IEEE Transactions on Magnetics*, 53(11):1–5, 2017.
- [15] S. A. Sauter and C. Schwab. Boundary element methods, vol 39 of springer series in computational mathematics, 2011.
- [16] J. Schöberl. Netgen an advancing front 2d/3d-mesh generator based on abstract rules. Computing and visualization in science, 1(1):41–52, 1997.
- [17] T. Schrefl, G. Hrkac, S. Bance, D. Suess, O. Ertl, and J. Fidler. *Numerical Methods in Micromagnetics (Finite Element Method)*. John Wiley & Sons, Ltd, 2007.
- [18] D. Sheen. A generalized Green's theorem. Applied mathematics letters, 5(4):95–98, 1992.

- [19] O. Steinbach. Numerical approximation methods for elliptic boundary value problems: finite and boundary elements. Springer Science & Business Media, 2007.
- [20] L. C. Thomson, R. J. Enkin, and W. Williams. Simulated annealing of three-dimensional micromagnetic structures and simulated thermoremanent magnetization. *Journal of Geophysical Research: Solid Earth*, 99(B1):603–609, 1994.