A preliminary DFT study of the adsorption and dissociation of CH_4 , SO_2 and O_2 reactions on $Cr_2O_3(0001)$

S. N. Hernández Guiance^a, D. Coria^b, I. M. Irurzun^{*,c}, E. E. Mola¹.

July 9, 2018

^aFacultad de Química, e Ingeniería, Pontificia Universidad Católica Argentina, Mendoza 4197 CP 2000 Rosario, Argentina.

^bUniversidad del Centro Educativo Latinoamericano. Av. Pellegrini 1332 CP 2000 Rosario, Argentina.

^cCCT La Plata – CONICET. Instituto de Investigaciones Fisicoquímicas Teóricas y Aplicadas (INIFTA),
Facultad de Ciencias Exactas, Universidad Nacional de La Plata. Diagonal 113 y 64, CP (1900), La Plata,
Argentina. Telephone: +54 221 425 74 30, ext. 149. Fax: +54 221 425 46 42.

*Correspondig Author

¹ In memory

Abstract

In the present work, we study the structures and molecular geometries of CH_4 , SO_2 and O_2 adsorbed on $Cr_2O_3(0001)$. Using computational calculations based on the density functional theory (DFT), we analyze the most suitable sites to carry out the adsorption of each of the molecules mentioned, and the influence of each species on the adsorption and dissociation of the others. The results allow us to understand the activation of the $Cr_2O_3(0001)$ surface, which leads to the presence of SO_2 during the oxidation of CH_4 , as was experimentally verified.

1 Introduction

Transition metal oxide surfaces have been a major focus of interest in the field of catalysis and corrosion. Environmental sciences have paid much attention to catalytic surfaces, which have been used to remove pollutant molecules, such as SO_2 , CH_4 , CO, and CO_2 , from the atmosphere. Among these molecules, SO_2 is one of the products from natural and anthropogenic sources emitted to the atmosphere that may turn into acid rain. Most of the SO_2 released into the atmosphere ($\approx 3/4$) is produced by human activities, especially by the combustion of fossil fuels. More than half of the world production comes from a few developed countries. In industrial stacks, SO_2 reduction occurs by reaction with CH_4 , which is then oxidized to CO_2 by O_2 . Therefore, the following reactions

$$CH_4 + 2SO_2 \xrightarrow{k_1} 2S^0 + CO_2 + 2H_2O \tag{1}$$

$$2O_2 + CH_4 \xrightarrow{k_2} k_2 CO_2 + 2H_2 O \tag{2}$$

$$SO_2 + CH_4 + O_2 \xrightarrow{k_3} S^0 + CO_2 + 2H_2O \tag{3}$$

as well as the development of catalysts that favor CH_4 oxidation in the presence of SO_2 and O_2 have been a major subject of research. In previous work, we studied the oxides of some transition metals (Co, Ni, Fe, V, Mn, Cr, and Mo) supported on alumina [1] in order to determine the best surface for capturing SO_2 . We found that the best adsorbent is Cr_2O_3/Al_2O_3 [2, 3], which also catalyzes CH_4 oxidation to obtain CO_2 . It was selected due to its thermal and mechanical resistance and its possibility to be regenerated. We also experimentally determined the activation energies of the aforementioned reactions on Cr_2O_3/Al_2O_3 under stoichiometric conditions [4]. We concluded that the presence of SO_2 favors CH_4 oxidation, decreasing the activation energy. In this paper, we present theoretical results based on the density functional theory on the adsorption and dissociation of diverse species involved in reactions (1)–(3) on Cr_2O_3/Al_2O_3 . We aim to provide additional theoretical information to understand the mechanism of the oxidation reaction of CH_4 on Cr_2O_3/Al_2O_3 in the presence of SO_2 and O_2 .

2 Theoretical

First-principles total energy calculations were performed using DFT+U to investigate individual and simultaneous adsorption of SO_2 , CH_4 and O_2 molecules on the $\alpha - Cr_2O_3(0001)$ surface as implemented in the Vienna Ab initio Simulation Package (VASP) code. The $\alpha - Cr_2O_3(0001)$ surface has been studied using different theoretical approaches [6, 7, 8, 9, 10, 11]. There is general agreement among the different methods that the surface undergoes strong vertical relaxations. In this paper, we take into account the strong correlation effects described by a Hubbard-type on-site Coulomb repulsion, not included in a density functional description [10]. The (0001) face was selected because in its natural state, Cr_2O_3 has this type of structure in 97.20% of its volume, which is maintained up to temperatures of about 973K.

The Kohn-Sham equations were solved using projector augmented wave (PAW) method and a plane-wave basis set including plane waves up to 400 eV. Electron exchange and correlation energies were calculated within the local spin density approximation (LSDA) in the Perdew-Zunger form. The DFT+U method was used with values J=1 and U=5 [10]. Convergence is considered achieved when the forces on the ions are less than 0.03 eV/Å. Periodic boundary conditions are applied in the three perpendicular directions. The Hessianmatrix of second derivatives was determined for ground structures within the harmonic approximation by two-sided finite differences, using a displacement step of 0.01 Å. Adsorbed atoms were displaced in the calculations, and diagonalization of the dynamic matrix yields the harmonic frequencies.

The surface is modelled as a rhomboid supercell with an edge size of 4.954Å and 20Å high. Each substrate layer is composed of one chromium atom, three oxygen atoms and one chromium atom, and is 2.263 Å thick. However, hereafter each layer composed of one type of atom only will be called a layer. The supercell used is shown in Fig. 1, while the geometric parameters obtained after surface optimization are listed in Table 1.



Figure 1: $Cr_2O_3(0001)$ supercell.

The first Brillouin zone was sampled with a $(3 \times 3 \times 1)$ gamma point centered mesh and only the gamma point was used for the cubic supercell used for the optimization of isolated molecules [3].

The adsorption energy of each adsorbate molecule is calculated as

Interlayer spacing	DFT+U LSD	GGA
$Cr_1 - O_2$	-61	-53
$O_2 - Cr_3$	+6	+14
$Cr_3 - Cr_4$	-44	+70
$Cr_4 - O_5$	+9	+12
$O_5 - Cr_6$	-2	+12
$Cr_6 - Cr_7$	+7	-56
$Cr_7 - O_8$	-2	+10
$O_8 - Cr_9$	-1	-5
$Cr_9 - Cr_{10}$	+3	-5

Table 1: Variation in atomic interlayer spacings of the $\alpha - Cr2O3(0001)$ substrate after surface optimization. The initial spacings are: Cr - O = 0.94Å, Cr - Cr = 0.38Å. Comparison of the results from DFT, LSDA and GGA methods.

$$E_a = E(Adsorbate/Cr_2O_3) - E(Adsorbate) - E(Cr_2O_3)$$
(4)

The first term is the energy of the optimized configuration for the relaxed adsorbate molecule bonded to the clean surface. The second term is the energy of the optimized gas-phase adsorbate molecule (isolated), and the third term is the energy of the optimized surface. Based on this definition, negative values of E_a correspond to stable configurations. The structures of each isolated molecule were optimized first; they are called "simples systems":

- SO_2 on $Cr_2O_3(0001)$
- CH_4 on $Cr_2O_3(0001)$
- O_2 on $Cr_2O_3(0001)$
- S on $Cr_2O_3(0001)$
- CO on $Cr_2O_3(0001)$
- CO_2 on $Cr_2O_3(0001)$

Using the results from the most stable geometries of these systems, molecules of other chemical species were adsorbed; they are called "compound systems":

$E_a(eV)$	X-Y Plane	X-Z Plane	$D\left[S - O_{ads}\right](\mathring{A})$	$D\left[S-Cr\right](\mathring{A})$
-3.09			1.51	1.77

Table 2: Most stable geometry of the SO_2 system on Cr_2O_3 optimized with the DFT+U formalism and its activation energy.

- SO_2 on O_2 preadsorbed on $Cr_2O_3(0001)$.
- CH_4 on O_2 preadsorbed on $Cr_2O_3(0001)$.
- O_2 on SO_2 , preadsorbed on $Cr_2O_3(0001)$.

In a first stage, the calculations were performed using pseudopotentials based on the local density approximation (LDA) [5, 6]. Then, in order to achieve greater accuracy, pseudopotentials within the generalized gradient approximation (GGA) were used.

3 Results

3.1 Simple systems: adsorbate on substrate

- SO_2 on $Cr_2O_3(0001)$: after generating a clean surface and optimizing each isolated molecule, a SO_2 molecule was adsorbed on the $Cr_2O_3(0001)$ surface in different positions and geometries. The most stable configuration was found in previous studies [2] using the LDA pseudopotentials. The final results are listed in Table 2.

The adsorption of SO_2 on the Cr_2O_3 surface is a chemisorption process involving sulfite species formation and surface oxygen atoms: the sulfur atom binds to one surface oxygen atom, while sulfur dioxide oxygen atoms are bound to chromium atoms.

- CH_4 on $Cr_2O_3(0001)$: one CH_4 molecule was adsorbed on the $Cr_2O_3(0001)$ surface in different positions and geometries. The most stable results, which are summarized in Table 3, indicate that no molecular adsorption occurred on the surface under study.

- O_2 on $Cr_2O_3(0001)$: the most stable results for this system are shown in Table 4 and Fig. 2. The two atoms of the oxygen molecules are adsorbed on the same surface chromium atom.

$E_a(eV)$	X-Y Plane	X-Z Plane	$D\left[C - Cr_{sup}\right](\mathring{A})$	$D\left[H_1 - Cr_{sup}\right](\mathring{A})$	$D\left[H_2 - Cr_{sup}\right](\mathring{A})$
-0.0159		×	5.255	5.836	5.438
-0.0138			5.235	5.532	4.155
-0.014			3.783	4.752	4.124

Table 3: Most stable geometries of the CH_4 system on Cr_2O_3 optimized with the DFT+U formalism and their activation energies.

$E_a(eV)$	X-Y Plane	X-Z Plane	$D\left[O_1 - O_2\right](\mathring{A})$	$D\left[O_1 - Cr_3\right](\mathring{A})$	$D\left[O_2 - Cr_2\right](\mathring{A})$
-0.478		1 AL	1.214	3.054	2.136
-0.446		No.	1.344	2.002	1.993

Table 4: Most stable geometries of the O_2 molecularly adsorbed on Cr_2O_3 optimized with the DFT+U formalism and their activation energies.



Figure 2: Geometric details of the first structure listed in Table 4.

$E_a(\text{eV})$	X-Y Plane	X-Z Plane	$D\left[O_1 - O_2\right](\mathring{A})$	$D\left[O_1 - Cr_3\right](\mathring{A})$	$D\left[O_2 - Cr_2\right](\mathring{A})$
-0.474			2.466	1.585	3.85

Table 5: Most stable geometry of the dissociative oxygen adsorption on Cr_2O_3 optimized with the DFT+U formalism and its activation energy.

- Dissociative O_2 adsorption on $Cr_2O_3(0001)$: in this system, two O_2 atoms were placed on the surface in order to study the stability of the adsorbate molecule and the possible availability of oxygen atoms to oxidize methane to CO_2 . The most stable dissociative adsorption configuration shows both O_2 atoms adsorbed on the same chromium atom in the first layer (see Table 5 and Fig. 3).

- S on $Cr_2O_3(0001)$: a sulfur atom was adsorbed on the $Cr_2O_3(0001)$ surface at five sites: on one chromium atom of the first layer, obtaining the lowest adsorption energy of -0.594 eV; on a chromium atom of the third layer; and on an oxygen atom of the second, fourth and fifth layers [2, 5].

- CO on $Cr_2O_3(0001)$: one CO molecule was adsorbed on the $Cr_2O_3(0001)$ surface, obtaining an adsorption energy of -2.33 eV in the most stable geometry [5].

- CO_2 on $Cr_2O_3(0001)$: one CO_2 molecule was adsorbed in different positions and geometries. The system obtained was more unstable than that of CO on the same surface, with an adsorption energy of -0.81 eV for the most stable geometry (see Fig. 5).



Figure 3: Geometric details of the first structure listed in Table 5.



Figure 4: Most stable optimized structure of S adsorbed on the $Cr_2O_3(0001)$ surface.



Figure 5: Most stable optimized geometry of CO_2 adsorbed on the $Cr_2O_3(0001)$ surface.



Figure 6: Most stable optimized geometry of CH_4 on O_2 dissociatively adsorbed on the $Cr_2O_3(0001)$ surface.

3.2 Complex systems: adsorption of one species on another one preadsorbed on the substrate

After obtaining the most stable geometries for the adsorption of one molecule on the catalytic surface, we investigated the adsorption of one of the species under study on another one preadsorbed on $Cr_2O_3(0001)$. Thus, the interaction between gas species on the surface was examined, obtaining the adsorption energies of the most stable configuration, together with the bond lengths, the variations in the angles formed between the atoms of those species, and the new compounds formed once the interactions between them had ceased.

- CH_4 on an O_2 molecule preadsorbed on $Cr_2O_3(0001)$: the adsorption of one methane molecule on the $Cr_2O_3(0001)$ surface was studied using the most stable geometry for the adsorption of one O_2 molecule. No stable geometry was found, indicating that methane does not adsorb on the O_2 molecule adsorbed on $Cr_2O_3(0001)$.

- CH_4 on O_2 dissociatively adsorbed on $Cr_2O_3(0001)$: a CH_4 molecule was placed in different positions on an O_2 molecule dissociatively adsorbed on the substrate. In this case, as in the above, the most stable geometry for the dissociative O_2 adsorption on $Cr_2O_3(0001)$ was used. The dissociation of the methane molecule was obtained, as well as the formation of OH species and methoxy groups $(-O - CH_3)$ as shown in Fig. 6.



Figure 7: Adsorption geometry ($E_a = -1.4982eV$) of CH_4 on O_2 dissociatively adsorbed on the $Cr_2O_3(0001)$ surface.



Figure 8: Most stable optimized geometry of CH_4 on SO_2 preadsorbed on the $Cr_2O_3(0001)$ surface.

The most stable geometry has an energy of -1.7914 eV. The next energy found was -1.4982 eV, whose adsorption geometry is depicted in Fig 7.

- CH_4 on SO_2 , preadsorbed on $Cr_2O_3(0001)$: in the most stable geometry, with an energy of -0.2758 eV, a hydroxyl with an O atom of the third substrate layer is formed, while sulfur binds to the methyl group (CH_3) and SO_2 oxygen atoms to the surface Cr atoms, as shown in Fig. 8.

- O_2 on SO_2 , preadsorbed on $Cr_2O_3(0001)$: an adsorption energy of -1.00 eV was found for the most stable configuration; oxygen dissociation led to the formation of SO_3 species on the surface.



Figure 9: Most stable optimized geometry of O_2 on SO_2 preadsorbed on the $Cr_2O_3(0001)$ surface.

4 Discussion and Conclusions

The adsorption of CH_4 on $Cr_2O_3(0001)$ is not stable; the presence of molecularly adsorbed oxygen does not favor adsorption. However, in the presence of sulfur dioxide or atomic oxygen, CH_4 may decompose to form hydroxyl species, methyl groups adsorbed on sulfur and/or methoxy group $(R - O - CH_3)$ atoms. SO_2 adsorption leads to the formation of sulfite species involving surface or preadsorbed oxygen atoms. No sulfate species formation was observed. O_2 adsorption in the presence of SO_2 favors oxygen dissociation to form sulfite species. Molecular and dissociative O_2 adsorption occurs on this substrate with almost the same energy. The most stable configuration is obtained with the two atoms on the same Cr atom. The presence of SO_2 favors the dissociative adsorption of oxygen to form sulfite species. In previous work [4] we experimentally showed that the activation energy of reaction (3) is lower than that of reaction (2) under stoichiometric conditions. The presence of SO_2 would activate the catalyst surface favoring oxygen dissociation and methane decomposition. FTIR spectroscopy studies on samples of the catalysts used in reactions (2) and (3) allowed us to identify hydroxyl and methyl species as the ones found in this work, as well as additional products of methane dehydrogenations [5]. These results will be presented in a future paper together with further DFT calculations. The stability of the oxygen molecule adsorbed on the Cr_2O_3 surface may affect the interaction of gas-phase SO_2 with adsorbed oxygen and deserves a more detailed study to be included in a future publication. The size of the cell used in the calculations as well as periodic boundary conditions simulate experimental conditions with high adsorbate coverage. The experiments were also performed in a continuous-flow fixed-bed reactor under conditions that are not directly comparable to theoretical conditions. Nevertheless, from previous comparisons with SO_2 desorption, reliable conclusions from calculations based on DFT+U can be drawn [3]. Then, we conclude that these calculations may provide useful information on the elementary stages of reactions (1)–(3) in order to establish the reaction mechanism.

5 Acknowledgments

This work was supported by Consejo de Investigaciones Científicas y Técnicas (CONICET), Agencia Nacional de Promoción Científica y Tecnológica (ANPCyT), Universidad Nacional de La Plata and the Faculty of Chemistry and Engineering Fray Roger Bacon

References

- [1] 1- I. Coria, S. Medina, I.R. Ramos, A.G. Ruiz, Energeia 1, 49-65 (2003).
- [2] I. D. Coria, O. Carattoli, S. Hernandez Guiance, Y. Malik, Energeia 5, 30-39 (2007).
- [3] 3- V.A. Ranea, S.N. Hernandez, S. Medina, I.M. Irurzun, I.D. Coria, E.E. Mola, Surface Science 605 489–493 (2011).
- [4] S. N. Hernandez Guiance, I. D. Coria, I. M. Irurzun, E. E. Mola, Chemical Physics Letters 660123-126 (2016).
- [5] S. N. Hernández Guiance. Estudio Teórico-Experimental de la Adsorción y Reducción Catalítica de SO₂ sobre Cr₂O₃/Al₂O₃ en Presencia de CH₄ y O₂ a Altas Temperaturas. Tesis Doctoral, Facultad de Ciencias Exactas, Universidad Nacional de La Plata, (2016).
- [6] M. Catti, G. Sandrone, G. Valerio, R. Dovesi, J. Phys. Chem. Solids 571735-1741(1996).
- [7] M.S.M. Barrera, J.F. Sanz, L. Alvarez, J. Odriozola, Phys. Rev. B 58 6057-6062 (1998).
- [8] J. Cline, A. Rigos, T. Arias, J. Phys. Chem. B 104 6195-6201 (2000).
- [9] X. Wang, J. Smith, Phys. Rev. B 68 201402 (2003).
- [10] A. Rohrbach, J. Hafner, G. Kresse, Phys. Rev. B 70125426 (2004).
- [11] S. N. Hernández Guiance. PhD Thesis. University of La Plata, Buenos Aires, Argentina, 2016.