

The Rouse ring chain with attractive harmonic potential of spherical symmetry.

Nail Fatkullin¹, Carlos Mattea¹, Kevin Lindt¹, Siegfried Stapf¹ and Margarita Kruteva²

¹*Technische Physik II/Polymerphysik, Technische Universität Ilmenau, D-98684 Ilmenau, Germany*

²*Jülich Centre for Neutron Science (JCNS-1) and Institute for Biological Information Processing (IBI-8),
Forschungszentrum Jülich GmbH, 52428 Jülich, Germany*

Corresponding authors: nfatkull@gmail.com

Abstract

We study the static and dynamic properties of a cyclic Rouse chain modified by the inclusion of an effective, spherically symmetric, attracting potential of entropic nature $U\{\vec{r}_n\} = \frac{3k_B T}{2} \sum_n \frac{(\vec{r}_n - \vec{r}_{cm})^2}{\tilde{R}^2}$,

$\vec{r}_{cm} = \frac{1}{N} \sum_n \vec{r}_n$ is the position vector of ring center of mass, \vec{r}_n is the position vector of the segment with number n , $k_B T$ is the Boltzmann constant multiplied on absolute temperature, \tilde{R} is a parameter of the potential, square of which is inverse to strength of the potential. It is shown that very weak potentials with $\tilde{R} > \frac{Nb}{6}$, N is the number Kuhn segments in polymer ring, b is the length of Kuhn segment, lead to dramatic compression of the polymer chain whose radius of inertia becomes much smaller compared to the free size

$\langle R_g^2 \rangle_{eq}^{1/2} = \sqrt{\frac{\tilde{R}b}{2}} \ll \sqrt{\frac{Nb^2}{12}}$. At values of the potential parameter of order $\tilde{R} \propto \frac{N^{2/3}}{\rho_s^{2/3} b}$, ρ_s is the

concentration of Kuhn segments in the melt, the concentration of the intrinsic segments of the polymer ring becomes of order ρ_s and the state of the polymer ring can be regarded as globular. The terminal relaxation

time of the polymer ring turns out to be of the order of $\tau_1 = \pi^2 \frac{\tau_s \tilde{R}^2}{b^2}$, the mean squared displacement of the

center of mass of the macromolecule during this time $\langle (\vec{r}_{cm}(t) - \vec{r}_{cm}(0))^2 \rangle = 2 \frac{\tilde{R}^2}{N} \ll 2 \langle R_g^2 \rangle_{eq}$, which can

lead to a pseudo plateau for the time dependence of the mean squared displacements of the polymer segments before entering the normal diffusion mode of motion.

1. Introduction.

In recent years, interest in polymeric systems containing ring macromolecules has increased markedly (see, for example, [1-16] and the literature cited therein. The absence of end segments in cyclic macromolecules, as it turned out, leads to serious differences in their conformations and dynamics in comparison with linear analogues of equal molecular mass. In particular, in melts linear macromolecules have conformations with sufficient accuracy close to ideal [17-22] and the mean square of their radius of gyration depends linearly on the molecular weight $R_{g,lin}^2 = \frac{Nb^2}{6}$, b is the length of Kuhn segment, N is the number of Kuhn segments per macromolecule. In the case of melts of cyclic macromolecules, the absence of end segments generates entropic interactions preventing mutual penetration of macromolecules into each other, which leads to a significant weakening of the molecular-mass dependence of the mean-square radius of gyration $R_{g,ring}^2 \propto b^2 N^\nu$, with, as show computer experiments, $\nu \approx \frac{2}{3}$, see, for example [6-7]. In other words, these additional topological constraints compared to linear macromolecules appear to be equivalent to effective intramolecular interactions of attraction to the center of inertia of rings, inducing their transition to more compact, globular conformations. The latter circumstance makes the analytical description of the structure and dynamics of cyclic macromolecules more complicated compared to their linear analogs, since even at the level of intramolecular interactions the non-Gaussian distribution of conformations gives rise to nonlinear equations of motion.

In the theory of dynamic properties of linear polymers, the Rouse model plays an important supporting role because it is exactly solvable [17-22]. Although it does not include entanglement effects, it can be at least phenomenological modified, for example, by constraints for chain motions only inside the tube for times smaller than the terminal relaxation time, as in the reptation tube model, to apply it satisfactorily even for highly entangled systems.

For the case of ring polymer melts, the Rouse model can be applied directly using appropriate boundary conditions for the ends of linear polymer chains, see for example [16]. In this case, ring macromolecules have a conformational distribution corresponding to a freely connected ring whose characteristic linear size is only $2^{1/2}$ times smaller than the linear size of linear chains containing the same number of Kuhn segments and mean squared radius of gyration scale as $R_{g,ring}^2 = \frac{1}{12} b^2 N$. In other words, this simplified approach does not take into account the effects of compression of polymer rings in melts associated with the above-mentioned topological constraints on mutual penetrations.

This compression effect can be at least a phenomenological accounted for by introducing a harmonic potential of spherical symmetry which attracts any of the ring segments to the ring centre of mass. The strength constant of this potential can be considered as a fitting parameter. After this modification, the model of a Rouse modified by a spherical attracting harmonically potential is still exactly analytically tractable and can play the role of a reference model for the dynamical properties of polymer rings. As far as we know, this model, although amenable to exact solution, has not yet been described in the literature, close models containing a modification of the Rouse model with an axially symmetric harmonic potential to study various aspects of the reptation model have been considered in the works [23,24]. In this paper, we describe the main properties of this model, which in our opinion are of independent scientific interest.

2. Theoretical part.

Consider a polymer ring formed of $N \gg 1$ Kuhn segments, the effective Hamiltonian, more precisely the effective intramolecular potential energy, is defined by the following expression:

$$H = \frac{3kT}{2} \sum_n \left(\frac{1}{b^2} \left(\frac{\partial \vec{r}_n}{\partial n} \right)^2 + \frac{(\vec{r}_n - \vec{r}_{cm})^2}{\tilde{R}^2} \right), \quad (1)$$

where \tilde{R} is a parameter of the potential. The first term in the right-hand side of relation (1) describes the traditional effectively intramolecular entropic interactions of an ideal polymer chain (see, for example, [39-43]), the second term, which has the structure of a harmonic potential, is related to the effects of entropic compression of the polymer chain caused by topological constraints of mutual penetration of cyclic macromolecules into each other. Note also because that $N \gg 1$ we are using continuous limit and summation over n is equivalent to integration over n .

In the case where we have only one segment, its mean square distance from the centre of the potential is equal:

$$\langle \tilde{r}^2 \rangle = \tilde{R}^2 \quad (2)$$

In the following we will call \tilde{R} the characteristic radius of the harmonic potential. The larger this quantity, the wicker potential.

Equation of motion for Rouse ring is the following:

$$\zeta \frac{\partial \vec{r}_n(t)}{\partial n} = \frac{3kT}{b^2} \frac{\partial^2}{\partial n^2} \vec{r}_n(t) - \frac{3k_B T}{\tilde{R}^2} (\vec{r}_n(t) - \vec{r}_{cm}(t)) + \vec{f}_n^L(t), \quad (3)$$

where ζ is the segmental friction coefficient, $\vec{f}_n^L(t)$ is the stochastic Langevin force acting on segment with

number n at time moment t , $\vec{r}_{cm}(t) = \frac{1}{N} \sum_n \vec{r}_n(t)$ -is position vector of the center of mass considered polymer ring at time moment t , $\vec{r}_n(t)$ is the position vector of the segment with number n at time moment t , $k_B T$ is the Boltzmann constant multiplied on absolute temperature.

The ring architecture of the polymer chain is taken into account by means of the following boundary conditions:

$$\vec{r}_0(t) \equiv \vec{r}_N(t). \quad (4)$$

These boundary conditions lead to the following Fourier decomposition:

$$\vec{r}_n(t) = \vec{X}_0(t) + \sum_{p=1, \dots, N/2} \left(2\vec{X}_p(t) \cos\left(\frac{2\pi}{N} pn\right) + 2\vec{Y}_p(t) \sin\left(\frac{2\pi}{N} pn\right) \right). \quad (5)$$

The normal relaxation Rouse modes of the ring macromolecule can be calculated from the expression (5) by the inverse Fourier transform:

$$\begin{aligned} \vec{X}_p(t) &= \frac{1}{N} \int_0^N \vec{r}_n(t) \cos\left(\frac{2\pi}{N} pn\right) dn \\ \vec{Y}_p(t) &= \frac{1}{N} \int_0^N \vec{r}_n(t) \sin\left(\frac{2\pi}{N} pn\right) dn \end{aligned} \quad (6)$$

By substituting the decomposition (6) into the relation (1), we express the Hamiltonian through the normal Rouse modes of the ring macromolecule:

$$H = \frac{3kT}{2} \sum_{p=1, \dots, N/2} \left\{ \frac{8\pi^2}{Nb^2} p^2 + \frac{2N}{\tilde{R}^2} \right\} (\vec{X}_p^2(t) + \vec{Y}_p^2(t)). \quad (7)$$

Assuming that the different normal modes fluctuate independently of each other and have a normal Gaussian distribution, we obtain the following relation for their mean-square values:

$$\frac{1}{\langle \vec{X}_p^2 \rangle_{eq}} = \frac{1}{\langle \vec{Y}_p^2 \rangle_{eq}} = \left\{ \frac{8\pi^2 p^2}{Nb^2} + \frac{2N}{\tilde{R}^2} \right\}. \quad (8)$$

Further, from the relations (5), (8) and orthogonality of different normal modes, the following expression for the RMS radius of gyration of the ring macromolecule is obtained:

$$\begin{aligned}
\langle R_g^2 \rangle_{eq} &= \frac{1}{N} \int_0^N \langle (\vec{r}_n(t)) - \vec{X}_0(t)^2 \rangle \\
&= 2 \sum_p \left\{ \langle \vec{X}_p^2 \rangle_{eq} + \langle \vec{Y}_p^2 \rangle_{eq} \right\} = 2 \sum_{p=1 \dots N/2} \frac{1}{\frac{4\pi^2 p^2}{Nb^2} + \frac{N}{3\tilde{R}^2}}.
\end{aligned} \tag{9}$$

For extremely weak harmonic potential, when $\frac{N^2 b^2}{4\pi^2} \ll \tilde{R}^2$ polymer ring has ideal, no perturbed size, see, for example [17]:

$$R_{g,ideal}^2 = \frac{Nb^2}{12}. \tag{10}$$

For large values we have the globular state for the Rouse ring:

$$\begin{aligned}
\langle R_g^2 \rangle_{eq} &\approx \int_1^{N/2} \frac{dp}{\frac{4\pi^2 p^2}{Nb^2} + \frac{N}{\tilde{R}^2}} = \frac{\tilde{R}b}{\pi} \left(\arctg\left(\frac{\pi\tilde{R}}{b}\right) - \arctg\left(\frac{2\pi\tilde{R}}{Nb}\right) \right) \\
&= \begin{cases} \frac{1}{2}\tilde{R}b & \text{if } \frac{Nb}{2\pi} \gg \tilde{R} \gg \frac{b}{\pi} \\ \tilde{R}^2 & \text{if } \tilde{R} \ll \frac{b}{\pi} \end{cases}.
\end{aligned} \tag{11}$$

The limit $\tilde{R} \ll \frac{b}{\pi}$ has mainly academic interest. And for interesting us case $\frac{Nb}{2\pi} \gg \tilde{R} \gg \frac{b}{\pi}$ we see that

$\langle R_g^2 \rangle_{eq} = \frac{1}{2}\tilde{R}b \ll \tilde{R}^2$. Recall that \tilde{R} is the inverse measure of the strength of the harmonic potential and it

is equal to the typical distance at which a potentially isolated polymer segment will be separated from the

center, see the expression (2), $\langle R_g^2 \rangle_{eq}^{1/2} = \sqrt{\frac{\tilde{R}b}{2}} \ll \tilde{R}$. When the polymer segment is not separated and is

located in the polymer ring, its typical distance from the center of mass is substantially smaller. This effect is directly related to the linear structure of the polymer ring and reflects the fact that there are neighboring segments in close proximity to any segment, resulting in an enhanced attraction by the center of potential.

Expressions for the decay rates of the normal modes, i.e., the inverse relaxation times, can be obtained by differentiating the relation (5) in time using the equations of motion (3). The result is as follows:

$$\frac{1}{\tau_p} = \frac{4}{\tau_s} \left\{ \left(\frac{p}{N} \right)^2 + \frac{1}{4\pi^2} \frac{b^2}{\tilde{R}^2} \right\} = \frac{1}{2\pi^2 \tau_s N} \frac{b^2}{\langle \bar{X}_p^2 \rangle} = \frac{1}{2\pi^2 \tau_s N} \frac{b^2}{\langle \bar{Y}_p^2 \rangle}, \quad (12)$$

with the segmental relaxation time $\tau_s = \frac{\zeta b^2}{3\pi^2 kT}$.

Note that the relaxation times of the long-wave Rouse modes with $p \ll \frac{1}{2\pi} \frac{bN}{\tilde{R}} = \frac{1}{4\pi} \frac{b^2 N}{\langle R_g^2 \rangle_{eq}}$ cease to depend on the mode number.

The mean squared displacement of ring segments can be derived from the expression (5):

$$\langle (\bar{r}_n(t) - \bar{r}_n(0))^2 \rangle = \langle (\bar{X}_0(t) - \bar{X}_0(0))^2 \rangle + 4 \sum_{p=1, \dots, N/2} [\langle \bar{X}_p^2 \rangle + \langle \bar{Y}_p^2 \rangle] \left(1 - \exp \left\{ -\frac{t}{\tau_p} \right\} \right). \quad (13)$$

The first contribution in the right part of the expression (13) is connected with the mean squared displacement of the center of mass, the second part, i.e. the sum over the normal modes $p = 1, \dots, N/2$ describes motion in coordinate system connected with center of mass.

For times $\tau_s \ll t \ll \frac{4\pi^2 \tau_s \langle R_g^2 \rangle_{eq}^2}{b^4}$ in the right part of the expression (13) dominates the second term

and we have anomalous Rouse diffusion

$$\begin{aligned} \langle (\bar{r}_n(t) - \bar{r}_n(0))^2 \rangle &\approx 4 \sum_{p=1, \dots, N/2} [\langle \bar{X}_p^2 \rangle + \langle \bar{Y}_p^2 \rangle] \left(1 - \exp \left\{ -\frac{t}{\tau_p} \right\} \right) \\ &= 8 \sum_{p=1, \dots, N/2} \langle \bar{X}_p^2 \rangle \left(1 - \exp \left\{ -\frac{t}{\tau_p} \right\} \right) \approx \frac{2b^2}{\pi^{3/2}} \left(\frac{t}{\tau_s} \right)^{1/2} \end{aligned} \quad (14)$$

For longer times $\frac{4\pi^2 \tau_s \langle R_g^2 \rangle_{eq}}{b^4} \ll t \ll 6\pi^2 \tau_s \frac{\langle R_g^2 \rangle_{eq} N}{b^2}$ the same term still dominates, but the time dependence disappears and a regime of quasi-limited diffusion sets in:

$$\langle (\bar{r}_n(t) - \bar{r}_n(0))^2 \rangle \approx 4 \sum_{p=1, \dots, N/2} [\langle \bar{X}_p^2 \rangle + \langle \bar{Y}_p^2 \rangle] = 2 \langle R_g^2 \rangle_{eq}. \quad (15)$$

Only for longer times $t \gg 6\pi^2 \tau_s \frac{\langle R_g^2 \rangle_{eq} N}{b^2}$ the first term in right part of the expression (13) describing diffusion of ring's center of mass starts dominate:

$$\left\langle (\vec{r}_n(t) - \vec{r}_n(0))^2 \right\rangle \approx \left\langle (\vec{X}_0(t) - \vec{X}_0(0))^2 \right\rangle = 6 \frac{b^2}{3\pi^2} \frac{t}{\tau_s N}. \quad (16)$$

Incoherent dynamical structure factor of ring macromolecules is given by the following relation:

$$S^{incoh}(k;t) \equiv \frac{1}{N} \sum_n \left\langle \exp \left\{ i\vec{k} \cdot (\vec{r}_n(t) - \vec{r}_n(0)) \right\} \right\rangle = \frac{1}{N} \sum_n \left\langle \exp \left\{ -\frac{1}{6} k^2 \left\langle (\vec{r}_n(t) - \vec{r}_n(0))^2 \right\rangle \right\} \right\rangle. \quad (17)$$

Coherent dynamical structure factor

$$\begin{aligned} S^{coh}(k;t) &\equiv \frac{1}{N} \sum_{n,m} \left\langle \exp \left\{ i\vec{k} \cdot (\vec{r}_n(t) - \vec{r}_m(0)) \right\} \right\rangle = \frac{1}{N} \sum_{n,k} \left\langle \exp \left\{ -\frac{1}{6} k^2 \left\langle (\vec{r}_n(t) - \vec{r}_m(0))^2 \right\rangle \right\} \right\rangle \\ &= \frac{1}{N} \sum_{n,m} \varphi_{nm}(k,t) \end{aligned} \quad (18)$$

$$\begin{aligned} \varphi_{nm}(k,t) &\equiv \left\langle \exp \left\{ i\vec{k} \cdot (\vec{r}_n(t) - \vec{r}_m(0)) \right\} \right\rangle \\ &= \exp \left\{ -\frac{k^2 \left\langle (\vec{X}_0(t) - \vec{X}_0(0))^2 \right\rangle + 8 \sum_{p=1, \dots, N/2} \left\langle \vec{X}_p^2 \right\rangle \left(1 - \exp \left\{ -\frac{t}{\tau_p} \right\} \cos \left(\frac{2\pi p}{N} (n-m) \right) \right)}{6} \right\}. \end{aligned} \quad (19)$$

3. Discussion.

We investigated the properties of a simple model, which allows us to carry out a sufficiently complete and accurate analytic study: the Rouse ring chain modified by adding an attractive harmonic potential of spherical symmetry. In spite of significant simplifications, the model has important nontrivial properties.

The model clearly illustrates the high sensitivity of the polymer ring conformation to the intensity of the attractive potential $U\{\vec{r}_n\} = \frac{3k_B T}{2} \sum_n \frac{(\vec{r}_n - \vec{r}_{cm})^2}{\tilde{R}^2}$ for polymer rings containing a large number of Kuhn

segments $N \gg 1$. As it follows from relation (11) at $\frac{Nb}{2\pi} \gg \tilde{R}$ the polymer rings experience strong compression in comparison with the ideal state and their characteristic linear dimensions become much smaller than the ideal rings. For example, if we consider a very weak attractive potential

$$U\{\vec{r}_n\} = \frac{3k_B T}{2} \sum_n \frac{\rho_s^{4/3} b^2}{N^{4/3}} (\vec{r}_n - \vec{r}_{cm})^2, \quad (20)$$

where ρ_s is the concentration of Kuhn segments in the melt, the radius of inertia of the ring is of the order of

$R_g \propto \rho_s^{-1/3} N^{1/3} \ll \sqrt{\frac{Nb^2}{12}}$, the concentration of the intrinsic ring segments inside the globule becomes comparable to the total concentration of Kuhn segments in the melt. Qualitatively similar behavior was observed in recent computer simulations [4,5].

Another feature of the model is related to the fact that the attractive potential (1) does not change the self-diffusion coefficient of the polymer ring, but strongly shortens the terminal relaxation time compared to the Rouse relaxation time, see relation (12):

$$\tau_1 \cong \pi^2 \frac{\tau_s \tilde{R}^2}{b^2} \ll \tau_R^2 = \tau_s N^2. \quad (21)$$

At times of order τ_1 , the mean squared displacements of the ring segments reach saturation, asymptotically approaching $2\langle R_g^2 \rangle_{eq} = \tilde{R}b$, while the mean squared displacement of the center of mass is even much smaller and only at much larger times $t \gg \tau_1 N$ begin to dominate. Effectively, it will lead to the fact that the transition to the normal diffusion regime will be prolonged for a long time interval $\tau_1 \leq t \leq \tau_1 N$, during which the time dependence of the mean-squared displacement of the segments will slow down demonstrating the quasi-plateau. Note also that the anomalous behavior on the normal diffusion regime in melts of cyclic macromolecules has been repeatedly noted in computer experiments (see, for example, [4,12]). Probably, though simplified, it is reflected already in the discussed strongly simplified model.

References.

1. Rubinstein, M. Dynamics of Ring Polymers in the Presence of Fixed Obstacles. *Phys. Rev. Lett.* **1986**, 57, 3023–3026, DOI: 10.1103/PhysRevLett.57.3023
2. Kruteva, M.; Allgaier, J.; Richter, D. Topology Matters: Conformation and Microscopic Dynamics of Ring Polymers. *Macromolecules* **2023**, 56, 7203–7229, DOI: 10.1021/acs.macromol.3c00560
3. Ge, T.; Panyukov, S.; Rubinstein, M. Self-Similar Conformations and Dynamics in Entangled Melts and Solutions of Nonconcatenated Ring Polymers. *Macromolecules* **2016**, 49, 708–722, DOI: 10.1021/acs.macromol.5b02319

4. Dell, Z. E.; Schweizer, K. S. Intermolecular Structural Correlations in Model Globular and Unconcatenated Ring Polymer Liquids. *Soft Matter* **2018**, *14*, 9132–9142, DOI: 10.1039/C8SM01722K
5. Mei, B.; Dell, Z. E.; Schweizer, K. S. Microscopic Theory of Long-Time Center-of-Mass Self-Diffusion and Anomalous Transport in Ring Polymer Liquids. *Macromolecules* **2020**, *53*, 10431–10445, DOI: 10.1021/acs.macromol.0c01737
6. Halverson, J. D.; Lee, W. B.; Grest, G. S.; Grosberg, A. Y.; Kremer, K. Molecular dynamics simulation study of nonconcatenated ring polymers in a melt. I. Statics. *J. Chem. Phys.* **2011**, *134*, 204904., DOI: 10.1063/1.3587137
7. Halverson, J. D.; Lee, W. B.; Grest, G. S.; Grosberg, A. Y.; Kremer, K. Molecular dynamics simulation study of nonconcatenated ring polymers in a melt. II. Dynamics. *J. Chem. Phys.* **2011**, *134*, 204905. DOI 10.1063/1.3587138
8. Tsalikis, D. G.; Mavrantzas, V. G.; Vlassopoulos, D. Analysis of Slow Modes in Ring Polymers: Threading of Rings Controls Long-Time Relaxation. *ACS Macro Lett.* **2016**, *5*, 755–760, DOI: 10.1021/acsmacrolett.6b00259
9. Kruteva, M.; Allgaier, J.; Monkenbusch, M.; Porcar, L.; Richter, D. Self-similar Polymer Ring Conformations Based on Elementary Loops: A Direct Observation by SANS. *ACS Macro Lett.* **2020**, *9*, 507–511, DOI: 10.1021/acsmacrolett.0c00190
10. Kruteva, M.; Monkenbusch, M.; Allgaier, J.; Holderer, O.; Pasini, S.; Hoffman, I.; Richter, D. Self-Similar Dynamics of Large Polymer Rings: A Neutron Spin Echo Study. *Phys. Rev. Lett.* **2020**, *125*, 238004, DOI: 10.1103/PhysRevLett.125.238004
11. Kruteva, M.; Allgaier, J.; Monkenbusch, M.; Hoffmann, I.; Richter, D. Structure and dynamics of large ring polymers. *J. Rheol.* **2021**, *65*, 713–727, DOI: 10.1122/8.0000206
12. Halverson, J. D.; Kremer, K.; Grosberg, A. Y. Comparing the results of lattice and off-lattice simulations for the melt of nonconcatenated rings. *J. Phys. A: Math. Theor.* **2013**, *46*, 065002, DOI: 10.1088/1751-8113/46/6/065002
13. Pasquino, R.; Vasilakopoulos, T. C.; Cheol Jeong, Y.; Lee, H.; Rogers, S.; Sakellariou, G.; Allgaier, J.; Takano, A.; Brás, A. R.; Chang, T.; Gooßen, S.; Pyckhout-Hintzen, W.; Wischniewski, A.; Hadjichristidis, N.; Richter, D.; Rubinstein, M.; Vlassopoulos, D. Viscosity of Ring Polymer Melts. *ACS Macro Lett.* **2013**, *2*, 874–878, DOI: 10.1021/mz400344e
14. Tu, M. Q.; Davydovich, O.; Mei, B.; Singh, P. K.; Grest, G. S.; Schweizer, K. S.; O'Connor, T. C.; Schroeder, C. M. Unexpected Slow Relaxation Dynamics in Pure Ring Polymers Arise from Intermolecular Interactions. *ACS Polym. Au* **2023**, *3*, 307-317, DOI: 10.1021/acspolymersau.2c00069
15. K. L. Ngai, On the $Z^{5.8}$ -dependence of viscosity of polymer rings over the range $15 < Z_w \leq 300$ of the entanglement number, *J Polym Sci.* 2024;62:174–181, DOI: 10.1002/pol.20230624 .

16. Shota Goto; Kang Kim, Nobuyuki Matubayasi, Effects of chain length on Rouse modes and non-Gaussianity in linear and ring polymer melts, *J. Chem. Phys.* 155, 124901 (2021), <https://doi.org/10.1063/5.0061281>
17. Yamakawa, Hiromi, Modern Theory of Polymer Solutions, Electronic Edition. Harper & Row, 1971, 434p.
18. M. Doi, S. F. Edwards, The Theory of Polymer Dynamics (Oxford Clarendon Press, 1989).
19. A. Y. Grosberg, A. R. Khokhlov, Statistical Physics of Macromolecules (AIP Press, 1994).
20. M. Rubinstein, R. H. Colby, Polymer Physics (Oxford University Press, 2003).
21. P. G. de Gennes, Scaling Concepts in Polymer Physics (Cornell University Press, Ithaca, 1979).
22. G. R. Strobl, The Physics of Polymers (Springer, 1997).
23. A. Denisov, M. Kroutieva, N. Fatkullin, R. Kimmich, Segment diffusion and nuclear magnetic resonance spin-lattice relaxation of polymer chains confined in tubes: Analytical treatment and Monte Carlo simulation of the crossover from Rouse to reptation dynamics *J. Chem. Phys.* 2002, 116, 5217, <https://doi.org/10.1063/1.1451242>.
24. Maxim Dolgushev, Margarita Krutyeva, Polymer Chain Confined Into a Harmonic Radial Potential, *Macromol. Theory Simul.* 2012, 21, 565–572, DOI: 10.1002/mats.201200045