Enhancing the hyperpolarizability of crystals with quantum geometry

Wojciech J. Jankowski,^{1,*} Robert-Jan Slager,^{2,1} and Michele Pizzochero^{3,4,†}

¹TCM Group, Cavendish Laboratory, University of Cambridge, J. J. Thomson Avenue, Cambridge CB3 0HE, UK

²Department of Physics and Astronomy, University of Manchester, Oxford Road, Manchester M13 9PL, UK

³Department of Physics, University of Bath, Claverton Down, Bath BA2 7AY, UK

⁴School of Engineering and Applied Sciences, Harvard University, Cambridge, MA 02138, USA

(Dated: February 6, 2025)

We demonstrate that higher-order electric susceptibilities in crystals can be enhanced and understood through nontrivial topological invariants and quantum geometry, using one-dimensional π -conjugated chains as representative model systems. First, we show that the crystalline-symmetry-protected topology of these chains imposes a lower bound on their quantum metric and hyperpolarizabilities. Second, we employ numerical simulations to reveal the tunability of non-linear, quantum geometry-driven optical responses in various onedimensional crystals in which band topology can be externally controlled. Third, we develop a semiclassical picture to deliver an intuitive understanding of these effects. Our findings offer a firm interpretation of otherwise elusive experimental observations of colossal hyperpolarizabilities and establish guidelines for designing topological materials of any dimensionality with enhanced non-linear optical properties.

Introduction.— Non-linear optics offers a rich platform to explore a broad range of intriguing phenomena, with implications ranging from fundamental science to engineering [1]. One-dimensional crystals, most notably π -conjugated linear chains [2, 3], constitute prime examples to probe enhanced optical responses at non-linear orders. Because these crystals are centrosymmetric, i.e., they feature an inversion symmetry, their optical responses occur at odd orders in optical fields. The first- and third-order optical responses of onedimensional π -conjugated chains have long been investigated, both experimentally [3, 4] and computationally [5, 6]. Of central interest in this context is the third-order hyperpolarizability, i.e., the third-order electric susceptibility $\chi^{(3)}$ in the static limit of vanishing optical field frequency, $\omega \rightarrow 0$, which quantifies the non-linear polarization response, $P^{(3)} = \chi^{(3)} E_x^3$, to electric field E_x . In π -conjugated chains, $\chi^{(3)}$ is known to acquire colossal values. For example, $\chi^{(3)}$ was inferred to be as high as 10^{-18} m²/V² in polyacetylene [1], 10^{-19} m²/V² in polydiacetylene, and 10^{-20} m²/V² in polyarylenes [3]. This unusually large hyperpolarizability has been heuristically ascribed to the responses of p_z -electrons forming the conjugated π -bonds. However, a rigorous and general theoretical understanding of the origin of these non-linear optical properties remains yet to be achieved.

In this Letter, we bridge this gap in knowledge by deploying the modern notions of band topology and quantum geometry. We show that the crystalline-symmetry-protected topology of π -conjugated chains induces a lower bound on the quantum metric, and thus on the hyperpolarizability. Then, we use numerical simulations to demonstrate the tunability of non-linear, quantum geometry-driven optical responses of a variety of one-dimensional crystals in which the band topology is controllable by an external parameter, such as lattice strain. Finally, we propose a general semiclassical picture to



FIG. 1. Crystalline topology and quantum geometricallyenhanced hyperpolarizability in one-dimensional crystals. (a) Schematic illustration of a one-dimensional inversion-symmetric model system with a topological invariant \mathbb{Z}_2 reflected by a Wannier charge center shift $\langle x \rangle$ and by the presence of a symmetry-protected exponentially-localized edge state, $|\psi_{edge}\rangle$. The model system with unit cell parameter a realizes a bipartite basis A, B, and effective hoppings t_1, t_2 across bonds with lengths a_1, a_2 , and is coupled to an optical field $E_x(\omega)$ introduced by photons with energy $\hbar\omega$. The minimal spread of the Wannier function $\langle \Delta x^2 \rangle$ is topologically-bounded, and evaluates to the band-averaged quantum metric $\langle g_{rr} \rangle$ [7], which determines the non-linear polarizability. (b) Control of the band gap and band topology with lattice strain (λ) across a topological phase transition (TPT). (c) Discontinuous control of the non-linear optical properties, such as the time-dependent third-order polarization $P^{(3)}(t)$ from a three-photon coupling, across a strain-induced TPT.

explain these remarkable optical properties, based on the scaling of quantum metric and band gaps with external param-

^{*} wjj25@cam.ac.uk

[†] mp2834@bath.ac.uk



FIG. 2. Quantum geometry and (non-)linear optics in one-dimensional crystals. (a) Quantum metric (red) over momentum-space as a function of the lattice strain parameter (λ) realized in the effective low-energy Hamiltonian. The critical strain ($\lambda = \lambda_c$) induces a topological phase transition across which the metric scales up at the band edge, overcoming the minimal average metric value per BZ (blue) necessary for satisfying the topological bound. (b) Band-averaged metric $\langle g_{xx} \rangle$ as a function of strain and hopping amplitude ratio t_2/t_1 . The corresponding optical absorptivity is manifestly larger and topologically lower-bounded in the topologically nontrivial phase. (c) Spectral resolution of strain-dependent optical conductivity $\sigma_{xx}(\omega)$ and cutoff (Λ) dependent optical weights $W_{xx}(\Lambda) = \int_0^{\Lambda} d\omega \frac{\sigma_{xx}(\omega)}{\omega}$ (black) in a topological chain with hoppings ($t_1 = 2.15 \text{ eV}, t_2 = 2.85 \text{ eV}$) as a function of the bounding value for $\Lambda \to \infty$ (blue). (d) Lattice strain control of the topologically-bounded hyperpolarizability $\chi^{(3)}$. Under the relatively-high values of strain λ/λ_0 , where λ_0 is a unit strain, the anomalous hyperpolarizability of the \mathbb{Z}_2 -topological phase can be quenched. In the subcritical strain limit, we find that due to distinct realized quantum metrics, the $\chi^{(3)}$ of a trivial phase (red) is multiple times smaller than the $\chi^{(3)}$ of a topological phase (blue) with identical band energies. At vanishing strain, we note that the effective model fitted to the t_1/t_2 of polyacetylene yields $\chi^{(3)} = 8 \times 10^{-19} \text{ m}^2/\text{V}^2$, in excellent agreement with the corresponding experimental value, $\chi^{(3)} \approx 10^{-18} \text{ m}^2/\text{V}^2$ [2–4].

eters. Overall, our findings provide a novel interpretation of otherwise elusive experimental observations, along with guiding principles for identifying and engineering materials for non-linear optics.

Ouantum geometry and topology in one dimension.— Over the past several years, crystalline topologies have been thoroughly investigated [8–13], culminating in a rather uniform view upon comparing momentum space constraints [11] and real space (Wannierizability) conditions [12, 13]. Within this framework, taking into account the fact that an exponentiallylocalized Wannier basis [14] can be always constructed [15] in one spatial dimension, it is directly inferred that the only form of nontrivial electronic topology is that of an obstructed limit. The topology [16, 17] arises from the interplay of band wavefunction $(|\psi_{n\mathbf{k}}\rangle = e^{i\mathbf{k}\cdot\mathbf{r}} |u_{n\mathbf{k}}\rangle)$ windings with additional symmetries, such as chiral or inversion (\mathcal{I}) symmetry [18]. Under \mathcal{I} -symmetry, in nonmagnetic systems, the topological invariant is determined by the band parity eigenvalues, $\delta_k = \pm 1$ at inversion-symmetric momenta, $k = 0, \pi/a$, where a is the lattice constant, which coincides with the Fu-Kane formula [18]: $v_{\rm FK} = (1 - \delta_0 \delta_{\pi/a})/2 \in \mathbb{Z}_2$. At the same time, the band topology of obstructed insulators provides for the minimal spread $\langle \Delta x^2 \rangle$ of the exponentially-localized Wannier functions [7], as schematically presented in Fig. 1(a). Furthermore, this can be understood with the notions of quantum geometry [19], and can be related to topological bounds [20].

We now elucidate how, in one-dimensional (1D) crystals, the crystalline topology gives rise to quantum geometry and, as a direct consequence, enhances their optical responses. We define a non-Abelian multiband quantum geometric tensor, $(\mathbf{Q}_{ij}^m)_{np} = \langle \partial_{k_i} u_{n\mathbf{k}} | u_{m\mathbf{k}} \rangle \langle u_{m\mathbf{k}} | \partial_{k_j} u_{p\mathbf{k}} \rangle$ over momentum space, with its real part, commonly known as the non-Abelian quantum metric, being $(\mathbf{g}_{ij}^m)_{np} = \text{Re} (\mathbf{Q}_{ij}^m)_{np}$ [19, 21, 22]. The multiband quantum metric encodes the optical transition dipole matrix elements, $(\mathbf{g}_{xx}^m)_{nn} = |\langle \psi_{n\mathbf{k}} | \hat{x} | \psi_{m\mathbf{k}} \rangle|^2$ [23, 24], which is at the heart of both linear and non-linear responses. The multiband quantum metric of electrons realizes lower bounds due to 1D crystalline topologies that translate into minimal values of (higher-order) optical susceptibilities,

$$\langle g_{xx} \rangle \equiv \sum_{m}^{\text{unocc}} \sum_{k} \text{Tr } \mathbf{g}_{xx}^{m} \ge \frac{a^{2}}{4} v_{\text{FK}},$$
 (1)

where $\langle g_{xx} \rangle$ is band-averaged quantum metric and $v_{FK} \in \mathbb{Z}_2$ the Fu-Kane parity invariant protected by the \mathcal{I} -symmetry [18]. In the context of the maximally localized Wannier functions, $\langle g_{xx} \rangle = \langle \Delta x^2 \rangle$ [7]. Hence, the invariant imposes a lower-bound constraint on the spread of the wave-function in the real-space basis. The derivation of Eq. (1) is provided in Sec. I of the Supplemental Material (SM). In topological crystalline phases, any topologically nontrivial band realizes $v_{FK} = 1$. In the following, we demonstrate that this bound yields a topological enhancement of the multiband geometry-dependent response functions within the first and third-order optical responses.

First- and third-order optical responses.— The linear optical conductivity of a band insulator in the first-order response to an electric field of frequency ω reads [24],

$$\sigma_{xx}(\omega) = \frac{e^2}{2\hbar^2} \int_{\text{BZ}} \frac{\mathrm{d}k}{2\pi} \sum_{n,m} f_{nm} E_{mn} \text{Tr} \, \mathbf{g}_{xx}^m \delta(\omega - E_{mn}/\hbar), \quad (2)$$

where $f_{nm} = f_n - f_m$ are the thermal Fermi-Dirac occupation factors and E_{mn} is the difference in energy between valence and conduction bands *n* and *m*, respectively. For crystals possessing the same band structure, the distinct first order optical conductivity is purely determined by the multiband quantum metric. This allows one to uniquely distinguish band topologies by inducing the corresponding band geometries. Importantly, changes in band topology, as realized through external parameters such as lattice strain, as shown in Fig. 1(a,b), result in changes in the optical response. As we shall discuss in the representative case of π -conjugate chains and related one-dimensional crystals, lattice strain can be leveraged to engineer the opacity and optical non-linearities, as illustrated in Fig. 1(c).

While the second-order optical responses vanish under the \mathcal{I} -symmetry in centrosymmetric crystals, third-order responses remain finite and can be controlled with band geometry. In the static limit, the third-order susceptibility can be enhanced quadratically with the considered multiband quantum metric

$$\chi^{(3)} = \frac{e^4}{\varepsilon_0} \int_{\mathrm{BZ}} \frac{\mathrm{d}k}{2\pi} \sum_{n,m,p,q} \frac{(\mathbf{g}_{xx}^p)_{nm}(\mathbf{g}_{xx}^q)_{mn}}{E_{mn}E_{pn}E_{qn}},\tag{3}$$

where ε_0 is the vacuum permittivity. The derivation of Eq. (3) is provided in Sec. II of the SM [25].

While the enhancement of $\chi^{(3)}$ can be induced by nontrivial quantum geometry in the numerator, it can be further achieved through the tunable band gap magnitudes in the denumerator. Notably, materials with identical band gaps, yet with distinct crystalline topologies, realize distinguishable numerators, with topological phase experiencing a quadratic enhancement. By combining this enhancement with Eq. (1) and sum rules, we derive a fundamental topological lower bound on the hyperpolarizability of a nontrivial insulator,

$$\chi^{(3)} \ge \alpha^{(3)} \times \frac{a^{10}}{n^3},\tag{4}$$

where $\alpha^{(3)} = \frac{1}{2}\pi^3 e^4 m_e^3 \varepsilon_0^{-1} \hbar^{-6} = 6 \times 10^{50} \text{ m}^{-5}/\text{V}^2$, m_e is the electron mass, and *n* is the number density of electrons in the crystal. The derivation of Eq. (4) is provided in Sec. IV of the SM [25].

From models to real materials.— We next develop an effective, two-band Hamiltonian to capture the geometry induced by \mathbb{Z}_2 obstructed topology in the presence of lattice strain. This model is schematically depicted in Fig. 1(a). The Hamiltonian that minimally realizes such general phenomenology on a quasi-one-dimensional chain takes the form of a strained SSH model [26, 27],

$$H(k_x,\lambda) = \begin{pmatrix} 0 & t_1(\lambda) + t_2(\lambda)e^{-ik_xa(\lambda)} \\ t_1(\lambda) + t_2(\lambda)e^{ik_xa(\lambda)} & 0 \end{pmatrix}, \quad (5)$$

where $\lambda > 0$ is an external tensile stress parameter, $a(\lambda) \equiv a_1(\lambda) + a_2(\lambda)$ is the strain-renormalized lattice parameter with bond lengths $a_j(\lambda) = a_j(0)[1 + \lambda]$, and $t_j(\lambda) = t_j(0)e^{-\gamma_j[a_j(\lambda)-a_j(0)]}$ are the strain-dependent hopping amplitudes, where γ_j 's parameterize bond stiffness [28]. We validate our strain-dependent models with hopping parameters obtained from first-principles calculations [29]. We correspondingly present our numerical results in Fig. 2. In Fig. 2(a), we show how the profile of quantum metric g_{xx} over *k*-space, with dominant contributions at $k = \pi/a$ at the band inversion point, changes with the strain λ . Upon crossing the critical strain $\lambda = \lambda_c$, the band edge metric



3



FIG. 3. Examples of materials for crystalline topology-induced, quantum-geometrically enhanced non-linear optics. From top to bottom: polyacetylene, poly-(*p*-phenylene), polypentacene, and graphene nanoribbons. Under external control, such as lattice strains, these materials can realize \mathcal{I} -symmetry protected nontrivial \mathbb{Z}_2 topology and topologically-enhanced hyperpolarizability $\chi^{(3)}$, which culminates in non-linear polarization $P^{(3)}$. Further chemical functionalizations of such \mathbb{Z}_2 -topological materials, e.g., through perhalogenations, can provide a further knob to tune the quantum metric and higher-order susceptibilities.

contributions provides for an average $\langle g_{xx} \rangle$ that satisfies the bound in the topological phase ($v_{FK} = 1$). Fig. 2(b) presents a dependence of the optical weight, i.e., weighted integrated optical conductivity, or equivalently, integrated interband contribution to the imaginary part of dielectric constant $W_{xx} = \int_0^\infty d\omega \frac{\sigma_{xx}(\omega)}{\omega} = \frac{\pi e^2}{\hbar} \langle g_{xx} \rangle$, which is also lower-bounded by the topological invariant. In. Fig. 2(c), we benchmark the first-order optical conductivity and show how its contributions to the bounded optical weights gradually arise. Fig. 2(d) shows how the colossal values of $\chi^{(3)}$ arise with strain λ , before vanishing sharply upon transitioning to the trivial phase across the critical point. We remark that the value of $\chi^{(3)}$ at vanishing λ is in excellent agreement with experimental observations. Further details on the model-dependent parameterization and controllability of quantum geometry within π -conjugated chains are given in Sec. III of SM [25].

We stress that this model Hamiltonian and accompanying results are effectively realized by the low-energy bands of an ample variety of one-dimensional π -conjugate systems, such as polyacetylene [26, 27], polyacenes [30], polyphenylenes, and graphene nanoribbons [28], as overviewed in Fig. 3. Their low-energy valence and conduction bands are universally governed by an effective physics of hopping between the Wannier orbitals *A*, *B* that are predominantly constituted by the weighted combinations of the atomic orbitals with p_z character [26, 29, 30]. Indeed, the introduction of additional bands does not alter out conclusions, as we demonstrate in Sec. V of the SM [25], where we also provide an extended discussion of multiband models. The reason for this traces back to the fact that the additional bands will experience higher energy gaps E_{mn} , suppressing the $\chi^{(3)}$ contributions as $1/E_{mn}^3$. Furthermore, the metric similarly scales with $1/E_{mn}^2$ [cf. Fig. 2(a)], which provides only a marginal contribution to the numerator of $\chi^{(3)}$.

From quantum to semiclassical picture.— We now present an intuitive picture of the topologically-induced quantum geometric phenomenology. Semiclassically, electrons in band gap insulators can be modeled with an effective non-linear anharmonic oscillator Hamiltonian, $H = \frac{p^2}{2m} + U(x)$ with a \mathcal{I} -symmetric confining non-linear potential $U(x) = \frac{1}{2}\kappa x^2 + \frac{1}{4}bx^4$, where κ is an effective spring constant, $\kappa = m\omega_0^2$, in which ω_0 is a resonant frequency and b quantifies the degree of anharmonicity. Notably, $\kappa \propto 1/\langle g_{xx} \rangle = 1/\langle \Delta x^2 \rangle$ [31], where $\langle \Delta x^2 \rangle$ is a spatial spread of a localized state wavefunction, as representable in terms of Wannier functions [7]. From the theory of non-linear anharmonic oscillator discussed in Sec. VI of the SM [25], one expects $\chi^{(3)} \propto b/\kappa^4$, by recognizing that, typically, $b \propto \kappa/\langle g_{xx} \rangle$, explaining the effective scaling of the $\chi^{(3)} \propto \langle g_{xx} \rangle^2$ within a full quantum-mechanical treatment. The semiclassical picture, in connection to quantum geometry, further supports the interpretation of our key result. Namely, the topological symmetry-indicated winding of the Bloch states in a onedimensional insulator: (i) induces a geometric spread in the localization of the bounded electrons, which (ii) semiclassically reflects an effective spring constant and its inteplay with anharmonicity. The latter determine the non-linear optical response of the driven localized electrons within an anharmonic oscillator picture.

Discussion and conclusions.- In summary, we have shown that the colossal linear and higher-order optical responses observed in one-dimensional π -conjugate chains can be understood by means of the modern notions of band topology and quantum geometry, where the latter is bounded from below by the former. We have established a transparent connection of the multiband quantum geometry with the third-order optical responses, demonstrating that the crystalline-symmetryprotected topology induces a lower-bound on the hyperpolarizability. Our quantum-geometric perspective sheds a new light on the longstanding controversy of discrepancy betweeen $\chi^{(3)}$ of *cis*- and *trans*-polyacetylene [3]. In the provided picture, cis-polyacetylene is topologically trivial $(v_{\rm FK} = 0)$, hence, realizes no bound on geometry with average quantum metric $\langle g_{xx} \rangle$ that induces an enhancement of the $\chi^{(3)}$, unlike in the topological *trans*-polyacetylene ($v_{\rm FK} = 1$). To conclude, our work demonstrates that higher-order optical, or electrodynamical, responses can be achieved in materials possessing nontrivial crystalline topology, thus opening a pathway to identify and engineer novel platforms for enhanced nonlinear phenomena within the growing family of topologically classified materials.

ACKNOWLEDGEMENTS

W.J.J. and R.-J.S. acknowledge Bartomeu Monserrat and Joshua J.P. Thompson for stimulating discussions. W.J.J. acknowledges funding from the Rod Smallwood Studentship at Trinity College, Cambridge. R.-J.S. acknowledges funding from an EPSRC ERC underwrite grant EP/X025829/1 and a Royal Society exchange grant IES/R1/221060 as well as Trinity College, Cambridge.

- R. Boyd, Nonlinear Optics, 4th Edition, (Elsevier, Amsterdam., 2019).
- [2] L.R. Dalton, J. Thomson, and H.S. Nalwa, "The role of extensively delocalized π -electrons in electrical conductivity, nonlinear optical properties and physical properties of polymers," Polymer **28**, 543–552 (1987).
- [3] J. L. Bredas, C. Adant, P. Tackx, A. Persoons, and B. M. Pierce, "Third-order nonlinear optical response in organic materials: Theoretical and experimental aspects," Chemical Reviews 94 (1994).
- [4] C. R. Fincher, M. Ozaki, M. Tanaka, D. Peebles, L. Lauchlan, A. J. Heeger, and A. G. MacDiarmid, "Electronic structure of polyacetylene: Optical and infrared studies of undoped semiconducting (CH)_x and heavily doped metallic (CH)_x," Phys. Rev. B 20, 1589–1602 (1979).
- [5] J. P. Hermann and J. Ducuing, "Third-order polarizabilities of long-chain molecules," Journal of Applied Physics 45 (1974).
- [6] K.C. Rustagi and J. Ducuing, "Third-order optical polarizability of conjugated organic molecules," Optics Communications 10 (1974).
- [7] Nicola Marzari and David Vanderbilt, "Maximally localized generalized Wannier functions for composite energy bands," Phys. Rev. B 56, 12847–12865 (1997).
- [8] Liang Fu, "Topological crystalline insulators," Phys. Rev. Lett. 106, 106802 (2011).
- [9] Robert-Jan Slager, "The translational side of topological band insulators," J. Phys. Chem. Solids 128, 24 – 38 (2019).
- [10] Robert-Jan Slager, Andrej Mesaros, Vladimir Juričić, and Jan Zaanen, "The space group classification of topological bandinsulators," Nature Physics 9, 98 (2012).
- [11] Jorrit Kruthoff, Jan de Boer, Jasper van Wezel, Charles L. Kane, and Robert-Jan Slager, "Topological classification of crystalline insulators through band structure combinatorics," Phys. Rev. X 7, 041069 (2017).
- [12] Hoi Chun Po, Ashvin Vishwanath, and Haruki Watanabe, "Symmetry-based indicators of band topology in the 230 space groups," Nat. Commun. 8, 50 (2017).
- [13] Barry Bradlyn, L. Elcoro, Jennifer Cano, M. G. Vergniory, Zhijun Wang, C. Felser, M. I. Aroyo, and B. Andrei Bernevig, "Topological quantum chemistry," Nature 547, 298 (2017).
- [14] Nicola Marzari, Arash A. Mostofi, Jonathan R. Yates, Ivo Souza, and David Vanderbilt, "Maximally localized Wannier functions: Theory and applications," Rev. Mod. Phys. 84, 1419–1475 (2012).
- [15] W. Kohn, "Analytic properties of Bloch waves and Wannier functions," Phys. Rev. 115, 809–821 (1959).
- [16] A. P. Schnyder, S. Ryu, A. Furusaki, and A. W. W. Ludwig, "Classification of topological insulators and superconductors in three spatial dimensions," Phys. Rev. B 78, 195125 (2008).

- [17] A. Kitaev, V. Lebedev, and M. Feigel'man, "Periodic table for topological insulators and superconductors," in *AIP Conference Proceedings* (AIP, 2009).
- [18] Liang Fu and C. L. Kane, "Topological insulators with inversion symmetry," Phys. Rev. B 76, 045302 (2007).
- [19] JP Provost and G Vallee, "Riemannian structure on manifolds of quantum states," Communications in Mathematical Physics 76, 289–301 (1980).
- [20] Jonah Herzog-Arbeitman, Valerio Peri, Frank Schindler, Sebastian D. Huber, and B. Andrei Bernevig, "Superfluid weight bounds from symmetry and quantum geometry in flat bands," Phys. Rev. Lett. **128**, 087002 (2022).
- [21] Yu-Quan Ma, Shu Chen, Heng Fan, and Wu-Ming Liu, "Abelian and non-Abelian quantum geometric tensor," Phys. Rev. B 81, 245129 (2010).
- [22] Adrien Bouhon, Abigail Timmel, and Robert-Jan Slager, "Quantum geometry beyond projective single bands," (2023), arXiv:2303.02180 [cond-mat.mes-hall].
- [23] Junyeong Ahn, Guang-Yu Guo, and Naoto Nagaosa, "Lowfrequency divergence and quantum geometry of the bulk photovoltaic effect in topological semimetals," Phys. Rev. X 10, 041041 (2020).
- [24] Junyeong Ahn, Guang-Yu Guo, Naoto Nagaosa, and Ashvin Vishwanath, "Riemannian geometry of resonant optical responses," Nature Physics 18, 290–295 (2021).
- [25] See Supplemental Material (SM) at [url] for more details on multiband quantum geometry and bounds (Sec. I), derivation of quantum geometry-dependent hyperpolarizability (Sec. II), control of quantum geometry with external fields (Sec. III), topological bound on hyperpolarizability (Sec. IV), multiband

generalizations of the model for different π -conjugated polymers (Sec. V), and anharmonic oscillator (Sec. VI). The Supplemental Material also contains Refs. [32, 33].

- [26] W. P. Su, J. R. Schrieffer, and A. J. Heeger, "Solitons in polyacetylene," Phys. Rev. Lett. 42, 1698–1701 (1979).
- [27] W. P. Su, J. R. Schrieffer, and A. J. Heeger, "Soliton excitations in polyacetylene," Phys. Rev. B 22, 2099–2111 (1980).
- [28] Nikita V. Tepliakov, Johannes Lischner, Efthimios Kaxiras, Arash A. Mostofi, and Michele Pizzochero, "Unveiling and manipulating hidden symmetries in graphene nanoribbons," Phys. Rev. Lett. 130, 026401 (2023).
- [29] Wojciech J. Jankowski, Joshua J. P. Thompson, Bartomeu Monserrat, and Robert-Jan Slager, "Excitonic topology and quantum geometry in organic semiconductors," (2024), arXiv:2406.11951 [cond-mat.mes-hall].
- [30] Borja Cirera, Ana Sánchez-Grande, Bruno de la Torre, José Santos, Shayan Edalatmanesh, Eider Rodríguez-Sánchez, Koen Lauwaet, Benjamin Mallada, Radek Zbořil, Rodolfo Miranda, Oliver Gröning, Pavel Jelínek, Nazario Martín, and David Ecija, "Tailoring topological order and π -conjugation to engineer quasi-metallic polymers," Nature Nanotechnology **15**, 437–443 (2020).
- [31] Yugo Onishi and Liang Fu, "Universal relation between energy gap and dielectric constant," Phys. Rev. B 110, 155107 (2024).
- [32] Taylor L. Hughes, Emil Prodan, and B. Andrei Bernevig, "Inversion-symmetric topological insulators," Phys. Rev. B 83, 245132 (2011).
- [33] J. E. Sipe and A. I. Shkrebtii, "Second-order optical response in semiconductors," Phys. Rev. B 61, 5337–5352 (2000).

arXiv:2502.02660v1 [cond-mat.mes-hall] 4 Feb 2025

SUPPLEMENTAL MATERIAL Enhancing the hyperpolarizability of crystals with quantum geometry

Wojciech J. Jankowski,^{1,*} Robert-Jan Slager,^{2,1} and Michele Pizzochero^{3,4,†}

¹TCM Group, Cavendish Laboratory, University of Cambridge, J. J. Thomson Avenue, Cambridge CB3 0HE, UK

²Department of Physics and Astronomy, University of Manchester, Oxford Road, Manchester M13 9PL, UK

³Department of Physics, University of Bath, Claverton Down, Bath BA2 7AY, UK

⁴School of Engineering and Applied Sciences, Harvard University, Cambridge, MA 02138, USA

(Dated: February 6, 2025)

CONTENTS

References	12
VI. Anharmonic classical oscillator in the inversion-symmetric potential	10
D. Graphene nanoribbons	9
C. Polypentacene	8
B. Poly(p-phenylene)	8
A. Polyacetylene	8
V. Multiband extension of the effective models	8
IV. Topological bound on hyperpolarizability	7
III. Control of quantum geometry with external fields	5
II. Hyperpolarizability in terms of quantum metric	4
I. Multiband geometry and topological bounds	2

^{*} wjj25@cam.ac.uk

[†] mp2834@bath.ac.uk

I. MULTIBAND GEOMETRY AND TOPOLOGICAL BOUNDS

We provide further details on the multiband geometry and topological bounds central to the main text. The band topology is geometrically encoded in the non-Abelian Berry connection $\mathbf{A}_{nm} = i \langle u_{nk} | \nabla_{\mathbf{k}} u_{mk} \rangle$, with the energy eigenstates of the Bloch wave form $|\psi_{nk}\rangle = e^{i\mathbf{k}\cdot\mathbf{r}} |u_{nk}\rangle$. Furthermore, the non-Abelian Berry connection determines the optical responses of materials, with transition dipole matrix elements $\mathbf{r}_{nm} = (1 - \delta_{mn}) \langle \psi_{nk} | \hat{\mathbf{r}} | \psi_{mk} \rangle = i(1 - \delta_{mn}) \mathbf{A}_{nm}$ between occupied bands *n* and unoccupied bands *m* [1]. The non-Abelian Berry connection determines the multiband metric [2],

$$g_{ij}^{nm} = -A_{nm}^{i}A_{mn}^{j} = \operatorname{Re} \left\langle \partial_{k_{i}}u_{n\mathbf{k}} \middle| u_{m\mathbf{k}} \right\rangle \left\langle u_{m\mathbf{k}} \middle| \partial_{k_{j}}u_{n\mathbf{k}} \right\rangle, \tag{1}$$

which is a gauge-independent quantity, given it can be rewritten as $g_{ij}^{nm} = -\frac{1}{2} \text{Tr} \left[(\partial_{k_i} P_n) (\partial_{k_j} P_m) \right]$, with $P_l = |u_{lk}\rangle \langle u_{lk}|$ gauge-independent projectors onto a band *l*. Hence, as a gauge-independent quantity, the multiband quantum metric can indeed be connected to the physical response functions, and in particular to optical signatures. In the context of the most general non-Abelian multiband quantum metric, here we specifically consider $g_{xx}^{nm} = (\mathbf{g}_{xx}^m)_{np}$, with $(\mathbf{g}_{xx}^m)_{np} = -A_{nm}^x A_{mp}^x$, which is consistent with the main text definition in terms of momentum-space tangent vectors ∂_{k_x} and associated geometry induced by the dreibeins $\{|u_{nk}\rangle, |u_{mk}\rangle, |u_{pk}\rangle\}$.

On summing over all unoccupied bands, as in the main text, one can retrieve a topological bound, as we show below:

$$g_{xx}^{n} \equiv \sum_{m}^{\text{unocc}} g_{xx}^{nm} \ge \frac{a^2}{4} v_{\text{FK}}^{n}, \tag{2}$$

with $v_{FK}^n \in \mathbb{Z}_2$, the crystalline Fu-Kane (FK) invariant [3] for inversion-symmetry protected topology of an isolated band *n* in one spatial dimension. In that context, in terms of the non-Abelian Berry connection, the FK invariant can be written as [4],

$$v_{\rm FK}^n = \frac{1}{2\pi} \int_{\rm hBZ} \mathrm{d}k \Big[A_{nn}^x(\mathbf{k}) + A_{nn}^x(\mathbf{k}) \Big],\tag{3}$$

with hBZ the irreducible half of a conventional Brillouin zone. Below, we provide the general derivation of the topological bound in the one-dimensional inversion-symmetric systems. The argument is analogous to the cases of obstructed insulators in higher dimensions [5]. For an alternative argument, in the context of the two band models discussed in the main text, see Sec. III. To proceed, we begin by noting that the *k*-space irreps of the occupied bands are constituted by the \mathcal{I} -symmetry eigenvalues at BZ points Γ (k = 0) and X ($k = \pi/a$). the multiplicities *m* of irreps satisfy:

$$m(X) - m(\Gamma) = \operatorname{Tr} D(\mathcal{I})P(\Gamma), \tag{4}$$

with a representation matrix $D(\mathcal{I}) = \text{diag}(1, -1)$ of \mathcal{I} -symmetry acting on the orbitals, and $P(k) = \sum_{n=1}^{\infty} P_n(k)$ a projector onto the occupied bands. Furthermore,

$$P(X) - P(\Gamma) = 2\sum_{n=1}^{2} p(-\mathcal{I}^{n}a) + (x > a) \text{ terms},$$
(5)

with $p(x) \equiv \int_{BZ} \frac{dk}{2\pi} e^{ikx} P(k)$, which follows definitionally. On taking a Frobenius norm and triangle inequality [5], we moreover have:

$$\|P(X) - P(\Gamma)\| \le \|p(-a)\| + \|p(a)\| + \|(x > a) \text{ terms}\|,\tag{6}$$

and furthermore ||p(a)|| = ||p(-a)||, directly from definition. From the same definition,

$$\langle g_{xx} \rangle = \frac{a}{2\pi} \int_{BZ} dk \, \frac{1}{2} \operatorname{Tr}[(\partial_{k_x} P)(\partial_{k_x} P)] = \sum_{x \in ja} |x|^2 ||p(x)||^2 \ge a^2 ||p(a)||^2, \tag{7}$$

with $j \in \mathbb{Z}$. We employ the inequality $||P(X) - P(\Gamma)||^2 \ge \text{Tr } ||D(\mathcal{I})(P(X) - P(\Gamma))||/2$, which here holds specifically for matrices with rank 2, and also holds for any other unitary matrix than $D(\mathcal{I})$, similarly to the conditions used in Ref. [5]. As a consequence, by an analogous optimization argument to Ref. [5],

$$\sum_{x \in ja} |x|^2 ||p(x)||^2 \ge a^2 \operatorname{Tr} ||D(\mathcal{I})(P(X) - P(\Gamma))|| = \frac{a^2}{4} \nu_{\mathrm{FK}},\tag{8}$$

with the last relation following directly on inserting the multiplicity relations Eq. (4). This relation concludes the derivation of the bound,

$$\langle g_{xx} \rangle \ge \frac{a^2}{4} \nu_{\text{FK}},$$
(9)

which for isolated bands can be generalized to individual single-band bounds, on sending: $g_{xx} \rightarrow g_{xx}^n$, $P \rightarrow P_n$, $p(x) \rightarrow p_n(x)$, $v_{FK} \rightarrow v_{FK}^n$, and on repeating exactly the same derivation (as above) under such substitution.

Importantly, the non-trivial FK invariant, coinciding with the parity index, $v_{FK} = 1$, can be realized in carbon-based polyacene [6, 7], graphene nanoribbons [8], and corresponds to the so-called obstructed topology, which in the spirit of the irrep considerations above, i.e. in terms of crystalline \mathcal{I} -symmetry indicators, is topologically-captured by the fractional gluing conditions on the elementary band representations [9–11].

II. HYPERPOLARIZABILITY IN TERMS OF QUANTUM METRIC

In the following, we derive the connection of the hyperpolarizability to quantum geometry. We begin by noting that, as follows from the third-order perturbation theory in electron-photon coupling $\Delta H = e\hat{\mathbf{r}} \cdot \mathbf{E}(t)$ written here in the length gauge, with $\mathbf{E}(t) = \mathbf{E}(\omega)\cos(\omega t)$, the third-order susceptibility in response to optical fields $E_x(\omega_i)$ compactly reads [12]:

$$\chi^{(3)}_{xxxx}(\omega;\omega_1,\omega_2,\omega_3) = \frac{e^4}{\epsilon_0 a} \sum_{n,m,p,q,\mathbf{k}} \mathcal{P}_F \frac{r_{nm}^x r_{mp}^x r_{pq}^x r_{qn}^x}{(\hbar\omega - E_{mn})(\hbar\omega - E_{pn} - \hbar\omega_2 - \hbar\omega_3)(E_{qn} - \hbar\omega_3)}.$$
(10)

In the above, \mathcal{P}_F denotes the permutation operator over all input and output frequencies [12], ϵ_0 is vacuum electric permittivity constant, and $r_{nm}^x = \langle \psi_{n\mathbf{k}} | \hat{x} | \psi_{m\mathbf{k}} \rangle$ is the transition dipole matrix element per electron charge [1, 13]. Here, we consider a coupling on combining the frequencies ω_i with i = 1, 2, 3, which result in a response with frequency, $\omega = \omega_1 + \omega_2 + \omega_3$.

In terms of non-Abelian Berry connection A_{nm}^x matrix, we retrieve:

$$\chi_{xxxx}^{(3)}(\omega;\omega_1,\omega_2,\omega_3) = \frac{e^4}{\epsilon_0 a} \sum_{n,m,p,q,\mathbf{k}} \mathcal{P}_F \frac{A_{nm}^x A_{mp}^x A_{pq}^x A_{qn}^x}{(\hbar\omega - E_{mn})(\hbar\omega - E_{pn} - \hbar\omega_2 - \hbar\omega_3)(E_{qn} - \hbar\omega_3)}.$$
(11)

As an example, the response associated with the Kerr nonlinearity [12] can be captured as,

$$\chi_{xxxx}^{(3)}(\omega; -\omega, \omega, \omega) = \frac{e^4}{\epsilon_0 a} \sum_{n,m,p,q,\mathbf{k}} \mathcal{P}_F \frac{A_{nm}^x A_{np}^x A_{pq}^x A_{qn}^x}{(\hbar\omega - E_{nn})(-E_{pn} - \hbar\omega)(E_{qn} - \hbar\omega)}.$$
(12)

On the other hand, as central to this work, the static hyperpolarizability $\chi^{(3)}$ in a one-dimensional system reads,

$$\chi^{(3)} \equiv \chi^{(3)}_{xxxx}(\omega \to 0; 0, 0, 0) = \frac{e^4}{\epsilon_0 a} \sum_{n,m,p,q,\mathbf{k}} \frac{A^x_{nm} A^x_{mp} A^x_{pq} A^x_{qn}}{E_{mn} E_{pn} E_{qn}}.$$
(13)

Hence, in terms of the non-Abelian quantum geometric tensor (QGT) defined in the main text, we arrive at:

$$\chi^{(3)} = \frac{e^4}{\epsilon_0 a} \sum_{n,m,p,q,\mathbf{k}} \frac{(\mathbf{Q}_{xx}^p)_{np} (\mathbf{Q}_{xx}^q)_{pn}}{E_{mn} E_{pn} E_{qn}},\tag{14}$$

where $\sum_{\mathbf{k}} \equiv \frac{a}{2\pi} \int_{BZ} dk$ in one spatial dimension (*x*). Moreover, the non-Abelian QGT coincides with the non-Abelian quantum metric: $\mathbf{g}_{xx}^p = \operatorname{Re} \mathbf{Q}_{xx}^p = \operatorname{Re} \mathbf{Q}_{xx}^p$. This culminates in the main result of the main text,

$$\chi^{(3)} = \frac{e^4}{\epsilon_0 a} \sum_{n,m,p,q,\mathbf{k}} \frac{(\mathbf{g}_{xx}^p)_{np}(\mathbf{g}_{xx}^q)_{pn}}{E_{mn} E_{pn} E_{qn}} = \frac{e^4}{\epsilon_0} \int_{\mathrm{BZ}} \frac{\mathrm{d}k}{2\pi} \sum_{n,m,p,q} \frac{(\mathbf{g}_{xx}^p)_{np}(\mathbf{g}_{xx}^q)_{pn}}{E_{mn} E_{pn} E_{qn}},\tag{15}$$

which in the effective model central to the main text, we limited to the low-energy subspace n, m, p, q = 1, 2. We note that the dominant contribution to $\chi^{(3)}$ is expected to emerge from the crystalline topological bands n = 1, m = 2 which can arise by a band inversion and are neighboring the band gap. Correspondingly, we have: $E_{21} = \min_{n \neq m} |E_{mn}|$, which demonstrates that the low energy bands contributions dominate the band sum with the suppression of the denominator as: $\chi^{(3)} \sim E_{21}^{-3}$. Moreover, in the band-resolved picture, see Sec. I, it is only the topological bands that are expected to realize topologically-enhanced quantum metric, providing for an additional enhancement $\chi^{(3)} \sim (g_{xx}^{12})^2$. The arguments above show that in the case of non-trivial crystalline band topology, it is precisely the bottom conduction and top valence bands that dominate amongst the other contributions to $\chi^{(3)}$.

III. CONTROL OF QUANTUM GEOMETRY WITH EXTERNAL FIELDS

We here consider the effects of the external fields, such as static strain fields λ to further enhance the quantum geometry and optics for potential material applications. In the presence of external fields, the Bloch states can be written as $|u_{n\mathbf{k}}(\lambda)\rangle$, and the multiband metric admits the external parameters as $g_{xx}^{nm}(\lambda)$.

While being close to the lower-bound saturation is not desirable for optical material design, the following question of: how close to saturating the bound one can get by perturbing the system, nevertheless arises. It is further interesting to consider the opposite limit of how away from the bound one can arrive, i.e. how big the metric can be. The metric should diverge in the gapless (metallic) limit, therefore small-gap materials with non-trivial quantum geometry are highly desirable for realizing the non-linear optical responses. In terms of the velocity operator $\hat{v}_x = \frac{i}{\hbar} [\hat{H}, \hat{x}]$, the quantum metric of interest reads,

$$g_{xx}^{12}(\lambda) = \hbar^2 \frac{|\langle \psi_{1\mathbf{k}}(\lambda)|\,\hat{v}_x |\psi_{2\mathbf{k}}(\lambda)\rangle|^2}{E_{21}^2(\lambda)},\tag{16}$$

with $|\psi_{n\mathbf{k}}(\lambda)\rangle = e^{i\mathbf{k}\cdot\mathbf{r}} |u_{n\mathbf{k}}(\lambda)\rangle$, the external parameter-dependent Bloch states. In terms of the scaling with the band energy difference $E_{21}(\lambda) = E_{2\mathbf{k}}(\lambda) - E_{1\mathbf{k}}(\lambda)$, with $E_{1\mathbf{k}}(\lambda)$, $E_{2\mathbf{k}}(\lambda)$ the single-band energies, this relation reflects the local enhancement of the momentum-space metric close to the direct band gap at the band edge $(k = \pi/a)$. We retrieved such scaling in the main text, as shown in Fig. 2. The corresponding scaling is intuitively justified by the change of the overlaps of the exponentially-localized basis (Wannier) orbitals. From the scaling of hoppings in the limit of high tensile strains $(\gamma_i \to \infty)$ one obtains a large gap trivial atomic insulator $(E_g \to \infty)$, topologically-equivalent to vacuum. With the provided physical limit in mind, the practical starting point is to begin with a \mathbb{Z}_2 -topological system, as the trivializations occur in the limit of large tensile strains. The tensile strains can trivialize the topology, while preserving the insulating character of the system $(E_q \neq 0)$ after the topological phase transition across a metallic state occurs.

We now provide more details on the controllable geometry based on the example realized in the strained SSH model [14, 15] central to the main text. The introduced two-band model can be compactly rewritten in terms of $\mathfrak{su}(2)$ Lie algebra of Pauli matrices $\sigma = (\sigma_x, \sigma_y, \sigma_z)$:

$$H(k_x,\lambda) = \mathbf{d}(k_x,\lambda) \cdot \boldsymbol{\sigma},\tag{17}$$

with the **d**-vector:

$$\mathbf{d}(k_x,\lambda) = \begin{pmatrix} t_1(\lambda) + t_2(\lambda)\cos k_x a(\lambda) \\ t_2(\lambda)\sin k_x a(\lambda) \\ 0 \end{pmatrix}.$$
 (18)

In the real material context, the hopping parameters t_1 and t_2 can be retrieved by fitting the effective band structure of the model to the first principles calculations, i.e. to the DFT band structure. The electronic wavefunctions of valence/conduction electrons read:

$$\left|u_{1/2\mathbf{k}}\right\rangle = \frac{1}{\sqrt{2|\mathbf{d}(k_x,\lambda)|^2}} \begin{pmatrix} d_x(k_x,\lambda) \pm id_y(k_x,\lambda) \\ |\mathbf{d}(k_x,\lambda)| \end{pmatrix},\tag{19}$$

and the electronic single-particle energies are given by:

$$E_{1/2\mathbf{k}}(\lambda) = \pm \sqrt{d_x^2(k_x, \lambda) + d_y^2(k_x, \lambda)} = \pm |\mathbf{d}(k_x, \lambda)|.$$
⁽²⁰⁾

Hence, the band energy differences read: $E_{21}(\lambda) = 2|\mathbf{d}(k_x, \lambda)|$. The normalized vector: $\hat{\mathbf{d}}(k_x, \lambda) \equiv \mathbf{d}(k_x, \lambda)/|\mathbf{d}(k_x, \lambda)|$, with $\hat{\mathbf{d}}(k_x, \lambda) \cdot \hat{\mathbf{d}}(k_x, \lambda) = 1$ fully determines the quantum metric as

$$g_{xx}^{12}(\lambda) = \frac{1}{4} \partial_{k_x} \hat{\mathbf{d}}(k_x, \lambda) \cdot \partial_{k_x} \hat{\mathbf{d}}(k_x, \lambda).$$
(21)

As a consequence, we can compactly rewrite the third-order susceptibility in the static limit, which corresponds to an externalparameter controllable hyperpolarizability:

$$\chi^{(3)}(\lambda) = \frac{e^4}{2\pi\epsilon_0} \int_{\mathrm{BZ}} \mathrm{d}k_x \; \frac{|\partial_{k_x} \hat{\mathbf{d}}(k_x, \lambda)|^4}{128|\mathbf{d}(k_x, \lambda)|^3}.$$
 (22)

The form compactly captures the geometric character of the hyperpolarizability, and its explicit dependence on strain λ , as captured by the vector $\hat{\mathbf{d}}(k_x, \lambda)$. The $\hat{\mathbf{d}}(k_x, \lambda)$ vector determines a measure of quantum distance with its tangent vector $\partial_{k_x} \hat{\mathbf{d}}(k_x, \lambda)$

over a great circle over a two-sphere S^2 in the parameter space of coefficients (d_x, d_y, d_z) . This observation provides an intuitive connection between the hyperpolarizability and the notion of quantum distance definitional for the Fubini-Study metric [16]: $ds^2 = g_{xx}dk_xdk_x$ over momentum space. It should be noted that this geometric interpretation directly induces the topological bound introduced in the main text, which within a two-band picture follows as,

$$\langle g_{xx} \rangle \equiv \frac{a}{2\pi} \int_{BZ} dk \ g_{xx}^{12} = \frac{a}{2\pi} \int_{BZ} dk \left(\frac{a^2}{4} \partial_{k_x} \hat{\mathbf{d}}(k_x, \lambda) \cdot \partial_{k_x} \hat{\mathbf{d}}(k_x, \lambda) \right) = \frac{a^2}{4} \times \frac{a}{2\pi} \int_{BZ} dk \ \hat{\mathbf{d}}(k_x, \lambda) \cdot \hat{\mathbf{d}}(k_x, \lambda) \geq \frac{a^3}{8\pi} \int_{BZ} dk \ |\partial_{k_x} \hat{\mathbf{d}}(k_x, \lambda)| = \frac{a^2}{4} \times \frac{a}{2\pi} \int_{BZ} dk \ |\hat{\mathbf{d}}(k_x, \lambda) \times \partial_{k_x} \hat{\mathbf{d}}(k_x, \lambda)| \geq \frac{a^2}{4} \left| \frac{a}{2\pi} \int_{BZ} dk \ \hat{\mathbf{d}}(k_x, \lambda) \times \partial_{k_x} \hat{\mathbf{d}}(k_x, \lambda) \right| = \frac{a^2}{4} \nu \geq \frac{a^2}{4} \nu_{FK},$$

$$(23)$$

with $v \in \mathbb{Z}$ an integer S²-winding number, and $v_{FK} = 0, 1$, the \mathbb{Z}_2 Fu-Kane invariant. In the above, we used the Cauchy-Schwarz inequality,

$$\left| \int dk \ f_1(k) f_2(k) \right|^2 \le \left(\int dk \ |f_1(k)|^2 \right) \left(\int dk \ |f_2(k)|^2 \right), \tag{24}$$

for general (vector) functions $f_1(k)$, $f_2(k)$. Here, we choose: $f_1(k) = |\partial_{k_x} \hat{\mathbf{d}}(k_x, \lambda)|$, $f_2(k) = |\hat{\mathbf{d}}(k_x, \lambda)|$. It should be noted that the presence of additional bands can only increase, rather than reduce the left-hand side, as for any band indices n, m: $g_{xx}^{nm} \ge 0$ by definition, and in the multiband case: $\langle g_{xx} \rangle = \frac{a}{2\pi} \int_{BZ} dk \sum_{n,m} g_{xx}^{nm}$, with *n* occupied and *m* unoccupied bands. Hence, the quantum geometric bound in the main text holds for any arbitrary number of valence and conduction bands of gapped one-dimensional chains respecting the sublattice and inversion symmetries. Notably, if the chain is gapless: $|\mathbf{d}| = 0$, and $\hat{\mathbf{d}} = \mathbf{d}/|\mathbf{d}|$ becomes ill-defined, while the hyperpolarizability in the metallic limit formally diverges.



Supplementary FIG. S1. The band structures and hyperpolarizabilities of the multiband extensions of π -conjugated polymer models. (a) polyacetylene [two π bands and two σ bands], (b) poly(p-phenylene) [six π bands], (c) polypentacene [six π bands], (d) graphene nanoribbon [sixteen π -bands]. The tight-binding parameters were approximately fitted to the band structures of materials with parametrizations provided in the corresponding subsections. We overlay the approximate two-band model hyperpolarizabilities over multiband hyperpolarizabilities $\chi^{(3)}$ obtained within the extended models. As anticipated with the intuitive $\chi^{(3)}$ scaling argument, we observe that in the topological phases, the hyperpolarizabilities change marginally on the logarithmic scale after having included the additional lower energy bands.

IV. TOPOLOGICAL BOUND ON HYPERPOLARIZABILITY

We here derive a topological bound on the hyperpolarizability due to (crystalline) band topology. We note that the variance of quantum metric over momentum space must be non-negative,

$$\operatorname{Var}\left\langle g_{xx}\right\rangle = \left\langle g_{xx}^{2}\right\rangle - \left\langle g_{xx}\right\rangle^{2} \ge 0. \tag{25}$$

Therefore, $\chi^{(3)} \sim \langle g_{xx}^2 \rangle \geq \langle g_{xx} \rangle^2 \sim v_{FK}^2$, cf. the previous Section on hyperpolarizability. As a consequence, in the presence of the band gap, $\Delta = \min_{\mathbf{k}} [E_{m\mathbf{k}} - E_{n\mathbf{k}}]$, with *n* running over all occupied and *m* over unoccupied band indices, $\chi^{(3)}$ is topologically bounded as:

$$\chi^{(3)} \ge \frac{e^4}{\epsilon_0} \frac{\langle g_{xx}^2 \rangle}{\Delta^3} \ge \frac{e^4}{\epsilon_0} \frac{\langle g_{xx} \rangle^2}{\Delta^3} \ge \frac{e^4}{\epsilon_0} \frac{a^4}{16\Delta^3} v_{\text{FK}}^2.$$
(26)

Using the *f*-sum rule [17], with $n \sim 1/a$, the ground state electron density, and m_e the electron mass, the gap is topologically bounded as [18, 19]:

$$\frac{\hbar}{\Delta} \frac{ne^2}{8m_e} = \frac{\hbar}{\Delta} \int_0^\infty d\omega \ \sigma_{xx}(\omega) \ge W_{xx} = \frac{\pi e^2}{\hbar} \langle g_{xx} \rangle \ge \frac{\pi e^2 a^2}{4\hbar} \nu_{\rm FK},\tag{27}$$

with W_{xx} an optical weight defined in the main text. Hence, on rearranging, one obtains:

$$\frac{1}{\Delta} \ge \frac{2\pi m_e a^2}{n\hbar^2} \nu_{\rm FK},\tag{28}$$

which combined with the previous inequalities, culminates in:

$$\chi^{(3)} \ge \frac{\pi^3 e^4 m_e^3 a^{10}}{2\epsilon_0 n^3 \hbar^6} v_{\rm FK}^4 = 6 \times 10^{50} \,\,{\rm m}^{-5} / {\rm V}^2 \times a^{10} / n^3. \tag{29}$$

This fundamental condition shows that for non-trivial band topology, i.e. $v_{FK} = 1$, the hyperpolarizability is bounded from below by the fundamental constants, charge density, and by the unit cell lattice parameter *a*. In the cases of the other known topological gap bounds, such as by the Chern numbers [19], our argument directly generalizes to the other band topologies. Namely, on replacing the topological invariant, one obtains an analogous bound for any other invariant that realizes a gap bound in any other dimensionality of interest.

V. MULTIBAND EXTENSION OF THE EFFECTIVE MODELS

We here detail the characteristics and responses of the effective Hamiltonians beyond the two-band low-energy theory, which mirror the band structures of realistic materials. We nonetheless show that while the additional band contributions are necessary for a quantitative match of the non-linear responses with experiments [20], given such extended picture includes all possible virtual processes, the two-band models provide the dominant contributions to the considered hyperpolarizability. In Fig. S1, we show all results associated with the multiband models detailed in the next subsections.

A. Polyacetylene

We discuss an extended polyacetylene model, where more electronic bands can be included. We begin with the polyacetylene parameterization: $t_1 = 2.15$ eV, $t_2 = 2.85$ eV, $a_1 = 0.642$ Å, $a_2 = 0.558$ Å [14, 15], and set the decay parameters $\gamma_1 = 15$ Å⁻¹, $\gamma_2 = 22$ Å⁻¹ for the single and double bonds respectively. We consider a multiband extension of the polyacetylene model, where two more orbitals are involved (one per each sublattice), resulting in a 4 × 4 Hamiltonian:

$$H(k_x) = \begin{pmatrix} 0 & 0 & 0 & t_3 + t_4 e^{ik_x a} \\ 0 & 0 & t_1 + t_2 e^{ik_x a} & 0 \\ 0 & t_1 + t_2 e^{-ik_x a} & 0 & 0 \\ t_3 + t_4 e^{-ik_x a} & 0 & 0 & 0 \end{pmatrix},$$
(30)

where $t_3 \ll t_1, t_2 \ll t_4$ are the additional couplings corresponding to the hoppings to higher energy orbitals. As long as $t_3 \ll t_1, t_2 \ll t_4$, which is justified given the energetic separation of the p_z constituting π -bands from the other σ -bands constituted by the sp^2 orbitals, the additional bands are less dispersive, with energies taking values far from Fermi level μ , i.e. $E_{21} \ll E_{31}, E_{42}$, which provides for a cubic suppression of the corresponding hyperpolarizability contribution, with negligible quantum metric contributions, which also scale with the band gap, cf. Sec. II of SM. In Fig. S1, we set $t_3 = -0.4$ eV, $t_4 = 5$ eV. We arrive at the same conclusions for topological bounds.

B. Poly(p-phenylene)

We detail a multiband model of poly(p-phenylene) (PPP), as an intermediate case between polyacetylene and polypentacene addressed in the next section. In the multiband extension, we assume that each phenylene ring contributes three occupied molecular orbitals (MOs) of benzene, which results in an effective 6×6 model Hamiltonian,

$$H(k_x) = \begin{pmatrix} \epsilon_2 & t_5 + t_6 e^{ik_x a} & 0 & 0 & 0 & 0\\ t_5 + t_6 e^{-ik_x a} & \epsilon_1 & 0 & 0 & 0 & 0\\ 0 & 0 & t_1 + t_2 e^{ik_x a} & 0 & 0\\ 0 & 0 & t_1 + t_2 e^{-ik_x a} & 0 & 0\\ 0 & 0 & 0 & \epsilon_2 & t_3 + t_4 e^{ik_x a}\\ 0 & 0 & 0 & 0 & t_3 + t_4 e^{-ik_x a} & \epsilon_1 \end{pmatrix},$$
(31)

with t_4 , $t_6 << t_1$, $t_2 << t_3$, t_5 , where t_5 , t_6 are the hoppings to/from the lower energy benzene molecular orbitals (MOs) with energies (ϵ_1 , $\epsilon_2 < 0$). We find that the HOMOs of benzene molecules, hoppings between which define t_1 , t_2 , contribute the most of the quantum metric. The lower energy orbitals that define t_3 , t_4 , t_5 , t_6 provide for additional bands with larger energy differences, and hence experience higher energy gaps than E_{21} . The higher energy gaps suppress the hyperpolarizability contributions due to additional bands in a cubic manner. For the purposes of Fig. S1, we set $\epsilon_1 = -2.5$ eV, $\epsilon_2 = -1.5$ eV, $t_1 = -0.65$ eV, $t_2 = -3.0$ eV, $t_3 = 0.1$ eV, $t_4 = 0.0$ eV, $t_5 = -1.0$ eV, $t_6 = 0.7$ eV.

C. Polypentacene

We detail a polyacene model, in particular for polypentacene, which is known to be topologically (\mathbb{Z}_2) non-trivial [6], and which was previously modelled with a two-band effective theory, similarly to as we adapt in the main text. For a multiorbital extension of the model, one can define a 6 × 6 Hamiltonian, where electrons can hop between molecular orbitals contributed by linear combinations of five rings (t_1 , t_3 , t_5), i.e., between different orbitals within a monomer unit, as well as from pentacene rings across the acetylene unit t_2 , t_4 , t_6 . The modified tight-binding Hamiltonian including internal hoppings between different

orbitals of pentacene, reads:

$$H(k_x) = \begin{pmatrix} \epsilon_2 & 0 & 0 & 0 & 0 & t_5 + t_6 e^{ik_x a} \\ 0 & \epsilon_1 & 0 & 0 & t_3 + t_4 e^{ik_x a} & 0 \\ 0 & 0 & t_1 + t_2 e^{ik_x a} & 0 & 0 \\ 0 & 0 & t_1 + t_2 e^{-ik_x a} & 0 & 0 & 0 \\ 0 & t_3 + t_4 e^{-ik_x a} & 0 & 0 & \epsilon_2 & 0 \\ t_5 + t_6 e^{-ik_x a} & 0 & 0 & 0 & \epsilon_1 \end{pmatrix},$$
(32)

with onsite energies of lower-energy pentacene MOs $\epsilon_1, \epsilon_2 < 0$ employed as the tight-binding basis functions, and hoppings $t_2 > t_1$ in the topological $\mathbb{Z}_2 = 1$ phase.

We find that even in the presence of additional electronic bands, the hyperpolarizability of the material is predominantly determined by the low-energy two-band subspace. This is to be expected, as the effective hoppings induce a significant dispersion only in the topological valence/conduction bands. As a result, the additional bands are less dispersive, realize marginal additional quantum geometric contributions, and are separated by larger gaps. Hence, correspondingly, both the numerator and denominator of the hyperpolarizability contributions due to these bands, are negligibly small, as long as $\mathbb{Z}_2 = 1$, which is consistent with the effective polypentacene bands retrieved in literature [6, 7]. For the purposes of Fig. S1, we set $\epsilon_1 = -2.5$ eV, $\epsilon_2 = -2.5$ eV, $t_1 = 0.3$ eV, $t_2 = 0.5$ eV, $t_3 = 0.5$ eV, $t_4 = 1$ eV, $t_5 = 0.1$ eV, $t_6 = 0.9$ eV.

D. Graphene nanoribbons

Further to the polyacetylene [14, 15], PPP, and polypentacene [6], we consider the graphene nanoribbons (GNRs), which are known to host a strain-dependent crystalline topology protected by inversion symmetry [8]. To minimally capture the phenomenology of GNRs, one can consider a set of coupled 4 × 4 Bloch Hamiltonians due to *n* cis π -bonding chains with a 4-orbital basis. The corresponding models enjoy a *U*(2*n*) gauge freedom in the occupied band manifold. In such case, the parameter space for realizing non-trivial Bloch state geometry is further spanned by a set of strain γ_i , with $\gamma_i = 1, 2, 3$ separately tunable for hoppings $t_i = t_1, t_2, t_3$.

The scaling of the hoppings and tensile strains $\varepsilon_i > 0$, with $\varepsilon_i \equiv (a_i(\lambda)/a_i - 1)$ [8] and $a_i(\lambda)$ strain-dependent lattice hopping distances, can be minimally captured within the considered models by a substitution: $t_i \rightarrow t_i e^{-\gamma_i \varepsilon_i}$, where γ_i reflect bond-dependent decay rates, which depend on the strains and on the geometry of the orbitals between which the hopping occurs. The hoppings t_1 , t_2 , t_3 correspondingly occur over nearest-neighbor (NN), next-nearest neighbor (NNN), and next-next-nearest neighbor (NNNN) vectors with x-direction projected lengths $|\mathbf{a}_1| = a_0/2$, $|\mathbf{a}_2| = \sqrt{3}a_0/2$, $|\mathbf{a}_3| = a_0$, with $a_0 = 3$ Å. The 4 × 4 chain Hamiltonian subblock reads,

$$H^{(4)}(k_x, \Delta_1, \Delta_2) = \begin{pmatrix} 0 & 2t_1 \cos k_x a_1 & 2t_2 \cos k_x a_2 & t_1 e^{ik_x a_1} + (t_1 + \Delta_2) e^{-ik_x a_1} + t_3 e^{ik_x a_3} \\ 2t_1 \cos k_x a_1 & 0 & t_1 e^{ik_x a_1} + (t_1 + \Delta_1) e^{-ik_x a_1} & 2t_2 \cos k_x a_2 \\ 2t_2 \cos k_x a_2 & t_1 e^{-ik_x a_1} + (t_1 + \Delta_1) e^{ik_x a_1} + 0 & 2t_1 \cos k_x a_1 \\ t_1 e^{-ik_x a_1} + (t_1 + \Delta_2) e^{ik_x a_1} + t_3 e^{-ik_x a_3} & 2t_2 \cos k_x a_2 & 2t_1 \cos k_x a_1 & 0 \end{pmatrix},$$
(33)

where Δ_1, Δ_2 are the hopping imbalances at both GNR edges, respectively. The hopping imbalance is consistent with the picture of Ref. [8]. Furthermore, the 4 × 4 chain subblocks are coupled by 4 × 4 interchain coupling matrices:

$$H^{(c)}(k_x) = \begin{pmatrix} 0 & 0 & 0 & 0 \\ 2t_1 \cos k_x a_1 & 0 & 0 & 2t_2 \cos k_x a_2 \\ 2t_2 \cos k_x a_2 & 0 & 0 & 2t_1 \cos k_x a_1 \\ 0 & 0 & 0 & 0 \end{pmatrix}.$$
 (34)

On combining the 4 × 4 chain Hamiltonian blocks with the interchain coupling blocks, we arrive at:

$$H^{(16)}(k_x,\Delta) = \begin{pmatrix} H^{(4)}(k_x,\Delta_1=\Delta,\Delta_2=0) & H^{(c)}(k_x) & 0 & 0\\ H^{(c)}(k_x) & H^{(4)}(k_x,\Delta_1=0,\Delta_2=0) & H^{(c)}(k_x) & 0\\ 0 & H^{(c)}(k_x) & H^{(4)}(k_x,\Delta_1=0,\Delta_2=0) & H^{(c)}(k_x)\\ 0 & 0 & H^{(c)}(k_x) & H^{(4)}(k_x,\Delta_1=0,\Delta_2=\Delta) \end{pmatrix}, \quad (35)$$

which is definitionally consistent with the models of Ref. [8], given the identical real space hoppings. For the purposes of Fig. S1, we set $\Delta = -0.2 \text{ eV}$, $t_1 = -2.88 \text{ eV}$, $t_2 = 0.22 \text{ eV}$, $t_3 = -0.25 \text{ eV}$ [8].

VI. ANHARMONIC CLASSICAL OSCILLATOR IN THE INVERSION-SYMMETRIC POTENTIAL

In the following, we provide further detail on the physics anharmonic classical oscillator in the inversion-symmetric potential within a semiclassical relation to the quantum geometry central to the main text. We begin with an anharmonic classical Hamiltonian with the lowest-order inversion-symmetric anharmonicity introduced in the main text: $H = \frac{p^2}{2m} + U(x) = \frac{p^2}{2m} + \frac{1}{2}kx^2 + \frac{1}{4}bx^4$, obtaining:

$$\dot{p} = -kx - bx^3,\tag{36}$$

from the Hamilton equation of motion $\dot{p} = -\partial H/\partial x$, with the other equation of motion obtaining $\dot{x} = \partial H/\partial p = p/m$. The spring constant can be moreover written as $k = m\omega_0^2$, with ω_0 the natural frequency of the oscillator.

We now focus on the semiclassical picture associated with the anharmonic oscillator from the unique perspective of quantum geometry central to this work. The polarization arises from the displacement of an oscillating charge

$$P(t) = -e \,\delta x(t),\tag{37}$$

where $\delta x(t)$ is a time-dependent charge displacement under the adiabatic forcing F. The forcing is equivalent to a perturbation:

$$\Delta H = Fx \cos \omega t = -eE_0 x \cos \omega t, \tag{38}$$

which on changing the Hamiltonian accordingly: $H \rightarrow H + \Delta H$, obtains the following equation of motion:

$$m\ddot{x} + kx + bx^3 = -eE_0\cos\omega t. \tag{39}$$

To proceed, we consider a perturbative solution of form $x(t) = \lambda_p x^{(1)}(t) + \lambda_p^2 x^{(2)}(t) + \lambda_p^3 x^{(3)}(t)$, with $x^{(n)}$ representing an oscillator component with frequency $n\omega$ and λ_p representing a parameter of perturbative expansion. We note that $x^{(2)}(t) = 0$ vanishes by inversion symmetry. On investigating the first and third order in λ_p , we have:

$$\ddot{x}^{(1)} + \omega_0^2 x^{(1)} = -\frac{eE_0}{m} \cos \omega t,$$
(40)

and at the third perturbative order,

$$\ddot{x}^{(3)} + \omega_0^2 x^{(3)} - \frac{b}{m} (x^{(1)})^3 = -\frac{eE_0}{m} \cos \omega t.$$
(41)

We assume steady state solutions of form:

$$x^{(1)}(t) = \int \mathrm{d}\omega \ x^{(1)}(\omega)e^{-i\omega t},\tag{42}$$

$$x^{(3)}(t) = \int d\omega' \ x^{(3)}(\omega')e^{-i\omega' t},$$
(43)

which on insertion to the equations of motion obtain:

$$x^{(1)}(\omega) = \frac{-eE_0}{m(\omega_0^2 - \omega^2)}.$$
(44)

On inserting to the third-order displacement equation, we have:

$$\ddot{x}^{(3)} + \omega_0^2 x^{(3)} - \frac{b}{m} (x^{(1)})^3 = -\int \int \int \int d\omega \, d\omega' \, d\omega'' \, \frac{b e^3 E_0(\omega) E_0(\omega') E_0(\omega'')}{m^4 (\omega_0^2 - \omega^2) (\omega_0^2 - \omega''^2)} e^{-i(\omega + \omega' + \omega'')t}, \tag{45}$$

which on solving the differential equation gives:

$$x^{(3)}(\omega) = -\int \int \int \int d\omega' \, d\omega'' \, d\omega''' \, \frac{be^3 E_0(\omega') E_0(\omega'') E_0(\omega''')}{m^4 (\omega_0^2 - \omega^2) (\omega_0^2 - \omega''^2) (\omega_0^2 - \omega'''^2) (\omega_0^2 - \omega'''^2)}.$$
(46)

On comparing with the definition of the third-order susceptibility:

$$P^{(3)}(\omega) = -e \ x^{(3)}(\omega) = \epsilon_0 \int d\omega' \int d\omega'' \int d\omega''' \ \chi^{(3)}_{xxxx}(\omega, \omega', \omega'', \omega''') E_0(\omega') E_0(\omega'') E_0(\omega'''), \tag{47}$$

we arrive at the third-order susceptibility per electron,

$$\chi^{(3)}_{_{XXXX}}(\omega,\omega',\omega'',\omega''') = \frac{be^4}{m^4(\omega_0^2 - \omega^2)(\omega_0^2 - \omega'^2)(\omega_0^2 - \omega''^2)(\omega_0^2 - \omega'''^2)}.$$
(48)

On setting a static limit $\omega, \omega', \omega'', \omega''' \to 0$ corresponding to the hyperpolarizability of interest:

$$\chi^{(3)} = \frac{be^4}{\epsilon_0 m^4 \omega_0^8}.$$
(49)

We now employ the interpretation of the averaged quantum metric as effective spring constant $k = m\omega_0^2 \sim 1/\langle g_{xx} \rangle$ [19]. We furthermore estimate $b/m = \omega_0^2/\langle g_{xx} \rangle$, as effectively, the anharmonic and restoring forces become comparable at the distance *d*: $bd^3 \sim kd = m\omega_0^2 d$, with the lengthscale *d* determined by the quantum metric weight $d^2 \sim \langle g_{xx} \rangle$, as given by the spread of the maximally-localized Wannier functions [21]. Hence, we have:

$$\chi^{(3)} = \frac{e^4}{\epsilon_0} \frac{b}{m} \frac{1}{k^3} \sim \frac{1}{\omega_0^2} \frac{b}{m} \frac{1}{k^3} \sim \frac{1}{\omega_0^2} \frac{\omega_0^2}{\langle g_{xx} \rangle} \langle g_{xx} \rangle^3 \sim \langle g_{xx} \rangle^2, \tag{50}$$

which concludes the derivation of the effective hyperpolarizability scaling with the averaged quantum metric $[\chi^{(3)} \sim \langle g_{xx} \rangle^2]$ mentioned in the main text.

- [1] J. Ahn, G.-Y. Guo, N. Nagaosa, and A. Vishwanath, Nature Physics 18, 290–295 (2021).
- [2] J. Ahn, G.-Y. Guo, and N. Nagaosa, Phys. Rev. X 10, 041041 (2020).
- [3] L. Fu and C. L. Kane, Phys. Rev. B 76, 045302 (2007).
- [4] T. L. Hughes, E. Prodan, and B. A. Bernevig, Phys. Rev. B 83, 245132 (2011).
- [5] J. Herzog-Arbeitman, V. Peri, F. Schindler, S. D. Huber, and B. A. Bernevig, Phys. Rev. Lett. 128, 087002 (2022).
- [6] B. Cirera, A. Sánchez-Grande, B. de la Torre, J. Santos, S. Edalatmanesh, E. Rodríguez-Sánchez, K. Lauwaet, B. Mallada, R. Zbořil, R. Miranda, O. Gröning, P. Jelínek, N. Martín, and D. Ecija, Nature Nanotechnology 15, 437–443 (2020).
- [7] W. J. Jankowski, J. J. P. Thompson, B. Monserrat, and R.-J. Slager, "Excitonic topology and quantum geometry in organic semiconductors," (2024), arXiv:2406.11951 [cond-mat.mes-hall].
- [8] N. V. Tepliakov, J. Lischner, E. Kaxiras, A. A. Mostofi, and M. Pizzochero, Phys. Rev. Lett. 130, 026401 (2023).
- [9] J. Kruthoff, J. de Boer, J. van Wezel, C. L. Kane, and R.-J. Slager, Phys. Rev. X 7, 041069 (2017).
- [10] H. C. Po, A. Vishwanath, and H. Watanabe, Nat. Commun. 8, 50 (2017).
- [11] B. Bradlyn, L. Elcoro, J. Cano, M. G. Vergniory, Z. Wang, C. Felser, M. I. Aroyo, and B. A. Bernevig, Nature 547, 298 (2017).
- [12] R. Boyd, Nonlinear Optics, 4th Edition, (Elsevier, Amsterdam., 2019).
- [13] J. E. Sipe and A. I. Shkrebtii, Phys. Rev. B 61, 5337 (2000).
- [14] W. P. Su, J. R. Schrieffer, and A. J. Heeger, Phys. Rev. Lett. 42, 1698 (1979).
- [15] W. P. Su, J. R. Schrieffer, and A. J. Heeger, Phys. Rev. B 22, 2099 (1980).
- [16] J. Provost and G. Vallee, Communications in Mathematical Physics 76, 289 (1980).
- [17] I. Souza, T. Wilkens, and R. M. Martin, Phys. Rev. B 62, 1666 (2000).
- [18] S. Kivelson, Phys. Rev. B 26, 4269 (1982).
- [19] Y. Onishi and L. Fu, Phys. Rev. B 110, 155107 (2024).
- [20] J. L. Bredas, C. Adant, P. Tackx, A. Persoons, and B. M. Pierce, Chemical Reviews 94 (1994).
- [21] N. Marzari and D. Vanderbilt, Phys. Rev. B 56, 12847 (1997).