Exploring Three-Atom-Thick Gold Structures as a Benchmark for Atomic-Scale Calibration of Break-Junction Systems

J.P. Cuenca, T. de Ara, A. Martinez-Garcia, E. Guzman, and C. Sabater^{*}

Departamento de Física Aplicada and Instituto Universitario de Materiales de Alicante (IUMA),

Universidad de Alicante, Campus de San Vicente del Raspeig, E-03690 Alicante, Spain. and

Institute of Physics, École Polytechnique Fédérale de Lausanne (EPFL), CH- 1015 Lausanne, Switzerland.

(Dated: March 4, 2025)

We present an in-depth study of electronic transport in atomic-sized gold contacts using Break-Junction (BJ) techniques under cryogenic and ambient conditions. Our experimental results, supported by classical molecular dynamics (CMD) simulations and *ab initio* calculations, provide compelling evidence for the formation of three-atom-thick structures in gold nanocontacts under tensile stress. These findings extend previous studies that confirmed the existence of one- and two-atomthick chains. Beyond identifying these novel atomic configurations, we introduce a fast and robust calibration method for Break-Junction systems, leveraging the characteristic length of these structures to convert piezo displacement into absolute distance in angstroms. Our approach presents a novel and robust method for calibrating atomic distances in atomic conductor systems at both cryogenic and room temperatures. The results also enable the assessment of electrode sharpness, even at room conditions.

I. INTRODUCTION

In the field of molecular and atomic electronics [1], one of the challenges is understanding the structure of electrodes at the nanoscale [2–5]. Typically, the most common techniques used to determine the electronic transport are the Scanning Tunneling Microscope in its break junction configuration (STM-BJ) [6] and the Mechanically Controllable Break Junction (MCBJ) [3, 7, 8]. Both methods are commonly used at low-temperature (4.2 K) and room conditions. However, measuring electronic transport through these techniques is insufficient to fully reveal the atomic structure. Usually, these experiments are supported by CMD simulations [9] and *ab initio* electronic transport calculations [1, 10–16].

Despite significant progress in understanding the geometry of atomic-sized gold contacts and the number of atoms coordinated between them [17–26], only atomic structures with one or two atoms of thickness have been identified so far, particularly at low temperatures. While all the studies have shed light on the structure and behavior of one- and two-atom-thick chains [17, 25], contacts thicker than two atoms have not been extensively studied at low temperatures, let alone under ambient conditions. Therefore, our goal is to investigate the existence of three-atom-thick structures and explore their use for calibrating the break-junction (BJ) system across different environments.

In this manuscript, we have combined STM-BJ at cryogenic temperature and MCBJ at room conditions experiments, CMD simulations, and electronic transport calculations. Thanks to this combination, we have identified three-atom-thick structures. Not only has there been progress in techniques to understand the atomicsized contacts geometries, but significant advancements have also been made in calibrating STM-BJ and MCBJ at low temperatures[27]. However, when it comes to developing new methods for calibrating a MCBJ at ambient conditions, progress has been limited. In our case, we have used the structures composed by three, two and one- atom-thick to calibrate or convert the applied voltage to the piezo system in relative displacement between electrodes. Once our systems are calibrated, we can represent conductance versus calibrated displacement, allowing us to study the slope of these curves historically named traces of conductance.

In summary, after unmasking the existence of three atom structures, our approach provides a rapid and robust method for calibrating distances, offering new insights into the geometry of atomic contacts at cryogenic temperature and room conditions. Another important aspect of our study is that, once the calibration is completed and after analyzing the slopes of conductance versus relative displacement curves, we can determine how much atomically sharpened the electrodes are during the dynamic process of rupture.

II. METHODS AND MATERIALS

A. Electronic transport in BJ techniques

The most commonly used experimental techniques for measuring electronic transport in atomic-sized contacts[1, 4, 5] are the Scanning Tunneling Microscope in its break junction configuration (STM-BJ)[2, 6] and the Mechanically Controllable Break Junction (MCBJ)[3, 8].

In this paper, we analyze atomic-sized gold contacts using break-junction techniques. Specifically, we performed experiments at low temperatures (4.2 K) using the STM-BJ method, while for experiments under ambient conditions, we employed the MCBJ technique. For

^{*} carlos.sabater@ua.es



Figure 1. Panel (a) shows an illustration of STM and panel (b) shows the MCBJ experimental setups. Panel (c) illustrates an atomic-sized contact connected in series with a battery and an ammeter.

the STM, the gold electrodes consisted of two wires with a diameter of 0.25 mm (Goodfellow), positioned facing each other by their circular surfaces and intersecting perpendicularly (see Figure 1a). In contrast, for the MBCJ, a single notched gold wire was used, grooved, and deposited onto a bendable substrate, as Figure 1 b) shows.

Regardless of the method used to create the atomicsized contact, we measured the conductance using two probes with DC current. Figure 1 c) illustrates a schematic of the basic circuit connections for measuring the current in an atomic-sized contact, where the bias voltage (V_{bias}) is applied to the atomic contact, which is connected in series with the ammeter. It is well known that a gold or any noble material contact has a resistance of 12906 Ω , and therefore, the current it produces would be in the microampere range, needing amplification of several orders of magnitude. In this case, current-tovoltage amplifiers are typically used, as they allow the amplified current to be converted into a voltage signal for recording by a Data Acquisition System (DAQ).

In our experiments, the bias voltage applied in both configurations (STM-BJ and MCBJ) was 100 mV, and the current was measured by a Femto I/V converter (model DLPCA-200) using an amplification factor of 10^5 V/A. Knowing the current and the voltage, we can expressed it in terms of conductance, as $G = \frac{1}{R} = \frac{V_{bias}}{I}$, and then convert it to units of quantum conductance, with $G_0 = \frac{1}{12906} \Omega^{-1} = \frac{2e^2}{h}$, where *e* is the charge of an electron, *h* is Planck's constant, and the factor of 2 comes from spin degeneracy.

Given that we are working with experiments involving junction rupture, we will represent conductance as a function of the relative distance between electrodes, which can be expressed in Ångströms if the system is calibrated, or in units of voltage applied to the piezoelectric if is not calibrated. Historically, theses curves are named conductance's traces. The traces can be either of rupture or formation, depending on whether the nanocontact is being stretched or compressed. In this manuscript, we will focus solely on the analysis of rupture traces.

B. Molecular Dynamics Simulations and *ab initio* calculations

Classical molecular dynamics (CMD) operates by solving Newton's second law to determine the trajectory of each atom throughout a simulation [28, 29]. In our case, we use CMD to simulate the rupture and formation of an atomic gold [9]. The simulation was performed using the LAMMPS [30–32] code with an embedded-atom model (EAM) [33] with the interatomic potential described by Zhou *et al.* [34, 35]. We simulate the pull-push process by applying opposite velocities of ± 0.04 Å/ps at each step to the upper and lower layers of the electrode, with steps of 1 ps. To ensure the formation and rupture of the junction, the rupture and formation take 250 ns and 254 ns, respectively. The temperature of the system was maintained at 300 K in an NVT canonical ensemble with a Nose-Hoover thermostat. The input configuration chosen is a gold nanowire oriented along the crystallographic direction (001) with a narrower middle section [24].

Every 5 ns in the simulation, a snapshot of the position is taken, allowing us to prepare the system for the *ab initio* calculations. For that purpose, we reduce the number of atoms in the snapshot by taking only ~ 80 atoms in the vicinity of the minimal cross-section. With a small CMD minimization process target at the outermost layers of the snapshots, we add two layers of gold (001) at the extremes needed for the following transport computation.

To compute the electronic transport over the snapshot, we used the non-equilibrium Green's function (NEGF) approach. The code used was the Atomistic Nano Transport (ANT.G) code [15, 36–39], which interfaces with Gaussian [40]. The added gold layers use the CRENBS basis set [41], the rest of the atoms have the basis pob-TZVP-rev2 [42, 43], prepared for metallic gold computations. Finally, the DFT computation is done at the GGA level with the implementation of PBE built-in Gaussian [44, 45].

III. RESULTS AND DISCUSSION

A. Low Temperature STM-BJ

As previously mentioned, the traces represent conductance versus the relative displacement of the electrodes, measured in distance units if the system is calibrated, or in voltage units if the piezoelectric system is not calibrated, regardless of the BJ technique used.

As noted by Untiedt *et al.* in the manuscript [27], before 2002, a controversy arose regarding the measurement of interatomic distances in gold chains, with some authors reporting a distance of 3.6 Å, while others found 2.5 Å. Thanks to Untiedt's manuscript, this issue was

3

resolved using three different calibration methods. Two of these methods are based on measurements of current in tunneling barriers, while the third utilizes an STM-BJ system combined with an interferometric setup and length histograms. However, the first two methods require knowledge of the material's work function, which is known to change in non-vacuum environments, such as under ambient conditions. Therefore, these methods cannot be applied in ambient conditions, making the only viable option the measurement of atomic distances through length histograms. Therefore, one of the objectives of this manuscript is to contribute with a new calibration method and reveal the corresponding geometry of structures with a thickness of three atoms.

To calibrate the distance in our STM-BJ experiments conducted at low temperature (4.2 K), we used the length histogram method, converting the voltage applied to the piezoelectric system into Ångströms (Å) [17, 18, 27]. Figure 2(a) shows a rupture trace of gold at 4.2 K, where the relative electrode displacement is expressed in Å. In other words, we define a plateau as a region where the conductance remains stable, without abrupt jumps between consecutive points. Three conductance plateaus can be observed in this Figure 2(a). To facilitate visualization, we assigned a color code—purple, yellow, and red—to indicate the conductance ranges of the first, second, and third plateaus, respectively. These plateaus correspond to cross-sectional structures of one, two, and three atoms in thickness, as also referenced in the following panel and throughout the rest of the paper.

One of the most common statistical analyses performed on conductance traces is the construction of conductance histograms, as they provide insight into the most frequently observed conductance values. These values relates to certain atomic geometries, which appear more often than others during the stretching process. Figure 2(b) shows a conductance histogram of Au traces at 4.2 K in high vacuum. The same color code is applied to the dashed rectangles to help in identifying the three different thicknesses of the structures, corresponding to the previously defined plateaus. This is typically the characteristic histogram for gold with a distinctive peak at 1 G_0 , which has been attributed to the contribution of monomers, dimers, and atomic chains [17, 21, 24, 46-49]. Furthermore, the atomic structures associated with the second plateau was revealed in Ref. [25]. However, the nature of the structures corresponding to the third plateau (or three-atom thickness) remains uncertain, with values ranging between approximately 2.1 and $3 G_0$.

As mentioned earlier, one way to convert piezo voltage to relative distance is through length histograms. In the literature, we can find length histograms already in distance units for both the first [17, 27, 47–49] and second plateau [25] (also recognized as structures of one and two atoms in thickness). In this manuscript, we plan to perform the length histogram on the plateau that hypothetically belongs to contacts with a thickness of three



Figure 2. Panel (a) illustrates a rupture trace featuring three distinct plateaus, each highlighted in a different color. The purple, yellow, and red regions correspond to the first, second, and third plateaus, respectively, representing atomic-sized geometries with thicknesses of one, two, and three atoms. Panel (b) shows a normalized conductance histogram constructed from 6000 rupture traces, using the same color code to indicate these atomic structures.

atoms (third plateau).

In Figure 3, we show the length histograms performed on the first, second, and third plateaus in approximately 6000 gold rupture traces at 4.2 K. The color code purple, vellow, and red represents, respectively, the structures of one, two, and three atoms in thickness. As seen in Fig. 3, the bottom panel (c) shows the length histogram (purple) of the first plateau characteristic of gold, which is similar to that described in the literature [17, 27, 47–49]. In the middle panel (b), the length histogram (yellow) is presented, which also agrees with previous results described in reference [25]. Finally, the upper panel (a) histogram (red) represents the length plateaus between 2.1 G_0 and 3.0 G_0 , and as observed, the most typical value is 2.5 Å, indicating that typically during the breaking process, contacts of approximately one atomic distance and a thickness of three atoms are formed. Moreover, observ-



Figure 3. Histogram of lengths for the last three conductance plateaus obtained from rupture traces at 4.2 K in cryogenic vacuum. The bottom panel (c) corresponds to the conductance range of 0.8–1.2 G_0 (purple histogram), the middle panel (b) shows the length histogram for plateaus in the range of 1.2–2.1 G_0 (yellow histogram), and the upper panel (a) presents the length histogram for plateaus within the range of 2.0–3.0 G_0 (red histogram).

ing the third-length histograms, the maximum frequency peak is 2.5 Å. That is, regardless of whether we have a structure of one, two, or three atoms in thickness, the distance that is reproduced the most frequently is that of an atomic distance of 2.5 Å.



Figure 4. The density plot was constructed from 6000 rupture traces of gold measured at 4.2 K in a cryogenic vacuum. The color bar is on a logarithmic scale, transitioning from warm to cold colors.

In Fig. 4, a density plot is shown. The relative displacement of all traces has been shifted to align at the collapse point, which corresponds to the first value of the first plateau at $1G_0$, when reading the trace from left to right. The color bar ranges from zero counts (white) to ten thousand counts (blue). The green color indicates that the event occurs approximately a hundred times. Fig. 4 shows that in the range of 0.8–1.0 G_0 , the green area extends up to 5 Å, which is in clear agreement with the length histogram (red) in Fig. 3 [49]. Furthermore, the blue-cyan region around $1G_0$ extends from 0 to 2.5 Å, corresponding to the first peak of the length histogram for the first plateau (purple) in Fig. 3.

Nevertheless, in a density plot of traces at room temperature, it appears that the point clouds corresponding to the regions of $2.5G_0$, $2G_0$, and $1G_0$ have similar lengths. This suggests that, although they are not calibrated, the most frequent regions in the plot exhibit the same apparent length, even though they are represented in volts rather than length units. Building on this observation, we propose a novel calibration method for BJ techniques. Specifically, we construct density plots in units of conductance versus relative displacement. Then, knowing that the regions corresponding to structures of 1, 2, and 3 atoms in thickness correspond to 2.5 Å, as observed at low temperatures, we perform an equivalence calibration along with an estimation of its calibration error.

B. MCBJ Approach at Room Condition

As it is well known, an MCBJ consists of a piezo element responsible for bending the flexible substrate on which the notched wire is mounted (as Fig.1 b) shows). When the piezo pushes against the substrate, it breaks the contact, allowing the measurement of a rupture conductance trace, where the units of relative displacement are in volts, as shown in Fig. 5a).

Regardless of whether the electrode displacement is calibrated or not, a conductance histogram can be obtained. Figure 5b) presents a typical conductance histogram, normalized in the range of 0.1 to 13 G_0 , constructed from 5000 rupture traces. The inset shows the normalized histogram in the range of 0.1 to 3.2 G_0 , where the highlighted rectangles indicate the conductance ranges attributed to structures of one-, two-, and three-atom thickness. These structures will be revealed through CMD simulations, and their electronic transport properties will be obtained by DFT calculation.

C. Identifying the structure of three atom thickness via MD and DFT

In Figure 6, the upper section shows some of the structures obtained through molecular dynamics simulations of continuous rupture cycles of the gold nanowire. These



Figure 5. (a) Trace of conductance of gold at room conditions measure in MCBJ. Where the relative displacement is volts units. The arrow indicates the direction to read the trace. (b) histogram of conductance in the range of 0.1 to 12 G_0 , inset show a zoom in of the range 0.1 to 3 G_0 , the colored rectangles indicates the structure attributed.

structures are highlighted with a colored rectangle, where the color code corresponds to the theoretically obtained conductance values.

The lower panel represents the conductance obtained throughout the simulation steps. This panel consists of three subgraphs, each displaying a simulated rupture trace. In each trace, a point marked with a circle indicates the corresponding structure, with a color code matching that of the upper panel. Additionally, in the background of the lower panel, three color-coded regions highlight the zones corresponding to one-, two-, and three-atom thicknesses, as consistently shown throughout the manuscript.

As observed in the figure, DFT calculations have revealed three-atom-thick structures with a triangular packing, exhibiting a conductance of approximately 2.5 G_0 . On the other hand, two-atom-thick structures show a conductance close to $1.6G_0$. Moreover, single-atomthick structures present a conductance of approximately $1G_0$. Finally, the conductance traces show that rupture occurs when the conductance approaches $0 G_0$.

Lastly, the lower right panel displays a histogram of the calculated conductances, which shows a resemblance to the experimental ones, as seen in the inset 5 (b). Despite the fact that the histogram is composed only by six handpicked simulated traces, while the experimental one is composed of thousands traces, the overall trend remains comparable.



Figure 6. Conductance of the MD snapshots, each color in the graph representing consecutive snapshots. On the right side there is a histogram of the conductance of the calculations. The color of the background is for the conductance range found in different plateaus: (0.8-1.2), (1.2-2.1) and (2.1-3.1) G_0 . Above the conductance graph, there are schematic representations of the points highlighted in the same color of the frame.

D. New methodology to calibrate a BJ system at room conditions based on experimental, simulation, and calculations results

However, a depicted trace provides only half of the information, as the relative distance can be expressed not only in volts but also in angstroms. To carry out the calibration and following the methodology described above, we have generated a density plot using the data from the rupture traces, ensuring that all of them are expressed in units of relative displacement in volts applied to the piezo. For the construction of the density plot, we will ensure that all traces are offset to the same point, where this is the first value less than or equal to $1G_0$ (see panel a) figure 7). The color bar is displayed on a logarithmic scale, spanning from 0 counts (white color) to approximately 800 counts(black color). It has been selected as a criterion that the red/orange color (where is the most representative area), Therefore, the areas marked in red/orange show very distinctive characteristics, and their relative distance in volts is very similar. Thus, following the previous discussion at 4.2 K, this means that these relative distances approximately measure 2.5 Å.

To highlight the fact that the first, second, and third plateaus exhibit similar relative displacements, we processed the data as shown in Figure 7 (b). In this panel, a density plot is illustrated, where counts below 80 units are color in white. From this cloud of points, the first 3 bins and the last three bins are selected to calculate an average value in mV units, thereby obtaining a relative voltage difference. The arrows on this panel, along with the color code used throughout the manuscript, indicate the relative distance expressed in voltage units (ΔV). This voltage will be expressed in absolute value (see Table I), as if we are below zero, they will be negative (the range between 1 and 3 G_0 is positioned to the left, meaning in negative values, while the range between 0 and 1 G_0 is positioned to the right, meaning in positive values). As we have seen in panel b), the three cyan-colored point clouds measure approximately the same distance in absolute value units ΔV . As we have reiterated throughout the discussion of this manuscript, these clouds have a length of 2.5 Å. Therefore, Table I shows the summarized results obtained from this panel (b).

Table I. The first column displays the conductance range for the cloud, the second column represents the absolute value in units of mV of the relative displacement, and the third column denotes the common value estimated for these plateaus.

| Conductance range (G_0) | $ \Delta V $ (mV) | Atomic distance Au $(\text{\AA})^{[27]}$ |
|---------------------------|-------------------|---|
| 2.1 - 3.1 | 7.3 | |
| 1.3 - 2.1 | 8.1 | 2.5 |
| 0.8 -1.2 | 7.6 | |

Therefore, by calculating the mean value and the standard deviation of the data in Table I, we obtain that the calibration factor is 7.7 ± 0.3 mV, which corresponds to 2.5 Å. Thanks to this calibration factor, we can now calibrate all our traces and density plots. Panel Fig. 7 (c) represents the calibrated density plot, where it can be observed that the areas from light orange to red approximately correspond to 2.5 Å.

Once our system is calibrated, it is fundamental to create histograms of length, just as was done for the gold data at low temperatures and with the STM-BJ. Figure 8, a length histogram is shown for plateaus ranging from 0.8 to 1.2 G_0 conductances (panel (c)). In panel (b), the histogram corresponding to plateaus ranging from 1.2 to 2.1 G_0 is presented. Finally, panel (a), the histogram of length is represented for plateaus ranging from 2.1 to 3.0 G_0 . As can be observed, in MCBJ at room condi-



Figure 7. (a) Density plot of gold rupture traces under room conditions, where relative displacement is not calibrated and units are in volts. (b) A two-dimensional plot was employed for calibration, with color counts representing only the maximum and one order of magnitude less. (c) Density plot of gold rupture traces under room conditions.

tions, the most typical value in all cases is 2.5 Å, which corresponds to a gold atom diameter, as was expected.

Once all calibrations have been completed, we can represent the relative displacement of the trace in Å as shown in Figure 9. An inset is presented to emphasize



Figure 8. Upper histogram of lengths (a) 2.1-3.0 G_0 (red), middle histogram of lengths (b) 1.2-2.1 G_0 (yellow), lower histogram of lengths (c) 0.8-1.2 G_0 (purple).

three plateaus that correspond to atomic structures. As a curiosity the plateau corresponding to the structure of three atoms thick is longer in distance than the first and second plateaus.



Figure 9. Calibrated trace of conductances, where the relative length electrodes is expressed in Å. The Inset is a zoom-in order to observe the shape of the plateaus in the range of 3 to 1 G_0 .

In our manuscript, we evaluate how the cross-section of the electrode decreases when is stretched, which indicates, how the electrode tapers under tension, both at low temperatures and at room conditions. To do this, we consider that gold (Au) at 4.2 K forms atomic chains (1 atom thick) and diatomic chains (2 atoms thick) with variable lengths.

Since our method is based on evaluating how the conductance slope varies with distance, long plateaus affect the overall slope of the analyzed trace. Therefore, to avoid these plateaus influencing our statistics, we have decided to adopt a precautionary approach: using structures that are above the 5 G_0 threshold. This method is based on obtaining, once the relative displacements are calibrated, the decay slopes ranging from 12 G_0 to 5 G_0 . Figure 10 shows an illustration of two different electrodes at the moment of being stretched. The image on the left shows the shape of its cross-section, presenting steeper slopes due to a more abrupt variation, as seen in the red curve in the central graph. On the other hand, the illustration on the right shows a smaller cross-section, where, by moving an atomic distance, fewer atoms are disconnected, resulting in a lower slope compared to the previous case (see blue curve). In other words, depending on the cross-section, slopes that tend to zero will indicate a smaller cross-section, while slopes that tend to infinity will suggest a larger cross-section.



Figure 10. Illustration of two electrodes with different crosssections. The central plot shows how the slope decreases for the different cross-sections, with the wider one represented in red and the smaller slope in blue.

Once all the slopes are fitted (see Figure 13 in SI), we create a histogram of the slopes in units of $G_0/\text{\AA}$, where all slopes are computed as absolute values, as shown in Figure 11.

It is clear that all the slopes are negative; however, to bring clarity to the histogram, we will use the absolute values. Figure 11 shows a normalized histogram of the 5000 slopes analyzed. Based on the previous results, we identified three distinct conductance decay slopes located at 0.58, 0.82, and 1.06 in units of $G_0/\text{Å}$. To gain insight into sharpness, we suggest thinking in terms of atomic distances. For example, if we assume that these are the three slopes we have and that the electrodes are moved by 2.5 Å, this would imply a conductance reduction of approximately 1.45, 2.05, and 2.62 G_0 for the three cases. In other words, in the first case, the cross-section is reduced by at least one atom, in the second case by at least two atoms, and in the last case by at least three.



Figure 11. (a) Normalized histogram of conductance decay slopes $G_0/\text{Å}$. The histogram represents the distribution of slope values obtained from rupture traces, fitted with Gaussian components (colored curves) corresponding to different characteristic slopes. (b) Representative rupture traces of conductance as a function of relative displacement, where each color corresponds to a specific slope distribution in the histogram above, illustrating different levels of electrode sharpness and structural evolution.

These slopes provide insights into the atomic-scale evolution of electrode sharpness during the rupture process. Specifically, the most typical slopes in terms of atomic distances are 1.45, 2.05, and 2.62 $G_0/\text{Å}$, which can be interpreted as different sharpness levels of the electrodes. The sharpest electrodes exhibit lower slopes, corresponding to the disconnection of a single atomic pathway per atomic displacement, whereas broader electrodes exhibit higher slopes, suggesting a loss of multiple atomic connections per unit of displacement. (see Sup. Inf. section Gaussian Fitting for more details).

In Fig. 11 upper panel is shown we see the histogram slopes, that is fitted by addition of three Gaussian. the green curve is the case with the high probability (slope is $0.5 G_0/\text{\AA}$ in blue and pink the second and third most probability cases. Fig. 11 bottom panel displays three representative traces with different slopes, whose values correspond to the centers of the Gaussian distributions in the upper panel, following the same color code. Specifi-

cally, the green trace corresponds to a slope of $0.5 G_0/\text{\AA}$, the blue trace to $0.8 G_0/\text{\AA}$, and the pink trace to $1 G_0/\text{\AA}$. In summary, the representation of the traces shows a transition from the sharpest (left) to the least sharp (right).



Figure 12. Conductance slopes and regression for different materials and temperatures. Left panels show normalized histograms of slopes $(G_0/\text{Å})$ from 5000 rupture traces for gold (Au) at 300 K (top), 4.2 K (middle), and alpha-tin (α -Sn) at 4.2 K (bottom). Gaussian fits highlight distinct slope distributions. Right panels display the coefficient of determination (R^2) for the linear fits, confirming the robustness of the slope extraction.

However, we not only aim to extend this new methodology to assess how sharp our electrodes are as a function of stretching, but also to apply it at different temperatures, such as Au at 4.2 K, as well as to other materials like alpha-tin (α -Sn). This material is particularly interesting because, among other characteristics, the conductance of a single atom is approximately 2.2 G_0 [50].

Figure 12 shows, in the left column, the slope histograms for atomic gold at room temperature, at 4.2 K, and for α -Sn at low temperatures. The right column displays the histograms of the coefficient of determination R^2 . As observed in all these histograms, the data are closely clustered around $R^2 = 0.95$.

Comparing the histograms for gold at 4.2 K, we see that there is only one peak corresponding to the value 0.47 $G_0/\text{\AA}$, which is in complete agreement with the most probable value for gold at 300 K. Against all expectations, this suggests that gold remains very sharp at low temperatures when stretched, whereas at room temper-

ature, the sharpening occurs more frequently.

On the other hand, α -Sn exhibits two distinct Gaussian distributions, one centered at 1.03 and the other at 1.37. Considering only the first Gaussian and knowing that a α -Sn atom has an interatomic distance of 2.9 Å [51], we estimate that if we displace by this distance, the conductance reduction upon stretching decreases by approximately 2.9 G_0 . This implies a reduction of at least one Sn atom, which, as mentioned previously, has a conductance of 2.2 G_0 . For the other pending case, if we displace by at least one atomic distance, we would decrease the conductance by approximately 4 G_0 , that is, at least 2 Sn atoms.

IV. CONCLUSIONS

In this work, we have experimentally identified the existence of three-atom-thick gold structures in atomic contacts and their typical triangular stacking arrangement, expanding the previous understanding limited to oneand two-atom-thick chains. The combination of Break-Junction (BJ) experimental techniques, including STM-BJ and MCBJ, along with molecular dynamics simulations and *ab initio* electronic transport calculations, has enabled us validate these findings and propose a novel and robust calibration methodology for BJ systems.

The proposed method allows for the conversion of piezoelectric displacement into absolute distances using the characteristic length of gold contacts at different thickness states. Additionally, we have developed a technique to assess the sharpness of electrodes during elongation, providing key insights into the geometry and structural evolution of atomic contacts.

The obtained results have direct applications in the precise calibration of Break-Junction systems, even under ambient conditions, which are typically challenging to calibrate due to the dependence on work functions and the necessity of characterizing the metal under these conditions. This represents a significant advancement in the characterization of metallic contacts at the atomic scale. This methodology could also be extended to other materials and studies in molecular electronics, enabling a better understanding of transport properties in metallic and molecular nanostructures, thereby providing insights into their geometry and mechanical properties at the atomic scale.

These findings not only contribute to the advancement of BJ system calibration but also allow us to explore new structures. Even for experiments under roomtemperature conditions, such as with silver (Ag) and copper (Cu), our methodology can be used for calibration. Moreover, the slope method has provided new insights into how materials sharpen or remain stable during the stretching process, and how many atoms are disconnected during this process. We propose that this method could be extended to molecular electronics, where the slope could reveal how the decoration of molecules on the wire affects its geometry and sharpening.

V. ACKNOWLEDGEMENT

The authors acknowledge financial support from Generalitat Valenciana through CIDEXG/2022/45, CIGRIS/2021/159, PROMETEO/2021/017 and by the Spanish Government through MFA/2022/045, PID2019-109539-GB-C41, PID2022-141712NB-C22 and and PID2023-146660OB-I00. This work forms part of the Advanced Materials programme and was supported by MCIN with funding from European Union NextGenerationEU (PRTR-C17.I1) and by Generalitat Valenciana (MFA/2022/045). The theoretical modelling was performed on the University of Alicante.

- J. C. Cuevas and E. Scheer, *Molecular Electronics*, 2nd ed. (WORLD SCIENTIFIC, 2017) https://www.worldscientific.com/doi/pdf/10.1142/10598.
- [2] N. Agraït, J. G. Rodrigo, and S. Vieira, Conductance steps and quantization in atomic-size contacts, Phys. Rev. B 47, 12345 (1993).
- [3] J. M. Krans, C. J. Muller, I. K. Yanson, T. C. M. Govaert, R. Hesper, and J. M. van Ruitenbeek, One-atom point contacts, Phys. Rev. B 48, 14721 (1993).
- [4] N. Agraït, A. L. Yeyati, and J. M. Van Ruitenbeek, Quantum properties of atomic-sized conductors, Phys. Rep. 377, 81 (2003).
- [5] F. Evers, R. Korytár, S. Tewari, and J. M. van Ruitenbeek, Advances and challenges in single-molecule electron transport, Rev. Mod. Phys. 92, 035001 (2020).
- [6] J. I. Pascual, J. Méndez, J. Gómez-Herrero, A. M. Baró, N. García, and V. T. Binh, Quantum contact in gold nanostructures by scanning tunneling microscopy, Phys. Rev. Lett. **71**, 1852 (1993).

- [7] J. M. Krans and J. M. van Ruitenbeek, Subquantum conductance steps in atom-sized contacts of the semimetal sb, Phys. Rev. B 50, 17659 (1994).
- [8] J. M. Krans, J. M. van Ruitenbeek, V. V. Fisun, I. K. Yanson, and L. J. de Jongh, The signature of conductance quantization in metallic point contacts, Nature **375**, 767 (1995).
- [9] U. Landman, W. D. Luedtke, N. A. Burnham, and R. J. Colton, Atomistic mechanisms and dynamics of adhesion, nanoindentation, and fracture, Science 248, 454 (1990).
- [10] M. D. Ventra, *Electrical Transport in Nanoscale Systems* (Cambridge University Press, 2008).
- [11] H. Haug and A.-P. Jauho, *Quantum Kinetics in Transport and Optics of Semiconductor*, 2nd ed. (SpringerVerlag, Berlin, 1996).
- [12] M. Brandbyge, J.-L. Mozos, P. Ordejón, J. Taylor, and K. Stokbro, Density-functional method for nonequilibrium electron transport, Phys. Rev. B 65, 165401 (2002).

- [13] A. R. Rocha, V. M. García-Suárez, S. Bailey, C. Lambert, J. Ferrer, and S. Sanvito, Spin and molecular electronics in atomically generated orbital landscapes, Phys. Rev. B 73, 085414 (2006).
- [14] F. Pauly, J. K. Viljas, U. Huniar, M. Häfner, S. Wohlthat, M. Bürkle, J. C. Cuevas, and G. Schön, Clusterbased density-functional approach to quantum transport through molecular and atomic contacts, New Journal of Physics 10, 125019 (2008).
- [15] D. Jacob and J. J. Palacios, Critical comparison of electrode models in density functional theory based quantum transport calculations, The Journal of Chemical Physics 134, 044118 (2011).
- [16] J. Ferrer, C. J. Lambert, V. M. García-Suárez, D. Z. Manrique, D. Visontai, L. Oroszlany, R. Rodríguez-Ferradás, I. Grace, S. W. D. Bailey, K. Gillemot, H. Sadeghi, and L. A. Algharagholy, Gollum: a nextgeneration simulation tool for electron, thermal and spin transport, New Journal of Physics 16, 093029 (2014).
- [17] A. I. Yanson, G. R. Bollinger, H. E. van den Brom, N. Agraït, and J. M. van Ruitenbeek, Formation and manipulation of a metallic wire of single gold atoms, Nature **395**, 783 (1998).
- [18] R. H. M. Smit, C. Untiedt, A. I. Yanson, and J. M. van Ruitenbeek, Common origin for surface reconstruction and the formation of chains of metal atoms, Phys. Rev. Lett. 87, 266102 (2001).
- [19] C. Untiedt, M. J. Caturla, M. R. Calvo, J. J. Palacios, R. C. Segers, and J. M. van Ruitenbeek, Formation of a metallic contact: Jump to contact revisited, Phys. Rev. Lett. 98, 206801 (2007).
- [20] C. Sabater, C. Untiedt, J. J. Palacios, and M. J. Caturla, Mechanical annealing of metallic electrodes at the atomic scale, Phys. Rev. Lett. 108, 205502 (2012).
- [21] C. Sabater, M. Caturla, J. Palacios, and C. Untiedt, Understanding the structure of the first atomic contact in gold, Nanoscale Res. Lett. 8, 257 (2013).
- [22] W. Dednam, C. Sabater, M. A. Fernandez, C. Untiedt, J. J. Palacios, and M. J. Caturla, Modeling contact formation between atomic-sized gold tips via molecular dynamics, Journal of Physics: Conference Series 574, 012045 (2015).
- [23] M. A. Fernández, C. Sabater, W. Dednam, J. J. Palacios, M. R. Calvo, C. Untiedt, and M. J. Caturla, Dynamic bonding of metallic nanocontacts: Insights from experiments and atomistic simulations, Phys. Rev. B 93, 085437 (2016).
- [24] C. Sabater, W. Dednam, M. R. Calvo, M. A. Fernández, C. Untiedt, and M. J. Caturla, Role of first-neighbor geometry in the electronic and mechanical properties of atomic contacts, Phys. Rev. B 97, 075418 (2018).
- [25] C. Sabater, J. J. Palacios, M. J. Caturla, and C. Untiedt, Revealing the geometry and conductance of doublestranded atomic chains of gold, The Journal of Physical Chemistry C 124, 26596 (2020).
- [26] W. Dednam, S. Tewari, E. B. Lombardi, J. J. Palacios, J. M. van Ruitenbeek, and C. Sabater, Dynamic bonding influenced by the proximity of adatoms to one atom high step edges, Phys. Rev. B **106**, 125418 (2022).
- [27] C. Untiedt, A. I. Yanson, R. Grande, G. Rubio-Bollinger, N. Agraït, S. Vieira, and J. van Ruitenbeek, Calibration of the length of a chain of single gold atoms, Phys. Rev. B 66, 085418 (2002).

- [28] D. Frenkel and B. Smit, Understanding Molecular Simulation: From Algorithms to Applications (Academic Press, 2002).
- [29] M. P. Allen and D. J. Tildesley, Computer simulation of liquids (Oxford university press, 1989).
- [30] S. Plimpton, Fast parallel algorithms for short-range molecular dynamics, J. Comput. Phys. 117, 1 (1995).
- [31] S. Plimpton et al., Computer code LAMMPS, publicly available from https://www.lammps.org, date of access: 14-Feb-2023.
- [32] A. P. Thompson, H. M. Aktulga, R. Berger, D. S. Bolintineanu, W. M. Brown, P. S. Crozier, P. J. in 't Veld, A. Kohlmeyer, S. G. Moore, T. D. Nguyen, and R. S. *et al.*, LAMMPS - a flexible simulation tool for particlebased materials modeling at the atomic, meso, and continuum scales, Comp. Phys. Comm. **271**, 108171 (2022).
- [33] M. S. Daw and M. I. Baskes, Semiempirical, quantum mechanical calculation of hydrogen embrittlement in metals, Phys. Rev. Lett. 50, 1285 (1983).
- [34] X. Zhou, H. Wadley, R. A. Johnson, D. Larson, N. Tabat, A. Cerezo, A. Petford-Long, G. Smith, P. Clifton, R. Martens, *et al.*, Atomic scale structure of sputtered metal multilayers, Acta Mater. **49**, 4005 (2001).
- [35] H. Wadley, X. Zhou, R. Johnson, and M. Neurock, Mechanisms, models and methods of vapor deposition, Prog. Mater. Sci 46, 329 (2001).
- [36] J. J. Palacios, A. J. Pérez-Jiménez, E. Louis, E. San-Fabián, and J. A. Vergés, First-principles approach to electrical transport in atomic-scale nanostructures, Physical Review B: Condensed Matter 66, 10.1103/physrevb.66.035322 (2002).
- [37] J. J. Palacios, A. J. Pérez-Jiménez, E. Louis, E. San-Fabián, J. A. Vergés, and Y. García, Molecular electronics with gaussian98/03, in *Computational Chemistry: Re*views of Current Trends (World Scientific, 2005) pp. 1– 46.
- [38] D. Jacob, J. Fernández-Rossier, and J. J. Palacios, Magnetic and orbital blocking in ni nanocontacts, Physical Review B: Condensed Matter and Materials Physics 71, 10.1103/physrevb.71.220403 (2005).
- [39] W. Dednam, L. A. Zotti, and J. J. Palacios, Computer code ant.gaussian, with soc corrections, Available from https://github.com/juanjosepalacios/ANT. Gaussian, date of access: 21-Jun-2024.
- [40] M. J. Frisch *et al.*, Computer code GAUSSIAN09, Revision C.01, Gaussian, Inc. Wallingford, CT, 2009.
- [41] R. B. Ross, J. M. Powers, T. Atashroo, W. C. Ermler, L. A. LaJohn, and P. A. Christiansen, Erratum: Ab initio relativistic effective potentials with spin-orbit operators. iv. cs through rn [j. chem. phys. 93, 6654 (1990)], The Journal of chemical physics **101**, 10198–10198 (1994).
- [42] J. Laun and T. Bredow, Bsse-corrected consistent gaussian basis sets of triple-zeta valence with polarization quality of the sixth period for solid-state calculations, Journal of computational chemistry 42, 1064–1072 (2021).
- [43] D. Figgen, G. Rauhut, M. Dolg, and H. Stoll, Energyconsistent pseudopotentials for group 11 and 12 atoms: adjustment to multi-configuration dirac-hartree-fock data, Chemical physics **311**, 227–244 (2005).
- [44] J. P. Perdew, K. Burke, and M. Ernzerhof, Generalized gradient approximation made simple, Physical review letters 77, 3865–3868 (1996).

- [45] J. P. Perdew, K. Burke, and M. Ernzerhof, Generalized gradient approximation made simple [phys. rev. lett. 77, 3865 (1996)], Physical review letters 78, 1396–1396 (1997).
- [46] H. Ohnishi, Y. Kondo, and K. Takayanagi, Quantized conductance through individual rows of suspended gold atoms, Nature **395**, 780 (1998).
- [47] R. H. M. Smit, C. Untiedt, G. Rubio-Bollinger, R. C. Segers, and J. M. van Ruitenbeek, Observation of a parity oscillation in the conductance of atomic wires, Phys. Rev. Lett. **91**, 076805 (2003).
- [48] C. Sabater, C. Untiedt, and J. M. van Ruitenbeek, Evidence for non-conservative current-induced forces in the breaking of au and pt atomic chains, Beilstein Journal of Nanotechnology 6, 2338 (2015).
- [49] R. Vardimon, T. Yelin, M. Klionsky, S. Sarkar, A. Biller, L. Kronik, and O. Tal, Probing the orbital origin of conductance oscillations in atomic chains, Nano Letters 14, 2988 (2014), pMID: 24810575, https://doi.org/10.1021/nl4041737.
- [50] A. Yanson, Phd thesis. leiden universitys, https://www.universiteitleiden.nl/en/search website=external, date of access: 2001.
- [51] J. C. Slater, Atomic radii in crystals, The Journal of Chemical Physics 41, https://doi.org/10.1063/1.1725697 (1964).

VI. SUPPLEMENTAL MATERIAL

A. Slope fitting

Fig. 13 shows a conductance trace (red dots) and the linear regression fit for the trace in the range from 12 to 5 G_0 .



Figure 13. The red dots correspond to the gold trace obtained at 300 K in MCBJ, while the blue line represents the linear fit. As shown in the upper part of the plot, the coefficient of determination R^2 is 0.95.

B. Gaussian fitting

To gain further insight into the types of slopes present in our data, we fitted three Gaussians in the upper panel of Figure 11. The mathematical expression for the fitting function is given by:

$$f(x) = \sum_{i=1}^{N} \frac{A_i}{w_i \sqrt{\pi/2}} e^{-\frac{(x-x_{c,i})^2}{2w_i^2}}$$
(1)

where *i* corresponds to the index of the Gaussians. The fitting function is a sum of *N* Gaussians, where each Gaussian is defined by its amplitude A_i , center $x_{c,i}$, and width w_i . A_i controls the area under the curve of the *i*-th Gaussian, $x_{c,i}$ represents the center or mean, and w_i determines the width or standard deviation of the curve. The normalization ensures that the total area under the curve is proportional to A_i , while w_i regulates the spread of the curve.

In this study, the Gaussians were fitted using leastsquares fitting, and Table II shows the parameters obtained from this fitting, which yielded an R^2 value of 0.9907. The high R^2 value indicates that the model accurately fits the experimental data, specifically referring to the fit of the sum of the Gaussians.

Table II. Gaussian parameters for each peak. The first column refers to the peak number, the second column to the amplitude (A_i) , the third column to the center of the Gaussian $(x_{c,i})$, the fourth column to the width (w_i) , and the fifth and sixth columns show the height and the Full Width at Half Maximum (FWHM), respectively.

| Peaks | A_i | $x_{c,i}$ | w_i | FWHM |
|-------|--------|-----------|--------|--------|
| 1 | 0.7340 | 0.5797 | 0.1108 | 0.2609 |
| 2 | 0.4869 | 0.8214 | 0.2151 | 0.5065 |
| 3 | 0.1882 | 1.0590 | 0.3754 | 0.8840 |