Volume dependence of microwave induced excess quasiparticles in superconducting resonators

Steven A. H. de Rooij,^{1,2,*} Jochem J. A. Baselmans,^{1,2} Juan Bueno,²

Vignesh Murugesan,¹ David J. Thoen,¹ and Pieter J. de Visser¹

¹SRON - Netherlands Institute for Space Research,

Niels Bohrweg 4, 2333 CA Leiden, The Netherlands

²Faculty of Electrical Engineering, Mathematics and Computer Science,

Delft University of Technology, Mekelweg 4, 2628 CD Delft, the Netherlands

(Dated: March 11, 2025)

The presence of quasiparticles typically degrades the performance of superconducting microwave circuits. The readout signal can generate non-equilibrium quasiparticles, which lead to excess microwave loss and decoherence. To understand this effect quantitatively, we measure quasiparticle fluctuations and extract the quasiparticle density across different temperatures, readout powers, and resonator volumes. We find that microwave power generates a higher quasiparticle density as the active resonator volume is reduced and show that this effect sets a sensitivity limit on kinetic inductance detectors. We compare our results with theoretical models of direct microwave photon absorption by quasiparticles and conclude that an unknown, indirect mechanism plays a dominant role in quasiparticle generation. These results provide a route to mitigate quasiparticle generation due to readout power in superconducting devices.

Superconducting devices have found numerous applications, ranging from advanced quantum circuits to the most sensitive radiation detectors. Quasiparticles (i.e., broken Cooper pairs) generally degrade the performance of these devices as they introduce microwave loss, decoherence [1] and reduced detector sensitivity [2]. The quasiparticle density exponentially decreases with decreasing bath temperature, but is typically observed to saturate at low temperatures [3, 4]. Multiple sources of quasiparticle generation have been identified and mitigated, including cosmic rays [5, 6], radioactivity [7], and stray light [8].

We focus on the quasiparticle generation by the microwave signal used to read out the superconducting devices [9]. The on-chip power of this readout signal (P_{read}) induces two nonlinear effects. The first is a nonlinear increase of the kinetic inductance when the current becomes a significant fraction of the critical current. This nonlinear inductance is used in parametric amplifiers [10] and tunable resonators [11]. It is an effect of the acceleration of the Cooper pair condensate. The second effect is the absorption of microwave photons by quasiparticles [12, 13], resulting in a redistribution to higher energies [14, 15]. Direct pair-breaking by microwave photons is not possible because their energy $(\hbar\omega_0)$ is usually much smaller than the gap energy (2Δ) . However, when the quasiparticle relaxation rate is small compared to the photon absorption rate, quasiparticles can absorb multiple microwave photons. As a result, redistributed quasiparticles with energies > 3Δ can emit phonons of $> 2\Delta$ to break Cooper pairs. This leads to an excess quasiparticle density at low bath temperatures, and this density increases with P_{read} [9].

Superconducting resonators are particularly sensitive to both these effects, since P_{read} accumulates to an internal power, $P_{int} \propto Q P_{read}$, where Q is the quality factor. This is typically limited by the coupling quality factor, Q_c , which is usually greater than 10^4 . Resonators are widely used in quantum circuits and as ultrasensitive radiation detectors spanning millimetre-wave to visible wavelengths, known as Microwave Kinetic Inductance Detectors (MKIDs) [16]. MKIDs are typically operated at a high P_{int} , just below the bifurcation power, P_{int}^{bif} , to reduce Two Level System (TLS) noise [17]. At P_{int}^{bif} the nonlinear kinetic inductance effect causes hysteresis in the resonance curve [18]. At such high P_{int} , we expect quasiparticle redistribution effects to become important. Another common approach to improve the sensitivity of MKIDs is reducing the absorption volume [19]. However, in Ref. [20] it is observed that decreasing V by a factor 7 does not increase the sensitivity when driving close to P_{int}^{bif} . At the same time, the quasiparticle recombination time is observed to decrease with decreasing volume. This raises the question: how are the excess quasiparticle density, MKID sensitivity, readout power and the resonator volume interrelated?

To answer this question, we measure the quasiparticle density in Al sections of different volumes, which are embedded in a NbTiN microwave resonator, see Fig. 1(a). The NbTiN (normal state resistivity $\rho_N = 158 \ \mu\Omega \text{cm}$, critical temperature $T_c = 14.6 \text{ K}$, thickness d = 110 nm) [22] is sputtered on a c-Sapphire substrate and patterned using a reactive ion etch as a large shunt interdigitated capacitor (IDC) [23] to decrease the impedance of that section. By changing the length of the IDC fingers we set the resonance frequency, $\omega_0/(2\pi)$, between 4.5 and 6.5 GHz. The resonator is capacitively coupled to the transmission line with a coupling bar, which sets Q_c be-

^{*} s.a.h.de.rooij@sron.nl



FIG. 1. Generation-recombination noise measurement on hybrid superconducting resonators. (a) Diagram of one of the resonators studied. The central line of the inductive part is a narrow $(1.7 \ \mu\text{m})$ Al line of various lengths. At the end of the inductive section, a twin-slot antenna is patterned in the NbTiN, which is not used in the measurement. The gaps to the NbTiN ground plane are 2 μ m for the inductive section. The NbTiN shunt capacitive part has a 40 μ m wide central line and 8 μ m wide gaps. We measure the forward transmission and calibrate it to the resonance curve to obtain δA and θ . (b) Energy diagram of the relevant processes regarding quasiparticles (red), Cooper pairs (blue), phonons (green) and microwave photons (orange). By analysing correlations in δA and θ , we extract information about the quasiparticle generation-recombination process. (c) Measured cross power spectral densities for one of the resonators, at different bath temperatures. From a fit (dashed line), we obtain the quasiparticle density and effective lifetime.

tween 30,000 and 100,000 for the resonators studied here. The inductive section is a co-planar waveguide with a sputtered and wet etched Al central line ($\rho_N = 0.7 \ \mu\Omega$ cm, $T_c = 1.18$ K, d = 40 nm), which is shorted at the end to make a quarter wave resonator.

From simulations, we know that more than 95% of the current is in the Al wire and that current uniformity in that wire is more 95%. That makes us only sensitive to the quasiparticles in the Al. Furthermore, the quasiparticles are trapped in the Al volume, because of the larger gap energy of NbTiN, and the microwave photons in the resonator mainly interact with the charge carriers in the Al, because of the larger impedance of the inductive section compared to capacitive section (83 Ω and 20 Ω , respectively) [24, 25]. Therefore, we assume in our analysis that we effectively probe an Al resonator with a volume equal to the Al volume.

We probe the resonator at its resonance frequency with P_{read} , resulting in an internal power [26],

$$P_{int} = \frac{\hbar\omega_0^2}{\pi} \langle n_{ph} \rangle = \frac{2Q^2}{\pi Q_c} P_{read}, \qquad (1)$$

where $\langle n_{ph} \rangle$ represents the average number of photons in

the resonator. $Q = (1/Q_c + 1/Q_i)^{-1}$ the loaded quality factor, with Q_i the internal quality factor. We measure the forward transmission and calibrate it with respect to the resonance circle in the IQ-plane, to obtain the normalized amplitude (δA) and phase (θ) [27]. δA corresponds to changes in the dissipation (i.e. $\delta(1/Q_i)$), induced by the quasiparticles, and θ to changes in the kinetic inductance (i.e. $\delta \omega_0$), induced by Cooper pairs, see Fig. 1(b). We record noise in δA and θ at different bath temperatures and calculate the cross power spectral density, shown in Fig. 1(c) [9]. As we select for correlated changes in δA and θ , we effectively probe the generationrecombination process [9]. This process is characterized by a Lorentzian spectrum [4, 28],

$$S_{\delta A,\theta}(\omega) = \frac{4\left\langle \delta N_{qp}^2 \right\rangle \tau_{qp}^*}{1 + (\omega \tau_{qp}^*)^2} \left[\frac{d\delta A}{dN_{qp}} \frac{d\theta}{dN_{qp}} \right].$$
(2)

Here, N_{qp} is the average number of quasiparticles inside the Al volume and τ_{qp}^* is the effective quasiparticle recombination time. We measure the term inside the brackets, i.e. the amplitude and phase responsivities to changes in quasiparticle number, independently, by sweeping the bath temperature for $T > T_c/5$ and record-



FIG. 2. Results of the noise measurements for (a) the smallest Al volume resonator at various internal signal powers and (b) for various Al volumes when the microwave signal power is close to the bifurcation point. Error bars indicate statistical fit errors (see Fig. 3(c)) and are smaller than the data points for most data points. The insets show the results for the effective quasiparticle lifetime, obtained from the same measurements. The black line in the insets is a fit to $\tau_{qp}^*(T) = \tau_{qp}(T)(1 + \tau_{esc}/\tau_{pb})/2$, with $\tau_{esc} = 0.42 \pm 0.07$ ns as only free fit parameter. The error indicates the spread in fit results for the different resonators. We get τ_{pb} and $\tau_{qp}(T)$ for Al from [21].

ing the change in resonance frequency (ω_0) and internal quality factor (Q_i) [29]. From the same measurement, we obtain the kinetic inductance fraction, α_k [30], which is between 2 and 8% for the devices studied here. With the responsivities known, we fit Eq. (2) to the data to obtain τ_{qp}^* and $\langle \delta N_{qp}^2 \rangle$. An example fit is shown in Fig. 1(c).

The quasiparticle fluctuation variance is given by $\left< \delta N_{qp}^2 \right>^{-1}$ $= 2\bar{R}N_{qp}^2\tau_{qp}^*/V$ [31], where \bar{R} = $2\Delta^2/((k_B T_c)^3 N_0 \bar{\tau}_0)$ is the recombination constant renormalized for phonon trapping (indicated by the bar). Here, k_B is the Boltzmann constant and $N_0 = 1.72 \times 10^4 \ \mu eV^{-1} \mu m^{-3}$ is the single spin density bar). of states at the Fermi level for Al [21]. For Δ , we use the BCS result, $2\Delta = 3.52k_BT_c$. $\bar{\tau}_0 = \tau_0(1 + \tau_{esc}/\tau_{pb})$ is the renormalized electron-phonon time constant, with $\tau_0 = 438$ ns describing the electron-phonon coupling strength and $\tau_{pb} = 0.28$ ns the phonon pair-breaking time in Al [21]. τ_{esc} is the phonon escape time, which we get from a fit to the high temperature data of $\tau_{qp}^* = \tau_{qp}(1 + \tau_{esc}/\tau_{pb})/2$, with $\tau_{qp} = 1/(2Rn_{qp}^T)$, where n_{qp}^{T} is the thermal quasiparticle density (black line in Fig. 2(a)). The fit is shown in the insets of Fig. 2 and results in $\tau_{esc} = 0.42 \pm 0.07$ ns. From an analytical calculation of the phonon transparency of the Al-Sapphire interface [32, 33] we find $\tau_{esc} = 0.40$ ns, which is consistent. Combining these results, we can extract the quasiparticle density, $n_{qp} = N_{qp}/V$ from the measured variance.

The expression we use for the variance has been recently calculated in Ref. [31] and includes the effects of quasiparticle generation by microwave readout power. When phonons dominate the quasiparticle generation, it results in $\langle N_{qp}^2 \rangle = N_{qp}$, because in this regime $\tau_{qp}^* = 1/(2\bar{R}n_{qp})$ [28]. When microwave power dominates, however, an excess quasiparticle density absorbs more microwave power, which results in a higher variance of $2N_{qp}$, and $\tau_{qp}^* = 1/(\bar{R}n_{qp})$.

Fig. 2(a) shows n_{qp} obtained in this way, for one resonator and various P_{int} . At high temperatures n_{qp} is equal to the thermal quasiparticle density, which verifies the method we use to extract n_{qp} . At high P_{int} and low temperatures, n_{qp} saturates at a value that increases with increasing P_{int} . The inset shows the results for τ_{qp}^* from the same fits, which saturates for low temperatures at lower values for higher P_{int} . This aligns with Ref. [9], confirming that the microwave power induces excess quasiparticles.

Fig. 2(b) shows n_{qp} for various Al volumes when P_{int} is close to P_{int}^{bif} , i.e. in the high microwave power regime. We estimate the bifurcation power for the kinetic inductance nonlinearity as,

$$P_{int}^{bif} = 0.64 N_0 \Delta^2 \frac{V\omega_0}{Q\alpha_k^2}.$$
(3)

This expression is derived for a quarter wave resonator with uniform current density [34] We observe from Fig. 2(b) that the excess quasiparticle density is higher and the effective quasiparticle lifetime decreases for the smaller Al volumes. We conclude that the quasiparticle generation by microwave readout power is more effective at small Al volumes.

To quantify this statement, we compare these results to theory. In Ref. [14], the authors numerically study the kinetic equations describing the phonon and quasiparticle distribution functions in a non-equilibrium state [37]. The readout power effects are included via a microwave drive term [12, 13], which is proportional to the quasiparticle-photon coupling constant c_{phot}^{qp} . The authors of Ref. [14] implicitly determine c_{phot}^{qp} by equating the absorbed power by the quasiparticles (P_{abs}^{qp}) to the power lost due to inelastic scattering (both quasiparticlephonon scattering and recombination). They take P_{abs}^{qp} as input parameter in the model. The dissipated power density in a resonator can be calculated as [26]

$$\frac{P_{abs}}{V} = \frac{2Q^2}{Q_i Q_c} \frac{P_{read}}{V} = \frac{\pi P_{int}}{Q_i V}.$$
(4)

If Q_i is dominated by quasiparticle losses (i.e. $Q_i = Q_i^{qp}$), P_{abs}^{qp} is equal to P_{abs} and can be obtained from measurements. The power lost due to inelastic scattering is obtained from the numerical calculations.

This results in two regimes. At high bath temperatures, thermal quasiparticles are redistributed to higher energies due to P_{abs}^{qp} , away from Δ , and Q_i increases ('redistribution regime'). At low bath temperatures, the excess quasiparticles induced by P_{abs}^{qp} dominate and Q_i decreases ('quasiparticle creation regime'). These two regimes are experimentally observed in Ref. [15]. The dependence of ω_0 on P_{int} was also measured there, which was much stronger than expected from the excess quasiparticle density. This was later identified as a nonlinear kinetic inductance effect [38, 39].

Here, we focus on the quasiparticle creation regime. In Fig. 3(a), we show the excess quasiparticle density, $n_{qp}^{ex} = n_{qp} - n_{qp}^{T}$, from Fig. 2(b) as a function of the absorbed power density $(P_{abs}/V, \text{ see Eq. }(4))$.

Ref. [14] predicts an excess quasiparticle density in the quasiparticle creation regime of,

$$n_{qp}^{ex} = \sqrt{\eta_{2\Delta} \frac{\pi P_{int}}{Q_i V} \frac{8(1 + \tau_{esc}/\tau_{pb}) N_0^2 \Delta k_B}{\Sigma_s}}, \qquad (5)$$

where the parameter $\Sigma_s = 3.4 \times 10^{10} \text{ W/m}^3/\text{K}$ for Al, as obtained from numerical calculations [14], describes the power flow density from the quasiparticles to the phonons. If only recombination would be taken into account, i.e. inelastic phonon scattering is disregarded, this would equal $\Sigma_s^{rec} = 2\pi k_B (2N_0 \Delta)^2 R = 2.7 \times 10^{10} \text{ W/m}^3/\text{K}$ [34]. The parameter $\eta_{2\Delta}$ in Eq. (5) is the fraction of the phonons with an energy > 2 Δ , which can be interpreted as a pair-breaking efficiency for the absorbed microwave power in the quasiparticle system. It has been numerically calculated to be 0.6 for Al, when $P_{abs}/V < 2.8 \times 10^{-3} \text{ W/m}^3$ and to logarithmically decrease for higher P_{abs}/V [35]. This results in the black line in Fig. 3(a), for which $\eta_{2\Delta} = 0.20 - 0.013$ in our P_{abs}/V regime. This prediction clearly does not describe the measured quasiparticle density. If we use $\eta_{2\Delta}$ as fit parameter, we obtain the dashed line with $\eta_{2\Delta} = 4 \times 10^{-4}$. This value for $\eta_{2\Delta}$ is comparable to the values found in Ref. [9] (where this parameter is defined as η_{read}). Because this describes the data satisfactory, we conclude that the excess quasiparticle density follows the dependence $n_{qp}^{ex} \propto \sqrt{P_{abs}/V}$.

To check this conclusion, we verify that the quasiparticle lifetime scales as $\tau_{qp}^* \propto 1/n_{qp} \propto \sqrt{P_{abs}/V}$. The inset in Fig. 3(a) shows the measured effective quasiparticle lifetimes at low temperatures (from Fig. 2(b)). The dashed line is given by $1/(\bar{R}n_{qp}^{ex})$, with n_{qp}^{ex} from Eq. (5) with $\eta_{2\Delta} = 4 \times 10^{-4}$. We observe that τ_{qp}^* at low P_{abs}/V is lower than expected from this trend. This could be due to additional quasiparticle relaxation channels, such as recombination in impurities [40] or enhanced recombination due to disorder [41–43]. To account for that, we included a saturation lifetime of 2 ms in the dotted line, which is a typical value for the effective lifetime in Al at low temperatures [41]. The dotted line describes the data well and we are confident that $n_{ap}^{ex} \propto \sqrt{P_{abs}/V}$.

The Noise Equivalent Power (NEP) of MKIDs is ultimately limited by the fluctuations of quasiparticles in the absorber volume [2], NEP_{GR} = $2\Delta\sqrt{n_{qp}V/\tau_{qp}^*}/\eta_{pb}$, with η_{pb} the pair-breaking efficiency of pair-breaking photons [44]. In the quasiparticle creation regime, this is thus limited by the excess quasiparticles generated by the microwave probe. If we assume the internal microwave power to be P_{int}^{bif} (Eq. (3)) and $k_BT \ll (\Delta, \hbar\omega_0)$, we can analytically estimate this to be [34],

$$\operatorname{NEP}_{GR}^{bif} = 0.3 \frac{\eta_{2\Delta}}{\eta_{pb}} \sqrt{\frac{\Delta^3}{\hbar \bar{R}}} \frac{\sqrt{V\omega_0}}{Q\alpha_k}.$$
 (6)

Filling in $\eta_{2\Delta} = 4 \times 10^{-4}, \ \eta_{pb} = 0.37 \ [20, 44]$ and the material and resonator parameters from Ref. [20], we obtain 1.8×10^{-20} W/ $\sqrt{\text{Hz}}$, which is close to the measured value 3.1×10^{-20} W/ $\sqrt{\text{Hz}}$. Moreover, the last factor in Eq. (6) is approximately constant for all resonators in Ref. [20], which is consistent with the observation that the measured NEP is approximately equal for all resonators. This suggests that fluctuations of the microwave induced excess quasiparticles can limit the NEP of small volume MKIDs driven at high readout powers. This limit can be relaxed by decreasing the last factor in Eq. (6) in the MKID design. However, TLS noise will increase by doing this, because that scales with $1/\sqrt{P_{int}}$ [45]. The maximum P_{int} is given by Eq. (3), which results in the reciprocal of the last factor in Eq. (6). Therefore, to improve the NEP, both this



FIG. 3. Excess quasiparticle density due to microwave power compared to kinetic equation calculations. (a) Comparison with the numerical study of Ref.[14] (Eq. (5)). The solid line is Eq. (5) with $\eta_{2\Delta}$ from Ref. [35] for Al. The dashed line is with $\eta_{2\Delta} = 4 \times 10^{-4}$ as a fit parameter. The data points are the low temperature data of Fig. 2(b) using the same colour coding for the device volume and with the error bars given by the standard deviation of the 3 lowest temperature points. The x-axis is P_{abs}/V (see Eq. (4)) with Q_i from measurement. The inset shows the saturated effective quasiparticle lifetime from Fig. 2(b) on the same x-axis as the main panel, compared to the expected effective lifetime from $\tau_{qp}^* = 1/(\bar{R}n_{qp}^{ex})$ with $\eta_{2\Delta} = 4 \times 10^{-4}$ as the dashed line. The dotted line includes an additional relaxation channel with a time constant of 2 ms. (b) Comparison with the analytical description in Ref. [36] (Eq. (9)) without fit parameter. The main difference is that in Ref. [36], the authors use an analytical expression for the quasiparticle-photon coupling constant, allowing P_{int} as parameter, as opposed to P_{abs}^{qp} in Ref. [14]. The data points are the same as in (a), but on a different x-axis. The inset shows the internal quality factor normalized to the quasiparticle density and resonator properties, $\hat{Q}_i = Q_i \alpha_k \hbar \omega_0 n_{qp}^{ex}/(2N_0 \Delta^2)$, on the same x-axis as the main panel. The dots are measured values, including Q_i from a separate measurement and n_{qp}^{ex} from the main panel. The solid line is the prediction for the quasiparticle creation regime and the dashed line for the redistribution regime, both from Ref. [36]. As the measured values are consistently lower, a process different from quasiparticle dissipation is likely to limit Q_i .

factor and TLS noise must be reduced simultaneously.

Our analysis so far has used the method in Ref. [14], which implicitly fixes c_{phot}^{qp} via the variable P_{abs} . From Fig. 3(a), we concluded that the absorbed power by quasiparticles generates excess quasiparticles with an efficiency $\eta_{2\Delta}$, but by what microscopic mechanism is not clear. The authors of Ref. [36] pursued an analytical approach to solving the kinetic equations, preserving the microscopic nature. They explicitly calculate the quasiparticle-photon coupling constant [46] for $\langle n_{ph} \rangle \gg 1$ as the ratio between the photon absorption and the normalized power dissipation in the resonator,

$$c_{phot}^{qp} = \frac{P_{abs}^{qp}}{\pi P_{int}} \frac{\sigma_N / \sigma_1}{2\hbar N_0 V} = \frac{1}{Q_i^{qp}} \frac{\sigma_N / \sigma_1}{2\hbar N_0 V} \approx \frac{\alpha_k \omega_0}{2\pi N_0 V \Delta}, \quad (7)$$

where the last approximation is valid for, $k_B T_{eff} \ll \Delta$, which introduces a maximum error of 7% for our measurements. With c_{phot}^{qp} known explicitly, they derive a temperature $(k_B T_*)^3/(k_B \Delta^2)$, that separates the redistribution from the quasiparticle creation regime when compared to the bath temperature. $k_B T_*$ characterizes the width of the quasiparticle distribution function and is given by,

$$\frac{k_B T_*}{\Delta} = \left(\frac{105\pi}{64} \left(\frac{k_B T_c}{\Delta}\right)^3 \frac{\hbar \tau_0}{\Delta^2} c_{phot}^{qp} P_{int}\right)^{1/6}.$$
 (8)

Assuming $\hbar\omega_0 \ll k_B T_* \lesssim \Delta$ and that the nonequilibrium phonons with energies below 2Δ have little effect on the quasiparticle distribution (both valid for Al at the microwave powers considered here), they come to an explicit expression for the excess quasiparticle number at low temperatures,

1

$$n_{qp}^{ex} = 0.42 \frac{\tau_{esc}}{\tau_{pb}} N_0 \Delta \left(\frac{k_B T_*}{\Delta}\right)^{9/2} \times \exp\left[-\sqrt{\frac{14}{5}} \left(\frac{k_B T_*}{\Delta}\right)^{-3}\right].$$
(9)

They verified this expression with numerical simulations [36]. We compare it to the data in Fig. 3(b), without

fit parameters. The variable on the x-axis combines the resonator-dependent variables in Eqs. (7) and (8).

We observe a much higher excess guasiparticle density at low microwave power densities than predicted by Eq. (9). Such a discrepancy is also observed in Ref. [36], where it is shown that the explicit expression for $Q_i(P_{int})$ in the quasiparticle creation regime does not agree with the measurements of Ref. [15]. This suggests that the excess quasiparticle density at low temperature and readout powers is not solely due to direct microwave photon absorption, but involves an additional mechanism. From Fig. 3(a) we know that such a mechanism should be readout power dependent, with an efficiency of only 4×10^{-4} with respect to the absorbed power.

The authors of Ref. [31] proposed a pair-breaking photon occupation generated by the the microwave signal generator as additional mechanism. We exclude this hypothesis by measuring the attenuation of several microwave components in the setup at frequencies above the gap frequency of the Al, which results in a total attenuation on the order of -300 dB. We also exclude pair-breaking photons radiated from the attenuator closest to the chip, that could be heated by microwave power. See the Supplementary Material for details [34]. To identify possible pair-breaking mechanisms, we show the measured Q_i , normalized to quasiparticle density and resonator properties, in the inset of Fig. 3(b). The solid black line is the prediction of Ref. [36] for Q_i^{qp} in the quasiparticle creation regime. This is much higher than the measured Q_i , which is consistent with the observation in [36]. The dashed line is the prediction for Q_i^{qp} in the redistribution regime [36][34], which applies when the excess quasiparticle density is generated via another mechanism [31][34]. Both these predictions are consistently higher than the measured Q_i , which implies that the Q_i is not limited by quasiparticle (i.e. Q_i^{qp}), but by another dissipation mechanism. This could for example be TLS loss in the inductor, which would locally heat the Al and, indirectly, create quasiparticles. Further study on different quasiparticle generation mechanisms, both theoretical and experimental, is needed to identify such a mechanism.

Apart from this, the kinetic inductance nonlinearity could also play a role. Effects of the condensate are

To conclude, we have shown that microwave readout power generates a higher excess quasiparticle density in resonators with a smaller active volume. The generated quasiparticles limit the sensitivity of MKIDs, which can only be mitigated by simultaneously reducing the TLS noise. A comparison with theoretical predictions showed that these results cannot be explained by direct microwave photon absorption. A complete analytical understanding needs a treatment of the non-equilibrium effects of multiple microwave power absorption channels.

non-equilibrium density of states and redistribution

[47].

effects is still lacking.

ACKNOWLEDGEMENTS

P.J.d.V. acknowledges support by the Netherlands Organisation for Scientific Research NWO (Veni Grant No. 639.041.750 and Projectruimte 680-91-127). J.J.A.B. acknowledges support by the European Research Council ERC (Consolidator Grant No. 648135 MOSAIC).

DATA AVAILABILITY

All data and analysis scripts presented and used in this work are openly available [48].

AUTHOR CONTRIBUTIONS

J.J.A.B. designed the devices, which V.M. and D.J.T. fabricated. J.B. performed the measurements and S.A.H.d.R. analyzed the data and wrote the manuscript. P.J.d.V. and J.J.A.B. supervised the entire process, including reviewing the manuscript.

- [1] L. Glazman and G. Catelani, Bogoliubov quasiparticles in superconducting qubits, SciPost Physics Lecture Notes , 031 (2021).
- [2] P. J. de Visser, J. J. A. Baselmans, P. Diener, S. J. C. Yates, A. Endo, and T. M. Klapwijk, Generation-Recombination Noise: The Fundamental Sensitivity Limit for Kinetic Inductance Detectors, Journal of Low Temperature Physics 167, 335 (2012).
- [3] J. M. Martinis, M. Ansmann, and J. Aumentado, Energy Decay in Superconducting Josephson-Junction Qubits

from Nonequilibrium Quasiparticle Excitations, Physical Review Letters 103, 097002 (2009).

- [4] P. J. de Visser, J. J. A. Baselmans, P. Diener, S. J. C. Yates, A. Endo, and T. M. Klapwijk, Number Fluctuations of Sparse Quasiparticles in a Superconductor, Physical Review Letters 106, 167004 (2011).
- [5] J. M. Martinis, Saving superconducting quantum processors from decay and correlated errors generated by gamma and cosmic rays, npj Quantum Information 7, 1 (2021).

- [6] M. McEwen, L. Faoro, K. Arya, A. Dunsworth, T. Huang, S. Kim, B. Burkett, A. Fowler, F. Arute, J. C. Bardin, A. Bengtsson, A. Bilmes, B. B. Buckley, N. Bushnell, Z. Chen, R. Collins, S. Demura, A. R. Derk, C. Erickson, M. Giustina, S. D. Harrington, S. Hong, E. Jeffrey, J. Kelly, P. V. Klimov, F. Kostritsa, P. Laptev, A. Locharla, X. Mi, K. C. Miao, S. Montazeri, J. Mutus, O. Naaman, M. Neeley, C. Neill, A. Opremcak, C. Quintana, N. Redd, P. Roushan, D. Sank, K. J. Satzinger, V. Shvarts, T. White, Z. J. Yao, P. Yeh, J. Yoo, Y. Chen, V. Smelyanskiy, J. M. Martinis, H. Neven, A. Megrant, L. Ioffe, and R. Barends, Resolving catastrophic error bursts from cosmic rays in large arrays of superconducting qubits, Nature Physics 18, 107 (2022).
- [7] L. Cardani, F. Valenti, N. Casali, G. Catelani, T. Charpentier, M. Clemenza, I. Colantoni, A. Cruciani, G. D'Imperio, L. Gironi, L. Grünhaupt, D. Gusenkova, F. Henriques, M. Lagoin, M. Martinez, G. Pettinari, C. Rusconi, O. Sander, C. Tomei, A. V. Ustinov, M. Weber, W. Wernsdorfer, M. Vignati, S. Pirro, and I. M. Pop, Reducing the impact of radioactivity on quantum circuits in a deep-underground facility, Nature Communications 12, 2733 (2021).
- [8] J. J. A. Baselmans, S. J. C. Yates, P. Diener, and P. J. de Visser, Ultra Low Background Cryogenic Test Facility for Far-Infrared Radiation Detectors, Journal of Low Temperature Physics 167, 360 (2012).
- [9] P. J. de Visser, J. J. A. Baselmans, S. J. C. Yates, P. Diener, A. Endo, and T. M. Klapwijk, Microwave-induced excess quasiparticles in superconducting resonators measured through correlated conductivity fluctuations, Applied Physics Letters 100, 162601 (2012).
- [10] M. Esposito, A. Ranadive, L. Planat, and N. Roch, Perspective on traveling wave microwave parametric amplifiers, Applied Physics Letters 119, 120501 (2021).
- [11] M. R. Vissers, J. Hubmayr, M. Sandberg, S. Chaudhuri, C. Bockstiegel, and J. Gao, Frequency-tunable superconducting resonators via nonlinear kinetic inductance, Applied Physics Letters 107, 062601 (2015).
- [12] G. M. Éliashberg, Inelastic Electron Collisions and Nonequilibrium Stationary States in Superconductors, Soviet Journal of Experimental and Theoretical Physics 34, 668 (1972).
- [13] B. I. Ivlev, S. G. Lisitsyn, and G. M. Eliashberg, Nonequilibrium excitations in superconductors in high-frequency fields, Journal of Low Temperature Physics 10, 449 (1973).
- [14] D. J. Goldie and S. Withington, Non-equilibrium superconductivity in quantum-sensing superconducting resonators, Superconductor Science and Technology 26, 015004 (2013).
- [15] P. J. de Visser, D. J. Goldie, P. Diener, S. Withington, J. J. A. Baselmans, and T. M. Klapwijk, Evidence of a Nonequilibrium Distribution of Quasiparticles in the Microwave Response of a Superconducting Aluminum Resonator, Physical Review Letters **112**, 047004 (2014).
- [16] P. K. Day, H. G. LeDuc, B. A. Mazin, A. Vayonakis, and J. Zmuidzinas, A broadband superconducting detector suitable for use in large arrays, Nature 425, 817 (2003).
- [17] J. Gao, J. Zmuidzinas, B. A. Mazin, H. G. LeDuc, and P. K. Day, Noise properties of superconducting coplanar waveguide microwave resonators, Applied Physics Letters **90**, 102507 (2007).

- [18] L. J. Swenson, P. K. Day, B. H. Eom, H. G. Leduc, N. Llombart, C. M. McKenney, O. Noroozian, and J. Zmuidzinas, Operation of a titanium nitride superconducting microresonator detector in the nonlinear regime, Journal of Applied Physics **113**, 104501 (2013).
- [19] S. Hailey-Dunsheath, R. M. J. Janssen, J. Glenn, C. M. Bradford, J. Perido, J. Redford, and J. Zmuidzinas, Kinetic inductance detectors for the Origins Space Telescope, Journal of Astronomical Telescopes, Instruments, and Systems 7, 011015 (2021).
- [20] J. J. A. Baselmans, F. Facchin, A. P. Laguna, J. Bueno, D. J. Thoen, V. Murugesan, N. Llombart, and P. J. de Visser, Ultra-sensitive THz microwave kinetic inductance detectors for future space telescopes, Astronomy & Astrophysics 665, A17 (2022).
- [21] S. B. Kaplan, C. C. Chi, D. N. Langenberg, J. J. Chang, S. Jafarey, and D. J. Scalapino, Quasiparticle and phonon lifetimes in superconductors, Physical Review B 14, 4854 (1976).
- [22] D. J. Thoen, B. G. C. Bos, E. A. F. Haalebos, T. M. Klapwijk, J. J. A. Baselmans, and A. Endo, Superconducting NbTiN Thin Films With Highly Uniform Properties Over a 100 mm Wafer, IEEE Transactions on Applied Superconductivity 27, 1 (2017).
- [23] O. Noroozian, J. Gao, J. Zmuidzinas, H. G. LeDuc, and B. A. Mazin, Two-level system noise reduction for Microwave Kinetic Inductance Detectors, AIP Conference Proceedings **1185**, 148 (2009).
- [24] A. A. Clerk, K. W. Lehnert, P. Bertet, J. R. Petta, and Y. Nakamura, Hybrid quantum systems with circuit quantum electrodynamics, Nature Physics 16, 257 (2020).
- [25] A. Wallraff, D. I. Schuster, A. Blais, L. Frunzio, R.-S. Huang, J. Majer, S. Kumar, S. M. Girvin, and R. J. Schoelkopf, Strong coupling of a single photon to a superconducting qubit using circuit quantum electrodynamics, Nature 431, 162 (2004).
- [26] J. Gao, The Physics of Superconducting Microwave Resonators, Ph.D. thesis, California Institute of Technology (2008).
- [27] R. Barends, J. J. A. Baselmans, S. J. C. Yates, J. R. Gao, J. N. Hovenier, and T. M. Klapwijk, Quasiparticle Relaxation in Optically Excited High-Q Superconducting Resonators, Physical Review Letters 100, 257002 (2008).
- [28] C. M. Wilson and D. E. Prober, Quasiparticle number fluctuations in superconductors, Physical Review B 69, 094524 (2004).
- [29] P. J. de Visser, Quasiparticle Dynamics in Aluminium Superconducting Microwave Resonators, Ph.D. thesis, Delft University of Technology, Delft (2014).
- [30] J. Gao, J. Zmuidzinas, B. A. Mazin, P. K. Day, and H. G. Leduc, Experimental study of the kinetic inductance fraction of superconducting coplanar waveguide, Nuclear Instruments and Methods in Physics Research Section A: Accelerators, Spectrometers, Detectors and Associated Equipment Proceedings of the 11th International Workshop on Low Temperature Detectors, **559**, 585 (2006).
- [31] P. B. Fischer and G. Catelani, Nonequilibrium quasiparticle distribution in superconducting resonators: Effect of pair-breaking photons, SciPost Physics 17, 070 (2024).
- [32] S. B. Kaplan, Acoustic matching of superconducting films to substrates, Journal of Low Temperature Physics 37, 343 (1979).

- [33] W. Eisenmenger, K. Laßmann, H. J. Trumpp, and R. Krau
 ß, Quasiparticle recombination and 2Δ-phonontrapping in superconducting tunneling junctions, Applied physics 11, 307 (1976).
- [34] See Supplemental Material at [URL] for a derivation of the bifurcation power in resonators, the noise equivalent power due to microwave-induced excess quasiparticles, analytical expressions for the quality factors for redistributed quasiparticles and the attenuation measurement for pair-breaking photons through the setup, including an analysis of radiated pair-breaking at the cold stage. This includes Refs. [49-58].
- [35] T. Guruswamy, D. J. Goldie, and S. Withington, Nonequilibrium superconducting thin films with sub-gap and pair-breaking photon illumination, Superconductor Science and Technology 28, 054002 (2015).
- [36] P. Fischer and G. Catelani, Nonequilibrium Quasiparticle Distribution in Superconducting Resonators: An Analytical Approach, Physical Review Applied **19**, 054087 (2023).
- [37] J.-J. Chang and D. J. Scalapino, Kinetic-equation approach to nonequilibrium superconductivity, Physical Review B 15, 2651 (1977).
- [38] A. V. Semenov, I. A. Devyatov, P. J. de Visser, and T. M. Klapwijk, Coherent Excited States in Superconductors due to a Microwave Field, Physical Review Letters 117, 047002 (2016).
- [39] A. Semenov, I. Devyatov, M. Westig, and T. Klapwijk, Effect of Microwaves on Superconductors for Kinetic Inductance Detection and Parametric Amplification, Physical Review Applied 13, 024079 (2020).
- [40] A. G. Kozorezov, A. A. Golubov, J. K. Wigmore, D. Martin, P. Verhoeve, R. A. Hijmering, and I. Jerjen, Inelastic scattering of quasiparticles in a superconductor with magnetic impurities, Physical Review B 78, 174501 (2008).
- [41] R. Barends, S. van Vliet, J. J. A. Baselmans, S. J. C. Yates, J. R. Gao, and T. M. Klapwijk, Enhancement of quasiparticle recombination in Ta and Al superconductors by implantation of magnetic and nonmagnetic atoms, Physical Review B **79**, 020509(R) (2009).
- [42] S. A. H. de Rooij, J. J. A. Baselmans, V. Murugesan, D. J. Thoen, and P. J. de Visser, Strong reduction of quasiparticle fluctuations in a superconductor due to decoupling of the quasiparticle number and lifetime, Physical Review B 104, L180506 (2021).
- [43] S. A. H. de Rooij, R. Fermin, K. Kouwenhoven, T. Coppens, V. Murugesan, D. J. Thoen, J. Aarts, J. J. A. Baselmans, and P. J. de Visser, Recombination of localized quasiparticles in disordered superconductors (2024), arXiv:2410.18802.
- [44] T. Guruswamy, D. J. Goldie, and S. Withington, Quasiparticle generation efficiency in superconducting thin films, Superconductor Science and Technology 27, 055012 (2014).
- [45] J. Gao, M. Daal, J. M. Martinis, A. Vayonakis, J. Zmuidzinas, B. Sadoulet, B. A. Mazin, P. K. Day, and H. G. Leduc, A semiempirical model for two-level system noise in superconducting microresonators, Applied Physics Letters 92, 212504 (2008).
- [46] G. Catelani and D. M. Basko, Non-equilibrium quasiparticles in superconducting circuits: Photons vs. phonons, SciPost Physics 6, 013 (2019).

- [47] T. M. Klapwijk and P. J. de Visser, The discovery, disappearance and re-emergence of radiation-stimulated superconductivity, Annals of Physics , 168104 (2020).
- $[48] \ 10.5281/zenodo.14999891.$
- [49] J. Zmuidzinas, Superconducting Microresonators: Physics and Applications, Annual Review of Condensed Matter Physics 3, 169 (2012).
- [50] D. C. Mattis and J. Bardeen, Theory of the Anomalous Skin Effect in Normal and Superconducting Metals, Physical Review 111, 412 (1958).
- [51] A. Anthore, H. Pothier, and D. Esteve, Density of States in a Superconductor Carrying a Supercurrent, Physical Review Letters 90, 127001 (2003).
- [52] J. R. Clem and V. G. Kogan, Kinetic impedance and depairing in thin and narrow superconducting films, Physical Review B 86, 174521 (2012).
- [53] J. R. Clem and K. K. Berggren, Geometry-dependent critical currents in superconducting nanocircuits, Physical Review B 84, 174510 (2011).
- [54] A. D. Semenov, M. Sidorova, M. A. Skvortsov, A. Kuzmin, K. Ilin, and M. Siegel, Local thermal fluctuations in current-carrying superconducting nanowires, Physical Review B 102, 184508 (2020).
- [55] Ref. [38] omitted a factor α_k as pointed out by Ref. [31]. However, an additional factor 0.16 is omitted in the derivation of P_0 in Ref. [38]. Since the resonator studied there have a α_k close to 0.16, these errors approximately cancel. Eq. (S.7) is consistent with Ref. [38], when these two errors are taken into account and considering that P_0 in Ref. [38] can also be expressed as $P_0 = 2N_0V\Delta^2\omega_0/\alpha_k$ for a distributed, half-wave resonator.
- [56] P. J. de Visser, J. J. A. Baselmans, J. Bueno, N. Llombart, and T. M. Klapwijk, Fluctuations in the electron system of a superconductor exposed to a photon flux, Nature Communications 5, 3130 (2014).
- [57] F. P. Milliken, J. R. Rozen, G. A. Keefe, and R. H. Koch, $50\,\Omega$ characteristic impedance low-pass metal powder filters, Review of Scientific Instruments **78**, 024701 (2007).
- [58] E8257D PSG Microwave Analog Signal Generator.
- [59] H. Nyquist, Thermal Agitation of Electric Charge in Conductors, Physical Review 32, 110 (1928).

Supplemental Material for: 'Volume dependence of microwave induced excess quasiparticles in superconducting resonators'

Steven A. H. de Rooij,^{1,2,*} Jochem J. A. Baselmans,^{1,2} Juan Bueno,² Vignesh

Murugesan,¹ David J. Thoen,¹ Pieter J. de Visser,¹ Steven A. H. de Rooij,^{1, 2, *} Jochem

J. A. Baselmans,^{1,2} Vignesh Murugesan,¹ David J. Thoen,¹ and Pieter J. de Visser¹

¹SRON - Netherlands Institute for Space Research,

Niels Bohrweg 4, 2333 CA Leiden, The Netherlands

²Faculty of Electrical Engineering, Mathematics and Computer Science,

Delft University of Technology, Mekelweg 4, 2628 CD Delft, the Netherlands

(Dated: March 11, 2025)

1. BIFURCATION POWER ESTIMATION

When a superconducting microwave resonator is driven above a certain power, the transmission curve becomes hysteretic [18, 49]. A resonator in this state is called to be bifurcated and the internal power at which this start to happen we call the bifurcation power or P_{int}^{bif} .

This behaviour can be modelled as a classical Duffing oscillator, with a nonlinearity parameter a that describes the resonance frequency shift in number of line widths when driving at resonance. For $a > 4\sqrt{3}/9 = 0.77$ the resonance is bifurcated [18, 49].

For the kinetic inductance nonlinearity, a depends on the ratio of the current density in the resonator over the critical current density in the superconductor: j_0/j_c where j_0 is the maximum current density in one cycle. We will first find j_0 as a function of internal microwave power, P_{int} .

The internal power is given by [26],

$$P_{int} = \frac{\omega_0 E_{res}}{4\pi m} = \frac{1}{2\pi m} \frac{Q^2}{Q_c} P_{read},\tag{S.1}$$

with m = 1/4 for a quarter-wave resonator (and lumped-element resonator) and m = 1/2 for a half-wave. ω_0 is the angular resonance frequency, $Q = (1/Q_c + 1/Q_i)^{-1}$ is the loaded quality factor with Q_c the coupling quality factor and Q_i the internal quality factor. E_{res} is the energy stored in the resonator, which can be expressed as,

$$E_{res} = \langle n_{ph} \rangle \hbar \omega_0 = \frac{1}{2} L I_0^2, \qquad (S.2)$$

with $\langle n_{ph} \rangle$ the average number of photons in the resonator, \hbar the reduced Planck constant, L the total inductance and I_0 the maximum current in the inductor over one cycle. In this equation, we assumed the current to be constant over the inductor wire and that all inductive energy in the resonator can be described by a single lumped element inductor with inductance L. This is a reasonable assumption for devices studied here, as 95% of the current in the resonator is in the Al section and the current uniformity is > 95% there. If we would consider a completely distributed resonator, i.e. a transmission line of finite length, there would be an additional factor 1/2 in Eq. (S.2). For now, we consider a quarter-wave resonator and set m = 1/4.

Combining Eqs. (S.1) and (S.2), we see,

$$j_0 = \sqrt{\frac{2\pi P_{int}}{L\omega_0 (dw)^2}},\tag{S.3}$$

where $j_0 = I_0/(dw)$ is the current density, d is the wire thickness and w is the wire width. The total inductance can be calculated via,

$$L = \frac{L_k}{\alpha_k} = \frac{L_{k,s}}{\alpha_k} \frac{l}{w},\tag{S.4}$$

^{*} s.a.h.de.rooij@sron.nl



FIG. S1. Verification of Eq. (S.9) with the resonators of the main text. P_{read}^{bif} is measured by visually checking the transmission curves at T = 100 mK with 4 dB steps in read power, which is indicated by the error bars. The black line is Eq. (S.9) without fit parameters, with Q_c and Q from a Lorentzian fit to the same transmission curves. α_k is obtained from transmission curves at higher bath temperatures [30].

with l the wire length, α_k the kinetic inductance fraction, L_k the total kinetic inductance and $L_{k,s}$ the sheet kinetic inductance. In the thin film, local limit we have $L_{k,s} = 1/(d\sigma_2\omega_0)$ [26] and at low temperatures, $k_BT \ll \Delta$, the imaginary part of the complex conductivity equals, $\sigma_2 = \pi \Delta/(\hbar\omega_0\rho_N)$ [50], with ρ_N the normal state resistivity. Putting this together, we find,

$$j_0 = \sqrt{\frac{4\pi^2}{\rho_N} \frac{\Delta}{\hbar\omega_0} \frac{\alpha_k P_{int}}{V}}.$$
(S.5)

The critical current density is given by [51, 52] [34],

$$j_c = 0.59 \sqrt{\frac{\pi \Delta^3 N_0}{\hbar \rho_N}} = 0.59 j_*, \tag{S.6}$$

where j_* is defined as the square-root term by convention. Because we assume that the current density is uniform over the wire, this critical current is given by the depairing current. If the wire would not be straight, but would have constrictions, sharp turns, or would be wider than the penetration depth, the critical current would be reduced [52, 53].

To first order, the kinetic inductance changes with (uniform) current as, $L_k(j) = L_k(0)(1 + 0.069(j/j_c)^2)$ [38, 54] under AC field, which coincides with the DC case when we take $j_{rms} = j_0/\sqrt{2} \rightarrow j_{DC}$ [51, 54]. This results in a fractional frequency shift compared to the zero current case [55],

$$\frac{\delta\omega}{\omega_0}\Big|_{L_k} = -\frac{\alpha_k}{2} \frac{\delta L_k}{L_k(0)} = -0.035\alpha_k \left(\frac{j_0}{j_c}\right)^2 = -1.2 \frac{\alpha_k^2 P_{int}}{N_0 V \Delta^2 \omega_0}.$$
(S.7)

Finally, bifurcation occurs when $\delta\omega/\omega_0 = -0.77/Q$ [18, 49], which results in

$$P_{int}^{bif} = 0.64 N_0 \Delta^2 \frac{V\omega_0}{\alpha_k^2 Q},\tag{S.8}$$

and for the microwave power on the read out line (see Eq. (S.1)),

$$P_{read}^{bif} = N_0 \Delta^2 \frac{V \omega_0 Q_c}{\alpha_k^2 Q^3}.$$
(S.9)

This equation agrees closely with the resonator data from the main text, see Fig. S1.

A. Quasiparticle non-linearity

Apart from the kinetic inductance non-linearity discussed above, the quasiparticle redistribution effects of read power also introduce a non-linearity in resonance frequency [14, 31, 36]. We can estimate this via the excess quasiparticle density, as $\delta\omega/\omega_0 = -\alpha_k n_{qp}^{ex}/(4N_0\Delta)$. The corrections for the reduced gap energy and quasiparticle distribution shape for this expression are of order unity [31]; approximately a factor 1.7 for the powers close to bifurcation in the resonators considered here.

We can take n_{qp}^{ex} from Eq. (5) from the main text, if we know Q_i and Σ_s in terms of superconductor and resonator properties. We can approximate,

$$Q_i^{qp} = \frac{\sigma_2}{\alpha_k \sigma_1} \approx \frac{2\pi N_0 \Delta}{\alpha_k n_{qp}} \sqrt{\frac{\hbar \omega_0}{2\Delta}},\tag{S.10}$$

which holds for $k_B T \ll (\Delta, \hbar \omega_0)$ [50].

If we assume that for Σ_s the power flow from quasiparticle to phonon system is via recombination only, we can equate,

$$\frac{P_{abs}}{V} = \frac{\Delta n_{qp}}{\eta_{2\Delta}\tau_{qp}^*} = \frac{\sum_s^{rec}\tau_0 (k_B T_c)^3}{16\pi\eta_{2\Delta}N_0 \Delta^3 k_B} \frac{n_{qp}}{\tau_{qp}^*},\tag{S.11}$$

where the last expression is from Ref. [14]. $\eta_{2\Delta}$ is the faction of pair-breaking phonons in the non-equilibrium phonon distribution function [14]. Solving for Σ_s^{rec} gives,

$$\Sigma_s^{rec} = 2\pi k_B (2N_0 \Delta)^2 R,\tag{S.12}$$

where $R = 2\Delta^2/((k_B T_c)^3 N_0 \tau_0)$. For Al, this results in $2.7 \times 10^{10} \text{ W/m}^3/\text{K}$, which is close to the value of $3.4 \times 10^{10} \text{ W/m}^3/\text{K}$ from numerical calculations [14]. Combining the analytical expression for Σ_s^{rec} , Q_i^{qp} and Eq. (5) results in,

$$n_{qp}^{ex} = \frac{\alpha_k P_{int}}{2N_0 \Delta V} \sqrt{\frac{2\Delta}{\hbar\omega_0}} \frac{\eta_{2\Delta}}{\pi \Delta \bar{R}}.$$
(S.13)

Here, $R = R/(1 + \tau_{esc}/\tau_{pb})$, with τ_{esc} the phonon escape time, τ_{pb} the phonon pair-breaking time and τ_0 the electronphonon characteristic interaction time.

Combining these expressions results in a resonance frequency shift due to the quasiparticle nonlinearity,

$$\frac{\delta\omega}{\omega_0}\Big|_{ap} = -\frac{\alpha_k^2 P_{int}}{N_0 V \Delta^2} \frac{\eta_{2\Delta}}{8\pi \bar{R} N_0 \Delta} \sqrt{\frac{2\Delta}{\hbar\omega_0}}.$$
(S.14)

From Eqs. (S.7) and (S.14) we thus find the ratio of the frequency shift due to kinetic inductance effects and quasiparticle redistribution effects to be,

$$\frac{\delta\omega|_{L_k}}{\delta\omega|_{qp}} = 21 \frac{\bar{R}N_0}{\eta_{2\Delta}} \sqrt{\frac{\bar{\hbar}\Delta}{\omega_0}}.$$
(S.15)

When filling in $\eta_{2\Delta} = 4 \times 10^{-4}$, the measured Al properties, $\tau_{esc} = 0.35$ ns and the resonance frequencies from the main text, we obtain 5.1 - 6.1 for this ratio. This implies the two nonlinear effects are of the same order of magnitude and the measured bifurcation is caused by the kinetic inductance nonlinearity that is described by Eqs. (S.8) and (S.9). In Eq. (S.10), we also assumed a thermal quasiparticle distribution, which seems to be the case in our measurement, as we verified in the main text. However, the quasiparticle distribution is generally not thermal when microwave photon absorption is considered [14, 36, 56]. The non-thermal distribution increases Q_i , which favours the kinetic inductance nonlinearity. See Section 3 for a quantitative description of this effect.

2. NEP LIMITED BY MICROWAVE INDUCED EXCESS QUASIPARTICLES

We can estimate the NEP from quasiparticle fluctuations as [2]

$$\operatorname{NEP}_{\mathrm{GR}} = \frac{2\Delta}{\eta_{pb}} \sqrt{\frac{n_{qp}V}{\tau_{qp}^*}} = \frac{2\Delta}{\eta_{pb}} n_{qp} \sqrt{\bar{R}V}, \qquad (S.16)$$

where we used that, in the quasiparticle creation regime, the effective quasiparticle lifetime is given by, $\tau_{qp}^* = 1/(\bar{R}n_{qp})$ [31]. If we use Eq. (S.13), i.e. assume $k_B T \ll (\Delta, \hbar\omega_0)$, and assume P_{int}^{bif} from Eq. (S.8) for P_{int} , we arrive at

$$\mathrm{NEP}_{\mathrm{GR}}^{bif} = 0.29 \frac{\eta_{2\Delta}}{\eta_{pb}} \sqrt{\frac{\Delta^3}{\hbar \bar{R}}} \frac{\sqrt{V\omega_0}}{\alpha_k Q}.$$
(S.17)

3. Q_i WHEN QUASIPARTICLES ARE REDISTRIBUTED

Eq. (62) from [36] gives for the redistributed quasiparticle Q_i in the quasiparticle creation regime,

$$Q_i^{qp,red.}\Big|_{crea} = \frac{19.3}{\alpha_k} \frac{\Delta}{\hbar\omega_0} \frac{\tau_{pb}}{\tau_{esc}} \left(\frac{\Delta}{k_B T_*}\right)^3 e^{\sqrt{14/5}(\Delta/k_B T_*)^3} = \frac{91.9}{\alpha_k} \frac{\Delta}{\hbar\omega_0} \frac{2N_0 \Delta}{n_{qp}^{ex}} \left(\frac{k_B T_*}{\Delta}\right)^{3/2},\tag{S.18}$$

where we used Eq. (9) from the main text in the last equality. In the redistribution regime, Q_i is predicted to follow Eq. (63) of [36],

$$Q_i^{qp,red.}\Big|_{red.} = \frac{4.1}{\alpha_k} \frac{\Delta}{\hbar\omega_0} \frac{2N_0\Delta}{n_{qp}} \left(\frac{k_B T_*}{\Delta}\right)^{3/2}.$$
(S.19)

This equation should also hold when n_{qp} is non-thermal due to another pair-breaking process, when setting $n_{qp} \rightarrow n_{qp}^{ex}$ [31].

4. PAIR BREAKING PHOTON ATTENUATION

From Fig. 3(b), we concluded that the measured excess quasiparticle density cannot be explained by direct microwave photon absorption by quasiparticles only. This is a similar conclusion as the authors of Ref. [36] when comparing their explicit expression for $Q_i(P_{int})$ with the data from Ref. [15]. There must be an additional quasiparticle generation effect.

Since we observe that the excess quasiparticle density increases with increasing read power (Fig. S4(a)), as is observed in Ref. [15], this additional generation mechanism must increase with increasing read power. In Ref. [31], the authors propose a *pair-breaking* photon occupation number that is read power dependent as this additional generation mechanism. They show that they can fit the data of Ref. [15] when they assume a pair-breaking photon occupation in the resonator, that is a factor 10^{-9} of the microwave photon occupation, i.e. -90 dBc.

The origin of these pair-breaking photons is not clear. Two possible sources are higher harmonics of the signal generator, also mentioned in [31], and heating of the 10 dB attenuator on the 100 mK stage (see Fig. S2). We show in this section that these hypotheses cannot explain the measured quasiparticle densities.

To estimate the effect of high harmonics generated by the signal generator, we measured the attenuation of pairbreaking radiation by several components in our setup, see Fig. S2. We used a Keysight-Agilent N5242A microwave network analyser and two Anritsu 3740A-EW modules for frequency up-conversion to the 75-110 GHz band, with adapters to go from WR-10 to SMA. We calibrated the setup with a THRU calibration, including adapters, and measured each component in Fig. S2 individually. The combined results of these measurements are presented in Fig. S3. The main contributions to the attenuation are the variable attenuator at 300 K and the custom made lowpass powder filter [8] at 100 mK. We measured an attenuation of -70 dB at most frequencies for these components, which is the noise floor of the setup. The actual attenuation is therefore likely to be higher.

On the other hand, the measured shown in Fig. S3 are performed at room temperature, while the components in the setup are cooled to the temperature specified in Fig. S2. We therefore disregard the losses in the superconducting NbTi wires. For the copper wire, we divide the attenuation (in dB) by the residual resistance ratio (RRR), which we



FIG. S2. Diagram showing the measured components in the microwave chain from signal generator to chip.



FIG. S3. Measured forward transmission of the total combined microwave chain (black) and the components of the various temperature stages, indicated by the colours. The gap frequency of the Al is indicted by the black dashed line.

assume to be 40. By doing this, we disregard losses in the dielectric of the coax cables, which might be significant at these frequencies. These corrections therefore lead to a conservative estimate of the attenuation in the wires. The attenuation of the low-pass filter is induced primarily by eddy currents in the metal powder dielectric, which is a bronze-Stycast mixture [8]. This attenuation has only a weak temperature dependence [57]. To account for this, we assume a RRR of bronze of 3 and divide the measured attenuation by the square root of that, as the skin depth in the metal grains scales with the square root of the resistance. These corrections are included in Fig. S3.

The signal generator is specified to generate less than -55 dBc in higher harmonics [58]. The average measured attenuation in the setup is -117 dBc \pm 10 dB, see Fig. S3. The pair-breaking photon occupation at the chip is thus at maximum -162 dBc. This is much lower than the required -90 dBc [31] to explain the data from Ref. [15].

For the measurement presented in the main text, we estimate the excess quasiparticle density generated by this pair-breaking photon occupation via [31],

$$n_{qp}^{ex} = 2N_0 \Delta \sqrt{\frac{\pi}{4}} \langle n_{pb} \rangle c_{phot,pb}^{qp} \tau_0 \frac{\xi}{\Delta} \left(\frac{k_B T_c}{\Delta}\right)^3.$$
(S.20)



FIG. S4. Estimation for excess quasiparticle density due to read out power heating of the 10 dB attenuator at 100 mK. (a): The measured excess quasiparticle density from Fig. 3, with the used on-chip read power on the x-axis. This shows that the quasiparticle density does increase with increasing read power. (b): Estimation of the excess quasiparticle density from Eq. (S.20) [31], when assuming a heated temperature for the 10 dB attenuator given by the x-axis. Different colours indicate the different resonators, like in Figs. S1 and 2. The coloured areas are the measured values from (a). Since these are much larger than the predicted values (dashed lines), we conclude that this effect is too small to explain the measured excess quasiparticle densities.

 $c_{phot,pb}^{qp} = \alpha_k \hbar \omega_{pb}^2 / (2\pi N_0 \Delta^2 V)$ [31] is the quasiparticle-photon coupling constant for pair-breaking photons with energy $\hbar \omega_{pb}$. $\langle n_{pb} \rangle$ is the pair-breaking photon occupation and $\xi = 2\Delta - \hbar \omega_{pb}$. If we take for $\langle n_{pb} \rangle = \chi P_{read} / (\hbar \omega_{pb}^2)$, with $\chi = 10^{-16.2}$, or -162 dB, the on-chip ratio of readout power and pair-breaking photons and $\hbar \omega_{pb} = 2.8\Delta$ [31], we come to $n_{qp}^{ex} \approx 10^{-3} \ \mu m^{-3}$. This is 5 orders of magnitude lower than measured at these read powers, see Fig. S4(a). We therefore exclude the signal generator as pair-breaking photon

source. Another possible source pair-breaking photons is radiation coming from the 10 dB attenuator at the 100 mK stage, see Fig. S2. We consider this the only relevant component for heating effects, since the read power must significantly

heat the component to obtain the read power dependence of n_{qp}^{ex} (Fig. S4(a)). We estimate the on-chip pair-breaking power coming from the 10 dB attenuator as 1D black-body radiation (i.e. Johnson-Nyquist noise [59]) that is attenuated by the low-pass powder filter,

$$P_{chip} = \int_{2\Delta/h}^{\infty} \left[\frac{hf}{e^{hf/k_B T_{att.}} - 1} + \frac{hf}{2} \right] e^{-f/f_c} df,$$
(S.21)

where $h = 2\pi\hbar$ is the Planck constant, $T_{att.}$ is the temperature of the 10 dB attenuator and $f_c = 10$ GHz is the cut-off frequency of the filter [8]. This filter shape has been confirmed up to 10 GHz. At 80 GHz this would be a attenuation of -45 dB, where we measured it to be at least -70 dB. Thus, the filter attenuates more at higher frequencies than we assume here.

We calculate the average photon energy as,

$$\langle E_{ph} \rangle = P_{chip} \bigg/ \int_{2\Delta/h}^{\infty} \bigg[\frac{1}{e^{hf/k_B T} - 1} + \frac{1}{2} \bigg] e^{-f/f_c} df , \qquad (S.22)$$

which results in $\xi = 0.22$. Using $\langle n_{pb} \rangle = h P_{chip} / \langle E_{ph} \rangle^2$ in Eq. (S.20), we obtain the dashed lines in Fig. S4(b). The different lines correspond to the different resonators. We deem it extremely unlikely that the attenuator at 100 mK is heated to 50 K or more, since it has a stainless steel body that is connect directly to the cryostat 100 mK stage. Moreover, we here did not consider the coupling of pair-breaking photon from transmission line to the Al section of

the resonator. That would give an additional attenuation of -32 dB, as estimated from a simulation of the resonator in SONNET. When taking this coupling into account, the dashed lines in Fig. S4(b) shift more than an order of magnitude downwards. We therefore conclude that also this mechanism is not the cause of the measured excess quasiparticle density.