arXiv:2504.01592v1 [quant-ph] 2 Apr 2025

Sub-second spin and lifetime-limited optical coherences in ¹⁷¹Yb³⁺:CaWO₄

Alexey Tiranov,^{1, *} Emanuel Green,² Sophie Hermans,² Erin Liu,² Federico Chiossi,¹ Diana Serrano,¹

Pascal Loiseau,¹ Achuthan Manoj Kumar,³ Sylvain Bertaina,³ Andrei Faraon,² and Philippe Goldner¹

¹Chimie ParisTech, PSL University, CNRS, Institut de Recherche de Chimie Paris, 75005 Paris, France

² Thomas J. Watson, Sr., Laboratory of Applied Physics, California Institute of Technology, Pasadena, CA, 91125, USA

³CNRS, Aix Marseille Univ, Université de Toulon, Institut Matériaux

Microélectronique et Nanosciences de Provence, IM2NP, 13013 Marseille, France

(Dated: April 3, 2025)

Optically addressable solid-state spins have been extensively studied for quantum technologies, offering unique advantages for quantum computing, communication, and sensing [1–3]. Advancing these applications is generally limited by finding materials that simultaneously provide lifetime-limited optical and long spin coherences. Here, we introduce 171 Yb³⁺ ions doped into a CaWO₄ crystal. We perform high-resolution spectroscopy of the excited state, and demonstrate all-optical coherent control of the electron-nuclear spin ensemble. We find narrow inhomogeneous broadening of the optical transitions of 185 MHz and radiative-lifetime-limited coherence time up to 0.75 ms. Next to this, we measure a spin-transition ensemble line width of 5 kHz and electron-nuclear spin coherence time reaching 0.15 seconds at zero magnetic field between 50 mK and 1 K temperatures. These results demonstrate the potential of 171 Yb³⁺:CaWO₄ as a low-noise platform for building quantum technologies with ensemble-based memories [4], microwave-to-optical transducers [5, 6], and optically addressable single-ion spin qubits [7, 8].

Solid-state optically addressable spins have been used to demonstrate a variety of applications including quantum state storage [9, 10], spin-spin entanglement [11], control of nuclear spin clusters [12], and quantum sensing [13]. Among the most popular platforms are optically active defects in diamond [14], semiconductor quantum dots [15], vacancies in silicon [16], silicon carbide [17] and hexagonal boron nitride [18]. Despite significant progress, the search for defects in a solid-state material simultaneously exhibiting lifetime-limited optical and long spin coherences remains ongoing.

Rare-earth ion based defects are particularly attractive due to their unique electronic configuration, leading to narrow optical transitions and long coherence times in many different crystalline host materials [19–25]. Ensembles of such defects have been used for quantum memories [4]. Single emitters coupled to integrated nanophotonic cavities [7, 8, 26–29] are actively explored as they enable single-shot spin readout [30–32], addressing of nearby nuclear spins [33–35], spin-photon entanglement [36], and entanglement between remote ions [37].

CaWO₄ has recently drawn a lot of attention as an appealing host material because of its low magnetic impurity background compared to conventional yttriumcontaining hosts. The remaining magnetic background is dominated by the ¹⁸³W isotope (low natural abundance of 14.3%) and paramagnetic impurities such as iron and other rare-earth ions [38]. The non-polar defect site symmetry yields a first-order insensitivity to electric fields. These material properties combined have enabled the demonstration of spin coherence times up to 23 ms for small ensembles (<1 ppb) in $\text{Er}^{3+}:\text{CaWO}_4$ [24] as well as two-photon interference and spin-photon entanglement using a single Er^{3+} ion in CaWO₄ coupled to a heterogeneous photonic crystal cavity [36].

Here, we explore a novel material dopant combination, CaWO₄ doped with $^{171}{\rm Yb^{3+}},$ and demonstrate exceptional optical and spin properties, even at substantial doping concentration. Among the trivalent rare-earth species, ¹⁷¹Yb³⁺ is the only paramagnetic isotope to possess a nuclear spin of I = 1/2. The hybrid electronnuclear spin states can be used as highly-coherent states, while a low I ensures simple spin manipulation. Using high-resolution optical spectroscopy we extract the so-far unknown excited state Hamiltonian parameters of 171 Yb³⁺ in CaWO₄. Having complete knowledge of the energy levels and the optical transitions allows us to realize efficient all-optical spin initialization and control. In ensembles, we demonstrate optical coherence times reaching 0.75 ms, nearly limited by radiative decay, and realize all-optical spin control with spin coherence times up to 0.15 s. Coherence properties are achieved at zero magnetic field and with temperatures up to a few K. These results make ¹⁷¹Yb³⁺:CaWO₄ a promising material to interface with other quantum technologies, including superconducting and nanophotonic quantum devices.

High-resolution spectroscopy of the ground and excited level structure. A CaWO₄ crystal doped with ¹⁷¹Yb³⁺ ions was grown using the Czochralski method with a nominal concentration of 20 ppm [39]. In this work, we study the tetragonal S_4 site in which the Yb³⁺ replaces a Ca²⁺. This dopant's optical transition connecting ²F_{7/2}(0) \rightarrow ²F_{5/2}(0) is centered around 973.16 nm (vac.) [39]. The concentration of ions in the S_4 site was measured to be \approx 5 ppm using electron paramagnetic resonance, with an isotopic purity of 96%. The high-resolution optical absorption spectrum at 4 K

^{*} Email to: alexey.tiranov@chimieparistech.psl.eu



FIG. 1. (color online) Energy level diagram and magnetic field dependence of ¹⁷¹Yb³⁺:CaWO₄. (a) Lowfield energy level diagram for the ${}^{2}F_{7/2}(0) \rightarrow {}^{2}F_{5/2}(0)$ transition of ¹⁷¹Yb³⁺:CaWO₄ at 973.1 nm. Energy splittings in the ground and excited state are determined using the ground state and extracted excited-state hyperfine tensors. The transitions corresponding to the observed absorption spectrum in (b) are shown with solid lines. (b) High-resolution absorption spectra of ¹⁷¹Yb³⁺:CaWO₄ at 4 K for light electric field polarized along the c axis $(E \parallel c)$ or perpendicular $(E \perp c)$ to the c axis. The labeling of the absorption peaks corresponds to the energy level diagram (a). Absorption peak C corresponds to Yb^{3+} isotopes with zero nuclear spin. Absorption peak D only appears for $E \perp c$. (c) Absorption spectra of ¹⁷¹Yb³⁺:CaWO₄ for varying magnetic field strengths applied perpendicular to the crystalline c-axis. The polarization of the incident light is $E \perp c$. Dashed lines show the results of the fit to the model given by Equation 1. Purple lines denote energy levels of the 171 Yb³⁺ ions and blue lines denote energy levels of the I = 0 isotopes. (d) CaWO₄ crystal structure, with a 171 Yb ${}^{3+}$ dopant replacing a Ca ${}^{2+}$ ion at a site of S_4 point symmetry.

showed a series of narrow peaks spanning several GHz (FIG. 1(b)). The narrow optical inhomogeneous broadening of 185 MHz indicates the high quality of the material and low distortion of the crystalline site induced by dopant ions. This allows us to optically address each ground state level separately (FIG. 1(b)).

 $^{171}{\rm Yb^{3+}}$ carries an electron spin S=1/2 and nuclear spin I=1/2, and both its ground and excited states spin levels can be described using the effective Hamiltonian

$$\mathcal{H}^{g/e} = \mathbf{I} \cdot \mathbf{A}^{g/e} \cdot \mathbf{S} + \mu_{\rm B} \mathbf{B} \cdot \mathbf{g}^{g/e} \cdot \mathbf{S} - \mu_{\rm n} \mathbf{B} \cdot \mathbf{g}_{\rm n} \cdot \mathbf{I}, \quad (1)$$

where $\mathbf{g}^{g/e}$, \mathbf{g}_n and $\mathbf{A}^{g/e}$ are the coupling tensors of the electronic Zeeman, nuclear Zeeman, and hyperfine interactions, respectively, and μ_B and μ_n are the electronic and nuclear spin magnetons. The superscript indicates the ground or excited state manifold. The S_4 point symmetry of the tetragonal occupation site significantly simplifies the spin interaction, giving a symmetry axis parallel to the *c*-axis of the crystal. As a result, the uniaxial interaction tensors consist of one parallel and two identical perpendicular components $A_{\parallel}^{g/e}$, $A_{\perp}^{g/e}$ and $g_{\parallel}^{g/e}$, $g_{\perp}^{g/e}$, for the \mathbf{A} and \mathbf{g} tensors, respectively. The nuclear Zeeman interaction \mathbf{g}_n tensor is considered to be isotropic with $g_n = 0.987$ for 171 Yb³⁺ nuclear spin.

We identified the energy level diagram for the ${}^{2}F_{7/2}(0)$ and ${}^{2}F_{5/2}(0)$ levels using the high-resolution optical spectroscopy with different polarisations of the incident light (FIG. 1). We extract the hyperfine tensors in the ground [40] and excited states: $A^g_{\parallel}/h = -0.789$ GHz, $A^g_{\perp}/h =$ -3.0819 GHz and $A_{\parallel}^{e}/h = -2.87$ GHz, $A_{\perp}^{e}/h = -2.72$ GHz. To complete the optical spectroscopy, we determine the excited state g^e -tensor by fitting the magnetic field dependence of the energy levels to the model given by Eq. (1). We sweep the magnetic field by varying the current through a set of Helmholtz coils mounted parallel (perpendicular) to the crystalline c-axis (FIG. 1(c)). The extracted values are $g_{\parallel}^{e} = -1.452(1)$ and $g_{\perp}^{e} = 1.362(1)$, qualitatively matching previous results [41]. At non-zero magnetic fields, symmetry-forbidden optical transitions become apparent as the symmetry of the site is reduced and the spin states mix. Surprisingly, to fully explain the optical absorption spectrum, we need to assume higher D_{2d} point symmetry, leading to S_4 site symmetry under a perturbation [39, 42].

At zero magnetic field, the eigenstates of the ground state manifold can be expressed as

$$\begin{split} |1\rangle_{g} &= (|\uparrow \Downarrow \rangle_{g} - |\downarrow \Uparrow \rangle_{g})/\sqrt{2}, \\ |2,3\rangle_{g} &= |\uparrow \Uparrow \rangle_{g}, |\downarrow \Downarrow \rangle_{g}, \\ |4\rangle_{g} &= (|\uparrow \Downarrow \rangle_{g} + |\downarrow \Uparrow \rangle_{g})/\sqrt{2}, \end{split}$$
(2)

and the excited state manifold as

$$\begin{split} |1,2\rangle_e &= |\uparrow\uparrow\rangle_e \,, |\downarrow\downarrow\rangle_e \,, \\ |3\rangle_e &= (|\uparrow\downarrow\rangle_e + |\downarrow\uparrow\rangle_e)/\sqrt{2}, \\ |4\rangle_e &= (|\uparrow\downarrow\rangle_e - |\downarrow\uparrow\rangle_e)/\sqrt{2}, \end{split}$$
(3)

where $|\uparrow\rangle = |m_S = +1/2\rangle$, $|\downarrow\rangle = |m_S = -1/2\rangle$ represent the electron spin and $|\uparrow\rangle = |m_I = +1/2\rangle$, $|\downarrow\rangle = |m_I = -1/2\rangle$ the nuclear spin projections. Two out of four electron-nuclear hyperfine states are completely entangled in their electronic and nuclear components (FIG. 1(a)). The average magnetic moment for these states is zero ($\langle i | \mathbf{S} | i \rangle = \langle i | \mathbf{I} | i \rangle = 0$), rendering the energy levels insensitive to external magnetic fields in first order. As a result, the $|1\rangle_g - |4\rangle_g$ spin transition connecting two hybridized states is considered a clock transition.



FIG. 2. (color online) All-optical coherent spin control. (a) Experimental pulse sequence used for all-optical detection of spin coherence. First, we polarise the spin ensemble of $^{171}\mathrm{Yb}^{3+}$ ions into the $\left|1\right\rangle_g$ state by optical pumping around the ω_A and ω_B frequencies. We then use optical pulses with frequency ω_A and ω_E to induce a Raman transition between the $|1\rangle_a$ and $|4\rangle_a$ spin states. The spin echo sequence with τ_{12} delay between the first two spin rotations ends with a pulse at the ω_A frequency used for detecting the spin echo signal. (b) Measurement of the $|1\rangle_q$ - $|4\rangle_q$ transition illustrating the inhomogeneous broadening at zero magnetic field with $\Delta_{14}/2\pi$ detuning around $\omega_A - \omega_E = 3083.87$ MHz. A Gaussian fit gives a FWHM of $\Gamma_{\rm inh}^s/2\pi = 5$ kHz. (c) Spin echo intensity as a function of the delay τ_{12} between the two spin rotations, at zero magnetic field. The solid line is the fit giving $T_2^s = 0.15$ s. (d) Spin coherence time as a function of the temperature, explained by the model based on flip-flops. The dashed line represents the measured $2T_1$ limit given by the spin-lattice interaction [39].

Similarly, optical transitions such as $|4\rangle_g - |4\rangle_e$ are also first-order protected from magnetic noise (FIG. 1(a)).

The combination of large hyperfine splittings and narrow optical lines allows for optical initialization of the whole spin ensemble into a desired ground state level. By addressing the $|4\rangle_g$ and $|2,3\rangle_g$ states via the A and B transitions (FIG. 1(b)), we prepare 171 Yb³⁺ ions into the $|1\rangle_g$ state with high efficiency. Efficient optical pumping is possible thanks to strongly suppressed spin-phonon relaxation processes at temperatures below 2 K. We measure a spin ensemble recovery time of more than 3 hours at 50 mK [39]. Together with a relatively short excited state lifetime of $T_1^o = 0.385$ ms, we achieve more than 99% initialization efficiency for the whole 171 Yb³⁺ spin ensemble [39].

Spin coherence. Next, we implement all-optical coherent spin control to measure the spin coherence properties of the ¹⁷¹Yb³⁺ ensemble. We use an optical Λ system, consisting of transitions A and E, to address the $|1\rangle_g - |4\rangle_g$ spin transition at 3.083 GHz (FIG. 1(a,b)). To drive the Raman transition, we use an electro-optic

modulator to generate two spectral tones separated by the $|1\rangle_q - |4\rangle_q$ energy splitting. Using this control, we perform a spin echo experiment consisting of a sequence of $\pi/2$ and π pulses separated by a τ_{12} delay (FIG. 2(a)). With a final probe pulse addressing the $|4\rangle_a$ state using the A transition, we observed the spin echo by detection of the coherent Raman scattering [43]. First, we varied the frequency separation of the two laser tones and detected the spin echo signal at a fixed delay to extract a spin inhomogeneous linewidth of 5 kHz (FIG. 2(b)). The observed spin inhomogeneous broadening is one the narrowest reported for paramagnetic solid-state ensembles, less than the 48 kHz in ${}^{171}Yb^{3+}$:YVO₄ [31] and 0.5 MHz in 171 Yb ${}^{3+}$:Y₂SiO₅ [44]. Then, by varying the delay between two pulses, we measured a spin coherence time up to $T_2^s = 0.15$ s (FIG. 2(c,d)). The measured spin coherence time is the longest achieved at zero magnetic fields among rare-earth ions, even those possessing nuclear spin $(15 \text{ ms in } {}^{151}\text{Eu}{}^{3+}:Y_2\text{SiO}_5 [45]).$

This long spin coherence time is governed by several features. First, the nuclear spin density of $CaWO_4$ is one of the lowest for crystalline materials and is dominated by the 183 W isotope [46]. Additionally, 183 W has a rather low $g_n = 0.2356$, resulting in weak interactions with ¹⁷¹Yb³⁺ spins. Second, the $|1\rangle_g - |4\rangle_g$ transition is protected by the clock condition, i.e. it is only secondorder sensitive to external magnetic noise. Third, the spin-spin dynamics between ¹⁷¹Yb³⁺ ions are suppressed due to the polarisation into the $|1\rangle_a$ state. We measured the temperature dependence of the coherence time up to 3 K, while repeating the spin polarisation in $|1\rangle_q$ via optical pumping (FIG. 2(d)). The measured spin coherence time is relatively constant up to 1 K and decreases to 10 ms at 3 K. We attribute this drop to 171 Yb³⁺ spins experiencing flip-flop processes that exchange their spin states due to long-range magnetic dipole-dipole interaction [23]. More specifically, at 1K, the optical pumping efficiency starts to drop due to the stronger spin-phonon relaxation and prevents the complete emptying of the $|2,3\rangle_q$ states. At 3 K, the spin-lattice relaxation rate increase to $\geq 2 \text{ s}^{-1}$ [39], resulting in $\approx 10\%$ of population staying in $|2,3\rangle_{a}$ states after the initial polarisation. This intensified flip-flop process between 171 Yb³⁺ ions affects the spin coherence in several ways (FIG. 3(b)) [47]. The spin coherence is directly affected due to an increase in spin flip-flops involving spins in $|2,3\rangle_a$ state, which is efficiently quenched at lower temperatures. Indirectly, the magnetic field noise is increased due to increased spin flipflops of ¹⁷¹Yb³⁺ spins near the probed ensemble. However, this effect is assumed to be small due to the low magnetic field sensitivity of the states and the modest concentration of 171 Yb³⁺ spins.

Lifetime-limited optical coherence.

In this section, we measure the optical coherence, and subsequently use the optical coherence measurements to provide more insight into the fast spin-spin dynamics. The optical coherence time T_2^o of the $|4\rangle_q - |4\rangle_e$ transition



FIG. 3. (color online) **Optical coherence of** 171 **Yb**³⁺:**CaWO**₄. (a) Experimental pulse sequence used for photon echo (PE) measurements. It consists of spin polarisation by optical pumping using ω_E and ω_F frequencies (see FIG. 1(a)). Optical pulses resonant with the D transition are then used for the photon echo (PE) sequence with a τ_{12} delay between the two pulses. (b) Left: indirect contribution to decoherence due to flips of neighboring spin pairs (light red) producing magnetic noise for the probed ions (dark red). Middle: flip-flops between the addressed ions and the neighboring spins directly contributes to a reduction in spin coherence. Right: spin dynamics rates for different transitions are highly transition dependent. Flip-flop rates with states involving $|2,3\rangle_g$ are two orders of magnitude larger than for $|1\rangle_g - |4\rangle_g$ transition. (c) Measurement of the PE intensity as a function of the delay τ_{12} after polarising the spin ensemble of 171 Yb³⁺ ions into $|4\rangle_g$ state (red) or reshuffling population between all the spin states (blue). Solid lines are exponential fits, giving optical coherence times $T_2^o = 0.75$ ms and $T_2^o = 0.54$ ms, respectively. (d) Absorption profile after polarising the spin ensemble into $|4\rangle_g$ state (solid line) or reshuffling population between all the spin states (dashed line). (e) Optical coherence time as a function of temperature while reshuffling the spin populations (blue diamond). The optical coherence time when polarising spins into the $|4\rangle_g$ state is enhanced (red circles) and approaches the $2T_1$ limit (dashed line). The solid and dash-dot lines show predictions from the model [39].

is measured through a standard photon echo technique using a single laser tone resonant with the D transition (FIG. 3(a)). Without optical pumping, an optical coherence time T_2^o up to 0.54 ms was measured, surpassing the excited state lifetime $T_1^o = 0.385$ ms (FIG. 3(c)). Next, using optical pumping, we initialize all the population in the $|4\rangle_g$ state (FIG. 3(d)). In this manner, the optical coherence time increases to $T_2^o = 0.75(2)$ ms, which is nearing the $2T_1 = 0.77$ ms limit (FIG. 3(e)).

We attribute the decrease of the optical coherence time without optical pumping to spin-spin dynamics via magnetic dipole-dipole interactions involving the $|2,3\rangle_g$ state, described above. Due to the high anisotropy of the **g** tensor, the spin flip-flop processes are strongly state-dependent and the flip-flop rate is proportional to g^4 [23]. Only the $|1\rangle_g - |4\rangle_g$ spin transition is solely coupled via g_{\parallel} , all other spin transitions involve g_{\perp} which is almost four times higher. Hence, the flip-flop rates involving the $|2,3\rangle_g$ are faster by a factor $g_{\parallel}^4/g_{\perp}^4 \approx 200$ and greatly reduce the spin coherence time T_2^s (FIG. 3(b)). We estimate the flip-flop rates involving the $|2,3\rangle_g$ states to reach 10^3 s^{-1} , leading to millisecond spin lifetimes [23]. Removing the population from $|2,3\rangle_g$ states is thus crucial to suppress the fastly decohering spin-spin dynamics. Above 2K, the additional decrease of the optical

coherence can be explained by phonon scattering in the excited state with a T^9 dependence (FIG. 3(e)). This optical coherence time of 0.75 ms is one of the longest observed for paramagnetic solid-state emitters comparable to 171 Yb³⁺:Y₂SiO₅ (1 ms [48]) and nuclear spin ions in Eu³⁺:Y₂SiO₅, (2.6 ms [49]).

Discussion and conclusion. We stress that even if the energy levels are insensitive to magnetic fields in the first order, the dipole moments of their transitions remain strong and correspond to electron spins. Such that, $\langle 1|_g \mu_{\rm B} \mathbf{g} \cdot \mathbf{S} | 4 \rangle_g = \mu_{\rm B} g_{\parallel}^g$, the spin transition can be driven using an AC magnetic field along the *c*-axis. The optimal orientation of the AC drive for all other spin transitions is perpendicular to the *c*-axis, with the transition dipole moment proportional to g_{\perp}^g . We emphasize that even under the clock condition, microwave driving can still be efficient and fast, making this system compatible with interfacing with superconducting circuits [24, 50].

Due to these strong transition dipole moments, electron spin-like fast spin-spin dynamics are present between 171 Yb³⁺ ions. As we demonstrate in this study, such dynamics can be suppressed at low temperatures by polarising the whole spin ensemble via optical pumping. However, applications involving large ensembles must have long-lived auxiliary spin states storing part of the popu-

lation. These states must be free from fast spin-spin processes to prevent coupling the spin population to other states. One way to suppress the fast spin-spin dynamics is to work with lower doping concentrations. For example, lowering the concentration to 0.5 ppm will suppress the fast flip-flop rate down to 10^2 s^{-1} level, while still exhibiting significant optical absorption. Another solution is to perform additional engineering of the material, and to controllably broaden the spin inhomogeneous linewidth without affecting the optical absorption. An example of this approach has been explored through co-doping of rare earth ions [51, 52].

Lowered doping concentrations would enable the observation of single 171 Yb³⁺ in CaWO₄ and is expected to yield even longer spin and optical coherence times. Promisingly, a 0.7 ppb natural concentration of Er³⁺ allowed for 23 ms spin coherence times at high magnetic fields [24]. The use of zero-field clock transitions, reported in our work, will strongly enhance coherences, while integration with nanophotonic structures will improve the properties of a spin-photon interface [36, 37].

In conclusion, we have experimentally investigated the novel material 171 Yb³⁺:CaWO₄ and reached lifetimelimited optical coherence and spin coherence times up to 0.15 s, facilitated by the clock transitions at zero magnetic fields. This material provides a set of exclusive properties such as optically resolved hyperfine transitions, the ability for all-optical initialization of the spin ensemble, and long coherence times, making it a unique resource for quantum networking and information applications. These features make 171 Yb³⁺:CaWO₄ appealing for optical quantum memories [4, 53], coupling to superconducting circuits [24], integrated spin-photon interfaces [36, 37], and optical-to-microwave quantum transducers [6].

Acknowledgement. This project has received funding from the CNRS under the Priority Quantum Research Programme and Equipment (PEPR, QMemo), NASA ROSES program, Gordon and Betty Moore Foundation Experimental Physics Investigators program. A.T. was supported by ANR under grant agreement no. ANR-22-CPJ2-0060-01. E.G. acknowledges support from the the National Gem Consortium as well as the National Science Foundation Graduate Research Fellowship under grant no. 2139433. S.H. acknowledges support from the AWS Quantum Postdoctoral Fellowship. E.L. acknowledges support from the DoD National Defense Science and Engineering Graduate Fellowship. S.B. thanks the support of the CNRS research infrastructure INFRANALYTICS (FR 2054). F.C. acknowledges financial support from Marie Curie Fellowship (101066781). A.M.K. is supported by ANR QuantEdu-France (22-CMAS-0001) and by France 2030 investment plan, as part of the Initiative d'Excellence d'Aix-Marseille Université – A*MIDEX (AMX-22-RE-AB-199). Authors thank M. Afzelius, L. Nicolas for discussions, and A. Ferrier for technical help.

- I. Aharonovich, D. Englund, and M. Toth, Nature Photonics 10, 631–641 (2016).
- [2] M. Atatüre, D. Englund, N. Vamivakas, S.-Y. Lee, and J. Wrachtrup, Nature Reviews Materials 3, 38–51 (2018).
- [3] D. D. Awschalom, R. Hanson, J. Wrachtrup, and B. B. Zhou, Nature Photonics 12, 516–527 (2018).
- [4] F. Bussières, N. Sangouard, M. Afzelius, H. de Riedmatten, C. Simon, and W. Tittel, Journal of Modern Optics 60, 1519–1537 (2013).
- [5] X. Fernandez-Gonzalvo, Y.-H. Chen, C. Yin, S. Rogge, and J. J. Longdell, Phys. Rev. A 92, 062313 (2015).
- [6] J. G. Bartholomew, J. Rochman, T. Xie, J. M. Kindem, A. Ruskuc, I. Craiciu, M. Lei, and A. Faraon, Nature Communications 11 (2020).
- [7] A. M. Dibos, M. Raha, C. M. Phenicie, and J. D. Thompson, Phys. Rev. Lett. **120**, 243601 (2018).
- [8] T. Zhong, J. M. Kindem, J. G. Bartholomew, J. Rochman, I. Craiciu, V. Verma, S. W. Nam, F. Marsili, M. D. Shaw, A. D. Beyer, and A. Faraon, Phys. Rev. Lett. **121**, 183603 (2018).
- [9] P. Jobez, C. Laplane, N. Timoney, N. Gisin, A. Ferrier, P. Goldner, and M. Afzelius, Phys. Rev. Lett. 114, 230502 (2015).
- [10] M. Gündoğan, P. M. Ledingham, K. Kutluer, M. Mazzera, and H. de Riedmatten, Phys. Rev. Lett. 114, 230501 (2015).

- [11] H. Bernien, B. Hensen, W. Pfaff, G. Koolstra, M. S. Blok, L. Robledo, T. H. Taminiau, M. Markham, D. J. Twitchen, L. Childress, and R. Hanson, Nature 497, 86–90 (2013).
- [12] C. E. Bradley, J. Randall, M. H. Abobeih, R. C. Berrevoets, M. J. Degen, M. A. Bakker, M. Markham, D. J. Twitchen, and T. H. Taminiau, Phys. Rev. X 9, 031045 (2019).
- [13] J. M. Taylor, P. Cappellaro, L. Childress, L. Jiang, D. Budker, P. R. Hemmer, A. Yacoby, R. Walsworth, and M. D. Lukin, Nature Physics 4, 810–816 (2008).
- [14] Y. Chu, N. de Leon, B. Shields, B. Hausmann, R. Evans, E. Togan, M. J. Burek, M. Markham, A. Stacey, A. Zibrov, A. Yacoby, D. Twitchen, M. Loncar, H. Park, P. Maletinsky, and M. Lukin, Nano Letters 14, 1982–1986 (2014).
- [15] P. Lodahl, S. Mahmoodian, and S. Stobbe, Rev. Mod. Phys. 87, 347 (2015).
- [16] W. Redjem, A. Durand, T. Herzig, A. Benali, S. Pezzagna, J. Meijer, A. Y. Kuznetsov, H. S. Nguyen, S. Cueff, J.-M. Gérard, I. Robert-Philip, B. Gil, D. Caliste, P. Pochet, M. Abbarchi, V. Jacques, A. Dréau, and G. Cassabois, Nature Electronics 3, 738–743 (2020).
- [17] N. Morioka, C. Babin, R. Nagy, I. Gediz, E. Hesselmeier, D. Liu, M. Joliffe, M. Niethammer, D. Dasari, V. Vorobyov, R. Kolesov, R. Stöhr, J. Ul-Hassan, N. T.

Son, T. Ohshima, P. Udvarhelyi, G. Thiering, A. Gali, J. Wrachtrup, and F. Kaiser, Nature Communications **11** (2020).

- [18] J. D. Caldwell, I. Aharonovich, G. Cassabois, J. H. Edgar, B. Gil, and D. N. Basov, Nature Reviews Materials 4, 552–567 (2019).
- [19] W. Tittel, M. Afzelius, T. Chaneliére, R. Cone, S. Kröll, S. Moiseev, and M. Sellars, Laser & Photonics Reviews 4, 244–267 (2010).
- [20] M. Rančić, M. P. Hedges, R. L. Ahlefeldt, and M. J. Sellars, Nature Physics 14, 50–54 (2017).
- [21] J. M. Kindem, J. G. Bartholomew, P. J. T. Woodburn, T. Zhong, I. Craiciu, R. L. Cone, C. W. Thiel, and A. Faraon, Phys. Rev. B 98, 024404 (2018).
- [22] A. Ortu, A. Tiranov, S. Welinski, F. Fröwis, N. Gisin, A. Ferrier, P. Goldner, and M. Afzelius, Nature Materials 17, 671–675 (2018).
- [23] S. Welinski, A. Tiranov, M. Businger, A. Ferrier, M. Afzelius, and P. Goldner, Phys. Rev. X 10, 031060 (2020).
- [24] M. Le Dantec, M. Rančić, S. Lin, E. Billaud, V. Ranjan, D. Flanigan, S. Bertaina, T. Chanelière, P. Goldner, A. Erb, R. B. Liu, D. Estève, D. Vion, E. Flurin, and P. Bertet, Science Advances 7 (2021).
- [25] L. Nicolas, M. Businger, T. Sanchez Mejia, A. Tiranov, T. Chanelière, E. Lafitte-Houssat, A. Ferrier, P. Goldner, and M. Afzelius, npj Quantum Information 9 (2023).
- [26] A. Ulanowski, B. Merkel, and A. Reiserer, Science Advances 8 (2022).
- [27] Y. Yu, D. Oser, G. Da Prato, E. Urbinati, J. C. Ávila, Y. Zhang, P. Remy, S. Marzban, S. Gröblacher, and W. Tittel, Phys. Rev. Lett. **131**, 170801 (2023).
- [28] J.-Y. Huang, P.-J. Liang, L. Zheng, P.-Y. Li, Y.-Z. Ma, D.-C. Liu, J.-H. Xie, Z.-Q. Zhou, C.-F. Li, and G.-C. Guo, Chinese Physics Letters 40, 070301 (2023).
- [29] L. Yang, S. Wang, M. Shen, J. Xie, and H. X. Tang, Nature Communications 14 (2023).
- [30] M. Raha, S. Chen, C. M. Phenicie, S. Ourari, A. M. Dibos, and J. D. Thompson, Nature Communications 11 (2020).
- [31] J. M. Kindem, A. Ruskuc, J. G. Bartholomew, J. Rochman, Y. Q. Huan, and A. Faraon, Nature 580, 201–204 (2020).
- [32] A. Gritsch, A. Ulanowski, J. Pforr, and A. Reiserer, Nature Communications 16 (2025).
- [33] T. Kornher, D.-W. Xiao, K. Xia, F. Sardi, N. Zhao, R. Kolesov, and J. Wrachtrup, Phys. Rev. Lett. 124, 170402 (2020).
- [34] A. Ruskuc, C.-J. Wu, J. Rochman, J. Choi, and A. Faraon, Nature 602, 408–413 (2022).
- [35] M. T. Uysal, M. Raha, S. Chen, C. M. Phenicie, S. Ourari, M. Wang, C. G. Van de Walle, V. V. Dobrovitski, and J. D. Thompson, PRX Quantum 4, 010323 (2023).
- [36] M. T. Uysal, L. Dusanowski, H. Xu, S. P. Horvath, S. Ourari, R. J. Cava, N. P. de Leon, and J. D. Thompson, Physical Review X 15 (2025), 10.1103/physrevx.15.011071.
- [37] A. Ruskuc, C.-J. Wu, E. Green, S. L. N. Hermans, W. Pajak, J. Choi, and A. Faraon, Nature 639, 54–59 (2025).
- [38] E. Billaud, L. Balembois, J. Travesedo, M. Le Dantec, M. Rančić, E. Albertinale, R. Truong, S. Bertaina, T. Chanelière, P. Goldner, D. Estève, D. Vion, E. Flurin,

and P. Bertet, Physical Review Research 7 (2025).

- [39] "Supplementary materials," (2025).
- [40] R. M. Rakhmatullin, I. N. Kurkin, G. V. Mamin, S. B. Orlinskii, M. R. Gafurov, E. I. Baibekov, B. Z. Malkin, S. Gambarelli, S. Bertaina, and B. Barbara, Phys. Rev. B 79, 172408 (2009).
- [41] G. R. Jones, The Journal of Chemical Physics 47, 4347–4355 (1967).
- [42] R. Hull, J. Parisi, R. M. Osgood, H. Warlimont, G. Liu, and B. Jacquier, eds., *Spectroscopic Properties of Rare Earths in Optical Materials*, Springer Series in Materials Science, Vol. 83 (Springer Berlin Heidelberg, Berlin, Heidelberg, 2005).
- [43] O. Guillot-Noël, P. Goldner, F. Beaudoux, Y. Le Du, J. Lejay, A. Amari, A. Walther, L. Rippe, and S. Kröll, Physical Review B **79** (2009), 10.1103/physrevb.79.155119.
- [44] A. Tiranov, A. Ortu, S. Welinski, A. Ferrier, P. Goldner, N. Gisin, and M. Afzelius, Phys. Rev. B 98, 195110 (2018).
- [45] A. L. Alexander, J. J. Longdell, and M. J. Sellars, Journal of the Optical Society of America B 24, 2479 (2007).
- [46] S. Kanai, F. J. Heremans, H. Seo, G. Wolfowicz, C. P. Anderson, S. E. Sullivan, M. Onizhuk, G. Galli, D. D. Awschalom, and H. Ohno, Proceedings of the National Academy of Sciences **119** (2022).
- [47] A. M. Tyryshkin, S. Tojo, J. J. L. Morton, H. Riemann, N. V. Abrosimov, P. Becker, H.-J. Pohl, T. Schenkel, M. L. W. Thewalt, K. M. Itoh, and S. A. Lyon, Nature Materials 11, 143–147 (2011).
- [48] F. Chiossi, E. Lafitte-Houssat, A. Ferrier, S. Welinski, L. Morvan, P. Berger, D. Serrano, M. Afzelius, and P. Goldner, Phys. Rev. B 109, 094114 (2024).
- [49] R. W. Equall, Y. Sun, R. L. Cone, and R. M. Macfarlane, Phys. Rev. Lett. **72**, 2179 (1994).
- [50] J. Alexander, G. Dold, O. W. Kennedy, M. Šimėnas, J. O'Sullivan, C. W. Zollitsch, S. Welinski, A. Ferrier, E. Lafitte-Houssat, T. Lindström, P. Goldner, and J. J. L. Morton, Physical Review B 106 (2022).
- [51] C. W. Thiel, W. R. Babbitt, and R. L. Cone, Physical Review B 85 (2012).
- [52] S. Welinski, C. Thiel, J. Dajczgewand, A. Ferrier, R. Cone, R. Macfarlane, T. Chanelière, A. Louchet-Chauvet, and P. Goldner, Optical Materials 63, 69–75 (2017).
- [53] M. Businger, L. Nicolas, T. S. Mejia, A. Ferrier, P. Goldner, and M. Afzelius, Nature Communications 13 (2022)

Supplementary Notes - Sub-second spin and lifetime-limited optical coherences in 171 Yb³⁺:CaWO₄

Alexey Tiranov,^{1, *} Emanuel Green,² Sophie Hermans,² Erin Liu,² Federico Chiossi,¹ Diana Serrano,¹

Pascal Loiseau,¹ Achuthan Manoj Kumar,³ Sylvain Bertaina,³ Andrei Faraon,² and Philippe Goldner¹

¹Chimie ParisTech, PSL University, CNRS, Institut de Recherche de Chimie Paris, 75005 Paris, France ²Thomas J. Watson, Sr., Laboratory of Applied Physics, California Institute of Technology, Pasadena, CA, 91125, USA ³CNRS, Aix Marseille Univ, Université de Toulon, Institut Matériaux Microélectronique et Nanosciences de Provence, IM2NP, 13013 Marseille, France

(Dated: April 3, 2025)

CONTENTS

	References	5
I.	Sample preparation	2
II.	Crystal structure	2
III.	Sample characterizationA. Emission spectraB. Optical absorption	2 2 3
IV.	 Coherence measurements A. Experimental setup B. High-resolution optical absorption C. Magnetic field sweeps. D. Optical pumping E. Spin-lattice relaxation (SLR) at zero magnetic field F. Optically detected spin echo G. Photon echo 	$egin{array}{c} 4 \\ 4 \\ 5 \\ 5 \\ 7 \\ 9 \\ 11 \\ 11 \end{array}$
V.	 Spin Hamiltonian A. Spin-spin dynamics B. Optical and spin decoherence C. Electron paramagnetic resonance (EPR) measurements D. Concentration estimation 	11 12 13 14 16
VI.	State representations and selection rules A. Ground state doublet ${}^{2}F_{7/2}(0)$ B. Excited state doublet ${}^{2}F_{5/2}(0)$ C. Effect of J mixing D. Selection rules	16 16 18 19 19
	neierences	22

^{*} Email to: alexey.tiranov@chimieparistech.psl.eu

I. SAMPLE PREPARATION

We used CaWO₄ scheelite crystals nominally doped with 0.002 at.% (20 ppm) 171 Yb³⁺ ions. The crystal sample was cut from a boule grown using the Czochralski method, starting from CaCO₃ and WO₃ raw materials with 99.97 at.% and 99.98 at.% purity, respectively. Isotopically purified 171 Yb₂O₃ with 95% purity was used for the doping.

Samples were cut along the a (b) and c crystallographic axes. Several samples with 1 cm and 1.5 cm sizes along the c axis were prepared, and polishing was done to get optically transmitting surfaces along several directions. For optical experiments, two samples with different sizes (9.2, 9.7, 9.9) and (15, 4.1, 4.8) mm in the (a, a, c) frame were prepared. For the electron paramagnetic resonance (EPR) study, a (1.5, 2.2, 2.5) mm sample weighing 63 mg was used.

II. CRYSTAL STRUCTURE

CaWO₄ has a tetragonal structure belonging to the $I4_1/a$ space group (#88). Yb³⁺ ions can substitute Ca²⁺ in two inversion-related sites, both of them having tetragonal S_4 symmetry and magnetically equivalent. For metallic ions in the trivalent oxidation state (such as rare-earth ions in general and Yb³⁺ in particular), charge compensation is necessary to insert them into the CaWO₄ lattice in a Ca²⁺ position. Previous studies indicated that the charge compensation mechanism occurs mainly over large distances [S1, S2], which results in a weak perturbation of the main Yb³⁺ sites, retaining Ca²⁺ S_4 site symmetry. This contributes to narrow inhomogeneous broadening observed in our study. However, charge compensation also occurs in the immediate vicinity for a significant part of the Yb³⁺ ions. This mechanism can involve a Ca vacancy or another monovalent ion present in the crystal. This compensation close to the ion can significantly perturb the crystal field at the position of the dopant, modifying its optical and magnetic properties and giving rise to several additional sites appearing in optical and spin resonance measurements.

III. SAMPLE CHARACTERIZATION

A. Emission spectra

The crystal field level structure of Yb³⁺ in CaWO₄ was measured previously [S3, S4] and is indicated in FIG. S1(a). We measured the emission spectra of ¹⁷¹Yb³⁺:CaWO₄ by using a Nd:YAG pumped OPO laser system with a spectral linewidth around 1 nm and nanosecond excitation pulse widths at a 10 Hz repetition rate. Excitation using the ${}^{2}F_{7/2}(0) \rightarrow {}^{2}F_{5/2}(1)$ transition around 10380 cm⁻¹ (963 nm) (FIG. S1(b,c)) was performed at a temperature of 15 K. The lines observed corresponding to the ${}^{2}F_{5/2}(0) \rightarrow {}^{2}F_{7/2}(0,1,2,3)$ transitions are found according to previous studies. The transition linewidths for the higher energy transitions are much broader than the main transition, which can be due to phonon broadening and vibronic transitions. The emission spectrum, when exciting the ${}^{2}F_{7/2}(0) \rightarrow {}^{2}F_{5/2}(2)$ transition around 10700 cm⁻¹ (954 nm), contains an additional line around 981.7 nm. The same line is also visible in the absorption spectra shown in the next section. The width of this line is much narrower than the other higher energy lines, which suggests that it comes from another Yb³⁺ site.

The excited state lifetime was measured by exciting the ${}^{2}F_{7/2}(0) \rightarrow {}^{2}F_{5/2}(0)$ transition and detecting the fluorescence at the ${}^{2}F_{5/2}(0) \rightarrow {}^{2}F_{7/2}(1)$ transition wavelength. The result of the exponential fit gives $T_{1} = 0.385$ ms (FIG. S2).

To estimate the branching ratio β from the first excited state ${}^{2}F_{5/2}(0)$ to the lowest ${}^{2}F_{7/2}(0)$ ground state level, we integrated the emission spectra from FIG. S1(b). The resulting percentage going to the ${}^{2}F_{5/2}(0) \rightarrow {}^{2}F_{7/2}(0)$ transition is around 5(1)%. We can also estimate this value by calculating the spontaneous emission rate Γ_{s} of a two-level emitter

$$\Gamma_s = \frac{2\pi e^2 \nu^2}{\epsilon_0 m_e c^3} n^2 \chi_L f \tag{S1}$$

where $\chi_L = (n^2 + 2)^2/9$, *e*, m_e are the electron charge and mass, ν is the transition frequency, *n* the refractive index, *c* the speed of light, ϵ_0 the vacuum permittivity, and *f* is the oscillator strength of the optical transition. *f* can be estimated from the absorption spectra using

$$f = \frac{4\pi\epsilon_0 m_e c}{\pi e^2} \frac{1}{3N} \sum_i \chi_L^{-1} \alpha_i(\nu) d\nu, \qquad (S2)$$

where N is the ion density and the summation is done over the three orthogonal polarisations. For CaWO₄, the refractive index along the a(b) axis is n = 1.895 at 973 nm, and the concentration of ¹⁷¹Yb³⁺ ions in the tetragonal



FIG. S1. (color online) **Crystal field (CF) levels and emission spectra of** 171 **Yb**³⁺**:CaWO**₄**.** (a) CF splittings of Yb³⁺ reproduced from [S3]. Emission spectra of 171 Yb³⁺:CaWO₄ at 15 K excited on the 0 - 1 transition at 963 nm (b) and the 0 - 2 transition at 954 nm (c). Transitions between CF levels are indicated with dashed lines. The line at 981.7 nm is attributed to another Yb³⁺ site.



FIG. S2. (color online) Excited-state ${}^{2}F_{5/2}(0)$ lifetime measurement via fluorescence decay. An exponential fit (solid line) gives 0.385 ms.

 S_4 site was estimated using electron paramagnetic resonance measurements to be 4.96 ppm, giving an ion density of $N = 6.97 \times 10^{16}$ cm⁻³. We thus estimated the oscillator strength to be $f = 2.4 \times 10^{-7}$ giving $\Gamma_s = 60$ s⁻¹. This results in the branching ratio being lower bounded by $\beta = \Gamma_s T_1 = 0.04$ which corresponds to a purely radiative emission, a reasonable assumption for Yb³⁺ at low concentrations [S5]. The results from optical characterization are summarized in TABLE S1.

B. Optical absorption

The absorption spectrum taken at 15 K is shown in FIG. S3. The position of the ${}^{2}F_{7/2}(0) \rightarrow {}^{2}F_{5/2}(0)$ transition of the tetragonal S_4 site is visible, while absorption lines from the ${}^{2}F_{7/2}(0) \rightarrow {}^{2}F_{5/2}(1,2)$ transitions are weaker and slightly shifted with respect to the expected values indicated by dashed lines. The width of the ${}^{2}F_{7/2}(0) \rightarrow {}^{2}F_{5/2}(0)$ transition peak is broadened by the resolution of the spectrophotometer (0.1 nm). The other transitions ${}^{2}F_{7/2}(0) \rightarrow {}^{2}F_{5/2}(1,2)$ are homogeneously broadened by phonon relaxation processes with FWHM between 15 and 30 cm⁻¹.

Satellite absorption peaks are visible close to the ${}^{2}F_{7/2}(0) \rightarrow {}^{2}F_{5/2}(0)$ transition, and can be attributed to Yb³⁺ sites



FIG. S3. (color online) **Absorption spectra of** 171 **Yb** ${}^{3+}$ **:CaWO**₄ **at 15K.** (a) Absorption spectrum of 171 **Yb** ${}^{3+}$ **:**CaWO₄ at 15 K with unpolarised light propagating along the *a* axis. Transitions between different crystal field levels are indicated for the tetragonal S_4 site. Multiple absorption peaks are visible on the zooms around 977 nm (b) and 963 nm (c).

shifted to lower energy due to the lower symmetry (FIG. S3(b)). They can appear from the charge compensation mechanism in the vicinity of the substitutional site but with different charge configurations leading to multiple lower symmetry orthorhombic D_2 sites [S1, S6]. Unidentified absorption peaks around 961.43 nm and 1024.85 nm are also visible in the spectrum in FIG. S3(a). The positions of all observed lines are summarised in TABLE S1.

IV. COHERENCE MEASUREMENTS

A. Experimental setup

The crystal was placed in a Bluefors dilution cryostat at about 50 mK. The crystal was fixed on a copper mount using silver glue, and the mount was screwed to the cold plate of the cryostat cooled down up to 40 mK. During the experiment a temperature sensor mounted on the cold plate went up to 60 mK, presumably due to heating through laser scattering.

A 980 nm DLPro Toptica external cavity diode laser was used for high resolution optical spectroscopy and coherence time measurements. We generated optical pulse sequences by controlling amplitude and frequency using acousto-optical modulators (AOMs). The AOM was driven using the arbitrary waveform generator AWG Keysight M320xA. The laser was split into two paths, namely the pump/probe sent to the crystal and a local oscillator used in a heterodyne detection scheme. The optical power in each path was approximately 5 mW.

For each path, a fiber-based electro-optical phase modulator (iXBLue NIR-MPX-LN-10) was used to add sidebands onto the carrier frequency. The phase modulators (PM) were driven with DS SG4400L and Stanford Research Systems SG390 rf generators, amplified to the 1 W power level. A series of TTL switches was used to alternate between several frequencies generating sidebands using the PM. The TTL switches and all the devices were synchronized using a SpinCore PulseBlaster module.

The pulse sequence consisted of an optical pumping step (300 ms), a delay (10 ms), and the coherence measurement (up to 600 ms). The entire sequence was run at a 1 Hz repetition rate.

The laser beam was focused into the crystal using a free-space path through the cryostat. A lens with 30 cm focal length was used to focus the laser beam down to a 2 mm diameter. The local oscillator was interfered with the optical probe after the cryostat. The beam was later detected using a Thorlabs PDB450C balanced photodiode. The detection is performed at 3 MHz given by the difference between two microwave generators driving PMs (FIG. S4).



 $|\omega_0 - \omega_{\rm LO} + \Delta_{\rm AOM}| = 2\pi \times 3 \text{ MHz}$

FIG. S4. (color online) Experimental setup (a) and time sequence of the experiment (see text for details). AWG - arbitrary waveform generator, AOM - acousto-optic modulator, PM - phase modulator, TTL- microwave switch, BPD - balanced phot diode, BS - beamsplitter.

B. High-resolution optical absorption

High-resolution absorption spectra for the ${}^{2}F_{7/2}(0) \leftrightarrow {}^{2}F_{5/2}(0)$ transitions of the tetragonal S_{4} site were measured at zero magnetic fields for various polarisation orientations (FIG. S5). For this, the laser was scanned using the piezo actuator. Absorption scans were taken for the electric field E perpendicular to c axis ($E \perp c$), along the c axis ($E \parallel c$), and with the wave vector k parallel to c ($k \parallel c$) (FIG. S5(a-c)).

The spectra consist of multiple narrow absorption peaks corresponding to transitions connecting various hyperfine levels in the ground and excited state for 171 Yb³⁺ ions. The central peak of the spectra at zero detuning contains the lines corresponding to I = 0 Yb³⁺ isotopes. The ratio between the total absorption of 171 Yb³⁺ I = 1/2 isotope and I = 0 isotopes gives around 5 % abundance of I = 0 isotopes in accordance with the purity of the Yb₂O₃ powder used during the crystal growth. The 173 Yb³⁺ isotope (I = 5/2) was not visible in the optical absorption spectra. All lines could be well fit by a Gaussian linewidth with a FWHM of 185 MHz. Such narrow inhomogeneous broadening, much lower than the hyperfine energy splittings, allows resolving the hyperfine structure in the ground and excited states and separately addressing different spin levels. This results in the possibility to optically pump the whole spin ensemble (see Section 4.D).

Due to the non-polar site symmetry of CaWO₄, the linear electric field shifts of the optical transitions are suppressed. This reduces the effect of electric field variations along the crystal, that can partly explain inhomogeneous broadening down to 140 MHz for the $k \parallel c$ absorption spectra (FIG. S5(c)). This measurement was done using the same sample but during a different cool down of the cryostat and after regluing the sample to the cold plate. The observed Γ_{inh} variation can be attributed to the strain inside crystal samples.

C. Magnetic field sweeps.

The bulk crystals were mounted in an u-bench on the cold plate of a dilution refrigerator. The base temperature during these measurements was ≈ 800 mK. We mounted a set of home-built Helmholtz coils either parallel or perpendicular to the crystalline c-axis and applied a current up to ± 10 A in steps of 0.1 A using a magnet power supply system (American Magnetics Inc.). Light from a tunable diode laser (Toptica CTL) was coupled to a fiber and sent through a set of polarisation paddles before being directed into the u-bench setup.



FIG. S5. (color online) High-resolution optical absorption spectra of the ${}^{2}F_{7/2}(0) \leftrightarrow {}^{2}F_{5/2}(0)$ transition for the tetragonal site of ${}^{171}Yb^{3+}$:CaWO₄ recorded for $k \perp c$ and light polarised perpendicular (a) and parallel (b) to the *c* axis, as well as a spectrum taken with $k \parallel c$ (c). The absorption spectra in (a) and (b) were measured at 4.6 K, while (c) was measured at 50 mK cryogenic temperatures.

TABLE S1. Optical transition parameters for the tetragonal site in ¹⁷¹Yb³⁺:CaWO₄. The listed parameters include: CF level energies, ${}^{2}F_{7/2}(0) \leftrightarrow {}^{2}F_{5/2}(0)$ transition wavelength (vac.) (λ_{vac}), inhomogeneous linewidths (Γ_{inh}), the integrated peak absorption coefficient for different light polarisations (α_{0}), oscillator strength (f), experimental fluorescence decay time (T_{1}), and the branching ratio for the 0-0 transition (β). Optical transitions for three orthorhombic sites of ¹⁷¹Yb³⁺:CaWO₄ are given, together with unidentified lines appearing in the absorption spectra at 10 K (FIG. S3).

	Energ	gy, $\rm cm^{-1}$	$\lambda_{vac},\mathrm{nm}$	$\Gamma_{\rm inh},{\rm GHz}$	$\alpha_0,{ m cm}^{-1}$	$f \times 10^7$	T_1 , ms	β
	${}^{2}\mathrm{F}_{7/2}$	${}^{2}\mathrm{F}_{5/2}$						
S_4 site	0	10277	973.162	$0.185~(E\perp c)$	5.3 $(E \perp c)$	2.3	0.385	0.025
	220	10380		$0.185~(E \parallel c)$	$0.78~(E\parallel c)$			
	366	10700		$0.140~(k \parallel c)$	5.95 $(k \parallel c)$			
	492							
Other sites		10270.98	973.62					
		10268.95	973.81					
		10189.83	981.37					
Unidentified		10401.2	961.43					
		9757.52	1024.85					

To sweep the laser frequency over the entire absorption spectrum, we used a triangle-shaped voltage waveform to modulate the piezo actuator of the laser. The piezo modulation and the transmission through the crystal were recorded on an oscilloscope, which allowed us to extract the absorption as a function of piezo voltage. To relate this to the frequency of the laser, a copy of the laser light was sent through a fiber Fabry-Perot cavity and its transmission recorded. The fiber cavity had a calibrated free spectral range of 136 MHz. By interpolating the frequency between the transmission peaks of the fiber cavity, a relative frequency axis for each magnetic field setting was obtained. As the laser could drift over the time scale of the experiment, the center frequency of the laser was measured during the sweep using a wavemeter (Bristol 771) in order to obtain an absolute frequency axis.

The eigenstates of the ground and excited states were described by the following Hamiltonian: $H_{(g/e)} = \mathbf{I} \cdot \mathbf{A} \cdot \mathbf{S} + \mu_B \mathbf{B} \cdot \mathbf{g}_{g/e} \cdot \mathbf{S}$, ignoring the nuclear Zeeman effect ($\mu_B \gg \mu_n$). We calculated the frequencies of all transitions between the ground and excited states and convoluted them with a Gaussian distribution with a full-width at half-maximum of 136 MHz for the ¹⁷¹Yb isotope and 153 MHz for the zero nuclear spin (ZNS) isotopes. Both values were obtained from fitting absorption scans. As a perfectly aligned magnetic field was assumed, the only free parameters in the fit are the excited state g-tensor, a scaling factor to relate the magnet current to the magnetic field, the amplitude of the absorption dips associated with ¹⁷¹Yb³⁺ and the zero nuclear spin isotopes, and an overall frequency offset. We performed the fit using a least-squares method (lmfit python package).

The extracted g-tensor principal values and magnetic field scaling for light polarised perpendicular or parallel to

TABLE S2. Extracted parameters from the fit of the magnetic field dataset. Scaling factor s relates the current through to coils to the applied magnetic field. The datasets acquired for the different polarisations $(E \parallel c \text{ and } E \perp c)$ should yield the same results.

	$E\parallel c$	$E \perp c$
$g_{e,\parallel}$	-1.453(1)	-1.451(1)
s_{\parallel}	143.63(8) G/A	143.64(5) G/A
$g_{e,\perp}$	1.363(1)	1.361(1)
s_{\perp}	165.52(2) G/A	166.20(2) G/A

c are listed in TABLE S2. As expected, the values are very close in both cases. FIG. S6 shows the acquired data overlayed with the fitted curves, for both polarisations and magnetic field directions. Absorption scans for two values of the magnetic field are plotted in FIG. S7, together with the numerical model assuming all optical transitions to be allowed with equal strength.



FIG. S6. (color online) Magnetic field dependence of the optical transitions between hyperfine levels in 171 Yb ${}^{3+}$:CaWO₄. Absorption spectra for varying magnetic field strengths applied parallel to the crystalline *a*-axis (left column) and parallel to the *a*-axis (right column). The upper and lower rows show scans with $E \perp c$, respectively $E \parallel c$. Dashed lines show fits to a model given by a spin Hamiltonian (see text). Red and blue lines correspond to 171 Yb ${}^{3+}$ and I = 0 isotopes.

D. Optical pumping

To extract the ground and excited state energy splittings and the relative intensities of each transition, we performed an optical pumping experiment at 50 mK temperature. An intense 0.3 s optical pulse was sent to the crystal using a laser resonant with one of the absorption peaks. The absorption profile after pumping into different initial states was then recorded after scanning the laser across all lines (FIG. S8).

We extracted the energy splittings in the excited state by analyzing the relative positions of all the lines. We verified the order of the energy levels in the ground state, for which the hyperfine A tensor was previously measured



FIG. S7. (color online) Absorption spectra for fixed magnetic fields applied perpendicular or parallel to the crystalline c-axis (left and right columns, blue lines). The top row shows spectra acquired under fields of 829 G (left) and 718 G (right), whereas the bottom row shows spectra recorded under fields of 1659 G (left) and 1436 G (right). The simulated spectra (red lines) assume all transitions are of equal strength.

TABLE S3. Relative branching ratios for optical transitions between hyperfine levels for the 171 Yb³⁺:CaWO₄ ${}^{2}F_{7/2}(0) \leftrightarrow {}^{2}F_{5/2}(0)$ transition of the tetragonal S_4 site. Measurements were performed for light polarised perpendicular to the *c*-axis (left) and parallel to the *c* axis (center), and with $k \parallel c$ (right).

	$ 1,2\rangle_e$	$ 3\rangle_e$	$ 4\rangle_e$		$ 1,2\rangle_e$	$ 3\rangle_e$	$ 4\rangle_e$		$ 1,2\rangle_e$	$ 3\rangle_e$	$ 4\rangle_e$
$\langle 1 _g$	0.3	0.7	0.0	$\langle 1 _g$	1.0	0.0	0.0	$\langle 1 _g$	1.0	0.0	0.0
$\langle 2,3 _g$	1	0.3	0.7	$\langle 2,3 _g$	0	1.0	1.0	$\langle 2,3 _g$	0	1.0	1.0
$\langle 4 _g$	0.7	0.0	0.3	$\langle 4 _g$	1.0	0.0	0.0	$\langle 4 _g$	1.0	0.0	0.0

by [S1, S7]. The absorption peak after pumping into the $|1\rangle_g$ state FIG. S8(a) contains two transitions with a splitting around 0.08 GHz, resulting in an overall broader inhomogeneous linewidth. The same is true for the peak on the left in FIG. S8(b), when pumping into $|2,3\rangle_g$ states. For the left-most absorption peak in FIG. S8(c) the linewidth is as narrow as for the other isolated peaks and equal to 0.185 GHz, suggesting that only one optical transition contributes to it.

The absorption peak at the zero laser detuning was not affected by the optical pumping sequences. It was the same for all the measured absorption spectra, confirming that it comes from Yb^{3+} isotopes with I = 0.

The optical initialization efficiency into $|1\rangle_g$ state was estimated to be > 99% after integrating the absorption corresponding to $|2,3\rangle_g$ and $|4\rangle_g$ states FIG. S8(d).

By fitting all the lines with fixed FWHM linewidths of 0.185 GHz, we extracted the relative transition intensities for transitions connecting a given ground state to different excited states. The result of doing it for all ground states is given in the TABLE S3. Some optical transitions in the hyperfine spectra are forbidden, leading to almost diagonal branching ratio tables for π ($E \parallel c$) and α ($k \parallel c$) polarisations. For σ ($E \perp c$) polarisation, additional lines appear, potentially coming from magnetic dipole optical transitions (see Section 6.D).



FIG. S8. (color online) High-resolution optical absorption spectra of the ${}^{2}F_{7/2}(0) \leftrightarrow {}^{2}F_{5/2}(0)$ transition for tetragonal site of 171 Yb ${}^{3+}$:CaWO₄ recorded for light polarised perpendicular to *c* axis pumping ions into $|1\rangle_{g}$ (a,d), $|2,3\rangle_{g}$ (b,e), and $|4\rangle_{g}$ (c,f) states. Absorption spectra without repumping are shown with a dashed gray line.

E. Spin-lattice relaxation (SLR) at zero magnetic field

The ability to polarise the whole spin ensemble via optical pumping allowed us to characterize the spin relaxation process through the spin-lattice interaction at temperatures down to 50 mK. For this, we initialized the spin ensemble in the $|1\rangle_g$ state, the same way it was done in the previous section. Polarisation above 99% was achieved at the lowest temperatures. We repeated the absorption spectra measurement after variable time delay after the polarisation (from millisecond to a few hours) to extract the spin dynamics due to the spin-lattice interaction at zero magnetic field and variable temperatures between 50 mK and 3.6 K. The absorption spectra were analyzed for each delay to extract populations n_{1g} , $n_{2,3g}$, and n_{4g} in $|1\rangle_g$, $|2,3\rangle_g$, and $|4\rangle_g$, respectively. The recovery of the perturbed spin population was measured towards the temperature equilibrium distribution of the spin ensemble n_{ig}^{eq} given by the energy spacings between different levels and the equilibrium temperature T^{eq} by $\exp\{-E_i/(k_B T^{\text{eq}})\}$, where k_B is the Boltzmann constant and E_i is the energy for state i.

The spin population recovery at the lowest temperature of the cryostat (50 mK) is shown on FIG. S9. The recovery times are extracted using exponential fits. The equilibrium populations in the fits were shared for populations from different levels. The extracted population distribution corresponds to an equilibrium temperature of $T^{eq} = 140$ mK. A higher value for T^{eq} compared to the 50 mK cryostat temperature can be due to the additional heat load from the optical windows of the cryostat and/or to phonon bottleneck effects in the crystal [S8].

The temperature dependence of the recovery time T_R was measured up to 3.6K temperature FIG. S10. A higher relaxation rate is observed at higher temperatures due to the spin-lattice relaxation mechanism. Below 1.5 K, the relaxation decreases quadratically with the temperature and phonon relaxation is expected to be limited by the direct phonon relaxation process induced by the hyperfine interaction [S9]. For temperatures above 2 K, the relaxation is due to the two-phonon Raman process [S10, S11]. The temperature dependence of the recovery rate was fitted using $R_{\rm ph} = R_0 + a_1 T^2 + a_2 T^9$, where the first term can be related to residual excitation from the environment, second term represents the direct phonon process limited by phonon bottleneck effect, and the third is given by the two-phonon Raman relaxation process. The best-fit results are given in TABLE S4.

FIG. S9. (color online) **Spin-lattice relaxation measurement at 50 mK temperature**. Spin populations in different levels n_{1g} (a), $n_{2,3g}$ (b), and n_{4g} (c) measured for different delay times τ after the spin polarisation step. The equilibrium temperature of the spin ensemble of $T^{\text{eq}} = 140$ mK was extracted from the fitting. The dashed lines indicate the population equilibrium values at T^{eq} . (d) An example absorption spectra measured after the first delay ($\tau = 3$ minutes) and last delay ($\tau = 8$ hours).

FIG. S10. (color online) **Spin-lattice relaxation at different temperatures**. The extracted spin population recovery times T_R (a) and recovery rates T_R^{-1} (b) for different levels measured at different temperatures. The temperature axis represents the equilibrium temperatures T^{eq} extracted from the fit. The solid lines are fits for $|2,3\rangle_g$ and $|4\rangle_g$ population using the model from the text.

TABLE S4. Spin lattice relaxation (SLR) parameters for 171 Yb $^{3+}$:CaWO₄. a_1 and a_2 correspond to the direct and Raman processes.

	$R_0 \times 10^{-4} \text{ Hz}$	$a_1 \times 10^{-4} \mathrm{Hz} \mathrm{K}^{-2}$	$a_2 \times 10^{-4} \text{ Hz K}^{-9}$
$n_{2,3g}$	0.2	3.8	0.55
n_{4g}	0.2	9	0.25

F. Optically detected spin echo

We measured the spin coherence time T_2^s through optical detection of a spin echo in a Hahn echo sequence using all-optical spin manipulation via Raman transitions through the excited state [S12]. All spin echo measurements reported in this paper were carried out on the $|1\rangle_g \rightarrow |4\rangle_g$ transition (3083.87 MHz) of the tetragonal S_4 site. Without compensating the Earth's magnetic field, a spin coherence time of 30 ms was measured. A permanent magnet was used to compensate the external magnetic field and optimise the coherence properties by maximising the spin echo signal at long delays.

The duration of optical pulses in the spin echo sequence was 2 µs and was optimised using the spin echo intensity. Optical pulses of 200 µs duration were used to resolve the spin linewidth, which was found to be around 5 kHz FWHM. The detected signal was analysed with a Fast Fourier Transform and the area of the peak corresponding to the beat at $|\omega_0 - \omega_{LO} + \Delta_{AOM}|$ (FIG. ??) was acquired at various time delays τ_{12} . The coherence time T_2^s was then extracted by fitting the peak area decays as $E_{\rm echo}(\tau) = E_0 \exp(-2\tau_{12}/T_2^{\rm s})$.

G. Photon echo

The optical coherence time T_2^{o} was measured in an analogous way by preparing a photon echo sequence on a transition between a ground and an excited state. We used the heterodyne signal to measure the echo intensity detected at $|\nu_{\rm LO} - \nu_0|$ to improve the detection sensitivity. The duration of the optical pulses was about 1 µs. The optical coherence time T_2° was extracted by fitting photon echo area using $E_{\rm echo}(\tau) = E_0 \exp(-2\tau_{12}/T_2^{\circ})$.

SPIN HAMILTONIAN V.

The optical transition ${}^{2}F_{7/2}(0) \longleftrightarrow {}^{2}F_{5/2}(0)$ connects the lowest energy crystal field doublets of the ground state and the excited states. These doublets can be described using an effective S = 1/2 spin Hamiltonian involving the interaction with an external magnetic field **B** [S10]. In this work, we focus on the 171 Yb isotope, which has a nuclear spin I = 1/2, such that the effective spin Hamiltonian for the ground and excited states can be written as

$$\mathcal{H} = \mathbf{I} \cdot \mathbf{A} \cdot \mathbf{S} + \mu_{\mathrm{B}} \mathbf{B} \cdot \mathbf{g} \cdot \mathbf{S} - \mu_{\mathrm{n}} \mathbf{B} \cdot \mathbf{g}_{\mathrm{n}} \cdot \mathbf{I}, \tag{S3}$$

where g and A are the coupling tensors of the electronic Zeeman and hyperfine interactions, respectively, μ_B and μ_n are the electronic and nuclear spin magnetons. The nuclear Zeeman interaction \mathbf{g}_n tensor is considered to be isotropic with $g_n = 0.987$ for ¹⁷¹Yb³⁺ nuclear spin.

The first term is due to the hyperfine coupling between the electron and nuclear spin, where I is the nuclear spin operator. The second term describes the electronic Zeeman interaction, where μ_B is the Bohr magneton, and **B** is the applied magnetic field. The last term arises from the nuclear Zeeman interaction, where μ_n is the nuclear magneton and $\mathbf{g}_{\mathbf{n}}$ is the nuclear Zeeman tensor.

Due to the symmetry of the crystal field for the tetragonal S_4 site, the spin Hamiltonian can be simplified to

$$\mathcal{H} = A_{\perp}(S_x I_x + S_y I_y) + A_{\parallel} S_z I_z + \mu_{\rm B}(g_{\perp}(B_x S_x + B_y S_y) + g_{\parallel} B_z S_z) - \tag{S4}$$

$$-\mu_{\mathbf{n}}g_{\mathbf{n}}(B_xI_x + B_yI_y + B_zI_z),\tag{S5}$$

where A_{\perp} and g_{\perp} (A_{\parallel} and g_{\parallel}) are the components of the **A** and **g** tensors corresponding to directions perpendicular (parallel) to the c axis of the crystal, aligned with the z axis in the above expression.

At zero magnetic field, $\mathbf{B} = 0$, the zero field energy splittings are given by the hyperfine interaction $\mathbf{I} \cdot \mathbf{A} \cdot \mathbf{S}$ eigenvalues:

$$E_{1g} = (-A_{\parallel g} - 2A_{\perp g})/4, \qquad \qquad E_{1e,2e} = A_{\parallel e}/4, \qquad (S6)$$

$$E_{2g,3g} = A_{\parallel g}/4, \qquad \qquad E_{3e} = (-A_{\parallel e} - 2A_{\perp e})/4, \qquad (S7)$$

$$E_{4g} = (-A_{\parallel g} + 2A_{\perp g})/4, \qquad \qquad E_{4e} = (-A_{\parallel e} + 2A_{\perp e})/4. \tag{S8}$$

Denoting the electron spin states as $|\uparrow\rangle = |S_z = +1/2\rangle$, $|\downarrow\rangle = |S_z = -1/2\rangle$ and nuclear spin components as $|\uparrow\rangle =$ $|I_z = +1/2\rangle, |\psi\rangle = |I_z = -1/2\rangle$, the corresponding eigenstates at zero magnetic field can be written as

$$|1\rangle_{a} = (|\uparrow \Downarrow\rangle_{a} - |\downarrow \uparrow \rangle_{a})/\sqrt{2}, \qquad \qquad |1,2\rangle_{e} = |\uparrow \uparrow \rangle_{e}, |\downarrow \Downarrow \rangle_{e}, \qquad (S9)$$

$$|3\rangle_{e} = |\uparrow\uparrow\rangle_{e}, |\downarrow\downarrow\rangle_{e}, \qquad |3\rangle_{e} = (|\uparrow\downarrow\rangle_{e} + |\downarrow\uparrow\rangle_{e})/\sqrt{2}, \qquad (S10)$$

$$\begin{aligned} |1\rangle_{g} &= (|1\psi\rangle_{g} - |\psi|\rangle_{g})/\sqrt{2}, \\ |2,3\rangle_{g} &= |\uparrow\uparrow\rangle_{g}, |\downarrow\psi\rangle_{g}, \\ |4\rangle_{g} &= (|\uparrow\downarrow\rangle_{g} + |\downarrow\uparrow\rangle_{g})/\sqrt{2}, \\ |4\rangle_{e} &= (|\uparrow\downarrow\downarrow\rangle_{e} - |\downarrow\uparrow\rangle_{e})/\sqrt{2}. \end{aligned}$$
(S10)

12

Applying a strong magnetic field along the c-axis will purify the eigenstates through the Zeeman interaction such that

$$|1\rangle_g = |\downarrow \Uparrow \rangle_g \qquad \qquad |1\rangle_e = |\downarrow \Downarrow \rangle_e \,, \tag{S12}$$

$$2\rangle_q = \left|\downarrow\Downarrow\right\rangle_q, \qquad \qquad \left|2\rangle_e = \left|\downarrow\Uparrow\right\rangle_e, \qquad (S13)$$

$$\begin{aligned} |3\rangle_{g} &= |\uparrow \Downarrow \rangle_{g}, \\ |4\rangle_{g} &= |\uparrow \uparrow \rangle_{g}, \end{aligned} \qquad \begin{aligned} |3\rangle_{e} &= |\uparrow \uparrow \rangle_{e}, \\ |4\rangle_{e} &= |\uparrow \Downarrow \rangle_{e}. \end{aligned} \tag{S14}$$

 $|4\rangle_e = |\uparrow \Downarrow \rangle_e \,.$ (S15)

The states are numbered from lowest to highest energies for the ground and excited state manifolds.

Due to the high symmetry of the crystal field, the degeneracy at zero magnetic field is not completely removed, leading to Zeeman doublets in both the ground and excited states. The magnetic field sensitivity of the levels' energies, in this case, strongly depends on the electron-nuclear wavefunction. The first order sensitivity for state $|i\rangle$ can be estimated using $\langle i | \mu_{\rm B} \mathbf{B} \cdot \mathbf{g} \cdot \mathbf{S} - \mu_{\rm n} \mathbf{B} \cdot \mathbf{g}_{\rm n} \cdot \mathbf{I} | i \rangle$. Non-degenerate states $|1\rangle_g$, $|4\rangle_g$, and $|3\rangle_e$, $|4\rangle_e$ are insensitive to magnetic field fluctuations at zero magnetic field, since the average electron $\langle i | \mathbf{S} | i \rangle$ and nuclear $\langle i | \mathbf{I} | i \rangle$ spin moments are zero for their wavefunctions:

$$\langle i | \mu_{\rm B} \mathbf{B} \cdot \mathbf{g} \cdot \mathbf{S} - \mu_{\rm n} \mathbf{B} \cdot \mathbf{g}_{\rm n} \cdot \mathbf{I} | i \rangle = 0.$$
 (S16)

For the degenerate doublet states $|2,3\rangle_a$ and $|1,2\rangle_e$,

$$\langle i | \mu_{\rm B} \mathbf{B} \cdot \mathbf{g} \cdot \mathbf{S} - \mu_{\rm n} \mathbf{B} \cdot \mathbf{g}_{\rm n} \cdot \mathbf{I} | i \rangle =$$
(S17)

$$= \langle i | B_{\parallel}(\mu_{\rm B}g_{\parallel}S_z - \mu_{\rm n}g_{\rm n}I_z) | i \rangle =$$
(S18)

$$= B_{\parallel}(\mu_{\rm B}g_{\parallel} - \mu_{\rm n}g_{\rm n})/2, \tag{S19}$$

leading to a linear sensitivity term for the magnetic field fluctuations along the c axis B_{\parallel} .

This makes the $|1\rangle_q - |4\rangle_q$ and $|3\rangle_e - |4\rangle_e$ spin transitions as well as the optical transitions connecting $|1\rangle_q$, $|4\rangle_q$ and $|3\rangle_e, |4\rangle_e$ protected from the magnetic noise environment to first-order, a situation known as clock transitions.

We note that even if the spin levels $|i\rangle$, $|j\rangle$ are not sensitive to the change of the external magnetic field, the magnetic dipole of the $|i\rangle - |j\rangle$ transition is strong and is given by the dipole moment $\mu_{ij} = -\langle i | \mu_{\rm B} \mathbf{B}_{\rm ac} \cdot \mathbf{g} \cdot \mathbf{S} | j \rangle / |\mathbf{B}_{\rm ac}|$. The dipole moment strongly depends on the \mathbf{B}_{ac} magnetic field orientation. At zero magnetic field for the $|1\rangle_q - |4\rangle_q$ spin transition, the magnetic dipole of the transition is non-zero only when \mathbf{B}_{ac} is oriented along the c axis such that $\hat{\mu}_{1g-4g} = -\langle 1|_g \,\mu_{\rm B}g_{\parallel}S_z \,|4\rangle_g = -\mu_{\rm B}g_{\parallel}.$ For the transitions $|1\rangle_g - |2\rangle_g$ and $|4\rangle_g - |2\rangle_g$, the non-zero orientation of the ac magnetic field is along the *a* axis such that $\mu_{1g-2g} = -\langle 1|_g \,\mu_{\rm B}g_{\perp}(S_x + S_y) \,|2\rangle_g = -\sqrt{2}\mu_{\rm B}g_{\perp}.$ The same is true for transitions connecting to the $|3\rangle_a$ state.

Α. Spin-spin dynamics

The cross-relaxation processes between 171 Yb $^{3+}$ spins strongly affects the measured coherence properties both for optical and spin transitions. The rate of the flip-flop spin process can be written as [S13, S14],

$$R_{\rm ff} = \beta_{\rm ff}(g, B) \frac{n^2}{\Gamma_{\rm h}^{(s)} + \Gamma_{\rm inh}^{(s)}} \operatorname{sech}^2\left(\frac{\Delta E}{2k_{\rm B}T}\right),\tag{S20}$$

where $\beta_{\rm ff}$ is the spin-spin coupling parameter, $\Gamma_{\rm inh}^{(s)}$ ($\Gamma_{\rm h}^{(s)}$) is the inhomogeneous (homogeneous) spin linewidth, and n is the concentration of dopant ${}^{171}{\rm Yb}^{3+}$ ions. The flip-flop rate is strongly temperature and magnetic field dependent due to the change in probability for neighboring spin pairs to be antiparallel. The $R_{\rm ff}$ rate strongly depends on the magnetic spin properties such that $\beta_{\rm ff} \propto g^4$ in the case of an isotropic g tensor. To derive the expression for $\beta_{\rm ff}$ for a more general case that takes into account the anistotropic magnetic and hyperfine interactions, we consider the magnetic dipole interaction as a perturbation to the spin Hamiltonian. The resulting Hamiltonian for two identical spins S_1 and S_2 interacting through magnetic dipole-dipole interaction \mathcal{H}_{dd} is given by

$$\mathcal{H} = \mathcal{H}_1 + \mathcal{H}_2 + \mathcal{H}_{dd} = \mathbf{I}_1 \cdot \mathbf{A} \cdot \mathbf{S}_1 + \mu_B \mathbf{B} \cdot \mathbf{g} \cdot \mathbf{S}_1 - \mu_n \mathbf{B} \cdot \mathbf{g}_n \cdot \mathbf{I}_1 +$$
(S21)

$$+ \mathbf{I}_2 \cdot \mathbf{A} \cdot \mathbf{S}_2 + \mu_{\rm B} \mathbf{B} \cdot \mathbf{g} \cdot \mathbf{S}_2 - \mu_{\rm n} \mathbf{B} \cdot \mathbf{g}_{\rm n} \cdot \mathbf{I}_2 + \mathcal{H}_{\rm dd}, \qquad (S22)$$

where

$$\mathcal{H}_{\rm dd} = \frac{\mu_0}{4\pi} \mu_{\rm B}^2 |\vec{r}_{12}|^{-3} [(1-3l^2)g_{\perp}^2 S_{1x} S_{2x} + (1-3m^2)g_{\perp}^2 S_{1y} S_{2y} + (1-3n^2)g_{\parallel}^2 S_{1z} S_{2z} \tag{S23}$$

$$-3lmg_{\perp}^{2}(S_{1x}S_{2y} + S_{1y}S_{2x}) - 3lng_{\perp}g_{\parallel}(S_{1x}S_{2z} + S_{1z}S_{2x}) - 3mng_{\perp}g_{\parallel}(S_{1y}S_{2z} + S_{1z}S_{2y})],$$
(S24)

where [l, m, n] are the direction cosines of the vector \vec{r}_{12} connecting two spins 1 and 2. We consider the dipole-dipole interaction \mathcal{H}_{dd} as a perturbation to the Zeeman interaction allowing us to use the Fermi golden rule to calculate the cross relaxation rate. The flip-flop rate for the transition between spin states $|i\rangle$ and $|j\rangle$ is then proportional to

$$\beta_{\rm ff} = |\langle i_1, j_2 | \mathcal{H}_{\rm dd} | j_1, i_2 \rangle|^2.$$
(S25)

In the case of an anisotropic magnetic interaction, $\beta_{\rm ff}$ strongly depends on the external magnetic field orientation [S15], defined by the anisotropy of the g tensor. We consider the case of zero magnetic field, where $\beta_{\rm ff}$ depends on electron-nuclear spin wavefunctions due to the hyperfine interaction.

Let's consider the flip-flop process for the $|1\rangle_g - |4\rangle_g$ transition. In this case, since only $\langle 1|_g S_z |4\rangle_g$ is non zero, the expression for the flip-flop rate is simplified, such that

$$\beta_{\rm ff}(l,m,n) = \left(\frac{\mu_0}{4\pi}\right)^2 \frac{g_{\parallel}^4 \mu_{\rm B}^4 (l^2 + m^2 - 2n^2)^2}{32 |\vec{r}|^6} \tag{S26}$$

We assume that the spins are separated by the average distance r_{avg} , while their relative orientations in space are random. The integration over all the angles on a spherical surface $\int_{lmn} \beta_{\text{ff}}(l,m,n) dS$ then gives

$$\beta_{\rm ff} = \left(\frac{\mu_0}{4\pi}\right)^2 \frac{\pi g_{\parallel}^4 \mu_{\rm B}^4}{10|r_{\rm avg}|^4}.$$
(S27)

For the flip-flop process for either the $|1\rangle_g - |2\rangle_g$ or $|4\rangle_g - |2\rangle_g$ transition, or transitions involving $|3\rangle_g$, the S_z component is zero, leading to a flip-flop process depending only on g_{\perp}

$$\beta_{\rm ff}(l,m,n) = \left(\frac{\mu_0}{4\pi}\right)^2 \frac{g_\perp^4 \mu_{\rm B}^4 (l^2 + m^2 - 2n^2)^2}{128 |\vec{r}|^6},\tag{S28}$$

The integration then gives

$$\beta_{\rm ff} = \left(\frac{\mu_0}{4\pi}\right)^2 \frac{\pi g_{\perp}^4 \mu_{\rm B}^4}{40 |r_{\rm avg}|^4},\tag{S29}$$

We can see that the flip-flop rate is strongly dependent on electron-nuclear wavefunctions of the transition, making the flip-flop rate highly unequal. For example, for this CaWO₄ crystal, the flip-flop rate for the $|1\rangle_g - |4\rangle_g$ is $0.5g_{\perp}^4/g_{\parallel}^4 \approx 100$ times slower than for the $|1\rangle_g - |2\rangle_g$ and $|1\rangle_g - |3\rangle_g$ transitions.

For the given crystal structure the average distance between dopants can be estimated using

$$r_{\rm avg} = \left(\frac{V}{Zn}\right)^{1/3},\tag{S30}$$

where V is the volume of the crystalline unit cell, Z is the number of sites in the volume, and n is the occupation percentage of these sites. The tetragonal unit cell of CaWO₄ with dimension a = b = 0.5243 nm, c = 1.1371 nm gives a unit cell volume of V = 0.2795 nm³ with an ion density of 1.43×10^{22} cm⁻³.

The unit cell of CaWO₄ contains 4 Ca²⁺ ions, so that the average Ca²⁺ ion-ion distance is approximately $(V/Z)^{1/3} = 0.411$ nm. For an ¹⁷¹Yb³⁺:CaWO₄ crystal with ≈ 5 ppm at. doping concentration, only 0.0005% of the Ca²⁺ sites are occupied by ¹⁷¹Yb³⁺. The average distance between ¹⁷¹Yb³⁺ ions then is $(V/Zn)^{1/3} = 24.2$ nm.

B. Optical and spin decoherence

The observed coherence times for various optical pumping conditions allows us to estimate various contributions to optical and spin decoherence.

The optical coherence was measured using the $|4\rangle_{g}$ - $|4\rangle_{e}$ transition, which has zero sensitivity to magnetic field fluctuations in the first order. All other allowed optical transitions contain a degenerate doublet in the ground or excited state, making them more sensitive to magnetic field noise.

The optical coherence time was measured to be $T_2^{(o)} = 0.540$ ms after reshuffling the population to avoid any optical pumping, especially at low temperatures. The optical $T_2^{(o)}$ stays constant up to 3 K but starts to drop slowly as the

temperature is increased, e.g. at 4 K, $T_2^{(o)} = 0.2$ ms. The $T_2^{(o)}$ is strongly enhanced up to $T_2^{(o)} = 0.75$ ms after pumping all ¹⁷¹Yb³⁺ ions into the $|4\rangle_g$ state.

The effect of the optical pumping on the optical coherence suggests that the spin dynamics of 171 Yb³⁺ ions are limiting $T_2^{(o)}$ at temperature below 1 K. The spin-lattice relaxation is very low, and the effect from magnetic field noise should be small due to the clock condition, which further suggests that spin-spin dynamics are the main limiting factor. The flip-flop process can affect the $T_2^{(o)}$ time by limiting the population lifetime of the spin ground state of optically excited 171 Yb³⁺ ions. The lowest limit for the optical homogeneous linewidth can then be written as

$$\pi \Gamma_h^{(o)} = \frac{1}{2T_1} + \frac{1}{2} \sum_i R_{\text{ff}}^{4_g, i_g} + \frac{1}{2} \sum_i R_{\text{SLR}}^{4_g, i_g},$$
(S31)

where only population decay processes are taken into account, such as the excited state lifetime T_1 , the spin lattice relaxation rate $R_{\text{SLR}}^{4_g,i_g}$, and the flip-flop processes $R_{\text{ff}}^{4_g,i_g}$ on the $|4\rangle_g - |i\rangle_g$ transition, where $i \neq 4$. Half of the contribution to the measured homogeneous linewidth without optical pumping comes from the excited

Half of the contribution to the measured homogeneous linewidth without optical pumping comes from the excited state lifetime. The second half comes from the flip-flop rate dynamics with $R_{\rm ff} \approx 2.5 \times 10^3 \, {\rm s}^{-1}$. We expect that the flip-flop rate should be fast for the $|4\rangle_g - |2\rangle_g$ and $|4\rangle_g - |3\rangle_g$ transitions, and much slower for $|1\rangle_g - |4\rangle_g$ transition due to the electron-nuclear spin wavefunctions (see previous sections). Since there are two fast processes connecting $|4\rangle_g$ state, the flip-flop rate for each of them can be estimated as $R_{\rm ff}^{4_g,2_g} = R_{\rm ff}^{4_g,3_g} \approx 1.25 \times 10^3 \, {\rm s}^{-1}$.

A spin coherence time $T_2^{(s)}$ of 150 ms was measured for $|1\rangle_g - |4\rangle_g$ transition after pumping all the ¹⁷¹Yb³⁺ ions into $|1\rangle_g$ level. The limit for the spin homogeneous linewidth is

$$\pi \Gamma_h^{(s)} = \frac{1}{2} \sum_{i,j} R_{\rm ff}^{j_g, i_g} + \frac{1}{2} \sum_{i,j} R_{\rm SLR}^{j_g, i_g}, \qquad (S32)$$

when SLR and flip-flop processes can happen from both $|1\rangle_g$, $|4\rangle_g$ states such that in the summation j = 1, 4 and $i \neq j$. At 100 mK temperatures, the SLR rate is much slower than the measured decoherence (see Section 4.E), making its contribution negligible. When polarising the whole spin ensemble in the $|1\rangle_g$ state, some flip-flop processes are quenched, such that the $\Gamma_h^{(s)}$ is limited by

$$\pi \Gamma_h^{(s)} = \frac{1}{2} (R_{\rm ff}^{1_g, 4_g} + R_{\rm ff}^{4_g, 1_g}), \tag{S33}$$

corresponding to the flip-flop processes involving spins excited via the spin echo sequence on the $|1\rangle_g - |4\rangle_g$ transition. In our experiments, we manipulate only a small part of the optical inhomogeneous broadening around 1 MHz, exciting around 0.5% of the population. In this case, only the processes of flipping from $|4\rangle_a$ to $|1\rangle_a$ will contribute such that

$$\pi \Gamma_h^{(s)} = \frac{1}{2} R_{\rm ff}^{1_g, 4_g}.$$
 (S34)

This allows us to give the lower bound of $R_{\rm ff}^{1_g,4_g} = 13.3 \text{ s}^{-1}$ for the flip-flop process on the $|4\rangle_g - |1\rangle_g$ transition assuming the spin polarisation is perfect.

C. Electron paramagnetic resonance (EPR) measurements

CW-EPR measurements were performed using a Bruker EMX spectrometer operating in the X-band with microwave frequencies around 9.4 GHz. The spectrometer is equipped with a He-flow cryostat (ESR900) and a cryogen-free cooler (Bruker Stinger) going down to 7 K. The angular dependence of EPR with respect to the static field was measured using an automatic goniometer installed on the spectrometer. Angular measurements were done in two planes, one containing the c axis (denoted as the c - a plane) and one perpendicular to the c axis (a - b plane). The 0° angle in the c - a plane corresponds to the direction parallel to the c axis. The microwave power was set low (< 1 mW) to prevent the EPR signal from saturating. The field modulation was kept under 1 G to avoid distortion of the EPR lines due to over-modulation effects.

Angular scans of different EPR lines in the c-a and a-b planes are shown in FIG. S11. Several lines with different intensities were observed in the angular scans. We focused on extracting the lines forming doublets, which should come from the I = 1/2 ¹⁷¹Yb³⁺ isotope. The most intense line comes ¹⁷¹Yb³⁺ ions occupying the tetragonal S_4 site of Ca²⁺ ions and dominates the spectra of FIG. S11(a-b). It shows nearly no angular dependence in the a-b

plane orthogonal to the *c* axis in agreement with the symmetry of the spin Hamiltonian. The resulting parameters for *g* and *A* extracted from previous EPR measurements [S1, S7] explain perfectly the observed spectra. The spin Hamiltonian parameters are summarized in TABLE S5. The other lines which correspond to the Yb³⁺ isotopes with nuclear spin I = 0 are visible with around 5% of intensity with respect to the ¹⁷¹Yb³⁺ isotope (FIG. S12). Narrow spin resonance lines with widths of few a MHz have been measured, making it possible to couple to high-quality microwave resonators.

In addition to the tetragonal S_4 site, contributions from lower symmetry orthorhombic D_2 sites are clearly visible in the spectra but with much lower intensity (FIG. S12). These D_2 sites were previously observed in EPR studies [S1] and attributed to nearby charge compensation centers giving rise to an added asymmetry of the crystal field configuration at the Yb³⁺ site.

TABLE S5. Spin Hamiltonian parameters for the tetragonal S_4 site (ground ${}^2F_{7/2}(0)$ and excited ${}^2F_{5/2}(0)$ states manifolds) in ${}^{171}Yb^{3+}$:CaWO₄ including the g and A tensor parameters.

Site	n, ppm	g_\perp	g_{\parallel}	A_{\perp}, GHz	$A_{\parallel}, \mathrm{GHz}$
$S_4 \pmod{{}^2\mathrm{F}_{7/2}(0)}$	4.96	3.916	1.053	3.08187	-0.78905
$S_4 \;(\mathrm{exc}\;^2\mathbf{F}_{5/2}(0))$		1.293(1)	-1.446(1)	2.72	-2.87

FIG. S11. (color online) **EPR angular spectra**. EPR transitions for 171 Yb³⁺:CaWO₄ in 2 F_{7/2}(0) ground state measured as a function of the angle in the c-a and a-b planes for tetragonal site (a)-(b). Grey points: experimental data; lines: spin Hamiltonian model.

FIG. S12. (color online) EPR transitions for 171 Yb³⁺:CaWO₄ in the 2 F_{7/2}(0) ground state measured with a magnetic field orientation with a small angle with respect to the *a*-axis. The lines corresponding to the tetragonal S_4 site (peaking outside the graph) and the three orthorhombic D_2 sites for 171 Yb³⁺ ions are indicated, as well as the line corresponding to I = 0 Yb³⁺ isotopes. The second part of the S_4 doublet appears at 201 mT.

D. Concentration estimation

The EPR measurements were used to estimate the concentration of sites occupied by 171 Yb³⁺ ions in the CaWO₄ crystal with a nominal concentration of 20 ppm. For this, comparison with a previously characterised CaWO₄ sample was used by performing measurements under the same conditions. This gave 4.96 ppm concentration for the main tetragonal S_4 site from the nominal concentration of 20 ppm.

Around 37% of the nominal doping concentration is present in the crystal. This is significantly higher compared with a previous report on the distribution coefficient for CaWO₄ crystal, which for Yb³⁺ was estimated to be around 0.15-0.2 [S16]. Around 70% of the ions are located in the main tetragonal S_4 site. Charge compensation methods based on adding sodium (Na) or niobium (Nb) oxides during the crystal growth significantly increase the occupation probabilities, but at higher doping concentrations [S16]. These effects at lower doping concentrations and their effect on optical and spin properties still require investigation.

VI. STATE REPRESENTATIONS AND SELECTION RULES

In this section, we derive the optical transition selection rules and state assignment for the 171 Yb³⁺:CaWO₄ crystal. The main idea is to follow the group theory approach to explain the optical absorption spectra and optical branching ratios quantified in the previous section. We show that the symmetry of the crystal and the observed transition rules appropriately explain the observed behavior.

We write down the selection rules for the electric and magnetic dipole operators using the rules between irreducible representations. We then figure out the corresponding labels for the observed states in our system by measuring which optical transitions are observed in the crystal for different orientations of the light polarization relative to the crystal symmetry axes. We measured absorption with light polarisation along the c axis (π), perpendicular to the c axis (σ), and with light propagating along the c axis (α).

Yb³⁺ ions substitute Ca²⁺ ions in the sites with tetragonal S_4 point symmetry in the CaWO₄ crystal. However, previously, the crystal symmetry for rare-earth ions in scheelite crystals was described by D_{2d} symmetry due to a small distortion from D_{2d} to S_4 [S17]. The crystal field Hamiltonian for tetragonal symmetry can be written in terms of the Stevens operator equivalents as

$$H_{CF} = B_2^0 O_2^0 + B_4^0 O_2^0 + B_6^0 O_6^0 + B_4^4 O_2^4 + B_6^4 O_6^6,$$

where B_k^q (where $k = 2, 4, 6 |q| \le k$) are the crystal-field parameters. The character table for S_4 and D_{2d} symmetries are given in TABLE S6 [S18, S19].

The 4f¹³ configuration of Yb³⁺ consists of only two electronic multiplets: ${}^{2}F_{5/2}$ in the ground state and ${}^{2}F_{7/2}$ in the excited state. We then write the spin-orbit ${}^{2}F_{5/2}$ and ${}^{2}F_{7/2}$ multiplets in terms of irreducible representations of S_{4} and D_{2d} symmetry. We use the corresponding full-rotational group compatibility table (TABLE S7) for a free-ion for both the J = 7/2 and J = 5/2 levels [S20].

The ${}^{2}F_{7/2}$ and ${}^{2}F_{5/2}$ multiplets split into 4 and 3 doublets, respectively, corresponding to $\Gamma_{5,6}$ or $\Gamma_{7,8}$ irreps for S_4 or Γ_6 or Γ_7 for D_{2d} .

A. Ground state doublet ${}^{2}F_{7/2}(0)$

Previously, the first doublet of the ${}^{2}F_{7/2}$ multiplet was attributed to $\Gamma_{5,6}$ irrep for S_4 symmetry based on EPR measurements [S1]. Due to the S_4 (D_{2d}) site symmetry, nonzero crystal field parameters correspond to B_2^0 , B_4^0 , B_6^0 , B_4^4 and B_6^4 , strongly limiting the mixing between different $|J, M_J\rangle$ states. The wavefunction components $|J, M_J\rangle$ are mixed by B_4^4 and B_6^4 terms and are given by [S21]

$$|\Gamma_5\rangle = a |7/2, +5/2\rangle + b |7/2, -3/2\rangle, |\Gamma_6\rangle = a^* |7/2, -5/2\rangle + b^* |7/2, +3/2\rangle,$$

$$|\Gamma_7\rangle = c |7/2, -7/2\rangle + d |7/2, +1/2\rangle, |\Gamma_8\rangle = -c^* |7/2, 7/2\rangle - d^* |7/2, -1/2\rangle.$$

Based on these wavefunctions, one can calculate the g-factors of the various doublets represented by Γ_{\pm} irreps as

$$g_{\parallel} = 2g_J \left\langle \Gamma_+ | J_z | \Gamma_+ \right\rangle, g_\perp = g_J \left(\left\langle \Gamma_+ | J_x | \Gamma_- \right\rangle + \left\langle \Gamma_- | J_x | \Gamma_+ \right\rangle \right)$$

S_4		E	C_2	S_4	\bar{S}_4
A	Γ_1	+1	+1	+1	+1
B	Γ_2	+1	+1	-1	-1
	Γ_3	+1	-1	-i	-i
	Γ_4	+1	-1	i	i
	Γ_5	+1	i	$-\omega^3$	ω
	Γ_6	+1	-i	ω	$-\omega^3$
	Γ_7	+1	i	ω^3	-ω
	Γ_8	+1	-i	-ω	ω^3

TABLE S6. Character table for S_4 and D_{2d} symmetry, where $\omega = e^{i\pi/4}$.

D_{2d}		E	$2S_4$	C_2	$2C'_2$	$2\sigma_d$	R	$2RS_4$	RC_2	$2RC_2'$	$2R\sigma_d$
A_1	Γ_1	1	1	1	1	1	1	1	1	1	1
A_2	Γ_2	1	1	1	-1	-1	1	1	1	-1	-1
B_1	Γ_3	1	-1	1	1	-1	1	-1	1	1	-1
B_2	Γ_4	1	-1	1	-1	1	1	-1	1	-1	1
E	Γ_5	2	0	-2	0	0	2	0	-2	0	0
$D_{1/2}$	Γ_6	2	$\sqrt{2}$	0	0	0	-2	$-\sqrt{2}$	0	0	0
$_2S$	Γ_7	2	$-\sqrt{2}$	0	0	0	-2	$\sqrt{2}$	0	0	0

TABLE S7. Irreducible representations for S_4 and D_{2d} symmetry.

J	S_4	J	D_{2d}
1/2	$\Gamma_{7,8}$	1/2	Γ_7
5/2	$2\Gamma_{5,6} + \Gamma_{7,8}$	5/2	$2\Gamma_6 + \Gamma_7$
7/2	$2\Gamma_{5,6} + 2\Gamma_{7,8}$	7/2	$2\Gamma_6 + 2\Gamma_7$

with $g_J = 1 + (J(J+1) + S(S+1) - L(L+1))/(2J(J+1))$, such that $g_{\frac{5}{2}} = 6/7$ and $g_{\frac{7}{2}} = 8/7$ with L = 3 and S = 1/2, and

$$\langle J, M_J' | J_z | J, M_J \rangle = \delta_{M_J', M_J} M_J,$$

$$\langle J, M'_J | J_x | J, M_J \rangle = (\delta_{M'_J, M_J + 1} + \delta_{M_J, M'_J + 1}) \frac{1}{2} (J(J+1) - M_J M'_J)^{1/2}.$$

Following the results from [S21], we get the expressions for g_{\parallel} and g_{\perp} for $^2{\rm F}_{7/2}$

$$|\Gamma_{5,6}\rangle$$
: $g_{\parallel} = g_{7/2}(5|a|^2 - 3|b|^2), \ g_{\perp} = 2\sqrt{3}g_{7/2}(ab + a^*b^*),$

$$|\Gamma_{7,8}\rangle$$
: $g_{\parallel} = g_{7/2}(7|c|^2 - |d|^2), \ g_{\perp} = -2g_{7/2}(d^2 + d^{*2}),$

resulting in the following relations when Γ_5 (Γ_7) is above Γ_6 (Γ_8) in energy

$$|\Gamma_{5,6}\rangle : 4g_{\perp}^2 = -3g_{\parallel}^2 + 6g_{\frac{7}{2}}g_{\parallel} + 45g_{\frac{7}{2}}^2,$$

$$|\Gamma_{7,8}\rangle$$
 : $2g_{\perp} = -g_{\parallel} - 7g_{\frac{7}{2}}$.

When Γ_5 (Γ_7) is below Γ_6 (Γ_8) in energy giving $g_{\parallel} < 0$

$$|\Gamma_{5,6}\rangle$$
: $g_{\parallel} = g_{7/2}(-5|a|^2 + 3|b|^2), \ g_{\perp} = 2\sqrt{3}g_{\frac{7}{2}}(ab + a^*b^*),$

$$|\Gamma_{7,8}\rangle$$
: $g_{\parallel} = g_{7/2}(-7|c|^2 + |d|^2), \ g_{\perp} = -2g_{7/2}(d^2 + d^{*2}),$

and

$$\begin{split} |\Gamma_{5,6}\rangle \; : \; 4g_{\perp}^2 &= -3g_{\parallel}^2 - 6g_{\frac{7}{2}}g_{\parallel} + 45g_{\frac{7}{2}}^2 \\ \\ |\Gamma_{7,8}\rangle \; : \; 2g_{\perp} &= g_{\parallel} - 7g_{\frac{7}{2}}. \end{split}$$

In D_{2d} symmetry, Γ_6 and Γ_7 correspond to $\Gamma_{5,6}$ and $\Gamma_{7,8}$, respectively. These expressions are written for S_4 symmetry but are also valid for D_{2d} irreps. As derived previously [S1], the first expression for $|\Gamma_{5,6}\rangle$ explains well the experimental values $g_{\parallel} = 1.05$ and $g_{\parallel} = 3.92$ for the ground state ${}^2F_{7/2}$, with a = 0.700 and b = 0.714. So, we attribute the ground state doublet ${}^2F_{7/2}(0)$ to the $|\Gamma_{5,6}\rangle$ irreps in S_4 ($|\Gamma_6\rangle$ in D_{2d}).

B. Excited state doublet ${}^{2}F_{5/2}(0)$

For ${}^{2}F_{5/2}$, we get similar expressions. Since two $\Gamma_{5,6}$ and one $\Gamma_{7,8}$ are expected for J = 5/2 we can write

$$\begin{split} |\Gamma_5\rangle &= a \left| 5/2, +5/2 \right\rangle + b \left| 5/2, -3/2 \right\rangle, |\Gamma_6\rangle = -a^* \left| 5/2, -5/2 \right\rangle - b^* \left| 5/2, +3/2 \right\rangle, \\ & \left| \Gamma_7 \right\rangle = \left| 5/2, -1/2 \right\rangle, |\Gamma_8\rangle = \left| 5/2, +1/2 \right\rangle, \\ & \left| \Gamma_{5,6} \right\rangle: \ g_{\parallel} = g_{\frac{5}{2}} (5|a|^2 - 3|b|^2), \ g_{\perp} = -\sqrt{5} g_{\frac{5}{2}} (ab^* + ba^*), \end{split}$$

$$|\Gamma_{7,8}\rangle: g_{\parallel} = g_{5/2}, g_{\perp} = 3g_{5/2},$$

resulting in following relations for Γ_5 (Γ_7) above Γ_6 (Γ_8) in energy

$$|\Gamma_{5,6}\rangle : 16g_{\perp}^2 = -5g_{\parallel}^2 + 10g_{\frac{5}{2}}g_{\parallel} + 75g_{\frac{5}{2}}^2,$$

$$|\Gamma_{7,8}\rangle : g_{\perp} = -3g_{\parallel}.$$

When Γ_5 (Γ_7) is below Γ_6 (Γ_8) in energy, $g_{\parallel} < 0$, and

$$|\Gamma_{5,6}\rangle: g_{\parallel} = g_{\frac{5}{2}}(-5|a|^2 + 3|b|^2), \ g_{\perp} = -\sqrt{5}g_{\frac{5}{2}}(ab^* + ba^*),$$

$$|\Gamma_{7,8}\rangle: g_{\parallel} = g_{5/2}, g_{\perp} = 3g_{5/2},$$

resulting in following relations

$$|\Gamma_{5,6}\rangle : 16g_{\perp}^2 = -5g_{\parallel}^2 - 10g_{\frac{5}{2}}g_{\parallel} + 75g_{\frac{5}{2}}^2,$$

$$|\Gamma_{7,8}\rangle$$
 : $g_{\perp} = 3g_{\parallel}$

Again, in D_{2d} symmetry, the situation is equivalent with Γ_6 and Γ_7 corresponding to $\Gamma_{5,6}$ and $\Gamma_{7,8}$, respectively. Previously, the values for the lowest Kramers doublet in the ${}^2F_{5/2}$ excited state were measured to be $g_{\perp} = 1.5$ and $g_{\parallel} = -1.2$ [S4]. For $B \perp c$, this gives a g-factor $g_{\text{eff}} = 2.4$ and 5.2, and for $B \parallel c g_{\text{eff}} = 0.15$ and 2.23. They also concluded that the lowest doublet has a $\Gamma_{5,6}$ irrep based on polarisation properties of the different crystal field levels absorption spectra [S4]. A negative g_{\parallel} value was assumed such that the expression for g-factors is then

$$|\Gamma_{5,6}\rangle : 16g_{\perp}^2 = -5g_{\parallel}^2 - 10g_{\frac{5}{2}}g_{\parallel} + 75g_{\frac{5}{2}}^2,$$

such that for $g_{\parallel} = -1.44$ observed in this work, it predicts $g_{\perp}^{th} = 1.42$, while $g_{\perp} = 1.29$ was measured. The deviation can come from the J = 7/2 mixing to the excited state wavefunction.

C. Effect of J mixing

The effect of J mixing with J = 7/2 in the can be derived assuming wavefunctions

$$\begin{aligned} |\Gamma_5\rangle &= a \left| 5/2, +5/2 \right\rangle + b \left| 5/2, -3/2 \right\rangle + c \left| 7/2, +5/2 \right\rangle + d \left| 7/2, -3/2 \right\rangle, \\ |\Gamma_6\rangle &= -a^* \left| 5/2, -5/2 \right\rangle - b^* \left| 5/2, +3/2 \right\rangle + c^* \left| 5/2, -5/2 \right\rangle + d^* \left| 5/2, +3/2 \right\rangle. \end{aligned}$$

Following the derivation from [S10, S21], the expressions of g_{\parallel} and g_{\perp} are

$$g_{\parallel} = g_{\frac{5}{2}}(5|a|^2 - 3|b|^2) - \frac{2\sqrt{6}}{7}(a^*c + ac^*) - \frac{2\sqrt{10}}{7}(b^*d + bd^*) + g_{\frac{7}{2}}(5|c|^2 - 3|d|^2),$$
$$g_{\perp} = \left|-2\sqrt{5}g_{\frac{5}{2}}ab - \frac{2\sqrt{30}}{7}bc - \frac{2\sqrt{2}}{7}ad + 4\sqrt{3}g_{\frac{7}{2}}cd\right|.$$

The observed g_{\parallel} and g_{\perp} values for the excited state can be explained with the mixing of R = 4%, where $R = (|c|^2 + |d|^2)/(|a|^2 + |b|^2)$ is the ratio between two J components of the wavefunction.

D. Selection rules

We check the set of irreps for each multiplet ${}^{2}F_{7/2}(0)$ and ${}^{2}F_{5/2}(0)$ using the observed polarisation properties. From the measured optical absorption, we got a maximum absorption for the α $(k \parallel c)$ and σ $(E \perp c)$ polarisations, while the π polarisation gave a 7 times lower absorption. We then calculate the selection rules between different states. For this, we use the multiplication table for S_4 and D_{2d} symmetries (TABLE S9 and TABLE S10) to get the transition rules between Γ_i and Γ_j , and we check if electric or magnetic dipoles (ED and MD) connect them using the corresponding table (TABLE S8) [S20].

The calculated selection rules between the crystal field levels are shown in TABLE S8. We see that electric and magnetic dipoles can explain the different line polarisations, making it difficult to decide on the dipole nature and how to connect irreps. Moreover, both electric and magnetic dipoles are expected to appear in the measured spectra since $\Delta J = \pm 1$, suggesting that additional analysis involving the nuclear spin states is needed.

We add that the nuclear spin 1/2 has the irrep $\Gamma_{7,8}$ according to TABLE S7. Using the multiplication table, the resulting irreps with the nuclear spin for S_4 are given by

$$\Gamma_{5,6} \times \Gamma_{7,8} = 2\Gamma_2 + \Gamma_3 + \Gamma_4, \tag{S35}$$

$$\Gamma_{7,8} \times \Gamma_{7,8} = 2\Gamma_1 + \Gamma_3 + \Gamma_4, \tag{S36}$$

while for D_{2d}

$$\Gamma_6 \times \Gamma_7 = \Gamma_3 + \Gamma_4 + \Gamma_5, \tag{S37}$$

$$\Gamma_7 \times \Gamma_7 = \Gamma_1 + \Gamma_2 + \Gamma_5. \tag{S38}$$

Introducing the nuclear spin into the ground and excited states splits them into three levels, where $\Gamma_{3,4}$ for S_4 (Γ_5 for D_{2d}) correspond to doubly degenerate energy levels in each manifold. This allows us to get the transition selection rules between all the states. Using electric and magnetic transition dipole moments (ED and MD) shown in TABLE S8, we get transition rules for each choice of irreps between the ground and excited manifolds for S_4 (TABLE S12) and D_{2d} (TABLE S13).

Comparing the observed (TABLE S11) and predicted transition rules for S_4 (TABLE S12) and D_{2d} (TABLE S13), we make several observations:

- The measured transition rules for α polarisation are well explained for both symmetries, although they do not show any difference difference depending on the choice of the dipole and the irrep.
- The π polarisation measurements, for which absorption is 7 times lower, can only be explained by adding MD transitions. This is the case for both symmetries. When assuming that the irrep for ground and excited states are different (left TABLE S12 and TABLE S13), the spectra are expected to have more ED transitions, which are not experimentally observed. When assuming the irrep is the same between the ground and excited state (right TABLE S12 and TABLE S13), only one ED-allowed π transition does not appear in the observed spectra $|2,3\rangle_g |1,2\rangle_e$. While not excluding the opposite, this suggests that the irrep stays the same for ground and excited states. This is true for both symmetries.

• For σ polarisation, the situation is different. The absorption for the D and E lines with σ polarisation can be explained only using MD with the right Tables when assuming that the irrep does not change. This is true for both symmetries. For S_4 symmetry, the absorption for MD-allowed $|1\rangle_g - |4\rangle_e$ and $|4\rangle_g - |3\rangle_e \sigma$ transitions are theoretically allowed, but not experimentally observed. However, for D_{2d} symmetry, it is possible to find an attribution of irreps, where these transitions are forbidden, and D and E lines are still well explained. This suggests that D_{2d} symmetry fits better to explain the spectra.

The predicted transition rules, in general, explain the observed absorption spectra satisfactorily. When assuming D_{2d} symmetry and that the irrep does not change between two manifolds (right table in TABLE S13), the predicted transition rules can explain the observed absorption spectra, with only a single exception of an ED-allowed π transition not appearing in the spectra.

EPR measurements of g factors do not contradict the choice of D_{2d} symmetry, suggesting that the ground and excited state manifolds have Γ_6 irreps. The extracted hyperfine A-tensor has $A_{\perp} = -2.72$ GHz and $A_{\parallel} = -2.87$ GHz with the ratio between the two elements close to 1.

 S_4 $\Gamma_{5,6}$ $\Gamma_{7,8}$ Γ_6 Γ_7 D_{2d} $\alpha, \sigma (\alpha, \sigma, \pi)$ $\alpha, \sigma (\alpha, \sigma, \pi)$ $\alpha, \sigma, \pi (\alpha, \pi)$ $\Gamma_{5.6}$ $\alpha, \sigma, \pi (\alpha, \pi)$ Γ_6 $\Gamma_{7,8}$ $\alpha, \sigma, \pi (\alpha, \pi)$ $\alpha, \sigma (\alpha, \sigma, \pi)$ Γ_7 $\alpha, \sigma, \pi (\alpha, \pi)$ $\alpha, \sigma (\alpha, \sigma, \pi)$ Γ_4 D_{2d} Γ_1 Γ_2 Γ_3 Γ_5 S_4 Γ_1 - (-) - (-) π (-) Γ_1 Γ_2 $\Gamma_{3,4}$ - (**o**) $\alpha, \sigma (\alpha, \pi)$ Γ_1 - (**o**) $\alpha, \sigma (\alpha, \pi)$ - (**o**) π (-) Γ_2 - (-) π (-) - (-) $\alpha, \sigma (\alpha, \pi)$ - (-) Γ_2 π (-) - (**o**) $\alpha, \sigma (\alpha, \pi)$ Γ_3 π (-) - (-) - (**o**) $\alpha, \sigma (\alpha, \pi)$ - (**o**) - (-) $\Gamma_{3,4}$ $\alpha, \sigma (\alpha, \pi)$ $\alpha, \sigma (\alpha, \pi)$ π (σ) Γ_4 π (-) - (-) $\alpha, \sigma (\alpha, \pi)$ Γ_5 $\alpha, \sigma (\alpha, \pi)$ $\alpha, \sigma (\alpha, \pi)$ $\alpha, \sigma (\alpha, \pi)$ $\alpha, \sigma (\alpha, \pi)$ π (σ)

TABLE S8. Selection rules in S_4 (left) and D_{2d} (right) symmetry for electric and magnetic dipoles (red).

TABLE S9. Multiplication table for S_4 symmetry [S18].

Γ_1	Γ_2	Γ_3	Γ_4	Γ_5	Γ_6	Γ_7	Γ_8	
Γ_1	Γ_2	Γ_3	Γ_4	Γ_5	Γ_6	Γ_7	Γ_8	Γ_1
	Γ_1	Γ_4	Γ_3	Γ_7	Γ_8	Γ_5	Γ_6	Γ_2
		Γ_2	Γ_1	Γ_8	Γ_5	Γ_6	Γ_7	Γ_3
			Γ_2	Γ_6	Γ_7	Γ_8	Γ_5	Γ_4
				Γ_3	Γ_1	Γ_4	Γ_2	Γ_5
					Γ_4	Γ_2	Γ_3	Γ_6
						Γ_3	Γ_1	Γ_7
							Γ_4	Γ_8

		ГАВІ	LE SI	0. Multiplication tal	ble for D_{2d} sym	metry [S18].	
Γ_1	Γ_2	Γ_3	Γ_4	Γ_5	Γ_6	Γ_7	
Γ_1	Γ_2	Γ_3	Γ_4	Γ_5	Γ_6	Γ_7	Γ_1
	Γ_1	Γ_4	Γ_3	Γ_5	Γ_6	Γ_7	Γ_2
		Γ_1	Γ_2	Γ_5	Γ_7	Γ_6	Γ_3
			Γ_1	Γ_5	Γ_7	Γ_6	Γ_4
				$\Gamma_1 + \Gamma_2 + \Gamma_3 + \Gamma_4$	$\Gamma_6 + \Gamma_7$	$\Gamma_6 + \Gamma_7$	Γ_5
					$\Gamma_1 + \Gamma_2 + \Gamma_5$	$\Gamma_3 + \Gamma_4 + \Gamma_5$	Γ_6
						$\Gamma_1 + \Gamma_2 + \Gamma_5$	Γ_7

TABLE S11. Observed selection rules for optical absorption between different hyperfine levels in ground ${}^{2}F_{7/2}(0)$ and ${}^{2}F_{5/2}(0)$ excited states.

	$\left 1,2\right\rangle_{e}$	$ 3\rangle_e$	$ 4\rangle_e$
$\langle 1 _g$	$lpha,\sigma,\pi$	σ	-
$\langle 2,3 _g$	σ	$lpha,\sigma,\pi$	α,σ,π
$\langle 4 _e$	$lpha,\sigma,\pi$	-	σ

TABLE S12. Selection rules for optical transitions between different hyperfine levels in ground and excited states for electric (black) and magnetic (red) dipoles for S_4 symmetry. Left: ground and excited states are assumed to have $\Gamma_{5,6}(\Gamma_{7,8})$ and $\Gamma_{7,8}(\Gamma_{5,6})$ irreps, respectively. Right: ground and excited states are assumed to have $\Gamma_{5,6}(\Gamma_{7,8})$ and $\Gamma_{5,6}(\Gamma_{7,8})$ irreps, respectively.

	$\left 1,2\right\rangle_{e}\left(\Gamma_{3,4}\right)$	$\left 3\right\rangle_{e}\left(\Gamma_{1}\right)$	$\left 4\right\rangle_{e}\left(\Gamma_{1}\right)$		$\left 1,2\right\rangle_{e}\left(\Gamma_{3,4}\right)$	$\left 3\right\rangle_{e}\left(\Gamma_{2}\right)$	$\left 4\right\rangle_{e}\left(\Gamma_{2}\right)$
$\left\langle 1\right _{g}\left(\Gamma_{2} ight)$	$\alpha, \sigma (\alpha, \pi)$	π (-)	π (-)	$\left\langle 1\right _{g}\left(\Gamma_{2} ight)$	$\alpha, \sigma (\alpha, \pi)$	- (o)	$-(\sigma)$
$\left\langle 2,3\right _{g}\left(\Gamma_{3,4}\right)$	π (σ)	$\alpha, \sigma (\alpha, \pi)$	$\alpha, \sigma (\alpha, \pi)$	$\left\langle 2,3\right _{g}\left(\Gamma_{3,4} ight)$	π (σ)	$\alpha, \sigma (\alpha, \pi)$	$\alpha, \sigma (\alpha, \pi)$
$\left\langle 4\right _{e}\left(\Gamma_{2}\right)$	$\alpha, \sigma (\alpha, \pi)$	π (-)	π (-)	$\left\langle 4\right _{e}\left(\Gamma_{2}\right)$	$\alpha, \sigma (\alpha, \pi)$	$-(\sigma)$	$-(\sigma)$

TABLE S13. Selection rules for optical transitions between different hyperfine levels in ground and excited states for electric (black) and magnetic (red) dipoles for D_{2d} symmetry. Left: ground state is assumed to be $\Gamma_6(\Gamma_7)$ and excited state $\Gamma_7(\Gamma_6)$ irreps. Right: ground state is assumed to be $\Gamma_7(\Gamma_6)$ and excited state $\Gamma_7(\Gamma_6)$ irreps.

	$\left 1,2\right\rangle_{e}\left(\Gamma_{5}\right)$	$\left 3\right\rangle_{e}\left(\Gamma_{2}\right)$	$\left 4\right\rangle_{e}\left(\Gamma_{1}\right)$		$\left 1,2\right\rangle_{e}\left(\Gamma_{5}\right)$	$\left 3\right\rangle_{e}\left(\Gamma_{4}\right)$	$\left 4\right\rangle_{e}\left(\Gamma_{3}\right)$
$\left\langle 1\right _{g}\left(\Gamma_{3} ight)$	$\alpha, \sigma (\alpha, \pi)$	π (-)	- (-)	$\left\langle 1\right _{g}\left(\Gamma_{3} ight)$	$lpha,\sigma\;(oldsymbollpha,\pi\;)$	- (o)	- (-)
$\left\langle 2,3\right _{g}\left(\Gamma_{5} ight)$	π (σ)	$\alpha, \sigma (\alpha, \pi)$	$\alpha, \sigma \ (\alpha, \pi)$	$\left\langle 2,3\right _{g}\left(\Gamma_{5} ight)$	π (σ)	$\alpha, \sigma (\alpha, \pi)$	$\alpha, \sigma (\alpha, \pi)$
$\left\langle 4\right _{e}\left(\Gamma_{4}\right)$	$\alpha, \sigma (\alpha, \pi)$	- (-)	π (-)	$\left\langle 4\right _{e}\left(\Gamma_{4}\right)$	$\alpha, \sigma (\alpha, \pi)$	- (-)	- (o)

- [S1] U. Ranon and V. Volterra, Phys. Rev. **134**, A1483 (1964).
- [S2] E. Billaud, L. Balembois, J. Travesedo, M. Le Dantec, M. Rančić, E. Albertinale, R. Truong, S. Bertaina, T. Chanelière, P. Goldner, D. Estève, D. Vion, E. Flurin, and P. Bertet, Physical Review Research 7 (2025).
- [S3] R. Pappalardo and D. Wood, Journal of Molecular Spectroscopy 10, 81–110 (1963).
- [S4] G. R. Jones, The Journal of Chemical Physics 47, 4347–4355 (1967).
- [S5] S. Welinski, A. Ferrier, M. Afzelius, and P. Goldner, Phys. Rev. B 94, 155116 (2016).
- [S6] J. Nemarich and W. Viehmann, Journal of Physics and Chemistry of Solids 29, 57–62 (1968).
- [S7] R. M. Rakhmatullin, I. N. Kurkin, G. V. Mamin, S. B. Orlinskii, M. R. Gafurov, E. I. Baibekov, B. Z. Malkin, S. Gambarelli, S. Bertaina, and B. Barbara, Phys. Rev. B 79, 172408 (2009).
- [S8] N. Kukharchyk, D. Sholokhov, O. Morozov, S. L. Korableva, A. A. Kalachev, and P. A. Bushev, Optics Express 28, 29166 (2020).
- [S9] J. M. Baker and N. C. Ford, Physical Review 136, A1692–A1701 (1964).
- [S10] A. Abragam and B. Bleaney, *Electron Paramagnetic Resonance of Transition Ions*, International series of monographs on physics (Clarendon P., 1970).
- [S11] F. Chiossi, E. Lafitte-Houssat, A. Ferrier, S. Welinski, L. Morvan, P. Berger, D. Serrano, M. Afzelius, and P. Goldner, Phys. Rev. B 109, 094114 (2024).
- [S12] M. Rančić, M. P. Hedges, R. L. Ahlefeldt, and M. J. Sellars, Nature Physics 14, 50–54 (2017).
- [S13] A. M. Portis, Phys. Rev. **104**, 584 (1956).
- [S14] T. Böttger, Y. Sun, C. W. Thiel, and R. L. Cone, Phys. Rev. B 74, 075107 (2006).
- [S15] E. Z. Cruzeiro, A. Tiranov, I. Usmani, C. Laplane, J. Lavoie, A. Ferrier, P. Goldner, N. Gisin, and M. Afzelius, Phys. Rev. B 95, 205119 (2017).
- [S16] K. Nassau and G. Loiacono, Journal of Physics and Chemistry of Solids 24, 1503–1510 (1963).
- [S17] I. Trabelsi, M. Dammak, R. Maâlej, and M. Kamoun, Physica B: Condensed Matter 406, 315–318 (2011).
- [S18] G. F. Koster, J. O. Dimmock, R. G. Wheeler, and H. Statz, *Properties of the 32 Point Groups* (MIT Press (Cambridge, Massachusetts), 1963).
- [S19] R. C. Powell, Symmetry, Group Theory, and the Physical Properties of Crystals (Springer New York, 2010).
- [S20] C. Görller-Walrand and K. Binnemans, Handbook on The Physics and Chemistry of Rare Earths 23, 121 (1996).
- [S21] J. P. Sattler and J. Nemarich, Phys. Rev. B 1, 4249 (1970)