

Spin-triplet superconductivity in quasi-one dimension

Mahito Kohmoto and Masatoshi Sato

Institute for Solid State Physics, University of Tokyo, 7-22-1 Roppongi, Minato-ku, Tokyo, Japan

We consider a system with electron-phonon interaction, antiferromagnetic fluctuations and disconnected open Fermi surfaces. The existence of odd-parity superconductivity in this circumstance is shown for the first time. If it is applied to the quasi-one-dimensional systems like the organic conductors (TMTSF)₂X we obtain spin-triplet superconductivity with nodeless gap. Our result is also valid in higher dimensions(2d and 3d).

PACS numbers: 74, 74.25-q, 74.25.Dw, 74.62.-c

In recent years the signs for unconventional superconductivity in many compounds have been accumulated. Examples include high T_c superconductors, heavy fermions, organic conductors, Sr₂RuO₄, etc. The common features of those compounds are quasi-low dimensionality and proximity of antiferromagnetic(AF) order.

Here we consider seemingly the simplest quasi-one-dimensional systems which are realized in (TMTSF)₂X family where X= PF₆, AsF₆, SbF₆, ClO₄, etc.(Bechgaard salts). At ambient pressure, most of these extremely anisotropic compounds undergo a metal-insulator transition at low temperature and have a spin-density-wave(SDW) fundamental state. Under moderate pressure, the SDW instability is suppressed and replaced by a superconducting transition at a critical temperature of order of 1K [1]. (One exception to this is (TMTSF)₂ClO₄ which is superconducting at ambient pressure.) Thus these compounds may be characterized by competition between superconducting and SDW ground states [2].

As for the gap symmetry, Takigawa et al. [3] measured nuclear relaxation rate of proton in (TMTSF)₂ClO₄. Their results show unconventional superconductivity(absence of coherence peak) and the existence of nodes. However their measurement is restricted to $T > 0.5T_c$ and the existence of nodes are not yet conclusive. More recently, Belin and Behnia [4] showed some evidences for nodeless gap by thermal conductivity measurement. Also experiments on (TMTSF)₂ClO₄ and (TMTSF)₂PF₆ show that H_{c2} for $\vec{B} \parallel \vec{a}$ and $\vec{B} \parallel \vec{b}$ far exceed the Pauli-limiting field $B_P \sim \Delta_0/(\sqrt{2})\mu_B \sim 2$ Tesla for Bechgaard salts, where Δ_0 is the superconducting order parameter at $T = 0$ and μ_B is the Bohrmagneton [5,6]. This suggests spin-triplet superconductivity. Maki et al. studied theoretically impurity effects and vortex states on these compounds [7].

In this paper we consider AF magnetic coupling and electron-phonon interaction under open disconnected Fermi surfaces. The spin-triplet superconductivity is possible under electron-phonon interaction and AF magnetic coupling [8]. We assume that AF fluctuation is not strong enough to give SDW gap. We shall show the existence of spin-triplet superconductivity in this circumstance for the first time. Our result is also applicable to higher dimensions(2d and 3d).

– *Open disconnected Fermi surface*

The Fermi surface of the system we consider is quasi-one-dimensional and consists of two separated parts, which are $(k_F)_x \sim c > 0$ and $(k_F)_x \sim -c$. (c is a constant.) It is also supposed to be symmetric under parity transformation $k \rightarrow -k$. This type of Fermi surface is realized in (TMTSF)₂X. The non-interacting part of the Hamiltonian of (TMTSF)₂X is often written

$$E = -2t_a \cos(k_x a) - 2t_b \cos(k_y b). \quad (1)$$

Here the ratio of t_a and t_b is about 10:1.

We take two interactions between electrons: one comes from electron-phonon coupling, the other comes from AF fluctuations.

– *Phonon-mediated interaction*

It is written

$$H_{\text{int}}^{\text{ph}} = - \sum_{kk'q} \sum_{\alpha\beta} f(q) a_{k+q,\alpha}^\dagger a_{k,\alpha} a_{k'-q,\beta}^\dagger a_{k',\beta}, \quad (2)$$

where a and a^\dagger are the usual fermion operators, α and β represent spin orientations and $f(q) > 0$ has a peak at $q = 0$. We assume $f(q) = f(-q)$. If one considers pairing interaction between k and $-k$, (2) reduces to

$$H_{\text{int}}^{\text{ph}} = -\frac{1}{2} \sum_{k,q} f(q) \left(\phi_0^\dagger(k+q) \phi_0(k) + \vec{\phi}^\dagger(k+q) \cdot \vec{\phi}(k) \right), \quad (3)$$

where

$$\phi_0(k) = a_{k,\alpha} (\sigma_2)_{\alpha,\beta} a_{-k,\beta}, \quad (4)$$

$$\vec{\phi}(k) = a_{k,\alpha} (\sigma_2 \vec{\sigma})_{\alpha,\beta} a_{-k,\beta}. \quad (5)$$

Here $\phi_0(k)$ is the spin-singlet pairing and $\vec{\phi}(k)$ is the spin-triplet one:

$$a_{k,\alpha} a_{-k,\beta} = -\frac{1}{2} (\sigma_2)_{\alpha\beta} \phi_0(k) + \frac{1}{2} (\vec{\sigma} \sigma_2)_{\alpha\beta} \cdot \vec{\phi}(k). \quad (6)$$

Since $f(q)$ has a peak at $q = 0$, this interaction is approximated by

$$\begin{aligned} H_{\text{int}}^{\text{ph}} &= -\frac{1}{2} \sum_k f(0) \left(\phi_0^\dagger(k) \phi_0(k) + \vec{\phi}^\dagger(k) \cdot \vec{\phi}(k) \right) \\ &= - \sum_{k_x > 0} f(0) \left(\phi_0^\dagger(k) \phi_0(k) + \vec{\phi}^\dagger(k) \cdot \vec{\phi}(k) \right). \end{aligned} \quad (7)$$

–Interaction due to AF fluctuations

It is written

$$H_{\text{int}}^{\text{AF}} = - \sum_{kk'q} \sum_{\alpha\beta\gamma\delta} J(q) \vec{\sigma}_{\alpha\beta} \cdot \vec{\sigma}_{\gamma\delta} a_{k+q,\alpha}^\dagger a_{k,\beta} a_{k'-q,\gamma}^\dagger a_{k',\delta}, \quad (8)$$

where $J(q) > 0$ represents interaction due to AF fluctuations and has a peak value at a nesting vector $q = \pm Q$. The nesting vector Q connects the two separated Fermi surfaces: $Q_x \sim 2c$. We assume $J(q) = J(-q)$. A similar analysis to above leads to

$$H_{\text{int}}^{\text{AF}} = \frac{1}{2} \sum_{k,q} J(q) \left(3\phi_0^\dagger(k+q)\phi_0(k) - \vec{\phi}^\dagger(k+q) \cdot \vec{\phi}(k) \right), \quad (9)$$

and this interaction is approximated by

$$H_{\text{int}}^{\text{AF}} = \frac{1}{2} \sum_k J(Q) \left(3\phi_0^\dagger(k+Q)\phi_0(k) - \vec{\phi}^\dagger(k+Q) \cdot \vec{\phi}(k) \right) + \frac{1}{2} \sum_k J(-Q) \left(3\phi_0^\dagger(k-Q)\phi_0(k) - \vec{\phi}^\dagger(k-Q) \cdot \vec{\phi}(k) \right). \quad (10)$$

For fermions on the Fermi surface, this becomes

$$H_{\text{int}}^{\text{AF}} = \frac{1}{2} \sum_{k_x \sim -c} J(Q) \left(3\phi_0^\dagger(k+Q)\phi_0(k) - \vec{\phi}^\dagger(k+Q) \cdot \vec{\phi}(k) \right) + \frac{1}{2} \sum_{k_x \sim c} J(-Q) \left(3\phi_0^\dagger(k-Q)\phi_0(k) - \vec{\phi}^\dagger(k-Q) \cdot \vec{\phi}(k) \right) = \sum_{k_x, k'_x \sim c} J(Q) \left(3\phi_0^\dagger(k')\phi_0(k) + \vec{\phi}^\dagger(k') \cdot \vec{\phi}(k) \right). \quad (11)$$

Here k' satisfies $k' = Q - k$.

–Spin-triplet superconductivity

Equation(7) shows that the phonon-mediated interaction of spin-triplet pairing has the same magnitude as that of spin-singlet one. In many systems, however, only the spin-singlet superconductivity is realized. This is because the Fermi surfaces of usual matters are connected. In a system of connected Fermi surface, the requirement of parity and continuity does not admit the constant spin-triplet gap. Therefore, the s-wave superconductivity is favored from the kinematic reason.

The quasi-one-dimensional system we consider, however, has disconnected Fermi surfaces, so it admits constant spin-triplet gap: $\vec{d}|_{k_x \sim c} = -\vec{d}|_{k_x \sim -c} = \text{const.}$ * Therefore, there is no reason to prefer s-wave superconductivity. From (11), the interaction due to AF fluctuation disturbs the spin-singlet superconductivity more

than the spin-triplet one, so the spin-triplet superconductivity is realized. This spin-triplet gap is nodeless.

–BCS analysis

Finally, we apply the BCS weak coupling theory. Since T_c of (TMTSF)₂X is rather low, one can expect that the strong coupling corrections do not change our results qualitatively. For the sake of simplicity, the cutoffs of the phonon-mediated interaction and AF one are taken to be same and denoted by $\hbar\omega_D$. We approximate the spin-singlet gap by

$$\psi|_{k_x \sim c} = \psi|_{k_x \sim -c} = \text{const.}, \quad (12)$$

and the spin-triplet gap by

$$\vec{d}|_{k_x \sim c} = -\vec{d}|_{k_x \sim -c} = \text{const.}. \quad (13)$$

If we denote the density of states on the Fermi surface as $N(k_F)$, the critical temperature of the spin-singlet superconductivity becomes [9]

$$T_c^{\text{even}} = 1.13\hbar\omega_D e^{1/\{N(k_F)V^{\text{even}}\}}, \quad (14)$$

where

$$V^{\text{even}} = -f(0) + 3J(Q), \quad (15)$$

and that of spin-triplet becomes

$$T_c^{\text{odd}} = 1.13\hbar\omega_D e^{1/\{N(k_F)V^{\text{odd}}\}}, \quad (16)$$

where

$$V^{\text{odd}} = -f(0) + J(Q). \quad (17)$$

From (15) and (17), the condition $V^{\text{odd}} < V^{\text{even}}$ is always satisfied. Thus $T_c^{\text{odd}} > T_c^{\text{even}}$ and spin-triplet superconductivity is present if $V^{\text{odd}} = -f(0) + J(Q) < 0$. This simple result show that there is no superconductivity if AF fluctuations dominate and we have spin-triplet superconductivity if phonon-mediated interaction dominates. Since $\vec{d}(k)$ is an odd function, the gaps at $(k_F)_x = \pm c$ have opposite signs and there is no node in the gap.

-
- [1] For a review, see T. Ishiguro, K. Yamaji, G. Saito, *Organic Superconductors* (Springer-Verlag, Berlin, 1998).
 - [2] D. Jérôme *et al.*, J. Phys. (Paris), Lett. **56**, L95 (1980).
 - [3] M. Takigawa, H. Yasuoka, and G. Saito, J. Phys. Soc. Jpn. **56**, 873 (1987).
 - [4] S. Belin and K. Behnia, Phys. Rev. Lett. **79** 2125 (1997).
 - [5] M.J. Naughton *et al.*, Synthetic Metals **85**, 1481 (1997).
 - [6] I.J. Lee *et al.*, Phys. Rev. Lett. **78**, 3555 (1997).
 - [7] Maki *et al.*, J. Superconductivity **12**, 551 (1999); Physica C **317-318**, 353 (1999); Synth. Metals **103**, 1933 (1999).
 - [8] M. Sato and M. Kohmoto, (unpublished).
 - [9] See, for example, P.G. De Gennes, *Superconductivity of Metal and Alloys* (Benjamin, New York, 1966).
 - [10] A. Leggett, Rev. Mod. Phys. **47**, 331 (1975); M. Sigrist and K. Ueda, Rev. Mod. Phys. **63**, 239 (1991).

* \vec{d} and ψ is defined as $\Delta(k) = i\sigma_2\psi(k) + i(\vec{d}(k) \cdot \vec{\sigma})\sigma_2$ [10].