

# Macroscopic Quantum Coherence in a Magnetic Nanoparticle Above the Surface of a Superconductor

Eugene M. Chudnovsky<sup>1</sup> and Jonathan R. Friedman<sup>2</sup>

<sup>1</sup> *Department of Physics and Astronomy, CUNY Lehman College  
250 Bedford Park Boulevard West, Bronx, NY 10468-1589*

<sup>2</sup> *Department of Physics and Astronomy, SUNY at Stony Brook  
Stony Brook, NY 11794-3800*

(November 19, 2018)

We study macroscopic quantum tunneling of the magnetic moment in a single-domain particle placed above the surface of a superconductor. Such a setup allows one to manipulate the height of the energy barrier, preserving the degeneracy of the ground state. The tunneling amplitude and the effect of the dissipation in the superconductor are computed.

PACS numbers: 75.45.+j, 75.50.Tt, 74.25.Nf

Tunneling of the magnetic moment in nanoparticles and molecular clusters has been intensively studied theoretically and experimentally in the last decade [1]. The interest in this problem is two-fold. Firstly, magnetic tunneling reveals itself at a quasiclassical level, that is, in situations where all three components of the magnetic moment,  $\mathbf{M}$ , can be rather accurately determined by a macroscopic measurement. The interaction of  $\mathbf{M}$  with microscopic degrees of freedom makes this problem one of tunneling with dissipation [2]. Secondly, tunneling of the magnetic moment changes the magnetic properties of small magnets, with potential implications for the data-storage technology. It also adds nanomagnets to the list of candidates for qubits - the elements of quantum computers.

In zero magnetic field the magnetic state of a classical magnet is degenerate with respect to  $\mathbf{M} \rightarrow -\mathbf{M}$  due to time-reversal symmetry. In nanoparticles the  $|\uparrow\rangle$  and  $|\downarrow\rangle$  minima of the energy are separated by a barrier,  $U$ , due to the magnetic anisotropy. The thermal rate of switching between the two classical states is proportional to  $\exp(-U/T)$ . At high temperatures, when the thermal rate is high, the particle is in the superparamagnetic regime. At low temperature, as far as the thermal rate is concerned, the magnetic moment should freeze along one of the anisotropy directions. In particles of sufficiently small size, however, even at  $T = 0$  the magnetic moment can switch due to quantum tunneling. The quantum switching rate,  $\Gamma$ , scales with the total spin  $S$  of the nanoparticle according [6–10] to  $\ln \Gamma \propto -S$ . If the switching time,  $\Gamma^{-1}$ , is small compared to the measuring time, the nanoparticle remains superparamagnetic in the limit of  $T = 0$ . If, in addition to that, the interaction of  $\mathbf{M}$  with microscopic degrees of freedom (phonons, itinerant electrons, nuclear spins, etc.) is small, the nanoparticle, during a certain decoherence time, can exist in a coherent quantum superposition of two classical states,  $\Psi_0 = |\uparrow\rangle + |\downarrow\rangle$ . In that state the probability that the moment of the particle has a certain orientation oscillates

in time as  $\cos(2\Gamma t)$ .

For a magnetic particle of considerable size to be in the quantum superparamagnetic (not necessarily coherent) regime, the energy barrier between the  $|\uparrow\rangle$  and  $|\downarrow\rangle$  states must be made sufficiently small. One way to decrease the barrier is to use an external magnetic field. This method has been used in experiments on magnetic particles and molecular clusters performed to date [3–5]. It has a clear drawback if one attempts to create a coherent superposition of the  $|\uparrow\rangle$  and  $|\downarrow\rangle$  states. Namely, the external field, unless it is applied exactly perpendicular to the anisotropy axis, removes the degeneracy between the  $|\uparrow\rangle$  and  $|\downarrow\rangle$  states. In this Letter, we suggest a method of controlling the barrier without breaking the degeneracy. This method is illustrated in Fig. 1. The nanoparticle is placed above the surface of a superconductor at a variable distance controlled by, e.g., a piezoelectric layer or holder. The current induced in the superconductor creates the magnetic image of the nanoparticle. The interaction between the nanoparticle and the superconductor is then equivalent to the dipole interaction between the nanoparticle and its image. The reduction of the barrier is similar to the one from the external magnetic field applied opposite to  $\mathbf{M}$ . However, contrary to the situation with the external field, the system (the nanoparticle plus the superconductor) is now degenerate with respect to  $\mathbf{M} \rightarrow -\mathbf{M}$ . It should be emphasized that such a degeneracy is a very general property of the system that is independent of the shape of the particle and the landscape of the superconducting surface. It is rooted in the time-reversal symmetry of the system in the absence of the field. The tunneling rate for the situation shown in Fig. 1 will be computed below.

A high tunneling rate does not automatically provide the coherent superposition of quasiclassical states. Different mechanisms of decoherence due to interactions inside the nanoparticle have been worked out in recent years [11–13]. At low temperature, in the absence of nuclear spins and itinerant electrons, the effect of dissi-

pation on the tunneling rate can be very small [1]. Decoherence is a more subtle issue. Generally speaking, macroscopic quantum coherence (MQC), that is  $\cos(2\Gamma t)$  oscillations of  $\mathbf{M}$ , occur only if the decohering interactions are small compared to the tunnel splitting of the ground state,  $\hbar\Gamma$ . We will show that this condition can be satisfied at least as far as the interaction between the nanoparticle and the superconductor is concerned. This question is of interest also in a more general context of measuring the rotation of a mesoscopic spin with the help of a superconducting device. Indeed, most of the experiments on individual nanoparticles used SQUIDS. Although the problem studied here is different from those experimental situations, some of the ideas should also apply in those cases.

Let us consider tunneling in a nanoparticle above the flat surface of a superconductor [14], as shown in Fig. 1, in the absence of dissipation. The external magnetic field will be considered zero throughout this paper. To make the classical electrodynamics of the problem less cumbersome, we will make certain simplifying assumptions about the superconductor, the shape of the particle and its magnetic anisotropy. None of them is important and any generalization can be studied along the same lines. First, we shall assume that the superconductor is in the Meissner regime; that is, the magnetic field at the surface of the superconductor does not exceed  $H_{c1}$ . We shall also assume that the characteristic geometrical dimensions of the problem, the size of the particle and its distance to the surface, are large compared to the penetration depth  $\lambda_L$ . In that case, it is a good approximation to take the field of the particle at the surface of the superconductor to be parallel to that surface. The effect of the superconductor on the particle is then equivalent to the magnetic dipole interaction with the image shown in Fig. 1.

Next we assume that the particle is of ellipsoidal shape (that is, uniformly magnetized) with crystal fields either small or dominated by the single-ion anisotropy. The total energy of the magnetic anisotropy of such a particle must be quadratic in the magnetization [15],

$$E_{an} = \frac{2\pi}{V} N_{ik} M_i M_k \quad , \quad (1)$$

where  $\mathbf{M}$  is the total magnetic moment of the particle,  $V$  is its volume, and the tensor  $N_{ik}$  includes both the demagnetizing effect (that is, shape anisotropy) and the magnetocrystalline anisotropy. In a ferromagnetic particle,  $M$  is proportional to  $V$ , while  $N_{ik}$  is independent of  $V$ . The factor  $V^{-1}$  in Eq. (1) is, therefore, needed to provide the correct linear scaling of  $E_{an}$  with  $V$ . We shall assume that the principal axes of  $N_{ik}$  coincide with the coordinate axes in Fig. 1; with  $Z$  being the easy magnetization direction and  $N_{xx} > N_{yy} > N_{zz}$ . The magnitude of  $\mathbf{M}$  is assumed, as usual, to be formed by a strong exchange interaction and, thus, independent of the orientation. That is,  $M_x^2 + M_y^2 + M_z^2 = M^2 = const.$

The energy of the magnetic anisotropy then becomes

$$E_{an} = \frac{1}{V} (\beta_x M_x^2 - \beta_z M_z^2) \quad , \quad (2)$$

where  $\beta_x, \beta_z$  are positive dimensionless coefficients of order unity.

Eq. (2) describes a magnet having a  $YZ$  easy magnetization plane with  $Z$  being the easy axis in that plane. The two degenerate minima of Eq. (2) correspond to  $\mathbf{M}$  looking along and opposite to the  $Z$  axis. In the Meissner state of the superconductor, the magnetic field of the particle induces superconducting currents whose field is equivalent to the field of the image shown in Fig. 1. As the particle moves closer to the superconductor, the interaction between the particle and its image increases and the barrier between the two equilibrium orientations of  $\mathbf{M}$  decreases. The magnetic moment of the particle,  $\mathbf{M}$ , and the moment of the image,  $\mathbf{m}$ , are related through

$$M_x = m_x \quad , \quad M_y = m_y \quad , \quad M_z = -m_z \quad . \quad (3)$$

With reasonable accuracy the energy of the magnetic dipole interaction between the particle and its image is given by

$$E_{int} = \frac{[\mathbf{M} \cdot \mathbf{m} - 3(\mathbf{n} \cdot \mathbf{M})(\mathbf{n} \cdot \mathbf{m})]}{(2d)^3} \quad , \quad (4)$$

where  $d$  is the distance from the (center of the) particle to the surface of the superconductor. With the help of relations (4), one obtains [14]

$$E_{int} = \frac{M_z^2}{(2d)^3} \quad . \quad (5)$$

The total energy of the system,  $E = E_{an} + E_{int}$  then becomes

$$E = \frac{1}{V} (-\beta_z \epsilon M_z^2 + \beta_x M_x^2) \quad , \quad (6)$$

where we have introduced  $\epsilon = 1 - V/\beta_z(2d)^3$ .

According to Eq. (6) the energy barrier between the degenerate  $|\uparrow\rangle$  and  $|\downarrow\rangle$  states of the particle is given by  $U = \beta_z \epsilon M_o^2 V$ , where  $M_o = M/V$  is the volume magnetization of the particle. Our main idea is to manipulate  $d$  in such a way that  $\epsilon$  and, consequently,  $U$  become small enough to provide a significant tunneling rate. Note that most deviations from the simplifying assumptions made above will renormalize  $\beta_{x,z}$  and  $d$  in Eq. (6) but will not change the form of the total energy. It is convenient to introduce the total dimensionless spin of the particle,  $\mathbf{S} = \mathbf{M}/\hbar\gamma$  ( $\gamma$  being the gyromagnetic ratio) and two characteristic frequencies:

$$\omega_{\parallel} = \beta_z \epsilon \gamma M_o \quad , \quad \omega_{\perp} = \beta_x \gamma M_o \quad . \quad (7)$$

The total energy can be then written as

$$E = \frac{1}{S} [-\hbar\omega_{\parallel}S_z^2 + \hbar\omega_{\perp}S_x^2] . \quad (8)$$

The corresponding tunneling problem has been studied by a number of authors [7–10]. In the limit of  $\omega_{\parallel} \ll \omega_{\perp}$ , i.e. at  $\epsilon \ll 1$ , the tunneling rate at  $T = 0$  in the absence of dissipation is given by  $\Gamma_o = A_o \exp(-B_o)$  with

$$A_o = \frac{16}{\sqrt{\pi}} S^{1/2} \omega_{\parallel}^{3/4} \omega_{\perp}^{1/4} \\ B_o = 2S \left( \frac{\omega_{\parallel}}{\omega_{\perp}} \right)^{1/2} . \quad (9)$$

So far, we have neglected non-dissipative terms in the total energy that come from the superconductor. One such term is the kinetic energy of the Cooper pairs,

$$E_{sc1} = \int d^3r \frac{n_s m \mathbf{v}_s^2}{2} , \quad (10)$$

where  $n_s$  is the concentration of superconducting electrons,  $m$  is their mass, and  $\mathbf{v}_s = \mathbf{j}_s / en_s$  is their drift velocity expressed in terms of the superconducting current  $j_s$ . Eq. (10) can be written as

$$E_{sc1} = \frac{4\pi\lambda_L^2}{c^2} \int d^3r \mathbf{j}_s^2 , \quad (11)$$

where  $\lambda_L = mc^2 / 4\pi e^2 n_s$  is the London penetration depth. The superconducting current is concentrated near the surface, resulting in the surface current [15]

$$\mathbf{g}_s = \int dz \mathbf{j}_s = \frac{c}{4\pi} \mathbf{n} \times \mathbf{B}(\mathbf{r}) , \quad (12)$$

where  $\mathbf{n}$  is the unit vector in the  $Z$  direction and  $\mathbf{B}(\mathbf{r})$  is the sum of the dipole fields of the magnetic particle and its image at  $z = 0$ . A somewhat tedious but straightforward calculation then gives

$$E_{sc1} = \frac{\lambda_L}{8\pi} \int d^2r \mathbf{B}^2(\mathbf{r}) = const + \frac{3\lambda_L}{16d^4} M_z^2 . \quad (13)$$

The contribution of the kinetic energy of the superconducting electrons to the total energy is small if  $d \gg \lambda_L$ . Even at  $d \sim \lambda_L$ , however, it reduces to the renormalization of the  $d$  dependence of the interaction between the magnetic particle and the superconductor. Since we are interested in  $d$  close to the critical value at which the barrier becomes zero, the form of the Hamiltonian, Eq. (8), and the expressions, Eq. (9), for the tunneling rate remain unaffected by that renormalization.

The next non-dissipative term in the energy is the inertia coming from the energy of the electric field,

$$E_{sc2} = \int d^3r \frac{\mathbf{E}^2}{8\pi} = \frac{1}{8\pi c^2} \int d^3r \left( \frac{d\mathbf{A}}{dt} \right)^2 . \quad (14)$$

where  $\mathbf{A} = -(4\pi\lambda_L^2/c)\mathbf{j}_s$  is the vector potential in the superconductor. Then, similarly to the previous case, one obtains

$$E_{sc2} = \frac{\lambda_L^3}{16\pi c^2} \int d^2r \left( \frac{d\mathbf{B}}{dt} \right)^2 = \frac{3\lambda_L^3}{32c^2 d^4} (\dot{\mathbf{M}}^2 + \dot{M}_z^2) . \quad (15)$$

To estimate the effect of this inertia term on tunneling, it should be compared, at the instanton frequency [1]  $\omega_{inst} = (\omega_{\parallel}\omega_{\perp})^{1/2}$ , with  $E$  of Eq. (8). The ratio of the energies is

$$E_{sc2}/E \sim (\lambda_L/d)^3 (l/d)(l/\lambda_{inst})^2 , \quad (16)$$

where we have introduced  $l = V^{1/3}$  and  $\lambda_{inst} = c/\omega_{inst}$ . Even if the experimental values of  $l, d$  and  $\lambda_L$  do not differ in order of magnitude,  $\lambda_{inst}$  can hardly be less than 1 cm, making the ratio of energies in Eq. (16) negligible for nanoparticles used in tunneling experiments. We may then conclude that Eq. (9) gives a good estimate of the tunneling rate in the absence of dissipation.

Spin tunneling with dissipation due to the interaction of  $\mathbf{M}$  with microscopic degrees of freedom inside the nanoparticle has been intensively studied [11,12]. Interactions with phonons, magnons, nuclear spins, etc. have been considered. Here we will study the mechanism of dissipation specific to our problem: the interaction of the magnetic moment with normal quasiparticles in the superconductor. This analysis may also be relevant to experiments on spin tunneling performed using SQUIDS.

We begin with the derivation of the energy dissipation in the superconductor due to the rotation of  $\mathbf{M}$ . With the help of the relations  $\mathbf{E} = -c^{-1}\partial\mathbf{A}/\partial t$  and  $\mathbf{j} = \sigma\mathbf{E}$ , one obtains

$$Q = \int d^3r \mathbf{j} \cdot \mathbf{E} = \frac{1}{c^2} \int d^3r \sigma(t) \dot{\mathbf{A}}^2 . \quad (17)$$

where  $\sigma$  is the conductivity due to quasiparticles. Its Fourier transform can be approximated as  $\sigma_{\omega} = e^2 n_q / m(\nu + i\omega)$ , where  $n_q$  is the quasiparticle concentration and  $\nu$  is their scattering rate. The latter is typically 2-3 orders of magnitude greater than the instanton frequency for the tunneling of  $\mathbf{M}$ . Consequently, the time dependence of  $\sigma$  in Eq. (17) can be neglected and one can use  $\sigma = e^2 n_q(T) / m\nu$ . Equation (17) then becomes similar to Eq. (14) and the same argument gives the surface integral that is proportional to  $(\dot{\mathbf{M}}^2 + \dot{M}_z^2) \propto [\dot{\theta}^2 + (\dot{\theta}^2 + \dot{\phi}^2)\sin^2\theta]$ . Due to the smallness of  $\epsilon$ , the hard-axis anisotropy in Eq. (8) is small compared to the easy-axis anisotropy. Under this condition, quasiclassical trajectories of  $\mathbf{M}$  must be close to the easy plane. This means  $\phi \approx \pi/2$ , while  $\theta$  for the tunneling trajectory changes from 0 to  $\pi$ . A more rigorous analysis shows that  $\dot{\phi}^2 \sim \epsilon \dot{\theta}^2$ . Thus, with good accuracy,

$$Q = \frac{\sigma\lambda_L^3}{2c^2} \int d^2r \dot{\mathbf{B}}^2 = \frac{3\lambda_L M^2}{16\nu d^4} \left( \frac{n_q}{n_s} \right) \dot{\theta}^2 (1 + \sin^2\theta) . \quad (18)$$

If Eq. (18) were quadratic in  $\dot{\theta}$ , it could be interpreted as linear dissipation with a friction coefficient  $\eta = 3\lambda_L M^2 n_q / 16\nu d^4 n_s$ . This would allow the Caldeira-Leggett [2] approach to tunneling with dissipation. The dissipation in the rotation of  $\mathbf{M}$  due to its interaction with quasiparticles is nonlinear in  $\theta$ , however. Nevertheless, since we only want to obtain an estimate of the effect of dissipation on tunneling, and because the  $\sin^2\theta$  term in Eq. (18) can hardly change this effect significantly, we shall go ahead and estimate the effective Caldeira-Leggett action as

$$I_{CL} = \frac{\eta}{4\pi} \int_{-\infty}^{\infty} d\tau' \int_{-\infty}^{\infty} d\tau \frac{[\theta(\tau) - \theta(\tau')]^2}{(\tau - \tau')^2}. \quad (19)$$

Note that the double-integral in Eq. (19) is dimensionless.

The measure of the effect of dissipation on tunneling is the ratio  $I_{CL}/\hbar B_o$  where  $\hbar B_o$  is the effective action in the absence of dissipation, with  $B_o$  given by Eq. (9). After simple algebra, one obtains

$$\frac{I_{CL}}{\hbar B} \sim \frac{3\pi}{128\sqrt{\epsilon}} \left(\frac{n_q}{n_s}\right) \left(\frac{\lambda_L}{d}\right) \left(\frac{l}{d}\right)^3 \left(\frac{\gamma M_o}{\nu}\right). \quad (20)$$

In a typical experiment, one should expect  $\lambda_L < d$  and  $l < d$ , while the ratio  $\gamma M_o/\nu$  may hardly exceed  $10^{-2}$ . Consequently, even at  $T \sim T_c$ , when  $n_q \sim n_s$ , the effect of the dissipation on the tunneling rate may become visible only at  $\epsilon$  less than  $10^{-5}$ .

A more rigorous approach along the lines of Ref. [16] shows that the ratio  $n_q/n_s$  in equations (19)-(21) should be replaced by the ratio of the coherence factors. Similar to other dissipation problems due to quasiparticles [16], its effect on tunneling must have a maximum at  $T$  slightly lower than  $T_c$ . Even at the maximum this effect should still be small. Coherence is a more subtle issue. It may be destroyed by a dissipative environment even if the effect of dissipation on tunneling is weak. The mechanism of dissipation discussed above goes down with temperature as  $\exp(-\Delta/T)$ , where  $\Delta$  is the superconducting gap. Consequently, preserving coherent oscillations of  $\mathbf{M}$  between  $|\uparrow\rangle$  and  $|\downarrow\rangle$  states requires  $T \ll \Delta$ .

The work of E.M.C. has been supported by the U.S. Department of Energy through Grant No. DE-FG02-93ER45487.

- 
- [1] E. M. Chudnovsky and J. Tejada, *Macroscopic Quantum Tunneling of the Magnetic Moment*, Cambridge University Press (1998).
  - [2] A. O. Caldeira and A. J. Leggett, Phys. Rev. Lett. **46**, 211 (1981); Ann. Phys. (N.Y.) **149**, 374 (1983).
  - [3] D. D. Awschalom et al., Phys. Rev. Lett. **68**, 3092 (1992).
  - [4] J. R. Friedman et al., Phys. Rev. Lett. **76**, 3830 (1996).
  - [5] W. Wernsdorfer et al., Phys. Rev. Lett. **79**, 4014 (1997).
  - [6] E. M. Chudnovsky, JETP **50**, 1035 (1979).
  - [7] M. Enz and R. Schilling, J. Phys. **C19**, L711 (1986).
  - [8] J. L. van Hemmen and A. Suto, Physica **B141**, 37 (1986).
  - [9] E. M. Chudnovsky and L. Gunther, Phys. Rev. Lett. **60** 661 (1988).
  - [10] D. A. Garanin, J. Phys. **A24**, L61 (1991).
  - [11] A. Garg and G.-H. Kim, Phys. Rev. Lett. **63**, 2512 (1989); A. Garg, Phys. Rev. Lett. **70**, 1541 (1993); ibid. **74**, 1458 (1995); Phys. Rev. **B51**, 15161 (1995).
  - [12] N. V. Prokof'yev and P. C. E. Stamp, J. Phys.: Condens. Matter **5**, L663 (1993); I. S. Tupitsyn, N. V. Prokof'yev, and P. C. E. Stamp, Int. J. Mod. Phys. **11**, 2901 (1997); M. Dube and P. C. E. Stamp, J. Low Temp. Phys. **110**, 779 (1998).
  - [13] G. Levine, Phys. Rev. **B56**, 7815 (1997).
  - [14] In general, the surface of the superconductor need not be flat. Other cases (e.g. when the superconductor is in the shape of a hemispherical mirror) may give a relatively larger interaction energy than Eq. (5) and, hence, may be more experimentally relevant.
  - [15] L. D. Landau and E. M. Lifhitz, *Electrodynamics of Continuous Media*, Nauka, 1982.
  - [16] M. Tinkham, *Introduction to Superconductivity*, McGraw-Hill, New York, 1975, p. 50.

FIG. 1. Magnetic particle above the surface of a superconductor. The effect of the superconductor on the particle is equivalent to the field from the image shown in the figure.

