## Comment on 'Two Dimensional Ordering and Fluctuations in $\alpha'$ -NaV<sub>2</sub>O<sub>5</sub>'

S. Ravy<sup>1</sup> and J. E. Lorenzo<sup>2</sup>

<sup>1</sup>Laboratoire de physique des solides, CNRS UMR 8502, Bât. 510, Université Paris-sud, 91405 Orsay Cedex, France <sup>2</sup>European Synchrotron Radiation Facility, 38042 Grenoble Cedex, France

In a recent letter, B. G. Gaulin et al. [1] present an x-ray study of the  $\alpha'$ -NaV<sub>2</sub>O<sub>5</sub> system. This compound, widely considered as a 1/4-filled spin ladder, exhibits a phase transition where charge and magnetic ordering occur (the ground state being spin-singlet) in addition to a structural distortion with the modulation wave vector (1/2,1/2,1/4). From their x-ray measurements above and below the transition temperature  $T_c$ =33.1 K, the authors claim that the transition is two-dimensional in nature and is due to a V<sup>4+</sup>/V<sup>5+</sup>-charge ordering mechanism. We do not agree with these conclusions for three reasons, as explained below.

The authors have measured the diffuse scattering above  $T_c$  in the three directions of the orthorhombic lattice (spin ladders are in the **b** direction, regrouped in (a,b) planes stacked in the c direction). In particular, scans in the  $\mathbf{c}^*$  directions around the superstructure spots, displayed in fig. 3 of [1], show the presence of critical scattering due to fluctuations. Without any quantitative analysis, the authors claim that these fluctuations develop within  $\sim 2$  K above  $T_c$ , and that the scattering is very different from that previously observed in [2]. The rod-like diffuse scattering that is mentioned in [1] has been also observed in [2] and is due to the overlap of the broad Lorentzians located at  $\Delta l = \pm 0.5$  from the measured one, and not due to a two-dimensional regime of fluctuations, at least below  $\sim 45$  K. Indeed, from the magnitude of the correlation lengths displayed in fig. 3 in [2], which have been obtained by analysing consistently the data in the three directions, one can see that they become very short-ranged along  $\mathbf{c}^* \sim 10 \text{ K}$  above  $\mathbf{T}_c$ . Therefore we do not see much difference between the data reported in [1] and [2], and hence the conclusion of [1] regarding the critical scattering is doubtful, at best. Especially, the statement that "the three dimensional state is built out of correlations developing between a-b planes which are already well ordered" is based on a misleading data analysis.

Secondly, the authors claim that their results show "two dimensional charge ordering to exist within the orthorhombic plane over an extensive temperature range above  $T_c$ ". This assertion is incorrect in the sense that x-ray mainly probe the lattice distortion and not the charge ordering (which has a weak amplitude compared to the first one). An analogous misconception is encountered in charge density wave (CDW) systems, in which the satellite reflections appearing below the phase transition are not due to the CDW itself, but to the associated lattice distortion. Evidencing charge ordering by x-ray is a challenging task requiring e.g. the use of anomalous scattering. This is not discussed in [1], where it is implicitly assumed that the lattice mirrors the charge or-

dering. Nevertheless, if the transition is triggered by a charge-ordering process coupled to the lattice, it is reasonnable to assume that the anisotropy of the lattice fluctuations observed by x-ray scattering is similar to that of the charge-ordering. In this respect, the long range character of Coulomb interactions involved in a charge-ordering process gives a natural explanation of the three dimensional nature of the lattice fluctuations as measured in [2], contrary to what is stated in [1].

At last, the authors have measured the temperature dependence of the superlattice peak below the transition temperature and obtained a  $\beta$ =0.17 critical exponent from a power law fit. From this value they conclude "... a very low value of  $\beta$  strongly suggests ordering which is two dimensional in nature". The authors then provide an explanation borrowed from results and theories of 2D magnetism (Refs. 20-24 of [1]), which is not applicable to the case of *structural* phase transitions in solids. Such low-dimensional magnetic phase transitions occur in 2D systems that are actually embedded in a threedimensional lattice but not coupled to the lattice. In this respect, the comparison between the transition in  $\alpha'$ - $NaV_2O_5$  and the magnetic phase transition of 2D systems (Refs. 20-24 of [1]), where a 2D regime of fluctuations is actually observed, is not relevant. Structural phase transitions of low-dimensional criticality have been observed in physically low-dimensional compounds, as for instance freely suspended liquid-crystal films, but not in real 3D solids. The proof of the 3D character of the transition is given by the existence of three-dimensionnal critical fluctuations  $\sim 10$  K above T<sub>c</sub> [2]. The authors' claim on the identification of  $\beta$ =0.17 as a critical exponent of a 2D order parameter in NaV<sub>2</sub>O<sub>5</sub> is too adventurous.

In conclusion, we think that the analysis presented in Ref. [1] does not prove neither the two-dimensional character of the transition in  $\rm NaV_2O_5$ , nor the charge ordering mechanism of the transition.

B. D. Gaulin, M. D. Lumsden, R. K. Kremer, M. A. Lumsden and H. Dabkowska, Phys. Rev. Lett. 84, 3446 (2000)

<sup>[2]</sup> S. Ravy, J. Jegoudez and A. Revcolevschi, Phys. Rev. B59, R681, (1999)