

# Strong-coupling superconductivity due to soft boson modes in $\text{MgB}_2$ , cuprates, borocarbides, and some heavy fermions

D. Lampakis<sup>1</sup>, A. Tatsi<sup>1</sup>, E. Liarokapis<sup>1</sup>, G. Varelogiannis<sup>2</sup>, P.M. Oppeneer<sup>3</sup>, M. Pissas<sup>4</sup>, T. Nishizaki<sup>5</sup>

<sup>1</sup>*Department of Applied Mathematics and Physics, National Technical University of Athens, GR-15780 Athens, Greece*

<sup>2</sup>*Institute of Electronic Structure and Laser, FORTH, P.O. Box 1527, GR-71110 Heraklion, Greece*

<sup>3</sup>*Institute of Solid State and Materials Research, P.O. Box 270016, D-01171 Dresden, Germany*

<sup>4</sup>*Institute for Materials Science, NCSR Demokritos, GR-15310 Athens, Greece*

<sup>5</sup>*Institute for Materials Science, Tohoku University, Katahira 2-1-1, Aoba-ku, Sendai 980-8577, Japan*

(November 20, 2018)

We report micro-Raman measurements that reveal a low-energy soft mode at 16–19 meV in  $\text{MgB}_2$  which becomes sharper in the superconducting state. With a boson spectrum based on this mode we reproduce, within Eliashberg theory, the  $T_c$ , the T-shape of the NMR relaxation rate as well as unusual dip-hump features in available tunneling data. We compare  $\text{MgB}_2$  to cuprates, borocarbides, and  $\text{UPd}_2\text{Al}_3$ , where we identify soft bosonic modes at energies which *scale with their  $T_c$* , suggesting that all these materials are very strong coupling superconductors to soft bosonic modes, that are possibly precursors of quantum instabilities.

PACS numbers: 74.25.Kx, 74.20.-z, 78.30.-j

A surprisingly high superconducting (SC) critical temperature  $T_c \approx 40$  K observed in a compound as simple as  $\text{MgB}_2$  [1] has stimulated enormous activity. The simplicity of this system gives rise to expectancies that the origin of the high  $T_c$  might be comparatively easy to establish. Isotope effect measurements [2,3] indicate that phonons participate in the pairing mechanism. For a material like  $\text{MgB}_2$ , the phonon spectrum and the electron-phonon coupling are plausibly accessible by density-functional theory (DFT) calculations and a number of such studies have been reported [4]. The main conclusion of all these studies is that the coupling should essentially involve the high-energy boron modes at around 70 meV and the coupling strength  $\lambda$  is estimated to be in the range  $0.4 \leq \lambda \leq 0.9$  [4]. In this range of weak couplings we find some of the most conventional simple superconductors like Al.

In this Letter, we report evidence against this idealized picture of totally conventional, weak-coupling superconductivity in  $\text{MgB}_2$ . Our Raman measurements reveal the existence of a distinct soft mode in the region 130–150  $\text{cm}^{-1}$  (16–19 meV) which becomes sharper in the SC state, suggesting its involvement in the pairing mechanism. Since all DFT calculations [4] agree that no harmonic phonon modes exist at such low energies in  $\text{MgB}_2$ , we attribute this soft mode to the proximity of an unknown instability for which DFT methods cannot account. We show, using Eliashberg theory with a boson spectrum based on this mode, that we reproduce the absence of the Hebel-Slichter peak in the T-shape of the nuclear magnetic resonance (NMR) relaxation rate in  $\text{MgB}_2$  as well as distinct qualitative features of the available tunneling spectra [5–7] (dip-hump structures and anomalous temperature behavior) that are characteristic of *exceptionally strong-coupling superconductivity in the range  $\lambda \approx 3$* . We conclude that the observed mode is a signature of the boson field (in conventional cases har-

monic phonons) that mediates the pairing. Since qualitative similar anomalous features in the tunneling quasi-particle spectrum were observed also for high- $T_c$  cuprates [8], borocarbides [9], and  $\text{UPd}_2\text{Al}_3$  [10], these superconductors are likely to be in the  $\lambda \approx 3$  regime as well. We identify in all these materials soft modes at energies *proportional to their respective  $T_c$ 's*. These soft modes govern the pairing and are therefore a necessary (but not sufficient) ingredient for high  $T_c$ 's.

We have carried out micro-Raman measurements on high-quality  $\text{MgB}_2$  powder samples. The data were obtained with a T64000 Jobin Yvon triple spectrometer with a liquid-nitrogen cooled CCD. An Oxford Micro-He cryostat was appropriately modified to allow the study of microcrystallites at various scattering geometries. The 488.0 nm  $\text{Ar}^+$  laser line was focused on 1–2  $\mu\text{m}$  large crystallites and the power was kept below 0.03 mW to avoid heating by the beam. Typical spectra recorded for selected temperatures are shown in Fig. 1. The main peak at about 600  $\text{cm}^{-1}$  was already reported in macro-Raman studies [11,12]. In the low-energy region 130–150  $\text{cm}^{-1}$  (16–19 meV) we observe an additional broad peak which becomes sharper in the SC state. A structure in the same energy range was also seen in a macro-Raman study [12], but was attributed to the peak in the quasi-particle density of states corresponding to the opening of the SC gap. However, in our spectra the feature is clearly visible in the normal state *as well*, therefore we identify it as a soft bosonic mode. Inelastic neutron scattering measurements also reported an excitation with a similar behavior in this energy range (around 17 meV [13]) supporting the assignment of the structure to bosonic excitations. Since there is no such soft phonon predicted for  $\text{MgB}_2$  by DFT calculations [4], our observed bosonic mode might result from the proximity to an instability. Indeed, a small addition of electrons via Al doping triggers a subtle structural transition in which the *c*-axis con-

tracts and  $T_c$  drops [14]. The soft boson mode could be the precursor of this instability. We argue below that this bosonic mode is likely to be the principal mediator of the pairing in MgB<sub>2</sub>. We furthermore observe in the SC state a narrow peak at about 80 cm<sup>-1</sup> which might be related to superconductivity. The energy of the latter peak is too low to be considered a measure of the SC gap.

The relevance of our 130 cm<sup>-1</sup> soft boson for the pairing mechanism is supported by our Eliashberg calculations of the NMR relaxation rate  $R = T_1^{-1}$  and the tunneling density of states. NMR has the advantage of being both a local probe and bulk sensitive, therefore the NMR relaxation data manifest the intrinsic SC character. We have calculated  $R$  under the constraint  $T_c \approx 39$  K using an Einstein spectrum at various energies. In Eliashberg theory, the reduced NMR relaxation rate is given by

$$\frac{R_s}{R_n} = 2 \int_0^\infty d\omega \left( -\frac{\partial f}{\partial \omega} \right) \left[ \left( \Re \left\{ \frac{\omega}{\sqrt{\omega^2 - \Delta^2(\omega, T)}} \right\} \right)^2 + \left( \Re \left\{ \frac{\Delta(\omega, T)}{\sqrt{\omega^2 - \Delta^2(\omega, T)}} \right\} \right)^2 \right], \quad (1)$$

where the complex gap function  $\Delta(\omega, T)$  results from the analytic continuation to real frequencies of the solutions of Eliashberg equations for imaginary Matsubara frequencies. We have verified in our calculation that the NMR relaxation rate is quasi-independent of the exact spectral shape. We show in Fig. 2 the NMR relaxation rate at four characteristic temperatures as a function of the involved boson energy for the two limiting values of the Coulomb pseudopotential  $\mu^* = 0.1$  and 0.2. All experimental points [15] in the corresponding temperature range lie within the black rectangle that we have centered at the energy of our soft boson mode. Clearly, the absence of the Hebel-Slichter peak in MgB<sub>2</sub> and the behavior of  $1/T_1$  near  $T_c$  points to frequencies of the order of our soft mode. With such low energies involved, the coupling strength necessary to produce  $T_c \approx 40$  K is sufficiently high  $\lambda \geq 2.5$  and the Hebel-Slichter peak is eliminated by lifetime effects [16]. We note that recently the behavior of the upper critical field in MgB<sub>2</sub> [17], and that of the electronic specific heat [18] were also proposed as indications of strong-coupling superconductivity.

With an Eliashberg function based on our boson mode and adjusted to produce  $T_c = 39$  K we have calculated the tunneling density of states. In the zero temperature regime we obtain a dip structure above the gap (at  $\approx 4\Delta(T=0)$ ) followed by a hump (see Fig. 3). As the temperature rises, the characteristic energies of the structures in the spectrum (peak-dip-hump) remain almost unchanged, while the structures broaden gradually. The gap is filled with states at finite  $T$  below  $T_c$  contrary to what is expected for a conventional second-order phase transition, like in BCS theory where no co-existence of phases occurs. Similar unusual behavior of

the quasiparticle density of states was observed so far in cuprate high- $T_c$  superconductors [8], in UPd<sub>2</sub>Al<sub>3</sub>, which is a heavy fermion superconductor [10], and in borocarbides [9]. In the case of MgB<sub>2</sub> a careful examination of all available tunneling data reveals clear evidence of this behavior [5–7]. For example, by applying a magnetic field, the quasiparticle density of states in MgB<sub>2</sub> (fig. 4 in [5]) evolves as already observed in UPd<sub>2</sub>Al<sub>3</sub> [10] showing the same anomalous critical behavior as with temperature in Fig. 3. The unusual tunneling spectrum arises within Eliashberg theory when at sufficiently strong coupling  $\lambda \geq 2.5$  the gap energy becomes comparable to the energy of the bosons that mediate the pairing [19,20]. The dip-hump features are not spectral structures as those reported by McMillan and Rowell [21] but are generic qualitative features of a very strong-coupling regime at the beginning of a cross-over towards Bose condensation [20].

Soft modes as the one we identify in MgB<sub>2</sub> are shown below to be present in *all* classes of materials that exhibit this unusual quasiparticle density of states. We have made a detailed Raman study under pressure on monocrystals of YBa<sub>2</sub>Cu<sub>3</sub>O<sub>6+x</sub> compounds. Some of our results are shown in Fig. 4. Confirming previous reports [22], we find in YBa<sub>2</sub>Cu<sub>3</sub>O<sub>7- $\delta$</sub>  ( $T_c = 90$  K) a soft mode at 320 cm<sup>-1</sup> *hidden by the B<sub>1g</sub> mode* (340 cm<sup>-1</sup>) with which it almost coincides energetically. By applying pressure, the energy of the harmonic B<sub>1g</sub> mode rises as expected, while the 320 cm<sup>-1</sup> mode remains unchanged [22] confirming its soft character. This mode could correspond to the phonon with abnormal behavior detected at 41 meV by neutron scattering [23]. The increase in the intensity of the 320 cm<sup>-1</sup> soft mode in the SC state may contribute significantly to the apparent softening of the B<sub>1g</sub> mode with the onset of superconductivity [23,24].

Most surprising is the discovery of a similar soft mode in YBa<sub>2</sub>Cu<sub>3</sub>O<sub>6.5</sub> ( $T_c = 60$  K) at 216 cm<sup>-1</sup> in our micro-Raman measurements under hydrostatic pressures (cf. Fig. 4). In this underdoped compound the 320 cm<sup>-1</sup> soft mode has disappeared and the 216 cm<sup>-1</sup> is the only soft mode we detect. Surprisingly, the ratio of the energies of the soft modes almost equals the ratio of the  $T_c$ 's (216/320  $\approx$  60/90). In La<sub>2-x</sub>Sr<sub>x</sub>CuO<sub>4</sub> compounds a well-known soft mode is identified in the Raman spectra [25]. The frequency of this mode is about 126 cm<sup>-1</sup> for the  $x = 0$  compound and it reduces continuously with doping as does also the temperature where the transition to the tetragonal phase occurs. In the case of borocarbides, the presence of a soft phonon mode was established by neutrons and widely discussed in the literature [26]. Finally, even in the heavy-fermion superconductor UPd<sub>2</sub>Al<sub>3</sub> a soft bosonic mode was observed by neutrons, which, conversely, was attributed to spin excitations [19,27].

Remarkably, all these soft modes appear at energies that *scale with the critical temperature of the respective*

materials (see Fig. 5). The proportionality of these modes to  $T_c$  cannot be attributed solely to gap features because they are visible well above  $T_c$ . The scaling instead suggests the involvement of these soft modes in the pairing mechanism, and points to a *similar, strong-coupling superconductivity in all these materials*. The occurrence of strong coupling to soft bosonic modes in compounds that are so different raises the question of a common underlying mechanism. The exceptional strength of the coupling of electrons to the soft-boson mode is probably due to singularities in the quasiparticle susceptibility, that are in turn related to the proximity of an instability. The nature of the instability may very well be different in different categories of materials. The proximity of quantum critical points has already been invoked for the understanding of superconductivity in cuprate [28] and heavy fermion [29] materials. In borocarbides the observed soft modes involve charge degrees of freedom [26]; this is also the case in  $\text{MgB}_2$  where it could also be related to the structural instability [14]. The proximity to an instability produces singularities not only in the frequency domain responsible for the exceptionally strong coupling, but also in momentum space, where these may lead to a SC gap with nodes in some of these compounds. Anisotropic and even non-s-wave superconductivity in  $\text{MgB}_2$  or in related compounds is plausible and compatible with the absence of spin degrees of freedom. In fact, even phonon-mediated pairing in the proximity of a phase separation instability is dominated by small-q processes, which may lead to anisotropic superconductivity possibly with unconventional gap symmetry and other anomalies [30].

In conclusion, we have detected a soft mode at low energies ( $\approx 17$  meV) in  $\text{MgB}_2$  which is strongly coupled to the carriers and mediates superconductivity in  $\text{MgB}_2$ . We show that  $\text{MgB}_2$  shares an exceptionally strong-coupling regime  $\lambda \approx 3$  with cuprates, borocarbides and  $\text{UPd}_2\text{Al}_3$ . We identify in all these compounds soft modes at energies which scale with their  $T_c$  and we argue that these are the bosons which govern the pairing. Tentatively, the soft modes result in all cases from the proximity to a (quantum) instability which appears to be a key element for obtaining a high critical temperature.

We are grateful to E.N. Economou and K. Prassides for useful discussions.

---

[1] J. Nagamatsu *et al.*, Nature **410**, 63 (2001).  
[2] S.L. Bud'ko *et al.*, Phys. Rev. Lett. **86**, 1877 (2001).  
[3] D.G. Hinks, H. Claus, and J.D. Jorgensen, cond-mat/0104242.  
[4] Y. Kong *et al.*, cond-mat/0102499; K-P. Bohnen, R. Heid, and B. Renker, cond-mat/0103319; N.I.

Medvedeva *et al.*, cond-mat/0103157; T. Yildirim *et al.*, cond-mat/0103469; J.B. Neaton and A. Perali, cond-mat/0104098; A.Y. Liu, I.I. Mazin, and J. Kortus, cond-mat/0103570; M.J. Mehl, D.A. Papaconstantopoulos, and D.J. Singh, cond-mat/0104548.  
[5] G. Karapetrov *et al.*, Phys. Rev. Lett. **86**, 4374 (2001).  
[6] A. Sharoni, I. Felner, and O. Millo, Phys. Rev. B (2001); A. Sharoni *et al.*, preprint.  
[7] G. Rubio-Bollinger, H. Suderow, and S. Vieira, cond-mat/0102242; H. Schmidt *et al.*, cond-mat/0102389; C.-T. Chen *et al.*, cond-mat/0104285; F. Giubileo *et al.*, cond-mat/0105146.  
[8] D. Mandrus *et al.*, Nature **351**, 460 (1991); J-X. Liu *et al.*, Phys. Rev. Lett. **67**, 2195 (1991); D.S. Dessau *et al.*, Phys. Rev. Lett. **66**, 2168 (1991).  
[9] H. Suderow *et al.*, cond-mat/0102152.  
[10] M. Jourdan, M. Huth, and H. Adrian, Nature **398**, 47 (1999).  
[11] K.-P. Bohnen, R. Heid, and B. Renker, cond-mat/0103319; A.F. Goncharov *et al.*, cond-mat/0104042; H. Martino *et al.*, cond-mat/0105204.  
[12] X.K. Chen *et al.*, cond-mat/0104005.  
[13] T.J. Sato, K. Shibata, and Y. Takano, cond-mat/0102468v2.  
[14] J.S. Slusky *et al.*, Nature **410**, 343 (2001).  
[15] H. Kotegawa *et al.*, cond-mat/0102334; J.K. Jung *et al.*, cond-mat/0103040; A. Gerashenko *et al.*, cond-mat/0102421.  
[16] P.B. Allen and D. Rainer, Nature **349**, 396 (1991); R. Combescot and G. Varelogiannis, Europhys. Lett. **17**, 625 (1992); G. Varelogiannis, Physica C **232**, 49 (1994).  
[17] K.-H. Müller *et al.*, preprint; S.V. Shulga *et al.*, cond-mat/0103154.  
[18] Ch. Wälti *et al.*, cond-mat/0102522.  
[19] N. Sato *et al.*, Nature **410**, 340 (2001).  
[20] G. Varelogiannis, Z. Phys. B **104**, 411 (1997); Phys. Rev. B **51**, 1381 (1995).  
[21] W.L. McMillan and J.M. Rowell, in *Superconductivity*, edited by R.D. Parks (Dekker, New York, 1969), Vol. I, p. 561.  
[22] K. Syassen *et al.*, Physica C **153–155**, 264 (1988).  
[23] H.F. Fong *et al.*, Phys. Rev. Lett. **75**, 316 (1995); M. Arai *et al.*, *ibid* **69**, 359 (1992).  
[24] B. Friedl, C. Thomsen, and M. Cardona, Phys. Rev. Lett. **65**, 915 (1990).  
[25] S. Sugai, Phys. Rev. B **39**, 4306 (1989); D. Lampakis *et al.*, Phys. Rev. B **62**, 8811 (2000).  
[26] P. Dervenagas *et al.*, Phys. Rev. B **52**, R9839 (1995); C. Stassis *et al.*, Physica C **317–318**, 127 (1999) and references there in.  
[27] N. Metoki *et al.*, Phys. Rev. Lett. **80**, 5417 (1998); N. Berhoeft *et al.*, *ibid* **81**, 4244 (1998).  
[28] see e.g. J. Zaanen, Physica C **317–318**, 217 (1999) and references there in.  
[29] see e.g. N.D. Mathur *et al.*, Nature **394**, 39 (1998) and references there in.  
[30] G. Varelogiannis, Phys. Rev. B **57**, 13743 (1998).

FIG. 1. Typical micro-Raman spectra measured on MgB<sub>2</sub> crystallites. The spectra are corrected for the Boltzmann thermal factor.

FIG. 2. The reduced NMR relaxation rate  $R_s/R_n$  at four characteristic temperatures near  $T_c$  ( $T/T_c=0.95, 0.90, 0.85,$  and  $0.80$  from top to bottom in the low energy side) for  $\mu^*=0.1$  (full lines) and  $\mu^*=0.2$  (dashed lines) as a function of the involved boson energy in MgB<sub>2</sub>. When  $R_s/R_n > 1$  the Hebel-Slichter peak is present. The available experimental points for  $0.8T_c \leq T \leq 0.95T_c$  lie within the black rectangle centered at the energy of our soft boson.

FIG. 3. The reduced density of states  $N_s/N_n$  for various temperatures using a boson spectrum based on our soft mode whose amplitude is adjusted to produce  $T_c=39$  K. In the inset we emphasize the conventional BCS-like T-behavior we obtain if we use instead a boson spectrum dominated by the  $E_{2g}$  phonon at 70 meV with the same  $T_c$  constraint. In both cases the temperatures are  $T=0.3T_c$  (full lines),  $0.7T_c$  (dashed lines)  $0.9T_c$  (long-dashed lines) and  $0.95T_c$  (dot-dashed lines).

FIG. 4. Selected Raman spectra on YBa<sub>2</sub>Cu<sub>3</sub>O<sub>6+x</sub> monocrystals. In the lower panel, the 320 cm<sup>-1</sup> soft mode at optimal doping is evidenced by pressure because it is insensitive while the harmonic B<sub>1g</sub> phonon at 340 cm<sup>-1</sup> stiffens. In the underdoped YBa<sub>2</sub>Cu<sub>3</sub>O<sub>6.5</sub> compound (upper panel) the 320 cm<sup>-1</sup> soft mode is absent and a new mode at 216 cm<sup>-1</sup> appears which is shown to be soft since it remains insensitive to pressure. In the inset is shown the evolution of the 216 cm<sup>-1</sup> mode as a function of the applied pressure. No other soft mode was detected.

FIG. 5. The energy of the soft modes identified in various materials that show unconventional tunneling behavior as a function of their respective  $T_c$ 's. The linear scaling is evident from the straight fit line through the origin.











