Nucleation in Systems with Elastic Forces

Abstract

Systems with long-range interactions when quenched into a metastable state near the pseudo-spinodal exhibit nucleation processes that are quite different from the classical nucleation seen near the coexistence curve. In systems with long-range elastic forces the description of the nucleation process can be quite subtle due to the presence of bulk/interface elastic compatibility constraints. We analyze the nucleation process in a simple 2d model with elastic forces and show that the nucleation process generates critical droplets with a different structure than the stable phase. This has implications for nucleation in many crystal-crystal transitions and the structure of the final state.

† Permanent Address, * Permanent Address

Nucleation in systems with long-range forces can be very different [1–5] than the process predicted by the classical theory [6,7]. The reason for the difference is the presence of a pseudo-spinodal (defined below) [8,9] that affects the structure of the critical droplet [2–4] and alters the dependence of the nucleation rate on the thermodynamic parameters [1,10]. An interesting and important class of materials that exhibits pseudo-spinodal behavior is those that interact through elastic forces; a subclass of which undergoes martensitic structural transitions. [11] An example of such a transition is when alloys such as FePd and NiTi transform on cooling from an "austenite" phase at high temperatures to an equal width mesoscale twin phase below the martensite transition temperature T_o [12]. This transition is first order and takes place via nucleation. However, the nucleation process in these systems is not well understood [13–15].

The purpose of this Letter is to present an analysis of nucleation near the pseudo-spinodal of a model with elastic forces. A complete specification of the critical droplet profile requires, in addition to the usual bulk terms, [3,10] a consideration of a term generated by the elastic compatibility constraints. This is, to our knowledge, the first treatment that describes nucleation near the pseudo-spinodal in this class of materials and is the first indication that the compatibility constraint plays an essential role in this nucleation process. In addition, this is the first indication that homogeneous nucleation in a crystal-crystal phase transition takes place with a critical droplet that does not have the symmetry of the stable phase.

In this Letter we analyze a model that exhibits a two-dimensional square to rectangle transition [16] and captures the essential physics of crystal-crystal transitions in systems with elastic forces. The order parameter (OP) is a rectangular or deviatoric strain, which is a symmetry adapted combination of the 2d strain tensor $\varepsilon_{\mu,\nu}(\mu,\nu=x,y)$. The non-OP, or secondary, strain components are related to the OP through a compatibility equation. We can write a Ginzburg-Landau (GL) free energy in the form [16] $F(\epsilon) = F_o(\epsilon) + F_{grad}(\nabla \epsilon) + F_{cs}(e_1, e_2)$, where

$$F_o(\epsilon) = \int d\vec{r} [(\tau - 1)\epsilon^2(\vec{r}) + \epsilon^2(\vec{r})(\epsilon^2(\vec{r}) - 1)^2], \tag{1}$$

$$F_{grad}(\nabla \epsilon) = \int d\vec{r} \left[\frac{a}{4} (\nabla \epsilon(\vec{r}))^2 + \frac{b}{8} (\nabla^2 \epsilon(\vec{r}))^2 \right], \tag{2}$$

$$F_{cs}(e_1, e_2) = \frac{1}{2} \int d\vec{r} [A_1 e_1^2(\vec{r}) + A_2 e_2^2(\vec{r})].$$
 (3)

Here $\epsilon(\vec{r}) = \frac{1}{\sqrt{2}} [\varepsilon_{(xx)}(\vec{r}) - \varepsilon_{(yy)}(\vec{r})]$ is the OP strain, $e_1(\vec{r}) = \frac{1}{\sqrt{2}} [\varepsilon_{(xx)}(\vec{r}) + \varepsilon_{(yy)}(\vec{r})]$, $e_2(\vec{r}) = \varepsilon_{(xy)}(\vec{r})$ are the compression and shear strain, respectively and $\tau = \frac{(T-T_c)}{(T_o-T_c)}$, where T_c is the temperature at which the OP would completely soften. The subscripts (xx), (xy) and (yy) denote partial derivatives, A_1 and A_2 are elastic constants for the compression and shear, and a and b are strain gradient constants independent of T.

The St. Venant compatibility equation for the symmetric strain tensor is $\nabla \times (\nabla \times \varepsilon(\vec{r}))^T = 0$. Using the Lagrangian multiplier formalism [17] in d = 2 we find for Fourier expandable strains $\epsilon(\vec{k})$ that $e_1(\vec{k})$ and $e_2(\vec{k})$ are proportional to $\epsilon(\vec{k})$, the Fourier transform of $\epsilon(\vec{r})$ with \vec{k} dependent coefficients. This result allows us to replace $F_{cs}(e_1, e_2)$ in Eq.(3) with an OP potential $F_{cs}(\epsilon) = F_{cs}^{bulk}(\epsilon) + F_{cs}^{surface}(\epsilon)$ where [16,18]

$$F_{cs}^{bulk}(\epsilon) = \int d\vec{k} U^{bulk}(\vec{k}) |\epsilon(\vec{k})|^2, \tag{4}$$

$$U^{bulk}(\vec{k}) = \frac{4\rho \left[\frac{(k_x^2 - k_y^2)}{k^2}\right]^2}{1 + 16\rho \frac{k_x^2 k_y^2}{k^4}},\tag{5}$$

$$F_{cs}^{surface} = \frac{A_2}{2} \int d\vec{k} \frac{|\frac{1}{2}[1 + i\frac{I(k)}{J}]\epsilon(\vec{k})|^2}{|k_y|} \delta(\vec{k} - \vec{k}_{surface}).$$
 (6)

where the surface term is generated by the interface between the high symmetry "austenite" phase and the low symmetry "martensite" phase. In Eq.(6) the integral is over the momentum modes of the interface, J is independent of \vec{k} and depends only on the ratio $\rho = A_2/2A_1$, and

$$I(\vec{k}) = \frac{\frac{k_x^2 - k_y^2}{2|k_x k_y|}}{1 + \rho \left[\frac{k_x^2 + k_y^2}{2|k_x k_y|}\right]^2}.$$
 (7)

In the above equations $k_{x(y)}$ is the x(y) component of \vec{k} with respect to the underlying square lattice [18] and $k = |\vec{k}|$.

In the thermodynamic limit we can ignore $F_{cs}^{surface}$ and we first assume a spatially homogeneous $\epsilon(\vec{r})$. The free energy has the following form; For $\tau > 4/3$ there is one minimum at $\epsilon = 0$. For $1 < \tau < 4/3$ there are three minima but $\epsilon = 0$ is the global minimum. For $0 < \tau < 1$ there are again three minima. The one at $\epsilon = 0$ (the "austenite" phase) is metastable while the two minima, symmetric about $\epsilon = 0$ (the "martensite" phase) are stable. For $\tau < 0$ there is no longer a minimum at $\epsilon = 0$. Note that this analysis does not consider instabilities to perturbations with non-zero wave vectors. We will return to this point below. We will first investigate the nucleation process from the metastable minimum at $\epsilon = 0$ near the spinodal at $\tau = 0$. From the spatially homogeneous free energy it is simple to calculate the order parameter exponent $\epsilon \sim \tau^{\beta}$ with $\beta = 1/2$. Reinstating the Laplacian term in free energy it can be seen that the correlation length diverges as $\xi \sim \tau^{-\nu}$ with $\nu = 1/2$. Adding a spatially homogeneous external field to the free energy leads to a susceptibility $\chi \sim \tau^{-\gamma}$ with $\gamma = 1$ [19].

Turning to nucleation near $\tau = 0$, we first note that nucleation does not occur in systems with infinite range interactions. That includes mean-field systems [10]. However, systems with elastic forces do not have infinite range interactions due to the screening from defects. [20] Hence we will be dealing with systems that have the same bulk and surface interactions as in eqs.(4-6) except they will have an exponential cutoff of the form $\exp(-\frac{r}{R})$, where R >> 1 is the interaction range and $r = |\vec{r}|$.

Since the interaction range is large but finite the system is no longer mean-field but near-mean-field [21,22]. In order for the mean-field approach, including the idea of a spinodal, to be a reasonable approximation when $R \neq \infty$ the system must satisfy the Ginzburg criterion [21,22] namely

$$\frac{\xi^d \chi}{\xi^{2d} \epsilon^2} = \frac{\tau^{-1}}{R^d \tau^{-\frac{d}{2}} \tau} \ll 1. \tag{8}$$

Note that the correlation length, ξ , as are all lengths, is in units of R. The Ginzburg criterion can be rewritten as $R^d\tau^{2-d/2}=A>>1$ where A is a fixed large number. When the Ginzburg criterion is satisfied, many aspects of the mean-field spinodal are still present. However, the singularity has been smeared out. [8,9] The larger A the better the spinodal is approximated by the pseudo-spinodal. Since A>>1 for these systems the pseudo-spinodal is very close to a true spinodal.

To calculate the nucleation or critical droplet structure we will use saddle point techniques [1,4,6,10]. Near the pseudo-spinodal there will be an incompletely softened mode that can be identified by examining the \vec{k} coefficient of the Gaussian term in the action. We take the action to be the free energy in Eqs.(1-3) [6]. Initially we will ignore the surface term given in Eq.(6). The structure factor $S(\vec{k})$ is then

$$S(\vec{k}) \sim \left[\tau + \frac{\pm |a|}{4}k^2 + \frac{b}{8}k^4 + U^{bulk}(\vec{k})\right]^{-1},$$
 (9)

where the +(-) is for a positive(negative). Consider first a, b > 0. Since all terms in $S(\vec{k})$ are positive semi-definite the only divergence is when $k \to 0$ and $k_x = k_y$. The surface

term in Eq.(6) would appear to strongly suppress the fluctuations that cause the divergence. However, this term was derived for a sharp interface [16,18]. We need to extend this result to an interface with width ξ . The reason for this particular scale will become clear. We can consider the smooth interface to be a sequence of sharp interfaces or steps each one contributing a term to the free energy of the form given in Eq.(6). Since $k_x = k_y$, $I(\vec{k}) = 0$. We will assume a form for the interface of $\epsilon_{interface} \propto \exp(-r/\xi)$ and $\xi >> R$. The difference in order parameter amplitude between steps is

$$\Delta \epsilon_{interface} \propto \frac{d}{dr} \exp(-r/\xi) dr = -\frac{\exp(-r/\xi)}{\xi} R, \tag{10}$$

where we have chosen our differential step dr = R. This is justified since all lengths are in units of R and R is the coarse graining scale in the GL theory [4,10]. Taking $k \sim \xi^{-1}$ and $dk \sim \xi^{-1}$ in Eq.(6) the free energy cost for the surface is $F^{surface} \sim \frac{\xi^2 \epsilon^2(\vec{r})}{\xi}$, where $\xi \epsilon(\vec{r})$ scales as $\epsilon(\vec{k})$ and the number of steps in the surface is ξ/R . As we will see the dominant contribution to the free energy F scales as $\int d\vec{r} \tau \epsilon^2(\vec{r}) = \xi^2 \tau \epsilon^2$, where by ϵ we mean to include only the dependence of $\epsilon(\vec{x})$ on τ . Comparing these two scaling forms we have $F^{surface} = F \frac{C}{A^{1/2}} \ll F$, where C is a constant of order 1 and A >> 1 from the Ginzburg criterion. The Ginzburg criterion also implies that for a fixed but large R, τ cannot reach zero [10] and the system remain near-mean-field. The ratio $F^{surface}/F = 0$ only as R and hence $A \to \infty$. For the long-range potential we are using the surface term is, in general, small enough to neglect. Note that if A is not infinite then the surface term is added to S(k)eliminating the divergence at k=0. Since A>>1 the structure factor can be extremely large and the true spinodal is well approximated. In calculating the surface contribution we have assumed that there is a domain with non-zero $\epsilon(\vec{x})$ with a linear size of the correlation length ξ imbedded in the metastable $\epsilon(\vec{x}) = 0$ phase. We now proceed to demonstrate the existence of this domain. First we note that a and b in Eq.(2) must have units of length to the second and fourth powers respectively and hence are proportional to R^2 and R^4 as all lengths must be proportional to R [10]. The Euler-Lagrange equation for the critical droplet is obtained by setting the functional derivative of $F(\epsilon)$ in Eqs. (1-3) equal to zero to obtain

$$-\frac{a}{2}\nabla^{2}\epsilon(\vec{r}) + \frac{b}{4}\nabla^{4}\epsilon(\vec{r}) + 2\tau\epsilon(\vec{r}) - 4\epsilon^{3}(\vec{r}) + 6\epsilon^{5}(\vec{r}) + \int d\vec{r}'\tilde{U}^{bulk}(\vec{r}, \vec{r}')\epsilon(\vec{r}') = 0$$
 (11)

where $\tilde{U}(\vec{r})^{bulk}$ is $U^{bulk}(\vec{r})$ multiplied by the exponential cutoff $\exp(-\frac{r}{R})$. We now assume a solution of the form

$$\epsilon(\vec{r}) = \sum_{n} c_n(\tau) \exp(i\vec{k}_{o,n} \cdot \vec{r}) \psi(\frac{\vec{r}}{L}) = G(\tau, \vec{r}) \psi(\frac{\vec{r}}{L}), \tag{12}$$

where L >> R, $\vec{k}_{o,0}$ is the value of $\vec{k}_{o,n}$ at which the mean-field structure factor (Eq.(9)) diverges and $c_0(\tau) >> c_n(\tau)$ for $n \neq 0$. For $\tau \sim 0$ the c_n for $n \neq 0$ can be neglected [22]. We are near a pronounced pseudo-spinodal so that we expect the critical droplet to have an interior structure similar to spinodal critical fluctuations [10](See Eq.(9).). Since a > 0 implies $\vec{k}_{o,0} = 0$, with the assumed form for $\epsilon(\vec{r})$ in Eq.(12) the Euler-Lagrange equation becomes

$$-\frac{a}{2}\nabla^{2}\psi(\frac{\vec{r}}{L}) + \frac{b}{4}\nabla^{4}\psi(\frac{\vec{r}}{L}) + 2\tau\psi(\frac{\vec{r}}{L}) - 4\psi^{3}(\frac{\vec{r}}{L}) + 6\psi^{5}(\frac{\vec{r}}{L}) = 0$$
 (13)

Since $k_x = k_y$ the term involving \tilde{U}^{bulk} gives no contribution and the $c_n(\tau)$ are chosen so that $G^3(\tau, \vec{r}) = G(\tau, \vec{r})$.

Since $\tau \sim 0$ the solution of Eq.(13) has the scaled form

$$\psi(\vec{r}) = D\tau^{1/2}\tilde{\psi}(\frac{B\vec{r}}{\xi}) \tag{14}$$

where the $\nabla^4 \psi(\frac{\vec{r}}{L})$ and $\psi^5(\frac{\vec{r}}{L})$ terms have been neglected since they are higher order in τ , B and D are constants that can be determined from Eq.(13) and $L = \xi$. This form of the solution is what we assumed when we calculated the contribution of the surface term in Eq.(6) for a smooth interface. Hence the omission of the surface term is justified self consistently as is the scaling of the bulk free energy used to compare with the surface contribution.

The nucleation barrier, ΔF , is calculated by inserting the critical droplet solution, Eq.(12), into the free energy [6], Eqs.(1-3). It is straightforward to see that $\Delta F \propto R^d \tau^{2-d/2} = A$. Therefore if $A = \infty$, the system is mean-field, rather than near-mean-field, and there is no nucleation.

Note that the saddle point object which is the nucleation droplet shows no evidence of the twin stripes seen in the simulation of the stable phase of this model [16]. The critical droplets near the pseudo-spinodal are unstable [2,10] and differ from the metastable phase by an order of magnitude given by $\tau^{1/2} \sim 0$. Their initial growth phase is a "filling in" or an increase in the order parameter difference. [2,10] The filled in droplet will have a sharp interface and hence must have twinning [16]. Therefore, the symmetry breaking which results in the twin stripes must appear in the growth phase. As we will see, if a, the coefficient of the $(\nabla \epsilon(\vec{r}))^2$ term, is negative the case is somewhat different. We treat this next.

For a < 0 and b > 0 we take the minus sign in the the structure factor in Eq.(9). Since $U^{bulk}(\vec{k})$ is independent of k, the value of k where the structure factor diverges is

$$k = \pm \frac{1}{2} \left[\frac{|a|}{4} \pm \left(\frac{|a|^2}{16} - \frac{(\tau + \tau_o)b}{2} \right)^{1/2} \right]^{1/2}, \tag{15}$$

where $0 \le \tau_o \le 4\rho$ is a fixed value of $U^{bulk}(\vec{k})$. For $\tau > \frac{|a|^2}{8b} - \tau_o$ there is no divergence for real k and hence no instability. Since the largest value of τ for which there is an instability is the spinodal then for a < 0, the spinodal is at $\tau_s = \frac{|a|^2}{8b} > 0$. The structure factor will now diverge at a non-zero value of $k = k_o$ where k_o is given by Eq.(15) with $\tau_o = 0$. Note that the additional instability generated by a < 0 is at a value of τ greater than $\tau = 0$ expected from a simple thermodynamics calculation. It is straightforward to calculate the exponents of the correlation length and the order parameter which have the same values as those at the $\tau = 0$ spinodal for a > 0.

Turning to the nucleation problem for a < 0 and initially ignoring the surface term, the Euler-Lagrange equation has the form

$$\int d\vec{r}' \tilde{S}^{-1}(\vec{r}') \epsilon(\vec{r} - \vec{r}') - 4\epsilon^3(\vec{r}) + 6\epsilon^5(\vec{r}) = 0, \tag{16}$$

where $\tilde{S}^{-1}(\vec{r})$ is given by the Fourier transform of the inverse of $S(\vec{k})$ in Eq.(9) with $U^{bulk}(\vec{k})$ replaced by $\tilde{U}^{bulk}(\vec{k})$. We again assume a solution of the form given in Eq.(12) where $\vec{k}_{o,0}$ is the vector at which the structure factor diverges with a < 0. Since $\tau_o = 0$ implies $k_x = k_y$ and $|\vec{k}_{o,0}|$ is given by Eq.(15), $\vec{k}_{o,0}$ is specified. We now expand $\psi(\frac{\vec{r}-\vec{r}'}{L})$ in a gradient expansion about $\frac{\vec{r}}{L}$ to obtain

$$\frac{-|a|}{2}\gamma_2\nabla^2\psi(\frac{\vec{r}}{L}) + (\tau - \tau_s)\gamma_0\psi(\frac{\vec{r}}{L}) - 4\psi^3(\frac{\vec{r}}{L}) = 0,$$
(17)

where, anticipating the scaling, higher order derivatives and higher powers of $\psi(\vec{r})$ have been neglected. The constants γ_0 and γ_2 are $\int d\vec{r} [\exp(i\vec{k}_{o,0}\cdot\vec{r}) + \exp(-i\vec{k}_{o,0}\cdot\vec{r})] \tilde{S}^{-1}(\vec{r})$ and $\int d\vec{r} r^2 [\exp(i\vec{k}_{o,0}\cdot\vec{r}) + \exp(-i\vec{k}_{o,0}\cdot\vec{r})] \tilde{S}^{-1}(\vec{r})$, respectively. As above, the c_n have been chosen so that $G^3(\tau,\vec{r}) = G(\tau,\vec{r})$. The solution of Eq.(17) is of the form

$$\psi(\frac{\vec{r}}{L}) = A(\tau - \tau_s)^{1/2} \tilde{\psi}(\frac{B\vec{r}}{\xi})$$
(18)

justifying the omission of higher order terms.

The strain field of the critical droplet

$$\epsilon(\vec{r}) \sim A(\tau - \tau_s)^{1/2} \left[\exp(i\vec{k}_{o,0} \cdot \vec{r}) + \exp(-i\vec{k}_{o,0} \cdot \vec{r}) \right] \tilde{\psi}(\frac{B\vec{r}}{\xi}), \tag{19}$$

where we have neglected terms with $n \neq 0$, is *not* that of the stable phase but *does* exhibit a spatial modulation of regions where $\epsilon(\vec{r}) \neq 0$. Consequently, the stable phase structure, as in the case a > 0 where there is no spatial variation in the strain, must evolve during the growth phase. Note that the solution, Eq.(18), justifies the omission of the surface term via an argument virtually identical to the one given above.

We have calculated the first critical droplet structures for nucleation from an "austenite" like phase to a twinned "martensite" like phase near the pseudo-spinodal in a system with elastic forces. The droplets do not have the stable phase structure as expected from classical nucleation [6,7] and in the a>0 case exhibit no spatial modulation. Droplets that do not have the stable phase structure have been predicted in the nucleation of the crystal from the melt [4,5] but this is the first indication of such a droplet structure in a crystal-crystal transition. It is also the first result that demonstrates the importance of the compatibility constraints to the phase transition kinetics.

It is important to note in systems with R >> 1 that classical nucleation is strongly suppressed. In the classical case the nucleation rate is proportional to $\exp(-\frac{R^d\sigma^d}{\Delta f^{d-1}})$ [6,7] where σ is the surface tension between the droplet and the surrounding metastable state and Δf is the free energy density difference between the stable and metastable states. For classical nucleation, near the coexistence curve, $\sigma \sim 1$ so that for R >> 1 nucleation is severely suppressed. In order to have nucleation in a reasonable time frame the quench must bring the system close to the pseudo-spinodal where $\sigma << 1$. Therefore, nucleation near the pseudo-spinodal will dominate the phase transition process in realistic experiments. Finally we note that the form of nucleation discussed in this Letter allows the possibility of evolution into metastable crystallites with symmetries different than the stable phase.

ACKNOWLEDGMENTS

This work was performed under the auspices of the DOE at the Los Alamos National Laboratory under grants DE-FG02-95ER14498, LDRD-DR-2001501 and W-7405-ENG-36. W.K. gratefully acknowledges the support and hospitality of the CNLS at LANL. D.H. gratefully acknowledges the support and hospitality of the T-11 Group at LANL.

REFERENCES

- [1] J. W. Cahn and J. E. Hilliard, Journal of Chem. Phys. **31**, 688 (1959).
- [2] D. W. Heermann and W. Klein, Phys. Rev. Lett. **50**, 1062 (1983).
- [3] L. Monette and W. Klein, Phys. Rev. Lett. 68, 2336 (1992).
- [4] W. Klein and F. Leyvraz, Phys. Rev. Lett. 57, 2485 (1986).
- [5] Y. C. Shen and D. Oxtoby, Phys. Rev. Lett. 77, 3585 (1996).
- [6] J. S. Langer, Annals of Physics 41, 108 (1967).
- [7] J. D. Gunton, P. S. Sahni, and M. S. Miguel, vol. 8 of *Phase Transitions and Critical Phenomena* eds. C. Domb and J. Lebowitz (Academic Press New York 1983).
- [8] D. W. Heermann, W. Klein, and D. Stauffer, Phys. Rev. Lett. 49, 1262 (1982).
- [9] M. Novotny, W. Klein, and P. A. Rikvold, Phys. Rev. B 33, 7729 (1986).
- [10] C. Unger and W. Klein, Phys. Rev. B **29**, 2698 (1984).
- [11] Z. Nishiyama, Martensitic Phase Transformations (Academic Press, New York 1978).
- [12] R. Oshima et al, Metall. Trans. A 19, 803 (1988).
- [13] G. B. Olson and A. L. Roitburd, Chapt. 9 of Martensite, ASM International, G. B. Olson and W. S. Owen eds. (1992).
- [14] A. C. E. Reid, G. B. Olson, and B. Moran, Phase Transitions 69, 309 (1999).
- [15] A. Borgenstam, Mat. Sci. and Eng., A273, 425 (1999)
- [16] S. R. Shenoy, T. Lookman, A. Saxena, and A. R. Bishop, Phys. Rev. B60, R12537 (1999).
- [17] S. Kartha et al. Phys. Rev. B **52**, 803 (1995).
- [18] S. R. Shenoy, T. Lookman, A. Saxena, and A. R. Bishop, (in preparation).
- [19] H. E. Stanley *Introduction to Phase Transitions and Critical Phenomena* (Oxford Univ. Press, New York, 1971).
- [20] J. D. Eshelby, Solid State Phys. 3, 79 (1957).
- [21] K. Binder, Phys. Rev. A **29**, 341 (1984).
- [22] W. Klein, Phys. Rev. E (submitted), cond-mat/0104342.