

Why is Bloch's $T^{3/2}$ -law also observed in d=2 dimensions ?

U. Krey,

Inst. für Physik II, Universität Regensburg, 93040 Regensburg, Germany

Oct. 30, 2002, updated Oct. 31, 2002; personal communication*

Abstract

Some arguments are given, related to the apparent universality with which Bloch's famous $T^{3/2}$ -law is not only found in d=3-dimensional ferromagnetic systems, but also in lower dimensions. It is argued that

- one should not simply apply the usual isotropic dispersion relation $\omega(\vec{k}) = D \cdot \vec{k}^2$ known to almost everyone but only valid for circular precession of the spins (i.e. where only the exchange interaction is taken into account), but instead one should consider also the other interactions and use the less-known relation $\omega(\vec{k}) = \sqrt{\omega_a(\vec{k}) \cdot \omega_b(\vec{k})}$ for *elliptical precession*,
- one might consider the apparent universality of Bloch's $T^{3/2}$ -law as some kind of 'quantum universality' in the finite-temperature region of a *quantum phase transition* at $T=0$,
- i.e. one should use certain *simple scaling arguments* for better understanding of the phenomena, instead of the usual, more complicated derivations by direct integration.

1 Introduction

This is some kind of 'discussion letter', i.e. a personal communication not intended for publication, but directly sent to few people interested

*e-mail: uwe.krey@physik.uni-regensburg.de ; updated versions of this communication at <http://www.physik.uni-regensburg.de/forschung/krey/commbloch.ps.gz>

in the problems related to the temperature dependence of the magnetization, i.e related to the famous Bloch's $T^{3/2}$ -law and generalizations thereof. The author simply hopes that some of the addressees just might read this text and communicate their questions, critique, and/or insights (also simply by e-mail) to him or perhaps to each other.

The letter grew out of discussions following a recent presentation of certain experimental results in our institute, [1], and although I do not think that the considerations presented below are worth being published, some of the participants of those discussions suggested that I should write down what I think. So here I do so, just hoping to broaden and intensify the discussion in this way.

2 Bloch's law

According to this law, the temperature dependence of the magnetization $M_s(T)$ of a bulk 3-dimensional ferromagnet is simply given by

$$M_s(T) = M_s(0) - \text{const.} \times \int_{BZ} d^3k \frac{1}{\exp \beta \epsilon(\vec{k}) - 1}, \quad (1)$$

because each excited magnon reduces the magnetic moment of a ferromagnetic sample by 2 Bohr magnetons.

Here T is the Kelvin temperature, $\beta = (k_B T)^{-1}$, where k_B is Boltzmann's constant, \vec{k} is the wavenumber, and BZ the Brillouin zone. For the excitation energy $\epsilon(\vec{k})$ of a 'magnon' in an Heisenberg ferromagnet (and also in itinerant ferromagnets where the spin-orbit interaction, and also the Stoner excitations, are neglected against the collective magnon-like spin excitations) one simply has (for simplicity we assume cubic symmetry): $\epsilon(\vec{k}) = D \cdot k^2$, where D is the so-called spin-wave stiffness. Therefore, by the substitution $x := \beta D \cdot k^2$ and the replacement $d^3k = 4\pi k^2 dk$ one gets the famous result $M_s(T) = M_s(0) - \text{const.}' \cdot (\frac{k_B T}{D})^{3/2}$, where (up to exponentially-small terms) the constant $\text{const.}' = \text{const.} \times 2\pi \int_0^\infty \frac{x^{1/2} dx}{\exp x - 1}$.

For Anderson's "poor man", instead of the usual derivation, one can also give the following simple argument: $\exp \beta D q^2 - 1$ is approximated for long enough wavelengths and/or high enough T by the

'quasi-classical thermal-energy approximation' $\beta D \cdot k^2$, so that one simply gets $M_s(T) = M_s(0) - \text{const.} \cdot (\frac{k_B T}{D}) \times PhsR(T)$, where $PhsR(T)$ means a typical phase-space radius in k-space, replacing the integral $\int_0^{\pi/a'} \frac{4\pi k^2}{k^2} dk$. Here ' π/a' ' represents a (very large) wavenumber-cutoff corresponding to the upper edge of the Brillouin zone, which is replaced by a sphere as in typical renormalization group arguments. But it would be wrong, if at this place one would perform directly the integration (after having made the above-mentioned quasi-classical approximation leading to the 'thermal energy prefactor' $(\frac{k_B T}{D})$); instead, one gets the correct $PhsR(T)$ by a Pippard-type argument, i.e. simply by equating the *dominating* energy- resp. temperature-ranges: $\epsilon(\vec{k}_{\text{dom.}}) = D \cdot k_{\text{dom.}}^2 \cong k_B T$, i.e. $PhsR(T) \cong k_{\text{dom.}} (\cong \Delta k) \propto (\frac{k_B T}{D})^{1/2}$.

What would be different in a planar system? One would again expect a quasi-classical (i.e. 'high- T ') approximation $\exp \beta \epsilon(\vec{k}) - 1 \rightarrow \beta \epsilon(\vec{k})$, but instead of $\epsilon(\vec{k}) = D \cdot k^2$ one would have $\epsilon(\vec{k}) = \sqrt{\epsilon_a(\vec{k}) \cdot \epsilon_b(\vec{k})}$, i.e. a pronounced elliptical precession instead of the circular one. E.g., if one is dealing with a film of infinite extension in the x- and y-directions, with finite thickness in the z-direction, then – if the film is magnetized in the x-direction, spin-wave deviations in the z-direction are strongly disfavoured energetically, due to the demagnetizing field $H_z^{\text{DM}} = -4\pi M_z$. Thus, one would have $\epsilon_b(\vec{k}) \equiv \epsilon_z(\vec{k}) = C_b + D \cdot k^2 (\cong C_b$ in the long-wavelength limit, where $C_b = \mu_B 2\pi M \times \text{Volume}$ is the effective anisotropy energy corresponding to the demagnetizing field). In contrast, spin deviations in the y-direction would not be disfavoured, i.e. $\epsilon_a(\vec{k}) \equiv \epsilon_y(\vec{k}) = D \cdot k^2$, as before.

As a consequence, for $k^2 \cdot l_{\text{exch}}^2 \lesssim 1$, where $l_{\text{exch}} = \sqrt{\frac{C_b}{D}}$ is an effective 'exchange-length', one would not have $\epsilon(\vec{k}) = D \cdot k^2$, but instead $\epsilon(\vec{k}) = D' \cdot k^1$, where $D' = \sqrt{C_b \cdot D}$.

This change of the spin-wave dispersion at small wavenumbers by the magnetostatic fields was already noted years ago by an early paper of P. Bruno, [2], who stated (among other things) that exactly in this way the famous Mermin-Wagner theorem (which says that in the Heisenberg model there cannot be magnetic long-range order in d=2 dimensions) is invalidated by a 'cut-off effect' related to the magnetostatic interactions, which are not considered in the Heisenberg model,

[3]. However, note that for the existence of an elliptical precession and of the planar uniaxial anisotropy, we do not need in principle a finite thickness of the magnetic film, i.e. it can also just be a monolayer.

So I suggest that in planar systems (magnetized 'in the plane' by the simultaneous influence of the exchange interaction and an effective in-plane uniaxial anisotropy), $M_s(T)$ should behave as

$$M_s(T) = M_s(0) - \text{const.}' \times \left(\frac{k_B T}{D'}\right) \times PhsR(T) \quad (2)$$

Here one expects a similar 'quasi-classical thermal-energy factor' $\left(\frac{k_B T}{D'}\right)$ as before, but the phase-space factor is now $PhsR(T) \cong \int_{l_{\text{exch}}^{-1}}^{\pi/a'} 2\pi \frac{k^1 dk}{k^1}$.

In this formula, the changes of the exponents of the nominator and of the denominator, both exponents changing from 2 to 1, result (for the denominator) from the fact that for $k^2 \cdot l_{\text{exch}}^2 \lesssim 1$ the exponent in the dispersion relation has changed from 2 to 1, whereas the change in the nominator comes from $d^2 k \sim k^1 dk$. But thermodynamically, the dominating modes are spin waves with $\epsilon(\vec{k}) = Dk^2$, since for $k^2 l_{\text{exch}}^2 \gtrsim 1$ one gets this quadratic dispersion, and so $PhsR(T)$ should once more be proportional to $\left(\frac{k_B T}{D}\right)^{\frac{1}{2}}$, i.e. also $PhsR(T)$ is essentially unchanged. As a consequence, one has again Bloch's $T^{3/2}$ -law: $M_s(T) = M_s(0) - \text{const.}'' \cdot T^{3/2}$ (although probably with a different constant).

In any case, it would again be wrong¹ to replace our simple scaling arguments by a direct integration, which would lead to the Döring-type behaviour, [4]

$$M_s(T) = M_s(0) - \text{const.}''' \times k_B T \cdot \int_{l_{\text{exch}}^{-1}}^{\pi/a'} d^2 k \frac{1}{k^2}, \quad (3)$$

i.e. to $M_s(T) = M_s(0) - \text{const.}''' \times T \cdot \ln \frac{T}{T_0}$, where T_0 is a constant temperature unit. As far as I know, this has never been observed.

¹Of course one should ask, why: An answer might be that (apart from the fact that one should always be careful with the interchange of limits) the effective number of magnons might be considerably reduced w.r.t. (1) by magnon-magnon interaction, thus explaining the deviation of our $T^{1/2}$ -phase space factor from the result of the direct integration

3 Is all this related to quantum phase transitions ?

Obviously, the detailed behaviour earns a more thorough study; actually, there is also the recent thorough analysis of an extremely large set of experimental results by U. Köbler, [5], which leads to an apparently universal classification for the behaviour of $M_s(T)$, although the arguments look quite complicated. The universality of the classification reminds to second-order phase transitions (i.e. for thermal phase transitions there is the well-known 'Griffiths Universality Hypothesis', [6]). But since here the universality is in the low-temperature scaling, and not in the scaling in the vicinity of the Curie temperature, the 'Griffiths universality' does not apply, and one is probably dealing with 'Quantum Phase Transitions', i.e. one is in the finite-temperature region of a weakly unstable 'quantum fixed point' and should consider the flow-lines in a diagram joining that 'quantum fixed point' and the thermal 'Curie' fixed point (see the Appendix). According to the recent book of S. Sachdev, [7], in this finite-T-region one should have a very wide range of scaling behaviour, which would explain the wide range of applicability of Bloch's law.

The experimental analysis of Köbler is additionally remarkable because of the fact that his generalized 'Bloch's law exponent'² depends on whether the spin-quantum number s of the magnetic atoms is *integer* or *half-integer*. In a quasi-classical approximation this distinction makes no sense, but in the context of a quantum phase transition it does. E.g. for an atom with half-integral spin a change $m \rightarrow (m - 1)$ would correspond to the flipping of a spin (e.g. $s = 1/2$), or for $s = m \geq 3/2$ to an essentially continuous reduction of the local magnetization, whereas for integer spins, e.g. $s = 1$, the change, e.g. $m = 1 \rightarrow m = 0$, might correspond to perfect vanishing of all local magnetic properties³.

As a consequence, one should re-consider the behaviour of $M_s(T)$ in the context of renormalization-group flow lines of quantum phase transitions. Perhaps, in this way one can better understand and unify

²This exponent, η , is defined by a power-law behaviour $M_s(T) = M_s(0) - \text{const. } T^\eta$.

³E.g. there is a pronounced difference in the thermodynamics of the Ising model, where all atoms have $s = 1/2$, and of Blume-Capel or Blume-Emery-Griffiths models, where a considerable part of the atoms have $s = 1$.

the Bloch-like behaviour in thin films and related (patterned) nanostructures, also for more complicated models as those advocated by U. Köbler, by simple scaling laws for various classes of models, arising from such an approach.

Acknowledgements

The author acknowledges stimulating communications from U. Köbler and fruitful discussions with C. Back, G. Bayreuther, R. Höllinger, A. Killinger, W. Kipferl, and J. Siewert.

References

- [1] W. Kipferl, *Spin-wave excitations in epitaxial Fe(001)-nanostructures on GaAs*, unpublished seminar talk, University of Regensburg, October 2002
- [2] P. Bruno, *Spin-wave theory of two-dimensional ferromagnets in the presence of dipolar interactions and magnetocrystalline anisotropy*, Phys. Rev. B **43** (1991) 8015
- [3] Actually, although rarely discussed, the square-root dispersion was already known much earlier, e.g. to Ch. Kittel, or to W. Döring, but they did not yet see the consequences, e.g. those calculated in [2].
- [4] W. Döring, *Über den Ferromagnetismus des Flächengitters*, Z. Naturforsch. **16a** (1961), 1008 (in German)
- [5] U. Köbler, Various recent papers, e.g. *Temperature dependence of the spontaneous magnetization of body-centred-cubic bulk iron, amorphous iron and thin iron films*, J. Phys.: CM **14** (2002) 8861
- [6] W. Gebhardt, U. Krey, *Phasenübergänge und Kritische Pänomene*, Vieweg, Wiesbaden, (1981, in German)
- [7] S. Sachdev, *Quantum Phase Transitions*, Cambridge University Press (1999)

Appendix:

Crossover-scaling from the quantum fixed point to the thermal fixed point for in-plane magnetized films

We consider a planar cartesian coordinate system, where along the horizontal axis ('x-axis') the (non-negative) reciprocal uniaxial anisotropy is plotted, i.e. $(C_b)^{-1} \rightarrow \dots$, whereas on the perpendicular axis ('y-axis') the temperature is plotted, i.e. $T \rightarrow \dots$. On the horizontal axis one has an 'ordered segment' ranging from $(C_b)^{-1} = 0$ up to a critical value (corresponding to a minimal necessary uniaxial anisotropy C_b^{\min}); if we equate this minimal anisotropy to an effective temperature T_x , i.e. $k_B T_x = C_b^{\min}$, then $(k_B T_x)^{-1}$ corresponds to our quantum fixed point. On the outer segment of the horizontal axis, i.e. from $(C_b)^{-1} \equiv (C_b^{\min})^{-1}$ to $(C_b)^{-1} = \infty$, the quantum fluctuations, which are always present in the case of elliptical spin precession, destroy $M_s(T=0)$ to zero.

From the quantum fixed point a flow line emerges, at first with a positive vertical slope, but soon turning to the left, resembling a flat elliptical segment running almost parallel to the x-axis in the direction of the y-axis, where it arrives, almost horizontally, at a small crossover temperature T^* , see below⁴. On the other hand, at the vertical axis one has a similar situation, namely long-range order up to a thermal critical temperature (Curie temperature) T_c , which is of the order of $D \cdot (\frac{\pi}{a})^2 / k_B$ ⁵. From this Curie fixed point an (attractive) flow line emerges, which starts at first horizontally, but soon turns downwards almost vertically, until it meets the horizontal axis roughly at $(k_B T^*)^{-1} (\ll (k_B T_x)^{-1})$, i.e. roughly at the crossover point, where $k_B T^* \approx \sqrt{C_b \cdot D \cdot (\pi/a)^2}$.

Now, what counts in the above-mentioned Bloch behaviour, is on the one-hand the thermal energy factor $k_B T$, and on the other hand the effective phase space radius $\propto (k_B T)^{1/2}$ corresponding to only the vertical

⁴The value of T^* does practically not change if one starts the flow not at the fixed point value C_q^{\min} , but at larger values.

⁵Actually, things are more complicated, since e.g. the Curie temperature of a Heisenberg-model with a general value of s is $\propto s^2$, whereas the largest magnon energy is only $\propto s$.

segment $T > T^*$ of the flow line.