

# Mechanical Spectroscopy on Volcanic Glasses

Norman Wagner

*Institute of Material Research and Testing at the Bauhaus-University Weimar,  
Amalienstr. 13, 99423 Weimar  
Tel: ++49-3643-564-221  
Fax: ++49-3643-564-202*

Klaus Heide

*Institute of Geoscience, Friedrich-Schiller-University Jena,  
Burgweg 11, 07743 Jena*

---

## Abstract

Mechanical relaxation behaviour of various natural volcanic glasses have been investigated in the temperature range  $RT - 1000^\circ\text{C}$  using special low frequency flexure ( $f \approx 0.63\text{Hz}$ ) pendulum experiments. The rheological properties complex Young's modulus  $M^*(\omega, \tau)$  and internal friction  $Q^{-1}(\omega, \tau)$  have been studied from a pure elastic solid at room temperature to pure viscous melt at  $\log(\eta[\text{Pas}]) = 8$ . The Young's modulus at room temperature  $M_{RT} = (70 \pm 10)\text{GPa}$  is nearly constant. There is a positive correlation with the water content and a weak negative correlation with the cooling rate. Several relaxation processes are assumed to act: the primary  $\alpha$ -relaxation (viscoelastic process,  $E_a = (344...554)\text{kJ/mol}$ ) above the glass transition temperature  $T_g = (935...1105)\text{K}$  and secondary anelastic  $\beta'$ ,  $\beta$  and  $\gamma$ -relaxation processes below  $T_g$ . The dynamic glass transition, i.e. the viscoelastic  $\alpha$ -transition, can be characterized with hierarchically coupled relaxation processes which lead to an equivalent distribution of relaxation times nearly independent of the fragility for all examined glasses. The observed secondary relaxation processes can be explained with different mechanisms: ( $\gamma, \beta$ ) cooperative movement of alkali ions in the vitreous state. ( $\beta'$ ) cooperative movement of alkaline earth ions and non bridging oxygen's near the glass transition range. Here the influence of water must be taken into account as well as alteration effects due to structural  $\alpha$ -relaxation. With a simple fractional Maxwell model with asymmetrical relaxation time distribution,  $H(\tau)$ , phenomenological the mechanical relaxation behaviour, is described. This establish a basis of realistic concepts for modelling of volcanic or magmatic processes.

---

\* norman.wagner@mfpa.de

# 1 Introduction

It is of great importance today, in material and geoscience, to be able to understand and predict the mechanical response (elasticity, anelasticity and viscoelasticity) of multicomponent silicate glasses and melts ((PS92), (Web97), (BZKH97), (Don01), (SSHB03), (DRVdB03), (MBJ<sup>+</sup>03), (Buc03a), (WBH04)). The evolution of terrestrial planets is determined by the rheological properties of silicate melts and their stability under different atmospheric conditions. An important roll plays the water content as well as the chemical composition of the natural materials which reflect and cause the evolution processes ((MS99)). By optical microscopy we know already since more than one hundred years textural patterns in vitreous and crystalline volcanic rocks ((Zir73), 1). This observations clearly indicate degassing induced crystallization as well as a high mobility of crystalline phases in the magma and lava during the emplacement process ((Hei89), (SML<sup>+</sup>00)). According to theoretical and experimental investigations of (GH96) formation of such patterns are only possible below viscosities  $\log(\eta[Pa\cdot s])=4$ , i.e. at temperatures far above the glass transformation range. In the case of rhyolitic glasses at approximately  $1300^{\circ}C$  under atmospheric conditions, i.e. far above field experience of emplacement of dacitic lava at  $\approx 925^{\circ}C$  (Tab. 1).

In addition in daily life silicate melts products are ubiquitous. Natural handling with glass usually misleads us to believe that the glass transition is one of the ten great outstanding challenges in physics ((GYI<sup>+</sup>01), (Nga00), (ANM<sup>+</sup>00), (Don01), (DS01)).

From a geoscientific point of view, experimental vulcanology and petrology examine the structure, dynamics and properties of natural and synthetic silicate systems ((PK91), (Sax92), (SMD95), (Mys03)). The rheological properties determine emplacement mechanisms generally and the hazard implications especially ((Fin90), (Smi97), (MS99)). Whereby fragmentation of vesicular magma

Table 1

Estimated extrusion temperatures from field observations as well as calculations from the mineralogy of various high viscose lavas ((Hal96))

Locality	Rock type	Temperature [ $^{\circ}C$ ]
Taupo, New Zealand	Rhyolite lava and pumice	735-890
Mono Craters, USA	Rhyolite lava	790-820
Island	Rhyodacite obsidian	900-925
New Britain	Andesite pumice	940-990
New Britain	Dacite lava and pumice	925
New Britain	Rhyodacite pumice	880




Fig. 1. (top) Copperplate engraving by Zirkel 1873 of a “magnetite spider” in an obsidian from Armenia (adapted from (Zir73)). (bottom) Turbulent hairline magnetite (fibres) in vitreous matrix of obsidian from Graber, Armenia together with fluidal adjusted bubbles.

is one of the main processes governing explosive volcanism ((Din96), (Pap99), (GM03)). Besides the material consuming and dangerous direct observation of lava flows it is also in some cases possible to reconstruct the emplacement history from microscopic texture in combination with experimental techniques under laboratory conditions ((Hei89), (Fin90), (MCCL98), (CC99), (ML01), (RM02), (CMC02), (CTCa04), (CTC04)). As products of very viscous melts

volcanic (rhyolitic in particular) glasses (obsidian) are the link to the melt. The characterization of rheological properties of these volcanic glasses are the subject of this work.

The material property, by which glass formation is determined, is the viscosity  $\eta$  or the structural or  $\alpha$ -relaxation time  $\tau_\alpha$ . Their dependence on pressure  $P$ , temperature  $T$ , chemical composition  $X$ , bubble content  $c_b$ , crystal content  $c_{xx}$  and volatile content  $c_v$  represents the goal of intensive geoscientific investigations ((BW72), (Sha72), (Ric84), (HA85), (Per91), (PS92), (SS92), (BDW94), (SDWB95), (LR95), (SDWS96), (Bak96), (HDW96), (BD97), (MCCL98), (SBDR98), (BLT00), (ML01), (SMCF01), (SBR01), (GD03)).

Since in the glass transition range the relaxation time reaches orders of magnitude, which are no longer accessible under laboratory conditions. Thus, the transition from viscous melt to solid elastic body, i.e. the viscoelastic response, determines the material behavior ((Ver92), (BD93), (BDW93), (BD97), (Bag99), (BMP<sup>+</sup>01), (Web97), (DGBP97a), (DGBP97b), (DG97), (DGB<sup>+</sup>97), (Duf98), (MBJ<sup>+</sup>03), (WBH03), (WJ03)).

In the vitreous state the structure of the melt is frozen in, however, here in addition dynamic processes (mobility of ions in the glassy network) take place, which can be measured by mechanical spectroscopy as internal friction, whereby a small water content cause unresolved phenomena ((Roe41), (Fit51a), (Fit51b), (Roe58a), (Roe58b), (RR61), (Coe61), (DR62a), (DR62b), (DS69), (SD69), (MD70), (SD70), (DS72), (Roe74), (Roe75), (DS74), (Day74b), (Day74a), (VS74), (TR74), (ZRD76), (TB79a), (TB79b), (Bar83), (Ver92), (Ke96), (BL96), (BZKH98a), (RI98b), (RI98a), (Rol01)).

In this study the rheological properties, Young's moduls  $M^*$  and internal friction  $\tan \delta = Q^{-1}$ , of natural volcanic glasses have been investigated in a wide temperature range from a purely elastic solid at room temperature to purely viscous melt at a viscosity  $\log(\eta[Pa\cdot s]) \approx 8$ . It will contribute to the understanding of the thermocinetics and dynamics that govern the glass transition, at temperatures well above, below and at the glass transition temperature  $T_g$  ((Don01)). In this context the rheological properties of natural and synthetic silicate glasses and melts are of interest. With a simple generalized fractional Maxwell model, the relaxation behavior is described phenomenologically. This establish a basis of realistic concepts for modelling of volcanic or magmatic processes.

## 2 Basics

A necessary and sufficient condition to glass formation is a corresponding (critical) cooling rate  $q_K$  to avoid crystallization. A coarse approximation for the estimate of  $q_K$  gives (Owe85), (Fel83) and (Deb96):

$$q_K = 2 \cdot 10^{-6} \frac{T_m^2 R}{V \eta(T_n)} = \frac{T_m - T_n}{\tau_{K,n}} \quad (1)$$

with the fusing temperature  $T_m$ , the gas constant  $R$ , the molar volume  $V$ , viscosity  $\eta$ , the so called nose temperature  $T_n$  and corresponding critical time  $\tau_{K,n}$ . Here, according to (Deb96) or (Ang88) the time  $\tau_K$  for formation of a critical volume  $V_K$  as well as the structural relaxation time  $\tau_\alpha$  and their interplay (time-temperature-transformation) is of great significance (cf. Fig. 2). Above the thermal glass transition temperature  $T_g^{exp}$  specified by the experimental conditions, which is determined by a characteristic structural or  $\alpha$  relaxation time  $\tau_\alpha$ , the mechanical glass transition occurs at the ‘mechanical’ relaxation time  $\tau_\alpha(T_\alpha)\omega \approx 1$ . The mechanical glass transition temperature  $T_\alpha$  shifts with measurement frequency  $\omega = 2\pi f$  in general via the Arrhenian equation

$$\ln\left(\frac{\Omega}{\omega}\right) = \frac{E_a(T)}{k_B T_\alpha} \quad (2)$$

with jump frequency  $\log(\Omega[Hz]) \approx 12 - 14$  as typical frequency of molecular vibration ((RGD03)), Boltzmann-constant  $k_B$  and a temperature dependent activation energy  $E_a(T)$  with  $\frac{dE_a}{dT} \leq 0$  ((GS95), (BL96)). The most common entrances to the modelling of the temperature dependence of the activation energies are:

- (1) the empirical VFT-equation ((Vog21), (Ful25), (TH26)) with the adjustable parameters  $B_{VFT}$  and  $T_0$  ( $T_0$  is usually equated with the Kauzmann-temperature ((Hod94), (Hod97)))

$$E_a(T) = \frac{B_{VFT}}{1 - \frac{T_0}{T}}. \quad (3)$$

- (2) the Adam-Gibbs-equation ((AG65)) with the adjustable parameter  $B_{AG}$  and a temperature dependend configurational entropy  $S_c(T)$

$$E_a(T) = \frac{k_B B_{AG}}{S_c(T)}. \quad (4)$$

- (3) the Avramov-equation ((AM88)) with a dimensionless activation energy




Fig. 2. Schematic representation to the construction of the  $TTT$ -curve (time-temperature-transformation). (a) isobar dependence of the free enthalpy  $G$  on temperature  $T$  of a gas, a liquid (stable and supercooled liquid), and a crystal as well as the corresponding glass of a pure substance with the boiling point  $T_B$ , melting point  $T_m$  and the glass transition temperature  $T_g$ . (b) The hypothetical intersection point between  $\tau_K$  and  $\tau_\alpha$  is not reached, since (c)  $\tau_K$  goes up strongly due to the drastic viscosity increase with  $\tau_\alpha$  (after (Deb96)).

$\varepsilon_A$ , the Avramov fragility index  $\alpha_A$  and the glass transition temperature  $T_g$  at a viscosity of  $\log(\eta[\text{Pas}]) = 12.3$

$$E_a(T) = \frac{k_B \varepsilon_A T_g^{\alpha_A}}{T^{\alpha_A - 1}}. \quad (5)$$

(4) the Williams-Landel-Ferry-equation (WLF, ((WLF55)) with the parameters  $A_{WLF}$ ,  $B_{WLF}$  and the fragility index  $m = \left. \frac{d \ln(\tau_\alpha)}{d(T_g/T)} \right|_{T_g}$  at the glass transition temperature  $T_g$  ((BA92), (Don01))

$$E_a(T) = mT - \frac{A_{WLF} T (T - T_g)}{B_{WLF} + (T - T_g)}. \quad (6)$$

$\log(\Omega)$  and the Kauzmann-Temperature  $T_0 \approx (48 \dots 815) \text{K}$  are the asymptotes concerning the frequency or temperature ((Don81), (Don92), (Don01), (Hod94), (ANM<sup>+</sup>00)).

The mechanical glass transition for small deformations  $10^{-4}$  is the linear viscoelastic response of the material. Then the linear response is completely determined by properties of the equilibrium melt if thermal fluctuations are included in the equilibrium concept. The fluctuation-dissipation theorem (FDT) of statistical physics implies the important statement that it is exclusively thermal fluctuations which determine the linear response ((Don01), (Rol01)). Especially for the understanding of processes<sup>1</sup> on a geological time scale these concepts are very useful ((NJ03)). Nonlinearity has to be taken into account for large deformations and high strain rates, i.e. under emplacement conditions ((BD93), (DT94), (DT96), (REH00), (BB00), (BM02)).

Above a critical temperature  $T_C$  predicted by the idealized mode coupling theory, *MCT*, the system is retained to ergodic and below non-ergodic ((GS92)). Non-ergodicity means that the correlation function  $\Phi$  does not converge against an expected equilibrium value of  $\lim_{t \rightarrow \infty} \Phi(t) = \Phi_\infty = 0$ , but reaches a final value  $\Phi_\infty > 0$ . Since the corresponding coupling parameters are temperature dependent, one finds the critical temperature  $T_C$  if the existence of a non-ergodic stage to the first time have been observed. In this sense one speaks of a phase transition at the glass transition but the precise designation is ergodicity transition. That is, that density fluctuations froze below  $T_C$ . Above  $T_C$  the structural  $\alpha$ -relaxation and second  $\beta$ -relaxation can not be distinguished. Below  $T_C$  diffusion processes and the structural  $\alpha$ -relaxation are to be observed separately. In the internal friction spectrum the characteristic secondary  $\beta$  loss maxima occur. Ergodicity can be restored by introduction of hopping-processes in the enlarged MCT also below  $T_C$ . The temperature dependence of the  $\alpha$ -time scale for  $T > T_C$  is of the form ((Sch00a), (Don01)):

$$\tau_a \propto \eta \propto (T - T_C)^\gamma. \quad (7)$$

with a parameter  $\gamma$ . The following general rule is valid ((Buc03b))

$$\tau_\alpha(T_c) \approx 10^{-7} s. \quad (8)$$

The distinction of the dynamics of the primary  $\alpha$  process and a  $\beta_{fast}$  process (in the sense of a microscopically fast movement) above  $T_C$  in the field of the undercooled liquid is predicted, however, through the *MCT* and confirmed by neutron and light scattering experiments onto different glass formers as well as through computer simulations ((RS96), (SR97), (HK02), (Buc03b)). The main problem with the *MCT* consists in the analysis of the  $\alpha$ -process. So (7) can only be observed experimentally in a small temperature range. If one identifies  $T_C$  with the Vogel temperature  $T_0$  or the glass transition

---

<sup>1</sup> Within glass science these processes called 'Thermometereffekt' according to internal friction investigations of (Roe41).

temperature  $T_g$ , then experimental relaxation times and (7) are not to bring into agreement. A comparison with experimental data leads to the reasonable statement  $T_C > T_g > T_0$  and  $T_C/T_g \approx 1.3...2.6 \propto 1/m$  for silicate melts ((Hes96), (Pfe98)). There according to the mode coupling theory for  $T < T_C$  the  $\alpha$  process no more is supposed to occur but is experimentally even strongly observed at  $T \approx T_g$ . For this reason one is today generally of the opinion, that the mode coupling approximation is a good theory for  $T > T_C$  and break down for temperatures below  $T_C$  especially for strong melts. In spite of these difficulties the *MCT* is today the widest driven forward analytical representation, that understands essential appearances of the glass transition correctly and contains also many possibilities of a generalization ((Sch00b)).




Fig. 3. Schematic representation of thermocinetic and dynamic  $\alpha$ -transition of an inorganic-glass or melt and related phenomena:  $\gamma_{R^+}$ -alkali ion transport,  $\beta_{H_2O}$  - water peak,  $\beta'$ - superposition of Johari-Goldstein relaxation and the thermal glass transition (c.f. (Dol02)).

During cooling, the mobility of the atoms decrease. At the (nonlinear) thermal glass transition range (the relaxation time is a function of temperature  $T$  and the structural state  $\tau(T, T_f)$ ) typical relaxation times are reached by seconds or minutes, in order to take the (metastable) equilibrium position. If the temperature now falls, the structure can not reach their equilibrium and is therefore “trapped” in a definite configurational state at the limit of the fictive temperature  $T_f$  ((Too41), (GN70), (Mar85)). (Rit56),



(MRBVG87), (RN92), (WWD95), (WWD96b), (WWD<sup>+</sup>96a), (WDBW00), (GD01a), (GD01b), (DS01), (TL01)). In the vitreous state it is possible to measure  $\beta$  or secondary mechanical relaxation processes which are substantially decoupled of the structural  $\alpha$  relaxation (c.f. Fig. 3). This processes can be explained with different mechanisms: ( $\gamma, \beta$ ) cooperative movement of alkali ions in the vitreous state. ( $\beta'$ ) cooperative movement of alkaline earth ions and non bridging oxygen's near the glass transition range. Here the influence of water must be taken into account as well as alteration effects due to structural  $\alpha$ -relaxation. The temperature dependents of diffusion, electrical conductivity and mechanical relaxation processes can be described in most cases by an Arrhenian-law via equation (2) with an equivalent activation energy (see (Fri75), (Pau98), (Maa99), (Nga00)).

Relaxation processes (ion mobility, viscoelasticity) deviating from the classical exponential (Debye) behavior are often encountered in the dynamics of complex materials such as silicate glasses below and above  $T_g$ , glass ceramics and partially molten rocks ((Jon77), (Mue83), (KB85), (BD93), (Web97), (RI98b), (ANM<sup>+</sup>00), (Don01), (Nga00)). In many cases experimentally observed relaxation functions exhibit a stretched exponential (Kohlrausch-Williams-Watts) decay (Koh47)

$$\Phi \propto \exp\left(-\left[\frac{t}{\tau}\right]^{\beta_{KWW}}\right) \quad (9)$$

with  $0 < \beta_{KWW} < 1$ , or a scaling decay

$$\Phi \propto \left[\frac{t}{\tau}\right]^a \quad (10)$$

with  $0 < a < 1$  ((BD93), (BDW93), (BD97), (Bag99), (BLT00), (MBJ<sup>+</sup>03)). An appropriate tool to describe phenomenologically this richness of dynamical features is fractional calculus (*FC*, see below) ((SOB95)).

## 2.1 Rheological models

Usually phenomenologic viscoelastic models are based on springs and dampers. A spring is purely elastic and describes the instantaneously acting Hooke law with the dynamic responses (complex modulus  $M^* = M' + iM''$  with storage modulus  $M'$  and loss modulus  $M''$  or complex creep compliance  $M^* \cdot D^* = 1$ ) being constant and real ( $M''/M' = Q^{-1} = 0$ ). The constitutive equation of stress  $\sigma$  and strain  $\varepsilon$  is of the form

$$\sigma(t) = M_0 \varepsilon(t), \quad M^* = M' = M_0 = D_0^{-1} \quad (11)$$

with an idealized Young's modulus  $M_0$ . A damper is purely viscous and describes the instantaneously acting Newton law with purely imaginary dynamic responses ( $Q^{-1} = \infty$ ) (Don92):

$$\sigma(t) = \eta \frac{d\varepsilon(t)}{dt}, \quad M^* = iM'' = i\omega\eta \quad (12)$$

Through combinations of springs and dashpots one arrives at standard viscoelastic models, such as the Maxwell or the Zener, these models involve a fairly small number of single elements. The problem here is that the corresponding ordinary differential equations have a relatively restricted class of solutions, which is, in general, too limited to provide an adequate description for the complex systems discussed in the introduction. To overcome this shortcoming one can relate stress and strain through fractional equations ((SOB95)):

$$\sigma(t) = M_0\tau^\beta \frac{d^\beta \varepsilon(t)}{dt^\beta} \quad (13)$$

with  $0 \leq \beta \leq 1$  and the relaxation time  $\tau$ . In this way one readily obtains scaling decays. In general,  $FC$  allows the interpolation between the purely elastic behaviour of equation (11), obtained for  $\beta = 0$  in equation (13), and the purely viscous pattern of equation (12), obtained for  $\beta = 1$  in equation (13). (SB93; SOB95; SB95; SMBN95; HB94; Hey96) and (Hey96) have demonstrated that the fractional relation, equation (13), can be realized physically through hierarchical arrangements of springs and dampers, such as ladders, trees or fractal structures. We now introduce the term fractional element ( $FE$ ) to denote such a hierarchical structure and specify it by the triple  $(\beta, M_0, \tau)$ .

## 2.2 Fractional Maxwell model

The classical viscoelastic Maxwell model (composed of a linear elastic element and a linear viscous element in series) may be modified by replacing the damper by a  $FE$ . The dynamic responses for this model is:

$$\frac{M^*(\omega, \tau)}{M_0} = \frac{(i\omega\tau)^\gamma}{1 + (i\omega\tau)^\gamma}, \quad \frac{D^*(\omega, \tau)}{D_0} = 1 + (i\omega\tau)^{-\gamma} \quad (14)$$

which is the so called Caputo-Model ((BLT00), (Bag99)) or Cole-Cole-Model ((CC41)). In the high temperature and low frequency limit (14) leads to constant- $Q^{-1}$ . For  $\gamma = 1$  (14) is transformed to the classical Maxwell model. When both elements are replaced by  $FE$ 's the dynamic responses is of the

Jonscher-type ((Jon77)):

$$\frac{M^*(\omega, \tau)}{M_0} = \frac{(i\omega\tau)^\alpha}{1 + (i\omega\tau)^{\alpha-\beta}}, \quad \frac{D^*(\omega, \tau)}{D_0} = (i\omega\tau)^{-\alpha} + (i\omega\tau)^{-\beta} \quad (15)$$

with  $\beta < \alpha$  and the constitutive equation is of the form:

$$\sigma(t) + \tau^{\alpha-\beta} \frac{d^{\alpha-\beta} \sigma(t)}{dt^{\alpha-\beta}} = M_0 \tau^\alpha \frac{d^\alpha \varepsilon(t)}{dt^\alpha} \quad (16)$$

Since  $0 \leq \beta < \alpha \leq 1$  the condition for thermodynamic compatibility is fulfilled ((HB94), (Hey96)). Transformation into a standard model is carried out by adding an elastic element of modulus  $M_1$  in series. The dynamic response  $M^*(\omega, \tau)$  and internal friction  $Q^{-1}$  then become:

$$\frac{M^*(\omega, \tau)}{M_0} = \frac{M_1 (i\omega\tau)^\alpha}{M_1 (1 + (i\omega\tau)^{\alpha-\beta}) + M_0 (i\omega\tau)^\alpha}, \quad (17)$$

$$\frac{D^*(\omega, \tau) - D_1}{D_0} = (i\omega\tau)^{-\alpha} + (i\omega\tau)^{-\beta}$$

$$Q^{-1}(\omega, \tau) = \frac{(\omega\tau)^{-\alpha} \sin\left(\frac{\alpha\pi}{2}\right) + (\omega\tau)^{-\beta} \sin\left(\frac{\beta\pi}{2}\right)}{(\omega\tau)^{-\alpha} \cos\left(\frac{\alpha\pi}{2}\right) + (\omega\tau)^{-\beta} \cos\left(\frac{\beta\pi}{2}\right) + \frac{M_0}{M_1}} \quad (18)$$

It is also possible to give an analytical expression for the relaxation time distribution  $h(\tau)$  with the relation  $M^*(\omega, \tau) = \hat{M}(p, \tau)|_{p=i\omega}$  (Glo93):

$$h(\tau) = \pm \lim_{\varepsilon \rightarrow 0} \Im[\hat{M}(p)]|_{p=-1/\tau \pm \varepsilon} \quad (19)$$

and one gets:

$$h(\tau) = \frac{\Omega_{\alpha,\beta}^S + \frac{M_0}{M_1}}{\tilde{\tau}^{-2\alpha} + \tilde{\tau}^{-2\beta} + 2\tilde{\tau}^{-\alpha-\beta} \cos([\alpha - \beta]\pi) + \frac{2M_0}{M_1} \Omega_{\alpha,\beta}^C + \frac{M_0^2}{M_1^2}} \quad (20)$$

with  $\tilde{\tau} = \tau/\tau_{max}$ ,  $\Omega_{i,j}^C = \tilde{\tau}^{-i} \cos(i\pi) + \tilde{\tau}^{-j} \cos(j\pi)$ ,  $\Omega_{i,j}^S = \tilde{\tau}^{-i} \sin(i\pi) + \tilde{\tau}^{-j} \sin(j\pi)$ .

Table 2

The summary of various spectral functions and their power-law behaviour. Abbreviation:  $p = i\omega\tau$ ,  $A'$ ,  $A$  - constants.

			$\omega\tau \rightarrow 0$			$\omega\tau \rightarrow \infty$		
	$M^*/M_0$		$M'/M_0$	$M''/M_0$	$Q^{-1}$	$M'/M_0$	$M''/M_0$	$Q^{-1}$
(Deb41)	$(1 + p^{-1})^{-1}$		$(\omega\tau)^2$	$(\omega\tau)^1$	$(\omega\tau)^{-1}$	1	$(\omega\tau)^{-1}$	$(\omega\tau)^{-1}$
(CC41)	$(1 + p^{-\alpha})^{-1}$	$0 < \alpha \leq 1$	$(\omega\tau)^\alpha$	$(\omega\tau)^\alpha$	$A'$	1	$(\omega\tau)^{-\alpha}$	$(\omega\tau)^{-\alpha}$
(Jon77)	$(p^{-\alpha} + p^{-\beta})^{-1}$	$0 < \beta \leq \alpha \leq 1$	$(\omega\tau)^\alpha$	$(\omega\tau)^\alpha$	$A'$	$(\omega\tau)^\beta$	$(\omega\tau)^\beta$	$A$
KWW ((Koh47))	$\exp(-(t/\tau)^\beta)$	$0 < \beta \leq 1$	$(\omega\tau)^2$	$(\omega\tau)^1$	$(\omega\tau)^{-1}$	1	$(\omega\tau)^{-\beta}$	$(\omega\tau)^{-\beta}$
(HN67)	$1 - (1 + p^\alpha)^{-\beta}$	$0 < \alpha, \beta < 1$	$(\omega\tau)^\alpha$	$(\omega\tau)^\alpha$	$A'$	1	$(\omega\tau)^{-\beta\alpha}$	$(\omega\tau)^{-\beta\alpha}$
(DC51)	$1 - (1 + p)^{-\beta}$	$0 < \beta \leq 1$	$(\omega\tau)^2$	$(\omega\tau)^1$	$(\omega\tau)^{-1}$	1	$(\omega\tau)^{-\beta}$	$(\omega\tau)^{-\beta}$
(Mue83)	$Q = (\omega\tau)^\gamma$	$0 < \gamma \leq 1$	$\rightarrow 0$	$(\omega\tau)^1$	$(\omega\tau)^{-\gamma}$	1	$(\omega\tau)^{-\gamma}$	$(\omega\tau)^{-\gamma}$
FC1	$(p^{-1} + p^{-\beta} + \frac{M_0}{M_1})^{-1}$	$0 < \beta \leq 1$	$(\omega\tau)^{2-\beta}$	$(\omega\tau)^1$	$(\omega\tau)^{-1+\beta}$	1	$(\omega\tau)^{-\beta}$	$(\omega\tau)^{-\beta}$
FC2	$(p^{-\alpha} + p^{-\beta} + \frac{M_0}{M_1})^{-1}$	$0 < \beta \leq \alpha \leq 1$	$(\omega\tau)^\alpha$	$(\omega\tau)^\alpha$	$A'$	1	$(\omega\tau)^{-\beta}$	$(\omega\tau)^{-\beta}$

### 3 Sample selection

The nine natural volcanic glasses used were fresh, unweathered, unaltered, and nonhydrated obsidians free of cracks with low crystal ( $< 1\%$ ) and bubble content ( $< 1\%$ ). Chemical composition of the matrix glass was quantified by electron microanalysis (SEM-EDX, DSM 940 CARL ZEISS, eXL 10 Spektrometer, Oxford Instruments). Volatile-species and thus water content are determined in high-vacuum degassing experiments (controlled heating rate 10K/min from RT-1500C) coupled with a quadropole mass spectrometer (QMA 125 Balzers, (SH00), (LBW<sup>+</sup>03), (HS03)).

*YEL* is a grey crystal-poor obsidian from Yellowstone (USA). *VUL* from Vulcano, *LIP* from Lipari (Italy) and *JAL* from Jalisco (Mexico) are grey crystal-free glasses. The sample *MIL* from Milos (Greek) is grey-black crystal-poor. *RAB* from Hrafninnuhryggur (Island) and *DYR* from Arteni (Armenia) are black crystal-poor glasses. The obsidian *ATS* from Artis (Armenia) is grey crystal-poor with crystal bands. *QUI* from Quironcolo (Argentina) and *IKI* from Ikizidre (Turkey) are transparent homogeneous obsidians with very few large crystals.

### 4 Experiments




Fig. 4. Flexure Pendulum Equipment.

The flexure pendulum is shown in Fig. 4. It operates in air at a frequency of about  $0.63Hz$  (small deformations  $\approx 10^{-5}...10^{-3}$ ) and temperatures up to  $T \approx 1000^{\circ}C$  (cf. (BZ94), (BZHK97), (BZKH97), (BZHK98), (BZKH98a), (BZKH98b), (WHBZ01)). The sample is a combination of two bars with a

Table 3

Chemical composition and water-content (wt.%) of the volcanic glasses. <dtl: less than detection limit, agpaitic index (mol%)  $AI = \frac{K_2O+Na_2O}{Al_2O_3}$ , aluminium saturation index  $ASI = \frac{Al_2O_3}{K_2O+Na_2O+CaO}$ , structur modifier (mol%)  $SM$  from (GD03), excess oxides (mol%)  $EO = SM - 0.5Fe_2O_{3t} - Al_2O_3$  from (GGD02).

	YEL	VUL	LIP	MIL	RAB	DYR	ATS	JAL	QUI
$SiO_2$	77.01	74.66	74.84	77.03	74.56	78.67	78.57	76.39	77.11
$TiO_2$	<dtl	<dtl	<dtl	0.22	<dtl	0.26	<dtl	<dtl	0.13
$Al_2O_3$	11.97	12.84	12.92	12.72	13.04	11.6	11.95	10.79	14.06
$Fe_2O_{3t}$	1.53	1.98	1.86	1.34	1.88	0.6	0.57	3.53	0.64
$CaO$	0.54	0.81	0.86	1.52	0.89	1.6	1.34	0.18	0.46
$MgO$	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl
$MnO$	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl
$Na_2O$	3.11	3.29	3.87	3.05	4.04	0.7	2.31	3.94	2.55
$K_2O$	5.61	5.92	5.2	3.98	5.17	6.28	5.07	5.05	4.56
Total	99.77	99.5	99.88	99.86	99.94	99.71	99.81	99.88	99.51
$AI^{-1}$	1.07	1.08	1.08	1.36	1.06	1.46	1.29	0.92	1.55
ASI	0.99	0.96	0.95	1.05	0.94	1.07	1.02	0.88	1.42
$\frac{NBO}{T}$	0.0103	0.0197	0.0257	2E-4	0.0199	0.0037	0.005	0.023	0.409
EO	0.47	0.89	1.16	-0.17	0.9	-0.38	0.23	1.05	-1.97
$H_2O$	0.096	0.163	0.21	0.113	0.101	0.085	0.106	0.027	0.222

rectangular cross section of  $(1 \times 1) \text{mm}^2$  and a length  $l$  of 40mm. One end of the specimen is held rigid and the other end is connected with the movable part of the flexure pendulum. Measurements were done under isothermal conditions in the range below the glass transition temperature  $T_g$  in 10K-steps and above  $T_g$  in 5K-steps. Experimentally determined quantities are the logarithmic decrement without specimen  $\Lambda_P$  and of the coupled system specimen-pendulum  $\Lambda_{SP}$ , oscillation period of pendulum  $t_P = f_P = 2\pi\omega_P$  and of the coupled system specimen-pendulum  $t_{SP}$ . With the direction moment  $D_P = (5.35 \pm 0.36) \text{Nm}$  of the pendulum and geometrical quantities of the specimen: free length  $l$ , moment of inertia  $I$  and experimentally determined quantities rheological parameters complex Young's modulus  $M^*(\omega_P, T)$ :

$$M'(\omega_P, T) = \frac{3 D_P l}{2 I} \left( \frac{t_P^2}{t_{SP}^2} - 1 \right), \quad (21)$$

$$M''(\omega_P, T) = \frac{3 D_P l}{2 \pi I} (\Lambda_{SP} - \Lambda_P) \quad (22)$$

and internal friction  $Q^{-1}(\omega_P, T)$  were calculated

$$Q^{-1}(\omega_P, T) = \frac{M''(\omega_P, T)}{M'(\omega_P, T)} = \frac{t_{SP}^2(\Lambda_{SP} - \Lambda_P)}{\pi(t_P^2 - t_{SP}^2)}. \quad (23)$$

The mechanical spectra are characterized by the complex Young's modulus  $M^*(T)$ , complex shear modulus  $G^*(T)$ , internal friction  $Q^{-1}(T)$ , complex creep compliance  $D^*(T)M^*(T) = 1$ , shear compliance  $J^*(T)G^*(T) = 1$  and/or the complex shear viscosity  $\eta^*(t)$ . The complex quantities can be separated into real (storage modulus  $M'$ ) and imaginary parts (loss modulus  $M''$ ). The Kramers-Kronig (dispersion) relations ((Kra26), (Kro26)) couple the real and imaginary parts of the complex quantities  $A^* = A' + iA''$  of a material by

$$A'(\omega) = -H[A''(\xi)], \quad A''(\omega) = H[A'(\xi)] \quad (24)$$

with the Hilbert-transform by principal value integral  $\oint$  ((Don01))

$$H[f(\xi)](\omega) = \frac{1}{\pi} \oint \frac{f(\xi)d\xi}{\xi - \omega}, \quad H^{-1} = -H. \quad (25)$$

These are purely mathematical implications of the linear and causal material equations. The discussion of the mechanical spectra can take place thereby on the individual modulus.

## 5 Results

Fig.5 represents the storage modulus  $M'$  and the loss modulus  $M''$  for the investigated natural glasses. All obsidians show a relatively similar behaviour. A deviation from the general trend shows the *LIP* sample due to strong vesiculation. Here, a particularly long-drawn-out thermal and mechanical glass transition can be observed in the storage modulus.

The storage modulus at room temperature  $M_{RT}$  is a material constant, i.e. the Young's-modulus<sup>2</sup> of the glass  $E = M_{RT}$ , which ranges for silicate glasses between  $60GPa$  and  $100GPa$  ((Wag04)). The obsidians exhibit a relatively constant value of  $(70 \pm 10)GPa$ . In principle,  $E$  is a function of the chemical composition, water-, bubble-, crystal content and temperature prehistory, however, the sensitivity on these influences is much less than those on the relaxation times ((Wag04)). There is a positive correlation with the water content and a weak negative correlation with the cooling rate (Fig. 7).

<sup>2</sup> If measurements of  $M'(T)$  are carried out below  $RT$ , one observes a further rise




Fig. 5. Temperature dependence of the real part (storage modulus)  $M'$  and imaginary part (loss modulus)  $M''$  of the complex Young's modulus  $M^* = M' + iM''$  for the natural volcanic glasses. (inset) Asymptotic behaviour of storage modulus at high temperature.






Fig. 6. Complex Youngs modulus  $M^*$  normalised with the unrelaxed Youngs modulus  $M_\alpha$  at  $T_g$  in the Gaussian-plane.

In the examined temperature range  $M'(T)$  decreases continuously for most silicate glasses (Fig. 8). An exception is silica glass with an anomalous increase of Young's modulus with temperature between  $100K$  and  $T_g$  ((Bru70), (Bru71)). Fig. 8 and Tab. 4 clearly indicate that the examined natural glasses have to be assigned to the silica glass with the exception of the LIP-obsidian.

The total temperature dependence of Young's modulus is given by the differential ((Bru71), (AMR93), (RC87), (VPR96), (SSHB03)).:

$$\frac{dM'(T)}{dT} = \alpha_T V \left( \frac{\partial M'}{\partial V} \right)_T + \left( \frac{\partial M'}{\partial T} \right)_V \quad (26)$$

with volume  $V$  and thermal coefficient of expansion  $\alpha_T = \frac{1}{V} \frac{\partial V}{\partial T}$ . The sign of  $dM'/dT$  will be governed by the sign of  $\left( \frac{\partial M'}{\partial T} \right)_V$ , if  $\alpha_T$  is negligibly small. In the case of a Born-von-Kármán solid, as in the case of a Debye and Grueneisen solid, it was shown that  $dM/dT$  is negative at low temperatures and large  $\alpha_T$ , and positive at high temperature and small  $\alpha_T$  ((Bru70)). However, steps occur in the storage modulus curve at the secondary relaxation transitions  $\gamma, \beta, \beta'$  (Fig. 9). Especially for the natural rhyolitic glasses  $dM'(T)/dT$  below  $T_g$  is very small and it is possible to observe the relaxation steps. A constant value of  $dM'/dT$  follows at a superposition of several processes or with a high thermal coefficient of expansion  $\alpha_T$  (c.f. and Tab. 4). If relaxation processes are strong and in different temperature ranges, then minima occur in  $dM'/dT$ .

with falling temperature or rising frequency due to relaxation processes ((Jag60)).




Fig. 7. Dependence of the Young's modulus  $M_{RT}$  on the chemical composition (according to  $NBO/T$  as well as  $EO$  and  $AI^{-1}$  to Tab. 3) as well as the water content for the examined obsidians. Lines are guides to the eye.




Fig. 8. Fragility index  $m$  versus the temperature derivative of the storage modulus  $\partial M'(T)/\partial T|_{T < T_g}$  in the temperature range below  $T_g$  for the obsidians in comparison with synthetic silicate glasses.

Table 4

Rheological properties of the examined volcanic glasses.  $NaSi-Na_2Si_3O_7$ ;  $\spadesuit$  (Hei04), Homosil,  $T = 1199^\circ\text{C}$ ;  $\diamond$  (BL96);  $\clubsuit$  (Bru71);  $\flat$  (EMMB75);  $\natural$  (PVTR02);  $\#$  (TR00);  $\S$ (MTS80),  $T = RT-350^\circ\text{C}$

	$M_{RT}$ [GPa]	$T_\alpha$ [ $^\circ\text{C}$ ]	$M_\alpha$ [GPa]	$-\frac{dM'}{dT}$ [ $\frac{MPa}{K}$ ]	$\frac{\partial \log M'}{\partial(1000/T)} = -\frac{T}{1000} \frac{\partial \log M'}{\partial \log T}$			$10^{-7} \alpha_T$ [1/K]
					$T < T_g$	$< T <$	$T_m < T$	
YEL	75	861	53	5.8	0.010	0.90	16.3	$\vdots$
VUL	77	817	72	4.9	0.017	1.22	28.7	$\vdots$
LIP	61	789	45	20.4	0.028	0.96	14.1	$\vdots$
MIL	67	891	58	4.8	0.009	0.74	19.8	$\vdots$
RAB	73	819	55	8.5	0.025	0.9	24.4	61.6 $\flat$
DYR	72	830	71	0.2	0.001	3.16	25.9	$\vdots$
ART	76	864	74	1.6	0.004	1.34	18.8	$\vdots$
JAL	70	782	64	4.4	0.022	–	31,4	$\vdots$
QUI	81	824	81	-0.2	-0.001	1.47	14.4	
$SiO_2$	79	1239 $\diamond$	75 $\spadesuit$	-5.6	-0.005	-0.46 $\natural$		5.4 $\clubsuit$
$Di$	92	769	79	18.5	0.02	4.6	71	139 $\#$
$NaSi$	61	523	55	20	0.026	2.5	43.7	123 $\S$

In the temperature range above  $T_g$   $M'$  can be characterized in the Arrhenius-diagram. It can be differentiated into two ranges:  $T_g \leq T \leq T_\alpha$  and above  $T_\alpha$ . Here,  $T_\alpha$  is the mechanical glass transition temperature at the loss modulus maximum (Tab. 4). By means of an Arrhenian-ansatz for temperatures  $T > T_\alpha$  it is possible to determine the apparent activation energy of viscous flow  $E'_{a,\alpha}$  ((Wag04)):

$$\frac{\partial \log M'}{\partial(1/T)} \approx \frac{2E'_{a,\alpha}}{2,303R}. \quad (27)$$

Above  $T_g$  all obsidians show a clear temperature dependence of the storage modulus  $M'$  which is caused by the strong change of the structure (configurational states). In principle, it is possible to determine the glass transition temperature  $T_g$  at a relaxation time  $\tau \approx 300\text{s}$  from the change of  $\partial M'(T)/\partial T$  if a linear decay of  $M'$  in the temperature range below and above  $T_g$  is observed. Attention must be paid to distinguish between  $T_g$  at  $q\tau \approx 1$  (Frenkel-Reiner-Kobeko Gleichung, (GS95)), the onset of the mechanical glass transition  $T_{ve}$  at  $\omega\tau \approx 100$ , and the mechanical glass transition temperature  $T_\alpha$  at  $\omega\tau \approx 1$




Fig. 9. (top) Relaxation steps  $\Delta M$  for two relaxation processes: cooperative motion of alkali-ions  $\gamma_{R^+}$  and mixed alkali-peak  $\beta_{mix}$  and (bottom) internal friction  $Q^{-1}$  in the case of the *RAB* obsidian.

(see Fig. 10).

Below  $T_{VE}$  no relaxation contributions (viscoelastic relaxation of the structure within the observation window) can be observed, and it is only possible to examine the mechanical characteristics of the appropriate “current” configurational state as well as anelastic relaxation processes such as the Johari-Goldstein relaxation or the loss due to the mobility of divalent cations. The temperature dependence is substantially smaller than above  $T_\alpha$ , whereby mechanical glass transition is essentially steered by the Maxwell- $\alpha$ -relaxation time  $\tau_\alpha(T)$ .

At relaxed melt viscosity two orders of magnitude above the Maxwell-relaxation time at  $T_\alpha$  ((WD90), (Web91), (Web92), (Web97)) above the temperature  $T_\mu \approx 930 \pm 60^\circ\text{C}$ , should hold the relation  $\lim_{\eta' \rightarrow \eta_{rel}} M'(T) = 0$  or  $\lim_{\eta' \rightarrow \eta_{rel}} G'(T) = 0$ .

Since, however, as a function of chemical composition of the glasses phase separation and crystallization features can arise, and a temperature range of a plateau in Young’s and shear modulus, a relaxed modulus  $M'_{rel}, G'_{rel} \neq 0$  can occur (vgl. Abb 11, (DGBP97a), (DGBP97b), (DG97), (DGB<sup>+</sup>97), (Duf98), (Wag04)). The plateau is typical for Polymers ((Don92)) in addition, for




Fig. 10. Definition of the temperatures used in this article. (a) Complex Young's modulus  $M^*$  (b) internal friction  $Q^{-1}$  of the *JAL*-obsidian in the Arrhenius diagram. (c) internal friction  $Q^{-1}$  as a function of the normalized relaxation time  $\log(\omega_P\tau_\alpha)$




Fig. 11. Asymptotic behavior for high temperatures and low frequencies in the representation of the complex modulus  $M^*$  in the Gaussian-plane (top) for the investigated volcanic glasses and (bottom) for starting glass (1: Jenit I, 3: JenitII) and ceramic (2: Jenit I, 4: JenitII) of machinable glass ceramic ((WHBZ01)), 5:  $16Na_2O - 10CaO - 74SiO_2$ , 6:  $16K_2O - 10CaO - 74SiO_2$ , 7: cordierite-glass which shows surface crystallization effects ((Wag04)) in comparison to the 8: *JAL*-obsidian.

partially crystalline rocks or glass ceramics ((BDW94), (BD97), (Smi97), (LJ98), (Bag99), (BLT00), (REH00)). Here, among other things, it was stated

that shear stress induced phase separation can occur ((QZY98), (ZZY+01), (AT01)). In the case of obsidians no plateaus can be observed (Fig. 5 and 11).

The loss modulus  $M''$  of the volcanic glasses is represented in Fig. 5. The mechanical spectrum can be essentially divided into three ranges, characterized by typical relaxation processes<sup>3</sup>: ( $\beta$ ) low-temperature range (RT-300°C), ( $\beta'$ ) range in the vicinity of  $T_g$  and ( $\alpha$ ) viscoelastic, mechanical glass transition.




Fig. 12. Loss modulus  $M''$  as a function of (top) temperature and (bottom) reduced temperature  $T - T_m$  in the temperature range  $T < T_g$ .

Fig. 12 shows the spectra below  $T_g$ . By scaling the spectra with  $T_\alpha$  it becomes clear that the temperature run of the curve for obsidian of different sources is very similar. It can be distinguished in two types: (A) a nearly temperature independence of the  $\beta$ -range<sup>4</sup> of  $M''$  with a average amplitude of 0,7GPa (*QUI, MIL, VUL*) and (B) a minimum in  $M''(T)$  with  $T - T_\alpha = -450^\circ$  (*LIP, DYR, YEL, RAB, JAL, ATS*). The  $\beta'$  transition deviates only for

<sup>3</sup> The relaxation behaviour in multi-component glasses is rather complex due to the superposition of several relaxation processes.

<sup>4</sup> Here it is to be counted for a superposition of several processes, i.e. a broad  $\beta$  transition superimposed by a  $\beta'$  process.

*MIL*-obsidian from the general trend. The temperatures of the minima and maxima,  $T_{\beta,max,min}$  and the values of internal friction are summarized in Tab. 5. Since the intensity of the effects and signal-to-noise ratio are small, all processes below  $T_g$  are understood for the *GMM* as two processes  $\beta$  and  $\beta'$ . However, it is in the case of *RAB*, *JAL*, *LIP*, *YEL* and *ATS* possible to separate the  $\beta$ -process into two overlapping relaxation transitions: cooperative motion of alkali cations in the glassy network  $\gamma_{R+}$  and a mixed alkali peak  $\beta_{mix}$ . This overlay was fitted by means of a double power law function of the form ((RI98a)):

$$Q^{-1}(T) = Q_b^{-1} + \sum_{j=1}^n \frac{Q_{0,j}^{-1}(\omega\tau_j)^{n_j}}{1 + (\omega\tau_j)^{m_j+n_j}} \quad (28)$$

with the background  $Q_b^{-1}$ , a constant  $Q_{0,j}^{-1}$  and the relaxation times

$$\tau_j = \tau_{0,j} \exp\left(\frac{E_{a,j}}{RT}\right). \quad (29)$$

Table 5

Temperature and magnitude of the internal friction maxima for temperature  $T < T_g$  without background subtraction.

	<i>AI</i>	$T_{m,\gamma_{R+}}$ [°C]	$Q_{m,\gamma_{R+}}^{-1}$	$T_{m,\beta_{mix}}$ [°C]	$Q_{m,\beta_{mix}}^{-1}$	$T_{min}$ [°C]	$Q_{min}^{-1}$	$Q_{Plateau}^{-1}$
RAB	1,06	54	0,010	182	0,0070	342	0,005	–
JAL	0,90	63	0,009	179	0,0090	342	0,006	–
LIP	1,08	91	0,009	182	0,0070	293	0,004	–
YEL	1,07	106	0,011	264	0,0100	395	0,005	–
ATS	1,29	152	0,007	314	0,0070	389	0,005	–
MIL	1,36	72	0,012	142	0,0110	(317)	–	0,009
VUL	1,09	121	0,009	280	0,0097	(355)	–	0,0098
QUI	1,55	195	0,010	431	0,0080	(500)	–	0,0076
DYR	1,46	–	–	105	0,0094	(431)	–	0,004

The volcanic glasses can be likewise divided according to the  $\alpha$  process into different groups (Fig. 13). By scaling the temperature axes with the temperature of maxima  $T_\alpha$  a master curve for the large group of melts (*MIL*, *VUL*, *YEL*, *JAL* and *ATS*) can be constructed, which is an indication for similar rheologic characteristics of these obsidians. Deviations from the general trend show the samples *DYR* and *LIP*. The *DYR*-obsidian has with  $\delta_\alpha = 84^\circ C$  a






Fig. 13. (Top) storage modulus  $M'$  normalized with the Young's modulus at the glass transition temperature  $M_{VE}$  and (bottom) loss modulus  $M''$  as a function of  $T - T_m$  in the temperature range  $T > T_g$ . In the figures (b)-(d) the deviations from the curve are represented, which the obsidians *MIL*, *VUL*, (*YEL*), *JAL*, (*QUI*) and *ATS* follow and which is clarified with the grey line.

substantially smaller half width and steeper slopes of the loss modulus flanks of the  $\alpha$ -maximum:

$$m_i = \frac{d \log M''}{d(10000/T)}, \quad i = \begin{cases} 1 & \text{for } \log(\omega\tau) < 1 \\ 2 & \text{for } \log(\omega\tau) > 1 \end{cases} \quad (30)$$

with  $m_1 = 2.04$ ,  $m_2 = -1.56$  than the other glasses (general trend  $\delta_\alpha \approx 140^\circ\text{C}$  and  $1.1 < m_1 < 1.5$ ,  $-1 < m_2 < -0.6$ ). *LIP* on the other hand exhibits clearly larger  $\delta_\alpha = 154^\circ\text{C}$  values and a smaller slopes  $m_1 = 1.04$ ,  $m_2 = -0.66$ . This obsidian has the smallest relaxation strength  $s_\alpha = 12\text{GPa}$  and  $s_D = 27\text{GPa}$  ( $s_\alpha^{\text{average}} = 20.4\text{GPa}$  and  $s_D^{\text{average}} = 35.5\text{GPa}$ ). The *RAB*-obsidian is featured by a pronounced shoulder<sup>5</sup>, which suggests a strong  $\beta_{R^{2+}}$  relaxation process. In the  $\alpha$  process of the *QUI*-glass an anomaly arises within the glass transition range. Here, it concerns an physical ageing effect during the measurement. Particularly, this obsidian exhibits few large ( $d \approx 0.5\text{mm}$ ) crystals (per sample approx. 3-4) causing the sample to crack under the experimental strain of  $10^{-4}$ .

The mechanical spectra could be parameterisiertparameterized with *GMM* (17) with the assumption of three relaxation processes ( $j = \alpha, \beta, \beta'$ ):

$$M^*(\omega, \tau) = \sum_{j=1}^3 \frac{M_{0,j} M_{1,j} (i\omega\tau_j)_j^\alpha}{M_{1,j} (1 + (i\omega\tau_j)^{\alpha_j - \beta_j}) + M_{0,j} (i\omega\tau_j)_j^\alpha} \quad (31)$$

## 6 Discussion

Internal friction spectra are shown in Fig. 5. Different relaxation processes can contribute to the relaxation behaviour (3): the dynamical glass transition above the glass transition temperature  $T_g$  the so called primary  $\alpha$ -relaxation (viscoelastic process) and several secondary relaxation processes below  $T_g$ : cooperative motion of alkali ions in the glassy network  $\gamma_{R^+}$ , mixed alkali peak  $\beta_{\text{mix}}$ , so-called water peak  $\beta_{\text{H}_2\text{O}}$ <sup>6</sup>, cooperative motion of alkaline earth ions in the vicinity of the thermal glass transition range  $\beta_{R^{2+}}$  ((RI98b), (Rol01), (Mar01)) and a so-called Johari-Goldstein relaxation  $\beta_{JG}$

<sup>5</sup> The shoulder-effect always showed up with all internal friction measurements accomplished at the obsidian in the same temperature range.

<sup>6</sup> This peak would be present according to (PJZ80) and (Ste85) only in the systems where non-bridging oxygens,  $\text{OH}^-$  groups and hydrogen bonds are present at the same time.

Table 6

Parameters of the relaxation processes from GMM-fitting (from top to bottom :  $\alpha$ ,  $\beta'$  und  $\beta$ ).

Obsidian	$-\log(\tau[s])$	$E_a$	$\beta$	$M_0$	$X$	$M_{VE}$
$\alpha$		[kJ/mol]		[GPa]		[GPa]
YEL	17,02	409	0,60	26	0,45	59
VUL	17,87	384	0,53	33	0,48	68
MIL	19,68	450	0,56	60	1,00	61
LIP	16,13	344	0,56	17	0,44	39
DYR	24,74	554	0,65	2	0,04	68
ATS	17,80	399	0,53	49	0,66	74
QUI	15,74	350	0,54	22	0,29	77
ISL	19,49	442	0,70	37	0,69	53
JAL	18,60	382	0,56	45	0,78	58
$\beta'$						
YEL	9,17	171	0,36	1,26	0,30	4,14
VUL	9,28	150	0,29	1,45	0,45	3,23
MIL	8,61	154	0,36	2,50	1,00	2,51
LIP	12,39	197	0,18	3,40	0,34	9,96
DYR	13,92	245	0,23	5,11	0,64	7,95
ATS	10,48	173	0,38	1,07	0,48	2,22
QUI	10,80	186	0,31	0,66	0,20	3,29
RAB	16,82	306	0,37	40,00	2,08	19,27
JAL	11,60	190	0,31	1,40	0,39	3,58
$\beta$						
YEL	4,67	46	0,27	1,17	0,16	7,35
VUL	3,49	41	0,31	0,84	0,15	5,48
MIL	4,26	46	0,26	0,96	0,14	6,95
LIP	5,30	54	0,31	1,38	0,12	11,11
DYR	4,02	35	0,30	0,88	0,14	6,13
ATS	4,80	49	0,26	1,02	0,20	4,99
QUI	4,70	54	0,31	0,88	0,16	5,37
RAB	4,59	65	0,17	0,86	0,08	11,46
JAL	2,89	23	0,31	1,05	0,24	4,34




Fig. 14. (Top) storage -  $M'$  and loss modulus  $M''$  as a function of temperature of the *MIL* obsidian with GMM-fit according to equation (31). (bottom) Residuum of the fit.

((ANM+00), (Don01), (NJ03)). It is impossible to distinguish the specific relaxation processes in every case because of the restricted frequency and temperature range. For this reason three relaxation processes are assumed:  $\beta$  - superposition of the  $\gamma_{R^+}$ ,  $\beta_{mix}$  and  $\beta_{H_2O}$  process,  $\beta'$  - superposition of the  $\beta_{R^{2+}}$ ,  $\beta_{JG}$  and the thermal glass transition as well as the viscoelastic  $\alpha$ -transition.

Further it is assumed, that the unrelaxed modulus  $M_\infty$  is a very weak function of temperature. This is true in the case of volcanic glasses (Fig. 8 and Tab. 4).

Since volcanic glasses are natural materials, these are heterogeneous up to certain degrees. The natural glasses have a smaller signal-to-noise ratio caused by these heterogeneities opposite to synthetic glasses. Thus, sensitivity is limited. Relaxation processes can only seriously be observed in relaxation behaviour if they are strongly enough. The different assumed influences and their effect on different relaxation processes are summarized in Tab. 7. On one hand it is shown, that there are processes, which are sensitive for different influences, c.f.  $\beta'$ . On the other hand, the  $\alpha$  process is caused by the chemical composition and water content. In addition, effects arise due to degassing and vesiculation. Here, however, it showed up clearly that even during very strong vesiculation of the *LIP*-sample, dynamics of the glass transition is detectable. In this specific case, temperature dependence of  $\alpha$ -relaxation time can only be modelled




Fig. 15. (a) and (b) storage -  $M'$  and loss modulus  $M''$  as a function of temperature with  $GMM$ -fit. (c) Complex Young's-modulus  $M^*$  with  $GMM$ -fit represented in the Gaussian-plane (selection of three obsidians  $MIL$ ,  $ATS$ ,  $JAL$ ).

in first approximation by an Arrhenian-equation due to water release.

Table 7

Assumed influences on the mechanical relaxation behaviour of the volcanic glasses:  
X - significant, (X) - weak, (-) - uncertain

influence	$\beta$ -process	$\beta'$ -process	$\alpha$ -process	$M_{RT}$
chemical composition	X	(-)	X	(X)
water content	(X)	(-)	X	(X)
bubble content (degassing)	(X)	(X)	(X)	(X)
crystals	(X)	(X)	(-)	(-)
temperature history	X	(X)	(-)	(-)

### 6.1 Relaxation behaviour below $T_g$

The influences of the chemical composition and the water content on the relaxation processes below  $T_g$  were examined in detail in several mechanical relaxation studies ( $Q^{-1}$ -spectroscopy) of synthetic glasses. It was shown that different mixing cation effects exist, which in addition depend on the water content and polymerization degree of glasses (c.t. (Day74a), (PJZ80) and (Ste85), (Mar01)). The examined volcanic glasses exhibit the following ions:  $Na^+$ ,  $K^+$ ,  $Ca^{2+}$ ,  $Mg^{2+}$ ,  $Fe^{2+}$  and water in different speciation ((Gab99), (Dor00), (Beh01), (Dor02)), which can contribute to the mechanical relaxation behaviour. Since the place-exchange processes can be observed both in the internal friction spectrum  $Q^{-1}(T)$  or in equivalence in the loss modulus  $M''(T)$  as maxima and in the storage modulus  $M'(T)$  as a step. The following views are accomplished on the basis of internal friction.

The *JAL*-obsidian is peralkalin, i.e. it exist on *NBO* bounded alkali ions  $R^+$  ( $\approx 1\text{mol}\%$ ), which are mobile in the glass network. The peak of  $\gamma_{Na^+}$  at a measuring frequency of  $1\text{Hz}$  is to be expected below  $RT$ . Investigations of internal friction of binary  $R_2O$ - $SiO_2$ -glasses with  $R^+ = Rb^+, K^+, Na^+, Li^+$  show ((ZRD76)) that the intensity  $Q_{m,\gamma}^{-1}$  and the temperature  $T_{\gamma_{R^+}}$  of this maximum depends on the field strength  $F = \frac{z}{a^2}$  of appropriate cations with the valence  $z$  and the Van der Waals radius  $a$ . It becomes clear that the  $\gamma_{R^+}$  process is coupled with the  $\beta_{H_2O}$  process, which exhibits a maximum at approximately  $200^\circ\text{C}$ .

If one further regards ternary glasses with two different kinds of alkali ions, then one observes the occurrence of a further maximum: the mixed alkali peak  $\beta_{mix}$  within the range of the water maximum. At a temperature of  $\approx 320^\circ\text{C}$  additional relaxation processes arise: a  $\beta'_{R^{2+}}$ -process in direct connection to

the mobility of alkaline-earth ions, the mobility of oxygen-ions with an activation energy of  $\approx 200\text{kJ/mol}$  and the Johari-Goldstein relaxation ((Rol01), (NJ03), (Wag04)). A substantial conclusion from the investigations of (Mar01) on ternary alkali and alkaline-earth silicate glasses is the fact that in systems with two kinds of cation, while one is substantially faster than the other one, the cation radius relationship affects the activation energy of the slower ions. The more similar the ion radii are, the smaller is the activation energy.

By the component  $Al_2O_3$  the location and intensity of the maxima change drastically. For the ternary sodium aluminosilicate glass examined by (DR62a) as well as (DR62b) the  $\gamma_{Na^+}$  as well as  $\beta_{H_2O}$  peak decreases with rising  $Al_2O_3$ -content, whereby at the ratio  $Al_2O_3/Na_2O = 1$  the  $\gamma_{Na^+}$  process is maximal and the  $\beta_{H_2O}$  process cannot be observed anymore.

Measurements of mixed alkali aluminosilicate glasses with  $Al_2O_3/R_2O = 1$  of (SY85) as well as (SY89) point out, that as in the case of the ternary mix alkali glasses, these systems exhibit a mixed alkali maximum  $\beta_{mix}$  at  $\approx 100^\circ C$ . At a ratio  $Na_2O/K_2O = 1$  arise a very strong maximum, which is formed by the superposition of the  $\gamma_{R^+}$  and  $\beta_{mix}$  processes.

(SY85) perform additional measurements of glasses, in which the  $Al_2O_3$ -content is varied at the expense of the  $SiO_2$ -content, at constant  $Na_2O/K_2O = 19$ . By the presence of  $Na^+$  and  $K^+$ -cations is formed again apart from the  $\gamma_{R^+}$  a mixed alkali maximum  $\beta_{mix}$ . With rising  $Al_2O_3$  the intensity of the  $\gamma_{R^+}$  peak increases, while those of the  $\beta_{mix}$  decreases. As in the case of ternary sodium aluminosilicate glasses from the investigation of (DR62a) as well as (DR62b) acquiring the intensity of the  $\gamma_{R^+}$  maximum and of  $\beta_{mix}$  minimum at  $Al_2O_3/Alk = 1$ .

From the reasons specified above, the following consequences resulted in the mechanical relaxation behaviour below  $T_g$  of the examined natural glasses:

- The water maximum is suppressed strongly by the  $Al_2O_3$ -content.
- The ratio  $Al_2O_3/Alk \approx 1$  leads to the formation of an intensive  $\gamma_{R^+}$  peak.
- The presence of two different alkali ions  $K^+$  and  $Na^+$  leads to the formation of a mixed alkali peak  $\beta_{mix}$  with  $T_{\beta_{mix}} \approx 140^\circ C$ .
- The  $\gamma_{R^+}$  process is superimposed by the  $\beta_{mix}$  process with the result of a relatively high internal friction  $Q^{-1} \approx 0.7$  within the temperature range  $RT - 300^\circ C$ .
- By the presence of divalent cations a further relaxation process  $\beta_{R^{2+}}$  arises in the vicinity of the glass transition range.

The compilation of data to the internal friction of volcanic glasses confirms the above assumptions (Fig. 12). In the case of the samples *LIP*, *RAB*, *YEL* and *JAL* it is suggested that it concerns a superposition of two processes. *ATS*, *MIL*, *QUI* and *VUL* exhibit a pronounced plateau. An exception is the




Fig. 16. Comparison of the Young's modulus at RT  $M_{RT}$  or  $T_g$   $M_{VE}$  and loss modulus at the  $\alpha$  peak  $M''_{\alpha,m}$  of the obsidians and several sythetic glasses ((Wag04)).

*DYR* sample. Here it seems that the  $\gamma_{R+}$  peak is below *RT*. It is suggested a further peak occurs at  $\approx 100^\circ C$ . In Tab. 5 the results are summarized. As mentioned, the decay of the storage modulus with temperature below  $T_g$  is likewise dependent on the chemical composition. In the special case of the obsidians it can be assumed that  $M_{RT}$  depends secondarily on the chemical composition, due to ion mobility in the glassy network, but is determined essentially by water content. However, practically no investigations of the influence of water content on elastic properties of synthetic and natural glasses exist in contrast to internal friction measurements. The occurrence of the *LIP* sample is interesting in this context with the smallest Young's modulus of  $M_{RT} = 61 GPa$ . It is possible to calculate  $M_{RT}$  with the model of (Pri01) (SciGlass information system) in accordance with the measured data.

## 6.2 Primary $\alpha$ -Process

### a) Chemical composition and water content

The comparison of the Young's modulus at RT ( $M_{RT}$ ) or  $T_g$  ( $M_{VE}$ ) and loss modulus at the  $\alpha$  peak ( $M''_{\alpha,m}$ ) is represented in Fig. 16. The drawn in lines refer to the deviation from simple Maxwell behavior ( $x = 1$ ):  $M''_m = x M'_{VE,RT}/2$ . The linear regression results are  $x_{RT} = 0,55 \pm 0,02$  and  $x_{VE} = 0,58 \pm 0,02$ .



The flat curve of the *LIP* sample is to be explained by strong vesiculation. A change of the sample caused by degassing and formation of bubbles leads to a change in the mechanical behavior, whereby the viscoelastic response is dominated by the mechanical glass transition. The parameter  $x$  is a measure relatively independent of the chemical composition, with which deviations can be interpreted as physically induced processes in contrast to the influence of the chemical composition or the water content, which causes a change of the properties of the glass. The *GMM*-fitting supplies the unrelaxed modulus at




Fig. 17. Temperature of the  $\alpha$ -peak  $T_{m,\alpha}$  as a function of the chemical composition and water content of the investigated volcanic glasses. The (HDW96) calculation scheme defined by the solid curve for viscosities ( $10^8 \dots 10^{11}$  Pas) closely fits the experimental data for the calc- and per-alkaline compositions. The dashed lines are an aid to the eye, and do not conform to any specific mathematical expression.

the mechanical glass transition  $M_{VE}|_{T_{VE}}$  which is  $\approx 2GPa$  lower than the elastic modulus at  $T_g$ . In the used model the  $\beta'$  process represents an overlay of a secondary<sup>7</sup> process and the thermal glass transition caused on experimental conditions. This secondary effect is observed likewise in organic glasses with dielectric spectroscopy, and gave reason to controversial discussions of the existence of the Johari-Goldstein-process ((NJ03), (Sch00a), (ANM<sup>+</sup>00)).

The occurrence of the  $\alpha$ -process is defined by the chemical composition and

<sup>7</sup> In the case of the obsidians the mobility of divalent cations and the Johari-Goldstein relaxation.

the water content ((Din95), (HD96), (SBDR98), (GD03)). In Fig. 17 one can notice different trends. The temperature  $T_\alpha$  decreases with increasing  $NBO/T$  and the amount of the absolute excess oxide value ( $|EO|$ ), i.e. with increasing depolymerization. Likewise the glass transition temperature as well as the temperature of water release follow this trend. The mechanical glass transition of the *MIL* obsidian with the smallest  $NBO/T = 2^{-4}$  and a  $|EO|$  close to zero  $\approx 0,17$  occurs at the highest temperature. The smallest maximum temperature  $T_{\alpha,\alpha}$  has the peralkaline *JAL* obsidian with  $NBO/T = 0,023$  and  $|EO| = 1,05$ . Even the *LIP* obsidian follows this trend. The occurrence of the mechanical glass transition (thus) is dominated by the chemical composition (see also the investigations of partially crystalline glasses by (MBJ+03)). This conclusion confirm measurements of Cordierite-glass ((WHBZ01), (Wag04)). Impurities (crystals, bubbles, cracks) influence the width of the maxima and relaxation strength. The activation energy and prefactor of the Arrhenius-




Fig. 18. Activation energy of viscous flow  $E_{a,\alpha}$  at the glass transition temperature  $T_g$  as a function of water content for the natural volcanic glasses of this work and the natural and remelted obsidians of (SBDR98).

equation for the temperature dependence of the relaxation time  $\tau_\alpha(T)$  can be determined from the *GMM*-fit and compared with the results of the measurements of other authors (viscosity measurements, torsion pendulum measurements) (Fig. ??). The activation energy of the  $\alpha$  relaxation time or viscosity at  $T_g$  is essentially a function of chemical composition and water content. A model that considers both influences sufficient for synthetic or natural silicate melts does not exist. The model of (Pri01) represents the most progressive

at present, in the connection between structure and properties (volatile excluded). For the description of volcanic glass, the empirical model of (Hes96) is most effective. This model was developed for water bearing leucogranitic melts but was also used to calculate the viscosity of metaluminous and peraluminous obsidian ((SBDR98)).




Fig. 19. Distribution parameter  $\beta_a$  ( $\alpha_a = 1$ ) as a function of the apparent activation energy for viscous flow  $E_{a,\alpha}$  at  $T_g$  of the synthetic and volcanic melts of this work in comparison to literature data. The  $\beta_a$  parameter was calculated from  $\beta_{KWW}$  with an empirical expression.

Fig. 19 show the range of variation of the distribution of relaxation times on the basis of the  $\beta_a$  parameter and activation energy  $E_a$  at the mechanical glass transition temperature for structurally different silicate melts. The  $\beta_a$ -parameter for the obsidians range between 0.5 and 0.6 with two exceptions *DYR* and *RAB*. The *RAB* glass has a very strong  $\beta'$  relaxation process so that the GMM-fitting leads to a narrower  $\alpha$ -process. In comparison, the *DYR* glass shows anomalous behaviour in all examined parameters.

The average value of all supercooled melts is  $\overline{\beta}_a = 0,52$ . Deviations can be observed for two volcanic glasses as well as the HPG8-melts from the work of (BDW93).

Under the condition that the distribution of relaxation times is nearly constant it should be possible to predict the occurrence and the width of the mechanical glass transition from viscosity data (see (WBH04)).

The variation of the distribution parameter is primarily caused by phase separation and crystallization processes as well as degassing and vesiculation. The temperature prehistory has little influence. The *DSC* investigation of




Fig. 20. Distribution parameter  $\beta_a$  ( $\alpha_\alpha = 1$ ) as a function of the apparent activation energy for viscous flow  $E_{a,\alpha}$  at  $T_g$  of the volcanic melts. (inset) Distribution parameter  $\beta_a$  ( $\alpha_\alpha = 1$ ) as a function of the cooling rate  $|q|$  of a *LIP*-obsidian ((GD01a)).

((GD01a) shows a negative correlation of the distribution parameter and the cooling rate. The variation of the  $\beta$  parameter is within the standard deviation of the 45 samples.

**In summary** the following points result:

- The mechanical  $\alpha$  relaxation (mechanical or viscoelastic glass transition) overlays a secondary  $\beta$  relaxation process.
- The occurrence of the transition is defined by the temperature dependence of viscosity.
- The width  $\delta$  of the transition depends on the fragility and the distribution of relaxation times.
- The distribution of relaxation times in the investigated temperature and frequency range is almost constant in comparison to the fragility index for inorganic glasses (see (Wag04)).
- The presence of crystals (in particular due to surface crystallisation) and bubbles  $> 1\text{-}2\text{Vol.}\%$  changes the dynamics of the transition and therefore the relaxation time distribution.

- Fragility is defined by the chemical composition and the presence of volatiles.
- Phase separation and degassing processes change strongly the dynamics and thermics <sup>8</sup> of the transition and lead to therorheologic complex behavior.

## 7 Conclusion

Obsian can considered as a thermorheological simple melt with a low fragility index  $m \approx 20$ . Variations in the ratio  $NBO/T$  determine the polymerization degree of the melts and thus the rheologic properties. A crucial factor which determines the mechanical relaxation behaviour in the thermal and dynamic glass transition range above  $T_g$ , is the relatively high water content. In the vitreous state the influence of water on the dynamical processes plays a minor role, since the volcanic glasses are almost completely polymerized ( $NBO/T \leq 0.4$ ). For clarifying this fact it requires more exact methods.

**Three section** can be distinguish in the mechanical spectra (a)  $T < T_g$ , (b)  $T \approx T_g$  und (c)  $T > T_g$ , with the following characteristics:

- (i) The Young's modulus  $M_{RT} = (70 \pm 10)$ GPa is nearly constant. There is a positive correlation with the water content and a weak negative correlation with the cooling rate ((Wag04)).
- (ii) Below  $T_g$  the mechanical relaxation behaviour is characterized by the cooperative motion of univalent cations (alkali-peak  $\gamma_{R^+}$ , mixed alkali-peak  $\beta_{mix}$ ) and the polymerisation degree. Impurities (bubbles, crystals, cracks, trace elements) in the natural glasses decrease the signal to noise ratio.
- (iii) All glasses exhibit a very weak, and in one case, an anomalous negative decay of the Young's modulus with temperature like silica glasses. In addition, it is possible to observe steps in the curve of Young's modulus ( $\Delta M' < 5$ GPa) which correspond with the  $\gamma_{R^+}$  or  $\beta_{mix}$  peak in internal friction.
- (iv) In the vicinity of the glass transition temperature there is a superposition of the  $\alpha$  and a  $\beta'$  process (cooperative motion of divalent cations: alkali earth peak  $\beta_{R^{2+}}$  and the Johari-Goldstein relaxation  $\beta_{JG}$ ) as well as the thermal glass transition defined by the experimental conditions. The thermal glass transition is reflected clearly in the loss modulus and in the storage modulus at least less than 1%.
- (v) The occurence of the mechanical or dynamic glass transition at a constant frequency as function of the temperature is specified by the temperature dependence of the structural  $\alpha$  relaxation time  $\tau_\alpha$ .

---

<sup>8</sup> Due to the nomenclature of (Don81) and (Don01).

- (vi) The temperature dependence of the structural  $\alpha$  relaxations time is determined by the polymerization degree with water as a quasi controlling parameter and can be computed by means of an empirical equation according to (Hes96) or (HD96) for the per- and metaluminous rhyolitic melts. The model of (Pri98) as well as (Gio02) for the computation of the temperature dependence of the viscosity of multicomponent melts cannot be used for the computation of the  $\alpha$  relaxation time. For strong melts and melts with high water content the glass transformation temperature and the activation energy of viscous flow are overestimated.
- (vii) Degassing processes in connection with bubble growth as well as other impurities (crystals) lead to macroscopic (cracks) and structural (polymerization degrees) changes, which cause instabilities of the samples.
- (viii) The dynamics of the mechanical glass transition is a universal process with very weak variation of the relaxation time distribution almost independent of chemical composition and water content (0,027... 0.44)Masse% of the examined natural melts.

The obsidians represents an interesting material class, which has many useful properties (concerning the methods of the mechanical spectroscopy)<sup>9</sup>, like thermalrheologically simple behavior, small fragility index and a high glass formation tendency, small variation of the Young's modulus in a wide temperature range, high polymerization degree, long-term resistance.

## References

- [AG65] G. Adam and J. H. Gibbs. On the temperature dependence of cooperative relaxation properties in glass-forming liquids. *Journal of Chemical Physics*, 43:139–146, 1965.
- [AM88] I. Avramov and A. Milchev. Effect of disorder on diffusion and viscosity in condensed systems. *Journal of Non-Crystalline Solids*, 104:253–260, 1988.
- [AMR93] V. Askarpour, M. Manghnani, and P. Richet. Elastic properties of diopside, anorthite, and grossular glasses and liquids: a brillouin scattering study up to 1400 K. *Journal of Geophysical Research*, 98(B10):17683–17689, 1993.
- [Ang88] C. A. Angell. Structural instability and relaxation in glassy phases. *Journal of Non-Crystalline Solids*, 102:205, 1988.
- [ANM<sup>+</sup>00] C. A. Angell, K. L. Ngai, G. B. McKenna, P. F. McMillan, and S. W. Martin. Relaxation in glassforming liquids and amorphous solids. *Journal of Applied Physics*, 88(6):3113–3157, 2000.

---

<sup>9</sup> "Impurities" have to keep in mind, which are able to effect the actual glass characteristics, like in the case of the *LIP*-sample

- [AT01] Takeaki Araki and Hajime Tanaka. Three-dimensional numerical simulations of viscoelastic phase separation: Morphological characteristics. *Macromolecules*, 34:1953–196, 2001.
- [BA92] R. Boehmer and C. A. Angell. Correlations of the nonexponentiality and state dependence of mechanical relaxations with bond connectivity in ge-as-se supercooled liquids. *Phys. Rev. B*, 45:10091–10094, 1992.
- [Bag99] N. S. Bagdassarov. Viscoelastic behaviour of mica-based glass-ceramic aggregate. *Physics and Chemistry of Minerals*, 26:513–520, 1999.
- [Bak96] D. R. Baker. Granitic melt viscosity: Empirical and configurational entropy models for their calculation. *American Mineralogist*, 81:126–134, 1996.
- [Bar83] G. M. Bartenev. Relaxationserscheinungen in anorganischen Glaesern. *Wissenschaftliche Zeitschrift der Friedrich Schiller Universitaet Jena, Math. Nat. Reihe*, 32:385–405, 1983. Uebersetzung aus dem Russischen.
- [BB00] S. Blake and B. C. Bruno. Modelling the emplacement of compound lava flows. *Earth and Planetary Science Letters*, 184:181–197, 2000.
- [BD93] N. S. Bagdassarov and D. B. Dingwell. Frequency dependent rheology of vesicular rhyolite. *Journal of Geophysical Research*, 98(B4):6477–6487, 1993.
- [BD97] N. Bagdassarov and A. Dorfman. Viscoelastic behavior of partially molten granites. *Tectonophysics*, 290:27–45, 1997.
- [BDW93] N. S. Bagdassarov, D. B. Dingwell, and S. L. Webb. Effect of boron, phosphorus and fluorine on shear stress relaxation in haplogranite melts. *European Journal of Mineralogy*, 5:409–425, 1993.
- [BDW94] N. S. Bagdassarov, D. B. Dingwell, and S. L. Webb. Viscoelasticity of crystal- and bubble-bearing rhyolite melts. *Physics of the Earth and Planetary Interiors*, 83:83–99, 1994.
- [Beh01] H. Behrens. Solubilty and diffusivity of volatiles in silicic melts. Universitaet Hannover, 2001. Habilitation.
- [BL96] G. M. Bartenev and V. A. Lomovskoi. Relaxation properties of alkali silicate glasses from mechanical measurements. *Inorg. Mater.- Engl. Tr.*, 32:541–551, 1996.
- [BLT00] N. S. Bagdassarov, D. Laporte, and A. B. Thomson. *Physics and Chemistry of Partially Molten Rocks*, volume 11 of *Petrology and Structural Geology*, chapter Anelastic and viscoelastic behaviour of partially molten rocks and lavas, pages 29–65. Kluwer, 2000.
- [BM02] C. Buisson and O. Merle. Experiments on internal strain in lava dome cross sections. *Bulletin Volcanology*, 64:363–371, 2002.
- [BMP<sup>+</sup>01] N. S. Bagdassarov, J. Maumus, B. Poe, A. B. Slutskiy, and V. K. Bulatov. Pressure dependence of  $T_g$  in Silicate Glasses from Elec-

- trical Impedance Measurements. *Geochimica et Cosmochimica Acta*, submitted, 2001.
- [Bru70] R. Brueckner. Properties and structure of vitreous silica. I. *Journal of non-Crystalline Solids*, 5:123–175, 1970.
- [Bru71] R. Brueckner. Properties and structure of vitreous silica. II. *Journal of non-Crystalline Solids*, 5:177–216, 1971.
- [Buc03a] U. Buchenau. The breakdown of the shear modulus at the glass transition. *Condensed Matter, abstract*, cond-mat/0202036, 2003.
- [Buc03b] U. Buchenau. Energy landscape - a key concept in the dynamics of liquids and glasses. *J. Phys.: Condens. Matter*, 15:S955–S966, 2003.
- [BW72] Y. Bottinga and D. F. Weill. The viscosities of magmatic silicate liquids: a model for calculation. *Journal of Science*, 272:438–475, 1972.
- [BZ94] S. Bark-Zollmann. Theoretische und experimentelle Untersuchungen von Relaxationserscheinungen in Glaesern. Friedrich-Schiller-Universitaet Jena, 1994. Dissertation.
- [BZHK97] S. Bark-Zollmann, K. Heide, and G. Kluge. Biegependelmessplatz zur Untersuchung der inneren Reibung von Glaesern und glasartigen Festkoerpern. *Tagungsband 71. Glastechnische Tagung in Bayreuth*, 1997.
- [BZHK98] S. Bark-Zollmann, K. Heide, and G. Kluge. Mechanisches Relaxationsverhalten von Glaesern, Untersuchungen mit der Biegependelmethode. *Tagungsband 72. Glastechnische Tagung in Muenster*, pages 134–137, 1998.
- [BZKH97] S. Bark-Zollmann, G. Kluge, and K. Heide. Untersuchung der inneren Reibung von Obsidianen und Glaskeramiken. *Beihefte European Journal of Mineralogy*, 9(1):39, 1997.
- [BZKH98a] S. Bark-Zollmann, G. Kluge, and K. Heide. Experimental investigations of the internal friction of optical and technical glasses with a flexure pendulum equipment. *Glass Science and Technology*, 71(3):57–66, 1998.
- [BZKH98b] S. Bark-Zollmann, G. Kluge, and K. Heide. Mechanical relaxation behaviour of glasses, glass-ceramics and obsidians. *Glastechnische Berichte-Glass Science and Technology (Proc. Vth Inter. Otto-Schott-Kolloquium)*, 71C(268-271), 1998.
- [CC41] K.S. Cole and R.H. Cole. Dispersion and Absorption in Dielectrics. *Journal of Chemical Physics*, 9(4/41):341–351, 1941.
- [CC99] Jonathan Castro and Katharine V. Cashman. Constraints on rheology of obsidian lavas based on mesoscopic folds. *Journal of Structural Geology*, 21:807–819, 1999.
- [CMC02] Jonathan Castro, Michael Manga, and Katharine Cashman. Dynamics of obsidian fows inferred from microstructures: insights from microlite preferred orientations. *Earth and Planetary Sci-*



- ence Letters, 199:211–226, 2002.
- [Coe61] M. Coenen. Mechanische Relaxation von Silikatglasern Eutektischer Zusammensetzung. *Zeitschrift fuer Elektrochemie*, 65(10):903–908, 1961.
- [CTC04] E. Cañón-Tapia and Jonathan Castrob. AMS measurements on obsidian from the Inyo Domes, CA: a comparison of magnetic and mineral preferred orientation fabrics. *Journal of Volcanology and Geothermal Research*, 134:169–182, 2004.
- [CTCa04] E. Cañón-Tapia and M. J. Chávez-Álvarez. Rotation of uniaxial ellipsoidal particles during simple shear revisited: the influence of elongation ratio, initial distribution of a multiparticle system and amount of shear in the acquisition of a stable orientation. *Journal of Structural Geology*, 26:2073–2087, 2004.
- [Day74a] D. E. Day. The internal friction of glasses containing water. *Wissenschaftliche Zeitschrift der Friedrich Schiller Universitaet Jena, Math. Nat. Reihe*, 23(2):293–305, 1974.
- [Day74b] D. E. Day. Internal friction of glasses with low water contents. *Journal of the American Ceramic Society*, 57(12):530–533, 1974.
- [DC51] D. Davidson and R. Cole. Dielectric relaxation in glycerol, propylene glycol, and n-propanol. *Journal of Chemical Physics*, 19:1484–1490, 1951.
- [Deb41] P Debye. *Polar Molecules*. Dover Publications, Inc., 1941.
- [Deb96] P. G. Debenedetti. *Metastable Liquids: Concepts and Principles (Physical Chemistry: Science and Engineering)*. Princeton University Press, 1996.
- [DG97] L. Duffrene and R. Gy. Viscoelastic constants of a soda-lime-silica glass. *Journal of Non-Crystalline Solids*, 211(1,2):30–38, 1997.
- [DGB<sup>+</sup>97] L. Duffrene, R. Gy, H. Burlet, R. Piques, A. Faivre, A. Sekkat, and J. Perez. Generalized Maxwell model for the viscoelastic behavior of a soda-lime-silica glass under low frequency shear loading. *Rheologica Acta*, 36:173–186, 1997.
- [DGBP97a] L. Duffrene, R. Gy, H. Burlet, and R. Piques. Multiaxial linear viscoelastic behavior of a soda-lime-silica glass based on a generalized maxwell model. *Journal of Rheology*, 41(5):1021–1038, 1997.
- [DGBP97b] L. Duffrene, R. Gy, H. Burlet, and R. Piques. Viscoelastic behavior of a soda-lime-silica glass: inadequacy of the kww function. *Journal of Non-Crystalline Solids*, 215(2,3):208–217, 1997.
- [Din95] D. B. Dingwell. Relaxation in silicate melts: some applications. In J. F. Stebbins, P.F. McMillan, and D.B. Dingwell, editors, *Structure, Dynamics and Properties Of Silicate Melts*, volume 32 of *Reviews in Mineralogy*, pages 21–63. Mineralogical Society of America, 1995.
- [Din96] D.B. Dingwell. Volcanic dilemma: Flow or blow? *Science*,

- 273:1054–1055, 1996.
- [Dol02] Burkhard Doliwa. The Dynamics of a Small Model Glass Former as Viewed from its Potential Energy Landscape. Johannes Gutenberg Universit at in Mainz, 2002. Dissertation.
- [Don81] E.-J. Donth. *Glasuebergang*, volume 272 of *Wissenschaftliche Taschenbuecher*. Akademie-Verlag, 1981.
- [Don92] E. J. Donth. *Relaxation and Thermodynamics in Polymeres*. Akademie Verlag, 1992.
- [Don01] E.J. Donth. *The glass transition: relaxation dynamics in liquids and disordered materials*, volume 48 of *Springer series in materials science*. Springer, 2001.
- [Dor00] R. H. Doremus. Water speciation in silicate glasses and melts: Langmuir limited site model. *American Mineralogist*, 85:1674–1680, 2000.
- [Dor02] R. H. Doremus. *Diffusion of Reaktive Molecules in Solids und Melts*. John Wiley & Sons, Inc., 2002.
- [DR62a] D. E. Day and G. E. Rindone. Properties of soda aluminosilicate glasses: I, refractive index, density, molar refractivity, and ifrared absorbtion spectra. *Journal of the American Ceramic Society*, 45(10):489–496, 1962.
- [DR62b] D. E. Day and G. E. Rindone. Properties of soda aluminosilicate glasses: II, internal friction. *Journal of the American Ceramic Society*, 45(10):496–504, 1962.
- [DRVdB03] R. G. Duan, G. Roebben, and O. Van der Biest. Glass microstructure evaluations using high temperature mechanical spectroscopy measurements. *Journal of Non-Crystalline solids*, 316(1):138–145, 2003.
- [DS69] D. E. Day and W. E. Steinkam. Mechanical damping spectrum for mixed-alkali  $R_2O$ - $Al_2O_3$ - $6SiO_2$  glasses. *Journal of the American Ceramic Society*, 52(11):571, 1969.
- [DS72] D. E. Day and J. M. Stevels. Internal friction of  $NaPO_3$  glasses containing water. *Journal of Non Crystalline Solids*, 11:459–470, 1972.
- [DS74] D. E. Day and J. M. Stevels. Effect of dissolved water on internal friction of glass. *Journal of Non Crystalline Solids*, 14:165–177, 1974.
- [DS01] Pablo G. Debenedetti and Frank H. Stillinger. Supercooled liquids and the glass transition. *Nature*, 410(8):259–267, 2001.
- [DT94] M. Dragoni and A. Tallarico. The effect of crystallization on the rheology and dynamics of lava flows. *Journal of Volcanology and Geothermal Research*, 59:241–252, 1994.
- [DT96] M. Dragoni and A. Tallarico. A model for the opening of ephemeral vents in a stationary lava flow. *Journal of Volcanology and Geothermal Research*, 74:39–47, 1996.
- [Duf98] L. Duffrene. Generalized maxwell model for the shear viscoelas-

- tic behavior of a soda-lime-silica glass: a mechanical relaxation using static and dynamic experiments. *Proceedings of International Congress on Glass, 18th, San Francisco, CA, United States, July 5-10*, pages 2561–2566, 1998.
- [EMMB75] J. E. Ericson, A. Makishima, J. D. MacKenzie, and R. Berger. Chemical and physical properties of obsidian: a naturally occurring glass. *Journal of Non-Crystalline Solids*, 17:129–142, 1975.
- [Fel83] A. Feltz. *Amorphe und glasartige anorganische Festkoerper*. Akademie Verlag Berlin, 1983.
- [Fin90] J. H. Fink. Lava flows and domes, emplacement mechanism and hazard implication. 1990.
- [Fit51a] J. V. Fitzgerald. Anelasticity of Glass: I, Introduction. *Journal of the American Ceramic Society*, 34:314–319, 1951.
- [Fit51b] J. V. Fitzgerald. Anelasticity of Glass: II, Internal Friction and Sodium Ion Diffusion in Tank Plate Glass, A Typical Soda-Lime-Silica Glass. *Journal of the American Ceramic Society*, 34:339–342, 1951.
- [Fri75] G. H. Frischat. *Ionic Diffusion in Oxide Glasses*. Number 3/4 in Diffusion and Defect Monograph Series. Trans Tech Publications, 1975.
- [Ful25] G. S. Fulcher. Analysis of recent measurements of the viscosity of glasses. *Jornal of the American Ceramical Society*, 8:339–355, 1925.
- [Gab99] M. Gaber. *Phaenomenologische Untersuchungen des Wasser-abgabeverhaltens von Alkali-Kalzium-Silikatglaesern mit der Vakuum-Extraktionsmethode*. PhD thesis, Hochschule des Saarlandes, 1999.
- [GD01a] J. Gottsmann and D.B. Dingwell. Cooling dynamics of spatterfed phonolite obsidian ows on Tenerife, Canary Islands. *J. Volcanol. Geotherm. Res.*, 105:323–342, 2001.
- [GD01b] J. Gottsmann and D.B. Dingwell. The cooling of frontal flow ramps: A calorimetric study on the rocche rosse rhyolite flow, Lipari, Aeolian Islands, Italy. *Terra Nova*, 12:157–164, 2001.
- [GD03] Daniele Giordano and Donald B. Dingwell. Non-arrhenian multi-component melt viscosity:a model. *Earth and Planetary Science Letters*, 208(3-4):337–349, 2003.
- [GGD02] Joachim Gottsmann, Daniele Giordano, and Donald B. Dingwell. Predicting shear viscosity during volcanic processes at the glass transition: a calorimetric calibration. *Earth and Planetary Science Letters*, 198(3-4):417–427, 2002.
- [GH96] I. Gutzow and K. Heide. Thermodynamic and Kinetic Problems in the Formation, Rheology and Crystallisation of Natural Glasses. *Chemie der Erde*, 56:331–354, 1996.
- [Gio02] D. Giordano. *Experimental Determinations an Modelling of the Viscosity of Multicomponent Natural Silicate Melts: Volcanolog-*

- ical Implications*. PhD thesis, Ludwig-Maximilians-Universitaet Muenchen, 2002.
- [Glo93] W. G. Gloeckle. Anwendung des fraktalen Differentialkalkuels auf Relaxationen in ungeordneten Systemen. Universitaet Ulm, 1993. Dissertation.
- [GM03] Helge M. Gonnermann and Michael Manga. Explosive volcanism may not be an inevitable consequence of magma fragmentation. *Nature*, 426:432–435, 2003.
- [GN70] R. Gardon and O. S. Narayanaswamy. Stress and volume relaxation in annealing flat glass. *J. Am. Ceram. Soc.*, 53:380, 1970.
- [GS92] W Goetze and L Sjoegren. Relaxation processes in supercooled liquids. *Reports on Progress in Physics*, 55(3):241–376, 1992.
- [GS95] I Gutzow and J. Schmelzer. *The vitreous state*. Springer, 1995.
- [GYI<sup>+</sup>01] I. Gutzow, V. Yamakov, D. Ilieva, P. Babalievski, and L. D. Pye. Generic Phenomenological Theory of Vitrification. *Glass Physics and Chemistry*, 27(2):148–159, 2001.
- [HA85] W. Hummel and J. Arndt. Variation of viscosity with temperature and composition in the plagioclase system. *Contributions Mineralogy and Petrology*, 90:83–92, 1985.
- [Hal96] A. Hall. *Igneous petrology*. Prentice Hall, 1996.
- [HB94] N. Heymans and J.-C. Bauwens. Fractal rheological models and fractional differential equations for viscoelastic behaviour. *Rheologica acta*, 33:210–219, 1994.
- [HD96] K. U. Hess and D. B. Dingwell. Viscosities of hydrous leucogranitic melts: a non-Arrhenian model. *American Mineralogist*, 81:1297–1300, 1996.
- [HDW96] K.U. Hess, D.B. Dingwell, and S.L. Webb. The influence of alkaline-earth oxides (BeO, MgO, CaO, SrO, BaO) on the viscosity of a haplogranitic melt: systematics of non-Arrhenian behaviour. *European Journal of Mineralogy*, 8:371–381, 1996.
- [Hei89] K. Heide. Gefüge natürlicher Gläser und deren Beziehung zu ihrer Genese. *Chemie der Erde*, 49:287–295, 1989.
- [Hei04] G. Heide, 2004. Personal communications.
- [Hes96] K. U. Hess. *Zur Temperaturabhaengigkeit der Viskositaet von haplogranitischen Schmelzen*. PhD thesis, Universitaet Bayreuth, 1996.
- [Hey96] N. Heymans. Hierarchical models for viscoelasticity: dynamic behaviour in the linear range. *Rheologica acta*, 35:508–519, 1996.
- [HK02] J. Horbach and W. Kob. The structural relaxation of molten sodium disilicate. *arXiv:cond-mat/0206070*, 2002.
- [HN67] S. Havriliak and S. Negami. A complex plane representation of dielectric and mechanical relaxation processes in some polymers. *Polymer*, 8(4):161–210, 1967.
- [Hod94] I. M. Hodge. Enthalpy relaxation and recovery in amorphous

- materials. *Journal of Non-Crystalline Solids*, 169:211–266, 1994.
- [Hod97] Ian M. Hodge. Adam-Gibbs Formulation of Enthalpy Relaxation Near the Glass Transition. *Journal of Research of the National Institute of Standards and Technology*, 102(2):195–205, 1997.
- [HS03] Klaus Heide and Christian M. Schmidt. Volatiles in vitreous basaltic rims, *HSDP 2*, big island, hawaii. *Journal of Non-Crystalline Solids*, 323:97–103, 2003.
- [Jag60] R. Jagdt. Untersuchungen von Relaxationserscheinungen an Alkali-Silikat-Glaesern. *Glastechn. Ber.*, 33(1):10–19, 1960.
- [Jon77] A. K. Jonscher. The universal dielectric response. *Nature*, 267(5613):673–679, 1977.
- [KB85] W. Kampfmann and H. Berckhemer. High temperature experiments on the elastic and anelastic behaviour of magmatic rocks. *Physics of Earth Planetary Interiors*, 40:223–247, 1985.
- [Ke96] T. S. Ke. Nonlinear anelastic internal friction associated with the diffusion of solute atoms in dislocation cores. *Phys. Stat. Solidi. A-Appl. Res.*, 155(83):83–93, 1996. My08.
- [Koh47] R. Kohlrausch. *Ann. Phys. (Leipzig)*, 12:393, 1847.
- [Kra26] H.A. Kramers. *Nature*, 117:775, 1926.
- [Kro26] R. de L. Kronig. *J. Opt. Soc. Am.*, 12:547, 1926.
- [LBW<sup>+</sup>03] M. Leschik, H. Behrens, M. Wiedenbeck, N. Wagner, K. Heide, H. Gei"slers, U. Reinholz, G. Heide, and G. H. Frischat. Determination of  $H_2O$  and  $D_2O$  contents in rhyolitic glasses using *KFT*, *NRA*, *EGA*, *IR* spectroscopy, and *SIMS*. *Physics and Chemistry of Glasses*, submitted, 2003.
- [LJ98] C. Lu and I. Jackson. Seismic-frequency laboratory measurements of shear mode viscoelasticity in crustal rocks *II*: Thermally stressed quartzite and granite. *Pure and Applied Geophysics*, 153:441–473, 1998.
- [LR95] A.-M. Lejeune and P. Richet. Rheology of crystal-bearing silicate melts: an experimental study at high viscosities. *Journal of Geophysical Research*, 100:4215–4229, 1995.
- [Maa99] Philipp Maass. Towards a theory for the mixed alkali effect in glasses. *Journal of Non Crystalline Solids*, 255:35–46, 1999.
- [Mar85] R. M. Martens. *Kalorimetrische Untersuchungen der kinetischen Parameter im Glastransformationsbereich bei Glaesern im System Diopsid-Anorthit-Albit und bei einem NBS 710 Standardglas*. PhD thesis, Johann Wolfgang Goethe Universitaet Frankfurt am Main, 1985.
- [Mar01] C. Martiny. Untersuchung von Mischkationeneffekten in Alkali-Erdalkali-Silikatglaesern mit Hilfe der mechanischen Verlust- und der elektrischen Leitfaehigkeitsspektroskopie. Westfaelische Wilhelms-Universitaet Muenster, 2001. Dissertation.
- [MBJ<sup>+</sup>03] K. Mueller, N. S. Bagdassarov, M. James, H. Schmeling, and J. Deubener. Internal friction spectroscopy in  $Li_2O - 2SiO_2$

- partially crystallised glasses. *Journal of Non-Crystalline Solids*, 319:44–56, 2003.
- [MCCL98] M. Manga, J. Castro, K. V. Cashman, and M. Loewenberg. Rheology of bubble-bearing magmas. *Journal of Volcanology and Geothermal Research*, 87:15–28, 1998.
- [MD70] G. L. McVay and D. E. Day. Diffusion and internal friction in Na-Rb silicate glasses. *Journal of the American Ceramic Society*, 53(9):508–513, 1970.
- [ML01] M. Manga and M. Loewenberg. Viscosity of magmas containing highly deformable bubbles. *Journal of Volcanology and Geothermal Research*, 105:19–24, 2001.
- [MRBVG87] R. M. Martens, M. Rosenhauer, H. Buettner, and K. Von Gehlen. Heat capacity and kinetic parameters in the glass transformation interval of diopside, anorthite and albite glass. *Chemical Geology*, 62:49–70, 1987.
- [MS99] O. Melnik and S. J. Sparks. Nonlinear dynamics of lava dome extrusion. *Nature*, 402:37–41, 1999.
- [MTS80] N. Mochida, K. Takahashi, and S. Shibusawa. *J. Ceram. Soc. Jpn.*, 88(10):583, 1980.
- [Mue83] G. Mueller. Rheological properties and velocity dispersion of a medium with power-law dependence of  $Q$  on frequency. *J. Geophysics*, 54:20–29, 1983.
- [Mys03] B. Mysen. Physics and chemistry of silicate glasses and melts. *European Journal of Mineralogy*, 15:781–802, 2003.
- [Nga00] K. L. Ngai. Dynamic and thermodynamic properties of glass-forming substances. *Journal of Non Crystalline Solids*, 275:7–51, 2000.
- [NJ03] S.V. Nemilov and G.P. Johari. A mechanism for spontaneous relaxation of glass at room temperature. *Philosophical Magazine*, 83(27):3117–3132, 2003.
- [Owe85] A. E. Owen. The Glass Transition. In N. H. March, R. A. Street, and M. Tosi, editors, *Amorphous Solids and the Liquid State*, Physics of Solids and Liquids, pages 395–431. Plenum Press, 1985.
- [Pap99] Paolo Papale. Strain-induced magma fragmentation in explosive eruptions. *Nature*, 397:425–428, 1999.
- [Pau98] D. Paulmann. *Monte-Carlo-Simulation zur Diffusion von Alkaliionen in oxidischen Glaesern*. PhD thesis, Georg-August-Universitaet Goettingen, 1998.
- [Per91] E.S. Persikov. The viscosity of magmatic liquids: Experiment, generalized patterns. a model for calculation and prediction. In L. L. Perchuk and I. Kushiro, editors, *Physical Chemistry of Magmas*, volume 9 of *Advances in Physical Geochemistry*, pages 1–40. Springer, 1991.
- [Pfe98] T. Pfeiffer. Viscosities and electrical conductivities of oxidic

- glass-forming melts. *Solid State Ionics*, 105:277–287, 1998.
- [PJZ80] Jean Phalippou, Rafi Jabra, and Jerzy Zarzycki. A new interpretation of internal friction in oxide glasses. *Journal of Non-Crystalline Solids*, 38-39(1):481–486, 1980.
- [PK91] L. L. Perchuk and I. Kushiro. *Relations Between Structure, Redox Equilibria of Iron, and Properties of Magmatic Liquids*, volume 9 of *Advances in Physical Geochemistry*. Springer, 1991.
- [Pri98] A. I. Priven. Calculation of the Viscosity of Glass-forming Melts: III. The  $Alk_2O - RO - Al_2O_3 - SiO_2$ -System. *Glass Physics and Chemistry*, 24(2):29–30, 1998.
- [Pri01] A. I. Priven. Calculation of Temperature Dependences of the Viscosity and Volume Relaxation Time for Oxide Glass-Forming Melts from Chemical Composition and Dilatometric Glass Transition Temperature. *Glass Physics and Chemistry*, 27(6):527–542, 2001.
- [PS92] H. Pinkerton and R. J. Stevenson. Methods of determining the rheological properties of magmas at sub-liquidus temperature. *Journal of Volcanology and Geothermal Research*, 53:47–66, 1992.
- [PVTR02] A. Polian, Dung Vo-Thanh, and P. Richet. Elastic properties of  $\alpha$ - $SiO_2$  up to 2300K from Brillouin scattering measurements. *Europhysics Letters*, 57(3):375381, 2002.
- [QZY98] Feng Qiu, Hongdong Zhang, and Yuliang Yanga. Chain stretching effect on domain growth during spinodal decomposition of binary polymer mixtures under simple shear flow. *Journal of Chemical Physics*, 22(8):9529–9536, 1998.
- [RC87] M. L. Rivers and I. S. E. Carmichael. Ultrasonic studies of silicate melts. *Journal of Geophysical Research*, 92(B9):9247–9270, 1987.
- [REH00] J. Renner, B. Evans, and G. Hirth. On the rheologically critical melt fraction. *Earth and Planetary Science Letters*, 181:585–594, 2000.
- [RGD03] J. K. Russell, D. Giordano, and D. B. Dingwell. High-temperature limits on viscosity of non-Arrhenian silicate melts. *American Mineralogist*, 88:1390–1394, 2003.
- [RI98a] Bernhard Roling and Malcom D. Ingram. Analysis of mechanical losses due to ion-transport processes in silicate glasses. *Physical Review B*, 57(22):14192–14199, 1998.
- [RI98b] Bernhard Roling and Malcom D. Ingram. Determination of divalent cation mobilities in glass by dynamic mechanical thermal analysis (dmta): evidence for cation coupling effects. *Solid State Ionics*, 105:47–53, 1998.
- [Ric84] P. Richet. Viscosity and configurational entropy of silicate melts. *Geochimica et Cosmochimica Acta*, 48:471–483, 1984.
- [Rit56] H. N. Ritland. Limitations of the fictive temperature concept.

- Journal of the American Ceramic Society*, 39(12):403–406, 1956.
- [RM02] A. C. Rust and M. Manga. Bubble shapes and orientations in low  $Re$  simple shear flow. *Journal of Colloid and Interface Science*, 249:476–480, 2002.
- [RN92] P. Richet and D. R. Neuville. Thermodynamics of Silicate Melts: Configurational Properties. In S. K. Saxena, editor, *Thermodynamic Data: Systematics and Estimation*, volume 10 of *Advances in Physical Geochemistry*, pages 132–161. Springer, 1992.
- [Roe41] H. Roetger. Elastische Nachwirkung durch Waermediffusion (thermische Reibung) und Materiediffusion (eigentliche innere Reibung) bei periodischem und aperiodischem Vorgang. *Glastechnische Berichte*, 19(6):192–200, 1941.
- [Roe58a] H. Roetger. Neue Erkenntnisse ueber das Relaxationsverhalten der Glaeser. *Wissenschaftliche Zeitschrift der Friedrich Schiller Universitaet Jena, Math. Nat. Reihe*, 7(2/3):237–246, 1958.
- [Roe58b] H. Roetger. Ueber das elastische Relaxationsverhalten von einfachen und gemischten Alkali-Silikat-Glaesern und von Borax. *Glastechn. Ber.*, 31(2):54–60, 1958.
- [Roe74] H. Roetger. Relaxation times and viscosity. *Journal of Non-Crystalline Solids*, 14:201–217, 1974.
- [Roe75] H. Roetger. Entwicklung und Anwendung der Vorstellung ueber das Relaxationsverhalten von Glas. *Sitzungsbericht der AdW der DDR, Mathematik-Naturwissenschaft-Technik*, 3/N:104–116, 1975.
- [Rol01] Bernhard Roling. Mechanical loss spectroscopy on inorganic glasses and glass ceramics. *Current Opinion in Solid State and Materials Science*, 5:203–210, 2001.
- [RR61] R. J. Ryder and G. E. Rindone. Internal friction of simple alkali silicate glasses containing alkaline-earth oxides . *II*. interpretation and discussion. *Journal of the American Ceramic Society*, 44(11):532–540, 1961.
- [RS96] E. Roessler and A. P. Sokolov. The dynamics of strong and fragile glass formers. *Chemical Geology*, 128(1-4):143–153, 1996.
- [Sax92] S. K. Saxena. *Thermodynamics of Silicate Melts: Configurational Properties*, volume 10 of *Advances in Physical Geochemistry*. Springer, 1992.
- [SB93] H. Schiessel and A. Blumen. Hierarchical analogues to fractional relaxation equations. *J. Phys. A: Math. Gen.*, 16:5057 – 5069, 1993.
- [SB95] H. Schiessel and A. Blumen. Mesoscopic pictures of the sol-gel transition: ladder models and fractal networks. *Macromolecules*, 28:4013–4019, 1995.
- [SBDR98] R. J. Stevenson, N. S. Bagdassarov, D. B. Dingwell, and C. Romano. The influence of trace amounts of water on the viscosity of rhyolithes. *Bull vulcanol*, 60:89–97, 1998.



- [SBR01] A. Sipp, Y. Bottinga, and P. Richet. New high viscosity data for 3D network liquids and new correlations between old parameters. *Journal of Non-Crystalline Solids*, 288:166–174, 2001.
- [Sch00a] Boris Wolfgang Schneider. Breitbandige dielektrische Studien der Dynamik struktureller Glasbildner. Universitaet Augsburg, 2000. Dissertation.
- [Sch00b] Beatrix Mercedes Schulz. Diffusion in Glaesern und anderen Komplexen Systemen. Martin-Luther-Universitaet Halle-Wittenberg, 2000. Dissertation.
- [SD69] J.F. Shelby and D.E. Day. Mechanical relaxations in Mixed-Alkali Silicate Glasses: *I*, Results. *Journal of the American Ceramic Society*, 52:169–174, 1969.
- [SD70] J.F. Shelby and D.E. Day. Mechanical relaxations in Mixed-Alkali Silicate Glasses: *II*, Discussion. *Journal of the American Ceramic Society*, 53:182, 1970.
- [SDWB95] R. J. Stevenson, D. B. Dingwell, S. L. Webb, and N. Bagdassarov. The equivalence of enthalpy and shear stress relaxation in rhyolitic obsidians and quantification of the liquid-glass transition in volcanic processes. *Journal of Volcanology and Geothermal Research*, 68:297–306, 1995.
- [SDWS96] R. J. Stevenson, D. B. Dingwell, S. L. Webb, and T. G. Sharp. Viscosity of microlite-bearing rhyolitic obsidians: an experimental study. *Bull Volcanol*, 58:298–309, 1996.
- [SH00] C.M. Schmidt and K. Heide. Degas ein neues Analysenverfahren in der organischen Geochemie. *Terra Nostra*, pages 92–94, 2000.
- [Sha72] H. R. Shaw. Viscosities of magmatic silicate liquids: empirical method of prediction. *Journal of Science*, 272:870–893, 1972.
- [SMBN95] H. Schiessel, R. Metzler, A. Blumen, and T.F. Nonnenmacher. Generalized viscoelastic models: their fractional equations with solutions. *J. Phys. A: Math. Gen.*, 28:6567–6584, 1995.
- [SMCF01] Martin O. Saar, Michael Manga, Katharine V. Cashman, and Sean Fremouw. Numerical models of the onset of yield strength in crystal-melt suspensions. *Earth and Planetary Science Letters*, 187:367–379, 2001.
- [SMD95] J. F. Stebbins, P.F. McMillan, and D.B. Dingwell. *Structure, Dynamics and Properties Of Silicate Melts*, volume 32 of *Reviews in Mineralogy*. Mineralogical Society of America, 1995.
- [Smi97] J. V. Smith. Shear thickening dilatancy in crystal-rich flows. *Journal of Volcanology and Geothermal Research*, 79:1–8, 1997.
- [SML+00] R. S. J. Sparks, M. D. Murphy, A. M. Lejeune, R. B. Watts, J. Barclay, and S. R. Young. Control on the emplacement of the andesite lava dome of the Soufriere Hills volcano, Montserrat by degassing induced crystallization. *Terra Nova*, 12:14–20, 2000.
- [SOB95] H. Schiessel, G. Oshanin, and A. Blumen. Dynamics and conformational properties of polyampholytes in external electrical

- fields. *Journal of Chemical Physics*, 28(103):5070 – 5 – 74, 1995.
- [SR97] R. Siewert and M. Rosenhauer. Viscoelastic relaxation measurements in the system  $SiO_2$ - $NaAlSiO_4$  by photon correlation spectroscopy. *American Mineralogist*, 82:1063–1072, 1997.
- [SS92] D.J. Stein and F.J. Spera. Rheology and microstructure of magmatic emulsions : theory and experiments. *Journal of Volcanology and Geothermal Research*, 49:157–174, 1992.
- [SSHB03] F. R. Schilling, S. V. Sinogeikin, M. Hauser, and J. D. Bass. Elastic properties of model basaltic melt compositions at high temperatures. *Journal of Geophysical Research-Solid Earth*, 108(B6):2304, 2003.
- [Ste85] J. M. Stevels. Relaxation phenomena in glass. *Journal of Non-Crystalline Solids*, 73(1-3):165–178, 1985.
- [SY85] H. Sakamura and I. Yasui. *Journal of the Ceramic Society of Japan*, 93(12):781, 1985.
- [SY89] H. Sakamura and I. Yasui. *Proc.XVth Intern.Congr.on Glass, Leningrad*, 2a:257, 1989.
- [TB79a] M. Taylor and G. E. Brown. Structure of mineral glasses: 1. feldspar glasses  $NaAlSiO_8$ ,  $NaAlSiO_8$ ,  $CaAl_2Si_2O_8$ . *Geochimica et Cosmochimica Acta*, 43(1):61–75, 1979.
- [TB79b] M. Taylor and G. E. Brown. Structure of mineral glasses: 2. feldspar glasses  $SiO_2$ - $NaAlSiO_4$  join. *Geochimica et Cosmochimica Acta*, 43(9):1467–1473, 1979.
- [TH26] G. Tammann and W. Hesse. Die Abhaengigkeit der Viskositaet von der Temperatur bei unterkuehlten Fluessigkeiten. *Zeitschrift fuer anorganische allgemeine Chemie*, 156:245–257, 1926.
- [TL01] J. A. Tangeman and R. A. Lange. Determination of the limiting fictive temperature of silicate glasses from calorimetric and dilatometric methods: Application to low-temperature liquid volume measurements. *American Mineralogist*, 86:1331–1344, 2001.
- [Too41] A. Q. Tool. Relation between inelastic deformability and thermal expansion of glass in its annealing range. *Journal of the American Ceramic Society*, 29:240–253, 1941.
- [TR74] T.D. Taylor and G.E. Ridone. Influence of distribution of water in silicate-glasses on mechanical relaxation. *Journal of Non Crystalline Solids*, 14:157–164, 1974.
- [TR00] M. J. Toplis and P. Richet. Equilibrium density and expansivity of silicate melts in the glass transition range. *Contributions to Mineralogy and Petrology*, 139(6):672–683, 2000.
- [Ver92] V. A. Versteeg. *Internal Friction in Lithium Aluminosilicate Glass-Ceramics*. PhD thesis, Cornell University, 1992.
- [Vog21] D. H. Vogel. Temperaturabhaengigkeitsgesetz der Viskositaet von Fluessigkeiten. *Physikalische Zeitschrift*, 22:645–646, 1921.
- [VPR96] D. VoThanh, A. Polian, and P. Richet. Elastic properties of

- silicate melts up to 2350 K from Brillouin scattering. *Geophysical Research Letters*, 23(5):423–426, 1996.
- [VS74] H. M. J. M. VanAss and J. M. Stevels. Internal-friction of mixed alkali metaphosphate glasses .I. results. *Journal of Non Crystalline Solids*, 15:215, 1974.
- [Wag04] Norman Wagner. *Mechanische Spektroskopie an vulkanischen Glaesern*. PhD thesis, Friedrich-Schiller-University Jena, 2004.
- [WBH03] N. Wagner, N. S. Bagdassarov, and K. Heide. Untersuchungen zum anelastischen und viskoelastischen Verhalten eines komplexen Aluminium-Silicatglases. *Tagungsband 77. Glastechnische Tagung in Leipzig*, Vortragsband:109–112, 2003.
- [WBH04] N. Wagner, N. S. Bagdassarov, and K. Heide. Mechanical spectroscopy of natural and synthetic silicate glasses and melts. In Hong Li, editor, *Melt Chemistry, Relaxation, and Solidification Kinetics of Glasses*, volume 170 of *Ceramic Transactions*, page in print. American Ceramic Society, 2004.
- [WD90] S. L. Webb and D. B. Dingwell. The onset of non-Newton rheology of silicate melts: A fiber elongation study. *Physics and Chemistry of Minerals*, 17:125–132, 1990.
- [WDBW00] M. Wilding, D. Dingwell, R. Batiza, and L. Wilson. Cooling rates of hyaloclastites: applications of relaxation geospeedometry to undersea volcanic deposits. *Bull Volcanol*, 61:527–536, 2000.
- [Web91] S. L. Webb. Shear and volume relaxation in  $Na_2Si_2O_5$ . *American Mineralogist*, 76:1449–1454, 1991.
- [Web92] S. L. Webb. Low-frequency shear and structural relaxation in rhyolite melt. *Physics and Chemistry of Minerals*, 19(4):240–245, 1992.
- [Web97] Sharon L. Webb. *Lectures in Earth Science 67: Silicate Melts*. Springer, 1997.
- [WHBZ01] N. Wagner, K. Heide, and S. Bark-Zollmann. Mechanisches Relaxationsverhalten rhyolithischer Obsidiane im Vergleich zu kristallisierenden Glaesern und Glaskeramiken. *Beihefte European Journal of Mineralogy*, 13(1):166, 2001.
- [WJ03] S. Webb and I. Jackson. Anelasticity and microcreep in polycrystalline  $MgO$  at high temperature: an exploratory study. *Physics and Chemistry of Minerals*, 30(3):157–166, 2003.
- [WLF55] M. L. Williams, R. F. Landel, and J. D. Ferry. The temperature dependence of relaxation mechanisms in amorphous polymers and other glass-forming liquids. *Journal of the American Chemical Society*, 77:3701 – 3707, 1955.
- [WWD95] M. C. Wilding, S. L. Webb, and D. B. Dingwell. Evaluation of a relaxation geospeedometer for volcanic glasses. *Chemical Geology*, 125:137–148, 1995.
- [WWD<sup>+</sup>96a] M. Wilding, S. Webb, D. Dingwell, G. Ablay, and J. Marti. Cooling rate variation in natural volcanic glasses from Tenerife, Ca-

- nary Islands. *Contrib Mineral Petrol*, 125:151–160, 1996.
- [WWD96b] M. C. Wilding, S. L. Webb, and D. B. Dingwell. Tektite cooling rates: calorimetric relaxation geospeedometry applied to a natural glass. *Geochim Cosmochim Acta*, 60:1099–1103, 1996.
- [Zir73] F. Zirkel. *Die mikroskopische Beschaffenheit der Minerale und Gesteine*. Verlag W. Engelmann Leipzig, 1873.
- [ZRD76] W. A. Zdaniewski, G. E. Rindone, and D. E. Day. The Internal Friction of Glasses. *Journal of Materials Science*, 14:763–765, 1976.
- [ZZY+01] Z. L. Zhang, H. D. Zhang, Y. L. Yang, I. Vinckier, and H. M. Laun. Rheology and morphology of phase-separating polymer blends. *Macromolecules*, 34:1416–1429, 2001.