

Mechanical Spectroscopy on Volcanic Glasses

Norman Wagner

*Institute of Material Research and Testing at the Bauhaus-University Weimar,
Amalienstr. 13, 99423 Weimar
Tel: ++49-3643-564-221
Fax: ++49-3643-564-202*

Klaus Heide

*Institute of Geoscience, Friedrich-Schiller-University Jena,
Burgweg 11, 07743 Jena*

Abstract

Mechanical relaxation behaviour of various natural volcanic glasses have been investigated in the temperature range $RT - 1000^\circ\text{C}$ using special low frequency flexure ($f \approx 0.63\text{Hz}$) pendulum experiments. The rheological properties complex Young's modulus $M^*(\omega, \tau)$ and internal friction $Q^{-1}(\omega, \tau)$ have been studied from a pure elastic solid at room temperature to pure viscous melt at $\log(\eta[\text{Pas}]) = 8$. The Young's modulus at room temperature $M_{RT} = (70 \pm 10)\text{GPa}$ is nearly constant. There is a positive correlation with the water content and a weak negative correlation with the cooling rate. Several relaxation processes are assumed to act: the primary α -relaxation (viscoelastic process, $E_a = (344...554)\text{kJ/mol}$) above the glass transition temperature $T_g = (935...1105)\text{K}$ and secondary anelastic β' , β and γ -relaxation processes below T_g . The dynamic glass transition, i.e. the viscoelastic α -transition, can be characterized with hierarchically coupled relaxation processes which lead to an equivalent distribution of relaxation times nearly independent of the fragility for all examined glasses. The observed secondary relaxation processes can be explained with different mechanisms: (γ, β) cooperative movement of alkali ions in the vitreous state. (β') cooperative movement of alkaline earth ions and non bridging oxygen's near the glass transition range. Here the influence of water must be taken into account as well as alteration effects due to structural α -relaxation. With a simple fractional Maxwell model with asymmetrical relaxation time distribution, $H(\tau)$, phenomenological the mechanical relaxation behaviour, is described. This establish a basis of realistic concepts for modelling of volcanic or magmatic processes.

* norman.wagner@mfpa.de

1 Introduction

It is of great importance today, in material and geoscience, to be able to understand and predict the mechanical response (elasticity, anelasticity and viscoelasticity) of multicomponent silicate glasses and melts (Pinkerton and Stevenson (1992), Webb (1997), Bark-Zollmann et al. (1997b), Donth (2001), Schilling et al. (2003), Duan et al. (2003), Mueller et al. (2003), Buchenau (2003a), Wagner et al. (2004)). The evolution of terrestrial planets is determined by the rheological properties of silicate melts and their stability under different atmospheric conditions. An important roll plays the water content as well as the chemical composition of the natural materials which reflect and cause the evolution processes (Melnik and Sparks (1999)). By optical microscopy we know already since more than one hundred years textural patterns in vitreous and crystalline volcanic rocks (Zirkel (1873), 1). This observations clearly indicate degassing induced crystallization as well as a high mobility of crystalline phases in the magma and lava during the emplacement process (Heide (1989), Sparks et al. (2000)). According to theoretical and experimental investigations of Gutzow and Heide (1996) formation of such patterns are only possible below viscosities $\log(\eta[Pa\cdot s])=4$, i.e. at temperatures far above the glass transformation range. In the case of rhyolitic glasses at approximately $1300^{\circ}C$ under atmospheric conditions, i.e. far above field experience of emplacement of dacitic lava at $\approx 925^{\circ}C$ (Tab. 1).

In addition in daily life silicate melts products are ubiquitous. Natural handling with glass usually misleads us to believe that the glass transition is one of the ten great outstanding challenges in physics (Gutzow et al. (2001), Ngai (2000), Angell et al. (2000), Donth (2001), Debenedetti and Stillinger (2001)).

From a geoscientific point of view, experimental vulcanology and petrology examine the structure, dynamics and properties of natural and synthetic sil-

Table 1

Estimated extrusion temperatures from field observations as well as calculations from the mineralogy of various high viscose lavas (Hall (1996))

Locality	Rock type	Temperature [$^{\circ}C$]
Taupo, New Zealand	Rhyolite lava and pumice	735-890
Mono Craters, USA	Rhyolite lava	790-820
Island	Rhyodacite obsidian	900-925
New Britain	Andesite pumice	940-990
New Britain	Dacite lava and pumice	925
New Britain	Rhyodacite pumice	880




Fig. 1. (top) Copperplate engraving by Zirkel 1873 of a “magnetite spider” in an obsidian from Armenia (adapted from Zirkel (1873)). (bottom) Turbulent hairline magnetite (fibres) in vitreous matrix of obsidian from Graber, Armenia together with fluidal adjusted bubbles.

icate systems (Perchuk and Kushiro (1991), Saxena (1992), Stebbins et al. (1995), Mysen (2003)). The rheological properties determine emplacement mechanisms generally and the hazard implications especially (Fink (1990), Smith (1997), Melnik and Sparks (1999)). Whereby fragmentation of vesicular magma is one of the main processes governing explosive volcanism (Dingwell (1996), Papale (1999), Gonnermann and Manga (2003)). Besides the material

consuming and dangerous direct observation of lava flows it is also in some cases possible to reconstruct the emplacement history from microscopic texture in combination with experimental techniques under laboratory conditions (Heide (1989), Fink (1990), Manga et al. (1998), Castro and Cashman (1999), Manga and Loewenberg (2001), Rust and Manga (2002), Castro et al. (2002), Cañón-Tapia and Chávez-Álvarez (2004), Cañón-Tapia and Castro (2004)). As products of very viscous melts volcanic (rhyolitic in particular) glasses (obsidian) are the link to the melt. The characterization of rheological properties of these volcanic glasses are the subject of this work.

The material property, by which glass formation is determined, is the viscosity η or the structural or α - relaxation time τ_α . Their dependence on pressure P , temperature T , chemical composition X , bubble content c_b , crystal content c_{xx} and volatile content c_v represents the goal of intensive geoscientific investigations (Bottinga and Weill (1972), Shaw (1972), Richet (1984), Hummel and Arndt (1985), Persikov (1991), Pinkerton and Stevenson (1992), Stein and Spera (1992), Bagdassarov et al. (1994), Stevenson et al. (1995), Lejeune and Richet (1995), Stevenson et al. (1996), Baker (1996), Hess et al. (1996), Bagdassarov and Dorfman (1997), Manga et al. (1998), Stevenson et al. (1998), Bagdassarov et al. (2000), Manga and Loewenberg (2001), Saar et al. (2001), Sipp et al. (2001), Giordano and Dingwell (2003)).

Since in the glass transition range the relaxation time reaches orders of magnitude, which are no longer accessible under laboratory conditions. Thus, the transition from viscous melt to solid elastic body, i.e. the viscoelastic response, determines the material behavior (Versteeg (1992), Bagdassarov and Dingwell (1993), Bagdassarov et al. (1993), Bagdassarov and Dorfman (1997), Bagdassarov (1999), Bagdassarov et al. (2001), Webb (1997), Duffrene et al. (1997a), Duffrene et al. (1997b), Duffrene and Gy (1997), Duffrene et al. (1997c), Duffrene (1998), Mueller et al. (2003), Wagner et al. (2003), Webb and Jackson (2003)).

In the vitreous state the structure of the melt is frozen in, however, here in addition dynamic processes (mobility of ions in the glassy network) take place, which can be measured by mechanical spectroscopy as internal friction, whereby a small water content cause unresolved phenomena (Roetger (1941), Fitzgerald (1951a), Fitzgerald (1951b), Roetger (1958a), Roetger (1958b), Ryder and Rindone (1961), Coenen (1961), Day and Rindone (1962a), Day and Rindone (1962b), Day and Steinkam (1969), Shelby and Day (1969), McVay and Day (1970), Shelby and Day (1970), Day and Stevels (1972), Roetger (1974), Roetger (1975), Day and Stevels (1974), Day (1974b), Day (1974a), VanAss and Stevels (1974), Taylor and Rindone (1974), Zdaniewski et al. (1976), Taylor and Brown (1979a), Taylor and Brown (1979b), Bartenev (1983), Versteeg (1992), Ke (1996), Bartenev and Lomovskoi

(1996), Bark-Zollmann et al. (1998b), Roling and Ingram (1998b), Roling and Ingram (1998a), Roling (2001)).

In this study the rheological properties, Young's moduls M^* and internal friction $\tan \delta = Q^{-1}$, of natural volcanic glasses have been investigated in a wide temperature range from a purely elastic solid at room temperature to purely viscous melt at a viscosity $\log(\eta[\text{Pas}]) \approx 8$. It will contribute to the understanding of the thermocinetics and dynamics that govern the glass transition, at temperatures well above, below and at the glass transition temperature T_g (Donth (2001)). In this context the rheological properties of natural and synthetic silicate glasses and melts are of interest. With a simple generalized fractional Maxwell model, the relaxation behavior is described phenomenologically. This establish a basis of realistic concepts for modelling of volcanic or magmatic processes.

2 Basics

A necessary and sufficient condition to glass formation is a corresponding (critical) cooling rate q_K to avoid cristallization. A coarse approximation for the estimate of q_K gives Owen (1985), Feltz (1983) and Debenedetti (1996):

$$q_K = 2 \cdot 10^{-6} \frac{T_m^2 R}{V \eta(T_n)} = \frac{T_m - T_n}{\tau_{K,n}} \quad (1)$$

with the fusing temperature T_m , the gas constant R , the molar volume V , viscosity η , the so called nose temperature T_n and corresponding critical time $\tau_{K,n}$. Here, according to Debenedetti (1996) or Angell (1988) the time τ_K for formation of a critical volume V_K as well as the structural relaxation time τ_α and their interplay (time-temperature-transformation) is of great significance (cf. Fig. 2). Above the thermal glass transition temperature T_g^{exp} specified by the experimental conditions, which is determined by a characteristic structural or α relaxation time τ_α , the mechanical glass transition occurs at the 'mechanical' relaxation time $\tau_\alpha(T_\alpha)\omega \approx 1$. The mechanical glass transition temperature T_α shifts with measurement frequency $\omega = 2\pi f$ in general via the Arrhenian equation

$$\ln\left(\frac{\Omega}{\omega}\right) = \frac{E_a(T)}{k_B T_\alpha} \quad (2)$$

with jump frequency $\log(\Omega[\text{Hz}]) \approx 12 - 14$ as typical frequency of molecular vibration (Russell et al. (2003)), Boltzmann-constant k_B and a temperature dependent activation energy $E_a(T)$ with $\frac{dE_a}{dT} \leq 0$ (Gutzow and Schmelzer




Fig. 2. Schematic representation to the construction of the TTT -curve (time-temperature-transformation). (a) isobar dependence of the free enthalpy G on temperature T of a gas, a liquid (stable and supercooled liquid), and a crystal as well as the corresponding glass of a pure substance with the boiling point T_B , melting point T_m and the glass transition temperature T_g . (b) The hypothetical intersection point between τ_K and τ_α is not reached, since (c) τ_K goes up strongly due to the drastic viscosity increase with τ_α (after Debenedetti (1996)).

(1995), Bartenev and Lomovskoi (1996)). The most common entrances to the modelling of the temperature dependence of the activation energies are:

- (1) the empirical VFT-equation (Vogel (1921), Fulcher (1925), Tammann and Hesse (1926)) with the adjustable parameters B_{VFT} and T_0 (T_0 is usually equated with the Kauzmann-temperature (Hodge (1994), Hodge (1997)))

$$E_a(T) = \frac{B_{VFT}}{1 - \frac{T_0}{T}}. \quad (3)$$

- (2) the Adam-Gibbs-equation (Adam and Gibbs (1965)) with the adjustable parameter B_{AG} and a temperature dependend configurational entropy $S_c(T)$

$$E_a(T) = \frac{k_B B_{AG}}{S_c(T)}. \quad (4)$$

- (3) the Avramov-equation (Avramov and Milchev (1988)) with a dimensionless activation energy ε_A , the Avramov fragility index α_A and the glass transition temperature T_g at a viscosity of $\log(\eta[Pa\cdot s]) = 12.3$

$$E_a(T) = \frac{k_B \varepsilon_A T_g^{\alpha_A}}{T^{\alpha_A - 1}}. \quad (5)$$

- (4) the Williams-Landel-Ferry-equation (WLF, (Williams et al. (1955)) with the parameters A_{WLF} , B_{WLF} and the fragility index $m = \left. \frac{d \ln(\tau_\alpha)}{d(T_g/T)} \right|_{T_g}$ at the glass transition temperature T_g (Boehmer and Angell (1992), Donth (2001))

$$E_a(T) = mT - \frac{A_{WLF} T (T - T_g)}{B_{WLF} + (T - T_g)}. \quad (6)$$

$\log(\Omega)$ and the Kauzmann-Temperature $T_0 \approx (48...815)K$ are the asymptotes concerning the frequency or temperature (Donth (1981), Donth (1992), Donth (2001), Hodge (1994), Angell et al. (2000)).

The mechanical glass transition for small deformations 10^{-4} is the linear viscoelastic response of the material. Then the linear response is completely determined by properties of the equilibrium melt if thermal fluctuations are included in the equilibrium concept. The fluctuation-dissipation theorem (FDT) of statistical physics implies the important statement that it is exclusively thermal fluctuations which determine the linear response (Donth (2001), Roling (2001)). Especially for the understanding of processes¹ on a geological time scale these concepts are very useful (Nemilov and Johari (2003)). Non-linearity has to be taken into account for large deformations and high strain rates, i.e. under emplacement conditions (Bagdassarov and Dingwell (1993), Dragoni and Tallarico (1994), Dragoni and Tallarico (1996), Renner et al. (2000), Blake and Bruno (2000), Buisson and Merle (2002)).

Above a critical temperature T_C predicted by the idealized mode coupling theory, *MCT*, the system is retained to ergodic and below non-ergodic (Goetze and Sjogren (1992)). Non-ergodicity means that the correlation function Φ does not converge against an expected equilibrium value of $\lim_{t \rightarrow \infty} \Phi(t) = \Phi_\infty = 0$, but reaches a final value $\Phi_\infty > 0$. Since the corresponding coupling parameters are temperature dependent, one finds the critical temperature T_C if the existence of a non-ergodic stage to the first time have been observed. In this sense one speaks of a phase transition at the glass transition but the precise designation is ergodicity transition. That is, that density fluctuations froze below T_C . Above T_C the structural α -relaxation and second β -relaxation can not be distinguished. Below T_C diffusion processes

¹ Within glass science these processes called 'Thermometereffekt' according to internal friction investigations of Roetger (1941).

and the structural α -relaxation are to be observed separately. In the internal friction spectrum the characteristic secondary β loss maxima occur. Ergodicity can be restored by introduction of hopping-processes in the enlarged MCT also below T_C . The temperature dependence of the α -time scale for $T > T_C$ is of the form (Schneider (2000), Donth (2001)):

$$\tau_a \propto \eta \propto (T - T_C)^\gamma. \quad (7)$$

with a parameter γ . The following general rule is valid (Buchenau (2003b))

$$\tau_\alpha(T_c) \approx 10^{-7} s. \quad (8)$$

The distinction of the dynamics of the primary α process and a β_{fast} process (in the sense of a microscopically fast movement) above T_C in the field of the undercooled liquid is predicted, however, through the MCT and confirmed by neutron and light scattering experiments onto different glass formers as well as through computer simulations (Roessler and Sokolov (1996), Siewert and Rosenhauer (1997), Horbach and Kob (2002), Buchenau (2003b)). The main problem with the MCT consists in the analysis of the α -process. So (7) can only be observed experimentally in a small temperature range. If one identifies T_C with the Vogel temperature T_0 or the glass transition temperature T_g , then experimental relaxation times and (7) are not to bring into agreement. A comparison with experimental data leads to the reasonable statement $T_C > T_g > T_0$ and $T_C/T_g \approx 1.3...2.6 \propto 1/m$ for silicate melts (Hess (1996), Pfeiffer (1998)). There according to the mode coupling theory for $T < T_C$ the α process no more is supposed to occur but is experimentally even strongly observed at $T \approx T_g$. For this reason one is today generally of the opinion, that the mode coupling approximation is a good theory for $T > T_C$ and break down for temperatures below T_C especially for strong melts. In spite of these difficulties the MCT is today the widest driven forward analytical representation, that understands essential appearances of the glass transition correctly and contains also many possibilities of a generalization (Schulz (2000)).

During cooling, the mobility of the atoms decrease. At the (nonlinear) thermal glass transition range (the relaxation time is a function of temperature T and the structural state $\tau(T, T_f)$) typical relaxation times are reached by seconds or minutes, in order to take the (metastable) equilibrium position. If the temperature now falls, the structure can not reach their equilibrium and is therefore “trapped” in a definite configurational state at the limit of the fictive temperature T_f (Tool (1941), Gardon and Narayanaswamy (1970), Martens (1985)). Ritland (1956), Martens et al. (1987), Richet and Neuville (1992), Wilding et al. (1995), Wilding et al. (1996b), Wilding et al. (1996a), Wilding et al. (2000),




Fig. 3. Schematic representation of thermocinetic and dynamic α -transition of an inorganic-glass or melt and related phenomena: γ_{R^+} -alkali ion transport, β_{H_2O} - water peak, β' - superposition of Johari-Goldstein relaxation and the thermal glass transition (c.f. Doliwa (2002)).

Gottsmann and Dingwell (2001a), Gottsmann and Dingwell (2001b), Debenedetti and Stillinger (2001), Tangeman and Lange (2001)). In the vitreous state it is possible to measure β or secondary mechanical relaxation processes which are substantially decoupled of the structural α relaxation (c.f. Fig. 3). This processes can be explained with different mechanisms: (γ, β) cooperative movement of alkali ions in the vitreous state. (β') cooperative movement of alkaline earth ions and non bridging oxygen's near the glass transition range. Here the influence of water must be taken into account as well as alteration effects due to structural α -relaxation. The temperature dependents of diffusion, electrical conductivity and mechanical relaxation processes can be described in most cases by an Arrhenian-law via equation (2) with an equivalent activation energy (see Frischat (1975), Paulmann (1998), Maass (1999), Ngai (2000)).

Relaxation processes (ion mobility, viscoelasticity) deviating from the classical exponential (Debye) behavior are often encountered in the dynamics of complex materials such as silicate glasses below and above T_g , glass ceramics and partially molten rocks (Jonscher (1977), Mueller (1983), Kampfmann and Berckhemer (1985), Bagdassarov and Dingwell (1993),

Webb (1997), Roling and Ingram (1998b), Angell et al. (2000), Donth (2001), Ngai (2000)). In many cases experimentally observed relaxation functions exhibit a stretched exponential (Kohlrausch-Williams-Watts) decay Kohlrausch (1847)

$$\Phi \propto \exp \left(- \left[\frac{t}{\tau} \right]^{\beta_{KWW}} \right) \quad (9)$$

with $0 < \beta_{KWW} < 1$, or a scaling decay

$$\Phi \propto \left[\frac{t}{\tau} \right]^a \quad (10)$$

with $0 < a < 1$ (Bagdassarov and Dingwell (1993), Bagdassarov et al. (1993), Bagdassarov and Dorfman (1997), Bagdassarov (1999), Bagdassarov et al. (2000), Mueller et al. (2003)). An appropriate tool to describe phenomenologically this richness of dynamical features is fractional calculus (*FC*, see below) (Schiessel et al. (1995b)).

2.1 Rheological models

Usually phenomenologic viscoelastic models are based on springs and dampers. A spring is purely elastic and describes the instantaneously acting Hooke law with the dynamic responses (complex modulus $M^* = M' + iM''$ with storage modulus M' and loss modulus M'' or complex creep compliance $M^* \cdot D^* = 1$) being constant and real ($M''/M' = Q^{-1} = 0$). The constitutive equation of stress σ and strain ε is of the form

$$\sigma(t) = M_0 \varepsilon(t), \quad M^* = M' = M_0 = D_0^{-1} \quad (11)$$

with an idealized Young's modulus M_0 . A damper is purely viscous and describes the instantaneously acting Newton law with purely imaginary dynamic responses ($Q^{-1} = \infty$) Donth (1992):

$$\sigma(t) = \eta \frac{d\varepsilon(t)}{dt}, \quad M^* = iM'' = i\omega\eta \quad (12)$$

Through combinations of springs and dashpots one arrives at standard viscoelastic models, such as the Maxwell or the Zener, these models involve a fairly small number of single elements. The problem here is that the corresponding ordinary differential equations have a relatively restricted class

of solutions, which is, in general, too limited to provide an adequate description for the complex systems discussed in the introduction. To overcome this shortcoming one can relate stress and strain through fractional equations (Schiessel et al. (1995b)):

$$\sigma(t) = M_0 \tau^\beta \frac{d^\beta \varepsilon(t)}{dt^\beta} \quad (13)$$

with $0 \leq \beta \leq 1$ and the relaxation time τ . In this way one readily obtains scaling decays. In general, FC allows the interpolation between the purely elastic behaviour of equation (11), obtained for $\beta = 0$ in equation (13), and the purely viscous pattern of equation (12), obtained for $\beta = 1$ in equation (13). Schiessel and Blumen (1993); Schiessel et al. (1995b); Schiessel and Blumen (1995); Schiessel et al. (1995a); Heymans and Bauwens (1994); Heymans (1996) and Heymans (1996) have demonstrated that the fractional relation, equation (13), can be realized physically through hierarchical arrangements of springs and dampers, such as ladders, trees or fractal structures. We now introduce the term fractional element (FE) to denote such a hierarchical structure and specify it by the triple (β, M_0, τ) .

2.2 Fractional Maxwell model

The classical viscoelastic Maxwell model (composed of a linear elastic element and a linear viscous element in series) may be modified by replacing the damper by a FE . The dynamic responses for this model is:

$$\frac{M^*(\omega, \tau)}{M_0} = \frac{(i\omega\tau)^\gamma}{1 + (i\omega\tau)^\gamma}, \quad \frac{D^*(\omega, \tau)}{D_0} = 1 + (i\omega\tau)^{-\gamma} \quad (14)$$

which is the so called Caputo-Model (Bagdassarov et al. (2000), Bagdassarov (1999)) or Cole-Cole-Model (Cole and Cole (1941)). In the high temperature and low frequency limit (14) leads to constant- Q^{-1} . For $\gamma = 1$ (14) is transformed to the classical Maxwell model. When both elements are replaced by FE 's the dynamic responses is of the Jonscher-type (Jonscher (1977)):

$$\frac{M^*(\omega, \tau)}{M_0} = \frac{(i\omega\tau)^\alpha}{1 + (i\omega\tau)^{\alpha-\beta}}, \quad \frac{D^*(\omega, \tau)}{D_0} = (i\omega\tau)^{-\alpha} + (i\omega\tau)^{-\beta} \quad (15)$$

with $\beta < \alpha$ and the constitutive equation is of the form:

$$\sigma(t) + \tau^{\alpha-\beta} \frac{d^{\alpha-\beta} \sigma(t)}{dt^{\alpha-\beta}} = M_0 \tau^\alpha \frac{d^\alpha \varepsilon(t)}{dt^\alpha} \quad (16)$$

Since $0 \leq \beta < \alpha \leq 1$ the condition for thermodynamic compatibility is fulfilled (Heymans and Bauwens (1994), Heymans (1996)). Transformation into a standard model is carried out by adding an elastic element of modulus M_1 in series. The dynamic response $M^*(\omega, \tau)$ and internal friction Q^{-1} then become:

$$\frac{M^*(\omega, \tau)}{M_0} = \frac{M_1(i\omega\tau)^\alpha}{M_1(1 + (i\omega\tau)^{\alpha-\beta}) + M_0(i\omega\tau)^\alpha}, \quad (17)$$

$$\frac{D^*(\omega, \tau) - D_1}{D_0} = (i\omega\tau)^{-\alpha} + (i\omega\tau)^{-\beta}$$

$$Q^{-1}(\omega, \tau) = \frac{(\omega\tau)^{-\alpha} \sin\left(\frac{\alpha\pi}{2}\right) + (\omega\tau)^{-\beta} \sin\left(\frac{\beta\pi}{2}\right)}{(\omega\tau)^{-\alpha} \cos\left(\frac{\alpha\pi}{2}\right) + (\omega\tau)^{-\beta} \cos\left(\frac{\beta\pi}{2}\right) + \frac{M_0}{M_1}} \quad (18)$$

It is also possible to give an analytical expression for the relaxation time distribution $h(\tau)$ with the relation $M^*(\omega, \tau) = \hat{M}(p, \tau)|_{p=i\omega}$ Gloeckle (1993):

$$h(\tau) = \pm \lim_{\varepsilon \rightarrow 0} \Im[\hat{M}(p)]|_{p=-1/\tau \pm \varepsilon} \quad (19)$$

and one gets:

$$h(\tau) = \frac{\Omega_{\alpha,\beta}^S + \frac{M_0}{M_1}}{\tilde{\tau}^{-2\alpha} + \tilde{\tau}^{-2\beta} + 2\tilde{\tau}^{-\alpha-\beta} \cos([\alpha - \beta]\pi) + \frac{2M_0}{M_1}\Omega_{\alpha,\beta}^C + \frac{M_0^2}{M_1^2}} \quad (20)$$

with $\tilde{\tau} = \tau/\tau_{max}$, $\Omega_{i,j}^C = \tilde{\tau}^{-i} \cos(i\pi) + \tilde{\tau}^{-j} \cos(j\pi)$, $\Omega_{i,j}^S = \tilde{\tau}^{-i} \sin(i\pi) + \tilde{\tau}^{-j} \sin(j\pi)$.

Table 2

The summary of various spectral functions and their power-law behaviour. Abbreviation: $p = i\omega\tau$, A', A - constants.

			$\omega\tau \rightarrow 0$			$\omega\tau \rightarrow \infty$		
	M^*/M_0		M'/M_0	M''/M_0	Q^{-1}	M'/M_0	M''/M_0	Q^{-1}
Debye (1941)	$(1 + p^{-1})^{-1}$		$(\omega\tau)^2$	$(\omega\tau)^1$	$(\omega\tau)^{-1}$	1	$(\omega\tau)^{-1}$	$(\omega\tau)^{-1}$
Cole and Cole (1941)	$(1 + p^{-\alpha})^{-1}$	$0 < \alpha \leq 1$	$(\omega\tau)^\alpha$	$(\omega\tau)^\alpha$	A'	1	$(\omega\tau)^{-\alpha}$	$(\omega\tau)^{-\alpha}$
Jonscher (1977)	$(p^{-\alpha} + p^{-\beta})^{-1}$	$0 < \beta \leq \alpha \leq 1$	$(\omega\tau)^\alpha$	$(\omega\tau)^\alpha$	A'	$(\omega\tau)^\beta$	$(\omega\tau)^\beta$	A
KWW (Kohlrausch (1847))	$\exp(-(t/\tau)^\beta)$	$0 < \beta \leq 1$	$(\omega\tau)^2$	$(\omega\tau)^1$	$(\omega\tau)^{-1}$	1	$(\omega\tau)^{-\beta}$	$(\omega\tau)^{-\beta}$
Havriliak and Negami (1967)	$1 - (1 + p^\alpha)^{-\beta}$	$0 < \alpha, \beta < 1$	$(\omega\tau)^\alpha$	$(\omega\tau)^\alpha$	A'	1	$(\omega\tau)^{-\beta\alpha}$	$(\omega\tau)^{-\beta\alpha}$
Davidson and Cole (1951)	$1 - (1 + p)^{-\beta}$	$0 < \beta \leq 1$	$(\omega\tau)^2$	$(\omega\tau)^1$	$(\omega\tau)^{-1}$	1	$(\omega\tau)^{-\beta}$	$(\omega\tau)^{-\beta}$
Mueller (1983)	$Q = (\omega\tau)^\gamma$	$0 < \gamma \leq 1$	$\rightarrow 0$	$(\omega\tau)^1$	$(\omega\tau)^{-\gamma}$	1	$(\omega\tau)^{-\gamma}$	$(\omega\tau)^{-\gamma}$
FC1	$(p^{-1} + p^{-\beta} + \frac{M_0}{M_1})^{-1}$	$0 < \beta \leq 1$	$(\omega\tau)^{2-\beta}$	$(\omega\tau)^1$	$(\omega\tau)^{-1+\beta}$	1	$(\omega\tau)^{-\beta}$	$(\omega\tau)^{-\beta}$
FC2	$(p^{-\alpha} + p^{-\beta} + \frac{M_0}{M_1})^{-1}$	$0 < \beta \leq \alpha \leq 1$	$(\omega\tau)^\alpha$	$(\omega\tau)^\alpha$	A'	1	$(\omega\tau)^{-\beta}$	$(\omega\tau)^{-\beta}$

3 Sample selection

The nine natural volcanic glasses used were fresh, unweathered, unaltered, and nonhydrated obsidians free of cracks with low crystal ($< 1\%$) and bubble content ($< 1\%$). Chemical composition of the matrix glass was quantified by electron microanalysis (SEM-EDX, DSM 940 CARL ZEISS, eXL 10 Spektrometer, Oxford Instruments). Volatile-species and thus water content are determined in high-vacuum degassing experiments (controlled heating rate $10\text{K}/\text{min}$ from RT - 1500C) coupled with a quadrupole mass spectrometer (QMA 125 Balzers, Schmidt and Heide (2000), Leschik et al. (2003), Heide and Schmidt (2003)).

YEL is a grey crystal-poor obsidian from Yellowstone (USA). *VUL* from Vulcano, *LIP* from Lipari (Italy) and *JAL* from Jalisco (Mexico) are grey crystal-free glasses. The sample *MIL* from Milos (Greek) is grey-black crystal-poor. *RAB* from Hrafninnuhryggur (Island) and *DYR* from Artenis (Armenia) are black crystal-poor glasses. The obsidian *ATS* from Artis (Armenia) is grey crystal-poor with crystal bands. *QUI* from Quironcolo (Argentina) and *IKI* from Ikizidre (Turkey) are transparent homogeneous obsidians with very few large crystals.

4 Experiments




Fig. 4. Flexure Pendulum Equipment.

The flexure pendulum is shown in Fig. 4. It operates in air at a frequency of about 0.63Hz (small deformations $\approx 10^{-5} \dots 10^{-3}$) and temperatures up to $T \approx 1000^\circ\text{C}$ (cf. Bark-Zollmann (1994), Bark-Zollmann et al. (1997a), Bark-Zollmann et al. (1997b), Bark-Zollmann et al. (1998a),

Table 3

Chemical composition and water-content (wt.%) of the volcanic glasses. <dtl: less then dedection limit, agpaitic index (mol%) $AI = \frac{K_2O+Na_2O}{Al_2O_3}$, aluminium saturation index $ASI = \frac{Al_2O_3}{K_2O+Na_2O+CaO}$, structur modifier (mol%) SM from Giordano and Dingwell (2003), exess oxides (mol%) $EO = SM - 0.5Fe_2O_{3t} - Al_2O_3$ from Gottsmann et al. (2002).

	YEL	VUL	LIP	MIL	RAB	DYR	ATS	JAL	QUI
SiO_2	77.01	74.66	74.84	77.03	74.56	78.67	78.57	76.39	77.11
TiO_2	<dtl	<dtl	<dtl	0.22	<dtl	0.26	<dtl	<dtl	0.13
Al_2O_3	11.97	12.84	12.92	12.72	13.04	11.6	11.95	10.79	14.06
Fe_2O_{3t}	1.53	1.98	1.86	1.34	1.88	0.6	0.57	3.53	0.64
CaO	0.54	0.81	0.86	1.52	0.89	1.6	1.34	0.18	0.46
MgO	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl
MnO	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl	<dtl
Na_2O	3.11	3.29	3.87	3.05	4.04	0.7	2.31	3.94	2.55
K_2O	5.61	5.92	5.2	3.98	5.17	6.28	5.07	5.05	4.56
Total	99.77	99.5	99.88	99.86	99.94	99.71	99.81	99.88	99.51
AI^{-1}	1.07	1.08	1.08	1.36	1.06	1.46	1.29	0.92	1.55
ASI	0.99	0.96	0.95	1.05	0.94	1.07	1.02	0.88	1.42
$\frac{NBO}{T}$	0.0103	0.0197	0.0257	2E-4	0.0199	0.0037	0.005	0.023	0.409
EO	0.47	0.89	1.16	-0.17	0.9	-0.38	0.23	1.05	-1.97
H ₂ O	0.096	0.163	0.21	0.113	0.101	0.085	0.106	0.027	0.222

Bark-Zollmann et al. (1998b), Bark-Zollmann et al. (1998c), Wagner et al. (2001)). The sample is a combination of two bars with a rectangular cross section of (1x1)mm² and a lenght l of 40mm. One end of the specimen is held rigid and the other end is connected with the movable part of the flexure pendulum. Measurements were done under isothermal conditions in the range below the glass transition temperature T_g in 10K-steps and above T_g in 5K-steps. Experimentally determined quantities are the logarithmic decrement without specimen Λ_P and of the coupled system specimen-pendulum Λ_{SP} , oscillation period of pendulum $t_P = f_P = 2\pi\omega_P$ and of the coupled system specimen-pendulum t_{SP} . With the direction moment $D_P = (5.35 \pm 0.36)Nm$ of the pendulum and geometrical quantities of the specimen: free length l , moment of inertia I and experimentally determined quantities rheological parameters complex Young's modulus $M^*(\omega_P, T)$:

$$M'(\omega_P, T) = \frac{3}{2} \frac{D_P l}{I} \left(\frac{t_P^2}{t_{SP}^2} - 1 \right), \quad (21)$$

$$M''(\omega_P, T) = \frac{3}{2} \frac{D_P l}{\pi I} (\Lambda_{SP} - \Lambda_P) \quad (22)$$

and internal friction $Q^{-1}(\omega_P, T)$ were calculated

$$Q^{-1}(\omega_P, T) = \frac{M''(\omega_P, T)}{M'(\omega_P, T)} = \frac{t_{SP}^2 (\Lambda_{SP} - \Lambda_P)}{\pi (t_P^2 - t_{SP}^2)}. \quad (23)$$

The mechanical spectra are characterized by the complex Young's modulus $M^*(T)$, complex shear modulus $G^*(T)$, internal friction $Q^{-1}(T)$, complex creep compliance $D^*(T)M^*(T) = 1$, shear compliance $J^*(T)G^*(T) = 1$ and/or the complex shear viscosity $\eta^*(t)$. The complex quantities can be separated into real (storage modulus M') and imaginary parts (loss modulus M''). The Kramers-Kronig (dispersion) relations (Kramers (1926), Kronig (1926)) couple the real and imaginary parts of the complex quantities $A^* = A' + iA''$ of a material by

$$A'(\omega) = -H[A''(\xi)], \quad A''(\omega) = H[A'(\xi)] \quad (24)$$

with the Hilbert-transform by principal value integral \oint (Donth (2001))

$$H[f(\xi)](\omega) = \frac{1}{\pi} \oint \frac{f(\xi) d\xi}{\xi - \omega}, \quad H^{-1} = -H. \quad (25)$$

These are purely mathematical implications of the linear and causal material equations. The discussion of the mechanical spectra can take place thereby on the individual modulus.

5 Results

Fig.5 represents the storage modulus M' and the loss modulus M'' for the investigated natural glasses. All obsidians show a relatively similar behaviour. A deviation from the general trend shows the *LIP* sample due to strong vesiculation. Here, a particularly long-drawn-out thermal and mechanical glass transition can be observed in the storage modulus.

The storage modulus at room temperature M_{RT} is a material constant, i.e. the Young's-modulus² of the glass $E = M_{RT}$, which ranges for silicate glasses

² If measurements of $M'(T)$ are carried out below RT , one observes a further rise with falling temperature or rising frequency due to relaxation processes (Jagdt (1960)).




Fig. 5. Temperature dependence of the real part (storage modulus) M' and imaginary part (loss modulus) M'' of the complex Young's modulus $M^* = M' + iM''$ for the natural volcanic glasses. (inset) Asymptotic behaviour of storage modulus at high temperature.




Fig. 6. Complex Young's modulus M^* normalised with the unrelaxed Young's modulus M_α at T_g in the Gaussian-plane.

between 60GPa and 100GPa (Wagner (2004)). The obsidians exhibit a relatively constant value of $(70 \pm 10)\text{GPa}$. In principle, E is a function of the chemical composition, water-, bubble-, crystal content and temperature pre-history, however, the sensitivity on these influences is much less than those on the relaxation times (Wagner (2004)). There is a positive correlation with the water content and a weak negative correlation with the cooling rate (Fig. 7).

In the examined temperature range $M'(T)$ decreases continuously for most silicate glasses (Fig. 8). An exception is silica glass with an anomalous increase of Young's modulus with temperature between 100K and T_g (Brueckner (1970), Brueckner (1971)). Fig. 8 and Tab. 4 clearly indicate that the examined natural glasses have to be assigned to the silica glass with the exception of the LIP-obsidian.

The total temperature dependence of Young's modulus is given by the differential (Brueckner (1971), Askarpour et al. (1993), Rivers and Carmichael (1987), VoThanh et al. (1996), Schilling et al. (2003)).:

$$\frac{dM'(T)}{dT} = \alpha_T V \left(\frac{\partial M'}{\partial V} \right)_T + \left(\frac{\partial M'}{\partial T} \right)_V \quad (26)$$

with volume V and thermal coefficient of expansion $\alpha_T = \frac{1}{V} \frac{\partial V}{\partial T}$. The sign of dM'/dT will be governed by the sign of $\left(\frac{\partial M'}{\partial T} \right)_V$, if α_T is negligibly small. In the case of a Born-von-Kármán solid, as in the case of a Debye and Grueneisen solid, it was shown that dM/dT is negative at low temperatures and large α_T ,




Fig. 7. Dependence of the Young's modulus M_{RT} on the chemical composition (according to NBO/T as well as EO and AI^{-1} to Tab. 3) as well as the water content for the examined obsidians. Lines are guides to the eye.




Fig. 8. Fragility index m versus the temperature derivative of the storage modulus $\partial M'(T)/\partial T|_{T < T_g}$ in the temperature range below T_g for the obsidians in comparison with synthetic silicate glasses.

Table 4

Rheological properties of the examined volcanic glasses. $NaSi-Na_2Si_3O_7$; \spadesuit Heide (2004), Homosil, $T = 1199^\circ\text{C}$; \diamond Bartenev and Lomovskoi (1996); \P Brueckner (1971); b Ericson et al. (1975); d Polian et al. (2002); $^\#$ Toplis and Richet (2000); § Mochida et al. (1980), $T=\text{RT-}350^\circ\text{C}$

	M_{RT} [GPa]	T_α [° C]	M_α [GPa]	$-\frac{dM'}{dT}$ [$\frac{MPa}{K}$]	$\frac{\partial \log M'}{\partial(1000/T)} = -\frac{T}{1000} \frac{\partial \log M'}{\partial \log T}$			$10^{-7}\alpha_T$ [1/K]
					$T < T_g$	$< T <$	$T_m < T$	
YEL	75	861	53	5.8	0.010	0.90	16.3	\vdots
VUL	77	817	72	4.9	0.017	1.22	28.7	\vdots
LIP	61	789	45	20.4	0.028	0.96	14.1	\vdots
MIL	67	891	58	4.8	0.009	0.74	19.8	\vdots
RAB	73	819	55	8.5	0.025	0.9	24.4	61.6^b
DYR	72	830	71	0.2	0.001	3.16	25.9	\vdots
ART	76	864	74	1.6	0.004	1.34	18.8	\vdots
JAL	70	782	64	4.4	0.022	–	31,4	\vdots
QUI	81	824	81	-0.2	-0.001	1.47	14.4	
SiO_2	79	1239^\diamond	75^\spadesuit	-5.6	-0.005	-0.46^d		5.4^\P
Di	92	769	79	18.5	0.02	4.6	71	$139^\#$
$NaSi$	61	523	55	20	0.026	2.5	43.7	123^\S

and positive at high temperature and small α_T (Brueckner (1970)). However, steps occur in the storage modulus curve at the secondary relaxation transitions γ, β, β' (Fig. 9). Especially for the natural rhyolitic glasses $dM'(T)/dT$ below T_g is very small and it is possible to observe the relaxation steps. A constant value of dM'/dT follows at a superposition of several processes or with a high thermal coefficient of expansion α_T (c.f. and Tab. 4). If relaxation processes are strong and in different temperature ranges, then minima occur in dM'/dT .

In the temperature range above T_g M' can be characterized in the Arrhenius-diagram. It can be differentiated into two ranges: $T_g \leq T \leq T_\alpha$ and above T_α . Here, T_α is the mechanical glass transition temperature at the loss modulus maximum (Tab. 4). By means of an Arrhenian-ansatz for temperatures $T > T_\alpha$ it is possible to determine the apparent activation energy of viscous flow $E'_{a,\alpha}$ (Wagner (2004)):

$$\frac{\partial \log M'}{\partial(1/T)} \approx \frac{2E'_{a,\alpha}}{2,303R}. \quad (27)$$




Fig. 9. (top) Relaxation steps ΔM for two relaxation processes: cooperative motion of alkali-ions γ_{R+} and mixed alkali-peak β_{mix} and (bottom) internal friction Q^{-1} in the case of the *RAB* obsidian.

Above T_g all obsidians show a clear temperature dependence of the storage modulus M' which is caused by the strong change of the structure (configurational states). In principle, it is possible to determine the glass transition temperature T_g at a relaxation time $\tau \approx 300s$ from the change of $\partial M'(T)/\partial T$ if a linear decay of M' in the temperature range below and above T_g is observed. Attention must be paid to distinguish between T_g at $q\tau \approx 1$ (Frenkel-Reiner-Kobeko Gleichung, Gutzow and Schmelzer (1995)), the onset of the mechanical glass transition T_{ve} at $\omega\tau \approx 100$, and the mechanical glass transition temperature T_α at $\omega\tau \approx 1$ (see Fig. 10).

Below T_{VE} no relaxation contributions (viscoelastic relaxation of the structure within the observation window) can be observed, and it is only possible to examine the mechanical characteristics of the appropriate “current” configurational state as well as anelastic relaxation processes such as the Johari-Goldstein relaxation or the loss due to the mobility of divalent cations. The temperature dependence is substantially smaller than above T_α , whereby mechanical glass transition is essentially steered by the Maxwell- α -relaxation time $\tau_\alpha(T)$.

At relaxed melt viscosity two orders of magnitude above the Maxwell-relaxation time at T_α (Webb and Dingwell (1990), Webb (1991), Webb (1992),




Fig. 10. Definition of the temperatures used in this article. (a) Complex Young's modulus M^* (b) internal friction Q^{-1} of the *JAL*-obsidian in the Arrhenius diagram. (c) internal friction Q^{-1} as a function of the normalized relaxation time $\log(\omega_P\tau_\alpha)$

Webb (1997)) above the temperature $T_\mu \approx 930 \pm 60^\circ C$, should hold the relation $\lim_{\eta' \rightarrow \eta_{rel}} M'(T) = 0$ or $\lim_{\eta' \rightarrow \eta_{rel}} G'(T) = 0$.

Since, however, as a function of chemical composition of the glasses phase separation and crystallization features can arise, and a temperature range of a plateau in Young's and shear modulus, a relaxed modulus $M'_{rel}, G'_{rel} \neq 0$ can occur (vgl. Abb 11, Duffrene et al. (1997a), Duffrene et al. (1997b), Duffrene and Gy (1997), Duffrene et al. (1997c), Duffrene (1998), Wagner (2004)). The plateau is typical for Polymers (Donth (1992)) in addition, for partially crystalline rocks or glass ceramics (Bagdassarov et al. (1994), Bagdassarov and Dorfman (1997), Smith (1997), Lu and Jackson (1998), Bagdassarov (1999), Bagdassarov et al. (2000), Renner et al. (2000)). Here, among other things, it was stated that shear stress induced phase separation can occur (Qiu et al. (1998), Zhang et al. (2001), Araki and Tanaka (2001)). In the case of obsidians no plateaus can be observed (Fig. 5 and 11).

The loss modulus M'' of the volcanic glasses is represented in Fig. 5. The mechanical spectrum can be essentially divided into three ranges, characterized by typical relaxation processes³: (β) low-temperature range (RT- $300^\circ C$), (β') range in the vicinity of T_g and (α) viscoelastic, mechanical glass transition.

Fig. 12 shows the spectra below T_g . By scaling the spectra with T_α it becomes clear that the temperature run of the curve for obsidian of different sources is very similar. It can be distinguished in two types: (A) a nearly temperature independence of the β -range⁴ of M'' with a average amplitude of 0,7GPa (*QUI, MIL, VUL*) and (B) a minimum in $M''(T)$ with $T - T_\alpha = -450^\circ$ (*LIP, DYR, YEL, RAB, JAL, ATS*). The β' transition deviates only for *MIL*-obsidian from the general trend. The temperatures of the minima and maxima, $T_{\beta,max,min}$ and the values of internal friction are summarized in Tab. 5. Since the intensity of the effects and signal-to-noise ratio are small, all processes below T_g are understood for the *GMM* as two processes β and β' . However, it is in the case of *RAB, JAL, LIP, YEL* and *ATS* possible to separate the β -process into two overlapping relaxation transitions: cooperative motion of alkali cations in the glassy network γ_{R+} and a mixed alkali peak β_{mix} . This overlay was fitted by means of a double power law function of the form (Roling and Ingram (1998a)):

$$Q^{-1}(T) = Q_b^{-1} + \sum_{j=1}^n \frac{Q_{0,j}^{-1}(\omega\tau_j)^{n_j}}{1 + (\omega\tau_j)^{m_j+n_j}} \quad (28)$$

³ The relaxation behaviour in multi-component glasses is rather complex due to the superposition of several relaxation processes.

⁴ Here it is to be counted for a superposition of several processes, i.e. a broad β transition superimposed by a β' process.




Fig. 11. Asymptotic behavior for high temperatures and low frequencies in the representation of the complex modulus M^* in the Gaussian-plane (top) for the investigated volcanic glasses and (bottom) for starting glass (1: Jenit I, 3: JenitII) and ceramic (2: Jenit I, 4: JenitII) of machinable glass ceramic (Wagner et al. (2001)), 5: $16Na_2O - 10CaO - 74SiO_2$, 6: $16K_2O - 10CaO - 74SiO_2$, 7: cordierite-glass which shows surface crystallization effects (Wagner (2004)) in comparison to the 8: *JAL*-obsidian.

with the background Q_b^{-1} , a constant $Q_{0,j}^{-1}$ and the relaxation times

$$\tau_j = \tau_{0,j} \exp\left(\frac{E_{a,j}}{RT}\right). \quad (29)$$




Fig. 12. Loss modulus M'' as a function of (top) temperature and (bottom) reduced temperature $T - T_m$ in the temperature range $T < T_g$.

The volcanic glasses can be likewise divided according to the α process into different groups (Fig. 13). By scaling the temperature axes with the temperature of maxima T_α a master curve for the large group of melts (*MIL*, *VUL*, *YEL*, *JAL* and *ATS*) can be constructed, which is an indication for similar rheologic characteristics of these obsidians. Deviations from the general trend show the samples *DYR* and *LIP*. The *DYR*-obsidian has with $\delta_\alpha = 84^\circ\text{C}$ a substantially smaller half width and steeper slopes of the loss modulus flanks of the α -maximum:

$$m_i = \frac{d \log M''}{d(10000/T)}, \quad i = \begin{cases} 1 & \text{for } \log(\omega\tau) < 1 \\ 2 & \text{for } \log(\omega\tau) > 1 \end{cases} \quad (30)$$

with $m_1 = 2.04$, $m_2 = -1.56$ than the other glasses (general trend $\delta_\alpha \approx 140^\circ\text{C}$ and $1.1 < m_1 < 1.5$, $-1 < m_2 < -0.6$). *LIP* on the other hand exhibits clearly larger $\delta_\alpha = 154^\circ\text{C}$ values and a smaller slopes $m_1 = 1.04$, $m_2 = -0.66$. This obsidian has the smallest relaxation strength $s_\alpha = 12\text{GPa}$ and $s_D = 27\text{GPa}$ ($s_\alpha^{\text{average}} = 20.4\text{GPa}$ and $s_D^{\text{average}} = 35.5\text{GPa}$). The *RAB*-obsidian is featured




Fig. 13. (Top) storage modulus M' normalized with the Young's modulus at the glass transition temperature M_{VE} and (bottom) loss modulus M'' as a function of $T - T_m$ in the temperature range $T > T_g$. In the figures (b)-(d) the deviations from the curve are represented, which the obsidians *MIL*, *VUL*, (*YEL*), *JAL*, (*QUI*) and *ATS* follow and which is clarified with the grey line.

Table 5

Temperature and magnitude of the internal friction maxima for temperature $T < T_g$ without background subtraction.

	AI	$T_{m,\gamma_{R^+}}$ [°C]	$Q_{m,\gamma_{R^+}}^{-1}$	$T_{m,\beta_{mix}}$ [°C]	$Q_{m,\beta_{mix}}^{-1}$	T_{min} [°C]	Q_{min}^{-1}	$Q_{Plateau}^{-1}$
RAB	1,06	54	0,010	182	0,0070	342	0,005	—
JAL	0,90	63	0,009	179	0,0090	342	0,006	—
LIP	1,08	91	0,009	182	0,0070	293	0,004	—
YEL	1,07	106	0,011	264	0,0100	395	0,005	—
ATS	1,29	152	0,007	314	0,0070	389	0,005	—
MIL	1,36	72	0,012	142	0,0110	(317)	—	0,009
VUL	1,09	121	0,009	280	0,0097	(355)	—	0,0098
QUI	1,55	195	0,010	431	0,0080	(500)	—	0,0076
DYR	1,46	—	—	105	0,0094	(431)	—	0,004

by a pronounced shoulder⁵, which suggests a strong β_{R^+} relaxation process. In the α process of the *QUI*-glass an anomaly arises within the glass transition range. Here, it concerns an physical ageing effect during the measurement. Particularly, this obsidian exhibits few large ($d \approx 0.5mm$) crystals (per sample approx. 3-4) causing the sample to crack under the experimental strain of 10^{-4} .

The mechanical spectra could be parameterisiertparameterized with *GMM* (17) with the assumption of three relaxation processes ($j = \alpha, \beta, \beta'$):

$$M^*(\omega, \tau) = \sum_{j=1}^3 \frac{M_{0,j} M_{1,j} (i\omega\tau_j)_j^\alpha}{M_{1,j} (1 + (i\omega\tau_j)^{\alpha_j - \beta_j}) + M_0 (i\omega\tau_j)_j^\alpha} \quad (31)$$

6 Discussion

Internal friction spectra are shown in Fig. 5. Different relaxation processes can contribute to the relaxation behaviour (3): the dynamical glass transition above the glass transition temperature T_g the so called primary α -relaxation (viscoelastic process) and several secondary relaxation processes below T_g : co-operative motion of alkali ions in the glassy network γ_{R^+} , mixed alkali peak

⁵ The shoulder-effect always showed up with all internal friction measurements accomplished at the obsidian in the same temperature range.

Table 6

Parameters of the relaxation processes from GMM-fitting (from top to bottom : α , β' und β).

Obsidian	$-\log(\tau[s])$	E_a	β	M_0	X	M_{VE}
α		[kJ/mol]		[GPa]		[GPa]
YEL	17,02	409	0,60	26	0,45	59
VUL	17,87	384	0,53	33	0,48	68
MIL	19,68	450	0,56	60	1,00	61
LIP	16,13	344	0,56	17	0,44	39
DYR	24,74	554	0,65	2	0,04	68
ATS	17,80	399	0,53	49	0,66	74
QUI	15,74	350	0,54	22	0,29	77
ISL	19,49	442	0,70	37	0,69	53
JAL	18,60	382	0,56	45	0,78	58
β'						
YEL	9,17	171	0,36	1,26	0,30	4,14
VUL	9,28	150	0,29	1,45	0,45	3,23
MIL	8,61	154	0,36	2,50	1,00	2,51
LIP	12,39	197	0,18	3,40	0,34	9,96
DYR	13,92	245	0,23	5,11	0,64	7,95
ATS	10,48	173	0,38	1,07	0,48	2,22
QUI	10,80	186	0,31	0,66	0,20	3,29
RAB	16,82	306	0,37	40,00	2,08	19,27
JAL	11,60	190	0,31	1,40	0,39	3,58
β						
YEL	4,67	46	0,27	1,17	0,16	7,35
VUL	3,49	41	0,31	0,84	0,15	5,48
MIL	4,26	46	0,26	0,96	0,14	6,95
LIP	5,30	54	0,31	1,38	0,12	11,11
DYR	4,02	35	0,30	0,88	0,14	6,13
ATS	4,80	49	0,26	1,02	0,20	4,99
QUI	4,70	54	0,31	0,88	0,16	5,37
RAB	4,59	65	0,17	0,86	0,08	11,46
JAL	2,89	23	0,31	1,05	0,24	4,34




Fig. 14. (Top) storage - M' and loss modulus M'' as a function of temperature of the *MIL* obsidian with GMM-fit according to equation (31). (bottom) Residuum of the fit.

β_{mix} , so-called water peak β_{H_2O} ⁶, cooperative motion of alkaline earth ions in the vicinity of the thermal glass transition range $\beta_{R^{2+}}$ (Röling and Ingram (1998b), Röling (2001), Martiny (2001)) and a so-called Johari-Goldstein relaxation β_{JG} (Angell et al. (2000), Donth (2001), Nemilov and Johari (2003)). It is impossible to distinguish the specific relaxation processes in every case because of the restricted frequency and temperature range. For this reason three relaxation processes are assumed: β - superposition of the $\gamma_{R^{2+}}$, β_{mix} and β_{H_2O} process, β' - superposition of the $\beta_{R^{2+}}$, β_{JG} and the thermal glass transition as well as the viscoelastic α -transition.

Further it is assumed, that the unrelaxed modulus M_∞ is a very weak function of temperature. This is true in the case of volcanic glasses (Fig. 8 and Tab. 4).

Since volcanic glasses are natural materials, these are heterogeneous up to certain degrees. The natural glasses have a smaller signal-to-noise ratio caused by these heterogeneities opposite to synthetic glasses. Thus, sensitivity is limited. Relaxation processes can only seriously be observed in relaxation behaviour if they are strongly enough. The different assumed influences and their effect

⁶ This peak would be present according to Phalippou et al. (1980) and Stevels (1985) only in the systems where non-bridging oxygens, OH^- groups and hydrogen bonds are present at the same time.




Fig. 15. (a) and (b) storage - M' and loss modulus M'' as a function of temperature with GMM -fit. (c) Complex Young's-modulus M^* with GMM -fit represented in the Gaussian-plane (selection of three obsidians MIL , ATS , JAL).

on different relaxation processes are summarized in Tab. 7. On one hand it is shown, that there are processes, which are sensitive for different influences, c.f. β' . On the other hand, the α process is caused by the chemical composition and water content. In addition, effects arise due to degassing and vesiculation. Here, however, it showed up clearly that even during very strong vesiculation of the *LIP*-sample, dynamics of the glass transition is detectable. In this specific case, temperature dependence of α -relaxation time can only be modelled in first approximation by an Arrhenian-equation due to water release.

Table 7

Assumed influences on the mechanical relaxation behaviour of the volcanic glasses:
X - significant, (X) - weak, (-) - uncertain

influence	β -process	β' -process	α -process	M_{RT}
chemical composition	X	(-)	X	(X)
water content	(X)	(-)	X	(X)
bubble content (degassing)	(X)	(X)	(X)	(X)
crystals	(X)	(X)	(-)	(-)
temperature history	X	(X)	(-)	(-)

6.1 Relaxation behaviour below T_g

The influences of the chemical composition and the water content on the relaxation processes below T_g were examined in detail in several mechanical relaxation studies (Q^{-1} -spectroscopy) of synthetic glasses. It was shown that different mixing cation effects exist, which in addition depend on the water content and polymerization degree of glasses (c.t. Day (1974a), Phalippou et al. (1980) and Stevels (1985), Martiny (2001)). The examined volcanic glasses exhibit the following ions: Na^+ , K^+ , Ca^{2+} , Mg^{2+} , Fe^{2+} and water in different speciation (Gaber (1999), Doremus (2000), Behrens (2001), Doremus (2002)), which can contribute to the mechanical relaxation behaviour. Since the place-exchange processes can be observed both in the internal friction spectrum $Q^{-1}(T)$ or in equivalence in the loss modulus $M''(T)$ as maxima and in the storage modulus $M'(T)$ as a step. The following views are accomplished on the basis of internal friction.

The *JAL*-obsidian is peralkalin, i.e. it exist on *NBO* bounded alkali ions R^+ ($\approx 1\text{mol}\%$), which are mobile in the glass network. The peak of γ_{Na^+} at a measuring frequency of 1Hz is to be expected below RT . Investigations of internal friction of binary $R_2O\text{-}SiO_2$ -glasses with $R^+ = Rb^+, K^+, Na^+, Li^+$ show (Zdaniewski et al. (1976)) that the intensity $Q_{m,\gamma}^{-1}$ and the temperature

$T_{\gamma_{R^+}}$ of this maximum depends on the field strength $F = \frac{z}{a^2}$ of appropriate cations with the valence z and the Van der Waals radius a . It becomes clear that the γ_{R^+} process is coupled with the β_{H_2O} process, which exhibits a maximum at approximately $200^\circ C$.

If one further regards ternary glasses with two different kinds of alkali ions, then one observes the occurrence of a further maximum: the mixed alkali peak β_{mix} within the range of the water maximum. At a temperature of $\approx 320^\circ C$ additional relaxation processes arise: a β'_{R^+} -process in direct connection to the mobility of alkaline-earth ions, the mobility of oxygen-ions with an activation energy of $\approx 200 kJ/mol$ and the Johari-Goldstein relaxation (Röling (2001), Nemilov and Johari (2003), Wagner (2004)). A substantial conclusion from the investigations of Martiny (2001) on ternary alkali and alkaline-earth silicate glasses is the fact that in systems with two kinds of cation, while one is substantially faster than the other one, the cation radius relationship affects the activation energy of the slower ions. The more similar the ion radii are, the smaller is the activation energy.

By the component Al_2O_3 the location and intensity of the maxima change drastically. For the ternary sodium aluminosilicate glass examined by Day and Rindone (1962a) as well as Day and Rindone (1962b) the γ_{Na^+} as well as β_{H_2O} peak decreases with rising Al_2O_3 -content, whereby at the ratio $Al_2O_3/Na_2O = 1$ the γ_{Na^+} process is maximal and the β_{H_2O} process cannot be observed anymore.

Measurements of mixed alkali aluminosilicate glasses with $Al_2O_3/R_2O = 1$ of Sakamura and Yasui (1985) as well as Sakamura and Yasui (1989) point out, that as in the case of the ternary mix alkali glasses, these systems exhibit a mixed alkali maximum β_{mix} at $\approx 100^\circ C$. At a ratio $Na_2O/K_2O = 1$ arise a very strong maximum, which is formed by the superposition of the γ_{R^+} and β_{mix} processes.

Sakamura and Yasui (1985) perform additional measurements of glasses, in which the Al_2O_3 -content is varied at the expense of the SiO_2 -content, at constant $Na_2O/K_2O = 19$. By the presence of Na^+ and K^+ -cations is formed again apart from the γ_{R^+} a mix alkali maximum β_{mix} . With rising Al_2O_3 the intensity of the γ_{R^+} peak increases, while those of the β_{mix} decreases. As in the case of ternary sodium aluminosilicate glasses from the investigation of Day and Rindone (1962a) as well as Day and Rindone (1962b) acquiring the intensity of the γ_{R^+} maximum and of β_{mix} minimum at $Al_2O_3/Alk = 1$.

From the reasons specified above, the following consequences resulted in the mechanical relaxation behaviour below T_g of the examined natural glasses:

- The water maximum is suppressed strongly by the Al_2O_3 -content.
- The ratio $Al_2O_3/Alk \approx 1$ leads to the formation of an intensive γ_{R^+} peak.

- The presence of two different alkali ions K^+ and Na^+ leads to the formation of a mixed alkali peak β_{mix} with $T_{\beta_{mix}} \approx 140^\circ C$.
- The γ_{R+} process is superimposed by the β_{mix} process with the result of a relatively high internal friction $Q^{-1} \approx 0.7$ within the temperature range $RT - 300^\circ C$.
- By the presence of divalent cations a further relaxation process $\beta_{R^{2+}}$ arises in the vicinity of the glass transition range.

The compilation of data to the internal friction of volcanic glasses confirms the above assumptions (Fig. 12). In the case of the samples *LIP*, *RAB*, *YEL* and *JAL* it is suggested that it concerns a superposition of two processes. *ATS*, *MIL*, *QUI* and *VUL* exhibit a pronounced plateau. An exception is the *DYR* sample. Here it seems that the γ_{R+} peak is below RT . It is suggested a further peak occurs at $\approx 100^\circ C$. In Tab. 5 the results are summarized. As mentioned, the decay of the storage modulus with temperature below T_g is likewise dependent on the chemical composition. In the special case of the obsidians it can be assumed that M_{RT} depends secondarily on the chemical composition, due to ion mobility in the glassy network, but is determined essentially by water content. However, practically no investigations of the influence of water content on elastic properties of synthetic and natural glasses exist in contrast to internal friction measurements. The occurrence of the *LIP* sample is interesting in this context with the smallest Young's modulus of $M_{RT} = 61 GPa$. It is possible to calculate M_{RT} with the model of Priven (2001) (SciGlass information system) in accordance with the measured data.

6.2 Primary α -Process

a) Chemical composition and water content

The comparison of the Young's modulus at RT (M_{RT}) or T_g (M_{VE}) and loss modulus at the α peak ($M''_{\alpha,m}$) is represented in Fig. 16. The drawn in lines refer to the deviation from simple Maxwell behavior ($x = 1$): $M''_m = x M'_{VE,RT}/2$. The linear regression results are $x_{RT} = 0,55 \pm 0,02$ and $x_{VE} = 0,58 \pm 0,02$. The flat curve of the *LIP* sample is to be explained by strong vesiculation. A change of the sample caused by degassing and formation of bubbles leads to a change in the mechanical behavior, whereby the viscoelastic response is dominated by the mechanical glass transition. The parameter x is a measure relatively independent of the chemical composition, with which deviations can be interpreted as physically induced processes in contrast to the influence of the chemical composition or the water content, which causes a change of the properties of the glass. The *GMM*-fitting supplies the unrelaxed modulus at the mechanical glass transition $M_{VE}|_{T_{VE}}$ which is $\approx 2 GPa$ lower than the elastic modulus at T_g . In the used model the β' process represents an overlay of a




Fig. 16. Comparison of the Young's modulus at RT M_{RT} or T_g M_{VE} and loss modulus at the α peak $M''_{\alpha,m}$ of the obsidians and several sythetic glasses (Wagner (2004)).

secondary⁷ process and the thermal glass transition caused on experimental conditions. This secondary effect is observed likewise in organic glasses with dielectric spectroscopy, and gave reason to controversial discussions of the existence of the Johari-Goldstein-process (Nemilov and Johari (2003), Schneider (2000), Angell et al. (2000)).

The occurrence of the α -process is defined by the chemical composition and the water content (Dingwell (1995), Hess and Dingwell (1996), Stevenson et al. (1998), Giordano and Dingwell (2003)). In Fig. 17 one can notice different trends. The temperature T_α decreases with increasing NBO/T and the amount of the absolute excess oxide value ($|EO|$), i.e. with increasing depolymerization. Likewise the glass transition temperature as well as the temperature of water release follow this trend. The mechanical glass transition of the *MIL* obsidian with the smallest $NBO/T = 2^{-4}$ and a $|EO|$ close to zero $\approx 0,17$ occurs at the highest temperature. The smallest maximum temperature $T_{\alpha,\alpha}$ has the peralkaline *JAl* obsidian with $NBO/T = 0,023$ and $|EO| = 1,05$. Even the *LIP* obsidian follows this trend. The occurrence of the mechanical glass transition (thus) is dominated by the chemical composition (see also the investigations of partially crystalline glasses by

⁷ In the case of the obsidians the mobility of divalent cations and the Johari-Goldstein relaxation.




Fig. 17. Temperature of the α -peak $T_{m,\alpha}$ as a function of the chemical composition and water content of the investigated volcanic glasses. The Hess et al. (1996) calculation scheme defined by the solid curve for viscosities ($10^8 \dots 10^{11}$ Pas) closely fits the experimental data for the calc- and per-alkaline compositions. The dashed lines are an aid to the eye, and do not conform to any specific mathematical expression.

Mueller et al. (2003)). This conclusion confirms measurements of Cordierite-glass (Wagner et al. (2001), Wagner (2004)). Impurities (crystals, bubbles, cracks) influence the width of the maxima and relaxation strength. The activation energy and prefactor of the Arrhenius-equation for the temperature dependence of the relaxation time $\tau_\alpha(T)$ can be determined from the *GMM*-fit and compared with the results of the measurements of other authors (viscosity measurements, torsion pendulum measurements) (Fig. ??). The activation energy of the α relaxation time or viscosity at T_g is essentially a function of chemical composition and water content. A model that considers both influences sufficient for synthetic or natural silicate melts does not exist. The model of Priven (2001) represents the most progressive at present, in the connection between structure and properties (volatile excluded). For the description of volcanic glass, the empirical model of Hess (1996) is most effective. This model was developed for water bearing leucogranitic melts but was also used to calculate the viscosity of metaluminous and peraluminous obsidian (Stevenson et al. (1998)).

Fig. 19 shows the range of variation of the distribution of relaxation times on the basis of the β_α parameter and activation energy E_a at the mechanical




Fig. 18. Activation energy of viscous flow $E_{a,\alpha}$ at the glass transition temperature T_g as a function of water content for the natural volcanic glasses of this work and the natural and remelted obsidians of Stevenson et al. (1998).




Fig. 19. Distribution parameter β_a ($\alpha_\alpha = 1$) as a function of the apparent activation energy for viscous flow $E_{a,\alpha}$ at T_g of the synthetic and volcanic melts of this work in comparison to literature data. The β_α parameter was calculated from β_{KWW} with an empirical expression.

glass transition temperature for structurally different silicate melts. The β_α -parameter for the obsidians range between 0.5 and 0.6 with two exceptions *DYR* and *RAB*. The *RAB* glass has a very strong β' relaxation process so that the GMM-fitting leads to a narrower α -process. In comparison, the *DYR* glass shows anomalous behaviour in all examined parameters.

The average value of all supercooled melts is $\bar{\beta}_\alpha = 0,52$. Deviations can be observed for two volcanic glasses as well as the HPG8-melts from the work of Bagdassarov et al. (1993).




Fig. 20. Distribution parameter β_a ($\alpha_\alpha = 1$) as a function of the apparent activation energy for viscous flow $E_{a,\alpha}$ at T_g of the volcanic melts. (inset) Distribution parameter β_a ($\alpha_\alpha = 1$) as a function of the cooling rate $|q|$ of a *LIP*-obsidian (Gottsmann and Dingwell (2001a)).

Under the condition that the distribution of relaxation times is nearly constant it should be possible to predict the occurrence and the width of the mechanical glass transition from viscosity data (see Wagner et al. (2004)).

The variation of the distribution parameter is primarily caused by phase separation and crystallization processes as well as degassing and vesiculation. The temperature prehistory has little influence. The *DSC* investigation of Gottsmann and Dingwell (2001a) shows a negative correlation of the distribution parameter and the cooling rate. The variation of the β parameter is

within the standard deviation of the 45 samples.

In summary the following points result:

- The mechanical α relaxation (mechanical or viscoelastic glass transition) overlays a secondary β relaxation process.
- The occurrence of the transition is defined by the temperature dependence of viscosity.
- The width δ of the transition depends on the fragility and the distribution of relaxation times.
- The distribution of relaxation times in the investigated temperature and frequency range is almost constant in comparison to the fragility index for inorganic glasses (see Wagner (2004)).
- The presence of crystals (in particular due to surface crystallisation) and bubbles $> 1\text{-}2\text{Vol.}\%$ changes the dynamics of the transition and therefore the relaxation time distribution.
- Fragility is defined by the chemical composition and the presence of volatiles.
- Phase separation and degassing processes change strongly the dynamics and thermics ⁸ of the transition and lead to therorheologic complex behavior.

7 Conclusion

Obsian can considered as a thermorheological simple melt with a low fragility index $m \approx 20$. Variations in the ratio NBO/T determine the polymerization degree of the melts and thus the rheologic properties. A crucial factor which determines the mechanical relaxation behaviour in the thermal and dynamic glass transition range above T_g , is the relatively high water content. In the vitreous state the influence of water on the dynamical processes plays a minor role, since the volcanic glasses are almost completely polymerized ($NBO/T \leq 0.4$). For clarifying this fact it requires more exact methods.

Three section can be distinguish in the mechanical spectra (a) $T < T_g$, (b) $T \approx T_g$ und (c) $T > T_g$, with the following characteristics:

- (i) The Young's modulus $M_{RT} = (70 \pm 10)\text{GPa}$ is nearly constant. There is a positive correlation with the water content and a weak negative correlation with the cooling rate (Wagner (2004)).

⁸ Due to the nomenclature of Donth (1981) and Donth (2001).

- (ii) Below T_g the mechanical relaxation behaviour is characterized by the cooperative motion of univalent cations (alkali-peak γ_{R+} , mixed alkali-peak β_{mix}) and the polymerisation degree. Impurities (bubbles, crystals, cracks, trace elements) in the natural glasses decrease the signal to noise ratio.
- (iii) All glasses exhibit a very weak, and in one case, an anomalous negative decay of the Young's modulus with temperature like silica glasses. In addition, it is possible to observe steps in the curve of Young's modulus ($\Delta M' < 5\text{GPa}$) which correspond with the γ_{R+} or β_{mix} peak in internal friction.
- (iv) In the vicinity of the glass transition temperature there is a superposition of the α and a β' process (cooperative motion of divalent cations: alkali earth peak $\beta_{R^{2+}}$ and the Johari-Goldstein relaxation β_{JG}) as well as the thermal glass transition defined by the experimental conditions. The thermal glass transition is reflected clearly in the loss modulus and in the storage modulus at least less than 1%.
- (v) The occurrence of the mechanical or dynamic glass transition at a constant frequency as function of the temperature is specified by the temperature dependence of the structural α relaxation time τ_α .
- (vi) The temperature dependence of the structural α relaxations time is determined by the polymerization degree with water as a quasi controlling parameter and can be computed by means of an empirical equation according to Hess (1996) or Hess and Dingwell (1996) for the per- and met-aluminous rhyolitic melts. The model of Priven (1998) as well as Giordano (2002) for the computation of the temperature dependence of the viscosity of multicomponent melts cannot be used for the computation of the α relaxation time. For strong melts and melts with high water content the glass transformation temperature and the activation energy of viscous flow are overestimated.
- (vii) Degassing processes in connection with bubble growth as well as other impurities (crystals) lead to macroscopic (cracks) and structural (polymerization degrees) changes, which cause instabilities of the samples.
- (viii) The dynamics of the mechanical glass transition is a universal process with very weak variation of the relaxation time distribution almost independent of chemical composition and water content (0,027... 0.44)Masse% of the examined natural melts.

The obsidians represents an interesting material class, which has many useful properties (concerning the methods of the mechanical spectroscopy)⁹, like thermalrheologically simple behavior, small fragility index and a high glass formation tendency, small variation of the Young's modulus in a wide temperature range, high polymerization degree, long-term resistance.

⁹ "Impurities" have to keep in mind, which are able to effect the actual glass characteristics, like in the case of the *LIP*-sample

References

- Adam, G., Gibbs, J. H., 1965. On the temperature dependence of cooperative relaxation properties in glass-forming liquids. *Journal of Chemical Physics* 43, 139–146.
- Angell, C. A., 1988. Structural instability and relaxation in glassy phases. *Journal of Non-Crystalline Solids* 102, 205.
- Angell, C. A., Ngai, K. L., McKenna, G. B., McMillan, P. F., Martin, S. W., 2000. Relaxation in glassforming liquids and amorphous solids. *Journal of Applied Physics* 88 (6), 3113–3157.
URL <http://link.aip.org/link/?JAP/88/3113/1>
- Araki, T., Tanaka, H., 2001. Three-dimensional numerical simulations of viscoelastic phase separation: Morphological characteristics. *Macromolecules* 34, 1953–196.
- Askarpour, V., Manghnani, M., Richet, P., 1993. Elastic properties of diopside, anorthite, and grossular glasses and liquids: a brillouin scattering study up to 1400 K. *Journal of Geophysical Research* 98 (B10), 17683–17689.
- Avramov, I., Milchev, A., 1988. Effect of disorder on diffusion and viscosity in condensed systems. *Journal of Non-Crystalline Solids* 104, 253–260.
- Bagdassarov, N., Dorfman, A., 1997. Viscoelastic behavior of partially molten granites. *Tectonophysics* 290, 27–45.
- Bagdassarov, N. S., 1999. Viscoelastic behaviour of mica-based glass-ceramic aggregate. *Physics and Chemistry of Minerals* 26, 513–520.
- Bagdassarov, N. S., Dingwell, D. B., 1993. Frequency dependent rheology of vesicular rhyolite. *Journal of Geophysical Research* 98 (B4), 6477–6487.
- Bagdassarov, N. S., Dingwell, D. B., Webb, S. L., 1993. Effect of boron, phosphorus and fluorine on shear stress relaxation in haplogranite melts. *European Journal of Mineralogy* 5, 409–425.
- Bagdassarov, N. S., Dingwell, D. B., Webb, S. L., 1994. Viscoelasticity of crystal- and bubble-bearing rhyolite melts. *Physics of the Earth and Planetary Interiors* 83, 83–99.
- Bagdassarov, N. S., Laporte, D., Thomson, A. B., 2000. *Physics and Chemistry of Partially Molten Rocks*. Vol. 11 of *Petrology and Structural Geology*. Kluwer, Ch. Anelastic and viscoelastic behaviour of partially molten rocks and lavas, pp. 29–65.
- Bagdassarov, N. S., Maumus, J., Poe, B., Slutskiy, A. B., Bulatov, V. K., 2001. Pressure dependence of T_g in Silicate Glasses from Electrical Impedance Measurements. *Geochimica et Cosmochimica Acta* submitted.
- Baker, D. R., 1996. Granitic melt viscosity: Empirical and configurational entropy models for their calculation. *American Mineralogist* 81, 126–134.
- Bark-Zollmann, S., 1994. Theoretische und experimentelle Untersuchungen von Relaxationserscheinungen in Glaesern. Friedrich-Schiller-Universitaet Jena, dissertation.
- Bark-Zollmann, S., Heide, K., Kluge, G., 1997a. Biegependelmessplatz zur Untersuchung der inneren Reibung von Glaesern und glasartigen Festkoerpern.

- Tagungsband 71. Glastechnische Tagung in Bayreuth.
- Bark-Zollmann, S., Heide, K., Kluge, G., 1998a. Mechanisches Relaxationsverhalten von Glaesern, Untersuchungen mit der Biegependelmethode. Tagungsband 72. Glastechnische Tagung in Muenster, 134–137.
- Bark-Zollmann, S., Kluge, G., Heide, K., 1997b. Untersuchung der inneren Reibung von Obsidianen und Glaskeramiken. Beihefte European Journal of Mineralogy 9 (1), 39.
- Bark-Zollmann, S., Kluge, G., Heide, K., 1998b. Experimental investigations of the internal friction of optical and technical glasses with a flexure pendulum equipment. Glass Science and Technology 71 (3), 57–66.
- Bark-Zollmann, S., Kluge, G., Heide, K., 1998c. Mechanical relaxation behaviour of glasses, glass-ceramics and obsidians. Glastechnische Berichte-Glass Science and Technology (Proc. Vlth Inter. Otto-Schott-Kolloquium) 71C (268-271).
- Bartenev, G. M., 1983. Relaxationserscheinungen in anorganischen Glaesern. Wissenschaftliche Zeitschrift der Friedrich Schiller Universitaet Jena, Math. Nat. Reihe 32, 385–405, uEbersetzung aus dem Russischen.
- Bartenev, G. M., Lomovskoi, V. A., 1996. Relaxation properties of alkali silicate glasses from mechanical measurements. Inorg. Mater.- Engl. Tr. 32, 541–551.
- Behrens, H., 2001. Solubilty and diffusivity of volatiles in silicic melts. Universitaet Hannover, habilitation.
- Blake, S., Bruno, B. C., 2000. Modelling the emplacement of compound lava flows. Earth and Planetary Science Letters 184, 181–197.
- Boehmer, R., Angell, C. A., 1992. Correlations of the nonexponentiality and state dependence of mechanical relaxations with bond connectivity in geas-se supercooled liquids. Phys. Rev. B 45, 10091–10094.
- Bottinga, Y., Weill, D. F., 1972. The viscosities of magmatic silicate liquids: a model for calculation. Journal of Science 272, 438–475.
- Brueckner, R., 1970. Properties and structure of vitreous silica. I. Journal of non-Crystalline Solids 5, 123–175.
- Brueckner, R., 1971. Properties and structure of vitreous silica. II. Journal of non-Crystalline Solids 5, 177–216.
- Buchenau, U., 2003a. The breakdown of the shear modulus at the glass transition. Condensed Matter, abstract cond-mat/0202036.
- Buchenau, U., 2003b. Energy landscape - a key concept in the dynamics of liquids and glasses. J. Phys.: Condens. Matter 15, S955–S966.
- Buisson, C., Merle, O., 2002. Experiments on internal strain in lava dome cross sections. Bulletin Volcanology 64, 363–371.
- Castro, J., Cashman, K. V., 1999. Constraints on rheology of obsidian lavas based on mesoscopic folds. Journal of Structural Geology 21, 807–819.
- Castro, J., Manga, M., Cashman, K., 2002. Dynamics of obsidian fows inferred from microstructures: insights from microlite preferred orientations. Earth and Planetary Science Letters 199, 211–226.
- Cañón-Tapia, E., Castrob, J., 2004. AMS measurements on obsidian from the

- Inyo Domes, CA: a comparison of magnetic and mineral preferred orientation fabrics. *Journal of Volcanology and Geothermal Research* 134, 169–182.
- Cañón-Tapia, E., Chávez-Álvarez, M. J., 2004. Rotation of uniaxial ellipsoidal particles during simple shear revisited: the influence of elongation ratio, initial distribution of a multiparticle system and amount of shear in the acquisition of a stable orientation. *Journal of Structural Geology* 26, 2073–2087.
- Coenen, M., 1961. Mechanische Relaxation von Silikatglasern Eutektischer Zusammensetzung. *Zeitschrift fuer Elektrochemie* 65 (10), 903–908.
- Cole, K., Cole, R., 1941. Dispersion and Absorption in Dielectrics. *Journal of Chemical Physics* 9 (4/41), 341–351.
- Davidson, D., Cole, R., 1951. Dielectric relaxation in glycerol, propylene glycol, and n-propanol. *Journal of Chemical Physics* 19, 1484–1490.
- Day, D. E., 1974a. The internal friction of glasses containing water. *Wissenschaftliche Zeitschrift der Friedrich Schiller Universitaet Jena, Math. Nat. Reihe* 23 (2), 293–305.
- Day, D. E., 1974b. Internal friction of glasses with low water contents. *Journal of the American Ceramic Society* 57 (12), 530–533.
- Day, D. E., Rindone, G. E., 1962a. Properties of soda aluminosilicate glasses: I, refractive index, density, molar refractivity, and infrared absorption spectra. *Journal of the American Ceramic Society* 45 (10), 489–496.
- Day, D. E., Rindone, G. E., 1962b. Properties of soda aluminosilicate glasses: II, internal friction. *Journal of the American Ceramic Society* 45 (10), 496–504.
- Day, D. E., Steinkam, W. E., 1969. Mechanical damping spectrum for mixed-alkali $R_2O-Al_2O_3-6SiO_2$ glasses. *Journal of the American Ceramic Society* 52 (11), 571.
- Day, D. E., Stevels, J. M., 1972. Internal friction of $NaPO_3$ glasses containing water. *Journal of Non Crystalline Solids* 11, 459–470.
- Day, D. E., Stevels, J. M., 1974. Effect of dissolved water on internal friction of glass. *Journal of Non Crystalline Solids* 14, 165–177.
- Debenedetti, P. G., 1996. *Metastable Liquids: Concepts and Principles* (Physical Chemistry: Science and Engineering). Princeton University Press.
- Debenedetti, P. G., Stillinger, F. H., 2001. Supercooled liquids and the glass transition. *Nature* 410 (8), 259–267.
- Debye, P., 1941. *Polar Molecules*. Dover Publications, Inc.
- Dingwell, D., 1996. Volcanic dilemma: Flow or blow? *Science* 273, 1054–1055.
- Dingwell, D. B., 1995. Relaxation in silicate melts: some applications. In: Stebbins, J. F., McMillan, P., Dingwell, D. (Eds.), *Structure, Dynamics and Properties Of Silicate Melts*. Vol. 32 of *Reviews in Mineralogy*. Mineralogical Society of America, pp. 21–63.
- Doliwa, B., 2002. The Dynamics of a Small Model Glass Former as Viewed from its Potential Energy Landscape. Johannes Gutenberg Universit at in Mainz, dissertation.
- Donth, E., 2001. The glass transition: relaxation dynamics in liquids and dis-

- ordered materials. Vol. 48 of Springer series in materials science. Springer.
- Donth, E.-J., 1981. Glasuebergang. Vol. 272 of Wissenschaftliche Taschenbuecher. Akademie-Verlag.
- Donth, E. J., 1992. Relaxation and Thermodynamics in Polymeres. Akademie Verlag.
- Doremus, R. H., 2000. Water speciation in silicate glasses and melts: Langmuir limited site model. *American Mineralogist* 85, 1674–1680.
- Doremus, R. H., 2002. Diffusion of Reaktive Molecules in Solids und Melts. John Wiley & Sons, Inc.
- Dragoni, M., Tallarico, A., 1994. The effect of crystallization on the rheology and dynamics of lava flows. *Journal of Volcanology and Geothermal Research* 59, 241–252.
- Dragoni, M., Tallarico, A., 1996. A model for the opening of ephemeral vents in a stationary lava flow. *Journal of Volcanology and Geothermal Research* 74, 39–47.
- Duan, R. G., Roebben, G., Van der Biest, O., 2003. Glass microstructure evaluations using high temperature mechanical spectroscopy measurements. *Journal of Non-Crystalline solids* 316 (1), 138–145.
- Duffrene, L., 1998. Generalized maxwell model for the shear viscoelastic behavior of a soda-lime-silica glass: a mechanical relaxation using static and dynamic experiments. *Proceedings of International Congress on Glass, 18th, San Francisco, CA, United States, July 5-10*, 2561–2566.
- Duffrene, L., Gy, R., 1997. Viscoelastic constants of a soda-lime-silica glass. *Journal of Non-Crystalline Solids* 211 (1,2), 30–38.
- Duffrene, L., Gy, R., Burlet, H., Piques, R., 1997a. Multiaxial linear viscoelastic behavior of a soda-lime-silica glass based on a generalized maxwell model. *Journal of Rheology* 41 (5), 1021–1038.
- Duffrene, L., Gy, R., Burlet, H., Piques, R., 1997b. Viscoelastic behavior of a soda-lime-silica glass: inadequacy of the kww function. *Journal of Non-Crystalline Solids* 215 (2,3), 208–217.
- Duffrene, L., Gy, R., Burlet, H., Piques, R., Faivre, A., Sekkat, A., Perez, J., 1997c. Generalized Maxwell model for the viscoelastic behavior of a soda-lime-silica glass under low frequency shear loading. *Rheologica Acta* 36, 173–186.
- Ericson, J. E., Makishima, A., MacKenzie, J. D., Berger, R., 1975. Chemical and physical properties of obsidian: a naturally occuring glass. *Journal of Non-Crystalline Solids* 17, 129–142.
- Feltz, A., 1983. Amorphe und glasartige anorganische Festkoerper. Akademie Verlag Berlin.
- Fink, J. H., 1990. Lava flows and domes, emplacement mechanism and hazard implication.
- Fitzgerald, J. V., 1951a. Anelasticity of Glass: I, Introduction. *Journal of the American Ceramic Society* 34, 314–319.
- Fitzgerald, J. V., 1951b. Anelasticity of Glass: II, Internal Friction and Sodium Ion Diffusion in Tank Plate Glass, A Typical Soda-Lime-Silica Glass. *Jour-*

- nal of the American Ceramic Society 34, 339–342.
- Frischat, G. H., 1975. Ionic Diffusion in Oxide Glasses. No. 3/4 in Diffusion and Defect Monograph Series. Trans Tech Publications.
- Fulcher, G. S., 1925. Analysis of recent measurements of the viscosity of glasses. Journal of the American Ceramical Society 8, 339–355.
- Gaber, M., 1999. Phaenomenologische Untersuchungen des Wasserabgabeverhaltens von Alkali-Kalzium-Silikatgläsern mit der Vakuum-Extraktionsmethode. Ph.D. thesis, Hochschule des Saarlandes.
- Gardon, R., Narayanaswamy, O. S., 1970. Stress and volume relaxation in annealing flat glass. J. Am. Ceram. Soc. 53, 380.
- Giordano, D., 2002. Experimental determinations and modelling of the viscosity of multicomponent natural silicate melts: Volcanological implications. Ph.D. thesis, Ludwig-Maximilians-Universität München.
- Giordano, D., Dingwell, D. B., 2003. Non-arrhenian multicomponent melt viscosity: a model. Earth and Planetary Science Letters 208 (3-4), 337–349.
- Gloockle, W. G., 1993. Anwendung des fraktalen Differentialkalküls auf Relaxationen in ungeordneten Systemen. Universität Ulm, dissertation.
- Goetze, W., Sjöegren, L., 1992. Relaxation processes in supercooled liquids. Reports on Progress in Physics 55 (3), 241–376.
- Gonnermann, H. M., Manga, M., 2003. Explosive volcanism may not be an inevitable consequence of magma fragmentation. Nature 426, 432–435.
- Gottsmann, J., Dingwell, D., 2001a. Cooling dynamics of spatter-fed phonolite obsidian flows on Tenerife, Canary Islands. J. Volcanol. Geotherm. Res. 105, 323–342.
- Gottsmann, J., Dingwell, D., 2001b. The cooling of frontal flow ramps: A calorimetric study on the rocche rosse rhyolite flow, Lipari, Aeolian Islands, Italy. Terra Nova 12, 157–164.
- Gottsmann, J., Giordano, D., Dingwell, D. B., 2002. Predicting shear viscosity during volcanic processes at the glass transition: a calorimetric calibration. Earth and Planetary Science Letters 198 (3-4), 417–427.
- Gutzow, I., Heide, K., 1996. Thermodynamic and Kinetic Problems in the Formation, Rheology and Crystallisation of Natural Glasses. Chemie der Erde 56, 331–354.
- Gutzow, I., Schmelzer, J., 1995. The vitreous state. Springer.
- Gutzow, I., Yamakov, V., Ilieva, D., Babalievski, P., Pye, L. D., 2001. Generic Phenomenological Theory of Vitrification. Glass Physics and Chemistry 27 (2), 148–159.
- Hall, A., 1996. Igneous petrology. Prentice Hall.
- Havriliak, S., Negami, S., 1967. A complex plane representation of dielectric and mechanical relaxation processes in some polymers. Polymer 8 (4), 161–210.
- Heide, G., 2004. Personal communications.
- Heide, K., 1989. Gefüge natürlicher Gläser und deren Beziehung zu ihrer Genese. Chemie der Erde 49, 287–295.
- Heide, K., Schmidt, C. M., 2003. Volatiles in vitreous basaltic rims, *HSDP*

- 2, big island, hawaii. *Journal of Non-Crystalline Solids* 323, 97–103.
- Hess, K., Dingwell, D., Webb, S., 1996. The influence of alkaline-earth oxides (BeO, MgO, CaO, SrO, BaO) on the viscosity of a haplogranitic melt: systematics of non-Arrhenian behaviour. *European Journal of Mineralogy* 8, 371–381.
- Hess, K. U., 1996. Zur Temperaturabhaengigkeit der Viskositaet von haplogranitischen Schmelzen. Ph.D. thesis, Universitaet Bayreuth.
- Hess, K. U., Dingwell, D. B., 1996. Viscosities of hydrous leucogranitic melts: a non-Arrhenian model. *American Mineralogist* 81, 1297–1300.
- Heymans, N., 1996. Hierarchical models for viscoelasticity: dynamic behaviour in the linear range. *Rheologica acta* 35, 508–519.
- Heymans, N., Bauwens, J.-C., 1994. Fractal rheological models and fractional differential equations for viscoelastic behaviour. *Rheologica acta* 33, 210–219.
- Hodge, I. M., 1994. Enthalpy relaxation and recovery in amorphous materials. *Journal of Non-Crystalline Solids* 169, 211–266.
- Hodge, I. M., 1997. Adam-Gibbs Formulation of Enthalpy Relaxation Near the Glass Transition. *Journal of Research of the National Institute of Standards and Technology* 102 (2), 195–205.
- Horbach, J., Kob, W., 2002. The structural relaxation of molten sodium disilicate. *arXiv:cond-mat/0206070*.
- Hummel, W., Arndt, J., 1985. Variation of viscosity with temperature and composition in the plagioclase system. *Contributions Mineralogy and Petrology* 90, 83–92.
- Jagdt, R., 1960. Untersuchungen von Relaxationserscheinungen an Alkali-Silikat-Glaesern. *Glastechn. Ber.* 33 (1), 10–19.
- Jonscher, A. K., 1977. The universal dielectric response. *Nature* 267 (5613), 673–679.
- Kampfmann, W., Berckhemer, H., 1985. High temperature experiments on the elastic and anelastic behaviour of magmatic rocks. *Physics of Earth Planetary Interiors* 40, 223–247.
- Ke, T. S., 1996. Nonlinear anelastic internal friction associated with the diffusion of solute atoms in dislocation cores. *Phys. Stat. Solidi. A-Appl. Res.* 155 (83), 83–93, my08.
- Kohlrausch, R., 1847. *Ann. Phys. (Leipzig)* 12, 393.
- Kramers, H., 1926. *Nature* 117, 775.
- Kronig, R. d. L., 1926. *J. Opt. Soc. Am.* 12, 547.
- Lejeune, A.-M., Richet, P., 1995. Rheology of crystal-bearing silicate melts: an experimental study at high viscosities. *Journal of Geophysical Research* 100, 4215–4229.
- Leschik, M., Behrens, H., Wiedenbeck, M., Wagner, N., Heide, K., Gei'sler, H., Reinholz, U., Heide, G., Frischat, G. H., 2003. Determination of H_2O and D_2O contents in rhyolitic glasses using *KFT*, *NRA*, *EGA*, *IR* spectroscopy, and *SIMS*. *Physics and Chemistry of Glasses* submitted.
- Lu, C., Jackson, I., 1998. Seismic-frequency laboratory measurements of shear

- mode viscoelasticity in crustal rocks *II*: Thermally stressed quartzite and granite. *Pure and Applied Geophysics* 153, 441–473.
- Maass, P., 1999. Towards a theory for the mixed alkali effect in glasses. *Journal of Non Crystalline Solids* 255, 35–46.
- Manga, M., Castro, J., Cashman, K. V., Loewenberg, M., 1998. Rheology of bubble-bearing magmas. *Journal of Volcanology and Geothermal Research* 87, 15–28.
- Manga, M., Loewenberg, M., 2001. Viscosity of magmas containing highly deformable bubbles. *Journal of Volcanology and Geothermal Research* 105, 19–24.
- Martens, R. M., 1985. Kalorimetrische Untersuchungen der kinetischen Parameter im Glastransformationsbereich bei Glaesern im System Diopsid-Anorthit-Albit und bei einem *NBS* 710 Standardglas. Ph.D. thesis, Johann Wolfgang Goethe Universitaet Frankfurt am Main.
- Martens, R. M., Rosenhauer, M., Buettner, H., Von Gehlen, K., 1987. Heat capacity and kinetic parameters in the glass transformation interval of diopside, anorthite and albite glass. *Chemical Geology* 62, 49–70.
- Martiny, C., 2001. Untersuchung von Mischkationeneffekten in Alkali-Erdalkali-Silikatglaesern mit Hilfe der mechanischen Verlust- und der elektrischen Leitfaehigkeitsspektroskopie. Westfaelische Wilhelms-Universitaet Muenster, dissertation.
- McVay, G. L., Day, D. E., 1970. Diffusion and internal friction in Na-Rb silicate glasses. *Journal of the American Ceramic Society* 53 (9), 508–513.
- Melnik, O., Sparks, S. J., 1999. Nonlinear dynamics of lava dome extrusion. *Nature* 402, 37–41.
- Mochida, N., Takahashi, K., Shibusawa, S., 1980. *J. Ceram. Soc. Jpn.* 88 (10), 583.
- Mueller, G., 1983. Rheological properties and velocity dispersion of a medium with power-law dependence of Q on frequency. *J. Geophysics* 54, 20–29.
- Mueller, K., Bagdassarov, N. S., James, M., Schmeling, H., Deubener, J., 2003. Internal friction spectroscopy in $Li_2O - 2SiO_2$ partially crystallised glasses. *Journal of Non-Crystalline Solids* 319, 44–56.
- Mysen, B., 2003. Physics and chemistry of silicate glasses and melts. *European Journal of Mineralogy* 15, 781–802.
- Nemilov, S., Johari, G., 2003. A mechanism for spontaneous relaxation of glass at room temperature. *Philosophical Magazine* 83 (27), 3117–3132.
- Ngai, K. L., 2000. Dynamic and thermodynamic properties of glass-forming substances. *Journal of Non Crystalline Solids* 275, 7–51.
- Owen, A. E., 1985. The Glass Transition. In: March, N. H., Street, R. A., Tosi, M. (Eds.), *Amorphous Solids and the Liquid State. Physics of Solids and Liquids*. Plenum Press, pp. 395–431.
- Papale, P., 1999. Strain-induced magma fragmentation in explosive eruptions. *Nature* 397, 425–428.
- Paulmann, D., 1998. Monte-Carlo-Simulation zur Diffusion von Alkaliionen in oxidischen Glaesern. Ph.D. thesis, Georg-August-Universitaet Goettingen.

- Perchuk, L. L., Kushiro, I., 1991. Relations Between Structure, Redox Equilibria of Iron, and Properties of Magmatic Liquids. Vol. 9 of Advances in Physical Geochemistry. Springer.
- Persikov, E., 1991. The viscosity of magmatic liquids: Experiment, generalized patterns. a model for calculation and prediction. In: Perchuk, L. L., Kushiro, I. (Eds.), Physical Chemistry of Magmas. Vol. 9 of Advances in Physical Geochemistry. Springer, pp. 1–40.
- Pfeiffer, T., 1998. Viscosities and electrical conductivities of oxidic glass-forming melts. Solid State Ionics 105, 277–287.
- Phalippou, J., Jabra, R., Zarzycki, J., 1980. A new interpretation of internal friction in oxide glasses. Journal of Non-Crystalline Solids 38-39 (1), 481–486.
- Pinkerton, H., Stevenson, R. J., 1992. Methods of determining the rheological properties of magmas at sub-liquidus temperature. Journal of Volcanology and Geothermal Research 53, 47–66.
- Polian, A., Vo-Thanh, D., Richet, P., 2002. Elastic properties of α - SiO_2 up to 2300K from Brillouin scattering measurements. Europhysics Letters 57 (3), 375381.
- Priven, A. I., 1998. Calculation of the Viscosity of Glass-forming Melts: *III*. The $\text{Alk}_2\text{O} - \text{RO} - \text{Al}_2\text{O}_3 - \text{SiO}_2$ -System. Glass Physics and Chemistry 24 (2), 29–30.
- Priven, A. I., 2001. Calculation of Temperature Dependences of the Viscosity and Volume Relaxation Time for Oxide Glass-Forming Melts from Chemical Composition and Dilatometric Glass Transition Temperature. Glass Physics and Chemistry 27 (6), 527–542.
- Qiu, F., Zhang, H., Yanga, Y., 1998. Chain stretching effect on domain growth during spinodal decomposition of binary polymer mixtures under simple shear flow. Journal of Chemical Physics 108 (8), 9529–9536.
- Renner, J., Evans, B., Hirth, G., 2000. On the rheologically critical melt fraction. Earth and Planetary Science Letters 181, 585–594.
- Richet, P., 1984. Viscosity and configurational entropy of silicate melts. Geochimica et Cosmochimica Acta 48, 471–483.
- Richet, P., Neuville, D. R., 1992. Thermodynamics of Silicate Melts: Configurational Properties. In: Saxena, S. K. (Ed.), Thermodynamic Data: Systematics and Estimation. Vol. 10 of Advances in Physical Geochemistry. Springer, pp. 132–161.
- Ritland, H. N., 1956. Limitations of the fictive temperature concept. Journal of the American Ceramic Society 39 (12), 403–406.
- Rivers, M. L., Carmichael, I. S. E., 1987. Ultrasonic studies of silicate melts. Journal of Geophysical Research 92 (B9), 9247–9270.
- Roessler, E., Sokolov, A. P., 1996. The dynamics of strong and fragile glass formers. Chemical Geology 128 (1-4), 143 – 153.
- Roetger, H., 1941. Elastische Nachwirkung durch Waermediffusion (thermische Reibung) und Materiediffusion (eigentliche innere Reibung) bei periodischem und aperiodischem Vorgang. Glastechnische Berichte 19 (6), 192–200.

- Roetger, H., 1958a. Neue Erkenntnisse ueber das Relaxationsverhalten der Glaeser. Wissenschaftliche Zeitschrift der Friedrich Schiller Universitaet Jena, Math. Nat. Reihe 7 (2/3), 237–246.
- Roetger, H., 1958b. Ueber das elastische Relaxationsverhalten von einfachen und gemischten Alkali-Silikat-Glaesern und von Borax. Glastechn. Ber. 31 (2), 54–60.
- Roetger, H., 1974. Relaxation times and viscosity. Journal of Non-Crystalline Solids 14, 201–217.
- Roetger, H., 1975. Entwicklung und Anwendung der Vorstellung ueber das Relaxationsverhalten von Glas. Sitzungsbericht der AdW der DDR, Mathematik-Naturwissenschaft-Technik 3/N, 104–116.
- Roling, B., 2001. Mechanical loss spectroscopy on inorganic glasses and glass ceramics. Current Opinion in Solid State and Materials Science 5, 203–210.
- Roling, B., Ingram, M. D., 1998a. Analysis of mechanical losses due to ion-transport processes in silicate glasses. Physical Review B 57 (22), 14192–14199.
- Roling, B., Ingram, M. D., 1998b. Determination of divalent cation mobilities in glass by dynamic mechanical thermal analysis (dmta): evidence for cation coupling effects. Solid State Ionics 105, 47–53.
- Russell, J. K., Giordano, D., Dingwell, D. B., 2003. High-temperature limits on viscosity of non-Arrhenian silicate melts. American Mineralogist 88, 1390–1394.
- Rust, A. C., Manga, M., 2002. Bubble shapes and orientations in low Re simple shear flow. Journal of Colloid and Interface Science 249, 476–480.
- Ryder, R. J., Rindone, G. E., 1961. Internal friction of simple alkali silicate glasses containing alkaline-earth oxides . *II*. interpretation and discussion. Journal of the American Ceramic Society 44 (11), 532–540.
- Saar, M. O., Manga, M., Cashman, K. V., Fremouw, S., 2001. Numerical models of the onset of yield strength in crystal-melt suspensions. Earth and Planetary Science Letters 187, 367–379.
- Sakamura, H., Yasui, I., 1985. Journal of the Ceramic Society of Japan 93 (12), 781.
- Sakamura, H., Yasui, I., 1989. Proc.XVth Intern.Congr.on Glass, Leningrad 2a, 257.
- Saxena, S. K., 1992. Thermodynamics of Silicate Melts: Configurational Properties. Vol. 10 of Advances in Physical Geochemistry. Springer.
- Schiessel, H., Blumen, A., 1993. Hierarchical analogues to fractional relaxation equations. J. Phys. A: Math. Gen. 16, 5057 – 5069.
- Schiessel, H., Blumen, A., 1995. Mesoscopic pictures of the sol-gel transition: ladder models and fractal networks. Macromolecules 28, 4013–4019.
- Schiessel, H., Metzler, R., Blumen, A., Nonnenmacher, T., 1995a. Generalized viscoelastic models: their fractional equations with solutions. J. Phys. A: Math. Gen. 28, 6567–6584.
- Schiessel, H., Oshanin, G., Blumen, A., 1995b. Dynamics and conformational properties of polyampholytes in external electrical fields. Journal of Chem-

- ical Physics 28 (103), 5070 – 5 – 74.
- Schilling, F. R., Sinogeikin, S. V., Hauser, M., Bass, J. D., 2003. Elastic properties of model basaltic melt compositions at high temperatures. *Journal of Geophysical Research-Solid Earth* 108 (B6), 2304.
- Schmidt, C., Heide, K., 2000. Degas ein neues Analysenverfahren in der organischen Geochemie. *Terra Nostra*, 92–94.
- Schneider, B. W., 2000. Breitbandige dielektrische Studien der Dynamik struktureller Glasbildner. *Universitaet Augsburg*, dissertation.
- Schulz, B. M., 2000. Diffusion in Glaesern und anderen Komplexen Systemen. *Martin-Luther-Universitaet Halle-Wittenberg*, dissertation.
- Shaw, H. R., 1972. Viscosities of magmatic silicate liquids: empirical method of prediction. *Journal of Science* 272, 870–893.
- Shelby, J., Day, D., 1969. Mechanical relaxations in Mixed-Alkali Silicate Glasses: *I*, Results. *Journal of the American Ceramic Society* 52, 169–174.
- Shelby, J., Day, D., 1970. Mechanical relaxations in Mixed-Alkali Silicate Glasses: *II*, Discussion. *Journal of the American Ceramic Society* 53, 182.
- Siewert, R., Rosenhauer, M., 1997. Viscoelastic relaxation measurements in the system SiO_2 - $NaAlSiO_4$ by photon correlation spectroscopy. *American Mineralogist* 82, 1063–1072.
- Sipp, A., Bottinga, Y., Richet, P., 2001. New high viscosity data for 3D network liquids an new correlations between old parameters. *Journal of Non-Crystalline Solids* 288, 166–174.
- Smith, J. V., 1997. Shear thickening dilatancy in crystal-rich flows. *Journal of Volcanology and Geothermal Research* 79, 1–8.
- Sparks, R. S. J., Murphy, M. D., Lejeune, A. M., Watts, R. B., Barclay, J., Young, S. R., 2000. Control on the emplacement of the andesite lava dome of the Soufriere Hills volcano, Montserrat by degassing induced crystallization. *Terra Nova* 12, 14–20.
- Stebbins, J. F., McMillan, P., Dingwell, D., 1995. Structure, Dynamics and Properties Of Silicate Melts. Vol. 32 of *Reviews in Mineralogy*. Mineralogical Society of America.
- Stein, D., Spera, F., 1992. Rheology and microstructure of magmatic emulsions : theory and experiments. *Journal of Volcanology and Geothermal Research* 49, 157–174.
- Stevens, J. M., 1985. Relaxation phenomena in glass. *Journal of Non-Crystalline Solids* 73 (1-3), 165–178.
- Stevenson, R. J., Bagdassarov, N. S., Dingwell, D. B., Romano, C., 1998. The influence of trace amounts of water on the viscosity of rhyolithes. *Bull vulcanol* 60, 89–97.
- Stevenson, R. J., Dingwell, D. B., Webb, S. L., Bagdassarov, N., 1995. The equivalence of enthalpy and shear stress relaxation in rhyolitic obsidians and quantification of the liquid-glass transition in volcanic prozesses. *Journal of Volcanology and Geothermal Research* 68, 297–306.
- Stevenson, R. J., Dingwell, D. B., Webb, S. L., Sharp, T. G., 1996. Viscosity of microlite-bearing rhyolitic obsidians: an experimental study. *Bull Volcanol*

- 58, 298–309.
- Tammann, G., Hesse, W., 1926. Die Abhaengigkeit der Viskosität von der Temperatur bei unterkuehlten Fluessigkeiten. *Zeitschrift fuer anorganische allgemeine Chemie* 156, 245–257.
- Tangeman, J. A., Lange, R. A., 2001. Determination of the limiting fictive temperature of silicate glasses from calorimetric and dilatometric methods: Application to low-temperature liquid volume measurements. *American Mineralogist* 86, 1331–1344.
- Taylor, M., Brown, G. E., 1979a. Structure of mineral glasses: 1. feldspar glasses $NaAlSiO_3$, $NaAlSiO_3$, $CaAl_2Si_2O_8$. *Geochimica et Cosmochimica Acta* 43 (1), 61–75.
- Taylor, M., Brown, G. E., 1979b. Structure of mineral glasses: 2. feldspar glasses SiO_2 - $NaAlSiO_3$ join. *Geochimica et Cosmochimica Acta* 43 (9), 1467–1473.
- Taylor, T., Ridone, G., 1974. Influence of distribution of water in silicate-glasses on mechanical relaxation. *Journal of Non Crystalline Solids* 14, 157–164.
- Tool, A. Q., 1941. Relation between inelastic deformability and thermal expansion of glass in its annealing range. *Journal of the American Ceramic Society* 29, 240–253.
- Toplis, M. J., Richet, P., 2000. Equilibrium density and expansivity of silicate melts in the glass transition range. *Contributions to Mineralogy and Petrology* 139 (6), 672–683.
- VanAss, H. M. J. M., Stevels, J. M., 1974. Internal-friction of mixed alkali metaphosphate glasses .I. results. *Journal of Non Crystalline Solids* 15, 215.
- Versteeg, V. A., 1992. Internal Friction in Lithium Aluminosilicate Glass-Ceramics. Ph.D. thesis, Cornell University.
- Vogel, D. H., 1921. Temperaturabhaengigkeitsgesetz der Viskosität von Fluessigkeiten. *Physikalische Zeitschrift* 22, 645–646.
- VoThanh, D., Polian, A., Richet, P., 1996. Elastic properties of silicate melts up to 2350 K from Brillouin scattering. *Geophysical Research Letters* 23 (5), 423–426.
- Wagner, N., 2004. Mechanische Spektroskopie an vulkanischen Glaesern. Ph.D. thesis, Friedrich-Schiller-University Jena.
- Wagner, N., Bagdassarov, N. S., Heide, K., 2003. Untersuchungen zum anelastischen und viskoelastischen Verhalten eines komplexen Aluminium-Silicatglases. Tagungsband 77. Glastechnische Tagung in Leipzig Vortragsband, 109–112.
- Wagner, N., Bagdassarov, N. S., Heide, K., 2004. Mechanical spectroscopy of natural and synthetic silicate glasses and melts. In: Li, H. (Ed.), *Melt Chemistry, Relaxation, and Solidification Kinetics of Glasses*. Vol. 170 of *Ceramic Transactions*. American Ceramic Society, p. in print.
- Wagner, N., Heide, K., Bark-Zollmann, S., 2001. Mechanisches Relaxationsverhalten rhyolithischer Obsidiane im Vergleich zu kristallisierenden Glaesern und Glaskeramiken. *Beihefte European Journal of Mineralogy* 13 (1), 166.

- Webb, S., Jackson, I., 2003. Anelasticity and microcreep in polycrystalline *MgO* at high temperature: an exploratory study. *Physics and Chemistry of Minerals* 30 (3), 157–166.
- Webb, S. L., 1991. Shear and volume relaxation in $Na_2Si_2O_5$. *American Mineralogist* 76, 1449–1454.
- Webb, S. L., 1992. Low-frequency shear and structural relaxation in rhyolite melt. *Physics and Chemistry of Minerals* 19 (4), 240–245.
- Webb, S. L., 1997. *Lectures in Earth Science 67: Silicate Melts*. Springer.
- Webb, S. L., Dingwell, D. B., 1990. The onset of non-Newton rheology of silicate melts: A fiber elongation study. *Physics and Chemistry of Minerals* 17, 125–132.
- Wilding, M., Dingwell, D., Batiza, R., Wilson, L., 2000. Cooling rates of hyaloclastites: applications of relaxation geospeedometry to undersea volcanic deposits. *Bull Volcanol* 61, 527–536.
- Wilding, M., Webb, S., Dingwell, D., Ablay, G., Marti, J., 1996a. Cooling rate variation in natural volcanic glasses from Tenerife, Canary Islands. *Contrib Mineral Petrol* 125, 151–160.
- Wilding, M. C., Webb, S. L., Dingwell, D. B., 1995. Evaluation of a relaxation geospeedometer for volcanic glasses. *Chemical Geology* 125, 137–148.
- Wilding, M. C., Webb, S. L., Dingwell, D. B., 1996b. Tektite cooling rates: calorimetric relaxation geospeedometry applied to a natural glass. *Geochim Cosmochim Acta* 60, 1099–1103.
- Williams, M. L., Landel, R. F., Ferry, J. D., 1955. The temperature dependence of relaxation mechanisms in amorphous polymers and other glass-forming liquids. *Journal of the American Chemical Society* 77, 3701 – 3707.
- Zdaniewski, W. A., Rindone, G. E., Day, D. E., 1976. The Internal Friction of Glasses. *Journal of Materials Science* 14, 763–765.
- Zhang, Z. L., Zhang, H. D., Yang, Y. L., Vinckier, I., Laun, H. M., 2001. Rheology and morphology of phase-separating polymer blends. *Macromolecules* 34, 1416–1429.
- Zirkel, F., 1873. *Die mikroskopische Beschaffenheit der Minerale und Gesteine*. Verlag W. Engelmann Leipzig.