

Oscillatory instability of crack propagations in quasi-static fracture

Shin-ichi Sasa

Department of physics, Kyoto University, Kyoto 606, Japan

Ken Sekimoto

Department of applied physics, Nagoya University, Nagoya 464-01, Japan

(July 13, 2021)

Abstract

Crack propagations in quasi-static fracture are studied theoretically. The Griffith theory is applied to discuss a crack extension condition and motion of crack tips in straight propagations. Stability of the straight propagations is investigated based on the simple assumption that a curvature near the crack tip is determined by a singular shear stress. It is shown that straight propagations become unstable under certain conditions. Combined with boundary effects, this instability leads to an oscillatory propagation of cracks. The critical conditions are calculated quantitatively.

62.20.Mk, 46.30.Nz

Typeset using REVTeX

Fracture has been studied extensively since Griffith wrote a breakthrough paper in 1920 [1], but still provides us with many unsolved problems [2] [3]. Yuse and Sano have recently carried out a nice experiment reminiscent of directional solidification [4]. In their experiment, a thin glass plate seeded with a small crack is moved from a hot region to a cold one at a velocity v . It was observed that various forms of crack patterns developed depending on the temperature difference δT and the velocity v . When the temperature difference is increased and reaches a critical value, the crack begins to extend along a line. At a larger temperature difference, a transition from the straight crack to a wavy crack occurs. In this letter, we present a theory in which the two critical temperature differences are calculated.

An experimental configuration is displayed in fig. 1. Here, a coordinate system (x, y) is fixed on the glass plate, which is assumed to be sufficiently thin, to have boundaries at $y = \pm W/2$, to be submerged in a cold bath in the region $-\infty < x < s$, and to contact a heating element at $x \rightarrow \infty$. We note that s is regarded as a variable specifying the time-dependent external condition and that the propagation velocity of cracks is close to ds/dt . This fact implies that the crack tip moves adiabatically with respect to the change of the external condition. We thus parametrize the time-evolution of the position of the crack tip by s as $(q(s), p(s))$. The problem we address is then to derive an equation of motion for $(q(s), p(s))$.

Suppose that a crack is positioned on the center line of a glass plate. According to the Griffith theory [1], when the strain-energy release rate G exceeds the energy needed to create a new surface Γ , the crack begins to extend at a speed of on the order of propagation of sound. For a fixed temperature profile, however, the crack would be arrested immediately at a position where G equals to Γ , because elastic forces arising from non-uniform thermal expansions are localized over a region where the temperature gradient is large. Then, if a temperature profile were translated infinitesimally along the plate, the crack tip would move because $G > \Gamma$, and then stop again at $G = \Gamma$ after infinitesimal extension. Since the translation velocity v is much smaller than the sound velocity in glass, the crack propagates so as to maintain the equality $G = \Gamma$. Such a fracture is called 'equilibrium fracture' or

'quasi-static fracture'. This should be distinguished from an 'unstable fracture' or 'dynamic fracture' in which the energy release rate G becomes larger as the crack extends. In quasi-static fracture, the equation $G = \Gamma$ gives not only a condition for the extension of a crack, but also the position of a tip of the straight crack.

In order to embody this idea, we focus on infinitely narrow cracks. Then, stresses σ_{ij} diverge at the crack tip. Using a polar coordinate system (r, θ) , we can expand σ_{ij} in \sqrt{r} around the crack tip. In particular, the singular part of the stress is characterized by stress intensity factors K_I and K_{II} related with basic 'modes' of crack-surface displacement called mode I (opening mode) and mode II (sliding mode), and its form is expressed by

$$\sigma_{ij}^{(sing)} = \frac{K_I}{\sqrt{2\pi r}} \Sigma_{ij}^{(1)}(\theta) + \frac{K_{II}}{\sqrt{2\pi r}} \Sigma_{ij}^{(2)}(\theta), \quad (1)$$

where $\Sigma_{ij}^{(1)}(\theta)$ and $\Sigma_{ij}^{(2)}(\theta)$ are universal functions [6]. Since the shear stress vanishes at the center of glass plates, the equality $K_{II} = 0$ holds for the straight propagation along the center line. Then, as shown by Irwin, the energy release rate G is related to the stress intensity factor K_I as $G = K_I^2/E$, where E is a Young modulus [5]. By introducing a critical stress intensity factor K_I^c such that $K_I^c = \sqrt{\Gamma E}$, the equation $G = \Gamma$ is reduced to

$$K_I = K_I^c, \quad (2)$$

where K_I is determined by the crack pattern and temperature profile, and K_I^c is intrinsic to the material in question. Noting that K_I is a function of $q(s) - s$ due to translational symmetry in the x -direction and that K_I does not depend on s because of (2), we obtain

$$q(s) = s + q_0, \quad (3)$$

where q_0 is a constant given by (2). A crack can not extend when a solution of (3) does not exist. The expression of K_I for a straight crack pattern will be given below, but before giving this derivation, we will discuss an instability of the straight propagation in the next two paragraphs.

To this point, the system has been assumed to be under pure mode I loading. However, once the crack is inclined or away from the center, a shear mode is superposed onto mode

I , and the crack is deflected from straight line geometry. We assume here that the crack extension condition (2) remains unchanged when the crack extends smoothly. Then, in order to describe the dynamics of tips of curved cracks, a relation between shear stresses and curvatures at the crack tips should be considered. Our hypothesis is as follows: a curvature at a tip is determined by only K_{II} and the crack tip tends toward the orientation of minimum shear loading. Since the curvature is well approximated by d^2p/ds^2 for a slightly curved crack, dimensional analysis leads to a simple expression:

$$\frac{d^2p}{ds^2} = \frac{1}{r_0} \Phi\left(\frac{K_{II}}{K_I^c}\right), \quad (4)$$

where the non-dimensional function $\Phi(z)$ is odd in z and negative for $z > 0$, and a new parameter r_0 with a length dimension has been introduced. A similar equation was considered by R.V. Gol'dstein and R.L. Salganic [7]. They identified r_0 as the length of the end region of cracks and derived the equation $K_{II} = 0$ by taking the limit $r_0 dp^2/ds^2 \rightarrow 0$. Our investigation is not limited to this limit. In fact, we will now derive the dependence of the crack oscillation on r_0 .

Since $K_{II}(s)$ depends on the crack pattern which is identical to the history of the crack tip, $(q(s'), p(s'))$, $(-\infty \leq s' \leq s)$, (4) is regarded as a non-Markov dynamical system. We thus need to consider perturbations with infinite degrees of freedom so as to investigate stability of the straight propagation of cracks. However, if instabilities are caused by perturbations with a longer curvature radius than the size of a most relevant region to K_{II} near the tip, we are allowed to employ a Markov approximation. Perturbations are then restricted to a linear combination of 'tilt' and 'translation' of the crack, and K_{II} is written as

$$K_{II} = K_{II}^{(1)} \frac{dp}{ds} + K_{II}^{(0)} p, \quad (5)$$

where the first and second term of the right-hand side correspond to the stress intensity factors of shear stresses coming from 'tilt' and 'translation', respectively. Substituting (5) into (4), we obtain a linearized equation around the straight propagation:

$$\frac{d^2 p}{ds^2} = -\frac{1}{r_0 K_I^c} (K_{II}^{(1)} \frac{dp}{ds} + K_{II}^{(0)} p), \quad (6)$$

where we have used a normalization of Φ such that $\Phi'(0) = -1$. The oscillatory instability observed in experiments then can be explained by checking the change of the sign of $K_{II}^{(1)}$ and the positivity of $K_{II}^{(0)}$. The critical point is given by $K_{II}^{(1)} = 0$ and therefore does not depend on the unknown parameter r_0 , while the wavelength of oscillation λ is proportional to $\sqrt{r_0}$:

$$\lambda = 2\pi \sqrt{\frac{r_0 K_I^c}{K_{II}^{(0)}}}. \quad (7)$$

Our theoretical result about the critical point can be compared to that in experiments and the length r_0 can be estimated from experimental data.

Now, we derive expressions for K_I , $K_{II}^{(0)}$ and $K_{II}^{(1)}$. Since glass plates are assumed to be sufficiently thin, we consider two-dimensional thermo-elastic systems under plane stress conditions. The equation of the force balance $\sum_j \partial_j \sigma_{ij} = 0$ can be satisfied automatically when the stresses are written in terms of the Airy stress function ϕ such that

$$\sigma_{xx} = \frac{\partial^2 \phi}{\partial y^2}, \quad \sigma_{yy} = \frac{\partial^2 \phi}{\partial x^2}, \quad \sigma_{xy} = -\frac{\partial^2 \phi}{\partial x \partial y}. \quad (8)$$

Then, using Hook's law and the compatibility condition of a set of strains, we obtain a basic equation in our system:

$$\Delta^2 \phi = -E\alpha \Delta T. \quad (9)$$

Here, α is a thermal expansion rate and the temperature profile $T(x, t)$ along the glass plate is derived under the assumptions that $T(x, t)$ equals to T_c in the cold bath $x \leq s$, and that $T(x, t)$ obeys a diffusion equation $\partial_t T = D\Delta T$ under a boundary condition $T(x, t) \rightarrow T_c + \delta T$ for $x \rightarrow \infty$, where D is a thermal diffusion constant. A steady moving solution at a velocity v is obtained in the form

$$T(x, t) = T_c + \theta(x - s)\delta T(1 - \exp(-(x - s)/d_0)), \quad (10)$$

where we have introduced a thermal diffusive length: $d_0 = D/v$. Stress intensity factors are given from solutions of (9) under boundary conditions $\sum_j \sigma_{ij} n_j = 0$, where n_j is a normal unit vector to boundaries. We solve the problem by dividing it into two steps. First, we calculate the stress $\tilde{\sigma}_{ij}$ in glass plates without cracks, where boundary conditions at $y = \pm W/2$ and $|x| \rightarrow \infty$ are assumed as $\tilde{\sigma}_{yy} = \tilde{\sigma}_{xy} = 0$ at $y = \pm W/2$ and $\tilde{\sigma}_{xx} = \tilde{\sigma}_{xy} \rightarrow 0$ for $|x| \rightarrow \infty$. The following expressions (with $\sigma_{ij}^0(x)$ denoting $\tilde{\sigma}_{ij}(x, y = 0)$) are then obtained:

$$\sigma_{xx}^0(x) = -E\alpha \int_{-\infty}^{\infty} dk e^{ikx} \hat{T}(k) f_-(k), \quad (11)$$

and

$$\sigma_{yy}^0(x) = -E\alpha \int_{-\infty}^{\infty} dk e^{ikx} \hat{T}(k) (1 - f_+(k)), \quad (12)$$

where $\hat{T}(k)$ is a Fourier mode of the temperature field given by (10) and

$$f_{\pm}(k) = \frac{kW \cosh(kW/2) \pm 2 \sinh(kW/2)}{kW + \sinh(kW)}. \quad (13)$$

Then, noting that existence of a crack alters *only* boundary conditions, we find that the stresses on the glass plate with a crack are given by $\tilde{\sigma}_{ij} + \sigma_{ij}^*$, where σ_{ij}^* is a solution of the homogeneous equation of (9) under fictious external forces introduced so as to satisfy the boundary conditions along the crack. Since a singularity appears in the stresses σ_{ij}^* , stress intensity factors K_I and K_{II} for a straight crack are expressed by the fictious forces such that [8]

$$K_I = \sqrt{\frac{2}{\pi}} \int_0^{\infty} dr \frac{\tilde{\sigma}_{\theta\theta}}{\sqrt{r}}, \quad \text{and} \quad K_{II} = \sqrt{\frac{2}{\pi}} \int_0^{\infty} dr \frac{\tilde{\sigma}_{\theta r}}{\sqrt{r}}, \quad (14)$$

where $\tilde{\sigma}_{\theta\theta}$ and $\tilde{\sigma}_{r\theta}$ correspond to the fictious forces contributing to K_I and K_{II} respectively, and r is measured along the crack from the tip. This formula, strictly speaking, should be applicable to cracks extending semi-infinitely in an infinitely large space. We expect however that this approximation is still effective for sufficiently large W/d_0 . By carrying out a partial integral, we obtain the expression of K_I for a straight crack on the line $y = 0$:

$$K_I = \frac{4}{3} \sqrt{\frac{2}{\pi}} \int_{-\infty}^q dx (\partial_x^2 \sigma_{yy}^0) (q - x)^{3/2}. \quad (15)$$

Also, noting a transformation $\tilde{\sigma}_{r\theta} = \tilde{\sigma}_{xy} - (\tilde{\sigma}_{xx} - \tilde{\sigma}_{yy})dp/ds$, we can obtain K_{II} for cracks inclined slightly and displaced from the center:

$$K_{II} = \sqrt{\frac{2}{\pi}} \left[\int_{-\infty}^q dx \frac{\tilde{\sigma}_{xy}}{\sqrt{q-x}} + \frac{dp}{ds} \int_{-\infty}^q dx \frac{\tilde{\sigma}_{yy} - \tilde{\sigma}_{xx}}{\sqrt{q-x}} \right], \quad (16)$$

where the stresses have x -dependence in the form $\tilde{\sigma}_{ij}(x, y(x))$, $y(x) = p + dp/ds \cdot (p - x)$. We further expand the right-hand side of this equation in p and dp/ds . The expansion coefficients $K_{II}^{(1)}$ and $K_{II}^{(0)}$ are then derived as

$$K_{II}^{(0)} = -2\sqrt{\frac{2}{\pi}} \int_{-\infty}^q dx (\partial_x^2 \sigma_{xx}^0) \sqrt{q-x}, \quad (17)$$

and

$$K_{II}^{(1)} = K_I - 2\sqrt{\frac{2}{\pi}} \int_{-\infty}^q dx (\partial_x^2 \sigma_{xx}^0) \cdot (q-x)^{3/2}, \quad (18)$$

where we have used the equation of force balance: $\partial_y \sigma_{xy} = -\partial_x \sigma_{xx}$. From (11),(12), (15), (17) and (18), we obtain K_I , $K_{II}^{(0)}$, and $K_{II}^{(1)}$.

We now introduce two control parameters defined by $\mu = W/d_0$ and $R = E\alpha\delta TW^{1/2}/K_I^c$. One may easily see that μ and R correspond to non-dimensional velocity and temperature difference, respectively. We further define ξ as a ratio of a crack length out of the cold bath to a thermal diffusive length: $\xi = q_0/d_0$. Then, K_I , $K_{II}^{(0)}$ and $K_{II}^{(1)}$ are expressed as $K_I = K_I^c R F_I(\mu, \xi)$, $K_{II}^{(0)} = K_I^c R F_{II}^{(0)}(\mu, \xi)/W$, and $K_{II}^{(1)} = K_I^c R F_{II}^{(1)}(\mu, \xi)$, where F_I , $F_{II}^{(0)}$, $F_{II}^{(1)}$ are non-dimensional functions calculated numerically. When we compute these numerical values, we fix the parameter value $\mu = 10$ as representaion of ideal experimental conditions under which the thermal diffusive length is much larger than a thickness of glass plates.

For sufficiently small R , there is no solution ξ satisfying $R F_I(\mu, \xi) = 1$ which is equivalent to $K_I = K_I^c$. In this case, the crack can not extend. For $R > R_c^{(1)}$, $R F_I(\mu, \xi) = 1$ has a solution ξ as is shown in fig. 2. Then, when the temperature difference is increased, the crack length increases, and $F_{II}^{(1)}$ changes its sign at $R_c^{(2)}$. The straight propagation is stable for $R_c^{(1)} < R < R_c^{(2)}$, but the shear stress arising from tilt makes the crack more inclined

for $R > R_c^{(2)}$. We also confirmed the positivity of $F_{II}^{(0)}$. Therefore, we can say that a Hopf bifurcation occurs at $R_c^{(2)}$ with a critical wavelength λ_c . Here, $R_c^{(1)}$, $R_c^{(2)}$ and λ_c were computed as $R_c^{(1)} = 5.6$, $R_c^{(2)} = 9.9$, and $\lambda_c = 4.5\sqrt{r_0W}$. Similarly, for an arbitrary μ , assuming that $F_I(\mu, \xi)$ takes a maximum value at $\xi_m(\mu)$ and that $F_{II}^{(1)}(\mu, \xi)$ becomes zero at $\xi_0(\mu)$, we obtain

$$R_c^{(1)} = F_I(\mu, \xi_m(\mu))^{-1}, \quad R_c^{(2)} = F_I(\mu, \xi_0(\mu))^{-1}, \quad (19)$$

and

$$\lambda_c = 2\pi \sqrt{\frac{F_I(\mu, \xi_0(\mu))}{F_{II}^{(0)}(\mu, \xi_0(\mu))}} \sqrt{r_0W}. \quad (20)$$

Let us discuss asymptotic forms of these equations for $\mu \rightarrow \infty$. First, from (11) and (12), we see that the stress σ^0 is proportional to μ in this limit. Then, (15), (17), (18), (19), and (20) lead to asymptotic forms for $\mu \rightarrow \infty$:

$$R_c^{(1)} \sim R_c^{(2)} \sim \mu^{-1}, \quad \text{and} \quad \lambda_c \sim \mu^0. \quad (21)$$

By using dimensional quantities, the asymptotic forms are rewritten as $\delta T_c \sim v^{-1}$ and $\lambda_c \sim v^0$ for $v \rightarrow \infty$, and $\delta T_c \sim W^{-3/2}$ and $\lambda_c \sim \sqrt{W}$ for $W \rightarrow \infty$. The latter relation implies that the oscillatory instability is caused by effects of the boundaries. In fact, if we assume the periodic boundary conditions at $y = \pm W/2$, $K_{II}^{(0)} = 0$ is obtained due to the translational symmetry in the y -direction and the crack then propagates at a finite angle to the line $y = 0$ when $K_{II}^{(1)} < 0$. Similar behavior was observed in experiments using glass cylinders instead of glass plates.

In the experiment done by Yuse and Sano [4], the thickness of the glass plates is greater than the thermal diffusive length in the range $v \geq 5$ [mm/s]. Therefore, their experimental system may be regarded as a two-dimensional one only in the range $v \ll 5$ [mm/s]. The relation (21) seems to be consistent with experimental results in the range 0.5 [mm/s] $\leq v \ll 5$ [mm/s]. In order to see correspondence with experiments more quantitatively, we use the following values of the material constants typical for glass plates: $\alpha = 8 \times 10^{-6}$ [K⁻¹],

$E = 7 \times 10^{10}$ [Pa], $\Gamma = 8$ [$\text{J} \cdot \text{m}^{-2}$], $D = 5 \times 10^{-3}$ [cm^2/s]. Then, for glass plates with $W = 2.4$ [cm], $\mu = 10$ corresponds to $v = 0.2$ [mm/s], and the critical temperatures $\delta T_c^{(1)}$ and $\delta T_c^{(2)}$ are computed as $\delta T_c^{(1)} = 50$ [K] and $\delta T_c^{(2)} = 80$ [K]. In the experiment [4], $T_c^{(1)}$ was found to be somewhat less than our result, while $T_c^{(2)}$ was approximately twice of ours. We believe that this discrepancy may be due to error in estimating Γ . It is not yet known how to accurately measure this value. Further investigations will be necessary.

Finally, we briefly discuss the parameter r_0 introduced above. From the experimental data that $\lambda_c = 3$ [mm] for $W = 1$ [cm], we obtain $r_0 = 0.05$ [mm]. As we expected above, this value is much smaller than curvatures of oscillating cracks. At this time, however, we are not able to satisfactorily estimate the value of r_0 using physical arguments. By clarifying what occurs on this scale, we hope to reach a deeper understanding of fracture phenomena.

In summary, we have proposed a theory for the transitions between the crack patterns in quasi-static fracture. Based on our theory, the critical points for $\mu = 10$ have been calculated quantitatively and the scaling relations for $\mu \rightarrow \infty$ have been derived. Recently, M. Marder attempted to explain the oscillatory instability [9] relying on the theory of Cotterell and Rice [10]. In addition, numerical simulations of discrete models were carried out [11]. We have not yet been able to work out the correspondence between these works and ours. In order to obtain a true understanding of this phenomena, we need to synthesize theories, numerical simulations and experiments.

We are grateful to M. Sano and A. Yuse for telling us detailed informations of their experiments. We thank Y-h Taguchi, Y. Hayakawa and H. Furukawa for communications about their numerical simulations prior to publications. We also thank H. Nakanishi, T. Mizuguchi, H. Hayakawa, and K. Sawada for stimulating discussions. G.C. Paquette are acknowledged for a critical reading of the manuscript. This work was supported in part by the Japanese Grant-in-aid for Science Research Fund from the Ministry of Education, Science and Culture (No. 05740258).

REFERENCES

- [1] A.A. Griffith, *Phil.Trans.Roy.Soc.A***221**, 163 (1920).
- [2] H.J. Herrmann and S. Roux, eds, *Statistical models for the fracture of disordered media*, (North Holland, Amsterdam, 1990)
- [3] J. Fineberg, S.P. Gross, M. Marder, and H.L. Swinny, *Phys.Rev.Lett***67**, 457 (1991); J.S. Langer, *Phys.Rev.Lett***70**, 3592 (1993); M. Marder and X. Liu, *Phys.Rev.Lett***71**, 2417 (1993).
- [4] A. Yuse and M. Sano, *Nature***362**, 329 (1993); See also M. Hirata, *Scient.Pap.Inst.Phys.Chem.Res.(Japan)***16**, 172 (1931).
- [5] G.R. Irwin, *J.Appl.Mech***24**, 361 (1957).
- [6] L.B. Freund, *Dynamic fracture mechanics*, (Cambridge University Press, New York, 1990); B. Lawn, *Fracture of brittle solids (2nd ed.)*, (Cambridge University Press, New York, 1993).
- [7] R.V. Gol'dstein and R.L. Salganic, *International Journal of Fracture***10**, 507 (1974).
- [8] N.I. Muskhelishvili, *Some basic problems of the theory of Elasticity (4th ed.)*, (Noordhoff, 1963).
- [9] M. Marder, *Nature***362**, 295 (1993); M. Marder, (preprint 1993).
- [10] B. Cotterell and J.R. Rice, *International Journal of Fracture***16**, 155 (1980).
- [11] Y-h. Taguchi, (preprint 1993); H. Furukawa, (preprint 1993), to be published in *Prog.Theor.Phys.*; Y. Hayakawa, (private communication).

FIGURES

FIG. 1. Schematic figure of an experimental configuration. The glass plate is submerged in the cold bath represented by the dotted region.

FIG. 2. ξ versus R (solid line) and $K_{II}^{(1)}/K_I^c$ versus R (dotted line). Vertical axes of solid and dotted lines are graduated on the left and right, respectively. These graphs starts from $R_c^{(1)}$, and $K_{II}^{(1)}/K_I^c$ is negative for $R \geq R_c^{(2)}$. Here, $R_c^{(1)} = 5.6$, and $R_c^{(2)} = 9.9$.



