## **Comments on "Viscosity of high crystal content melts: dependence on solid fraction"**

Antonio Costa<sup>1,2</sup>

<sup>1</sup>Centre for Environmental and Geophysical Flows, Department of Earth

Sciences, University of Bristol

<sup>2</sup>Also Istituto Nazionale di Geofisica e Vulcanologia, sezione di Napoli, Italy

A new parameterisation describing the relationship between viscosity and solid fraction valid at large solid content was recently proposed in *Costa* [2005]:

$$\eta(\phi) = \frac{1}{\left\{1 - \alpha \operatorname{erf}\left(\frac{\sqrt{\pi}}{2}\phi \left[1 + \frac{\beta}{(1 - \phi)^{\gamma}}\right]\right)\right\}^{B/\alpha}}$$
(1)

where  $\eta$  is the relative viscosity,  $\phi$  the volume fraction of particles, B the Einstein coefficient (with a theoretical value B = 2.5), and  $\alpha$ ,  $\beta$ ,  $\gamma$  are three adjustable parameters. The proposed parameterisation approximately reduces to the classical, well established relationships for small fractions. On the other hand, a weak point of equation (1) is that for large  $\phi$ , the relative viscosity tends quickly to a constant value, because the non-linear term in the erf function rapidly saturates

## Submitted in the Geophysical Research Letters, 2005.

A. Costa, Department of Earth Sciences, University of Bristol, Wills Memorial Building, Queen's Road, Bristol BS8 1RJ - UK. (e-mail: a.costa@bris.ac.uk)

it as  $\phi$  approaches unity.

For very large solid fractions, no reliable experimental data are available and there are also some intrinsic problems even in properly defining relative viscosity [see *Costa*, 2005]. However, we can reasonably assume that the trend of the viscosity-crystal content relationship obtained from data by *van der Molen and Paterson* [1979] at high solid fractions for partially-melted granite is generally valid, and this it can be roughly described by a power law relationship. In fact, there is no reason to assume that effective relative viscosity of melted rocks tends towards a plateau region as  $\phi \rightarrow 1$  as predicted by (1). From a quantitative point of view it is no simple to determine correctly the controlling parameters, such as the critical fraction at which a rheological transition occurs or the maximum value that effective relative viscosity can reach as  $\phi \rightarrow 1$ . Moreover there are several indications that these values strongly depend on the particle shape and particle size distribution. However, since magma viscosity controls magma transport, when modelling volcanic processes such as dome growth there is a strong need to estimate the viscosity dependence on crystal-content, even in the limit of very high crystal content where no experimental observations are available [see e.g., *Melnik and Sparks*, 2005].

Here we propose a simple modification of relationship (1) which improves all the main positive features of it, yet at the same time, does not show a plateau region as  $\phi \rightarrow 1$ , generally increases the performance of the model, and exactly recovers the classical well established relationships valid for small fractions. In order to obtain a satisfactory description of the effective relative viscosity on the entire range of  $\phi$ , from zero to near the unity, one more parameter is necessary,

DRAFT

i.e. four parameters. The final four parameter model we adopt is the following:

$$\eta(\phi) = \frac{1 + \left(\frac{\phi}{\phi_*}\right)^{\sigma}}{\left(1 - \alpha \operatorname{erf}\left\{\frac{\sqrt{\pi}}{2\alpha} \frac{\phi}{\phi_*} \left[1 + \left(\frac{\phi}{\phi_*}\right)^{\gamma}\right]\right\}\right)^{B\phi_*}}$$
(2)

where  $0 < \alpha < 1$ ,  $\phi_*$  represents the critical transition fraction,  $\gamma > 1$  is a measure of the rapidity of the rheological transition, and  $\delta$  controls the increase of  $\eta$  as  $\phi \rightarrow 1$ . We can note that, for large  $\delta$ , the second term at the numerator represents a negligible correction when  $\phi < \phi_*$ , whilst it becomes important when  $\phi > \phi_*$ . It easy to see that as  $\phi < \phi_*$  with decreasing  $\phi$ , the parameterisation (2) tends exactly to the *Krieger and Dougherty* [1959] relationship:

$$\eta = \left(1 - \frac{\phi}{\phi_*}\right)^{-B\phi_*} \tag{3}$$

and as  $\phi \rightarrow 0$ , it recovers exactly the Einstein equation:

$$\eta(\phi) \simeq (1 + B\phi) \tag{4}$$

where B is the Einstein coefficient.

An example of the good performance of relationship (2) is shown in Figure 1. Here we plotted relative viscosities deduced from the data of *van der Molen and Paterson* [1979] in the high crystal fraction regime, considering a crystal-free fluid viscosity of  $10^4$  Pa s as suggested by *van der Molen and Paterson* [1979]. These values are matched with and mean values of relative viscosities reported by *Thomas* [1965]. Although we must keep in mind all the intrinsic limitations of these data [see *Costa*, 2005], we can observe that over the entire range of solid fraction, the model is able to reproduce all data with an excellent correlation ( $R^2 = 0.999$ ) and the curve behaviour suggested by *van der Molen and Paterson* [1979]. Another example is shown in Figure 2 where, as in *Costa* [2005], the relative viscosities for Mg<sub>3</sub>Al<sub>2</sub>Si<sub>3</sub>O<sub>12</sub> and Li<sub>2</sub>Si<sub>2</sub>O<sub>5</sub> measured by *Lejeune and Richet* [1995] and the fitted values are shown. However a direct comparison with Figure 2 D R A F T August 21, 2018, 8:58am D R A F T

of *Costa* [2005] is not possible because the relative viscosities values reported in Figure 2 of *Costa* [2005] were erroneously underestimated in systematic way for both  $Mg_3Al_2Si_3O_{12}$  and  $Li_2Si_2O_5$ .

Acknowledgments. This work was supported by NERC research grant reference NE/C509958/1. The author would like to thank O. Melnik for his useful comments and for the discussions had during his stay at the Institute of Mechanics, Moscow State University, in December 2005.

## References

- Costa, Viscosity of high crystal content melts: dependence on solid fraction, *Geophys. Res. Lett.*, *32*, 2005, doi: 10.1029/2005GL024303.
- Krieger, I., and T. Dougherty, A mechanism for non-Newtonian flow in suspension of rigid spheres, *Trans. Soc. Rheol.*, *3*, 137–152, 1959.
- Lejeune, A., and P. Richet, Rheology of crystal-bearing silicate melts: An experimental study at high viscosity, *J. Geophys. Res.*, *100*, 4215–4229, 1995.
- Melnik, O., and R. Sparks, Controls on conduit magma flow dynamics during lava dome building eruptions, *J. Geophys. Res.*, *110*, 2005, doi:10.1029/2004JB003183.
- Thomas, D., Transport characteristics of suspensions: VIII. A note on the viscosity of Newtonian suspensions of uniform spherical particles, *J. Colloid Sci.*, 20, 267–277, 1965.
- van der Molen, I., and M. Paterson, Experimental deformation of partially melted granite, *Contrib. Mineral. Petrol.*, 70, 299–318, 1979.



Figure 1. Effective relative viscosities deduced from data by *van der Molen and Paterson* [1979] at high solid fraction (circles), and from mean value of relative viscosities reported by *Thomas* [1965] at low solid fraction (squares). For data by *van der Molen and Paterson* [1979], for crystal-free fluid viscosity at 800°C and 300 MPa, we considered a value of  $\mu_l = 10^4$  Pa s. The correlation coefficient is 0.999. The best fit parameters are  $\alpha = 0.999916$ ,  $\phi_* = 0.673$  and  $\gamma = 3.98937$ ,  $\delta = 16.9386$ .

DRAFT

η

August 21, 2018, 8:58am

DRAFT



**Figure 2.** Relative viscosities from data by *Lejeune and Richet* [1995] (triangles) and values using eq. (2) (line) for Mg<sub>3</sub>Al<sub>2</sub>Si<sub>3</sub>O<sub>12</sub>(left) and Li<sub>2</sub>Si<sub>2</sub>O<sub>5</sub> (right). The best fit parameters are  $\alpha =$ 0.9703; 0.9995,  $\phi_* = 0.503$ ; 0.409 and  $\gamma = 0.924$ ; 4.214,  $\delta = 40.386$ ; 1.149for Mg<sub>3</sub>Al<sub>2</sub>Si<sub>3</sub>O<sub>12</sub> and Li<sub>2</sub>Si<sub>2</sub>O<sub>5</sub> respectively.

X - 6