A simple formula for the L-gap width of a face-centered-cubic photonic crystal

Alexander Moroz*

FOM-Instituut voor Atoom- en Molecuulfysica, Kruislaan 407, 1098 SJ Amsterdam, The Netherlands

Abstract

The width Δ_L of the first Bragg's scattering peak in the (111) direction of a face-centered-cubic lattice of air spheres can be well approximated by a simple formula which only involves the volume averaged ε and ε^2 over the lattice unit cell, ε being the (position dependent) dielectric constant of the medium, and the effective dielectric constant ε_{eff} in the long-wavelength limit approximated by Maxwell-Garnett's formula. Apparently, our formula describes the asymptotic behaviour of the absolute gap width Δ_L for high dielectric contrast δ exactly. The standard deviation σ steadily decreases well below 1% as δ increases. For example $\sigma < 0.1\%$ for the sphere filling fraction f = 0.2 and $\delta \geq 20$. On the interval $\delta \in (1, 100)$, our formula still approximates gap widths with a reasonable precision, namely the absolute gap width Δ_L with a standard deviation 3% for low filling fractions up to 6.5% for the close-packed case and the relative gap width Δ_L for high discussed.

(J. Opt. A: Pure Appl. Opt. 1, 471-475 (1999))

PACS numbers: 42.70.Qs, 71.20.

Typeset using REVT_EX

^{*}http://www.amolf.nl/external/wwwlab/atoms/theory/

I. INTRODUCTION

The propagation of light in a periodic dielectric medium has recently attracted much attention due to the possibility of opening a gap in the spectrum of electromagnetic waves for both polarizations and all directions of the incident waves [1–5]. In such a medium, the density of states (DOS) can be, in a certain frequency interval, either reduced down to zero (photonic band gap) or enhanced with respect to the vacuum case. The changes in the DOS affect various physical quantities. The most transparent is the change in the spontaneous emission rate of embedded atoms and molecules which may have applications for semiconductor lasers, heterojunction bipolar transistors, and thresholdless lasers [1] or to create new sources of light for ultra-fast optical communication systems.

Existence of the full photonic band gap was first demonstrated at microwaves [5]. Recently, thanks to the intense experimental effort, we have witnessed a significant progress in fabrication of complete photonic-bandgap structures at near-infrared [6–8]. In two dimensions, complete photonic-bandgap structures have been fabricating for TM polarization [6]. In three dimensions, a promissing structure has been fabricated by Sandia's group [7]. Nevertheless, in one direction this structure extends less than two unit cells and there is ongoing experimental search to improve its properties. One of the most promising candidates to achieve a complete photonic bandgap at optical wavelengths and fabricate large enough structures at near-infrared wavelengths are collodial systems of microspheres. Indeed, the latter can self-assemble into three-dimensional crystals with excellent long-range periodicity with the lattice constant well below infrared scale [9–13]. This long-range periodicity gives rise to strong optical Bragg's scattering clearly visible by the naked eye and already described in 1963 [14]. Monodisperse collodial suspensions of microspheres crystalize either in a face-centered-cubic (fcc) [11,15,16] or (for small sphere filling fraction) in a body-centered-cubic (bcc) lattice [12]. Using suspensions of microspheres of different sizes one can also prepare crystals with a complex unit cell (containing more than one scatterer). Both the case of "dense spheres" [16] and "air spheres" [17] when the dielectric constant of spheres ε_s is greater and smaller than the dielectric constant ε_b of the background medium, respectively, can be realized experimentally. There is a significant difference between the two cases, since, according to numerical calculations, simple dielectric lattices of homogeneous spheres [18–20] in air do not exhibit a full photonic band gap, while for air spheres a full band gap can open for a simple fcc lattice [18–20]. Unfortunately, the required dielectric contrast $\delta = \max(\varepsilon_s/\varepsilon_b, \varepsilon_b/\varepsilon_s)$ for opening the full band gap, either $\gtrsim 8.4$ obtained using the plane wave method [19], or, $\gtrsim 8.13$ obtained by the photonic analogue of the Korringa-Kohn-Rostocker (KKR) method [20,21], is currently out of experimental reach at optical and near-infrared frequencies for photonic colloidal structures. The absence of a full gap in this frequency range in currently available collodial crystals of homogeneous and single size spheres does not mean the absence of interesting physics in this weak photonic region. For example, the change in the spontaneous emission rate of dye molecules in an fcc collodial crystal can be observed already at a relatively low $\delta \approx 1.2$ [22].

In contrast to the full gap, Bragg's reflection can be observed for arbitrarily small δ as long as a sample has sufficient long-range periodicity. Analysis of Bragg's scattering might not only be useful to understand the physics of photonic crystals, but it has already found practical application in distributed feedback lasers in the visible region of the spectrum [23]. The first Bragg's peak can be characterized by the width of the (lowest) stop gap (gap at a fixed direction of the incident light) at a certain point on the boundary of the Brillouin zone. We focus here on the case of a simple fcc lattice of air spheres [17], which is among the most promising candidates to achieve a full photonic band gap. For an fcc lattice, it is convenient to consider Bragg's scattering in the (111) direction which corresponds to the L direction of the Brillouin zone (see [26] for the classification of special points of three-dimensional lattices). Apart from numerous experimental data now available [11,15,16,27], there are at least two other reasons for this choice. First, the width of the first stop gap takes on its maximum at the L point and, second, experimental techniques make it possible to allow one to grow collodial crystals such that the L direction corresponds to normal incidence on the crystal surface.

Let $\varepsilon(\mathbf{r})$ be the dielectric constant of an fcc photonic crystal. One has $\varepsilon(\mathbf{r}) = \varepsilon_s$ if \mathbf{r} is inside the sphere and $\varepsilon(\mathbf{r}) = \varepsilon_b$ otherwise. Let f be the sphere filling fraction, i.e., volume of the sphere(s) in the unit cell per unit cell volume. Once f is fixed, the spectrum is only a function of the dielectric contrast δ . By a suitable rescaling, one can always set $\varepsilon_s = 1$ for the case of "air" spheres ($\varepsilon_b = 1$ for the case of "dense" spheres). As δ and f are varied, both the absolute L-gap width Δ_L and the L-midgap frequency ν_c change. As a function of δ , $\Delta_L(\delta)$ takes on its maximum at some $\delta = \delta_m(f)$ while $\nu_c(\delta)$ monotonically decreases. We address the question of whether the width Δ_L can be understood in terms of simple quantities, namely, the volume averaged dielectric constant,

$$\overline{\varepsilon} = f\varepsilon_s + (1 - f)\varepsilon_b,$$

the volume averaged $\varepsilon^2(\mathbf{r})$,

$$\overline{\varepsilon^2} = [f\varepsilon_s^2 + (1-f)\varepsilon_b^2],$$

and the effective dielectric constant ε_{eff} . The latter characterizes optical properties of the crystal in the long-wavelength limit and is (theoretically) determined by the slope of the linear part of the band structure, $\varepsilon_{eff}^{-1/2} = \lim_{k\to 0} d\omega/(cdk)$. Note that due to the vector character of electromagnetic waves, ε_{eff} differs from $\overline{\varepsilon}$, in contrast to the scalar case where $\varepsilon_{eff} = \overline{\varepsilon}$ [24]. One can show that for any f, ε_b , and ε_s ,

$$\varepsilon_{eff} \le \overline{\varepsilon} \le \sqrt{\overline{\varepsilon^2}}.$$
 (1)

Equality in (1) occurs if and only if either f = 0 or f = 1, or, if $\delta = 1$, i.e., if $\varepsilon_b = \varepsilon_s$. The effective dielectric constant can be well approximated [20,24] by Maxwell-Garnett's formula [25],

$$\varepsilon_{eff} \approx \varepsilon_{eff}^{MG} = \varepsilon_b \left(1 + 2 f \alpha\right) / (1 - f \alpha),$$
(2)

where, for a homogeneous sphere, the polarizability factor $\alpha = (\varepsilon_s - \varepsilon_b)/(\varepsilon_s + 2\varepsilon_b)$. Note, however, that in the case of air (dense) spheres ε_{eff}^{MG} slightly overestimates (underestimates) the exact value of ε_{eff} as calculated from the band structure [20,24].

II. RESULTS

Obtaining exact analytic results for dielectric lattices turns out to be notoriously difficult and numerics has been the main tool to understand photonic gaps so far [3,4,18–20,24]. A simple analytical formula, if any, may be a good starting point for obtaining a better insight into the problem. It was rather surprising to find out that such a formula can be found for the L-gap width Δ_L . Namely, in the case for air spheres, Δ_L can be approximated by the formula (see Fig. 1)

$$\Delta_L \approx Cg = C \left(\sqrt{\overline{\varepsilon^2}} - \varepsilon_{eff} \right)^{1/2} / \bar{\varepsilon}.$$
(3)

For a given filling fraction f, the constant C = C(f) was determined by taking the average over Δ_L/g where Δ_L is the L-gap width calculated numerically using a photonic analogue [21] of the KKR method [28]. The latter method gives results which are in excellent agreement with experimental values [16].

Apparently, for sufficiently high $\delta \gg \delta_m(f)$, our formula captures the asymptotic behaviour of the absolute gap width Δ_L exactly. The standard deviation σ steadily decreases well below 1% as one investigates region $\delta \geq \delta_c$ for higher and higher δ_c . For $\delta \geq 20$ one has $\sigma < 0.1\%$ for f = 0.2, $\sigma < 0.4\%$ for f = 0.1, and $\sigma < 0.3\%$ for f = 0.4 (see, for example, Fig. 1). For $\delta \geq 36$ and f = 0.6, $\sigma < 0.5\%$, while for the close-packed case, $\sigma \leq 1\%$. If, however, in the latter case $\delta \geq 50$, σ drops below 0.7\%.

For $\delta \in (1, 100]$, our formula (3) still describes Δ_L with a reasonable accuracy ranging from 3.3% to 6.5% (depending on the filling fraction). The values of C, their standard quadratic deviation σ , and the relative error $\sigma_r = \sigma/C$ are shown in Tab. I. Approximately thirty values of the dielectric contrast within the interval $\delta \in (1, 100]$ were taken for every filling fraction considered. For a given filling fraction, the main part of the error is picked up

	f = 0.1	f = 0.2	f = 0.4	f = 0.6	f = 0.74
C	0.762	0.868	0.875	0.808	0.736
σ	0.031	0.03	0.029	0.038	0.048
σ_r	4.1%	3.4%	3.3%	4.7%	6.5%

TABLE I. The values of C, their standard quadratic deviation σ , and the relative error $\sigma_r = \sigma/C$ for different filling fractions and $\delta \in (1, 100]$.

around $\delta = \delta_m(f)$ for which Δ_L takes on its maximum. At the maximum of the L-gap width Δ_L our formula (3) gives persistently a slightly lower value for Δ_L . Note that for moderate δ Maxwell-Garnett overestimates ε_{eff} for the case of air spheres [20,24]. Therefore, using the exact ε_{eff} may reduce errors further.

According to Tab. I, the quantity C shows a weak dependence on f which can be approximated with high accuracy (relative error 2.5%) by the formula

$$C(f) = C_0 + 0.14 f \left(2f_m - f\right) / f_m^2.$$
(4)

Here $C_0 \approx 0.74$ is the minimal value of C and f_m is the filling fraction for which C takes on its maximal value. Table I indicates that C takes on its minimal value C_0 at the extreme filling fractions f = 0 and f = 0.74, and its maximal value is $C_m \approx 0.88$ at $f_m \approx 0.74/2$. The factor 0.14 in the interpolation formula (4) is the difference $C_m - C_0$. Using C(f) in (3) does not raise the relative error σ_r more than 0.4% for intermediate filling fractions. Fig. 1 shows approximations to the L-gap width for f = 0.4 using formula (3) with optimized C taken from Tab. I and with C(f) given by the formula (4). As the dielectric contrast δ increases, Δ_L first increases to its maximal value and then slowly decreases as $\delta^{-1/2}$. This behavior is well reflected by our formula (3) which in the limit $\delta \gg 1$ yields

$$\Delta_L \sim C(f) \frac{2}{\sqrt{(1-f)(2+f)}} \left(\frac{2+f}{2\sqrt{1-f}} - 1\right)^{1/2} \delta^{-1/2}.$$
 (5)

Since the L-midgap frequency ν_c changes as f and δ are varied, an invariant characteristic of Bragg's scattering is provided by the relative L-gap width

$$\triangle_L^r = \triangle_L / \nu_c$$

 Δ_L^r increases monotonically as δ increases (see Fig. 3) and saturates very fast for $\delta > \delta_m$. Our observation here is that the L-midgap frequency ν_c can be well approximated by

$$\nu_c \approx c k_L / (2\pi n_{eff}^{MG}),\tag{6}$$

where $n_{eff}^{MG} = \sqrt{\varepsilon_{eff}^{MG}}$ and k_L is the length of the Bloch vector at the L point. In units where the length of the side of the conventional unit cell of the cubic lattice [29] is A = 2, one has $k_L/\pi = \sqrt{0.75}$. Recent measurements of ν_c for moderate δ [16] agree well with formula (6) (see also Fig. 2). For all filling fractions considered δ within the range and $1 \le \delta \le 100$, the maximal deviation of the L-midgap frequency given by formula (6) is less than 8% with respect to the exact value. Therefore, the formula

$$\Delta_L^r \approx 2\pi n_{eff}^{MG} \Delta_L / k_L \tag{7}$$

is a natural candidate to describe \triangle_L^r . However, as shown in Fig. 2, formula (6) systematically overestimates the exact value of ν_c by a little bit. This systematic error is also apparent from Fig. 4. Due to the systematic error, the relative L-gap width \triangle_L^r is described by the formula (7) with a slightly larger relative error than is \triangle_L by the formula (3). There are now two main contributions to the errors, one around the maximum of \triangle_L and the other due to the systematic error. However, in the asymptotic region $\delta \gg \delta_m$ the first contribution disappears whereas the systematic error saturates (see Fig. 2). As a result, in the asymptotic region, the relative error $\tilde{\sigma}_r$ is still within $\approx 1\%$. Fig. 4 shows that even at $\delta = 100$ the error in \triangle_L^r is less than 2%.

For $\delta \in (1, 100]$, our formula (3) still describes Δ_L with a reasonable accuracy ranging from 4.1% to 8% (depending on the filling fraction) For a given filling fraction, the relative error $\tilde{\sigma}_r = \tilde{\sigma}/\overline{R}$ was determined by calculating the standard quadratic deviation $\tilde{\sigma}$ of the average value \overline{R} of the ratio $R = \Delta_L^{r;exact}/\Delta_L^{r;approx}$, where $\Delta_L^{r;exact}$ is the exact value of Δ_L^r calculated numerically and $\Delta_L^{r;approx}$ is its approximation calculated using Eq. (7). The values of \overline{R} , $\tilde{\sigma}$, and $\tilde{\sigma}_r$ are collected in Table II.

	f = 0.1	f = 0.2	f = 0.4	f = 0.6	f = 0.74
\overline{R}	1.004	1.012	1.025	1.030	1.031
$\tilde{\sigma}$	0.044	0.042	0.052	0.068	0.082
$\tilde{\sigma}_r$	4.37%	4.17%	5.05%	6.61%	7.95%

TABLE II. The average value \overline{R} , the standard quadratic deviation $\tilde{\sigma}$, and the relative error $\tilde{\sigma}_r$ for Δ_L^r approximated by Eq. (7) for different filling fractions and $\delta \in (1, 100]$.

One expects a deviations [of the order 5% from the behavior described by the formula (7)] only in a rare case when a Mie resonance crosses the edge of the L-gap [30].

III. DISCUSSION

Formulas (3) [together with (4)], (6), and (7) are the main results of this work. They fit nicely experimental data on Bragg's scattering in fcc photonic crystals of air spheres [15–17]. Note that Δ_L also characterizes the transmission of light through such a crystal (see [27] for microwaves). The fact that such simple relations can describe one of the photonic gaps has been completely unexpected. Indeed, the numerical calculation of photonic band structures is a great deal more involved than that in the case of scalar waves (including the case of electrons) where no analog of formulas (3) and (7) is known. Numerics has been the main tool to understand photonic gaps [3,4,18–20,24]. This is also the case of two recent discussions of Bragg's scattering in the (111) direction [32]. A previous attempt to understand Bragg's scattering in photonic crystals involved an introduction of a "photonic strength" parameter $\Psi = 3f \alpha$ [16]. It was shown that the dynamical diffraction theory [33], which is well known in x-ray diffraction, already fails to describe Bragg's scattering in a photonic crystal for $\Psi \approx 0.5$ [16].

Formulas (3) and (7) immediately raise questions whether one can understand and derive them analytically. The L-gap width for fcc structures is a natural measure to characterize their scattering strength, because, in contrast to the full band gap, $\Delta_L \neq 0$ for arbitrarily small f and δ . The latter suggests to take Δ_L^r given by Eq. (7) as a natural "photonic strength" parameter for the air spheres case. Neither the parameter Ψ [16], nor the parameter ter $\varepsilon_r = \left(\overline{\varepsilon^2} - \overline{\varepsilon}^2\right)^{1/2} / \overline{\varepsilon}$, introduced in [18], are directly related to a gap width. However, it turns out that formulas (3) and (7) cannot be applied to the case of dense spheres. The simple fcc lattices of air and dense spheres have for the same dielectric contrast rather different behavior with respect to the full photonic band gap [18–20] and to the first Bragg's peak [11,15–17]. Our numerical calculation shows that, for dense spheres, Δ_L^r does not increase monotonically with δ as in the case of air spheres. Instead Δ_L^r first reaches a local maximum, then it returns to zero and only afterwards starts to increase monotonically [31]. This behavior is reminiscent to that of the relative X-gap width \triangle_X^r (X is another special point of the Brillouin zone of an fcc lattice [26]) in the case of air spheres [3,27]. It has been argued that the vanishing of \triangle_X^r is due to the vanishing of the scattering form-factors [3,27]. Also, if \triangle_L^r is plotted against the filling fraction, one observes that the maximum of \triangle_L^r shifts to lower f for dense spheres and towards close-packing for air spheres [31]. It would be interesting to understand what causes this different behavior. The latter can be partially attributed

to the fact that, for a lattice of spheres, ε_b no longer describes the dielectric constant of the surrounding medium, which is instead described by the effective dielectric constant ε_{eff} . Therefore, the bare dielectric contrast δ is renormalized to $\delta_{eff} = \max(\varepsilon_s/\varepsilon_{eff}, \varepsilon_{eff}/\varepsilon_s)$, where $1 < \varepsilon_{eff} < \delta$ for $\varepsilon_s \neq \varepsilon_b$. Given the bare dielectric contrast δ , one finds that the renormalized dielectric contrast $\delta^d_{eff} = \varepsilon_s/\varepsilon_{eff}$ in the case of dense spheres is always smaller than the renormalized dielectric contrast $\delta^a_{eff} = \varepsilon_{eff}$ in the case of air spheres [20]. The latter is easy to verify in the limit when the bare dielectric contrast δ tends to infinity, where the Maxwell-Garnett equation (2) implies

$$\delta_{eff}^{d} \sim \delta (1 - f) / (1 + 2f) < \delta_{eff}^{a} \sim \delta (1 - f) / (1 + f/2).$$
(8)

Nevertheless, a full understanding of the differences between the lattices of air and dense spheres still remains a theoretical challenge.

IV. CONCLUSION

To conclude we have found that, despite of the complexity of the problem of propagation of electromagnetic waves in a periodic dielectric medium, the absolute and the relative width of the first Bragg's peak in the (111) direction for an fcc lattice of air spheres can be accurately described by the simple empirical formulas (3) and (7), respectively. Apparently, for sufficiently high $\delta \gg 1$, our formula (3) captures the asymptotic behaviour of Δ_L exactly. Indeed, the relative error σ_r steadily decreases as one investigates region $\delta \geq \delta_c$ for higher and higher δ_c . For all filling fractions σ_r falls well below 1% if sufficiently high δ is taken. For example for $\delta \geq 20$ one obtains $\sigma_r < 0.1\%$ for f = 0.2 and $\sigma_r < 0.3\%$ for f = 0.4. For $\delta \in (1, 100]$ formula (3) still describes Δ_L with a reasonable precision, namely, with the relative error ranging from 3.3% to 6.5% (depending on the filling fraction). The main contribution to the error is picked up around $\delta = \delta_m(f)$ for which Δ_L takes on its maximum. At $\delta = \delta_m$, our formula (3) gives persistently a slightly lower value for Δ_L . The relative L-gap width \triangle_L^r is described by the formula (7) with a slightly larger relative error ranging from 4.1% to 8% (depending on the filling fraction). The reason is that there are now two main contributions to the error, that around the maximum of Δ_L and the second systematic error due to the overestimation of the L-midgap frequency ν_c when using Eq. (6). All the formulas only involve the effective dielectric constant of the medium ε_{eff} approximated by Maxwell-Garnett's formula (2), and volume averaged $\varepsilon(\mathbf{r})$ and $\varepsilon^2(\mathbf{r})$ over the lattice unit cell. Since $\overline{\varepsilon}$, $\overline{\varepsilon^2}$, and ε_{eff} have well-defined meaning for any lattice, this suggests that a similar gap behavior may occur for other lattices. It would be interesting to find out if the same is true for the width of the full photonic band gap [31].

I would like to thank A. van Blaaderen, A. Tip, and W. L. Vos for careful reading of the manuscript and useful comments, and other members of the photonic crystals interest group for discussion. This work is part of the research program by the Stichting voor Fundamenteel Onderzoek der Materie (Foundation for Fundamental Research on Matter) which was made possible by financial support from the Nederlandse Organisatie voor Wetenschappelijk Onderzoek (Netherlands Organization for Scientific Research). SARA computer facilities are also gratefully acknowledged.

REFERENCES

- V. P. Bykov, Sov. J. Quant. Electron. 4, 861 (1975); E. Yablonovitch, Phys. Rev. Lett. 58, 2059 (1987).
- [2] S. John, Phys. Rev. Lett. **58**, 2486 (1987).
- [3] K. M. Leung and Y. F. Liu, Phys. Rev. Lett. 65, 2646 (1990).
- [4] Z. Zhang and S. Satpathy, Phys. Rev. Lett. 65, 2650 (1990); K. M. Ho, C. T. Chan, and C. M. Soukoulis, ibid. 65, 3152 (1990).
- [5] E. Yablonovitch, T. J. Gmitter, and K. M. Leung, Phys. Rev. Lett. 67, 2295 (1991).
- [6] T. F. Krauss, R. M. De la Rue, and S. Brandt, Nature **383**, 699 (1996).
- [7] S. Y. Lin et al., Nature **394**, 251 (1998).
- [8] B. G. Levi, Phys. Today (January), 17 (1999).
- [9] P. Pieranski, Contemp. Physics 24, 25 (1983).
- [10] V. N. Bogomolov et al., Appl. Phys. A: Solids Surf. 63, 613 (1996).
- [11] I. I. Tarhan and G. H. Watson, Phys. Rev. Lett. **76**, 315 (1997).
- [12] R. Pradhan, J. A. Bloodgood, and G. J. Watson, Phys. Rev. B 55, 9503 (1997).
- [13] A. van Blaaderen, R. Ruel, and P. Wiltzius, Nature **385**, 321 (1997).
- [14] W. Luck, M. Klier, and H. Wesslau, Naturwissenschaften 50, 485 (1963).
- [15] V. N. Astratov et al., Nuovo Cimento D 17, 1349 (1995); Phys. Lett. A 222, 349 (1996);
 Yu. A. Vlasov, V. N. Astratov, O. Z. Karimov, and A. A. Kaplyanski, Phys. Rev. B 55, R13 357 (1997); D. Mei, H. Liu, B. Cheng, Z. Lin, D. Zhang, and P. Dong, ibid. 58, 35 (1998); H. Míguez, A. Blanco, F. Mesegeur, C. López, H. M. Yates, M. E. Pemble, V. Fornés, and A. Mifsud, ibid. 59, 1563 (1999).
- [16] W. L. Vos, R. Sprik, A. van Blaaderen, A. Imhof, A. Lagendijk, and G. H. Wegdam, Phys. Rev. B 53, 16 231 (1996); W. L. Vos, M. Megens, C. M. van Kats, and P. Bösecke, J. Phys.: Condens. Matter 8, 9503 (1996).
- [17] O. D. Velev, T. A. Jede, R. F. Lobo, and A. M. Lenhoff, Nature **389**, 447 (1997); A. Imhof and D. J. Pine, ibid. **389**, 948 (1997); B. T. Holland, C. F. Blanford, and A. Stein, Science **281**, 538 (1998); J. E. J. G. Wijnhoven and W. L. Vos, Science **281**, 802 (1998).
- [18] H. S. Sözüer, J. W. Haus, and R. Inguva, Phys. Rev. B 45, 13 962 (1992); T. Suzuki and P. K. Yu, J. Opt. Soc. B 12, 804 (1995).
- [19] R. Biswas, M. M. Sigalas, G. Subramania, and K. M. Ho, Phys. Rev. B 57, 3701 (1998).
- [20] A. Moroz and C. Sommers, J. Phys.: Condens. Matter 11, 997 (1999).
- [21] A. Moroz, Phys. Rev. B 51, 2068 (1995); A. Moroz, in *Confined Electrons and Photons : New Physics and Applications*, eds. E. Burstein and C. Weisbuch (Plenum Press, New York, 1995), p. 741. See also X. Wang, X.-G. Zhang, Q. Yu, and B. N. Harmon, Phys. Rev. B 47, 4161 (1993).
- [22] T. Yamasaki and T. Tsutsui, Appl. Phys. Lett. 72, 1957 (1998); M. Megens, J. E. G. J. Wijnhoven, A. Lagendijk and W. L. Vos, Light sources inside photonic crystals, to appear in Phys. Rev. A.
- [23] J. Martorell and N. M. Lawandy, in *Proceedings of the International Conference on Quantum Electronics*, 1990, Technical Digest Series Vol. 8 (Opt. Soc. of America, Washington, DC, 1990), pp. 176-177.
- [24] S. Datta, C. T. Chan, K. M. Ho, and C. M. Soukoulis, Phys. Rev. B 48, 14 936 (1993).

- [25] J. C. Maxwell Garnett, Phil. Trans. R. Soc. London 203, 385 (1904).
- [26] G. F. Koster, Space Groups and Their Representations, in Solid State Physics, Vol. 5, eds. F. Seitz and D. Turnbull (Academic Press, New York, 1957), p. 173.
- [27] E. Yablonovitch and T. J. Gmitter, Phys. Rev. Lett. 63, 1950 (1989).
- [28] J. Korringa, Physica 13, 392 (1947); W. Kohn and N. Rostoker, Phys. Rev. 94, 1111 (1954).
- [29] N. W. Ashcroft and N. D. Mermin, Solid State Physics (Saunders College, 1976), p. 73.
- [30] A. Moroz and A. Tip, J. Phys.: Condens. Matter **11**, 2503 (1999).
- [31] A. Moroz, in preparation.
- [32] T. Suzuki and P. K. Yu, J. Opt. Soc. B 12, 583 (1995); V. Yannopapas, N. Stefanou, and A. Modinos, J. Phys. C: Cond. Matt. 9, 10261 (1997).
- [33] W. H. Zachariasen, Theory of X-ray Diffraction (Willey, New York, 1945).

FIGURES



FIG. 1. The L-gap width in units $c/\pi A$, where c is the speed of light in vacuum and A is a length of the side of the conventional unit cell of the cubic lattice [25], for an fcc lattice of air spheres with f = 0.4 calculated exactly (the solid line) and approximated by the formula (3) with optimized C (the dashed line) and with C given by the formula (4) (the long-dashed line). The last two curves almost overlap.







FIG. 2. The L-midgap frequency ν_c for air spheres in the units $k_L/(2\pi n_{eff}^{MG})$, where k_L is the length of the Bloch vector at the L point and n_{eff}^{MG} is the effective refractive index of the medium calculated by Maxwell-Garnett's formula (2). The dot-dashed line is for the sphere filling fraction f = 0.1, the long-dashed line is for f = 0.2, the dashed line is for f = 0.4, finely dotted line is for f = 0.6, and the solid line corresponds to the close-packed case (f = 0.74).





FIG. 3. The relative L-gap width (the L-gap width divided by the midgap frequency) for an fcc lattice of air spheres shows a rather simple dependence on the refractive index contrast $n_b/n_s = \sqrt{\delta}$. The dot-dashed line is for the sphere filling fraction f = 0.1, the long-dashed line is for f = 0.2, the dashed line is for f = 0.4, finely dotted line is for f = 0.6, and the solid line corresponds to the close-packed case (f = 0.74).



FIG. 4. The relative L-gap width \triangle_L^r for the close-packed fcc lattice of air spheres (solid line) and its approximation using the formula (7) with optimized \overline{R} (long-dashed line). Once \overline{R} is optimized, $\tilde{\sigma}_r$ can be reduced to $\approx 1\%$. Even at $\delta = 100$, the error in \triangle_L^r is less than 2%.