

NMR evidence for an inhomogeneous transition between the ferromagnetic and antiferromagnetic ground states in $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$ manganites

M.S. Reis* and V.S. Amaral

Departamento de Física and CICECO, Universidade de Aveiro, 3810-193 Aveiro, Portugal

P.B. Tavares

Departamento de Química, Universidade de Trás-os-Montes e Alto Douro, 5001-911 Vila Real, Portugal

A.M. Gomes, A.Y. Takeuchi, A.P. Guimarães and I.S. Oliveira

Centro Brasileiro de Pesquisas Físicas, Rua Dr. Xavier Sigaud 150 Urca, 22290-180 Rio de Janeiro-RJ, Brasil

P. Panissod

*Institut de Physique et Chimie des Matériaux de Strasbourg,
UMR 75040 du CNRS, 23 rue du Loess, 67037 Strasbourg, France*

(Dated: November 16, 2018)

The low temperature behavior of $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$ manganites are known to undergo a transition at $x \sim 0.3$, from an insulating ferromagnetic state, at low Ca concentration, to an insulating antiferromagnetic state. Above the onset concentration for the charge-ordering effect ($x \sim 0.3$), a metal-insulator transition induced by an external magnetic field is also observed and related to the collapse of the charge-ordered state. In this paper we show that the ferro-antiferromagnetic transition takes place in an inhomogeneous way: around the critical concentration the sample is a mixture of ferromagnetic and antiferromagnetic regions. The zero-field NMR measurements show that a fraction of the ferromagnetic regions is in a fast hopping regime, which suggests that a small fraction of the sample could be metallic, even in zero field. This fraction of fast hopping regions is maximal at $x = 0.3$, which is also the concentration for which the insulator-metal transition has been observed in the smallest field.

PACS numbers:

I. INTRODUCTION

The mixed-valence manganites AMnO_3 , where A is a trivalent rare-earth mixed with a divalent alkaline-earth, were the subject of an enormous quantity of work [1], in connection with the peculiar magnetic and electrical properties observed in these systems. Due to the competition of several interactions (double exchange, superexchange, charge ordering, Jahn-Teller effect of Mn^{3+} , among others), a strong tendency to phase separation, with a large phase coexistence between the two phases, appears in these compounds.

In this direction, Allodi *et al.* investigated the $\text{La}_{1-x}\text{Ca}_x\text{MnO}_3$ [2], $(\text{LaMn})_{1-x/6}\text{O}_3$ [3], LaMnO_{3-x} [4] and $\text{Pr}_{0.5}\text{Sr}_{0.5}\text{MnO}_3$ [5] manganites, using the NMR technique. They stressed out a phase coexistence around the transition, from ferromagnetic to antiferromagnetic phase, induced by field, temperature or concentration. In addition, they observed a peculiar magnetic structure revealed by the NMR spectra, signaling an inhomogeneous spin arrangement, possibly due to a coexistence of ferromagnetic and antiferromagnetic clusters. Kapusta *et al.* [6], Kumagai *et al.* [7] and Dho *et al.* [8] enforced

the results reported by Allodi and co-workers.

Particularly interesting is the $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$ system, since its phase diagram exhibit a rich variety of magnetic and electronic structures. Following the complete phase diagram established by Martin *et al.* [9] (figure 1), a ferromagnetic-insulator phase arises for $x < 0.27$, with Curie temperature T_C and magnetic moment at 4 K around 100 K and $3.5 \mu_B/\text{mol Mn}$, respectively. For $0.34 < x < 0.85$, an antiferromagnetic-insulator phase arises for temperatures typically below 170 K, coexisting with a charge-ordering state with onset temperature T_{CO} between 200 K for $x = 0.35$ and 100 K for $x = 0.85$, and an associated metal-insulator transition induced by magnetic field [10, 11]. A significant loss of magnetic moment, comparatively to $x < 0.27$, is observed for this concentration range and this quantity at 4 K reaches $0.01 \mu_B/\text{mol Mn}$. Finally, for $0.27 < x < 0.35$ a remarkable phase competition between the antiferromagnetic-insulator charge ordered state and ferromagnetic-insulator state arises. Note that all values mentioned above are slightly dependent on the sample preparation procedure.

Additionally, we can consider the magnetic and electrical effects due to $\text{Ca}^{2+}\text{-Pr}^{3+}$ substitution as a pure valence effect [12], since the A site ionic radius is kept constant through the series, i.e., Pr^{3+} and Ca^{2+} ionic radii are rather similar: 1.179 \AA for Pr^{3+} and 1.180 \AA for Ca^{2+} [13]. However, in this series, even with the A size constant, the volume cell decreases as the ratio

*Present address: Centro Brasileiro de Pesquisas Físicas, Rua Dr. Xavier Sigaud 150 Urca, 22290-180 Rio de Janeiro-RJ, Brasil; Electronic address: marior@fis.ua.pt

$\text{Mn}^{3+}/\text{Mn}^{4+}$ decreases (increasing x), in agreement with the relation $r_{\text{Mn}^{4+}} < r_{\text{Mn}^{3+}}$ [12].

In the present work we aim to explore the nature of the magnetic ground state through the concentration range of phase competition, between the antiferromagnetic-insulator charge ordered state and the ferromagnetic-insulator state, using, for that, the zero-field NMR technique.

II. EXPERIMENTAL DETAILS

The samples were prepared by the ceramic route, starting from the stoichiometric amount of Pr_2O_3 (99.9 %), CaCO_3 (>99 %) and MnO_2 (>99 %), and heated in air, with five intermediate crushing/pressing steps. The final crushed powders were compressed in cylindrical rods, which were sintered in air at 1350 °C during 45 hours, with a subsequent fast freezing of the samples. X-ray diffraction patterns confirmed that the samples are a single orthorhombic phase, with the space group $Pbnm$. The NMR experiments have been performed on ^{55}Mn using a broad band frequency scanning spectrometer with phase sensitive detection. Spin echo intensity has been recorded every 1 MHz in the frequency range 170-530 MHz. The spectra were recorded at several values of the radio-frequency (RF) excitation field. This procedure allows to measure the NMR enhancement factor associated with the transverse susceptibility of the electronic magnetization and to correct the signal amplitude for this enhancement factor.

III. RESULTS AND DISCUSSION

Figure 2 displays the spectra observed at 1.4 K for the Ca concentrations $x = 0.20, 0.25, 0.30$ and 0.32 . Except for $x = 0.20$, the observed signal is rather low and the integral intensity (figure 3) decreases by a factor 30 between $x = 0.20$ and $x = 0.32$. This means that, in the latter samples, either the NMR enhancement factor, arising from the transverse magnetic susceptibility, is small - as in an antiferromagnet -, or that only a part of the sample is observed. Actually, the enhancement factor measured on the spectra is in the range 50 to 100, which shows that the signal arises from ferromagnetic domains. Thus, no signal from antiferromagnetic regions could be observed at the maximum available RF power.

In previous works [14, 15] the existence of a small residual ferromagnetic component above $x = 0.3$ has been assigned to a possibility of a small canting of the moments in the antiferromagnetic state. In such a case, all the Mn nuclei would have been observed and the decrease of the NMR signal would have been due to the decrease of the enhancement factor associated with the decrease of the effective ferromagnetic moment. The present measurements show that the enhancement factor does not decrease. It even increases from 50 to 100 between $x = 0.20$

and $x = 0.32$. Therefore, we can unambiguously conclude that the samples always contains some ferromagnetic parts and that the small residual moment in the antiferromagnetic state is due to the inhomogeneous character of the ferro-antiferromagnetic transition.

Assuming that the whole sample is ferromagnetic for $x = 0.20$, the measured intensity for $x = 0.32$ shows that a volume fraction of about 3% of the sample is still ferromagnetic, in agreement with the residual ferromagnetic component measured on standard magnetization curves. A detailed analysis of the magnetic and thermal properties of this $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$ manganites is discussed elsewhere [16].

Whether the magnetic inhomogeneity of the samples is intrinsic or extrinsic is a matter of discussion. Indeed, it can be speculated that the residual ferromagnetic fraction in the antiferromagnetic phase arises from the presence of defects and/or impurities, but, concentration dependence? However, the intrinsic fluctuations of composition in a random alloy can also explain the observation as shown below.

Let us assume that d_m is the minimum diameter for a statistical cluster to show ferromagnetic or antiferromagnetic order. In other words, d_m is a typical coherence length for the magnetic order. Be n the number of formula units within a sphere of diameter d_m , and, on average, such spheres contain $m = nx$ Ca atoms. Let us now assume that x_c is the critical local concentration, above (below) which the sphere shows an antiferromagnetic (ferromagnetic) coherence. Correspondingly, $m_c = nx_c$ is the critical number of Ca atoms within the sphere above (below) which the sphere is antiferromagnetic (ferromagnetic).

However, there are statistical concentration fluctuations between the spheres. For a sample with nominal concentration x , the probability $P_{x,n}(k)$ to find k Ca atoms inside a sphere of diameter d_m , is given by the binomial law:

$$P_{x,n}(k) = \frac{n!}{k!(n-k)!} x^k (1-x)^{n-k} \quad (1)$$

and the probability $P_f(x)$ to find a ferromagnetic sphere is:

$$P_f(x) = \sum_{k=0}^{m_c} P_{x,n}(k) \quad (2)$$

Considering that n is most probably large, a continuous approximation for the binomial probability can be safely used in the form of the normal distribution:

$$P_{x,n}(y) = \frac{1}{\sqrt{2\pi[x(1-x)]/n}} \exp\left(-\frac{(y-x)^2}{2[x(1-x)]/n}\right) \quad (3)$$

where $y = k/n$ is the local concentration within the sphere. The average value $\langle y \rangle = x$ and variance $\sigma^2 =$

$x(1-x)/n$ of the normal distribution takes the same values as those of the binomial law.

Then, the fraction of ferromagnetic phase in a sample with nominal Ca concentration x is :

$$F_f(x) = \int_0^{x_c} P_{x,n}(y) dy \quad (4)$$

$$F_f(x) = \frac{1}{2} \left\{ \operatorname{erf} \left[\sqrt{\frac{n}{2x(1-x)}} (x_c - x) \right] + \operatorname{erf} \left[\sqrt{\frac{n}{2x(1-x)}} x \right] \right\} \quad (5)$$

where *erf* is the *error function*, with x_c and n acting as free parameters. This function $F_f(x)$ is centered on x_c , with a width $\sqrt{x_c(1-x_c)/n}$. Although we have not enough data points to make an accurate fit, we can estimate that the minimum number of formula units contained in ferromagnetic clusters is of the order of $n=150$. Additionally, the critical local concentration $x_c = 0.24$ above (below) which an antiferromagnetic (ferromagnetic) order is established, was also found. Figure 3 presents the normalized spectra integral intensity, considering that $x=0.20$ is fully ferromagnetic. The solid line is calculated from Eq.5.

As to the spectral shapes, they are nearly identical at both ends of the studied concentration range ($x=0.20$ and $x=0.32$). They show a narrow line at 320 MHz and a broad structured hump in the 370-440 MHz range. As the samples are insulators, one indeed expects two lines arising from the ^{55}Mn nuclei: a line from the Mn^{4+} sites around 300 MHz, and a line from the Mn^{3+} sites around 400 MHz. The broadening of the upper frequency line is understood as arising from the Jahn-Teller distortion around the Mn^{3+} sites, which induces magnetic and electric anisotropies. However, the observed intensity ratio of the two lines is not that expected from the charge balance: an intensity ratio of $x/(1-x)$ is expected between lower (Mn^{4+}) and upper (Mn^{3+}) frequency lines, whereas the observed intensities are about equal. The reason for the discrepancy has to be found in the existence of a ^{141}Pr line around 320 MHz. Indeed, the ^{141}Pr resonance has been identified in this low frequency range in a previous study of the $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$ system [15]. Then, the expected ratio between the lower (Pr^{3+} and Mn^{4+}) and upper (Mn^{3+}) frequency lines is $1/(1-x)$, in much better agreement with the observation. Figure 4 shows a fit of the spectrum observed for $x=0.20$, using two gaussian lines for Pr and Mn^{4+} around 320 MHz, and a quadrupolar split spectrum including magnetic anisotropy for Mn^{3+} , centered at 400 MHz. The relative integral intensities of the three lines are in the ratio 0.84/0.21/0.75, in rather fair agreement with the $(1-x)/x/(1-x)$ ratio expected from the charge balance.

As mentioned above, the spectrum observed for $x=0.32$ is nearly identical to the one observed for

$x=0.20$, even though its integral intensity is 30 times smaller. This means that the residual ferromagnetic regions have a Ca content close to 20 %. The slight change of shape of the Mn^{3+} line (380-420 MHz) can be explained, from the simulation we have made, by a rotation of 90° of the easy axis with respect to that in the totally ferromagnetic sample.

By contrast, the spectra for the intermediate compositions are significantly different, as they show a significant intensity peaking in the intermediate frequency range 360-380 MHz (see figure 2). ^{55}Mn NMR has been observed in this range in metallic manganites [17]. Indeed, in samples where the hopping rate is fast (faster than the NMR frequency), it averages the hyperfine field for the two ionic configurations, resulting in a single line at the center of gravity of the two ^{55}Mn lines observed in insulating samples. This mere observation shows that the two samples with $x=0.25$ and $x=0.30$ embed regions where the hopping rate is fast, even in zero field. The fast hopping signal is maximum for $x=0.30$, which is in agreement with the fact that this sample shows also the lowest field for the insulator-metal transition [10]. Whether the fast hopping regions are metallic or not is still an open question. Considering the intensity of the fast hopping line, which is at most 1/3 of the total intensity, one can deduce that it corresponds to a volume fraction of 5% for $x=0.30$. This would be too small a fraction to make the whole sample conducting.

IV. CONCLUSION

There are already a number of experimental evidences for the coexistence of two phases around the various transitions exhibited by the mixed-valency manganites systems (see Ref.[1] and references therein). The present study has shown that this is also the case for the transition between the insulating-ferromagnetic state and the insulating-antiferromagnetic state in $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$.

Although the extrinsic nature of the phase admixture cannot be excluded, we have shown that a statistical model that takes into account the concentration fluctuations in a random homogeneous alloy, can explain the observed results. The volume fraction of the ferromagnetic phase observed by NMR agrees with that calculated within the model provided here, where a ferromagnetic (antiferromagnetic) order establishes in a statistical cluster with a local Ca concentration smaller (larger) than $x=0.24$. The minimum coherent size of such clusters would correspond to about 150 unit cells.

In addition, we have evidenced, in a limited concentration range of fast hopping, possible metallic regions in a virgin samples and zero external magnetic field. The volume fraction of these "metallic" regions is, at most, 5 %. The maximum fraction is observed for $x=0.30$, which is also the concentration that requires the smaller external magnetic field to induce the insulator-metal transition.

V. ACKNOWLEDGEMENTS

The authors thanks FAPERJ and CAPES/Brasil and FCT/Portugal (contract POCTI/CTM/35462/99), for financial support, and P.P. the support of the CNPq/CNRS cooperation.

VI. FIGURE CAPTIONS

Figure 1 - Magnetic and electrical phase diagram for $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$. After Martin *et al.* [9].

Figure 2 - ^{55}Mn zero field NMR spectra in

$\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$ at 1.4 K, for $x = 0.20, 0.25, 0.30$ and 0.32 . This range of concentration cover the region of the phase diagram where ferro and antiferromagnetic order coexist.

Figure 3 - NMR integral intensity vs. concentration. The closed circles represent the ferromagnetic fraction of each sample obtained from the integral intensity of spectra, whereas the solid line represent our statistical model for concentration fluctuations in a random homogeneous alloy (Eq.5).

Figure 4 - Zero field NMR spectra at 1.4 K, for $x = 0.20$. The solid lines represent the Gaussian fit of each resonance peak.

-
- [1] E. Dagotto, T. Hotta, and A. Moreo, Phys. Rep. **344**, 1 (2001).
 - [2] G. Allodi, R. DeRenzi, F. Licci, and M. W. Pieper, Phys. Rev. Lett. **81**, 4736 (1998).
 - [3] G. Allodi, R. DeRenzi, and G. Guidi, Phys. Rev. B **57**, 1024 (1998).
 - [4] G. Allodi, R. DeRenzi, G. Guidi, F. Licci, and M. W. Pieper, Phys. Rev. B **56**, 6036 (1997).
 - [5] G. Allodi, R. DeRenzi, M. Solzi, K. Kamenev, G. Balakrishnan, and M. W. Pieper, Phys. Rev. B **61**, 5924 (2000).
 - [6] C. Kapusta, P. C. Riedi, M. Sikora, and M. R. Ibarra, Phys. Rev. Lett. **84**, 4216 (2000).
 - [7] K. Kumagai, A. Iwai, Y. Tomioka, H. Kuwahara, Y. Tokura, and A. Yakubovskii, Phys. Rev. B **59**, 97 (1999).
 - [8] J. Dho, I. Kim, and S. Lee, Phys. Rev. B **60**, 14545 (1999).
 - [9] C. Martin, A. Maignan, M. Hervieu, and B. Raveau, Phys. Rev. B **60**, 12191 (1999).
 - [10] Y. Tokura and Y. Tomioka, J. Magn. Magn. Mater. **200**, 1 (1999).
 - [11] Y. Tomioka, A. Asamitsu, H. Kuwahara, Y. Moritomo, and Y. Tokura, Phys. Rev. B **53**, R1689 (1996).
 - [12] A. Maignan, C. Martin, F. Damay, and B. Raveau, Z. Phys. B **104**, 21 (1997).
 - [13] R. D. Shannon, Acta Crystallogr. **A32**, 751 (1976).
 - [14] K. Hagdorn, D. Hohlwein, J. Ihringer, K. Knorr, W. Prandl, H. Ritte, H. Schmid, and T. Zeiske, Eur. Phys. J. B **11**, 243 (1999).
 - [15] M. M. Savosta, P. Novak, M. Marysko, Z. Jirak, J. Hejtmanek, J. Englich, J. Kohout, C. Martin, and B. Raveau, Phys. Rev. B **62**, 9532 (2000).
 - [16] M. S. Reis and A. M. Gomes and J. P. Araújo and V. S. Amaral and P. B. Tavares and A. Y. Takeuchi and I. S. Oliveira, **to be published**.
 - [17] J. P. Renard and A. Anane, Materials Science and Engineering **63**, 22 (1999).







